The Composition and Physicochemical Properties of Hyaluronic Acids Prepared from Ox Synovial Fluid and from a Case of Mesothelioma

By B. N. PRESTON, M. DAVIES AND A. G. OGSTON

Department of Physical Biochemistry, Australian National University, Canberra, A.C.T., Australia

(Received 31 July 1964)

1. Materials containing hyaluronic acid have been prepared by filtration (Ogston & Stanier, 1950) from ox synovial fluid and from a protein-rich human mesothelioma fluid. The ox material has been deproteinized by treatment with chloroform and pentanol and by gradient elution on DEAE-Sephadex; several fractions were obtained by the latter method. These materials can be stored in solution at -20° without change of properties. The ox material contained 21% of protein; all other preparations contained less than 6% of protein. 2. The two materials have been compared by sedimentation and viscosity and shown to be closely similar. Treatment of the ox material with neuraminidase caused no change in its viscosity behaviour. 3. Information about the molecular configuration of the ox material has been obtained from measurements of light-scattering and viscosity. The results, though consistent with a highly extended configuration, are not consistent with a linear random-coil configuration. It is tentatively suggested that the structure may have some degree of branching and of cross-linking, which give it a rigidity with respect to expansion of the molecular domain that would not be possessed by a random coil. 4. The deproteinized material recovered from DEAE-Sephadex, though polydisperse, showed unchanged average molecular weight; however, the average radius of gyration was greater than before this treatment. 5. Acidification to approx. pH 3 resulted in a contraction of the structure, with only a slight degree of expansion when the pH was restored to 6.8–7.0. 6. Measurements of optical rotatory dispersion qualitatively support a structure less simple than a linear random coil. 7. Colloid osmotic pressures of mixed solutions of bovine serum albumin and of hyaluronic acid prepared by filtration from ox synovial fluid have been measured. The results agree approximately with those of Laurent & Ogston (1963) but are in quantitative disagreement with the partition measurements of Ogston & Phelps (1960). The relationships between thermodynamic quantities in a quaternary system of electrolytes are discussed in Appendix 2. 8. Refractometric measurements have been made in connexion with light-scattering measurements, as the basis for a convenient method of determining the concentrations of solutions of hyaluronic acids, and to measure the partition of sodium chloride in dialysis experiments. The theory of the last use is discussed in Appendix 1. 9. Sedimentation measurements on the ox preparation have been made up to a concentration of 1.4×10^{-2} g./ml. The form of the sedimentation coefficient-concentration relationship is discussed. The value of the sedimentation coefficient at higher concentration is the basis of an illustration of the likely effect of hyaluronic acid on the flow of water through narrow channels in connective tissue. 10. Available colorimetric methods have been shown to give low estimates for glucuronic acid when applied to highly polymerized materials, as compared with estimates by decarboxylation. A spectrophotometric titration with cetylpyridinium bromide has been shown to give estimates of carboxyl groups that agree well with those of decarboxylation when applied to preparations of hyaluronic acid under suitable conditions; the results are not affected by the presence of protein. 11. Estimates of glucosamine (Ogston, 1964) have been found to be low compared with those of total acetyl, independently of the presence of protein. The magnitude of the discrepancy is characteristically different for preparations from ox synovial fluid

and from mesothelioma. 12. Sialic acid was estimated in several preparations. It is likely that this forms part of the protein. 13. Analyses of preparations for total nitrogen, amino acids, total acetyl, glucuronic acid (by decarboxylation) and ash account for at least 95.7% of the dry weight in terms of *N*-acetylglucosaminyl, glucuronyl, protein and metal ions. Previously published analyses of hyaluronic acids are reviewed. 14. The estimated molar ratios of glucuronic acid to glucosamine were all significantly greater than unity. 15. The analytical results are interpreted as agreeing with the physicochemical measurements in suggesting a more complex structure, for at least some hyaluronic acids, than that of an alternate linear copolymer in random-coil configuration.

The work described below is a continuation of a programme aimed to throw light on the properties and physiological significance of hyaluronic acid, which is widely distributed in connective tissues and forms an important part of the 'ground substance' (Meyer, 1960). The material has been studied *in vitro* rather than *in situ* since it is then possible to make precise physicochemical measurements and to relate these to controllable variables.

For the physiological interpretation of such measurements it is desirable to know the conditions under which the material is present *in vivo*. Unfortunately, there is no very precise information about this, but it seems likely (Yoffey & Courtice, 1956) that the ionic composition of connective tissue is close to that of blood or lymph, that the hyaluronic acid, though it may bind bi- and multi-valent ions strongly, does not bind univalent ions markedly (Ropes, Robertson, Rossmeisl, Peabody & Bauer, 1947; Aldrich, 1958), that the hyaluronic acid occurs as a highly viscous solution, with some gel-like properties, stabilized by collagen fibres (Ogston & Stanier, 1953a; Fessler, 1960), and that its concentration is about 10mg./ml. (Rienits, 1960; T. F. Sherman, personal communication).

The present paper describes measurements of refractive properties, osmotic pressures, light-scattering, viscosity, sedimentation and optical rotatory dispersion. The results provide evidence on the configuration of hyaluronic acid in solution and its interactions with other solutes. Analyses are also reported that give definitive information on the composition and indications of the configuration of the materials studied. Most of the measurements have been made on preparations from ox synovial fluid; analyses and some physicochemical measurements have also been made on hyaluronic acid prepared from a case of human mesothelioma.

EXPERIMENTAL

Materials

Preparation of hyaluronic acid from ox synovial fluid by filtration. This was done by the method of Ogston & Stanier (1950, 1952), with attention at all stages to the avoidance of bacterial contamination. The synovial fluid was centri-

fuged at approx. 0° for 60 min. at 29000 rev./min. (Spinco model L centrifuge, no. 30 rotor) immediately after collection; 12 cycles of filtration and re-solution were used: the final solution was centrifuged under the same conditions before storage at -20°. The yield by this method is 80-100% and the preparation of 400mg. of hyaluronic acid takes about 14 days; the method compares favourably with others with regard both to yield and time required. The hyaluronic acid dispersed completely within 24 hr. after thawing from -20°; freezing at this temperature and storage for up to a year caused no detectable change in its properties (see below). The material prepared in this way contained, in accordance with previous experience, about 20% of protein, which was not removed by more extensive filtration and which did not sediment with a separate boundary in the ultracentrifuge. To avoid prejudice as to the status of this protein, we return to the original description of UFR* (Ogston & Stanier, 1950) rather than describe it as 'hyaluronic acid-protein complex'. Different preparations are identified by series numbers, e.g. B.42.

Preparation of hyaluronic acid from a case of human mesothelioma. The source was fluid secreted into the peritoneal cavity of a patient suffering from mesothelioma of the bowel. This sample was given to us by Dr J. E. Scott, who with Dr D. E. Lowther identified the hexosamine and uronic acid in the major polymeric material as D-glucosamine and D-glucuronic acid (personal communication). The fluid was diluted fivefold with 0.2M-NaCl and the hyaluronic acid was isolated by filtration. In spite of the presence of approx. 5g. of protein/100 ml. of original fluid, the product contained only very little protein. Preparations are identified as M.30 etc.

Deproteinization of UFR by the Sevag method. This followed exactly the description given by Blix & Snellman (1945). UFR preparation B.35,36 yielded deproteinized preparation B.39.

Hyaluronic acid from ox vitreous humour. This was prepared by removal of protein with sodium dodecyl sulphate, by the method of Kay, Simmons & Dounce (1952).

Removal of protein from UFR with DEAE-Sephadex. DEAE-Sephadex A-50 (medium grade) was cycled in the Cl⁻ form and finally equilibrated with buffer (0.1M-NaCl-10mM-phosphate, pH 6.9). The column (23cm. x 5cm., containing 50-60g. of DEAE-Sephadex) was fitted with sintered-glass disks at each end. UFR (approx. 100mg. in 100ml.) dialysed against the same buffer was added to the column and eluted with a variable gradient (Peterson & Sober, 1959) of NaCl (0.1-0.4M) in the phosphate buffer at approx. 35ml./hr. The protein was removed by the time

* Abbreviation: UFR, ultrafilter residue.

the NaCl concentration had reached 0.35M, the hyaluronic acid being entirely retained. The column was then inverted and three fractions were recovered: the first by elution with 0.4 M-NaCl buffer; the second by discontinuing elution for 12 hr. and then collecting eluate till no more hyaluronic acid could be detected in it; the third by increasing the pH of the eluent to 9.6 (10 mM-phosphate buffer). Hyaluronic acid was detected in the eluate by use of a capillary viscometer (water time 130 sec.); this method could detect 5 μ g./ml. Separation into fractions was not strictly reproducible. Recoveries of protein from the column were 90% or better and of hyaluronic acid about 80%. Both materials were concentrated by pressure dialysis of the eluates. No separation was achieved with columns of neutral Sephadex (G-50 or G-200) or if the DEAE-Sephadex column was first equilibrated with 0.4 M-NaCl.

Water. The water used in all procedures was twice distilled in an all-glass still.

Reagents. The reagents used were of analytical quality, unless otherwise specified.

Cetylpyridinium bromide. This was Fluka A.G. (Buchs, Switzerland) 'purum' grade recrystallized from dioxan-acetone (Hauser & Niles, 1941). Its equivalence was estimated by electrometric titration of bromide (Clark, 1926). Its molar extinction at 259 m μ was 4050 ± 50 .

Buffers. For most physicochemical measurements the buffer used was 0.12 M-NaHCO₃ in equilibrium with laboratory air. Repeated tests showed that this controlled the pH within the range 6.8–7.0 [Leeds and Northrup (Philadelphia, Pa., U.S.A.) pH-meter and glass electrode, calibrated with 50 mM-potassium hydrogen phthalate buffer, pH 4.0].

Analytical methods

Determination of concentrations of solutions. Several methods were used.

(i) The ultimate method was the determination of the dry weights of solutions dialysed against water or 0.12 M-NaHCO₃. Samples (2–5 g. containing 3–5 mg.) were evaporated at 95° and then dried to constant weight at 105°.

(ii) The concentrations of solution dialysed against water or 0.12 M-NaHCO₃ could be determined refractometrically, against the corresponding solvent, once the determination of the relevant specific refractive increments had been made.

(iii) Where solutions in water or 0.12 M-NaHCO₃ of known initial concentration were dialysed to equilibrium with NaCl solutions, the change of concentration during dialysis was obtained from the change of weight of the dialysis sac and its contents, making allowance for the moist weight of the sac. By careful attention to the mopping of excess of fluid from the outside of the sac, the change of weight could be determined within ± 5 mg.; the error in concentration of the final solution (usually 2 g.) was thus $\pm 0.25\%$.

(iv) Dilutions of stock solutions were made by weight.

Determination of ash. Samples that had been dried to constant weight were ignited to bright red heat for approx. 2 min.

Glucosamine. This was estimated by the modification of the method of Elson & Morgan (1933) described by Ogston (1964), in which glucosamine is used as an internal standard. This procedure resulted (on this material) in estimates substantially higher than those obtained with the normal

method. Even so it appears that the estimation was incomplete (see below). All estimations were made in triplicate or quadruplicate.

Total acetyl. This was estimated by hydrolysis of approx. 1 mg. samples in 4 N-HCl for 5 hr. at 100° under N₂. Acetic acid was recovered by steam-distillation at pH 3.6 (0.5 M-citrate buffer) in a modified Markham (1942) still under carefully standardized conditions (with a stream of N₂ run through the apparatus) and titrated under N₂ with a Leeds and Northrup Coulometric Analyzer. Blank values were reproducible within the range 0.22–0.24 μ mole and duplicate estimations agreed within 0.02 μ mole. Recoveries of known amounts of acetic acid were correspondingly reproducible, between 88 and 92% according to the amounts estimated. Gas-liquid chromatography showed that all the volatile acid was acetic acid.

O-Acetyl. The method was the same as for total acetyl except that hydrolysis was performed in 2.5 N-H₂SO₄ for 44 hr. at room temperature (Marks & Neuberger, 1961).

Total nitrogen. Total nitrogen was determined either by the micro-Kjeldahl method of McKenzie & Wallace (1954) or by that of Jacobs (1962); the results of the two methods agreed closely.

Amino acids. These were estimated on hydrolysates of UFR in 6 N-HCl at 110° under N₂, the HCl being subsequently removed *in vacuo* over NaOH; the hydrolysates were redissolved and run on a Spinco amino acid analyser by Dr C. M. Mauritzen or Dr D. C. Shaw. Hydroxyproline was looked for independently by the method of Martin & Axelrod (1953) and was found to be absent. Amino acids were also estimated by Dr D. Shaw on a sample of the protein isolated from ox UFR on DEAE-Sephadex.

Sialic acid. To determine this satisfactorily it was necessary to concentrate the UFR. Freeze-dried preparation B.28 and about 10% of its weight of hyaluronidase (about 300 U.S.P. units/mg.; Nutritional Biochemicals Corp., Cleveland, Ohio, U.S.A.) were weighed accurately, and incubated with water at 37° for about 1 hr., to give a solution containing about 8 mg. of depolymerized hyaluronic acid/ml. A sample of preparation B.38 was concentrated by dialysis for about 16 hr. against a 10% solution in water of polyethylene glycol (Carbowax 6000; Carbide and Carbon Co., New York, N.Y., U.S.A.). The resultant jelly was dispersed to ensure uniformity by incubation with a little hyaluronidase, and the dry weight of the solution was determined.

The sialic acid contents of weighed amounts of these solutions were determined by a slight modification of the method of Aminoff (1961). To account for losses of sialic acid during the analysis an internal standard was used; two samples of each solution were required, to one of which was added a known amount of pure *N*-acetylneuraminic acid (a gift from Dr W. H. Murphy). Hydrolysis was then carried out in 0.1 N-HCl at 84°. Recoveries of sialic acid in the analyses, found by comparison of the internal standards with an external standard not treated with HCl, were close to those of Aminoff (1961) for sialic acid alone and did not vary with the amount of *N*-acetylneuraminic acid added. The results were corrected for the sialic acid liberated from hyaluronidase under the same conditions of hydrolysis. For 1 hr. of hydrolysis this was 0.36% (w/w) of the hyaluronidase. The time of hydrolysis was varied for preparation B.28, with the following results, expressed in m-equiv./g.: 1 hr., 0.054; 2 hr., 0.051; 4 hr., 0.049. Preparation B.38 was hydrolysed for 1 hr. It was found, by use of periodate at

Table 1. *Apparent contents of glucuronic acids estimated by colorimetric and decarboxylation methods and by combination with cetylpyridinium ion*

(a) Method of Dische (1947); (b) method of Bitter & Muir (1962); (c) method of Gregory (1960); (d) method of Moretti & Whitehouse (1963). Heparin was obtained as Pularin from Evans Medical Ltd., Speke, Liverpool; chondroitin sulphate was obtained from Mann Research Laboratories, New York, N.Y., U.S.A.; menthol glucuronide was obtained from Sigma Chemical Co., St Louis, Mo., U.S.A.; pectin was obtained from Fluka A.G., Buchs, Switzerland.

Material	Source	Glucuronyl content (%)				
		Carbazole			Decarboxylation	Cetylpyridinium titration
		(a)	(b)	(c)		
Ox UFR B.35	Ox synovial fluid	32.0	24.7	25.4	18.3	36.3
Ox UFR B.38	Ox synovial fluid	32.3	24.3	26.8	20.5	37.2
Ox UFR B.41	Ox synovial fluid	32.3	26.6	25.2	21.8	39.6
UFR M.43	Mesothelioma	40.1	34.5	36.3	29.1	46.5
Ox UFR S.16*	Ox synovial fluid	36.8	31.8	—	26.5	47.2
Hyaluronic acid	Bovine vitreous humour	46.3	46.2	—	—	45.4
Heparin (10 ⁵ units/ml.)		36.6	29.1	27.0	15.9	—
Chondroitin sulphate		26.5	26.6	27.2	19.3	21.4
Menthol glucuronide		47.7	47.2	48.5	49.7	33.4
Pectin		81.0	79.1	79.8	92.8	52.6†
					80.6	

* Deproteinized on DEAE-Sephadex.

† Theoretical value 53.0.

pH 7 (Aminoff, 1961), that there was no unbound sialic acid in preparation B.38.

Glucuronic acid. Considerable variations of the apparent glucuronic content of UFR were found in preliminary studies, according to the method used. The techniques tried were: the carbazole method of Dische (1947) and modifications of this by Gregory (1960) and Bitter & Muir (1962); the orcinol method as described by Moretti & Whitehouse (1963); the decarboxylation method as described by Ogston & Stanier (1951b) with slight modifications. For the last method the sample was weighed into a glass bulb and 8N-HCl added to give a final concentration of 3.3N. The bulb was sealed off during evacuation on a water pump and then heated in an electric oven at 115°. The absorbent for CO₂ was 0.01N-Ba(OH)₂ and the titration with 0.01N-HCl was carried out in a Perspex cabinet, pressurized with CO₂-free air. With the present apparatus a low result was obtained if the diffusion period of 1 hr. recommended by Ogston & Stanier (1951b) was employed, diffusion for 10 hr. being required for 100% yield of CO₂. Results are given in Table 1.

Estimation of uronic acid in hyaluronic acid by precipitation with cetylpyridinium ion. Aldrich (1958) used this method, suggested by Scott (1960), to estimate the anionic equivalence of UFR. His value of 3.2 m-equiv./g. seemed too high and we have reinvestigated this method. Weighed amounts (0.05–0.6 g.) of UFR solution (approx. 1 mg./ml.) were added to 2 ml. portions of 0.7 mM-cetylpyridinium bromide. After separation of the clot formed on gentle mixing, by centrifuging, the extinction of the supernatant was measured at 259 mμ. The linear plot of extinction against weight of sample was extrapolated to zero extinction to give the equivalence. The observed equivalence was independent of salt concentration between 5 mM and 10 mM-Na₂SO₄. It was increased by further increase of the concen-

Table 2. *Correction of apparent cetylpyridinium equivalences measured in the presence of sodium chloride to the values in the absence of sodium chloride*

Q, Observed equivalence in the presence of NaCl; *Q*₀, equivalence corrected to values in the absence of NaCl.

Ox UFR preparation	Concn. of NaCl (mM)	<i>Q</i> (m-equiv./g.)	<i>Q</i> ₀ (m-equiv./g.)
B.29	66	3.68	2.04
B.32	50	3.32	2.02
B.32	70	4.23	2.13
B.32	75	4.28	2.19
B.33	40	3.23	2.10
B.34	40	3.23	2.10

tration of Na₂SO₄. It was also increased linearly with concentration of NaCl added to 5 mM-Na₂SO₄ up to 60 mM-NaCl according to:

$$Q = Q_0 + 28.2[\text{NaCl}] \quad (1)$$

where *Q* is the apparent equivalence in the presence of NaCl, *Q*₀ is the equivalence in 5 mM-Na₂SO₄ and [NaCl] is the concentration of NaCl at the equivalence point. Correction can thus be made for the effect of NaCl in the hyaluronic acid solution (Table 2). In 0.1 M-NaCl no precipitate was formed. In routine estimations, the Na₂SO₄ concentration was 5 mM. The results are given in Table 1.

Physical methods

Refractometry. A differential refractometer similar to that described by Cecil & Ogston (1951) was used. Its range was

Table 3. *Refractometer constant, from data of Kruis (1936) and eqn. (2)*

Concn. $10^3 \times$ of NaCl (m)	Refractive increment 25° (Kruis)	D (eqn. 2)	$10^7 \times$ Refractometer constant
0-01610	0-1682	333	5-051
0-01774	0-1834	367	4-997
0-05774	0-5990	1187	5-046
0-09627	0-9936	1972	5-039
0-11805	1-2150	2412	5-037
0-19350	1-9779	3927	5-037
Least-square best value			5-038

Table 4. *Observed refractive differences for sodium chloride in water at 25° compared with those calculated from eqn. (2)*

Units are in μ of refractometer reading. $D_{\text{obs.}}$, Observed refractive difference for NaCl in water; $D_{\text{calc.}}$, refractive difference calculated from eqn. (2)

Concn. of NaCl (m)	$D_{\text{calc.}}$	$D_{\text{obs.}}$	Difference
0-01699	351	352	+1
0-03427	707	711	+4
0-06990	1436	1438	+2
0-06990	1436	1435	-1
0-10220	2092	2093	+1
0-14977	3051	3052	+1
0-21552	4366	4365	-1
0-28638	5772	5771	-1
0-28638	5772	5773	+1
0-35092	7046	7042	-4
0-35092	7046	7042	-4
0-39766	7967	7966	-1
0-39766	7967	7969	+2
0-39766	7967	7969	+2

s.d. of difference = 2.3.

up to 5×10^{-3} of refractive index and its precision 10^{-6} . It was calibrated with solutions of NaCl in water. Measurements were corrected to 25° and compared with the data of Kruis (1936). The refractometer constant was 5.038×10^{-7} units of refractive difference/ μ (Table 3). All the results (Table 4) fitted the relationship:

$$D_{\text{NaCl}} = 2.07043 \times 10^4 m - 2.523 \times 10^3 m^2 + 2.103 \times 10^3 m^3 \quad (2)$$

where D_{NaCl} is the refractometer reading in μ and m is the molality of NaCl.

Osmotic pressure. The colloid osmotic pressures of systems containing hyaluronic acid are of interest in the biological context since these may play a part in determining the partition of fluid between intracellular, intravascular and interstitial compartments of the body. Ogston (1962) made predictions, based on the partition measurements of Ogston & Phelps (1960), of the non-ideal osmotic behaviour

of mixtures of hyaluronic acid and protein. Laurent & Ogston (1963) have shown, since the present work was undertaken, that these predictions are qualitatively fulfilled. The main object of the present measurements was to provide a further test of these thermodynamic properties.

The osmometer used was specially constructed to allow small osmotic pressures to be measured with accuracy, and to avoid the following errors:

(i) Apparent osmotic pressure when no osmotically active substance is present ('membrane asymmetry'), which is due to very slight leaking in the system.

(ii) Changes of concentration near the membrane due to the passage of solvent in the setting-up of osmotic equilibrium. This instrument is described in detail by Davies (1965). It is essentially a refinement of the osmometer of Rowe & Abrams (1957) with a Statham stretched-wire transducer used as the detector of volume change. Close attention was paid in the design and construction of the osmometer to perfect sealing at all points and to control of temperature. The pressures could be read to 0.01 cm. H₂O and unbalance detected with this sensitivity.

Solutions were made up by weight from solutions of ox UFR and of Armour Pharmaceutical Co. Ltd. (Eastbourne, Sussex) bovine serum albumin and buffer; each solution had been thoroughly dialysed against 0.2M-NaCl-0.12M-NaHCO₃ and was of known final concentration. The two solutions and buffer were mixed so as to provide sets in which the hyaluronic acid concentration varied at constant concentration of serum albumin and vice versa. Each mixture was stirred before use by placing a glass bead in the containing vessel, and rotating the latter slowly at 2° for 2-3 hr. They were used within 2 days of being made up.

The surface tension of each solution was measured after removal from the osmometer by the drop method of Harkins (1960). Instead of weighing the drops, the drop volume was determined by delivery from a micrometer syringe through a needle whose end was ground square and bevelled on the inside to give a sharp edge of 0.332 cm. diam. The value measured for water was within 1% of the accepted value. Measured osmotic pressures were corrected for surface tension in the osmometer.

The membranes were collodion, of water permeabilities 150×10^{-5} - 250×10^{-5} ml. hr.⁻¹ cm.⁻² (cm. H₂O)⁻¹.

Light-scattering. This was measured in a Brice-Phoenix (Phoenix Precision Instrument Co., Philadelphia, Pa., U.S.A.) photometer at a series of angles between 25° and 135° or in a Sofica (Le Mesnil Saint Denis, Seine-et-Oise, France) photometer between 30° and 150° with unpolarized light of wavelength 436 or 546 m μ . Stock solutions were thoroughly dialysed against solvent and clarified by centrifuging for 30 min. at 30 000 rev./min. (Spinco model L centrifuge, no. 30 rotor). Solvent was clarified by filtration through grade VF Millipore membrane (pore diam. 10 m μ). Dilutions were made in the photometer cells, in a dust-free cabinet. The results were plotted by the method of Zimm (1948); the mean molecular weight was obtained from the intercept at zero angle and zero concentration; the radius of gyration, ρ_g , was obtained from this intercept and from the slope of the extrapolated line at zero concentration; the second virial coefficient was obtained from the slope of the extrapolated line at zero angle.

Viscosity. Viscosities were measured at 25° , either in a capillary viscometer (BS/U type B, water time 80 sec.) or in a Couette viscometer similar to that of Ogston & Stanier

(1953b). The sensitivity and accuracy of the latter were considerably increased by the following modifications: (i) drive from a motor generator controlled by a Servomex control unit through a 1:10 belt reduction; (ii) use of 43s.w.g. beryllium-copper suspension wire; (iii) use of a graduated torsion head at the upper end of the suspension, so that only fractions of a degree deflexion were read optically. Deflexions could be read to $\pm 0.03^\circ$ and the sensitivity, with water, was $0.16^\circ/\text{unit velocity gradient}$. Measurements were normally made at ten values of velocity gradient between 0.5 and 50sec.^{-1} .

Reduced viscosities of UFR solutions were calculated by comparison with the flow times (in the capillary viscometer) or the deflexions (in the Couette viscometer) obtained with solutions identical except for the absence of UFR.

Sedimentation. This was observed in a Spinco model E ultracentrifuge at 59780rev./min. at 20° in cells with 3mm. or 12mm. aluminium centre-pieces. Schlieren optics were used.

Optical rotatory dispersion. Measurements were made in a Perkin-Elmer model 141 polarimeter at wavelengths 578, 546, 436, 364 and $313\text{m}\mu$, in a 10cm. jacketed quartz cell at 25° .

RESULTS AND DISCUSSION

Refractometry

Specific refractive increment of hyaluronic acids in water and in 0.12mM-sodium hydrogen carbonate. The results of measurements on a number of preparations, given in Table 5, shows that the values were satisfactorily constant and independent of concentration. Values in 0.12M-sodium hydrogen carbonate (pH 6.8–7.0) were significantly higher than in water (approx. pH 6) presumably because of the lower degree of ionization at the lower pH. The value for the deproteinized sample, S.16, was, as would be expected, markedly lower than that for the protein-containing material. From the com-

position of the protein it would be expected that its specific refractive increment would be near to 0.18; the value expected for the material that contains 20% of protein would then be 0.152 (in 0.12mM-sodium hydrogen carbonate) in good agreement with the observed value. The result for preparation S.16 is a little lower than that reported by Blumberg, Ogston, Lowther & Rogers (1958) for protein-free bacterial hyaluronic acid (0.144).

Specific refractive increments in sodium chloride solutions. The refractive increments of solutions of UFR containing sodium chloride up to 0.35M and measured against water or 0.12mM-sodium hydrogen carbonate are the resultant of the contributions of both solutes (see Appendix 1). The contribution of sodium chloride may be regarded as its refractive increment at the same molality, calculated from eqn. (2); subtracting this value gives the contribution of UFR. Expressing the concentration of UFR as g./g. of solution, the results are satisfactorily represented by:

$$\text{in water } D_{\text{HA}}^{\text{sp}} = 293 \times 10^3 - 2.28 (\text{s.e. } 0.50) D_{\text{NaCl}} \quad (3)$$

in 0.12mM-sodium hydrogen carbonate

$$D_{\text{HA}}^{\text{sp}} = 300 \times 10^3 - 2.20 (\text{s.e. } 0.70) D_{\text{NaCl}} \quad (4)$$

where $D_{\text{HA}}^{\text{sp}}$ and D_{NaCl} are expressed in refractometer readings in μ (conversion into units of refractive index is performed by the use of the refractometer constant; see above).

Specific refractive increments in dialysed solutions. When solutions of UFR were dialysed to equilibrium against solutions of sodium chloride in 0.12mM-sodium hydrogen carbonate and measured against diffusate, the differences were consistently less than would be expected from eqn. (4), except at zero concentration of sodium chloride. In Table 6 the apparent specific refractive differences, $D_{\text{HA}}^{\text{sp}}(\text{app.})$, are compared with the values predicted from eqn. (4), $D_{\text{HA}}^{\text{sp}}(\text{calc.})$.

The values (omitting those for zero concentration of sodium chloride) are represented by:

$$D_{\text{HA}}^{\text{sp}}(\text{app.}) = 279 \times 10^3 - 2.30 (\text{s.e. } 0.64) D_{\text{NaCl}} \quad (5)$$

The constant terms in eqns. (4) and (5) differ significantly by -20 (s.e.m. 5.2), whereas the coefficients of D_{NaCl} do not. That these differences are not due to error in assessing the changes of concentration during dialysis is shown by the agreement of apparent and predicted values at zero concentration of sodium chloride (first two rows) of Table 6.

Partition of sodium chloride. The observed differences can be ascribed to an unequal partition of sodium chloride between the UFR solution and its diffusate (see Appendix 1). Such inequality might arise either from the steric exclusion of solute by UFR discussed by Ogston & Phelps (1960) or

Table 5. *Specific refractive increments of ox UFR in water and in 0.12mM-sodium hydrogen carbonate, corrected to 25°*

Ox UFR prepara- tion	Solvent	$10^3 \times \text{Concn.}$ of UFR (g./g. of solution)	Specific refractive increment (g./g.)
B.32	Water	0.67	0.146
B.33	Water	0.65	0.149
B.34	Water	0.56	0.149
B.35,36	Water	0.98	0.147
B.38	Water	0.80	0.147
B.41	Water	1.52	0.148
B.44	Water	1.98	0.148
B.41	0.12mM-NaHCO ₃	1.45	0.151
B.45	0.12mM-NaHCO ₃	1.76	0.151
B.46	0.12mM-NaHCO ₃	2.65	0.151
S.16*	0.12mM-NaHCO ₃	0.504	0.141

* Deproteinized on DEAE-Sephadex column.

Table 6. *Apparent specific refractive differences of ox UFR dialysed against sodium chloride (in 0.12mM-sodium hydrogen carbonate), and differences from the calculated values (eqns. 2 and 4)*

Specific refractive differences are expressed as μ of refractometer reading $\times$ g./g.

$10^3 \times$ Concn. of UFR (g./g. of solution)	Concn. of NaCl (m)	D_{NaCl}	$10^{-3} \times D_{\text{HA}}^{\text{app.}}$	$10^{-3} \times D_{\text{HA}}^{\text{calc.}}$	$10^{-3} \times$ Difference for UFR concn. (g./g. of solution)
1.660	0	0	299	300	-1*
1.626	0	0	304	300	+4*
1.459	0.00897	136	278	299	-21
1.459	0.00897	186	279	299	-20
1.969	0.00965	200	285	299	-14
1.957	0.02191	452	284	298	-14
1.943	0.03744	772	271	297	-26
1.641	0.05583	1148	271	297	-26
1.887	0.08044	1650	277	295	-18
1.632	0.11525	2356	276	294	-18
1.763	0.16743	3406	265	292	-27
1.622	0.19804	4018	270	290	-20
1.582	0.19804	4018	267	290	-23
1.745	0.22485	4552	270	289	-19
1.550	0.33233	6679	256	284	-28
1.754	0.35839	7193	273	283	-10

* Control experiments.

Table 7. *Osmotic pressures of mixed solutions of ox UFR and bovine serum albumin in 0.2M-sodium chloride-0.12mM-sodium hydrogen carbonate at 25°*

The concentration units for UFR are 0.709×10^{-3} g./g. of buffer, and those for serum albumin are 5.512×10^{-3} g./g. of buffer.

Concn. of serum albumin	Concn. of ox UFR	Osmotic pressure (cm.H ₂ O)						
		... 0	1	2	3	4	5	6
0		0	0.045	0.032	0.082	0.254	0.464	0.681
1		1.196	1.939	2.152	2.344	2.560	2.795	3.121
2		3.982	4.182	4.395	4.642	4.946	5.238	5.616
3		6.247	6.438	6.552	7.018	7.409	7.738	8.307
4		8.462	8.875	9.149	9.277	10.166	10.640	11.272
5		11.183	11.563	11.969	12.520	13.152	13.811	14.523
6		14.116	14.594	14.973	15.549	15.996	16.943	17.722

from a Gibbs-Donnan equilibrium (since UFR is a polyanion). The former effect would be expected to cause a difference proportional to the concentration of sodium chloride (though this might be distorted by any effect of varying sodium chloride concentration on the configuration of UFR); the latter should be almost independent of the concentration of sodium chloride over the range covered. The apparent constancy of differences shown in Table 6 might suggest that the Gibbs-Donnan equilibrium is the major effect; also, the sodium chloride concentration difference of 1 mM for a UFR concentration of 1 mg./g. of solution would in an ideal Gibbs-Donnan equilibrium correspond to an anionic

equivalence of 2m-equiv./g., which agrees rather well with the estimates of carboxyl (Tables 1 and 18). However, this conclusion would not be very safe in view of the likelihood of non-ideality of the Gibbs-Donnan equilibrium (see Overbeek, 1956; Aldrich, 1958) and the considerable statistical uncertainty that attaches to the constancy of the differences.

Whatever the cause of the unequal partition of sodium chloride, it will have an effect on the osmotic properties of solutions of UFR. This is discussed in Appendix 2.

Uses of refractometric measurements. Measurements of refractive differences provide an accurate

and convenient method for determining concentration once the necessary calibrations have been performed. Direct measurements of refractive differences between solutions and their diffusates provide values of (dn/dc) required for interpreting light-scattering measurements (Casassa & Eisenberg, 1960). Also, as shown here and in Appendix 1, they can be used to measure the partition of diffusible components between solutions and their diffusates.

Osmotic pressures

The results of the measurements of osmotic pressures corrected for surface tensions (Table 8) are given in Table 7. The values for solutions containing UFR showed a tendency to drift upwards during measurement, usually becoming stable after 20 min. The values at 20 min. have been accepted and are those quoted. The absence of drift with solutions of bovine serum albumin shows that this was not of instrumental origin.

Analysis of osmotic-pressure results. By following Ogston (1962) and treating the system as ternary (UFR = 3; protein = 2; solvent = 1) the osmotic pressure across a membrane permeable only to component 1 can be expressed by:

$$\frac{1000 v_1}{RTM_1} {}^{23}\pi_1 = m_2 + m_3 + \frac{c}{2}m_2^2 + \frac{d_1}{2}m_3^2 + \frac{2d_2}{3}m_3^3 + a_1m_2m_3 + a_2m_2m_3^2 + \dots \quad (6)$$

where m_2 and m_3 are molalities. This is equivalent to:

$$\frac{1000}{RT\rho} {}^{23}\pi_1 = A_1C_2 + A_2C_3 + A_3C_2^2 + A_4C_3^2 + A_5C_3^3 + A_6C_2C_3 + A_7C_2C_3^2 + \dots \quad (7)$$

where the concentrations are expressed as g. of solute/g. of solvent; ρ , the density of the solvent, is a close approximation to M_1/v_1 . Eqn. (7) is the more convenient form for computation; also, since the

terms of eqn. (6) contain the molecular weights M_2 and M_3 (of bovine serum albumin and UFR respectively), eqn. (7) and its A coefficients provide a better basis for comparing results obtained with different preparations of hyaluronic acid and serum albumin.

Although the experiments were designed to allow analysis at constant protein or constant hyaluronic acid concentration, it was realized later that it would be more efficient to analyse the whole set of results as a multivariate regression. This was done on an IBM computer; the programme was for a linear multivariate regression with constant term suppressed. Fitting was tried with the whole regression, with $A_5 = 0$, with $A_7 = 0$ and with both $A_5 = 0$ and $A_7 = 0$. The least residual variance was obtained with $A_7 = 0$; however, the fit with both $A_5 = 0$ and $A_7 = 0$ was hardly less good and is perhaps the better choice, for reasons given below. The estimates of the A coefficients and their s.e.m. values are given in the second column of Table 9. For comparison the values of the same coefficients obtained by Laurent & Ogston (1963) are given in the third column of Table 9. A number of features require comment:

(i) The value of A_1 given in Table 9, which was derived from the analysis as a whole, corresponds to a value of 7.94×10^4 for the molecular weight of bovine serum albumin, i.e. M_2 . Closely similar results were obtained from the data given in Table 7 for serum albumin alone, and also from two independent sets of measurements on solutions of the same batch of protein. Examination of this material by velocity sedimentation showed that it contained not less than 16% of material which sedimented

Table 8. *Surface tensions of solutions of ox UFR and bovine serum albumin*

The concentration units for UFR are 0.709×10^{-3} g./g. of buffer, and those for serum albumin are 5.512×10^{-3} g./g. of buffer.

Concn. of ox UFR ...	Surface tension (dynes/cm.)						
	0	1	2	3	4	5	6
Concn. of serum albumin							
0	73	52	58	60	61	56	59
1	54	—	—	—	—	—	—
3	51	—	—	53	—	—	52
6	52	52	—	—	52	—	54

Table 9. *Least-square estimates of coefficients in eqn. (7) for the osmotic pressures of mixed solutions of ox UFR and bovine serum albumin*

Co-efficient	Values from this work	Values from Laurent & Ogston (1963)	
		Original values	Recalculated values (see the text)
A_1	$1.26(\pm 0.015) \times 10^{-2}$	1.41×10^{-2}	1.41×10^{-2}
A_2	$1.19(\pm 2.69) \times 10^{-3*}$	2.42×10^{-2}	Not significant
A_3	$1.19(\pm 0.049) \times 10^{-1}$	0	0
A_4	$1.23(\pm 1.70)^*$	2.6	$3.6(\pm 0.73)$
A_5	$1.70(\pm 2.69) \times 10^{-3*}$	0	0
A_6	$0.81(\pm 0.029)$	0.34	1.13
A_7	0	1.3×10^{-2}	Not significant
Values assuming $A_5 = 0$			
A_2	$-1.93(\pm 6.9) \times 10^{-3*}$		
A_4	$1.94(\pm 0.61)$		

* Not significant.

faster than the main component; this was presumably dimer or a mixture of dimer and more highly aggregated material. Measurements made on another sample of bovine serum albumin (Sigma Chemical Co., St Louis, Mo., U.S.A.) gave a molecular weight of 7.32×10^4 ; this sample contained much less aggregated material.

(ii) The estimate of A_2 from our measurements does not differ significantly from zero; statistical examination of the results of Laurent & Ogston (1963) (their Figs. 1 and 2) shows that this is true also of their value of A_2 . This means that the estimated value of M_3 , the molecular weight of hyaluronic acid, does not differ significantly from infinity in either set of measurements.

(iii) Accordingly, to obtain from the A coefficients the corresponding quantities in eqn. (6), other estimates of M_3 must be used. On the basis of light-scattering measurements and supporting evidence (see below) we have used $M_3 = 14 \times 10^6$ for our material and $M_3 = 1.5 \times 10^6$ for the hyaluronic acid used by Laurent & Ogston (1963) (Laurent, Ryan & Pietruszkiewicz, 1960) to obtain the coefficients given in Table 10.

(iv) The significant value of A_3 indicates non-ideal behaviour of solutions containing only bovine serum albumin. This does not appear in Laurent & Ogston's (1963) results.

(v) Although a non-linear increase of osmotic pressure with concentration of UFR is obvious in Table 7 the estimates of A_4 and A_5 are individually not statistically significant. However, if A_5 is assumed to be zero, a significant estimate of A_4 is obtained (Table 9). It seems that the inclusion of the term in C_3^3 (eqn. 7) is not justified.

(vi) Statistical recalculation of Laurent & Ogston's (1963) results leads to a revised value for A_4 and shows that their value of a_2 (corresponding to A_7) does not differ significantly from zero. The

recalculated values are shown in the last column of Table 9 and are used to obtain the corresponding coefficients in Table 10.

Osmotic coefficients. Table 9 shows that there is fair agreement between the values of the A coefficients that we have obtained from our osmotic pressure measurements and those of Laurent & Ogston (1963) as recalculated.

A_4 represents the second virial coefficient of hyaluronic acid, expressed on a weight concentration basis, and corresponds to the molal coefficient d_1 (Table 10). Our value of A_4 (assuming $A_5 = 0$) is about half that obtained by Laurent & Ogston (1963) on a different preparation and in 0.5M- instead of 0.2M-sodium chloride. Both values are much less than that assumed by Ogston (1962) ($d_1 = 2.64 \times 10^9$, $M_3 = 10^7$, giving $A_4 = 13.2$). However, this assumed value was based on the assumption of zero energy of interaction ($\chi = 0$) in the Flory-Huggins theory (Flory, 1953). It also neglected effects of the components' being electrolytes, discussed in the Appendix 2.

A more interesting and serious discrepancy appears in the values of A_6 (corresponding with the molal coefficient a_1). This coefficient represents the thermodynamic interaction between hyaluronic acid and protein components, which is reflected also in the unequal partition of protein between hyaluronic acid solution and buffer (Ogston & Phelps, 1960). It is easy to show that, for a ternary system of non-electrolytes, the same value must be obtained from either measurement. We have not been able to prove this generally for a quaternary system of electrolytes, but it seems probable (see Appendix 2). In fact, there is fair agreement between our value of A_6 and the recalculated ($A_7 = 0$) value from the osmotic data of Laurent & Ogston (1963); and Laurent (1964) has recently obtained partition values that agree well with the latter value. However, Ogston & Phelps (1960), using a preparation of hyaluronic acid similar to ours (about tenfold more highly polymerized than that used in Laurent's work), obtained from partition measurements a value some sixfold greater ($a_1 = 5.8 \times 10^6$, $A_6 = 5.2$). These discrepancies do not seem at present to be explicable either on experimental or on theoretical grounds.

The lower values of A_4 (or d_1) and A_6 (or a_1) found here affect quantitatively, though not qualitatively, the conclusions of Ogston (1962) with regard to the behaviour of solutions of hyaluronic acid and protein. First, the predicted values for osmotic pressures across a membrane permeable to protein are lowered. Secondly, a solution of UFR and serum albumin would not be expected to separate into two phases below a protein concentration about 7g./100ml.; this is probably beyond the concentration reached in normal connective tissues. Thirdly,

Table 10. *Values of coefficients for the osmotic pressures of mixtures of α UFR and bovine serum albumin required for expression on a molal basis (eqn. 6)*

	Values from this work	Values from Laurent & Ogston (1963) (recalculated)
M_2	7.94×10^4	7.1×10^4
M_3	14.0×10^6 *	1.5×10^6 *
c	1.50×10^3	0
d_1	4.8×10^8	1.6×10^7
d_2	7.0×10^9	0
a_1	9.0×10^5	1.2×10^5
a_2	0	0
Value assuming $d_2 = 0$		
d_1	7.6×10^8	

* Value assumed (see the text).

the magnitude of the effect of protein on the dimensions of the hyaluronic acid molecule (assuming this to be a random coil) is diminished (Fig. 5).

The value of the second virial coefficient of ox UFR obtained from light-scattering agrees approximately with the value of A_4 from osmotic measurements. However, these two measurements are not exactly equivalent, yielding, as they do, different averages over any distribution of species present (Casassa, 1960). The agreement may therefore be fortuitous.

Light-scattering

Storage and freezing. Comparison of the molecular dimensions of a freshly prepared sample of UFR, after storage at 2° and at -20°, and with addition of antibiotics, is made in Table 11. None of these treatments caused significant changes.

Table 11. *Molecular weights and radii of gyration of ox UFR preparations determined by light-scattering*

Ox UFR preparation	Treatment	$10^{-6} \times \text{Mol. wt.}$	Radius of gyration (Å)
B.29	Stored at -20° for 10 months	12.5	2420
B.32	Freshly prepared	12.8	2380
B.32	Stored at 2° for 7 days	12.5	2550
B.32	Stored at -20° for 1 day	13.0	2580
B.33	Added penicillin + streptomycin (2 µg./ml.)	12.4	2600
B.34	Added chloromycetin (2 µg./ml.)	13.2	2450

Effect of pH. A solution of UFR initially at pH 6.8 in 0.2M-sodium chloride-0.12mM-sodium hydrogen carbonate was titrated with 0.1N-hydrochloric acid to pH 3.3. The Zimm plots under the two conditions are shown in Fig. 1. The molecular weight did not change, though the radius of gyration became much smaller (Table 12) and the second virial coefficient became close to zero. The variation of the reciprocal particle scattering factor, $P^{-1}(\theta)$, is shown in Fig. 2 to change from that characteristic of a stiffened polydisperse coil (Fig. 2a) to that more nearly resembling a rigid rod (Fig. 2b). The effect of increased polydispersity would be in the same direction, but the increase would have to be extreme to produce the observed effect and is made unlikely by the lack of change of the mean molecular weight. Ishihara (1964) has shown that the scattered intensities are a function of molecular weight. The deviations from the theoretical curves (which were calculated for monodisperse systems) are therefore not necessarily due entirely to deviations of shape. The dissymmetry Z (Fig. 3) varied markedly with UFR concentration at pH 6.8, but was constant at pH 3.3 over the range studied. In a separate experiment the values of the molecular weight and radius of gyration obtained from a solution at pH 3 in the absence of salt were similar to those obtained at pH 3.3 in 0.2M-sodium chloride. On readjusting the pH from 3.3 to 6.8 (in 0.2M-sodium chloride) and leaving the solution at this pH for 6 days at 2°, only a slight degree of reversal towards the original form occurred (Table 12 and Fig. 2c). Comparison of the values of $\rho_g/M^{1/2}$ (Table 12) also indicates that the molecule assumed a more compact form at pH 3.3, with only partial reversal on return to pH 6.8.

Effect of ionic strength. Table 12 shows that the effects of changing the concentration of sodium

Table 12. *Molecular parameters of UFR preparations as determined by light-scattering*

Ox UFR preparation	Concn. of NaCl (M)	pH	$10^{-6} \times \text{Mol. wt.}$	$10^8 \times \rho_g (\text{cm.})$	$10^9 \times \rho_g/M^{1/2}$	Second virial coefficient*
B.46	0.001	6.8	13.2	2230	6.4	4.4×10^{-1}
B.46	0.001	6.8	13.4	2140	5.8	2.6×10^{-1}
B.46	0.005	6.8	12.8	2190	6.1	6.0×10^{-1}
B.46	0.03	6.8	13.2	2530	7.0	1.2
B.46	0.2	6.8	12.8	2520	7.0	3.3
B.46	0.2	6.8	12.9	2360	6.6	2.0
B.46	—	3.0	12.7	1170	3.3	0
B.46	0.2	3.3	13.5	880	2.4	0
B.46	0.2	6.8	14.2	1460	3.9	0
		(after acid treatment)				
B.48	—	6.8	~50.0	4540	6.4	—
B.48	0.005	6.8	12.6	2350	6.6	6.2×10^{-1}
B.48	0.2	6.8	13.5	2600	7.1	3.9

* Concn. of UFR expressed in g./1000g. of solvent.

Fig. 1. Light-scattering Zimm plots for UFR in 0.2M-NaCl; ●, Experimental points at pH6.8; ○, experimental points at pH3.3; ×, points obtained by extrapolation.

chloride at pH6.8 between 0.2M and 1mM were remarkably small. The molecular weight of the UFR did not change; there was a slight tendency for the radius of gyration to decrease as the sodium

chloride concentration was lowered. When the material was dialysed against water, the molecular weight increased together with the radius of gyration, but without change of compactness as measured

Fig. 2. Reciprocal of the particle scattering factor of UFR in 0.2M-NaCl as a function of $\sin^2(\theta/2)$ (a) at pH 6.8, (b) at pH 3.3, (c) at pH 6.8 after titration down to pH 3.0. The theoretical plots for systems of polydisperse random coils (A) and monodisperse rods (B) are included.

Fig. 3. Variation of the dissymmetry, Z , with concentration for an ox UFR preparation in solutions of increasing NaCl concentration and differing pH. $\times$, 1mM-NaCl, pH 6.8; $\circ$, 5mM-NaCl, pH 6.8; $+$, 30mM-NaCl, pH 6.8; Δ , 0.2M-NaCl, pH 6.8; $\bullet$, 0.2M-NaCl, pH 3.3.

by $\rho_g/M^{\frac{1}{2}}$. There was a significant fall of the second virial coefficient with fall of sodium chloride concentration (Table 12). Fig. 3 shows that at all ionic strengths the dissymmetry decreased initially with concentration of UFR: similar behaviour has been observed with un-ionized polymers (Hyde & Taylor, 1963) and with polyelectrolytes at low ionic strength (Oth & Doty, 1952; Doty & Steiner, 1952). There was a tendency for the dissymmetry to decrease with increase of ionic strength.

Table 13. Molecular parameters of hyaluronic acid as determined by light-scattering after deproteinization on DEAE-Sephadex

Hyaluronic acid preparation	Concn. of NaCl (M)	$10^{-6} \times$ Mol. wt.	$10^8 \times \rho$ (cm.)	$10^9 \times \rho_g/M^{\frac{1}{2}}$
S.15 (fraction 1)	0.1	26.3	2320	4.5
S.15 (fraction 2)	0.2	6.3	3050	12.2
S.16 (unfractionated)	0.2	13.2	3800	10.5
S.17 (fraction 1)	0.2	28.0	4240	8.0
S.17 (fraction 2)	0.2	3.9	2300	11.7

Deproteinized hyaluronic acid (Table 13). Hyaluronic acid recovered from a DEAE-Sephadex column showed no change in the average molecular weight of the unfractionated material (preparation S.16). However, the value for the radius of gyration was greater than that of the original UFR. When the two fractions were examined separately striking differences between them and the original UFR were seen: fraction 1 had much greater molecular weight and radius of gyration than fraction 2, but also a smaller value of $\rho_g/M^{\frac{1}{2}}$; this, and the reciprocal particle scattering factor (Fig. 4), suggest that the material of lower molecular weight is more compact, stiffer and more 'rod-like' than the other.

Fig. 4. Reciprocal of the particle scattering factor of two fractions of UFR deproteinized on a DEAE-Sephadex column. (a) Sample S.17 (fraction 1); (b) sample S.17 (fraction 2) (see Table 13). The theoretical plots for systems of random coils (A) and monodisperse rods (B) are included.

Viscosity

Effect of protein on viscosity. Ogston (1962) calculated, on the basis of the partition experiments of Ogston & Phelps (1960) and the theory of Flory (1953) for the dimensions of a random coil, that the dimensions of the molecular domain of UFR should be sensitive to the presence of protein. Use of the values of the coefficients a and d obtained from our osmotic measurements, both lower than those used by Ogston (1962) (see above), still leads to the prediction of substantial effects. These should affect the reduced viscosity in the way predicted in Fig. 5. The measurements shown in Fig. 5 were made in the capillary viscometer at a concentration (8×10^{-5} g./ml.) where molecular domains should not overlap greatly. The results are inconsistent with the prediction, suggesting a configuration insensitive to the presence of protein.

Effect of salt and concentration on viscosity. For comparison with the results of light-scattering, measurements were made in the capillary viscometer over a wide range of salt concentration and over a range of UFR concentration between 1.8×10^{-5} and 40×10^{-5} g./ml. (at pH 6.8–7, in 0.12M-sodium hydrogen carbonate). The results are plotted in Fig. 6. It is clear that there is a marked effect of salt concentration on the reduced viscosity; on the other hand, there appears to be rather a small dependence of reduced viscosity on the concentration of UFR, significant deviations occurring from linearity of η_{red} against concentration, particularly

Fig. 5. Reduced viscosities of UFR measured in a capillary viscometer in the presence of protein. Experimental values: ●, UFR 19.3×10^{-5} – 22.4×10^{-5} g./ml.; ○, UFR 8.2×10^{-5} – 9.1×10^{-5} g./ml. Curves A and B: expected variation calculated from the theory of Flory by using coefficients assumed by Ogston (1962) (A) and coefficients derived from the osmotic measurements in the present work (see the text) (B).

Fig. 6. Reduced viscosities of UFR solutions measured in a capillary viscometer at various concentrations of NaCl: A, 0.12M; B, 0.45M; C, 1.2M; D, 3.4M; E, 11M; F, 32M; G, 0.2M.

at lower ionic strengths. It must be remembered that the maximum velocity gradient in the capillary viscometer varied over a range of nearly sevenfold,

Table 14. *Reduced viscosity of solutions of ox UFR in 0.12M-sodium hydrogen carbonate at 25° measured in a Couette viscometer*

Concn. of NaCl (M)	10 ⁵ × Concn. of UFR (g./ml.)	Velocity gradient (sec. ⁻¹)	10 ⁻³ × Reduced viscosity			
			... 0	1	10	50
0	36.3		2200	565	102	35.0
	18.2		1940	501	99	37.1
	8.97		1270	423	98.1	39.6
	5.42		810	339	94.7	40.6
	2.77		580	308	98.2	40.9
	1.25		350	228	94.4	47.8
	0.81		320	230	93.5	48.8
0.001	36.2		482	228	65.3	28.0
	18.2		267	160	59.1	27.1
	9.11		151	109	52.5	27.8
	4.62		98	82	47.0	28.0
	1.91		67	59	42.7	28.5
0.01	36.3		65	53	30.0	16.4
	18.1		50	37	23.8	15.4
	9.31		48	39	21.1	14.7
	7.27		41	27	17.9	13.3
	4.57		27	19	17.6	14.2
	3.58		20	18	16.7	14.0
	3.53		18	18	16.6	14.0
	2.14		18	17	17.7	14.0
0.2	36.2		14	11	8.8	6.8
	18.1		14	9	6.5	5.9
	9.03		14	10	6.7	5.6
	6.21		15	10	6.2	5.6
	4.58		13	9	6.1	5.1

from about 2000sec.⁻¹ for the lowest viscosities measured to about 300sec.⁻¹ for the highest viscosities. Since these solutions all exhibit non-Newtonian viscosity (see below), this fact will tend to make the variations seen in Fig. 6 greater than they would be if measured at constant velocity gradient.

Because of this a more limited series of measurements was made in the Couette viscometer. Reduced viscosities at selected velocity gradients are given in Table 14, together with values extrapolated to zero velocity gradient. Though these results show a complex relationship of viscosity to concentration, ionic strength and velocity gradient, two interesting conclusions can be drawn from them:

(i) The viscosity is strongly dependent on ionic strength under all conditions.

(ii) Contrary to the conclusions of Ogston & Stanier (1951a), there is a marked dependence of reduced viscosity on velocity gradient even in 0.2M-sodium chloride and at very low concentration. We ascribe this difference to the greater accuracy and sensitivity of our Couette viscometer compared with that used by Ogston & Stanier (1951a).

Fig. 7. Reduced viscosity of UFR measured in a capillary viscometer as a function of pH. The concentration of UFR was approx. 9×10^{-5} g./ml. ●, UFR initially in 0.12M-NaHCO₃; ○, UFR initially in 0.2M-NaCl-0.12M-NaHCO₃.

Effect of pH on viscosity. This was measured in the capillary viscometer by titrating 9ml. of UFR solution, in 0.12M-sodium hydrogen carbonate, with N-hydrochloric acid added from a micrometer burette. The measurements were repeated in the solvent 0.2M-sodium chloride-0.12M-sodium hydrogen carbonate. The corresponding pH values were measured by a parallel titration with a Leeds and Northrup pH-meter standardized with 50mM-potassium hydrogen phthalate buffer, pH 4.0. The results are shown in Fig. 7.

Comparison of hyaluronic acids. The viscosity of human mesothelioma UFR was measured in the Couette viscometer over a concentration range of 6×10^{-4} – 22×10^{-4} g./ml. between velocity gradients of 1 and 50sec.⁻¹, in 0.2M-sodium chloride-77mM-disodium hydrogen phosphate-23mM-potassium dihydrogen phosphate buffer, pH 7.3, for comparison with previous data (Ogston & Stanier, 1952) on ox UFR. Comparison was made of the slopes and intercepts of the approximately linear plots of $\log \eta_{red}$ against concentration; these are shown in Table 15.

The material prepared from ox UFR by separation of protein on a DEAE-Sephadex column was measured between 1 and 50sec.⁻¹ in 0.12M-sodium hydrogen carbonate and in 0.2M-sodium chloride-0.12M-sodium hydrogen carbonate. The results are given in Table 16 and may be compared with those in Table 14.

Effect of neuraminidase. Sialic acid was found (Table 18) to be present in ox UFR to about 1.5%, probably associated with the protein part of this

Table 15. Comparison of the viscosities of human mesothelioma UFR and of ox UFR in 0.2M-sodium chloride-77mM-disodium hydrogen phosphate-23mM-potassium dihydrogen phosphate at 25° measured in the Couette viscometer

Slope and intercept of $\log \eta_{\text{red.}}$ were plotted against concentration (g./100 ml.).

Material	Velocity gradient (sec. ⁻¹)	10 ⁻² × Slope	Intercept	10 ⁻³ × Intrinsic viscosity
Human M.18	0	8.6	3.71	5.1
M.30	0	9.2	3.65	4.5
M.37	0	7.8	3.67	4.7
Ox UFR*	0	11.1	3.72	5.3
Human M.18	43.3	4.2	3.82	6.6
M.30	50	4.8	3.67	4.7
Ox UFR*	50	3.5	3.68	4.8

* Values taken from the results of Ogston & Stanier (1952) measured in the same buffer.

Table 16. Reduced viscosity of solutions of ox UFR, freed from protein on a DEAE-Sephadex column, in 0.12M-sodium hydrogen carbonate at 25° measured in the Couette viscometer

Concn. of NaCl (M)	10 ⁵ × Concn. of UFR (g./ml.)	Velocity gradient (sec. ⁻¹)	10 ⁻³ × Reduced viscosity		
			 1	10	50
0	8.47		290	100	44.5
0.2	16.8		7.0	6.5	5.7

material. The effect of neuraminidase on the viscosity was measured to see whether it might have anything to do with the configuration of the UFR. No significant effect on the viscosity was found by measurements carried out in the Couette viscometer when the sialic acid content of the UFR was decreased tenfold by neuraminidase.

Sedimentation

The sedimentation of a preparation of ox UFR was studied over a range of concentration up to 13.6×10^{-3} g./ml., with the object of obtaining information on the permeability of ground substance to water. UFR was concentrated by partial ultrafiltration to about 15×10^{-3} g./ml. The semi-gelatinous material was made thoroughly homogeneous by stirring it gently at intervals over a period of 10 days; it was then transferred to a dialysis sac and dialysed against 0.2M-sodium chloride-77mM-disodium hydrogen phosphate-23mM-potassium dihydrogen phosphate buffer,

Fig. 8. Variation of the reciprocal of the sedimentation coefficient of UFR with concentration. The straight lines are the estimated limiting slopes at high and low concentration.

Fig. 9. Variation of the reciprocal of the sedimentation coefficients of hyaluronic acids with the square root of the concentration. ×, Ox UFR; ○, mesothelioma UFR; ●, values for umbilical-cord hyaluronic acid (Laurent & Pietruszkiewicz, 1961).

pH 7.3. The concentration before dialysis was determined from the dry weight of a sample, and the change of concentration during dialysis by the method described above. Dilutions with buffer were made by weight, care being taken that the diluted solution was homogeneously mixed. Dilutions were carried to the lowest concentration at which a sedimentation boundary was visible. The results are given in Table 17 and Figs. 8 and 9.

Similar measurements were made, over a smaller range of concentration, on the material derived from

Table 17. Sedimentation coefficients of UFR preparations in 0.2M-sodium chloride, pH 7

$10^3 \times \text{Concn. of UFR (g./g.)}$	$\sqrt{10^3 \times \text{Concn. of UFR (g./g.)}}$	$10^{13} \times S_{20} \text{ (sec.)}$	$10^{-13}/S_{20} \text{ (sec.}^{-1}\text{)}$
Ox UFR (B.41)			
13.6	3.69	0.812, 0.803	1.238
9.1	3.02	0.965	1.036
6.9	2.63	1.075	0.930
4.5	2.12	1.225, 1.223	0.817
3.7	1.92	1.440	0.694
3.12	1.77	1.490	0.671
1.93	1.39	1.971	0.507
1.41	1.19	2.330	0.429
0.88	0.94	2.903	0.344
0.44	0.66	4.074	0.245
0.23	0.48	5.527	0.181
0.12	0.35	8.02	0.125
UFR from human mesothelioma (M.44)			
3.10	1.76	1.40	0.71
1.54	1.24	1.92	0.52
0.79	0.89	2.61	0.38
0.384	0.62	3.76	0.266
0.170	0.41	5.65	0.177

a case of human mesothelioma. The results are given in Table 17 and Fig. 9. The results of Laurent & Pietruszkiewicz (1961) on a less highly polymerized sample of hyaluronic acid (from umbilical cord) are included in Fig. 9.

A few sedimentation measurements were made in 2M-sodium chloride to see whether the protein of ox UFR would be dissociated and would sediment independently under these conditions. Only a single boundary, characteristic of hyaluronic acid, was seen.

It seems that the limiting (zero-concentration) value of the sedimentation coefficient cannot be established with confidence. On the one hand, a plot of $1/S$ against c (Fig. 8) still shows curvature at the lowest concentration at which measurements could be made. There are theoretical reasons for supposing that this plot should become linear at low enough concentration (Ogston, 1953; Ogston & Woods, 1954), and a free-hand extrapolation based on this assumption gives as least estimates a limiting slope 5×10^{15} and S^0 16×10^{-13} sec. Ogston & Woods (1954) argued that this plot should also become linear, with a different slope, at higher concentration and this expectation seems to be fulfilled (Fig. 8). At high concentration the solution should contain a uniform entanglement of chains; by following Ogston & Woods' (1954) calculation, the chain radius obtained is $3\text{\AA}$.

On the other hand, a plot of $1/S$ against $\sqrt{c}$ gives a good straight line, especially in the lower range of concentration. Extrapolation of this plot would

Fig. 10. Lowry plots of optical rotatory dispersion of UFR (1.8×10^{-3} g./ml.) under various conditions (see the text). The ordinate scale applies to the uppermost curve; each subsequent curve has been displaced downwards by 1 unit of ordinate scale. All measurements were made in 0.12M- NaHCO_3 , pH 6.8–7.0. Concentrations of NaCl were: A, 0.2M; B, 80mM; C, 0.96mM; D, 0.25mM; E, 0. Curves F and G were measured after exposure to pH 3 (see the text); concentrations of NaCl were: F, 0.2M; G, 0.

give S^0 50×10^{-13} sec. or higher. However, the theory of Ogston (1953) does not support this extrapolation, since it would necessarily imply an infinite limiting slope of $1/S$ against c .

The sedimentation measurements of Laurent & Pietruszkiewicz (1961) also give a fair straight line when $1/S$ is plotted against $\sqrt{c}$ (Fig. 9). The molecular weight of their material, estimated on the basis of light-scattering, was 1.7×10^6 , whereas our material has a molecular weight 1.3×10^7 . The respective slopes of the plots of $1/S$ against $\sqrt{c}$ are 1.4×10^{14} and 1.1×10^{14} . Whatever method of extrapolation is used, it appears that the limiting sedimentation coefficient is larger for material of larger molecular weight.

Optical rotatory dispersion

Measurements were made on solutions containing 1.8×10^{-3} g. of UFR/ml. in 0.12M-sodium hydrogen carbonate and several concentrations of sodium chloride. Solutions were clarified before measurement by centrifuging for 30–60 min. at 29000 rev./min. (Spinco model L centrifuge, no. 30 rotor). The

readings did not change with time. The results are plotted in Fig. 10. A sample of solution initially at pH 6.8 in 0.12M-sodium hydrogen carbonate was brought to pH 3 by dialysis against 0.2M-sodium chloride-mN-hydrochloric acid. It was brought back to pH 6.8 by dialysis against 0.2M-sodium chloride-0.12M-sodium hydrogen carbonate. It was then clarified and its optical rotatory dispersion was measured. The same solution was exhaustively dialysed against 0.12M-sodium hydrogen carbonate, clarified and measured again. The concentrations of these solutions were not exactly known, but were approx. 1.8×10^{-3} g./ml. The results are included in Fig. 10.

Estimation of glucosamine and acetyl

In spite of the higher estimates of glucosamine obtained by the method of Ogston (1964), these are decidedly lower than the estimates of acetyl on ox

UFR and a little lower than those on mesothelioma UFR (Tables 18 and 20). The presence or absence of protein in ox material does not affect this conclusion. If the acetyl values represent the true content of *N*-acetylglucosamine, the recoveries from both materials are satisfactory (Table 19), whereas the recoveries would be markedly low, particularly with the ox preparations, if the direct estimates of glucosamine were accepted.

Estimation of glucuronic acid

The results in Table 1 show that the colorimetric methods give low values for glucuronic acid in the highly polymerized samples of hyaluronic acid studied compared with those obtained by decarboxylation; the presence or absence of protein in the sample had no effect. By contrast, agreeing results with the two methods have been reported in the literature, usually with samples that have probably

Table 18. *Analysis of preparations of hyaluronic acids*

Preparation	Glucosamine (m-equiv./g.)	Total acetyl (m-equiv./g.)	O-Acetyl (m-equiv./g.)	Sialic acid (m-equiv./g.)	Glucuronic acid (m-equiv./g.)	Total N (%)	Ash (%)
Ox UFR B.28	—	—	—	0.049	—	—	—
Ox UFR B.32	—	—	—	—	2.10	—	6.6
Ox UFR B.33	—	—	—	—	1.98	—	12.9
Ox UFR B.34	—	—	—	—	2.06	—	5.6
Ox UFR B.35,36	1.51	1.82	0.04	—	2.08	5.78	3.6
Ox UFR B.38	1.51	1.79	0.05	0.052	2.15	5.91	3.2
Ox UFR B.41	1.59	1.76	—	—	2.21	—	—
Ox UFR B.39*	1.90	2.31	—	—	2.59	3.74	5.2
Ox UFR S.16†	1.83	2.20	—	—	2.58	4.00	8.3
Mesothelioma UFR M.30	2.19	2.30	—	—	2.80	3.58	4.0
Mesothelioma UFR M.37,43	2.22	2.32	0.02	0.0035	2.69	3.47	4.0

* Deproteinized by Sevag method.

† Deproteinized by DEAE-Sephadex (unfractionated).

Table 19. *Total recoveries in analyses of hyaluronic acids*

Recoveries of acetylglucosaminyl are calculated from the acetyl values in Table 18. For details of the recoveries of protein and Ca^{2+} , see the text.

UFR preparation ...	Recovery (g./100g. dry wt.)					
	B.35,36	B.38	B.39	S.16	M.30	M.37,43
Acetylglucosaminyl	36.9	36.4	46.9	45.7	45.7	47.0
Glucuronyl	36.6	37.4	45.5	45.4	48.6	47.0
Protein	20.8	21.9	3.0	5.9	2.2	2.2
Ca^{2+}	1.4	1.3	2.1	3.3	3.2	3.2
	<u>95.7</u>	<u>97.0</u>	<u>97.5</u>	<u>100.3</u>	<u>99.7</u>	<u>99.4</u>

Table 20. *Molar ratios deduced from data of Table 18*

UFR preparation ...	B.35,36	B.38	B.41	B.39	S.16	M.30	M.37,43
Acetyl/apparent glucosamine	1.20	1.19	1.11	1.21	1.20	1.05	1.04
Glucuronic acid/acetyl	1.14	1.20	1.26	1.12	1.17	1.22	1.16

been extensively depolymerized (Lowther & Rogers, 1956; Schiller, Mathews, Jefferson, Ludowieg & Dorfman, 1954; Meyer, Davidson, Linker & Hoffman, 1956) (Table 22); our results on hyaluronic acid made from bovine vitreous humour (which was less highly polymerized) also show good agreement, as do those on pectin and on menthol glucuronide.

The combination of cetylpyridinium ion with purified hyaluronic acid preparations under the conditions that we describe gives highly reproducible results, agreeing well with the decarboxylation method, and also independent of the presence or absence of protein (Table 1).

We regard the decarboxylation and cetylpyridinium values as reliable for this material; the values quoted in Tables 18, 19 and 20 were obtained by their use.

Estimation of amino acids and protein

In the analyses of Ogston & Stanier (1952) it was assumed that excess of N represented protein having an N content of 15.5%. The correctness of this assumption is shown by the amino acid analyses given in Table 21. The summed weights of amino acid residues obtained from Table 21, with 20 hr. hydrolysis, also agree with the protein content based on N determinations. The protein values given in Table 19 have therefore been based on excess of N over glucosamine N (estimated by

Table 21. *Analytical values for amino acids in UFR and in isolated protein*

Preparation ...	Amino acid composition (m-mole/g. of total amino acids)				
	B.41*	B.45†	B.45‡	B.49§	Protein
Lys	0.58	0.50	0.67	0.49	0.45
His	0.21	0.17	0.17	0.19	0.15
Arg	0.37	0.40	0.45	0.38	0.35
Asp	0.85	0.86	0.95	0.84	0.82
Thr	0.75	0.77	0.72	0.79	0.80
Ser	0.83	0.82	1.06	0.85	0.99
Glu	1.16	1.13	0.99	1.17	1.09
Pro	0.77	0.72	0.86	0.75	0.64
Gly	0.69	0.73	0.86	0.70	0.73
Ala	0.59	0.63	0.65	0.58	0.54
Cys	—	—	—	0.13	0.12
Val	0.79	0.77	0.45	0.74	0.84
Met	0.07	0.09	0.07	0.11	0.10
Ile	0.35	0.36	0.21	0.36	0.33
Leu	0.70	0.69	0.65	0.69	0.71
Tyr	0.18	0.27	0.29	0.21	0.32
Phe	0.34	0.33	0.33	0.31	0.32
N (% of total amino acid residues)	15.9	13.9	15.8	15.8	15.5

* Hydrolysed in 8N-HCl for 20 hr. at 110°.

† Hydrolysed in 6N-HCl for 22 hr. at 110°.

‡ Hydrolysed in 6N-HCl for 2 hr. at 110°.

§ Hydrolysed in 6N-HCl for 20 hr. at 110°.

|| Separated from ox UFR preparation B.49 on DEAE-Sephadex column, and hydrolysed in 6N-HCl for 20 hr. at 110°.

Table 22. *Summary of previous analytical data on hyaluronic acids*

Source	Authors	Acetyl-glucosaminyl (%)	Glucuronyl (%)	Protein (%)	Glucuronic acid/glucosamine molar ratio	Recovery (%)
Ox synovial fluid	Meyer, Smyth & Dawson (1939)	39.1-49.5*	32.6-46.1¶	0	0.75-1.36	73.4-94.7
	Ogston & Stanier (1952)	44.3-50.0†				
	Caputo & Marcante (1960)	30.3*	35.0	27.6††	1.33	92.9
		40.8*, 42.5†	29.0‡	13††	0.82*, 0.78†	82.8*, 84.5†
Human synovial fluid	Hamerman & Sandson (1960)	32.6*	28.7‡	2.5**	1.01	63.8
Umbilical cord	Meyer & Palmer (1936)	49.0*, 63.3†	44.1¶	0	1.04*, 0.81†	93.1*, 107.4†
	Madinaveitia & Stacey (1944)	40*	41	15**	1.18	96
	Rapport, Meyer & Linker (1951)	45.0*	40.0	0	1.02	85.0
	Weissman, Rapport, Linker & Meyer (1953)	43.2*	37.7	0	1.00	80.9
	Blumberg, Oster & Meyer (1955)	43.2*	41.3‡	0	1.10	84.5
	Ringertz & Reichard (1960)	55.9*	44.4	5.7**	0.91	106.0
	Caputo & Marcante (1960)	45.3*, 44.0†	37.2‡	10††	0.95*, 0.97†	92.5*, 91.2†
	Quinn & Bettelheim (1963)	37.6*	47.1‡	0	1.44	84.7

Table 22 (*continued*)

Source	Authors	Acetyl-glucosaminyl (%)	Glucuronyl (%)	Protein (%)	Glucuronic acid/glucosamine molar ratio	Recovery (%)
Skin (pig)	Meyer & Chaffee (1941)	43.5*, 53.4†	38.2	0	1.01*, 0.82†	81.7*, 91.6†
(rabbit)	Schiller <i>et al.</i> (1954)	44.2*, 47.3†	42.3 , 46.6‡	0	1.03† , 1.22*‡	86.5* , 93.9†‡
(pig)	Meyer <i>et al.</i> (1956)	40.3*	38.7 , 40.8‡	0	1.10 , 1.16‡	79.0 , 81.1‡
(pig embryo)	Loewi & Meyer (1958)	46.6*	39.0‡, 33.0	0	0.96‡, 0.82	85.6‡, 79.6
(pig embryo)	Loewi & Meyer (1958)	46.3*	42.0‡, 38.6	0	1.04*, 0.96	88.3‡, 84.9
(pig embryo)	Loewi & Meyer (1958)	45.1*	46.7‡, 38.6	0	1.16‡, 0.96	91.8‡, 83.7
(human)	Loewi (1961)	31.5-46.3*	31.4-40.5‡, 24.3-28.8§	0	0.79-1.45‡	68.1-80.4
(rabbit)	Davidson & Small (1963)	37.0*	27.9‡	0	0.87	64.9
Vitreous humour	Meyer & Palmer (1936)	45.0*, 57.1†	41.0¶	0	1.05*, 0.88†	86.0*, 98.1†
	Laurent (1955)	44.5*	39.4	5.4**	1.02	83.9
Cock's comb	Caputo & Marcante (1960)	45.3*, 45.3†	34.5‡	21††	0.88	100.8
Micro-organisms	Kendall, Heidelberger & Dawson (1937)	54.8†	42.3-45.1	0	0.89-0.95	97.1-99.9
	Roseman, Moses, Ludowieg & Dorfman (1953)	56.1*	42.4	0	0.87	98.5
	Blumberg <i>et al.</i> (1955)	46.3*	40.0‡	0	0.99	86.3
	Lowther & Rogers (1956)	44.3*	40.0 , 41.0‡	0	1.04 , 1.06‡	84.3 , 85.3§
	Blumberg <i>et al.</i> (1958)	41.0*, 44.0*	38.0 , 39.0‡	0	1.07-1.02	79.0-83.0
Fowl sarcoma	Kabat (1939)	44.5*, 43.7†	35.0	0	0.90*, 0.92†	79.5*, 78.7†
	Fujita (1954)	38.5*, 52.4†	36.5‡	0	1.09*, 0.80†	75.0*, 88.9†
	Caputo & Marcante (1960)	34.0*, 34.0†	25.4†	18††	0.86	77.4
Pleural fluid	Meyer & Chaffee (1940)	47.6*, 51.0†	44.4¶	0	1.07*, 1.00†	92.0*, 95.4†
Callus tissue	Maurer & Hudack (1952)	26.8*, 41.0†	22.2‡	38.1**	0.95*, 0.62†	87.1*, 101.3†
Bone	Meyer <i>et al.</i> (1956)	44.4*	39.3‡	0	1.02	83.7
Aorta	Meyer <i>et al.</i> (1956)	41.0*	37.9‡	0	1.06	88.9
Heart valve	Meyer <i>et al.</i> (1956)	46.3*	42.2‡	0	1.05	88.5
Ligament	Meyer <i>et al.</i> (1956)	41.3*	37.7‡	0	1.05	79.0
Electric organ (eel)	Meyer <i>et al.</i> (1956)	43.6*	39.4‡	0	1.04	83.0
Pleural fluid	Meyer <i>et al.</i> (1956)	45.8*	37.9	2.4**	0.95	86.1
Liposarcoma	Meyer <i>et al.</i> (1956)	44.5*	40.1‡, 40.8	0	1.04‡, 1.06*	84.6‡, 85.3
Pig tendon	Meyer <i>et al.</i> (1956)	42.8*	37.5	4.6**	1.01	84.9
Granulation tissue	Berenson & Dalferes (1960)	39.8*	27.7‡	15.2**	0.80	82.7

* Elson-Morgan (or modification) estimation of glucosamine.

† Acetyl estimation.

‡ Dische (1947) carbazole method.

§ Orcinol method.

|| Decarboxylation.

¶ Lefevre & Tollens (1907) method.

** Protein calculated from total N and glucosamine.

†† Authors' values.

acetyl), assuming that the protein contains 15.5% of N.

Estimation of metal content

This is based on the ash content on the assumption that this is all calcium carbonate (Table 19). Although UFR retains Ca^{2+} (Aldrich, 1958) rather tenaciously, some of the ash may be calcium chloride, sodium carbonate or sodium chloride; if any of these

is present, the quantity to be entered in the last row of Table 19 would be larger and the percentage recoveries would be even better.

GENERAL DISCUSSION

Composition of hyaluronic acids. We have tried to provide complete compositional analyses of hyaluronic acids derived from two sources. Although such

methods as enzymic degradation may provide more interesting information, one cannot be certain that the whole structure is satisfactorily derived unless nearly 100% of the material has been accounted for. In this respect previous analyses as a whole fall far short of the ideal. These are summarized in Table 22; where the published information has allowed, they are expressed on an ash-free basis.

Our experiments have shown the difficulties of estimating completely both glucosamine and glucuronic acid in highly polymerized material. Obviously a molar ratio based on incomplete analysis is of little value. Although it is generally assumed that the molar ratio is 1:1, and that the hyaluronic acids are alternate co-polymers, the published analyses do not support this view very strongly. Our own estimates (Table 20) are all substantially different from unity. The completeness of the recoveries shown in Table 19 make it doubtful that our estimates of the molar ratio are seriously in error.

Comparison of hyaluronic acids. The compositions of the carbohydrate components of the preparations from ox synovial fluid and from human mesothelioma are closely similar (Tables 18, 19 and 20). Their viscosities and sedimentation rates are not very different (Tables 15 and 17, and Fig. 9). However, they show two interesting differences:

(i) Although ox UFR constantly contains about 20% of a protein that appears to be characteristic (Curtain, 1955), the UFR prepared by the same method from mesothelioma fluid (which was rich in protein) contained very little. This could be due to differences in the hyaluronic acids, or to the absence of suitable protein from the mesothelioma fluid.

(ii) The proportion of glucosamine that could be directly estimated was greater in the mesothelioma than in the ox material; this was not a result of the protein content of the latter (Table 20). The most likely cause of failure to estimate all the glucosamine is that a part of it is extremely resistant to liberation by hydrolysis; this difference between the two materials therefore suggests a difference in the chemical environment of some part of their glucosamine contents.

This evidence suggests that hyaluronic acids from different sources may not be as simple or as uniform in chemical structure as is commonly assumed. This conclusion holds good even if notice is taken of the heterogeneity within preparations with respect to molecular weight and configuration (and possibly with respect to chemical composition) shown by fractionation of the bovine material on DEAE-Sephadex.

Molecular weight of ox UFR

Previous estimates of the average molecular weight of our material have been in the range

8×10^6 – 10×10^6 . These have been based chiefly on sedimentation and viscosity measurements by making use of the relationship between S^0 , the variation of $1/S$ with c and the intrinsic viscosity deduced by Ogston (1953). If the lower values $S^0 = 16 \times 10^{-13}$ and $d(1/S)/dc = 5 \times 10^{15}$ were accepted, the molecular weight based on Ogston's (1953) treatment would be about 14×10^6 . However, as has been shown above, these values must be regarded as very uncertain and little reliance can be placed on the estimate of molecular weight based on them.

Our light-scattering measurements on unfractionated material gave molecular weights in the range 12×10^6 – 14×10^6 over a wide range of conditions. Acidification to pH 3.0, though it caused a great decrease of radius of gyration, did not affect the molecular weight. Removal of protein on a DEAE-Sephadex column caused no marked change in the mean molecular weight, though it gave evidence of separation into fractions of different molecular weights (Table 13): Berman (1963) was able to fractionate the hyaluronic acid from vitreous humour by this means. In salt-free solutions the molecular weight appears to increase, with parallel increase of the radius of gyration, in agreement with the findings of Lacapère & Delaville (1960); however, extrapolation of light-scattering data under these conditions is less satisfactory than in the presence of salt, owing to the strong concentration-dependence of the reduced intensities.

The relationship established by Laurent *et al.* (1960) between the intrinsic viscosity and molecular weight (from light-scattering) of hyaluronic acids gives a value for the molecular weight of our material of 1.5×10^7 , taking the intrinsic viscosity as 1.4×10^4 ml./g.

Configuration of ox UFR in solution. It has been generally accepted that hyaluronic acids are linear flexible polymers, which in solution take up a configuration approaching a random coil, somewhat stiffened by incompletely free rotation and by repulsion between anionic groups (see reviews by Blumberg & Ogston, 1958; Balazs, 1958; Rogers, 1961). Such a configuration would be approximately spherical and the volume of the molecular domain would be very large. This configuration is generally supported by our measurements of light-scattering (Fig. 2a). The radius of gyration would suggest a molecular volume of about 1.4×10^{-13} cm.³ (Debye, 1948); the intrinsic viscosity would give 1.3×10^{-13} cm.³. A rod-like structure consistent with the intrinsic viscosity would require a substantially larger radius of gyration from light-scattering. The dissymmetry factor (Fig. 3) varies in a way similar to that of polymethacrylic acid (Oth & Doty, 1952), decreasing at first with increasing concentration and reaching a minimum at a concentration of about 1.3×10^{-4} g./ml. This is about the concentra-

tion at which, with the value of the molecular volume quoted above, the solution becomes 'filled' with the molecular domains. On neutralization of the anionic charges by acidification, the molecule shrinks and Z becomes independent of concentration within the range studied. Arabic acid shows similar behaviour (Veis & Eggenberger, 1954). A spherical molecule of the dimensions suggested would have a sedimentation coefficient at zero concentration of about 13×10^{-13} sec., which is near the lower limit of possible extrapolated values. It should also exhibit only a small degree of streaming birefringence at low velocity gradient, as was observed by Ogston & Stanier (1951a). The evidence quoted so far supports a voluminous, approximately spherical structure that could, but need not, be a random coil.

In general, the variation of viscosity with ionic strength supports the flexible random-coil model, suggesting expansion of the molecule as the interaction between anionic groups is increased. The only discordant feature is the apparent persistence of non-Newtonian viscosity to zero concentration, even at high ionic strength. This finding, which is in disagreement with the conclusions of Ogston & Stanier (1951a), would be consistent with a rigid ellipsoid structure of axial ratio at least 16 (Yang, 1961); alternatively, it might arise from distortion of a flexible structure in the shear gradient.

In contrast with this is the failure of the radius of gyration to increase as the ionic strength is lowered. This evidence and the failure of added protein to modify the viscosity indicate that the structure lacks the flexibility of a random coil with respect to expansion or contraction. The apparent discrepancy between this evidence and that of viscosity could perhaps be reconciled by a branched structure, with partial cross-linking to form a 'cage' within which most of the branches remain mobile. Such a structure would have an internal 'osmotic pressure', due to the flexible internal branches (just as would a random coil), sufficient to keep the 'cage' fully distended. Changes of stiffness of the internal branches would then not affect the size of the molecular domain, but only the detail of distribution of mass within it. There might therefore be little effect on the radius of gyration measured by light-scattering. However, the degree of internal 'free draining', and consequently the viscosity, would be strongly affected by the configuration of the internal chains.

The evidence of optical rotatory dispersion, as far as it can be interpreted, is consistent with this model. The nearly linear Lowry plot (Fig. 10) obtained at high ionic strength is (at least for polypeptides) characteristic of random configuration (Urnes & Doty, 1961). At low ionic strength the Lowry plot becomes strongly non-linear, suggesting a higher

degree of internal order, such as might arise from stiffening of individual chains.

As has been pointed out, the analytical data suggest that ox UFR is not wholly a linear alternate co-polymer. Those glucosamine residues that seem particularly difficult to liberate by hydrolysis might form branch points. In a molecule of degree of polymerization about 50 000 a substantial number of chain ends could escape chemical detection. The apparent expansion of the molecule after removal of protein on DEAE-Sephadex might indicate a cross-linking function for the protein. This treatment caused little change in the viscosity.

Physiological considerations

Pappenheimer (1953) has defined the permeability coefficient, P , for a membrane (of any given thickness) as volume flow per time, per area and per pressure gradient. The same quantity can be obtained from the sedimentation coefficient; this method is free from the objection to the more direct method of measuring permeability used by Ogston & Sherman (1961), that hyaluronic acid flows with the solvent and accumulates against the membrane during the measurement. The effective weight, $(1 - \bar{v}\rho)c$, of hyaluronic acid in sedimentation in 1 ml. of solution corresponds to the pressure gradient in Pappenheimer's (1953) coefficient, and the rate of sedimentation (cm./sec.) corresponds to the rate of volume flow/area. Thus $S/(1 - \bar{v}\rho)c$ is dimensionally identical with P for a thickness of 1 cm. For example, the value of P for 1 cm. thickness of hyaluronic acid gel at a concentration of 10 mg./ml. ($S = 1 \times 10^{-13}$ sec.) is 3×10^{-11} g.cm.³sec.⁻¹. Pappenheimer's (1953) value for capillaries is about 3×10^{-8} if the pressure gradient is expressed in cm. H₂O/cm.², or 3×10^{-11} g.cm.³sec.⁻¹. This shows, contrary to the statement made by Ogston (1963), which was based on a misreading of Pappenheimer's (1953) values, that, though a thin layer of hyaluronic acid may offer substantial resistance to the flow of water, this is not likely to be comparable with the resistance offered by the capillary wall.

The effect that hyaluronic acid may have on the flow of water through connective tissue may be illustrated by comparing the rate of flow of water in a vertical capillary of 0.1 mm. diam. with the flow through the same capillary containing immobilized hyaluronic acid at 10 mg./ml. The former value is given by Poiseuille's law as

$$\pi g \cdot r^4 / 8 \eta = 2.4 \times 10^{-5} \text{ ml./sec.}$$

the latter by

$$P \times \pi r^2 = 2.4 \times 10^{-12} \text{ ml./sec.}$$

Even if the capillary diameter is taken as 1μ , the flow rates still differ by more than 1000-fold. This

simple model illustrates the suggestion made for example by Fessler (1960) of how hyaluronic acid may immobilize interstitial fluid.

This work confirms Laurent & Ogston's (1963) finding that mixtures of hyaluronic acid and protein have anomalously high osmotic pressures, measured across a membrane impermeable to both; from this Ogston's (1962) conclusion follows, of thermodynamic necessity, that across a membrane permeable to protein the osmotic pressure is lowered, if the protein is at equilibrium [though the magnitude of the effect will be smaller than Ogston (1962) predicted]. The difficulty in using this information in a physiological context is that there steady-state rather than equilibrium conditions hold good.

We are grateful to Dr J. B. Langridge of the Commonwealth Scientific and Industrial Research Organisation for a gift of menthol glucuronide, to Dr W. D. Crow of the Australian National University for gas-liquid chromatography, to Dr D. C. Shaw of the Australian National University and Dr C. M. Mauritzen of the University of Melbourne for amino acid analysis, to Dr J. E. Fildes of the Australian National University for nitrogen estimations by the method of Jacobs, to Dr B. E. Robson and Mr R. J. Baxter of the Australian National University for assistance with computer programming, to Dr J. E. Scott for a gift of fluid from a case of human mesothelioma, to the Supervisor and staff of the Australian Capital Territory abattoirs and to Dr T. C. Laurent for showing us his results in advance of publication.

REFERENCES

- Aldrich, B. I. (1958). *Biochem. J.* **70**, 236.
 Aminoff, D. (1961). *Biochem. J.* **81**, 384.
 Balazs, E. A. (1958). *Fed. Proc.* **17**, 1086.
 Berenson, G. S. & Dalferes, E. R. (1960). *Brit. J. exp. Path.* **41**, 422.
 Berman, E. R. (1963). *Exp. Eye Res.* **2**, 1.
 Bitter, T. & Muir, H. M. (1962). *Analyt. Biochem.* **4**, 330.
 Blix, G. & Snellman, O. (1945). *Ark. Kemi Min. Geol.* **19A**, no. 32.
 Blumberg, B. S. & Ogston, A. G. (1958). *Ciba Found. Symp.: Chemistry and Biology of Mucopolysaccharides*, p. 22. Ed. by Wolstenholme, G. E. W. & O'Connor, M. London: J. and A. Churchill Ltd.
 Blumberg, B. S., Ogston, A. G., Lowther, D. A. & Rogers, H. J. (1958). *Biochem. J.* **70**, 1.
 Blumberg, B. S., Oster, G. & Meyer, K. (1955). *J. clin. Invest.* **34**, 1454.
 Caputo, A. & Marcante, M. L. (1960). *Clin. chim. Acta*, **5**, 477.
 Casassa, E. F. (1960). *Polymer*, **1**, 169.
 Casassa, E. F. & Eisenberg, H. (1960). *J. phys. Chem.* **64**, 753.
 Cecil, R. & Ogston, A. G. (1951). *J. sci. Instrum.* **28**, 253.
 Clark, W. (1926). *J. chem. Soc.* p. 749.
 Curtin, C. C. (1955). *Biochem. J.* **61**, 688.
 Davidson, E. H. & Small, W. (1963). *Biochim. biophys. Acta*, **69**, 453.
 Davies, M. (1965). *Makromol. Chem.* (in the Press).
 Debye, P. (1948). In *Les Grosses Molécules en Solution, Hommage National à Paul Langevin et Jean Perrin*, p. 39. Paris: Collège de France.
 Dische, Z. (1947). *J. biol. Chem.* **167**, 189.
 Doty, P. & Steiner, R. F. (1952). *J. chem. Phys.* **20**, 85.
 Elson, L. A. & Morgan, W. T. J. (1933). *Biochem. J.* **27**, 1824.
 Fessler, J. H. (1960). *Biochem. J.* **76**, 124.
 Flory, P. J. (1953). *Principles of Polymer Chemistry*, pp. 595 *et seq.* Ithaca, N.Y.: Cornell University Press.
 Fujita, K. (1954). *Nagoya J. med. Sci.* **17**, 98.
 Gregory, J. D. (1960). *Arch. Biochem. Biophys.* **89**, 157.
 Hamerman, D. & Sandson, J. (1960). *Nature, Lond.*, **188**, 1194.
 Harkins, W. D. (1960). In *Technique of Organic Chemistry*, 3rd ed., vol. 1, p. 757. Ed. by Weissberger, A. New York: Interscience Publishers Inc.
 Hauser, E. A. & Niles, G. E. (1941). *J. phys. Chem.* **45**, 954.
 Hyde, A. J. & Taylor, R. B. (1963). *Makromol. Chem.* **62**, 204.
 Ishihara, A. (1964). *J. chem. Phys.* **40**, 1137.
 Jacobs, S. (1962). *Analyst*, **87**, 53.
 Kabat, E. A. (1939). *J. biol. Chem.* **130**, 143.
 Kay, E. R. M., Simmons, N. S. & Dounce, A. L. (1952). *J. Amer. chem. Soc.* **74**, 1724.
 Kendall, F. E., Heidelberger, M. & Dawson, M. H. (1937). *J. biol. Chem.* **118**, 61.
 Kruis, A. (1936). *Z. phys. Chem.* **34**, 13.
 Lacapère, J. & Delaville, G. (1960). *Path. Biol.* **8**, 29.
 Laurent, T. C. (1955). *J. biol. Chem.* **216**, 263.
 Laurent, T. C. (1964). *Biochem. J.* **93**, 106.
 Laurent, T. C. & Ogston, A. G. (1963). *Biochem. J.* **89**, 249.
 Laurent, T. C. & Pietruszkiewicz, A. (1961). *Biochim. biophys. Acta*, **49**, 258.
 Laurent, T. C., Ryan, M. & Pietruszkiewicz, A. (1960). *Biochim. biophys. Acta*, **42**, 476.
 Lefèvre, K. V. & Tollens, B. (1907). *Ber. dtsch. chem. Ges.* **40**, 4513.
 Loewi, G. (1961). *Biochim. biophys. Acta*, **52**, 435.
 Loewi, G. & Meyer, K. (1958). *Biochim. biophys. Acta*, **27**, 453.
 Lowther, D. A. & Rogers, H. J. (1956). *Biochem. J.* **62**, 304.
 McKenzie, H. A. & Wallace, H. S. (1954). *Aust. J. Chem.* **7**, 55.
 Madinaveitia, J. & Stacey, M. (1944). *Biochem. J.* **38**, 413.
 Markham, R. (1942). *Biochem. J.* **36**, 790.
 Marks, G. S. & Neuberger, A. (1961). *J. chem. Soc.* p. 4872.
 Martin, C. J. & Axelrod, A. E. (1953). *Proc. Soc. exp. Biol., N.Y.*, **83**, 461.
 Maurer, P. H. & Hudack, S. S. (1952). *Arch. Biochem. Biophys.* **38**, 49.
 Meyer, K. (1960). In *Molecular Biology*, p. 69. Ed. by Nachmansohn, D. New York: Academic Press Inc.
 Meyer, K. & Chaffee, E. (1940). *J. biol. Chem.* **133**, 83.
 Meyer, K. & Chaffee, E. (1941). *J. biol. Chem.* **138**, 491.
 Meyer, K., Davidson, E., Linker, A. & Hoffman, P. (1956). *Biochim. biophys. Acta*, **21**, 506.
 Meyer, K. & Palmer, J. W. (1936). *J. biol. Chem.* **114**, 689.
 Meyer, K., Smyth, E. M. & Dawson, M. H. (1939). *J. biol. Chem.* **128**, 319.
 Moretti, A. & Whitehouse, M. W. (1963). *Biochem. J.* **87**, 396.
 Ogston, A. G. (1953). *Trans. Faraday Soc.* **49**, 1481.
 Ogston, A. G. (1962). *Arch. Biochem. Biophys.* Suppl. **1**, 39.

- Ogston, A. G. (1963). In *Ultracentrifugal Analysis in Theory and Experiment*, p. 263. Ed. by Williams, J. W. New York: Academic Press Inc.
- Ogston, A. G. (1964). *Analyt. Biochem.* **8**, 337.
- Ogston, A. G. & Phelps, C. F. (1960). *Biochem. J.* **78**, 827.
- Ogston, A. G. & Sherman, T. F. (1961). *J. Physiol.* **156**, 67.
- Ogston, A. G. & Stanier, J. E. (1950). *Biochem. J.* **46**, 364.
- Ogston, A. G. & Stanier, J. E. (1951a). *Biochem. J.* **49**, 585.
- Ogston, A. G. & Stanier, J. E. (1951b). *Biochem. J.* **49**, 591.
- Ogston, A. G. & Stanier, J. E. (1952). *Biochem. J.* **52**, 149.
- Ogston, A. G. & Stanier, J. E. (1953a). *J. Physiol.* **119**, 244.
- Ogston, A. G. & Stanier, J. E. (1953b). *Biochem. J.* **53**, 4.
- Ogston, A. G. & Woods, E. F. (1954). *Trans. Faraday Soc.* **50**, 635.
- Oth, A. & Doty, P. (1952). *J. phys. Chem.* **56**, 43.
- Overbeek, J. Th. G. (1956). *Progr. Biophys. biophys. Chem.* **6**, 58.
- Pappenheimer, J. R. (1953). *Physiol. Rev.* **33**, 387.
- Peterson, E. A. & Sober, H. A. (1959). *Analyt. Chem.* **31**, 857.
- Quinn, F. R. & Bettelheim, F. A. (1963). *Biochim. biophys. Acta*, **69**, 544.
- Rapport, M. M., Meyer, K. & Linker, A. (1951). *J. Amer. chem. Soc.* **73**, 2416.
- Rienits, K. G. (1960). *Biochem. J.* **74**, 27.
- Ringertz, N. R. & Reichard, P. (1960). *Acta chem. scand.* **14**, 303.
- Rogers, H. J. (1961). *Symp. biochem. Soc.* **20**, 51.
- Ropes, M. W., Robertson, W. v.B., Rossmeisl, E. C., Peabody, R. B. & Bauer, W. (1947). *Acta med. scand.* **196** (Suppl.), 700.
- Roseman, S., Moses, F. E., Ludowieg, J. & Dorfman, A. (1953). *J. biol. Chem.* **203**, 213.
- Rowe, D. S. & Abrams, M. E. (1957). *Biochem. J.* **67**, 431.
- Schiller, S., Mathews, M. B., Jefferson, H., Ludowieg, J. & Dorfman, A. (1954). *J. biol. Chem.* **211**, 717.
- Scott, J. E. (1960). *Meth. biochem. Anal.* **8**, 145.
- Tanford, C. & Buzzell, J. G. (1956). *J. phys. Chem.* **60**, 225.
- Urnes, P. & Doty, P. (1961). *Advanc. Protein Chem.* **16**, 401.
- Veis, A. & Eggenberger, D. N. (1954). *J. Amer. chem. Soc.* **76**, 1560.
- Weissman, B., Rapport, M. M., Linker, A. & Meyer, K. (1953). *J. biol. Chem.* **205**, 205.
- Yang, J. T. (1961). *Advanc. Protein Chem.* **16**, 323.
- Yoffey, J. M. & Courtice, F. C. (1956). *Lymphatics, Lymph and Lymphoid Tissue*, 2nd ed., p. 242. London: Edward Arnold (Publishers) Ltd.
- Zimm, B. H. (1948). *J. chem. Phys.* **16**, 1099.

Biochem. J. (1965) **96**, 471

APPENDIX 1

Use of Refractive Difference for Measuring the Partition of a Diffusible Solute

Although it is strictly the polarizations of components that are additive in determining that of a mixture, the refractive quantities are very nearly linearly additive provided that the refractive indices of the solutions differ little from that of solvent, and that compositions are expressed on a volume basis. We may therefore write for a k -component solution, in which components 2 to k are solutes:

$$n_{1..j,k} = \sum_{i=1}^k n_i v_i = n_1 v_1 + \sum_{i=2}^k \bar{n}_i v_i \quad (8)$$

where $n_{1..j,k}$ is the refractive index of the solution, n_1 that of solvent, $\bar{n}_i$ is a constant for each solute component (not necessarily equal to the refractive index of the pure component, except for the solvent), v_i is the volume fraction of component i . Since $\sum v_i = 1$:

$$\begin{aligned} n_{1..j,k} &= n_1 + \sum_{i=2}^k (\bar{n}_i - n_1) v_i \\ &= n_1 + R_k v_k + \sum_{i=2}^j R_i v_i \end{aligned} \quad (9)$$

where R_i replaces $(\bar{n}_i - n_1)$ and is a characteristic constant for each solute.

A solution that contains all components but k in the same relative proportions has volume fractions given by:

$$\phi_i = v_i / (1 - v_k) \quad (10)$$

remembering that

$$\sum_{i=1}^j \phi_i = 1$$

and provided that there are no differential volume changes of mixing. The refractive index of this solution is given by:

$$n_{1..j} = n_1 + \sum_{i=2}^j R_i \phi_i \quad (11)$$

From eqns. (9), (10) and (11):

$$\begin{aligned} n_{1..j,k} - n_{1..j} &= R_k v_k + \sum_{i=2}^j R_i (v_i - \phi_i) \\ &= v_k \left(R_k - \sum_{i=2}^j R_i \phi_i \right) \end{aligned} \quad (12a)$$

$$= v_k (R_k - [n_{1..j} - n_1]) \quad (12b)$$

Eqns. (12) show: (i) that the refractive difference due to component k in a mixture is proportional to