CLXX. INVESTIGATIONS ON GELATIN.

PART IX. THE SCISSION OF GELATIN INTO CONSTITUENT PROTEINS.

BY SAMUEL BARNETT SCHRYVER
AND KENNETH VIVIAN THIMANN (*Beit Fellow of the Imperial
College of Science and Technology*).

*From the Biochemical Department, Imperial College of Science and
Technology.*

(Received October 5th, 1927.)

RECENT investigations carried out in this laboratory indicate that gelatin consists of molecules, or aggregates of molecules, which readily undergo intramolecular change. It has been shown, for example, by Knaggs [1923] that if gelatin is hydrolysed rapidly by throwing it into boiling 25 % hydrochloric acid solution, it yields a distinctly smaller fraction of basic products precipitable by phosphotungstic acid than it yields when it has been allowed to stand with the cold acid solution before boiling. This phenomenon has been further investigated by Schryver and Buston [1927], who have found that the increased amount of basic product obtained by treating the gelatin with cold acid before hydrolysis is due mainly to the presence of *dl*-lysine, which cannot be ascribed merely to the racemisation of the *l*-lysine, since the latter occurs along with the optically inactive base in normal (or slightly more than normal) quantities. Thornley [1927] has found that the treatment of gelatin with relatively dilute cold solutions of acids or alkalis can give rise to changes in the amounts of basic products obtained when the sample thus treated is afterwards submitted to rapid hydrolysis with strong acids. Furthermore, Knaggs and Schryver [1924, 1] have shown that when gelatin is heated in water and then hydrolysed by boiling acids in the usual way, there is in the hydrolysis products more nitrogen in the form of non-amino-nitrogen than in those obtained in a similar way from gelatin not previously heated with water—indicating that this comparatively mild treatment causes the formation of stable nitrogenous rings, which are not opened up by subsequent hydrolysis with strong acids.

ELECTROLYSIS OF GELATIN HYDROCHLORIDE AND SODIUM GELATINATE.

In view of the accumulating evidence of the readiness with which structural change takes place within the molecules, it was of interest to ascertain whether gelatin possesses the same structure when functioning as anion and as cation.

Some evidence has been afforded by the investigation of ultra-violet absorption spectra by Baker and Davidson [1925] that two distinct forms of gelatin exist. The experiments recorded in this communication tend to confirm the conclusions drawn by these authors.

For the purposes of the experiments, a gelatin was employed which had been freed from ash and separated from simpler degradation products, which are present in ordinary commercial samples, by flocculation in an electric field [Knaggs, Manning and Schryver, 1923; Knaggs and Schryver, 1924, 2]. The flocculum thus obtained was thoroughly washed on a filter with cold water. Two portions of this were taken and dissolved in water; to one solution hydrochloric acid was added to bring it to p_H 3.0, and to the other sodium hydroxide to bring it to p_H 8.0 or 9.0. The gelatin was precipitated from these solutions by electrolysis, the poles being separated from the gelatin solutions by means of semi-permeable membranes¹.

When the gelatin was deposited cationically by the electrolysis of the hydrochloride, the lower pole of the apparatus was made the cathode; when, on the other hand, it was deposited anionically by electrolysis of sodium gelatinates, the lower pole was the anode. The upper poles were washed with a continuous stream of CO_2 -free water. Electrolysis was carried out with very small currents, which hardly ever exceeded 10 milliamps., and were generally appreciably less. Noticeable heating effects were thereby avoided. The electrolysis was continued until the washings of the upper pole showed no traces of chlorine, or of alkali. At this stage, with a potential fall of 20–30 volts per centimetre, the current passing had usually fallen below 1 milliampere.

The difference between the appearance of the gelatin deposited cationically and that deposited anionically was extremely well marked. The former separated as a compact, almost transparent gel on the collodion membrane, from which it could be peeled off as a single solid mass by a knife. The gel occupied only a relatively small bulk of the whole system, and the supernatant liquid was water-white and clear; it contained only a small amount of nitrogen, which amounted to about 3.5 % of the total originally present in the solution. The gelatin deposited anionically formed, on the other hand, a bulky flocculum extending from one-half to two-thirds of the way up the cylinder, while the clear liquid in which this flocculum was suspended was relatively rich in nitrogen, containing nearly 18 % of the total. (See Experimental Details, Series A.)

By the electrolysis of sodium gelatinates, therefore, a considerable portion of the nitrogen remains unprecipitated, and two distinct fractions are thus obtained, *viz.* a soluble and an insoluble.

¹ The apparatus employed was similar to that figured in the *Biochem. J.* 1924, **18**, 1082. Simple cylinders were used instead of bell-jars, and a number of such units were placed either in series or in parallel, so that several experiments could be carried out at one time. By a suitable arrangement of plugs and switches the current passing through any unit could be measured when required. Platinum electrodes were employed in all cases.

The insoluble ana-fraction.

The insoluble fraction, provisionally designated insoluble ana-gelatin, carries down with it a certain amount of the soluble fraction—soluble ana-gelatin—which at the conclusion of the electrolysis is not distributed evenly throughout the liquid, but tends to pass with the insoluble fraction towards the anode. Most of the soluble portion is, however, readily removed from the insoluble ana-gelatin by washing. If the latter be shaken thoroughly with ice-cold water, and the mixture be then centrifuged, a certain amount of nitrogen will be found in the supernatant liquid. If these processes of washing and centrifuging be repeated several times, it will be found that the nitrogen in the supernatant fluid rapidly diminishes with successive treatments until after three or four such treatments it becomes approximately constant, amounting to about 3 mg. per 100 cc. of the liquid. This must be taken as a measure of the solubility of this fraction in water, and it indicates that this so-called insoluble fraction is soluble in water to the extent of about 15 parts in 100,000. (See Experimental Details, Series B.)

The soluble portion removed by these washings may not represent the total amount of gelatin in the soluble form, since a part of this remains attached to the insoluble, and can only be separated from it by repeated flocculations from neutral or alkaline solution. Probably it is enclosed within the particles, from which it is only set free by repeated complete dispersions in water.

If the insoluble fraction, freed as above from the soluble product, be dissolved in water, and flocculated in an electric field, it separates out readily as a bulky flocculum. The nitrogen remaining in the supernatant fluid, however, even after repeated flocculations, is appreciably higher than that due to the actual solubility of this fraction when freed from the soluble ana-gelatin (*i.e.* about 3 mg. nitrogen per 100 cc.). (See Experimental Details, Series C.) The insoluble product was also converted into the sodium salt and into the hydrochloride, and separated again from the solution of these salts by means of electrolysis. In both cases it was precipitated in the form of a flocculum. When separated from the solution of the hydrochloride, the nitrogen remaining in the supernatant liquid was lower—when separated from the sodium salt, higher—than the nitrogen remaining in the supernatant fluid when the unionised product was flocculated. In all cases, however, it was higher than 3 mg. per 100 cc. (See Experimental Details, Series A, Part 2.)

These facts seem to the authors to have a definite significance. In an earlier paper of this series [Knaggs, Manning and Schryver, 1923] it was found that gelatin after being freed from inorganic salts readily separated from dilute solution as a flocculum. After repeated separation from solution (“recrystallisation”) the nitrogen in the supernatant fluid became constant, and it was assumed at the time that a product had been obtained which was in equilibrium with its saturated solution. Certain facts, however, militated against this

assumption. It was found that, if a solution were prepared containing enough gelatin for saturation and this were concentrated at low temperatures to a small bulk, the gelatin did not always separate, as it would have been expected to do from a supersaturated solution. This was especially the case if the saturated solution had been allowed to stand a day or two before concentration.

These facts indicate that "insoluble" gelatin cannot be dispersed in water at 25–30° without undergoing a certain amount of change and of conversion to the soluble form, and Manning [1924] showed that the most highly purified gelatin obtained up to the time of his work underwent a distinct irreversible change at a slightly higher temperature (37°) which was readily revealed by viscosity measurements. In the experiments described in detail later (Series A, Part 2 and Series C) it would appear that, on dispersion in water at 30°, from 3–5 % of the insoluble ana-gelatin is converted into a soluble non-flocculable form.

The soluble ana-fraction.

This was obtained by concentration of the supernatant fluid and washings from the anionic flocculation at room temperature. No gel was obtained, but a thick syrupy solution, from which the protein could be obtained by means of acetone as a white granular powder. (See Experimental Details, Series D.) This is a substance of high molecular weight, 50,000–60,000, which appears to vary slightly with the concentration [cf. Horne, 1924]. (See Experimental Details, Series E.)

The protein is readily precipitated from the syrup by saturated ammonium sulphate. Precipitation commences at 28.5 % saturation, and is complete at or about 50 % saturation. Its solution normally possesses a p_H of 4.8, which is probably its isoelectric point, whereas the p_H of the suspension of the insoluble product was 5.8. The latter could be dried in the form of sheets, not distinguishable at first sight from those of ordinary gelatin. (See Experimental Details, Series F.)

Attempt to resynthesise a gel from soluble and insoluble ana-gelatins.

It was thought that it might be possible to obtain a gel by recombination of the soluble and insoluble ana-gelatins, since neither fraction alone was in the form of a gel. These were accordingly mixed in the proportions in which they were obtained by the electrolysis of their sodium salts as above, and the solution of the mixture was dried down into a sheet at room temperature. The sheet was redissolved in water, and to the solution hydrochloric acid was added to bring it to p_H 3.0. The gelatin was then separated cationically by electrolysis. It did not, however, come down in the form of a gel, but as a flocculum. The supernatant fluid, furthermore, contained the same amount of nitrogen as would have been found in that from (a) the electrolysis of the hydrochloride of the insoluble fraction alone, plus (b) the nitrogen of the added amount of soluble fraction. There is no evidence, therefore, that the soluble

and insoluble ana-gelatins can be made to recombine to form a gel. Now certain other facts have been discovered, which offer an explanation of this negative result.

It was found that the cata-gelatin gel, obtained by the electrolysis of the hydrochloride, gave on hydrolysis a diamino-nitrogen value of about 29. The corresponding number for the insoluble ana-gelatin was 23.5, while that for the soluble ana-gelatin was found to be 19. These numbers indicate, therefore, that the molecules in the ana- and cata-gelatins possess a different structural arrangement, and thus the cata-gelatin gel is not a simple combination of the soluble and insoluble ana-fractions. (See Experimental Details, Series H.)

THE RELATIONSHIP OF THE SEPARATED PROTEINS TO ONE ANOTHER,
AND THE MECHANISM OF GEL FORMATION.

Proteins yield on hydrolysis in many cases single amino-acids in very small amounts. If these are formed from a single kind of molecule, or from aggregates of the same kind of molecules, the latter must be of very large size. It is conceivable, however, that proteins may be made up of aggregates of different kinds of molecules, each with a skeletal polypeptide structure, held together in some form of loose combination. Many attempts, which need not be discussed here in detail, were made to separate pure gelatin into such constituents, by its submission, after various treatments, to the action of an electric field. It is possible that by the electrolysis of the sodium salts as described the scission of gelatin has been effected into constituent proteins (which may have undergone intramolecular change during the process) which have no known relationship to one another, beyond their association together to form the gelatin complex.

There is, however, another possible explanation of the results, which needs discussion, according to which the two proteins obtained by the electrolysis of sodium gelatinate are much more intimately related to one another. Before dealing with this possibility, however, it is necessary to digress for a moment in order to discuss the effect of heating gelatin with water.

When gelatin is warmed with water, it undergoes an irreversible change, and some experiments, quoted above, indicate that this takes place to a small extent when a flocculated gelatin is dissolved, or rather dispersed, in water. Hitherto, it has been generally assumed that this change is of a degradative nature, accompanied by the scission of some of the polypeptide linkages. Some colour is given to this assumption by experiments recorded by various authors, and by the fact that commercial preparations of gelatin contain simple nitrogenous constituents which readily pass through the membranes used for dialysis. A change into simpler nitrogenous products readily takes place when the gelatin samples have not been completely freed from salts, and also occurs during its preparation on an industrial scale from its precursors, which, before the extraction process, have been submitted to the action of

fairly strong acids or alkalis, which are not completely removed by subsequent washing with water. (See Experimental Details, Series A, Part 2.)

Now experiments carried out in this laboratory on an ash-free gelatin, which had been separated from simple nitrogenous products by flocculation in an electric field followed by thorough washing of the flocculum, indicate that the irreversible change produced by heating with water is not of the degradative character mentioned. The authors are indebted to Dr A. B. P. Page for these experiments. (See Experimental Details, Series K.)

It was found that in the case of a 2 % solution of a purified gelatin which had been boiled for 22 hours under a condenser—a treatment which produces a profound change in its properties—no evidence of peptide scission could be detected, either by the Foreman method of titration in alcohol, or by Van Slyke's nitrous acid method. When, however, Sørensen's formaldehyde method was employed, and the titration was carried out electrometrically, it was found that the heated gelatin solution required a very small amount more alkali to bring the E.M.F. to 650 millivolts than did the unheated portion. If this slight excess required be ascribed to the scission of peptide linkages, then the nitrogen involved in this process amounts to distinctly less than 1 % of the total, and it is extremely improbable that this just detectable change can account for the marked changes in the properties (such as solubility, flocculability, etc.) of the solution.

A similar conclusion was arrived at by an entirely different series of experiments. A gelatin solution which had been boiled for 5 hours (during which period the greater part of the viscosity change had taken place) was submitted to fractional dialysis. This was carried out in hollowed ebonite cylinders, which were clamped together at their flattened edges, between which was secured a collodion membrane, which thus separated the two cylinders. Into one cylinder was introduced the heated gelatin solution, and into the other water. Arrangements were made to secure a difference between the pressures on the two sides of the membrane, to accelerate the rate of dialysis and prevent dilution of the gelatin solution. A membrane of small permeability, softened by the method of Brown [1922] in 60 % alcohol, was first used, and dialysis was continued until no further nitrogen could be detected in the dialysate. The membrane was then replaced by a more permeable one (soaked in 80 % alcohol). After completion of a second dialysis, the heated gelatin solution was submitted to a third, using a membrane soaked in 90 % alcohol, the most permeable collodion membrane which can be manipulated without difficulty. As a result it was found that only minute traces of nitrogen passed the membranes, even when the most permeable one was employed. It appears, therefore, as a result of these experiments, that the irreversible change in gelatin produced by the action of water is not due to peptide scission, but to the change into a soluble, non-gelling, complex protein.

In the literature the term "meta-protein" has been suggested for natural

proteins which have undergone some change during "denaturation," such as coagulated egg-albumin. This term may be conveniently retained to include products which have been obtained from proteins without measurable peptide scission. The products obtained by heating with water a purified gelatin may therefore be designated "meta-gelatins."

To revert now to the discussion of the explanation of the relationship between the two protein fractions, soluble and insoluble, of gelatin. Evidence has been given which indicates that a certain amount of meta-gelatin is produced when a flocculated gelatin is dispersed in water at 30°. If one assumes the micellar structure for gelatin, then it is conceivable that during the dispersal process, the peripheral part of the micellar structure undergoes change into the soluble meta-gelatin. When the changed micellae are sufficiently close together, the outer layers of meta-gelatin could form a continuous phase and thus produce a gel, as shown in the diagram.

On cooling dilute solutions, however, the unchanged gelatin would separate as a flocculum, whereas the greater part of the meta-gelatin would remain dissolved in the water-phase, a small amount being also carried down with the flocculum. If this view is correct, a more complete separation of the gelatin and meta-gelatin takes place after electrolysis of the sodium salts than after electrolysis of the acid or neutral solution. The products provisionally called insoluble and soluble ana-gelatin would therefore be simply gelatin and meta-gelatin, which have undergone intramolecular change during the electrolysis

of the solution of their sodium salts¹. In the cata-form, the soluble and insoluble fractions appear to be in some form of combination, possibly due to the presence of the free amino-group of *dl*-lysine in the insoluble fraction (*vide supra*, p. 1284) and the somewhat acidic character of the soluble meta-gelatin.

The data at the moment available are not sufficient for determining which of the above explanations of the relationship of soluble ana-gelatin to insoluble ana-gelatin is correct. By the employment of the experimental methods described above, it may, however, be possible to arrive at a definite solution of the problem. By heating gelatin with water for a relatively short time, it is possible to convert a small part of the gelatin into meta-gelatin. The two fractions could then be separated either by flocculation in an electric field or by electrolysis of their salts. The floccula or gels thus obtained could then be heated again and a further fraction of soluble product obtained. This process could be repeated until no more insoluble fraction remains. By systematic investigation of the soluble fractions it should be possible to ascertain whether gelatin is made up of several different proteins, or whether the insoluble gelatin consists mainly of one class of molecules, which by the action of hot water are converted by stages into the soluble form. Work on these lines is now proceeding.

The authors, before concluding, would like again to draw attention to the importance of considering the intramolecular changes which take place so readily when gelatin is submitted to mild treatment. They are of the opinion that the ordinary physico-chemical methods, the results of which have been interpreted on the assumption that gelatin is simply a colloidal ampholyte, are not, by themselves, sufficient to explain the various properties, including gel formation, of this product.

EXPERIMENTAL DETAILS.

Series A. Part 1.

Cationic flocculation. 3.5 g. of gelatin, freed from ash by washing and electro-dialysis and freshly flocculated from 1.5 % neutral solution, were washed

¹ The view that gel formation is due to the presence of soluble and insoluble products is, of course, not new, though the above method of presentation probably is. The view has recently been subjected to experimental investigation by Northrop and Kunitz [1926]. They claim to have partially separated gelatin, purified by Loeb's method, into fractions differing in their solubilities in water. The authors of this paper are of opinion that the methods adopted by Northrop and Kunitz are open to criticism on various grounds. In the first place, their own experiments indicate that a gelatin, purified by Loeb's method, still contains sufficient degradation products to account for almost the whole of their soluble fraction. (See also Experimental Details, Series A, Part 2.) Secondly, the repeated solution of their precipitates of the more insoluble fraction in water at 32° must result in the partial conversion of the more insoluble fraction of the gelatin into the more soluble. It is probable that the two fractions obtained by these workers represent two different mixtures of soluble and insoluble gelatin, more or less contaminated with degradation products. A much more convenient method of separating gelatin into soluble and insoluble fractions has been described in previous papers of this series, which have been completely ignored by Northrop and Kunitz.

on the filter and made up to 1.5 % solution by warming at 40°. The solution was brought to p_H 3.0 with HCl and submitted to a potential difference of 200 volts in the apparatus previously described. After 6 days no further acid could be detected in the anode liquor and the current passing was 0.2 milli-amp. The nitrogen in the solution was found to vary from a very low value at the top to 4.4 mg. per 100 cc. towards the bottom of the vessel. The bulk of the gelatin was precipitated as a hard clear gel on the lower membrane, about 1" thick. This cake was broken up and the solid filtered off.

N in supernatant liquid (200 cc.)	...	...	6.8 mg.	} Total soluble N = 13.1 mg.
N in filtrate from broken solid (30 cc.)	...	...	6.3 mg.	
N in original solution	...	...	380.0 mg.	
Hence N not precipitated	...	...	3.5 % of total N	

Anionic flocculation. A similarly prepared solution was brought to p_H 8.0 with KOH, by titration. An apparatus completely enclosed was used in order to avoid absorption of CO₂ from the air by the alkaline solution, freshly boiled distilled water being employed throughout for the same purpose. After 24 hours under a P.D. of 200 volts a bulky white flocculum was precipitated, and after 4 days no further alkali could be detected in the cathode liquor. The flocculum was filtered off and the nitrogen determined in the solution.

N in supernatant liquid (125 cc.)	...	29.0 mg.	} Total soluble N = 54.6 mg.
N in filtrate from flocculum (100 cc.)	...	25.6 mg.	
N in original solution	...	310.5 mg.	
Hence N not precipitated	...	17.7 % of total N	

Thus from the acid solution almost the whole of the gelatin is obtained as a clear gel, while from the alkaline solution a considerable portion of the nitrogen remains unprecipitated and the rest is obtained as a flocculum.

Series A., Part 2.

Flocculations of crude gelatin. A series of flocculations was carried out on samples of unpurified gelatin with a view to determining whether (a) separation into two fractions by anionic flocculation, and (b) precipitation as gel by cationic flocculation took place. The proportion of nitrogen of true soluble protein to the nitrogen merely due to soluble breakdown products was also investigated.

A sample of gelatin which had been freed from ash by washing and electrodialysis, but not by flocculation, was separated by electrolysis from acid (p_H 3), alkaline (p_H 9), and neutral solutions; the results after 5 days are given in Table I.

Table I. *Unflocculated ash-free gelatin.*

p_H of original solution (colorimetric measurement)	Type of precipitate obtained	Total N in solution mg. per 100 cc.
5.0	Bulky flocculum	36.4
3.0	Gel + slight flocculum	33.6
9.0	Flocculum (less bulky)	39.7

Thus, using the crude material, a gel may be obtained by means of cationic flocculation, but the soluble nitrogen is high in all cases. Further experiments show that this is due to the presence of diffusible degradation products.

Some Coignet's "Gold Label" gelatin was flocculated directly from a 1.5 % solution at p_H 3.4, the outside of both membranes being washed very completely with a stream of freshly boiled water. After 4 days a clear gel was precipitated and after 9 days the current had fallen nearly to zero. The thick layer of approximately 10 % gelatin gel was removed and the N determined in the supernatant and wash-liquids.

Table II. *Coignet's "Gold Label" gelatin.*

	mg.	% of total N
Total N in supernatant liquid ...	44.7	7.15
Total N in outer liquid at cathode	9.4	1.50
Total N in outer liquid at anode	19.3	3.09
Hence total soluble N ...	73.4	11.74
And total diffusible soluble N ...	—	4.59

Thus, in the case of crude gelatin, the true soluble ana-gelatin is accompanied by an amount of diffusible degradation products, the proportion of which approximates to 4.6 % [cf. Northrop and Kunitz, 1926]. These substances remain in solution equally when the gelatin is precipitated anionically or cationically, the slight differences observed above being due to the soluble ana-gelatin itself. After flocculation, however, the bulk of the nitrogen remaining in solution is due to the soluble fraction, the diffusible products representing only 0.5 % of the total. Further flocculations reduce this to zero.

The gel obtained from flocculation of the crude gelatin was reflocculated from acid and alkali; the results (Table III), which are typical, show the reduction in the diffusible nitrogen effected by the second flocculation, and also the difference between the quantities of soluble nitrogen in the case of anionic and cationic flocculations.

Table III.

	Reflocculation of gelatin from alkaline solution			Reflocculation of gelatin from acid solution		
	mg. N per 100 cc.	Total N mg.	N %	mg. N per 100 cc.	Total N mg.	N %
N in supernatant liquid and filtrate	18.7	44.88	7.51	11.2	25.76	4.48
N in outer liquid at anode ...	—	0.95	0.38	—	1.60	0.64
N in outer liquid at cathode ...	—	1.08	0.43	—	Trace	—
Total diffusible N ...	—	2.03	0.81	—	1.60	0.64

Further flocculations of purified gelatin. Similar results were obtained from the large-scale experiments in which the soluble ana-gelatin was prepared. The freshly washed flocculum, corresponding to 36 g. of gelatin, was dissolved at 37°, and made up to 2½ litres. The solution was brought to p_H 9.0, and then electrolysed for 5 days, the current eventually falling to about 1 milliampere. Both poles were kept washed and the liquids afterwards acidified and evaporated down.

Table IV.

	mg. N	% of total N
Total N (approx.)	6000.0	—
N passing anode membrane	19.4	0.36
N passing cathode membrane	9.7	0.16
N in supernatant liquid ...	799.3	13.32

A part of the 0.52 % diffusible nitrogen obtained here and in other experiments on purified gelatins is probably due to the membranes, which are usually found to be slightly permeable at the commencement of an experiment. Lower values are obtained with older membranes.

An additional experiment may be quoted here to illustrate the effect of the p_H on the result of the flocculation. The gelatin used had been freed partially from the soluble fraction by flocculating twice from neutral 1.5 % solution. It was thoroughly washed on the filter, pressed and reflocculated from neutral, acid, and alkaline solutions by redissolving as quickly as possible at about 30° and instantly electrolysing. The nitrogen in the total liquid was determined after 5 days, the precipitate being centrifuged off in the usual way.

Table V.

Original p_H of solution	Total N mg. per 100 cc.	Type of precipitate	N in solution mg. per 100 cc.
5.0	127.2	Bulky flocculum	9.8
3.0	140.0	Clear weak gel	7.4
9.0	146.1	Flocculum (less bulky)	11.3

Thus cationic precipitation seems to cause the two separate fractions to remain held together, whereas in alkaline solutions they tend to separate. Neutral solutions occupy an intermediate position. If now from the values for nitrogen in solution, given above, be subtracted an amount representing the actual solubility of the insoluble fraction the determination of which is given below (Series B), 4.4 mg. per 100 cc., or 3.5 % of the total nitrogen, is found to be the smallest percentage of nitrogen converted to the soluble form by the act of dispersing in water and warming. The neutral and alkaline solutions yield values of 4.9 and 5.7 % respectively.

Series B.

Solubility of the "insoluble" fraction. The residual flocculum from the anionic flocculation described under Series D, representing 87 % of the gelatin, was pressed on the filter and washed thoroughly to be as free as possible from the soluble ana-gelatin.

10 g. of the flocculum (7.5 % gelatin) were shaken for 45 minutes with 10 times the volume (100 cc.) of ice-cold freshly boiled distilled water. The whole mass was centrifuged and the slightly opalescent liquid filtered and the nitrogen determined therein. The residual substance, still containing small lumps unbroken by the shaking, was again shaken with 10 volumes of water and centrifuged, and this process was repeated until an approximately constant value for the nitrogen extracted on each shaking was reached.

Table VI. *Soluble N extracted by shaking with cold water.*

First shaking	23.8 mg. N per 100 cc.
Second "	14.0 "
Third "	3.6 "
Fourth "	2.9 "
Fifth "	3.4 "
Sixth "	2.5 "

Apart from slight irregularities due to the difficulty of completely removing the finely suspended solid from the clear solution, these figures show an approximately constant solubility, after three extractions with water, of 2.5–3.0 mg. N per 100 cc., corresponding to 15 parts of gelatin in 100,000.

Series C.

Further flocculation of the insoluble fraction (ana-gelatin). The previous determination of the solubility of gelatin [Knaggs, Manning and Schryver, 1923; Manning, 1924] was based on the nitrogen remaining in solution in the supernatant fluid after repeated flocculations. This figure, 48 parts per 100,000, cannot be regarded as accurate, since the work recorded in the previous section shows that the bulk of the soluble nitrogen is in the liquid immediately surrounding the flocculum, and not diffused equally throughout the supernatant fluid. The following determinations were therefore made on the whole liquid.

The insoluble residue after six extractions with water was warmed to 40° for 2 minutes in 30 cc. water, and cooled instantly. The opaque liquid was at once flocculated. Within 30 minutes a precipitate had formed, and after 2 days' electrolysis the heavy white flocculum was centrifuged off and the nitrogen determined in the filtered liquid.

Nitrogen in solution after flocculation 13.2 mg. per 100 cc.

By repeated flocculation, however, the soluble nitrogen can be reduced to a lower limit than the above. Thus 11 g. flocculum were made up to 33 cc. in water at 37° and flocculated repeatedly. A more and more bulky flocculum was obtained each time, and eventually a constant value for the soluble nitrogen was obtained.

Table VII.

	Time of flocculation (hours)	Soluble N mg. per 100 cc.
First flocculation	48	26.3
Second "	96	11.2
Third "	48	12.2
Fourth "	96	8.8
Fifth "	48	8.1

Longer periods of flocculation lead to the attainment of the equilibrium in fewer operations.

Table VIII.

	Time of flocculation	Soluble N mg. per 100 cc.
First flocculation	48 hours	22.6
Second "	7 days	14.4
Third "	5 "	6.8
Fourth "	3 "	6.8

These numbers are only about one-half that for the nitrogen left in solution after flocculating the material which had been thoroughly extracted with water, and this fact seems to indicate that a part of the soluble fraction is enclosed within the micellae, is not removed by extraction with water and can only be set free on dispersion.

This smallest number, 6.8 mg. per 100 cc., is greater than that obtained by the simple extraction with water of the washed flocculum. If the latter number (2.5 mg. per 100 cc.) be subtracted from the former, a figure should be obtained which would give a measure of the amount of insoluble gelatin converted to the soluble form (*vide supra*, p. 1287) on dispersing in water at 37°, namely, 4.3 mg. per 100 cc., or 3.7 % of the total nitrogen. Reference may be made to experiments at the end of Series A, Part 2, which confirm approximately this calculation, the value there given being determined for 30°, and therefore slightly lower than the above.

The very slight irregularities in the final numbers may be ascribed to:

- (a) different times of flocculation;
- (b) variation in the resistance of the membranes and of the whole system, and therefore of the current density applied;
- (c) temperature effects, the outside temperature varying over a range of 5°.

Series D.

Isolation of the soluble fraction. 45 g. of purified gelatin, freed from ash, were flocculated from water once, and the white flocculum filtered and washed with water. Three litres of 1.3 % solution were then made up by warming and brought to p_H 9.0 with KOH, 0.4047 g. being required. This solution was then flocculated, the apparatus being enclosed and the cathode being kept washed to remove alkali. The voltage was slowly raised from 50 to 200 volts, as the resistance of the solution increased, an average current of about 4.5 milliamperes being passed. After 10 days no further alkali could be detected in the cathode washings; the flocculation was therefore stopped, the clear supernatant liquid removed as completely as possible, and the flocculum filtered on paper and washed. The supernatant liquid and filtrate combined showed a nitrogen content of 16.1 mg. per 100 cc., or a total of 480 mg. of soluble nitrogen. Washings from the precipitate contained a further 17 mg. nitrogen. The bulky precipitate was pressed on a Büchner funnel to remove as much as possible of the soluble fraction adhering, and the filtrate liquids, totalling 2.9 litres, were then evaporated to 60 cc. at ordinary temperature, by means of a fan. The resulting clear syrup was poured slowly into 8 volumes (500 cc.) of absolute acetone, stirred thoroughly, and after standing overnight, stirred, filtered, stirred up with a further small quantity of acetone and again filtered. This process was repeated three times. Finally, the precipitate was sucked dry, transferred to a porous tile and dried *in vacuo* for several days.

A dull white granular powder was thus obtained; it was only very slightly

hygroscopic when thoroughly dried, and dissolved in water to a clear pale yellow solution, without warming. It charred on heating, without melting. It was completely precipitated by ammonium sulphate solution, the precipitation limits being between 28.5 and 50 % saturation.

Series E.

Osmotic pressure determinations. Sac membranes of necolloidine were prepared, and soaked in 60 % aqueous alcohol before use [Brown, 1922]. A rapid rise was observed, reaching a maximum in 1–3 days, and afterwards a slow fall. If started above the constant value, a rapid fall was observed, reaching the constant value and remaining there for some days, followed by a slight further fall.

Table IX.

N in final solution mg. per 100 cc.	Constant osmotic pressure (mm.)	Temperature °C.	Molecular weight
223.2	64.0	20.5	53,300
287.2	76.0	18.5	57,400
302.4	74.5	17.0	61,600

This molecular weight, although varying slightly with concentration [cf. Horne, 1924], is definitely that of a complex protein.

Series F.

Hydrogen ion concentration determinations. In general, solutions of soluble ana-gelatin are more acidic than those of the insoluble portion. The p_H of the syrup from the anionic flocculation was found to be 4.1 and 4.2 respectively, in two preparations. These may have been too acid owing to traces of CO_2 in solution. A quantity of the syrup, diluted with three-quarters of its volume of boiled water, was therefore electrolysed for 3 days till all traces of electrolyte were removed; the resultant solution had a p_H of 4.8. This probably represents the isoelectric point of the soluble ana-gelatin.

The electrometric buffer-titration curve is fairly smooth. It shows a slight point of inflection at p_H 4.8, but no obvious inflection at p_H 7.7 [cf. Wilson and Kern, 1922, 1923].

The p_H of solutions of insoluble ana-gelatin varied from 5.6 to 6.8, and of the flocculum itself from 5.1 to 6.5. A quantity of the substance, freshly flocculated from alkaline solution, was mixed with water without dissolving and electrolysed for 3 days till all traces of electrolyte were removed. The p_H of the precipitate, determined colorimetrically by spreading out on a watch-glass with the indicator, was then 5.8, and of the supernatant liquid 6.1. Probably 5.8 represents the fairest value of the isoelectric point of insoluble ana-gelatin.

It should be noted, parenthetically, that the p_H of the solution after electrolysis of a crude gelatin corresponds with that of the soluble fraction, which is present in large amount, while the p_H of the solution after electrolysis of a purified sample approximates to 5.8, the isoelectric point of the insoluble fraction.

Series G.

Attempt to resynthesise a gel from soluble and insoluble ana-gelatins. To a quantity of the insoluble ana-gelatin some of the syrupy solution of the soluble fraction was added, in such proportion that the added nitrogen was equivalent to 12 % of the total nitrogen in the mixture, this corresponding to the proportion of the soluble ana-gelatin present after anionic separation. The mixture was melted at 37°, and on cooling a fairly clear gel was produced, which was cut up and dried down in the cold, redissolved, made up to p_H 3.0, and flocculated. After 6 days the current had fallen to 0.5 milliamperes and the p_H of the anode liquid was 4.5. The compact flocculum obtained was centrifuged off. The nitrogen in solution showed no recombination.

Table X.

Soluble N calculated						mg. per 100 cc.	
Due to added soluble ana-gelatin						...	13.5
Due to insoluble ana-gelatin, corresponding to second flocculation						...	14.4
(see Series C)						...	27.9
Total						...	30.4
Soluble N found						...	

The agreement is sufficiently close to leave no doubt that the two fractions, once separated, do not recombine to form a gel.

*Series H.**Hausmann numbers of the fractions.*

Soluble ana-gelatin. The nitrogen distribution was determined by the micro-method previously described [Thimann, 1926] both on the concentrated syrup before precipitation and on the dried and powdered soluble substance. Close agreement was observed, as the following numbers show, so that the precipitation by means of acetone does not appreciably affect the product. Furthermore, standing with acid in the cold before hydrolysis causes no increase in the basic nitrogen [cf. Knaggs, 1923]. The third set of numbers in the table was obtained after allowing the powder to stand for 24 hours in 18 % HCl.

Table XI.

	Amide-N	Humin-N	Diamino-N	Mono- + non-amino-N	Total N
Syrup	2.8	0	19.2	77.3	99.4
Powder	3.3	Trace	19.3	77.5	100.1
Powder (stood in acid)	3.3	0	18.3	78.4	100.1

In each case these represent the mean of at least two determinations.

Insoluble gelatins. The original flocculum from the anionic flocculation contains still some soluble fraction, as was shown above, but this amounts only to a small percentage of the total, and hence should not greatly affect the hydrolysis numbers. A slight increase in the amide-nitrogen of the unwashed gelatin may be due to the soluble fraction present. The cata-gelatin gel shows, however, a higher figure than either, pointing to structural difference. The insoluble ana-gelatin is more labile than the soluble,

since on standing in 18 % acid before hydrolysis, the basic nitrogen is definitely increased.

Table XII.

	Amide-N	Humin-N	Diamino-N	Mono- + non- amino-N	Total N
Precipitate from flocculation in alkaline solution	1.8	0	23.2	75.3	100.3
Ditto, after six washings	1.6	0.1	23.5	74.9	100.1
Ditto, after standing 24 hours in 18 % HCl	1.5	0	25.9	72.7	100.1
Cata-gelatin gel	1.5	0	29.2	69.2	99.9

Two differences are thus observed between the soluble and insoluble ana-fractions; the amide-nitrogen, which is nearly twice as high in the former case, and the diamino-nitrogen, which is 4 % higher in the latter. The insoluble cata-gelatin has the same amide-nitrogen as the insoluble ana-gelatin, but a higher diamino-nitrogen than either of the ana-gelatins.

(In experiments upon the effect of acid and alkali treatment of the precursor of gelatin, it was found that the diamino-nitrogen of the precipitated portion, after alkali treatment, was 24.7, and of the supernatant liquid (corresponding with the soluble fraction) about 18 %. These numbers show close agreement with those above, which may thus give a clue to the effect of precursor treatment [Knaggs and Schryver, 1924, 3].)

Series K. (Experiments by Dr A. B. P. Page.)

Effect of heat treatment of purified gelatin. Within the somewhat large limits of error in the Van Slyke method for determination of amino-nitrogen there was no change in the amino-nitrogen after heating for 20 hours at 100°.

Electrometric formaldehyde titration. The heated gelatin was diluted 1 : 1 before titration. Titrations were then made until the E.M.F., using a hydrogen electrode, reached 650 millivolts—the limit beyond which the electrodes became unreliable in the presence of formalin.

Titre of the 25 cc. formalin	2.95 cc. NaOH
Titre of 25 cc. unheated 2 % gelatin	9.25 — 2.95 = 6.3 cc. NaOH
Titre of 25 cc. unheated 1 % gelatin	3.13 „
Titre of 25 cc. heated 1 % gelatin	6.50 — 2.95 = 3.55 „
Hence difference due to heating	0.42 „
This is equivalent to	0.29 mg. nitrogen
25 cc. heated 1 % gelatin contained	42.0 „
Hence % increase of amino-N on heating a 2 % solution for 21 hours at 100°	... 0.69 %

Fractional dialysis. 300 cc. of a 1.85 % solution of a once flocculated gelatin were heated for 5 hours at 100°. 200 cc. were used for dialysis. The collodion membranes were poured on a glass plate from 5 % alcohol-ether solution of necolloidine, and covered with a Petri dish. They were air-dried, soaked overnight in alcohol of the required strength and finally washed for 3 or 4 hours in frequent changes of distilled water.

Two or three changes of dialysis water were made with each membrane, and the nitrogen determined in each. The amount of nitrogen which diffused in the time, and its percentage of the total nitrogen are given below.

Table XIII.

Membrane soaked in	Time of dialysis (hours)	Total N diffused (mg.)	% of total N
60 % alcohol	21	0.39	0.06
	Subsequent 67	0	0
	„ 89	0	0
	Total 177	0.39	0.06
80 % alcohol	16	2.0	0.32
	Subsequent 40	0.5	0.08
	„ 84	0.4	0.06
	Total 140	2.9	0.46
90 % alcohol	25	0.75	0.12
	Subsequent 41	0	0
	Total 66	0.75	0.12

Hence the total nitrogen diffused in 383 hours = 0.64 %. This agrees with the change in amino-nitrogen, and also with the diffusible nitrogen found for purified gelatin in Series A, Part 2.

SUMMARY.

1. Evidence has been given to show that the molecules, or aggregates of molecules, of which gelatin is composed readily undergo intramolecular change.

2. This evidence suggested the possibility that the intramolecular arrangement was different according to whether gelatin was functioning as anion or cation.

3. By the electrolysis of the hydrochloride, gelatin was obtained in the form of a gel, with very little nitrogen in the supernatant fluid. By the electrolysis of the sodium salt, two fractions were obtained, *viz.* an insoluble fraction (insol. ana-gelatin) and a soluble fraction (sol. ana-gelatin). Both were complex proteins. Insoluble ana-gelatin is soluble in water to the extent of about 15 parts in 100,000 at 15°; soluble ana-gelatin has a molecular weight of 50,000–60,000.

4. Attempts were made to resynthesise a gel by combination of the soluble and insoluble ana-gelatins, but without success.

5. Two possible relationships between the soluble and insoluble proteins into which gelatin is separated on electrolysis of the sodium salt are suggested:

(a) that they are independent proteins having no relationship to one another other than their association together in the gelatin complex;

(b) that the soluble fraction is a product of the action of water on an insoluble gelatin. The combination of a soluble and insoluble fraction in some form is responsible for the gel formation.

On electrolysis of the sodium salt the two fractions separate, undergoing in the process intramolecular change, which prevents their recombination.

6. Evidence is given to show that by the action of water on gelatin a product is produced which is a highly complex protein, and that the change is not accompanied by any appreciable amount of peptide scission. For the changed gelatin the term *meta-gelatin* is suggested. If the second of the above conceptions is correct, the gel called cata-gelatin is a close combination of gelatin and meta-gelatin, which separate on electrolysis of their sodium salts, undergoing at the same time an intramolecular change. There is also evidence that insoluble gelatin cannot be dispersed in water without undergoing a slight irreversible change and conversion to a soluble form.

The authors are much indebted to Dr Mastin for help in the earlier stages of this work, and also to the Adhesives Committee of the Department of Scientific and Industrial Research, through whose agency the services of Dr Mastin were made available. One of the authors (K. V. T.) is also indebted to the Department for a studentship.

REFERENCES.

- Baker and Davidson (1925). *Nature*, **116**, 172.
Brown (1922). *Ann. Bot.* **36**, 433.
Horne (1924). *Biochem. J.* **18**, 1107.
Knaggs (1923). *Biochem. J.* **17**, 488.
Knaggs, Manning and Schryver (1923). *Biochem. J.* **17**, 473.
Knaggs and Schryver (1924, 1). *Biochem. J.* **18**, 1102.
——— (1924, 2). *Biochem. J.* **18**, 1079.
——— (1924, 3). *Biochem. J.* **18**, 1095.
Manning (1924). *Biochem. J.* **18**, 1085.
Northrop and Kunitz (1926). *J. Gen. Physiol.* **10**, 161.
Schryver and Buston (1927). *Proc. Roy. Soc. London, B*, **101**, 519.
Thimann (1926). *Biochem. J.* **20**, 1190.
Thornley (1927). *Biochem. J.* **21**, 1302.
Wilson and Kern (1922). *J. Amer. Chem. Soc.* **44**, 2633.
——— (1923). *J. Amer. Chem. Soc.* **45**, 3139.