XLVI. ON THE DETERIORATION OF COTTON ON WET STORAGE.

BY NANCY FLEMING AND AAGE CHRISTIAN THAYSEN.

From the Bacteriological Laboratory of the R.N. Cordite Factory.

(Received April 30th, 1921.)

THE bacterial decomposition of raw cotton on wet storage has for some considerable time been under investigation at this laboratory. A preliminary account of the progress of this investigation was published in this *Journal* about a year ago [1920]. As further material bearing on the subject has now been collected, a more detailed account appears justifiable.

It has already been pointed out that an intimate connection exists between the amount of moisture in a raw cotton and the rate of development of the bacteria present, and further, that a moisture content of 9 %, or less, is insufficient to allow bacteria to develop, so that a dry raw cotton will be protected against the action of bacteria. That this is so is shown in Table I where a sample of good Indian raw cotton with low moisture content and containing a fair number of bacteria was wetted to varying degrees.

Table I.

Percentage of moisture in cotton	Number of organisms per g. found in cotton, originally containing 1·4 millions, after 3 days at 16°
6·5	1·4 millions
7	1·5 "
8	2·26 "
9	1·4 "
10	124 "
15	499 "
20	1112 "
30	1540 "
50	9040 "

Though the above experiment explains the reason for the very large number of bacteria often met with in raw cotton, it does not indicate the source of the original, very considerable, infection of this cotton. To get further information on this point it was decided to examine raw cottons at various stages of their production, and to determine, as far as possible, the source of the infection met with. Through the kind offices of the then Director of Pro-

pellant Supplies of the Ministry of Munitions, Col. Sir Frederic Nathan, it was possible to send a request to various cotton growers in India and the United States to supply this laboratory with representative samples of raw cottons taken from ripe cotton bolls, from seed cotton which had not been ginned, from ginned, and from baled cottons, and to give a detailed description of the conditions under which the samples had been grown and harvested.

On their arrival at this laboratory the samples were examined bacteriologically and their moisture content taken. The analysis took into consideration not only the types of organisms developing on agar and gelatin plates, but also the aerobic and anaerobic cellulose-decomposing bacteria, and the thermophilic bacteria. It may perhaps be of interest to give the result of a few representative analyses, since they appear to throw some light on the source of the infection of raw cottons. The analyses of these samples are tabulated in Tables II, III and IV.

Table II. *Indian cottons (Khangaon fields).*

Sample	Agar and gelatin plates		Cellulose decomposing bacteria		Thermophilic bacteria	Moisture %
	Bacteria	Moulds	Aerobic	Anaerobic		
Cotton from open ripe boll, not exposed to damp	20,000 per g. <i>Streptothrix chromogena</i> only	50,000 per g. <i>Aspergillus niger</i>	+	+	None	6.1
Seed cotton not exposed to damp	30,000 per g. <i>Streptothrix chromogena</i>	100,000 per g. <i>Aspergillus niger</i> ; <i>Penicillium glaucum</i>	+	+	None	6.5
Cotton after ginning; sample had been picked about 14 days before ginning. During that time exposed to damp and rain though protected by tarpaulin	6,100,000 per g. <i>Streptothrix chromogena</i> , <i>Bact. herbicola aur.</i>	100,000 per g. <i>Aspergillus niger</i> ; <i>Rhizopus niger</i>	+	+	+	6.1
Cotton 24 hours after pressing. Five days exposure to damp and rain before pressing	2,300,000 per g., spor-ing rod of <i>Subtilis</i> type, <i>Bact. herbicola aur.</i> ; <i>B. fluorescens</i>	200,000 per g. <i>Aspergillus niger</i>	+	+	+	6.1

Table III. *Indian cotton from Auraiga fields.*

Cotton from ripe bolls taken immediately after picking. Some of the bolls attacked by pink boll worm. Not exposed to damp	630,000 per g., rod of <i>Subtilis</i> type. <i>S. chromogena</i>	80,000 per g. <i>P. glaucum</i>	+	-	None	5.6
Seed cotton just before ginning. A number of the pink boll worm found and cotton stained. Not exposed to damp	140,000 per g., rod of <i>Subtilis</i> type. <i>S. chromogena</i> ; <i>B. herbicola aur.</i>	60,000 per g., <i>A. niger</i> ; <i>A. oryzae</i> (?)	-	+	None	6.5

Table IV. *American cotton. Mississippi Delta Planting Co.*

Seed cotton exposed to little or no rain	220,000 per g., <i>B. herbicola aur.</i> ; <i>S. alba</i> ; coccus with yellow colonies	4000 per g., <i>Rhizopus niger</i>	-	-	+	8.9
Cotton after ginning; not exposed to damp	1,200,000 per g., <i>B. mesentericus</i> ; <i>B. herbicola aur.</i> ; <i>S. alba</i> ; <i>B. fluoresc. liq.</i>	1000 per g., <i>Rhizopus niger</i>	+	-	+	6.9
Cotton after pressing; not exposed to damp	7,000,000 per g., <i>B. herbicola aur.</i> ; coccus with yellow colonies	20,000 per g., <i>P. glauc.</i> ; <i>A. glauc.</i>	+	+	+	7.3

It will be seen that practically all the types of micro-organisms found in these cotton samples are typical representatives of the soil flora, and there is no doubt that contamination with soil particles contributes largely to the infection of raw cottons.

Where it was possible to examine samples still in the bolls, the number of micro-organisms was always small, except in the case of the Auraiga sample, which had been attacked by the pink boll worm. Whether this pest contributed to the infection of the sample is difficult to decide. It is hoped, however, to make further inquiries into this point, when more of these samples are available.

As to the effect of damp to which some of the samples had been exposed, the evidence is contradictory. Taking the India samples alone, there certainly is a larger number of bacteria in the exposed samples than in those which had been protected. On the other hand, the American samples, which had not been damped, show quite as many bacteria as the exposed Indian cottons. In no case does the infection reach anything like the figures found in the damped Indian cottons quoted in Table I. It would appear, therefore, that at this early stage in the history of raw cottons, the wetting to which they may normally be exposed is of far less importance for the increase in number of bacteria than is the contamination with soil particles.

In addition to the typical cellulose decomposers the *Streptothrix* were found to be able to attack the cotton fibres. The moulds, the coccus, the bacteria of the *Subtilis* group and the *B. herbicola aureum* did not attack the cellulose.

The changes taking place in the cotton fibres after attack by bacteria have already been described [1920]. They were found to be so characteristic that a method, based on them, could be worked out for the quantitative determination of damaged fibres present in good cotton. An outline of this method, which may conveniently be termed the "swelling test," was given in the paper already referred to. As it has proved useful in various directions, a more detailed description of it is given below.

The swelling test is based on Balls' observation [1918] that treatment with carbon disulphide and alkali causes the cotton fibres to swell, thereby rendering the structure of the fibres visible under the microscope. On applying Balls'

treatment to a cotton fibre damaged by bacteria it was found that its structure had undergone changes, which made it readily distinguishable from a normal fibre. Microphotographs illustrating these changes were published in the short paper referred to above.

Two further microphotographs of good and damaged cotton fibres, before and after treatment with carbon disulphide and alkali, are given here. The fibres in Pl. I, fig. 1 have not been treated; of the three seen, the centre one has been damaged by bacteria, the two others not. In the second figure, where the fibres have been swelled, the third and the fourth from the top have been damaged, the others not. Comparing the two photographs it will be seen that the swelling greatly facilitates the differentiation between normal and damaged fibres.

The technique of the actual swelling of the fibres is substantially the same as that described by Balls. However, the preliminary cleaning of the fibres by boiling with 1 % NaOH, washing and neutralisation with 1 % acetic acid, has been dispensed with, except in cases of very dirty cotton samples. The fibres to be examined are now simply soaked in the mixture of alkali and carbon disulphide and left in contact with this mixture for the required time.

If a quantitative analysis has to be made to determine the damage suffered by a cotton, great care is taken to select a really representative sample for examination. This is done by very careful mixing of about 3 g. of the cotton in question.

About 0.2 g. of this uniform sample is mixed with 1.5 g. each of carbon disulphide and 15 % NaOH solution, and the flask containing the mixture is shaken well from time to time. The time during which the fibres have to be left in contact with the alkali carbon disulphide mixture varies considerably with the cotton used, and with the degree of damage, and no fixed rule can be laid down in this respect. The fibres from an Indian cotton shown in fig. 2 had been in contact with the mixture for 10 minutes, which apparently represents the minimum time advisable for this class of cottons, since the structures of the damaged fibres are not yet fully developed. Until practice has been acquired in judging when a cotton has been sufficiently treated, it is advisable to examine small test samples—a few fibres—under the microscope from time to time, say every 10 minutes.

When the degree of swelling has reached its optimum (see Figs. 2 and 3 of the earlier publication) three small samples, each of them of the size of a large pea, are taken from the swelled cotton and placed on three microscope slides. Here each sample is again carefully mixed, for instance with two ordinary pins, and about 20 fibres, taken at random, are spread out horizontally on the slides and covered with cover slips (see fig. 3). A drop of water is left to diffuse between the slip and the slide, and the preparations are ready for examination under the microscope. A magnification of $\times 45$ –50 may conveniently be used.

Ten counts are taken from each slide, the first running along the right-

ERRATUM

Page 410, line 9, *for* third and the fourth *read* fourth and the fifth

hand edge of the cover slip, vertically on the fibres, the following parallel with, and to the left of the first. The ten counts should cover the whole of the preparation from the right-hand edge of the cover slip to the left. The average count from each of the three slides should vary very little in well-mixed cotton samples. However, even where a considerable variation does exist, the average of these three counts has been found to give reliable figures.

In order to obtain consistent results with the swelling test, it is, of course, necessary to lay down definite rules as to when a fibre is to be regarded as damaged, and when not. It is very noticeable that the action of the bacteria is confined to small local eruptions when the fibres are first attacked, and that the damage spreads gradually over the fibre. The authors, therefore, do not count a fibre as deteriorated until it has been attacked throughout its whole length. The term fibre, as used in this connection, does not necessarily mean the whole length of a fibre, but may be any fraction of one, however small, which for some reason or other has been separated from the main part.

The swelling test has already been tried on a good many cotton samples, and has always been found both reliable and easy to carry out. In one set of experiments it was used parallel with the alkali solubility test, a test which is generally used for detecting deterioration in cottons. The results obtained appear sufficiently interesting to be given in detail.

The analyses were carried out on four cotton samples of known origin, two of which were American and two Indian. One American and one Indian sample were taken from hand-picked seed, the two others came from an American and an Indian ginning factory. Each of the four samples was wetted with its own weight of sterile distilled water and then divided into two lots, one of which was infected with a suspension of bacteria obtained from a badly deteriorated cotton, while the other was left not infected.

This infection of some of the samples was done because an earlier experiment had shown that an Indian cotton sample, straight from the bolls and containing very few cellulose decomposing bacteria, broke down very slowly unless infected with the necessary bacteria.

It soon became evident, however, that this precaution of artificially infecting the fibres had been unnecessary in this case, as even the carefully hand-picked cottons from the bolls deteriorated spontaneously at a rate scarcely slower than that of the infected samples.

After wetting and infection, the various lots of cotton were incubated at room temperature (16°) and analysed every third day.

A glance at Tables V and VI shows the striking difference in the usefulness of the two methods employed. While the swelling test (Table V) registers a steady rise in the percentage of physically damaged fibres, the alkali solubility test (Table VI) remains more or less constant, till the destruction of the cotton has reached a point, where it is affected chemically, and may be easily detected, even by the inexperienced eye.

Table V.

Percentage of decomposed fibres found in the cotton after x days' incubation at room temperature (16°)

Sample of cotton from	0	3	6	9	12	15	18	72
Indian bolls	0	0	4	10	16	23	19?	—
„ „ infected	0	0	4	12	22	23	30	—
American bolls	0	0	0	1	2	5?	2	54
„ „ infected... ..	0	0	0	1	2	3	3	48
Indian ginning factory	2	2	4	22	36	43	53	—
„ „ „ infected	2	3	6	24	32	39	51	—
American ginning factory	0	0	0	1	1	4	3	42
„ „ „ infected	0	0	0	1	1	3	2	32

Table VI.

Percentage of decomposed fibres found in the cotton after x days' incubation at room temperature (16°) shown as percentage of solubility in alkali

Sample of cotton from	0	3	6	9	12	15	18	72
Indian bolls	6.6	5.8	5.25	6.3	6.1	6.4	7.1	—
„ „ infected	—	5.6	5.7	5.7	6.3	5.3	7.3	—
American bolls	4.6	4.4	4.2	4.2	4.3	4.2	4.8	5.8
„ „ infected	—	4.2	4.3	4.6	4.6	5.4	4.4	6.5
Indian ginning factory	12.9?	9.6	8.55	9.09	8.5	9.09	10.3	—
„ „ „ infected	—	9.3	8.4	8.8	9.1	8.6	11.1	—
American ginning factory	5.9	5.5	5.2	5.2	4.6	4.8	5.4	6.3
„ „ „ infected	—	5.3	5.1	5.2	5.2	4.8	5.3	5.5

The alkali solubility test, therefore, does not appear to be sufficiently sensitive to be used for determining the extent to which a cotton has been physically damaged by bacteria. For this purpose the swelling test is distinctly superior, giving a clear reaction when comparatively few fibres have been destroyed.

On looking through the figures in Table V it will be noticed that the four samples of Indian cotton were much more readily attacked by bacteria than the corresponding American samples. This can scarcely be accidental, and is certainly not due to the absence of the necessary bacteria from the latter, since the infected American cottons decomposed at the same slower rate as the uninfected American samples. It seems more likely that the different behaviour of the Indian and the American cottons is due to morphological or physiological differences of the two types, caused perhaps by climatic conditions.

A further investigation of this point carried out to confirm and amplify the above results gave similar results.

Table VII gives the results of the examination of one Japanese, one Chinese, two further Indian and American and two Egyptian cottons. All the samples were wetted like the samples mentioned in Table V and left for the stated number of days at 16°. Bacteriological analysis had shown that all samples contained cellulose decomposing bacteria.

Table VII.

Percentage of damaged fibres found in

Exposed to damp for	Japanese waste	Chinese waste	Indian No. 1	Indian No. 2	American No. 8	American No. 18	Egyptian silver	Egyptian scukher lap
0 days	0	0	0	0	0	0	0	0
3 "	0	0	0	0	0	0	0	0
6 "	0	3	1	0	0	0	0	0
9 "	0	3	1	2	0	0	3	1
12 "	0	10	4	2	0	0	0?	3
15 "	5	23	8	11	1	4	3	4
19 "	6	16?	13	14	2	3	4	11?
22 "	7	57	33	27	5	7	8	11

Though the two Indian and American samples of Table VII were of totally different origin to those previously tested (Table V) their rates of deterioration were almost identical, *i.e.* very slow in the case of the American, and rapid in the case of the Indian. The Egyptian cottons apparently take a middle course, being more susceptible than the American, and less so than the Indian. Of the remaining samples in Table VII the Japanese cotton compares with the American, and the Chinese with the Indian.

Judging from these experiments there is little doubt that a difference exists in the susceptibility of cottons of different origin to attack by bacteria, an observation which should be of sufficient importance from the planter's point of view to justify a careful investigation.

This investigation is now proceeding and, though little information has so far been obtained, it may be worth while mentioning, that contrary to expectations agricultural and climatic conditions do not seem to be of great importance. This will be seen from Table VIII giving the results of an analysis of two cottons grown in India from American seed.

Table VIII.

Percentage of damaged fibres found in cotton grown in India from American seed

Exposed to damp for	Gadag cotton	Akola Berai cotton
0 days	0	0
3 "	0	0
6 "	0	0
9 "	1	0
12 "	1	1
15 "	1	3?
19 "	1	1
22 "	5	4

The preliminary treatment of the two samples was the same as that used in the earlier experiments (Tables VI and VII), and both of these cottons were shown to contain sufficient cellulose decomposing bacteria to cause deterioration. Both samples are still typical American cottons from the point of view

of resistance to bacterial attack. Whatever effect, therefore, climatic and agricultural conditions may have, they are not brought to light in one generation, but must be of a cumulative nature. This and other questions are matters for further investigation.

CONCLUSIONS.

If a very large number of micro-organisms is found in a raw cotton, it is generally safe to assume that the cotton has been exposed to damp.

Smaller numbers, up to a few millions per gram, are due to a contamination of the cotton during the various stages of its preparation, including exposure on the fields.

With the help of the viscose treatment it is possible to show that changes occur in the structure of cotton fibres when attacked by bacteria. A method, based on this observation, has been worked out for the quantitative determination of the bacterial deterioration of cotton.

On applying this "swelling test" to cottons of various origins it was found that a difference exists in the susceptibility to attack by bacteria, and that Indian cottons deteriorate quicker than American samples. Samples of cotton grown in India from American seed were found to be as resistant to attack as American cottons.

REFERENCES.

- Balls (1918). The existence of daily layers of growth in the cell wall of cotton hairs. Author's MS.
Fleming and Thaysen (1920). *Biochem. J.* 14, 25.

Fig. 1

Fig. 2

Fig. 3