XXIX. ON THE THEORY OF GELS. IV.

By SAMUEL CLEMENT BRADFORD.

From the Science Museum, London.

(Received March 12th, 1923.)

THE investigation of the physical properties of the natural emulsoids has produced an enormous literature. For the correlation of this, and for the study of many problems of biology and industry a theory of the sol-gel transformation is needed which fits the facts. The present condition of uncertainty is illustrated by the multitude of mutually incompatible *ad hoc* theories of gel structure which are current. The many hypotheses may be classified in three groups: (1) one-phase or molecular systems, (2) two-phase liquid-liquid systems and (3) two-phase liquid-solid systems. To theories in the first class it must be objected that they are unable to explain the loss of mobility that occurs on setting. Those in the second group have the additional difficulty that no liquid-liquid systems can be imagined which would have the elastic properties of gels [Hatschek, 1917]. Nor is there any direct evidence for hypotheses in either of these two categories. Thus we are obliged to assume that gels have a solid phase. This idea is the most natural and was the earliest to be held [Frankenheim, 1835]. The suggestion of K. von Nägeli [1858] is well known, that gels are composed of molecular complexes or micellae with crystalline properties, in the interstices within and between which the water is held by molecular attraction. It has been inferred that von Nägeli intended a geometrical framework, and attempts have been made to devise a network that would account for the elastic and thermal properties of gels. If, however, it is realised both that the elastic properties of gels differ greatly and that the directive forces inherent in the ultimate particles of gels are probably different, it seems unlikely that a single framework could be found to account for the different properties of different gels. It is more probable that the structure of gels varies according to the nature of the gel substance. Bütschli's hypothesis [1892, 1896, 1898, 1900] that gels have a honeycomb structure is disproved by the work of Zsigmondy [1911], Anderson [1914] and Bachmann [1917] on the vapour pressure isotherms of gels, which shows that they must contain fine pores with a radius of from 2.5 to 5μ , some 300 times smaller than Bütschli's honeycombs. These experiments are particularly interesting as they give an explanation of van Bemmelen's [1878, 1880] curious hysteresis cycle. From microscopic work on soap curds and gels, Zsigmondy and Bachmann [1912] have favoured a fibrillar structure. On the other hand McBain [1920] considers that identical colloidal particles are present in the sol and gel

state, which differ only in mechanical rigidity and elasticity. Moeller [1916, 1917] supports the view that gelatin gels have a fibrillar structure. But it must be objected to his experiments that the use of alcohol and tanning reagents may alter the structure of the gels or modify the gelation process. Barratt [1920], also, has given evidence that fibrinogen gels are composed of fibrils. For the soaps and fibrinogen there is direct microscopic evidence that fibrils can be formed by the cooling solutions, which suggests that the ultra- or amicroscopic structure of the gels may be fibrillar. For gelatin, agar and silicic acid, however, a globulitic structure is indicated. In gelating 2 % gelatin, submicrons develop gradually from 4, showing Brownian movement, in a square division of the field with a side of 9μ , to 80 to 100 at rest in the same area [Menz, 1909]. Moreover the ultramicroscopic appearance of gelatin gels deprived of water is globulitic [Bachmann, 1911].

Thus there is much evidence that gels contain a solid phase. But none of the theories mentioned is sufficiently definite to explain the reversible sol-gel transformation, or to permit the deduction of the physical properties of gels. Nor do they suggest why such substances as gelatin and agar should occur almost invariably in the colloid form. If it be granted that gels have a solid phase, the origin of the solid must be investigated. The simplest assumption, that the solid was originally in solution and has crystallised out, must be considered first. Here we enter the realm of the theory of solutions, which, unfortunately, is in an altogether unsatisfactory state. Little is known of the forces which hold substances in solution or cause their deposition. Nor is current theory able to suggest the cause of the different solubilities and solvent powers of different substances. Some attempt to study the forces acting on solvent and solute has been made [Bradford, 1919, 1922]. But a subject so vast needs many workers. When these relations are understood, it may be possible to deduce a sound theory of the stability of colloid solutions.

Fortunately, however, von Weimarn's long series of experiments [1914] have thrown some light on the conditions governing the separation of solid from solution. His formula

$$N = U \frac{P}{L}$$

expresses a relation between N , the "form coefficient" of the precipitate, and U , P and L , respectively functions of the viscosity of the reaction medium together with the size and structure of the particles in solution, the excess concentration of the substance to be precipitated, and its solubility. From a great many experiments von Weimarn was able to show that, as N increases, the precipitate passes through stages in which it appears as (1) large complete crystals only after some years, (2) ordinary crystals in a short time (3) growth figures or needles, (4) amorphous precipitates frequently showing microscopic spherical grains, and (5) as a gel which cannot be resolved by the microscope. The colloid condition results when N is extremely great. If, at the same time,

the excess concentration, P , is small, a sol is produced; if P is great, a gel is formed. The formula is not exact. Experiments in progress may help to a more definite statement. But, in practice, the incomplete equation is very useful in showing how to vary the grain size of a given material. The formula suggests directly that gelation is merely an extreme case of crystallisation and that gelatin and agar are substances whose properties lead naturally to a high value of N [Bradford, 1917; 1918; 1920, 1, 2; 1921]. This hypothesis is abundantly confirmed by experiment.

Gelatin sols behave exactly as supersaturated solutions. Certain curious temperature relations of the sols can be simply explained only on the assumption that gelatin has a definite solubility at a given temperature. Moreover, by reducing the value of N in von Weimarn's formula, the particles of gelatin gels can be increased in size as desired and are found to be definitely crystalline.

The molecular theory of solution [Bradford, 1919, 1922] shows that every substance must have a definite solubility, however small, in a given solvent, with which it does not combine chemically. Consider the case of a hot solution of a substance, of high molecular weight and very low diffusivity, in a liquid, in which its solubility, L , is considerable at high temperatures but small at low.

On cooling, the Noyes-Nernst formula,

$$V = \frac{D}{\delta} S (C - L),$$

shows that the velocity of crystallisation will be small, owing to the very small value of the diffusion coefficient, D . The solution will become gradually more and more supersaturated and the particles of solute increasingly aggregated. The value of L in von Weimarn's formula will diminish rapidly, while P increases correspondingly. When, eventually, spontaneous crystallisation occurs, U will be large on account of the high molecular weight and aggregation, P also will be large and L small, giving a maximum value of N . Therefore, the solution will set slowly to a jelly.

A substance with greater solubility, such as oxy-haemoglobin, or egg albumin, will be obtained as micro- or macroscopic crystals even though its molecular weight be very high. But it can be shown that gelatin corresponds exactly to the case considered above. Its molecular weight is not known. However, Dakin's recent analyses [1920] show that gelatin contains 1.4 % of phenylalanine of molecular weight 165. Since one molecule of gelatin cannot contain less than one molecule of phenylalanine the lowest possible molecular weight of gelatin is 11,800. Loeb's [1922] osmotic pressure experiments indicate twice this figure. It is safe to conclude, therefore, that gelatin has a very high molecular weight. A value of 10,000 would correspond to molecules themselves of colloid size with a diameter of 1.75μ .

The solubility of gelatin was determined in the course of experiments to show that it behaves exactly in accordance with von Weimarn's formula. Dilute filtered solutions of ashless gelatin, purified by electrolysis, from the

(Note added on May 17th, 1923.) Since writing this paper Professor Schryver has very kindly supplied a small sample of specially pure isoelectric gelatin prepared by a new method. This readily yields dilute jellies with marked granular structure in which small spherical particles can be separately resolved, and appears, generally, to behave like the gelatins used for these experiments, except that some doubt has arisen whether large spherites can be obtained under the conditions described.

S. C. B.

Osmosis Co., of different strengths, which had been quickly boiled and sealed in tubes, were allowed to stand at room temperature. Instead of setting to a jelly the solutions became opalescent and the excess of gelatin was deposited slowly as a gelatinous precipitate. When the volumes of the precipitate were plotted against the concentrations, the curve was found to be a straight line cutting the concentration axis at the point corresponding to 0.12 % of dry gelatin per 100 cc. of solution. Above this concentration the volume of the precipitate is proportional to the excess concentration. This figure is undoubtedly the true solubility of gelatin at room temperature, which remained fairly uniform at 18° during the experiment.

Confirmation was supplied by making up solutions of 0.12, 0.13 and 0.135 % and allowing to stand as before. The first remained perfectly clear, the second developed in a few days a beautiful clear bluish opalescence which persisted for months. This was evidently a metastable solution of gelatin, the permanence of which was due to the low diffusion constant of gelatin. With the 0.135 % solution the metastable limit was overstepped and a trace of gelatinous precipitate was deposited. Further confirmation is afforded by the fact that water stirred with gelatin for two hours takes up 0.114 g. of solid. The experiments are being continued with ashless gelatin in a thermostat at different temperatures, and the solubility is being calculated, also, from the amount of solid left in solution in the mother liquor. The results leave no doubt that gelatin has a true solubility in water which increases rapidly with rise of temperature. The high molecular weight is sufficient to account for a very low value of the diffusion constant. Thus gelatin fulfils all the conditions which have been assumed in the hypothetical case considered above. It follows that von Weimarn's formula is sufficient to explain the occurrence of gelatin in the colloid state and that the gelation of gelatin sols is an extreme case of crystallisation.

The theory requires that there shall be a gradual increase in the size of the deposited solid gelatin particles with decrease in supersaturation, until, with very dilute solutions, the precipitated particles become visible microscopically. This is exactly what happens. Six per cent. gelatin gels, from which the liquid has been expressed, cannot be differentiated in the ultra-microscope [Bachmann, 1911]. With less concentration a globulitic structure becomes apparent, and the size of the granules increases as the concentration is reduced. When the concentration is reduced to 0.4 % microscopic examination of the white gelatinous precipitate gives the appearance of an enormous number of particles like grains of sand, just too small to be differentiated, among which there are a number of larger spherical particles big enough to be seen. These are mostly aggregated into clusters. With further decrease in concentration the sand-like appearance becomes more marked and the larger spherical particles fewer and bigger, until, at 0.2 % they reach nearly 1μ in size. When a gelatin solution is cooled, the bulk of the precipitate increases with the concentration and the particles decrease in size until, at about 0.7 % at 18°

the precipitate fills the solution and forms a continuous jelly. This jelly is white and opaque owing to the large size of the particles. As the concentration is increased the particles get smaller and eventually the jelly becomes clear. A gelatin jelly is, therefore, a gelatinous precipitate of gelatin of more than 0.7 % concentration. The relative sizes of the grains can be determined also in another way. Solutions of ashless gelatin, containing from 0.25 to 1.0 % of dry gelatin, were boiled and sealed in test-tubes and allowed to stand at room temperature. Within 24 hours the solutions up to 0.51 % had become distinctly opalescent, 0.77 % solutions had set to very cloudy just coherent jellies and the 1.0 % tubes contained a slightly stronger jelly that was still rather more cloudy. In about three weeks, the jellies had separated a film of clear liquid above. In the remaining tubes, containing the weaker solutions, the opalescence developed from day to day, and, after about ten days, the precipitate appeared to be subsiding in the tubes. The rate of fall was measured from time to time, and the curious fact was observed that there are three distinct stages in the fall of the surface of the opalescence: (1) a long gradual fall at a uniform rate, for from about 20 to 30 days according to the concentration, during which time the particles are discrete, because the surface of the opalescence is easily disturbed, (2) a sudden drop, for one or two days, after which the precipitate appears to have coalesced to a continuous jelly, and (3) a gradual shrinkage, at a somewhat slower rate than (1), which shows all the signs of syneresis. The application of Stokes's law to the long continuous free fall, (1), enables the relative sizes of the particles to be calculated, and confirms the fact that particles increase in size with diminishing supersaturation. These experiments are being continued in a thermostat at different temperatures, from which it is hoped to determine a more exact relation between the size of the precipitated particles and the solubility and excess concentration. However, each series takes several months, and the solubility increases rapidly with rising temperature, so that a preliminary series is necessary at each stage. Consequently, with very little opportunity for experimental work, it will be some time before the complete results can be published. Similar experiments with dialysed agar give exactly comparable results.

There is no doubt that the solubility of gelatin, like that of any other substance, varies with temperature and with the presence of other bodies. As an amphoteric compound, it is particularly sensitive to changes in the p_H . This is confirmed by Loeb's experiments on the rate of solution of gelatin in the presence of salts, acids and alkalis. If, therefore, a solution of gelatin contain more of this substance than corresponds to its solubility under the conditions of the experiment, the excess will be deposited slowly. The gelatin molecules will aggregate gradually in the process of precipitation, and the properties of the liquid will be affected by the presence of these aggregates. Experiments on the viscosity of gelatin solutions compelled Loeb [1922] to assume that the forces holding gelatin and crystalloids in solution are the

same. The viscosity of gelatin solutions is essentially different from that of simple amino-acids or of egg albumin. It is of an altogether higher order, and is much affected by the presence of electrolytes. If it be assumed, as experiments indicate, that the viscosity of gelatin and albumin solutions is a function of the volume of the protein in solution, gelatin solutions must possess a mechanism, which albumin solutions do not, of increasing the volume of the solute. This mechanism is likely to be connected with their tendency to set to a jelly. From which it may be concluded that, in gelatin solutions, solid particles of gelatin, or micellae, are formed gradually, which occlude relatively large quantities of water, whereby the relative volume of the particles is increased.

In egg albumin solutions these particles are lacking because the solutions do not set, *i.e.* the solubility is greater. But if the p_H is below 1.0 and the temperature higher, solutions of albumin do tend to gelate, and then their viscosity is of the same order as that of gelatin solutions.

The influence of electrolytes on the viscosity of gelatin solutions, and not of albumin solutions, is explained by the presence of a Donnan equilibrium between the submicroscopic gelatin particles and the surrounding solution, which regulates the amount of water occluded. This was confirmed by experiments on the viscosity of suspensions of finely powdered gelatin in water, whose viscosity varied directly with the observed volume of the particles, and was influenced by electrolytes exactly as are solutions of gelatin. The effect of electrolytes on the viscosity of gelatin solutions would be explained if it could be shown that they contain submicroscopic particles of solid gelatin capable of swelling. Loeb gives much indirect evidence that solid particles are formed in gelatin solutions, under given conditions, when the temperature falls below a certain point. For instance, the viscosity of 2 % gelatin at p_H 2.7 increases rapidly on standing at temperatures below a point which lies between 25° and 35° and which the experimental values indicate to be at about 27° to 28°. Above this point the viscosity decreases slowly at rates which increase slightly with rising temperature. That is to say a 2 % solution of gelatin at p_H 2.7 is saturated at about 27° or 28°. Below this temperature the excess of gelatin gradually forms solid aggregates, and at higher temperatures the aggregates are gradually dissolved. The actual proof is supplied by direct experiments on the crystallisation of gelatin which show that super-saturated gelatin solutions do deposit solid gelatin.

It follows that the terms "melting point" and "setting point" have no exact meaning as usually applied to gelatin jellies and solutions. A 1.15 % jelly of ashless gelatin will just dissolve completely if it be maintained at 26.45°. If it be kept at a lower temperature, an amount of gelatin, corresponding to the solubility of gelatin at that temperature will go into solution. But, if the jelly be warmed gradually until melted, it will not melt until the temperature has been raised considerably above 26.45° on account of the slow velocity of solution. Conversely, if a warm 1.15 % solution of gelatin

be cooled, the liquid will not set until the temperature has fallen much below 26.45° , or actually to the room temperature. If the temperature be maintained at a point below 26.45° , the gelatin in excess of the solubility at that temperature will be precipitated. Whether the precipitate will form a jelly, or not, will depend on its amount. Obviously, the observed melting and setting points depend on the rate of heating. Similarly the grain size of the jelly is affected by the temperature at which the bulk of the excess gelatin is precipitated. When a more exact expression for the grain size has been found, it should be possible to deduce the relations between the excess concentration, and the elasticity, vapour pressure and other properties of the resulting gels.

It remains to investigate the nature of the deposited solid. It has been mentioned that, when the particles of gelatin became large enough to see, they are spherical in shape. Von Nägeli observed the beautiful brushes shown by spherites between crossed nicols and described their radiating-needle structure, but he was unable to say whether his micellae were identical with spherites. However, it is now certain that gelatin particles have this conformation. The study of substances which crystallise in this shape, and experimental investigation, show that bodies of high molecular weight, and those that exist in solution in the aggregated state, tend to crystallise in the form of spherites. Indeed, it is obvious that a slow moving, comparatively large particle, is able to orientate itself to fit a growing spherite, composed of radiating needles, more easily than a crystal of another shape. It is reasonable to suppose, therefore, that the granules composing jellies of gelatin and agar are spherites.

Spherites are known in every gradation, from the obviously crystalline form, built up of coarse radiating needles separately visible, through stages showing only a more or less radiating formation and often a banded structure, but giving the well-known shadow-cross in polarised light, to apparently isotropic bodies giving little definite evidence of crystalline structure. Microscopic examination of gelatin spherites proves that they are crystalline and belong to the second class. This completes the evidence that gelation is a crystallisation process.

Granules deposited from dilute solutions of pure ashless gelatin under aseptic conditions may reach 1μ in size. These show perfect shadow crosses when viewed between crossed nicols. It is convenient, however, to grow them larger. This is done exactly in the same way as larger particles of other substances would be grown, *i.e.* by spontaneous evaporation of saturated solutions. In these experiments 0.3 % solutions were made in water containing 0.1 % of mercuric chloride or camphor as antiseptic. The liquid was filtered into chemically clean glass crystallising dishes, which were covered and allowed to stand at room temperature for periods of from one to six months. The liquid becomes opalescent within 24 hours as the precipitation of the gelatin begins. Soon a white, or slightly buff-coloured, powder is seen on the base of the dish. The tint may be due to a trace of pigment, or be the actual colour of the gelatin

particles. Smaller particles always appear white, but it is possible that this may be caused by the greater subdivision. After some time the supernatant liquid is observed to have set to a jelly. This is because evaporation has taken place faster than the gelatin could diffuse through the liquid to the growing spherites. When this happens, further diffusion is practically stopped and the spherites can increase in size only by actual increase in concentration of the liquid in their immediate vicinity, or at the expense of smaller adjacent particles. Consequently the spherites attain nearly their maximum size in a month or two. The precipitate was scraped from the base of the dishes and mounted either in mother liquor, the refractive index of which differs but little from that of the gelatin particles [Walpole, 1913], or glycerol of much higher refractive index, but the spherites appeared to dissolve slowly in the latter medium. The edges of the cover glasses were cemented with Japan gold size. After two months the precipitate consisted entirely of spherites up to 3μ in diameter with a few rather larger grains. They were viewed with a Leitz fluorite $\frac{1}{12}$ inch objective and an eyepiece magnifying twelve times. Between crossed nicols many showed perfect shadow crosses, but, of course, only one or two could be brought into focus at a time. After three months the spherites were up to 3μ or slightly over. There were also a few spherites from each of which a bundle of fibrils had grown like the tail of a comet. Similar appendages are shown occasionally by spherites of silver dichromate. After four months' evaporation, the particles had grown to about 4μ . By six months the larger particles had reached 4.4μ in size. Almost all showed shadow crosses more or less complete. But the crosses were the more perfect the smaller the size of the particles. This gives no reason for supposing that the still smaller particles of jellies are not crystalline. The appearance of the precipitate after two months' growth is shown in the photographs (Figs. 1 and 2, Plate III), for help in taking which the writer is indebted to the kindness of Dr L. C. Martin. The shadow crosses show best when the equators of the particles are exactly in focus, and are altogether different in appearance from those shown by light polarised by reflection at the surfaces of air bubbles. Grains of mastic grown by Perrin's method showed no shadow crosses but only a slight luminescence. By evaporation at 23.5° spherites have since been obtained up to 6μ . This proves that the gelatin spherites are crystalline.

Since agar also separates from solution in the form of granules, it appears probable that the structure of jellies of this substance and of gelatin is that of a pile of shot. Such a fine grained structure is compatible with all the known properties of jellies except the heat of swelling, 5.7 cal. per g. [Wiedemann and Lüdeking, 1885] and the so-called "thermal anomaly" [Bjerkén, 1891]. Re-determination of the former gave a value 33.25 cal., which corresponds to that for starch. Investigation of the thermal anomaly showed that it was unfounded. The pile-of-shot structure offers a simple explanation of the lens-shaped form of gas bubbles in gels investigated

by Hatschek [1914]. Moreover, the crystallisation theory explains another curious phenomenon observed by Hatschek [1920]. It is well known that mechanical strain causes gelatin gels to exhibit optical anisotropy in polarised light. When a rectangular prism of jelly is bent between three stops, the usual coloured appearance is observed in polarised light. After five days in a moist chamber, the mechanical stress disappears, so that the specimen can be removed without straightening itself appreciably. Extraordinarily enough, however, the appearance in polarised light remains unchanged. The explanation may be as follows. Gelatin and agar are remarkable for their stability, although most substances that can be obtained in the gel form, under suitable conditions, develop rapidly microscopic crystals. The permanence of the natural gels is due to the low solubility, the very low rate of diffusion of the gel substances, and to the fact that dissolved material is almost unable to diffuse through the jelly. But, if the crystallisation theory is true, very slow re-crystallisation should be going on. Evidences of slow re-crystallisation in silicic acid gels have been observed previously. They have now been obtained in the case of gelatin.

Optically clear aseptic 5 % gelatin gels were sealed in tubes and kept at room temperature. After three months a distinct opalescence had developed, which grew from month to month until, after ten months, it had become very marked. Microscopic examination after four months showed an almost clear field in which some very tiny round particles could just be seen. With lapse of time the visible particles increased in number and size. In ten months some had reached nearly 1μ in size. It appears, therefore, that there is an extremely slow process of re-crystallisation taking place constantly in gelatin jellies, by which the larger particles are growing continually at the expense of the smaller ones, just as in the case of any ordinary substance in contact with a solvent. Moreover, the marked increase in the modulus of elasticity during the first 24 hours indicates that the separation of gelatin from solution, in the slow process of setting, is not complete even within that time. Since gel substance is being deposited on the larger particles in a gel, whether strained or not, in a strained gel the larger particles will become cemented in their constrained positions. So that, on removal of the stress, the particles will be unable to move, but the internal strain will continue and maintain the optical appearance in polarised light.

In default of evidence to the contrary, therefore, we must conclude that the forces which hold gelatin and agar in solution are the same as those that operate between other solutes and solvents, and that the setting of jellies of the natural emulsoids is merely a process of crystallisation.

The writer desires to express his gratitude to the Government Grant Committee of the Royal Society and to the Chemical Society for grants which have enabled these experiments to be continued.

Fig. 1. Gelatin spherulites. $\times 1400$.

Fig. 2. Gelatin spherulites between crossed nicols. $\times 1400$

REFERENCES.

- Anderson (1914). *Ann. Chim. Phys.* [vi], **29**, 505.
Bachmann (1911). *Z. anorg. Chem.* **73**, 150.
— (1917). *Z. anorg. Chem.* **100**, 1.
Barratt (1920). *The physics and chemistry of colloids*. A discussion by the Faraday and Physical Society, 1921.
Bemmelen (1878). *Ber. deutsch. chem. Ges.* **11**, 2232.
— (1880). *Ber. deutsch. chem. Ges.* **13**, 1466.
Bjerkén (1891). *Ann. Phys. Chem.* **43**, 819.
Bradford (1917). *Science Prog.* **12**, 63.
— (1918). *Biochem. J.* **12**, 351.
— (1919). *Phil. Mag.* **38**, 696.
— (1920, 1). *Biochem. J.* **14**, 91.
— (1920, 2). *The physics and chemistry of colloids*. A discussion, 1921.
— (1921). *Biochem. J.* **14**, 553.
— (1922). *Phil. Mag.* **44**, 897.
Bütschli (1892). *Untersuchungen über mikroskopische Schaume*, Leipzig.
— (1896). *Über den Bau quellbarer Körper*, Göttingen.
— (1898). *Untersuchungen über Strukturen*, Leipzig.
— (1900). *Untersuchungen über den Mikrostruktur...Kieselsäure-gallerten*, Heidelberg.
Dakin (1920). *J. Biol. Chem.* **44**, 499.
Frankenhein (1835). *Die Lehre von der Kohäsion*, Breslau.
Hatschek (1914). *Koll. Z.* **15**, 226.
— (1917). *Trans. Farad. Soc.* **12**, 17.
— (1920). *The physics and chemistry of colloids*. A discussion, 1921.
Loeb (1922). *Proteins and the theory of colloidal behaviour*, New York.
McBain (1920). *The physics and chemistry of colloids*. A discussion, 1921.
Menz (1909). *Z. physikal. Chem.* **66**, 137.
Moeller (1916). *Koll. Z.* **19**, 205.
— (1917). *Koll. Z.* **20**, 257.
Nägeli (1858). *Pflanzenphysiologische Untersuchungen*, Heft 7, Zurich.
Walpole (1913). *Koll. Z.* **13**, 241.
Weimarn (1914). *Zur Lehre von den Zuständen der Materie*, Dresden.
Wiedemann and Lüdeking (1885). *Ann. Phys. Chem.* **25**, 147.
Zsigmondy (1911). *Z. anorg. Chem.* **71**, 356.
— and Bachmann (1912). *Koll. Z.* **11**, 145.