LXXIV. WOOD CELLULOSE.

III. THE "RESISTANT PORTIONS."

BY DAVID JAMES BELL.

*From the Chemistry Research Laboratories of the United College of St Salvator
and St Leonard, The University of St Andrews.*

(Received April 30th, 1932.)

THE application by the author [1932, 1] of the methylation process to α -celluloses of wood has revealed a definite difference between wood cellulose and that from cotton and esparto, the only other varieties similarly investigated. Etherification of the wood celluloses could not be carried beyond a methoxyl content of 37–39 % despite the fact that, under identical conditions, a very resistant specimen of cotton could be methylated almost to the theoretical maximum. Cleavage of the wood methylates yielded a fully-methylated portion which manifested itself as 2:3:6-trimethyl-methylglucoside. The remainder of the starting material was apparently unaffected, appeared as an insoluble amorphous substance of methoxyl content 27–30 %, and proved resistant to further methylation above 30–32 % of methoxyl. These "resistant portions" form the subject of the present paper.

Further work by the author [1932, 2] on the acetates of the wood celluloses showed that the properties of the acetyl derivatives could be correlated with the proportion of resistant material contained in the polysaccharide. Increase in the amount of resistant material was accompanied by a corresponding increase in the specific rotation (in chloroform) in the dextro-sense. It was further shown that this resistance survived acetylation, de-acetylation and methylation, resulting in the formation of a soluble methylate of "depolymerised wood cellulose," thereby showing that mechanical properties (fibrous structure) or physical condition (high degree of polymerisation) were not in themselves factors inhibiting etherification, or producing resistance to hydrolysis.

From the first, work was hampered by an unavoidable lack of material but, as will be seen, a considerable amount of data regarding the "resistant portions" has been accumulated. Much of the evidence points to the "resistant portions" of different woods being chemically indistinguishable. Such a view, attractive as it seems, is put forward with every reservation on the grounds that we have here to deal with physical measurements relating to complex amorphous substances of unknown constitution.

It is now advantageous to detail the various steps involved in the investigation of the wood celluloses; the following scheme in the later stages (VI,

VII and VIII) could not, in every instance, be carried out, owing to insufficient quantities of material being available.

Stage III. Effect of the methylating reagents on the "resistant portions."

Repeated treatment with methyl sulphate and alkali, under varied conditions, resulted in only a small increase in the methoxyl contents of the resistant fractions. The products were white amorphous powders, insoluble in all solvents and showing no trace of organised structure, fibrous or otherwise, when examined microscopically (Table I).

Table I.

Source of cellulose	<i>Quercus pedunculata</i>	<i>Fagus sylvatica</i>	Thiriëna pulp	Sitka spruce
"Resistant portion," yield %	40.1	23.9	22.5	19.1
"Resistant portion," OMe %	30.0	27.7	28.0	27.8
"Resistant portion," OMe % after methylation	32.2	31.5	30.3	29.6
Methylated cellulose, OMe %	38.8	39.1	39.0	37.3

Stage IV. Acetylation of the fully-methylated "resistant portions."

Subjection of the fully-methylated materials to acetylation by Barnett's method [1921] produced derivatives which displayed virtually identical analytical data and optical activities. The methoxyl contents were all slightly lower than was to be expected from the composition of the starting materials; a similar fact was observed by Denham and Woodhouse [1913] on acetylation

partially methylated cotton. The acetates were colourless, amorphous substances, easily soluble in all organic solvents except the paraffins; the solutions were clear and of inconsiderable viscosities. The specific rotations in chloroform were all identical, and the solids possessed closely similar melting-points. The apparent identity of these products is strongly emphasised by consideration of Table II.

Table II.

Source of "resistant portion"	<i>Quercus pedunculata</i>	<i>Fagus sylvatica</i>	Thiriena pulp	Sitka spruce
Acetate, yield %	89.6	89.0	84.1	95.7
" OMe %	23.1	22.4	23.2	22.2
" COCH ₃ %	17.9	17.7	17.8	17.9
" $[\alpha]_D$ in CHCl ₃	+18.7°	+18.2°	+18.7°	+18.2°
" M.P.	224-30°	226-30°	224-27°	230°

Calculated for C₁₀H₁₈O₆: OCH₃, 26.7 %
COCH₃, 18.3 %

Stage V. Cleavage of the acetyl derivatives.

Twenty-four hours' treatment at 120° with 2 % hydrogen chloride in methyl alcohol sufficed for complete hydrolysis of the acetates. The products were worked up in the manner described in a previous communication on wood cellulose [1932, 1]; the results of the experiments are detailed in Table III.

Table III.

Source of "resistant portion"	<i>Fagus sylvatica</i>	Thiriena pulp	Sitka spruce
Cleavage products isolated, %	78.8	88.3	70.0
Trimethyl-methylglucoside, %	31.1	32.9	32.4
Dimethyl-methylglucoside, %	44.2	44.1	55.5
Residual material, %	(accidentally lost)	10.5	4.1
" OMe %	—	23.9	—

Calculated for C₇H₁₄O₆: OMe, 29.8 %.

It will be seen that the proportions of the different cleavage products show agreement in the different experiments. The increased amount of dimethyl-methylglucoside isolated from the Sitka spruce material is compensated by a corresponding decrease in the amount of residue. The latter was a hard glass and had a methoxyl content too low for monomethyl-methylglucoside, and may have been either unhydrolysed starting-material, or else impure monomethyl-methylglucoside.

Stage VI. The trimethyl-methylglucoside.

This portion of the cleavage products proved, in each case, to consist of 2:3:6-trimethyl-methylglucoside. No evidence of isomeric glucoses was found, and tetramethylglucose was present only in very minute traces. The occurrence of the latter compound need not be attributed to structural factors, for it is obvious that adventitious chains derived from the non-resistant fraction could remain associated with the resistant portions after the separation treatment.

Stage VII. The dimethyl-methylglucoside (material from Thiriena pulp).

The absence of substitution in the fourth hydroxyl group was proved by the fact that complete condensation took place in the cold between the free sugars and methyl alcohol containing hydrogen chloride. Employing the methods devised in this Laboratory by Rutherford [1932] and Oldham and Rutherford [1932] the amounts of 2:3-, 2:6- and 3:6-dimethyl-methylglucoside were determined in this portion of the cleavage products. The results were as follows:

2:3-Dimethyl-methylglucoside	4.4 %
3:6- " "	37.0 %
2:6- " "	58.6 %

Stage VIII. The residual material.

A portion of this material was found to distil at 190°/0.05 mm. After aqueous acid hydrolysis strong reduction of Fehling's solution was observed; the methoxyl content was 30.3 % (calculated for monomethyl-methylglucoside, 29.8 %). There is little doubt that the distillate was mainly this glucoside. The reducing solution was treated in the usual way with phenylhydrazine and crystals of an osazone-like substance were obtained, unfortunately in too small amount to permit of examination beyond that of melting-point determination. After recrystallisation, the crystals melted at 178° which is the melting-point of 6-monomethylglucosazone. The mixed melting-point with the latter substance showed no depression, while admixture with 3-monomethylglucosazone caused considerable lowering. A portion, therefore, of this residual material appears to consist of 6-monomethyl-methylglucoside.

Comparative experiments on partially methylated cotton.

Cotton cellulose methylated to the extent of 30.3 % of methoxyl was treated with Barnett's reagents under conditions identical with those of the acetylation of the "resistant portions." The insoluble material isolated amounted to 74.4 % of the calculated amount, had a methoxyl content of 16.7 % and showed $[\alpha]_D$ in chloroform, +10.0°. The material, therefore, differed markedly from that portion of the wood cellulose composing the "resistant portion." The noticeable loss of highly methylated material is in accordance with the observations of Denham quoted above.

The "resistant portion" of methylated depolymerised wood cellulose (Thiriena pulp).

Cleavage of the methylated depolymerised wood cellulose showed that, although the resistance to etherification had persisted, the resistant fraction no longer completely defied hydrolysis. The insoluble material isolated after 400 hours' treatment with 1 % hydrogen chloride in methyl alcohol had a methoxyl content of 29.9 % and exhaustive methylation raised this value to 32.3 %. The material was completely insoluble in chloroform, and after

acetylation a product apparently identical with the acetate of the "resistant portion" of the intact wood cellulose was obtained in 75.8 % yield. The analytical data of this material are compared with the corresponding values of the derivative of the depolymerised cellulose in Table IV.

Table IV.

Source of material	Intact cellulose	Depolymerised cellulose
"Resistant portion," yield %	22.5	14.0
" " OMe %	28.0	29.9
Acetyl derivative, yield %	84.1	75.8
" " OMe %	23.2	24.1
" " COCH ₃ %	17.8	16.9
$[\alpha]_D$ in chloroform of acetyl derivative	+18.7°	+18.9°
M.P. of acetyl derivative	224–227°	225–228°

As will be seen, apparently no significant change has occurred in the properties of the acetylated resistant fractions, although it must be admitted that the means of determining similarity of such substances are few and by no means reliable.

EXPERIMENTAL.

The general methods have been previously detailed in the other communications on wood cellulose.

Acetylation of the "resistant portions."

This was effected by Barnett's method, at a temperature of 50°. Solution of the methylated material in the reagents rapidly took place: the clear, yellow solution was poured into ten times its bulk of water containing a little sodium acetate, and the solid which separated collected on a filter and dried on filter-paper. The product was dissolved in chloroform, the solution dried over anhydrous sodium sulphate, filtered and the solvent evaporated under diminished pressure. The acetate was deposited as a colourless film, the properties of which have been detailed above. The relevant experimental data are given in Table V.

Table V.

Source of "resistant portion"	Wt. of material g.	Yield g.
<i>Quercus pedunculata</i>	2.175	2.379
<i>Fagus sylvatica</i>	1.880	1.942
Thiriena pulp	1.381	1.302
Sitka spruce	2.363	2.763
Depolymerised Thiriena pulp	0.514	0.476

Cleavage of the acetates of the "resistant portions."

The acetate (1 part) was heated for 24 hours with 2 % methyl alcoholic hydrogen chloride (25 parts) at 80°. Complete solution of the material rapidly took place. The reaction products were worked up as previously described. The data are given in Table VI.

Table VI.

Source of "resistant portion"	<i>Fagus sylvatica</i>	Thiriena pulp	Sitka spruce
Total cleavage products, g.	1.541	4.506	1.110
Trimethyl-methylglucoside, g.	0.485	1.481	0.360
Dimethyl-methylglucoside, g.	0.680	1.988	0.616
Residual material, g.	0.384	0.642	0.046
Wt. of acetate taken, g.	2.389	5.942	1.687

SUMMARY.

1. The "resistant portions" of wood celluloses cannot be methylated beyond a stage at which the composition of the methylate corresponds with that of a dimethyl-cellulose.

2. Acetyl derivatives of the "resistant portions" have been prepared. These derivatives from the different sources are soluble in a wide range of solvents and display a very close similarity in properties, strongly suggesting that they are identical. While the available data may lead to the conclusion that these acetates are one and the same substance, it does not follow that the "resistant portions," as they exist in the intact polysaccharide, are themselves identical.

3. The resistant material isolated on cleavage of fully methylated depolymerised wood cellulose displays properties very closely similar to those of the "resistant portion" of the corresponding intact methylated cellulose. This possibly indicates that Barnett's reagents effect depolymerisation until a definite level of complexity is attained, after which this action virtually ceases.

4. Cotton cellulose, methylated to 30 % of methoxyl, yields an acetyl derivative which displays no properties common to the acetates of the "resistant portions."

5. The cleavage products of the acetyl derivatives of the "resistant portions" have been shown to be a mixture of 2:3:6-trimethylglucoside, dimethyl-methylglucosides, and monomethyl-methylglucosides. In the case of Thiriena pulp cellulose the mixture of dimethyl-methylglucosides was shown to consist mainly of the 2:6- and 3:6- with a little of the 2:3-dimethyl-methylglucosides. Indication of the presence of 6-monomethyl-methylglucoside in the residual material was also obtained.

The author desires to place on record his indebtedness to Sir J. C. Irvine for the interest which he took in this work, and to the Carnegie Trust for the grant of a Senior Scholarship.

REFERENCES.

- Barnett (1921). *J. Soc. Chem. Ind.* **40**, 8 T.
 Bell (1932, 1). *Biochem. J.* **26**, 590.
 — (1932, 2). *Biochem. J.* **26**, 598.
 Denham and Woodhouse (1913). *J. Chem. Soc.* 1735.
 Oldham and Rutherford (1932). *J. Amer. Chem. Soc.* **54**, 366.
 Rutherford (1932). (Private communication.)