Removal of hexavalent chromium from aqueous solution by iron nanoparticles^{*}

NIU Shao-feng (牛少凤)^{1,2}, LIU Yong (刘永)¹, XU Xin-hua (徐新华)^{†1}, LOU Zhang-hua (楼章华)²

(¹Department of Environmental Engineering, Zhejiang University, Hangzhou 310027, China)

(²School of Civil Engineering and Architecture, Zhejiang University, Hangzhou 310027, China)

[†]E-mail: xhxu@hzcnc.com

Received June 29, 2005; revision accepted July 24, 2005

Abstract: Groundwater remediation by nanoparticles has received increasing interest in recent years. This report presents a thorough evaluation of hexavalent chromium removal in aqueous solutions using iron (Fe⁰) nanoparticles. Cr(VI) is a major pollutant of groundwater. Zero-valent iron, an important natural reductant of Cr(VI), is an option in the remediation of contaminated sites, transforming Cr(VI) to essentially nontoxic Cr(III). At a dose of 0.4 g/L, 100% of Cr(VI) (20 mg/L) was degraded. The Cr(VI) removal efficiency decreased significantly with increasing initial pH. Different Fe⁰ type was compared in the same conditions. The reactivity was in the order starch-stabilized Fe⁰ nanoparticles > Fe⁰ nanoparticles > Fe⁰ powder > Fe⁰ filings. Electrochemical analysis of the reaction process led to the conclusion that Cr(OH)₃ should be the final product of Cr(VI). Iron nanoparticles are good choice for the remediation of heavy metals in groundwater.

Key words: Hexavalent chromium, Iron nanoparticles, Starch, Stabilize, Remediation

doi:10.1631/jzus.2005.B1022

Document code: A

CLC number: X703; X131.2

INTRODUCTION

Chromium is a commonly identified contaminant in soils and groundwater and is widely applied in industries. In the United States, it is considered a major pollutant. Cr(VI) is toxic, carcinogenic to human and animals. In the environment Cr(VI)'s great subsurface mobility does great harm to the environment. In contrast, Cr(III) is much less toxic and immobile and can be a nutriment for human and animals. Therefore, reduction of Cr(VI) to Cr(III) is favorable for the environment and feasible method in the remediation of environmental sites.

Much research has focused on the remediation of Cr(VI) and many treatment processes have been developed. Physio-chemical adsorption has long been

researched (Bowman, 2003; Hideaki *et al.*, 2002), but the cost is high and the Cr(VI) is just transferred but not removed. Bioremediation by strains of bacteria (Chen and Hao, 1998) can effectively degrade Cr(VI) and is an economically favor but the bactericidal toxicants at many waste sites would limit their growth and effectiveness. Chemical reduction is known to remove Cr(VI) rapidly and effectively. Many reductants were employed such as H₂S, Fe²⁺, Fe⁰, etc. (Hua and Deng, 2003; Buerge and Hug, 1999). Cr(VI) reduction by Fe⁰ (Alowitz and Scherer, 2002; Ponder *et al.*, 2000; Powell *et al.*, 1995; Pratt *et al.*, 1997) appears to be one of the most promising technologies. Powell *et al.* (1995) suggested that the mechanisms of Cr(VI) reduction by Fe⁰ is a cyclic and consists of multiple reactions electrochemical corrosion. Alowitz and Scherer (2002) evaluated the effect of iron metal type, Fe⁰ area concentration and pH value on the rate of Cr(VI) reduction by Fe⁰. Ponder *et al.* (2000) tested nanoscale Fe⁰ particles for their ability to separate and

[‡] Corresponding author

^{*} Project (No. 20407015) supported by the National Natural Science Foundation of China

immobilize Cr(VI) ions from aqueous solution. Fe^0 nanoparticles, due to their extremely high effective surface area, can enhance the reduction rates markedly. However, because of the extremely high reactivity, the initially formed nanoparticles tend to either react rapidly with surrounding media [e.g., dissolved oxygen (DO) or water] or agglomerate rapidly, resulting in the formation of numerous large particles and rapid loss in reactivity. A new process must be found to prepare physically more stable Fe^0 nanoparticles. Raveendran *et al.* (2003) showed that starch could serve as a good dispersant for preparing nanoscale Ag particles in aqueous media. He and Zhao (2005) prepared and characterized a new class of starch-stabilized bimetallic nanoparticles. Starch, a “greener” for environmental applications, could apparently prevent agglomerated nanoparticles from becoming more reactive.

A range of Fe(0) and Fe(II) bearing materials promoted reduction and precipitation of Cr(VI). The net reactions of Cr(VI) reduction and coprecipitation of Cr(III) and Fe(III) are (Lee *et al.*, 2003):

The primary objective of this work is to prepare Fe^0 or starch-stabilized Fe^0 nanoparticles for degradation of Cr(VI). The specific objectives are to (1) characterize the Fe^0 nanoparticles with environmental scanning electron microscope (ESEM); (2) quantify the effect of Fe^0 nanoparticles' dosage, Cr(VI) concentration, and initial pH on the rate of Cr(VI) reduction; (3) compare the effectiveness of Cr(VI) reduction by different type of Fe^0 particles; (4) analyse the reaction process electrochemically.

MATERIALS AND METHODS

Chemicals

All chemical reagents, such as $\text{K}_2\text{Cr}_2\text{O}_7$, starch, $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$, sulfuric acid (H_2SO_4) and acetone were analytical reagent grade. The starch was purchased from Linghu foodstuff chemical plant of Huzhou, Zhejiang. The waste iron filings (30~40 mesh) were obtained from Machine factory of Zhejiang University. The commercial Fe^0 powder (>98%, <200 mesh)

was purchased from Jinshan Metallurgical Factory (China). Both iron particles were pretreated by wash using acetone and sulfuric acid solution (pH=2), which created fresh sites for oxidation and made the surface more active (Ruiz *et al.*, 1995). Deionized water was used for preparing all solutions.

The Fe^0 and starch-stabilized Fe^0 nanoparticles were synthesized before use. The preparation of Fe^0 nanoparticles and starch-stabilized Fe^0 nanoparticles followed the methods described by Wei *et al.* (2004) and He and Zhao (2005), respectively. The iron nanoparticles were synthesized by dropwise addition of stoichiometric amounts of NaBH_4 aqueous solution into a 1000 ml three-necked flask containing $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ aqueous solution simultaneously with electrical stirring at ambient temperature. The ferrous iron was reduced to zero-valent iron according to the following reaction:

The Fe^0 nanoparticles were then rinsed several times with deionized water.

In the preparation of starch-stabilized Fe^0 nanoparticles, $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ aqueous solution was added to a starch solution in a 1000 ml three-necked flask to yield a solution with desired Fe concentration and 0.2% starch concentration. The next steps were the same as those for preparation of Fe^0 nanoparticles.

Batch experiments

The batch experiments for the reduction of Cr(VI) were performed in the same three-necked flask into which Fe^0 nanoparticles were introduced. Then $\text{Cr}_2\text{O}_7^{2-}$ aqueous solution was added into the flask. The reaction solution was stirred under nitrogen flow and periodically sampled by glass syringe. The sample was filtered immediately through 0.22 μm membrane filters for analysis.

The effect of various parameters on the Cr(VI) reduction was researched. Fe^0 nanoparticles concentration used in this study was 0.1 to 0.4 g/L. The initial Cr(VI) concentration was 10 to 25 mg/L, and the initial pH was 3 to 10. Different size Fe^0 particles at desired concentration were compared.

Characterization and analytical methods

The morphology of the metal particles was ob-

served under an XL30-ESEM at 100 kV. Prior to scanning the fresh prepared metal particles were dried in vacuum at 25 °C for 60 min. Cr(VI) was determined spectrophotometrically with diphenylcarbazide at 540 nm using UV-VIS spectrophotometer (TU-1800PC, Beijing, China).

RESULTS AND DISCUSSION

Characterization of both Fe^0 nanoparticles

Fig.1 compares the ESEM micrographs of the Fe^0 nanoparticles before or after reaction. Both micrographs show that the Fe^0 nanoparticles do not appear as discrete particles but form much larger dendritic flocs whose size could reach micron scale. The aggregation is attributed to the magnetic forces among the Fe particles. Similar phenomenon was observed by other researchers (Wei *et al.*, 2004; He and Zhao, 2005). Fig.1a shows the loose structure and fine tentacles of Fe^0 nanoparticles so that greater reactivity is expected. In contrast, Fig.1b shows tighter structure and thicker tentacles owing to the form of the hydroxide solid $(\text{Cr}_x\text{Fe}_{1-x})(\text{OH})_3$ which covered the surface of the Fe^0 nanoparticles.

Fig.1 ESEM image of Fe^0 nanoparticles (a) before reaction and (b) after reaction

Fig.2 compares the ESEM images of the Fe^0 nanoparticles without or with starch stabilizer. Fig.2a shows that Fe^0 nanoparticles formed much larger dendritic flocs without starch. Fig.2b shows discrete Fe^0 nanoscale particles in the presence of starch (splinter-shaped crystalloid). The presence of starch effectively prevents agglomeration of the iron particles and thus maintains high surface area and great reactivity.

Fig.2 ESEM image of (a) Fe^0 nanoparticles without starch and (b) starch-stabilized Fe^0 nanoparticles

Effect of Fe^0 nanoparticles concentration

Four Fe^0 nanoparticles concentrations were employed in this study. Fig.3 shows that the increase of Fe^0 concentration greatly enhanced the removal efficiency. All Cr(VI) was removed when the Fe^0 mass concentration was 0.4 g/L, but only 26% was removed when the Fe^0 mass concentration was 0.1 g/L. Cr(VI) concentration decreased dramatically in the initial one minute, then slightly decreased in the later reaction. It was apparent that there was an initial sorption phase which appeared to be complete after 1 min. Thus, the overall mechanism is more complicated than just chemical reaction.

Fig.3 Effect of Fe^0 nanoparticles concentration on the Cr(VI) removal efficiency

$C_{\text{Cr(VI)}}=20 \text{ mg/L}$, $\text{pH}=7.0$, $T=25^\circ\text{C}$, $\omega=600 \text{ r/min}$

Effect of initial Cr(VI) concentration

Fig.4 shows results of batch experiments conducted at concentrations of 10 to 25 mg/L. The Cr(VI) removal efficiency increased inversely with the concentration of initial Cr(VI) , 42% at concentration of 25 mg/L and 100% at concentration of 10 mg/L. The proper mass ratio of Fe^0 nanoparticles to Cr(VI) was about 20:1.

Fig.4 Effect of initial Cr(VI) concentration on the Cr(VI) removal efficiency

$C_{\text{Fe}}=0.2 \text{ g/L}$, $\text{pH}=7.0$, $T=25^\circ\text{C}$, $\omega=600 \text{ r/min}$

Effect of the initial pH value

As shown in Fig.5, the Cr(VI) removal efficiency increased significantly with decreasing pH, mainly because in acid condition, the accelerated corrosion of Fe^0 enhanced the reaction rate. In the initial five minutes, the plots below pH 5 decreased rapidly, in-

dicating that the Fe^0 nanoparticles were still high reactivity. In contrast, the $\text{pH}>8$ plots decreased gently because of the form of Fe(OH)_3 during high pH value. The almost horizontal segment of the plots after sixty minutes was caused by Fe^0 oxidation.

Fig.5 Effect of initial pH value on the Cr(VI) removal efficiency

$C_{\text{Fe}}=0.2 \text{ g/L}$, $C_{\text{Cr(VI)}}=20 \text{ mg/L}$, $T=25^\circ\text{C}$, $\omega=600 \text{ r/min}$

Comparison of different Fe^0 type

Fig.6 shows that the removal rates, especially for Fe^0 nanoparticles and starch-stabilized Fe^0 nanoparticles, were rapid in the first minute. There was an initial sorption phase combined with Cr(VI) reduction, which were enhanced with the increasing surface area of Fe^0 . After the first minute, the Cr(VI) removal rates were significantly slower. The removal efficiency was around 10% for Fe^0 filings and powder in 60 min,

Fig.6 Comparison of different Fe^0 type on the Cr(VI) removal efficiency

$C_{\text{Fe}}=0.2 \text{ g/L}$, $C_{\text{Cr(VI)}}=20 \text{ mg/L}$, $T=25^\circ\text{C}$, $\text{pH}=7.0$, $\omega=600 \text{ r/min}$

but was 55% and 98% for Fe^0 nanoparticles and starch-stabilized Fe^0 nanoparticles, respectively. The reactivity was in the order starch-stabilized Fe^0 nanoparticles > Fe^0 nanoparticles > Fe^0 powder > Fe^0 filings. The comparison shows that Fe^0 nanoparticles could reach significantly higher efficiency than Fe^0 filings or powder, but could not maintain the activity for long because of the agglomeration. While starch-stabilized Fe^0 nanoparticles were apparently prevented to agglomerated to become more reactive and keep longer activity.

Electrochemical analysis of the reaction process

The standard reduction potentials of $E_{\text{Fe(II)/Fe(0)}}^\ominus$ and $E_{\text{Cr(VI)/Cr(III)}}^\ominus$ are -0.44 V and 1.33 V, respectively. When mixed with $\text{Cr}_2\text{O}_7^{2-}$, Fe^0 would be corroded and dissolved, causing the reduction of Cr(VI) to Cr(III). The standard reduction potential of $E_{\text{Cr(III)/Cr(0)}}^\ominus$ is -0.74 V, which is lower than that of Fe^0 . It means that the Cr(III) or Cr(III) hydroxide should be the steady product in the reaction. In fact, several investigators have reported that the removal mechanism involves reduction of highly soluble $\text{Cr}_2\text{O}_7^{2-}$ to weakly soluble Cr(III) compounds at the surface of the iron. Spectroscopic data showed that Cr(OH)_3 and mixed Cr(III)/Fe(III) hydroxides are precipitated on the iron surface (Ponder *et al.*, 2000; Powell *et al.*, 1995; Pratt *et al.*, 1997). The net reactions of Cr(VI) reduction with Fe(0) and coprecipitation of Cr(III) and Fe(III) could be expressed by Eq.(1) and Eq.(2). No dissolved Cr(III) was detected during the reaction, which indicated that all the Cr(III) was coprecipitated with Fe(III). This observation is consistent with former observation (Pratt *et al.*, 1997).

Insight into the process of Cr(VI) removal can also be obtained by detecting the reduction potential E and pH values in solution. The E and pH values of the $\text{Cr}_2\text{O}_7^{2-}$ solution (10^{-4} mol/L) were 0.239 V and 7.00 , respectively. In Fig.7, the reduction potential E decreased with increasing pH initially in the reaction, which indicates that Cr(VI) trended to form Cr(OH)_3 . After achieving minimum, E increased with the decreasing pH due to the form of Cr(III)/Fe(III) hydroxides which covered the surface of Fe^0 nanoparticles to cut down the reaction activity. The detected point during the reaction was always in the area where

Cr(OH)_3 was dominant. This observation led to the conclusion that Cr(OH)_3 should be the final and dominant product of Cr(VI).

Fig.7 The E -pH diagram of chromium ($C_{\text{total Cr}}=10^{-4}$ mol/L)

Δ: Actually detected in the reaction, $C_{\text{Fe}}=0.2$ g/L, $C_{\text{Cr(VI)}}=10^{-4}$ mol/L, $T=25$ °C, $\omega=600$ r/min

CONCLUSION

Reduction of Cr(VI) by Fe^0 nanoparticles as reductant was studied using potassium dichromate solution as the model contaminant. The concentration of Fe^0 nanoparticles had significant effect on the reduction of Cr(VI). When the mass ratio of Fe^0 to Cr(VI) was 20:1, 100% removal efficiency was achieved. The reaction occurred in broad pH value scale and the reaction efficiency increased significantly with decreasing initial pH. The starch-stabilized Fe^0 nanoparticles exhibited higher removal efficiency because starch as a good dispersant could prevent Fe^0 nanoparticles agglomeration. Electrochemical analysis of the reaction process showed that Cr(OH)_3 should be the final and dominant product of Cr(VI). The remediation of Cr(VI) was widely researched before. This study indicated that Fe^0 nanoparticles, especially those which were starch-stabilized, can yield a high removal efficiency in the remediation of Cr(VI)-contaminated soils and groundwater.

References

- Alowitz, M.J., Scherer, M.M., 2002. Kinetics of nitrate, nitrite, and Cr(VI) reduction by iron metal. *Environ. Sci. Technol.*, **36**:299-306.
- Bowman, R.S., 2003. Applications of surfactant-modified zeolites to environmental remediation. *Microporous and*

- Mesoporous Materials*, **61**:43-56.
- Buerge, I.J., Hug, S.J., 1999. Influence of mineral surfaces on chromium(VI) reduction by iron(II). *Environ. Sci. Technol.*, **33**:4285-4291.
- Chen, J.M., Hao, O.J., 1998. Microbial chromium(VI) reduction. *Critical Rev. Environ. Sci. Technol.*, **28**:219-251.
- He, F., Zhao, D., 2005. Preparation and characterization of a new class of starch-stabilized bimetallic nanoparticles for degradation of chlorinated hydrocarbons in water. *Environ. Sci. Technol.*, **39**:3314-3320.
- Hideaki, Y., Toshiyuki, Y., Takashi, T., 2002. Adsorption of chromate and arsenate by amino-functionalized MCM-41 and SBA-1. *Chem. Mater.*, **14**:4603-4610.
- Hua, B., Deng, B., 2003. Influences of water vapor on Cr(VI) reduction by gaseous hydrogen sulfide. *Environ. Sci. Technol.*, **37**:4771-4777.
- Lee, T., Lim, H., Lee, Y., Park, J., 2003. Use of waste iron metal for removal of Cr(VI) from water. *Chemosphere*, **53**:479-485.
- Ponder, S.M., Darab, J.G., Mallouk, T.E., 2000. Remediation of Cr(VI) and Pb(II) aqueous solutions using supported, nanoscale zero-valent iron. *Environ. Sci. Technol.*, **34**:2564-2569.
- Powell, R.M., Puls, R.W., Hightower, S.K., Sabantini, D.A., 1995. Coupled iron corrosion and chromate reduction: mechanisms for subsurface remediation. *Environ. Sci. Technol.*, **29**:1913-1922.
- Pratt, A.R., Blowes, D.W., Ptacek, C.J., 1997. Products of chromate reduction on proposed subsurface remediation material. *Environ. Sci. Technol.*, **31**:2492-2498.
- Raveendran, P., Fu, J., Wallen, S.L., 2003. Complete "green" synthesis and stabilization of metal nanoparticles. *J. Am. Chem. Soc.*, **125**:13940-13941.
- Ruiz, N., Seal, S., Reinhart, D., 1995. Surface chemical reactivity in selected zero-valent iron samples used in groundwater remediation. *Journal of Hazardous Materials*, **B80**:107-117.
- Wei, J.J., Xu, X.H., Liu, Y., 2004. Kinetics and mechanism of dechlorination of *o*-chlorophenol by nanoscale Pd/Fe. *Chem. Res. Chinese U.*, **20**:73-76.

Welcome Contributions to JZUS-B

Introducing a New One----Journal of Zhejiang University SCIENCE B (Biomedicine and Biotechnology), ISSN 1673-1581, Monthly

- JZUS-B is indexed & abstracted by the famous database MEDLINE, and will also be accepted by PubMed Central (PMC) which is a new core full text-online database of MEDLINE in Life Science Periodicals and today, is among 189 Biology and Science journals accepted by PMC. JZUS-B will be the only one from China.
- JZUS-B has linked its website (<http://www.zju.edu.cn/jzus>) to:
MEDLINE: <http://www.ncbi.nlm.nih.gov/PubMed>;
CrossRef: <http://www.crossref.org>; (doi:10.1631/jzus.xxxx.Bxxxx), etc.
 Therefore, your latest research would be rapidly spread on-line and read by researchers in biology and medicine area in the world.
- JZUS-B has an International Editorial Board, International Peer Review System, International Author-Pool and International network, all of which are highly appraised by MEDLINE, Ei and SCI, etc.

Contributions requests

- (1) Electronic manuscript should be sent to **jzus@zju.edu.cn** only. If you have any question, please feel free to visit our website: <http://www.zju.edu.cn/jzus>, and hit "For Authors".
- (2) English abstract should include Objective, Method, Result and Conclusion.
- (3) Tables and figures could be used to prove your research result.
- (4) Full text of the Science Letters should be in 3-4 pages. The length of articles and reviews are not limited.
- (5) Please visit our website (<http://www.zju.edu.cn/jzus/pformat.htm>) to see paper format.