Published in final edited form as:

Curr Opin Biotechnol. 2007 October ; 18(5): 448–453.

Polymers to Direct Cell Fate by Controlling the Microenvironment

R. Warren Sands¹ and David J. Mooney^{1,†}

¹ *Harvard University, School of Engineering and Applied Sciences, Cambridge, MA 02138 USA*

Abstract

Enhanced understanding of the signals within the microenvironment that regulate cell fate has led to the development of increasingly sophisticated polymeric biomaterials for tissue engineering and regenerative medicine applications. This advancement is exemplified by biomaterials with precisely controlled scaffold architecture, that regulate the spatio-temporal release of growth factors and morphogens, and respond dynamically to microenvironmental cues. Further understanding of the biology, qualitatively and quantitatively, of cells within their microenvironments and at the tissue-material interface will expand the design space of future biomaterials.

Introduction

Tissue engineering and regenerative medicine hold the promise to treat and even cure a wide range of diseases ranging from acute pathology (e.g. traumatic injury) to chronic diseases (e.g. cardiovascular disease, cancer, and diabetes) and materials will typically play a prominent role in these therapies. In addition to maintaining, replacing or regenerating lost, diseased, or damaged tissues, tissue engineering and regenerative medicine may provide artificial tissues for extracorporeal support, pharmacologic testing, or the enhancement of normal tissue function. The field has already contributed model systems to facilitate basic biological studies and led to the development of FDA approved therapies [1]. Materials are a cornerstone of tissue engineering and regenerative medicine and have grown from inert mechanical supports, physical bridges, or cell and drug delivery vehicles with poorly understood biologic functions or limited control to dynamic substrates that serve as cell instructive materials by directing interactions at the tissue-material interface. By better understanding and incorporating elements of the cellular microenvironment, this new generation of materials promises to allow greater control over cell fate and ultimate tissue structure and function. This review will address the recent progress in material designs and fabrication approaches that are leading to the development of increasingly multifunctional mimics of the native cellular microenvironment. As the fundamental biology of the cellular microenvironment is often the inspiration for material design, this review will begin with a brief discussion of the cellular milieu, and then highlight polymers that direct the tissue-material interface through the controlled presentation of specific cues in time or space, or in response to external signals. Finally, a discussion of current and potential future approaches to further develop a quantitative understanding of the biology within cellular microenvironments and at the tissue-material interface will be provided as this knowledge will enrich the palette for future polymer design. The chemistry and physical properties of materials are critical parameters for directing cell fate and are discussed as they pertain to the spatial control of the scaffold architecture, the spatial and temporal control of morphogen and growth factor delivery, and dynamic polymer design; for a more

[†]To whom correspondence should be addressed. David Mooney, Email: mooneyd@seas.harvard.edu.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

comprehensive review on these topics the reader is encouraged to refer to other recent reviews [2,3].

The cellular microenvironment

The cell is immersed in a dynamic landscape composed of insoluble macromolecules of the extracellular matrix (ECM), soluble bioactive factors, and neighboring cells (Figure 1). The landscape varies from tissue to tissue and changes during disease and aging. Three of the principle molecular signals within this environment include insoluble hydrated macromolecules, soluble molecules, and cell surface proteins [4]. These signals are sensed, integrated, and processed by the cell to determine behavior and function, and information is passed bi-directionally as the microenvironment is remodeled by the cells. Information is encoded within the chemical identity, localization, duration, and context of these molecular cues. Spatial cues are displayed in 3D [5] and can include signaling gradients such as that observed during chemo-, hapto-, and mechanotaxis. Moreover, spatial cues are found at many length scales. Architectures range from the nanometer to the centimeter length scales [2,6–10], exemplified by ECM fibers, cells, and tissue tubes, folds, and bends. In addition, the concentration, duration, and context of the molecular cues contain information that dictates cell fate. As exemplified by angiogenesis, certain growth factors initiate angiogenesis while a second group of growth factors induce maturation. Later, a third cohort of molecules maintains the integrity of the established vasculature [11,12]. If the appropriate concentration, duration, and context (e.g. presence and sequence of multiple factors) is not achieved, poor vascularization results. Finally, the microenvironment changes dynamically over time. The ECM is continually processed, degraded, and synthesized anew, altering the matrix's presentation of chemical cues and elasticity, and leaving behind proteolytic fragments and cryptic domains that in turn affect cellular activity [13,14]. Meanwhile, soluble bioactive factors are secreted and destroyed as the cells migrate, differentiate, proliferate, and undergo apoptosis.

Spatial control of the scaffold architecture

Polymeric materials designed in the past incorporated many signals found within the microenvironment, but typically only provided one or two cues in a static manner. The focus of current efforts is to dynamically encode the localization, duration, and context of multiple cues to adequately integrate signaling and direct cell fate in light of the host microenvironment. This aim requires control over architecture at multiple size scales, spatio-temporally regulated release of signaling molecules, and dynamic polymer design.

Within the past decade, a dramatic increase in the resolution of control over scaffold architecture has been achieved through microfabrication technologies and has led to the recent widespread use of this technology for tissue engineering and regenerative medicine applications. In comparison to traditional polymer processing methods, microfabrication, and more recently nanofabrication, may allow for design at the nanometer to the supramillimeter length scale (Figure 2) [15,16] and for exquisite control of the internal architecture of the material *a priori*, facilitating the patterning of immobilized chemicals, cells, and mechanical gradients [17]. High resolution spatial control could benefit a wide range of applications from artificial blood vessels with compliances that match host tissue to directional nerve guidance channels to aid neural regeneration. In many fabrication procedures, however, increased spatial resolution comes at the expense of long fabrication times. Thus, efforts are underway to create high throughput technologies suitable for bulk fabrication of a wide range of materials that can maintain spatial resolution.

Soft lithography and multiphoton photocrosslinking allow for submicrometer to supramillimeter spatial control. Soft lithography has been used with microfluidics to create

hydrogels with gradients of adhesive ligands and mechanical properties [18] and complex spatial gradients can be readily generated [19]. Increased 3D resolution down to the submicron range can be achieved with multiphoton photocrosslinking, but at the expense of fabrication time. To decrease processing time, mask-based methods for rapid prototyping have been developed [20] and could be further improved if used in tandem with a micro-mirror based masking device [21]. The utility of microfabrication techniques has been demonstrated in the design of 3D skin substitutes with an artificial epidermis containing micrometer scale features similar to the rete ridges and dermal papillae found in normal skin at the epidermal-dermal junction [22]. The depth and width of the engineered invaginations was demonstrated to influence keratinocyte stratification and differentiation.

Electrospinning has emerged as a prominent method for nanometer scale design not addressable with traditional microfabrication techniques, at the expense of control over internal scaffold architecture, void space connectivity, and mechanical properties. However, both synthetic and natural polymers can be electrospun into fibers with diameters ranging from the 10's of nanometers to several micrometers [23,24]. The goal of recent work has been to create more complex materials with defined internal architectures. To this end, composite materials and aligned fibers have been synthesized and utilized for vascular [25] and meniscal [26] tissue engineering applications, respectively. The modulus of tissues formed from aligned nanofibers can be dramatically increased as compared to unaligned fibers [26]. Finally, electric fields can be utilized during the electrospinning process to create oriented polymers within the nanofibers that further recapitulate the hierarchical design found within natural anisotropic ECM [27]. Soft lithography, multiphoton photocrosslinking, and electrospinning may be used in combination with other materials and processing methods to create scaffolds with even greater control over spatial properties to potentially enhance material performance.

Spatial and temporal control of morphogen and growth factor delivery

Additional direction over cell fate, beyond control of scaffold architecture, can be achieved through the spatio-temporal control of morphogen and growth factor delivery from the scaffolding material (Figure 3). Polymeric systems allow for independent regulation of the localization, duration, and availability of one or more soluble factors [28–30], while limiting the overall quantity of drug and minimizing the potential side effects of systemic dosing. Many techniques have been developed to regulate the kinetics and distribution of soluble factors, including multiple levels of encapsulation [31] as well as noncovalently bonding the bioactive factors to peptides with a range of dissociation constants mimicking ECM immobilization of growth factors [32]. With respect to the latter, phage display has been a powerful technique for identifying ligands that can tightly control the kinetics of factor release [32]. Dual delivery of multiple growth factors and morphogens has been achieved in multiple systems including poly (lactide-co-glycolide) (PLG) [31], oligo(poly(ethylene glycol) fumarate) [33], and alginate [34] scaffolds. Multiple factors can be delivered sequentially, simultaneously, or both, and these techniques can be combined with DNA or RNAi delivery to enable long-standing protein expression [35] or abrogation of expression [36]. The physiologic relevance of control over factors availability in time and space has been demonstrated by differentiation of stem cells [37], regulation over the extent of vascular network maturation with time [31], enhanced delivery and integration of transplanted cells [38], and the simultaneous formation of vascular networks at distinct stages of maturation in distinct spatial compartments [28].

Dynamic polymer design

One goal of biomaterial design is to develop systems that respond dynamically and reversibly to external or microenvironmental cues. At the extreme, a material may act as a microprocessor, a closed-loop system that surveys the external cues and the microenvironment, integrates the

information, and responds accordingly in real-time. It is unclear what level of complexity will be required for advanced tissue engineering and regenerative medicine applications; however, progress has been achieved to create polymeric systems that alter their properties in response to external or microenvironmental effectors. Polypyrrole based neural interfaces [39] and electroactive self-assembled monolayers [40] respond dynamically to external controls by functioning as electrical relays or surfaces that change conformation, respectively, in response to an electric potential. Other materials have been designed to respond directly to microenvironmental effectors. In the context of material degradation, materials have been developed that incorporate proteolytic domains [41] or bioactive linkers [42], and their degradation and function is altered by contacting cells. Other bioresponsive polymers change physical properties irreversibly with or without material degradation in response to small molecule receptors/ligands, or cell-secreted factors such as enzymes or enzymatic substrates [43]. Reversibility may often be desired and has been demonstrated in response to cellular ligands [44] and enzymes [45]. In the former, the structure of calmodulin was altered by ligand binding, leading to macroscopic shape changes in the hydrogel. In the latter, a pentapeptidic hydrogelator reversibly self-assembled or disassembled as a result of its phosphorylation state.

Expanding the design space and developing tomorrow's biomaterials

A bottleneck in the successful clinical implementation for many polymeric materials rests in our limited understanding of biological principles, both in the fundamental biology relating how cells interact with their environment, as well as in the quantitative aspects of these interactions. The increasingly important question is not how to make a material, but what and how biological cues should be incorporated into the material. To this end, the work of many interdisciplinary teams is helping to define the future landscape of polymer design.

A quantitative understanding of biological processes is and will be of great import for material design. Specifically, a quantitative understanding of the concentration, distribution, and interaction of molecules within normal, diseased, and regenerating systems as they change with time is important to be able to adequately design polymeric materials that can recapitulate these events. For example, correlation microscopy studies are defining integrin dynamics and focal adhesion-actin coupling [48]. Other studies are teasing apart the environmental factors that influence 3D cellular migration [48]; however, the quantitative relationship between ligand bonding and integrin dynamics, focal adhesion-actin coupling, and motility is largely unknown. This relationship can be explored using techniques such as fluorescence resonance energy transfer (FRET) to quantify bond formation in real-time 3D culture [49], and the subsequent dynamic process of cell-mediated ECM remodeling [52]. These events can ultimately be correlated with cellular activity, such as the mechanism of motility, and fabrication methods could then be applied to incorporate the appropriate signaling cues for the desired material performance. Additionally, recent studies suggest that the cellular reprogramming of somatic cells requires a delicate balance of factors [53–54]. As the expression of these factors becomes known, controlled delivery may allow for *in situ* reprogramming to generate stem cell and differentiated cell populations. Detailed knowledge of cues regulating cell fate is already being exploited to design materials that direct stem cell fate *in vivo* [38].

A number of studies have also revealed complex biological subtleties at the tissue-material interface that may greatly affect material performance. First, the influences of the material on the host, such as cell migration into a scaffold or differentiation of autologous stem cells within a polymer, will likely depend upon the sex, disease state, and age of the patient [55–57]. Second, most materials elicit immunogenic responses following transplantation, and even some polymers that are typically considered biocompatible may harbor subtle, but important immunogenic activity [58]. Understanding the role of these activities for a given material in a specific tissue engineering/regenerative medicine context may provide routes to minimize

detrimental immunologic activity. Conversely, harnessing immunologic activity may provide additional opportunities.

Conclusion

A deeper understanding of the interactions between cells and their microenvironments has led to the development of increasingly sophisticated polymeric materials for tissue engineering and regenerative medicine. Future advances in the biological sciences, particularly with respect to qualitative and quantitative biology of cells within their microenvironments and at the tissue-material interface, will increase the design space of future biomaterials.

Acknowledgements

We apologize to authors whose work could not be cited due to space constraints and would like to thank Alexander Augst and Prakriti Tayalia for helpful discussions. Our work in this area is supported by the National Institutes of Health (R37 DE013033, R01 DE013349 and R01 HL069957) and the US Army Research Laboratories and Research Office (DAAD-19-03-1-0168).

References

1. Fisher, JP.; Mikos, AG.; Bronzino, JD. Tissue Engineering. CRC Press; 2007.
2. Ingber DE. Cellular mechanotransduction: putting all the pieces together again. *Faseb Journal* 2006;20:811–827. [PubMed: 16675838]
3. Lutolf MP, Hubbell JA. Synthetic biomaterials as instructive extracellular microenvironments for morphogenesis in tissue engineering. *Nature Biotechnology* 2005;23:47–55.
4. Lodish, H.; Berk, A.; Matsudaira, P.; Kaiser, CA.; Krieger, M.; Scott, MP.; Zipursky, L.; Darnell, J. *Molecular Cell Biology*. 5. W. H. Freeman; 2003.
5. Cukierman E, Pankov R, Stevens DR, Yamada KM. Taking cell-matrix adhesions to the third dimension. *Science* 2001;294:1708–1712. [PubMed: 11721053]
6. Koo LY, Irvine DJ, Mayes AM, Lauffenburger DA, Griffith LG. Co-regulation of cell adhesion by nanoscale RGD organization and mechanical stimulus. *Journal of Cell Science* 2002;115:1423–1433. [PubMed: 11896190]
7. Cavalcanti-Adam EA, Volberg T, Micoulet A, Kessler H, Geiger B, Spatz JP. Cell spreading and focal adhesion dynamics are regulated by spacing of integrin ligands. *Biophysical Journal* 2007;92:2964–2974. [PubMed: 17277192]
8. Kong HJ, Hsiong S, Mooney DJ. Nanoscale cell adhesion ligand presentation regulates nonviral gene delivery and expression. *Nano Letters* 2007;7:161–166. [PubMed: 17212457]
9. McBeath R, Pirone DM, Nelson CM, Bhadriraju K, Chen CS. Cell shape, cytoskeletal tension, and RhoA regulate stem cell lineage commitment. *Developmental Cell* 2004;6:483–495. [PubMed: 15068789]
10. Nelson CM, Jean RP, Tan JL, Liu WF, Sniadecki NJ, Spector AA, Chen CS. Emergent patterns of growth controlled by multicellular form and mechanics. *Proceedings of the National Academy of Sciences of the United States of America* 2005;102:11594–11599. [PubMed: 16049098]
11. Yancopoulos GD, Davis S, Gale NW, Rudge JS, Wiegand SJ, Holash J. Vascular-specific growth factors and blood vessel formation. *Nature* 2000;407:242–248. [PubMed: 11001067]
12. Laschke MW, Harder Y, Amon M, Martin I, Farhadi J, Ring A, Torio-Padron N, Schramm R, Rucker M, Junker D, et al. Angiogenesis in tissue engineering: Breathing life into constructed tissue substitutes. *Tissue Engineering* 2006;12:2093–2104. [PubMed: 16968151]
13. Koshikawa N, Schenk S, Moeckel G, Sharabi A, Miyazaki K, Gardner H, Zent R, Quaranta V. Proteolytic processing of laminin-5 by MT1-MMP in tissues and its effects on epithelial cell morphology. *Faseb Journal* 2003;17:364. [PubMed: 14688206]
14. Swindle CS, Tran KT, Johnson TD, Banerjee P, Mayes AM, Griffith L, Wells A. Epidermal growth factor (EGF)-like repeats of human tenascin-C as ligands for EGF receptor. *Journal of Cell Biology* 2001;154:459–468. [PubMed: 11470832]

15. Foo CWP, Patwardhan SV, Belton DJ, Kitchel B, Anastasiades D, Huang J, Naik RR, Perry CC, Kaplan DL. Novel nanocomposites from spider silk-silica fusion (chimeric) proteins. *Proceedings of the National Academy of Sciences of the United States of America* 2006;103:9428–9433. [PubMed: 16769898]
16. Huang NF, Patel S, Thakar RG, Wu J, Hsiao BS, Chu B, Lee RJ, Li S. Myotube assembly on nanofibrous and micropatterned polymers. *Nano Letters* 2006;6:537–542. [PubMed: 16522058]
17. Tsang, VL.; Bhatia, SN. *Tissue Engineering II*. 103. Springer Berlin / Heidelberg: *Advances in Biochemical Engineering/Biotechnology*; 2007. Fabrication of three-dimensional tissues; p. 189–205.
18. Burdick JA, Khademhosseini A, Langer R. Fabrication of gradient hydrogels using a microfluidics/photopolymerization process. *Langmuir* 2004;20:5153–5156. [PubMed: 15986641]
19. Campbell K, Groisman A. Generation of complex concentration profiles in microchannels in a logarithmically small number of steps. *Lab on a Chip* 2007;7:264–272. [PubMed: 17268630]
20. Kaehr B, Shear JB. Mask-directed multiphoton lithography. *Journal of the American Chemical Society* 2007;129:1904. [PubMed: 17260997]
21. • Lu Y, Mapili G, Suhali G, Chen SC, Roy K. A digital micro-mirror device-based system for the microfabrication of complex, spatially patterned tissue engineering scaffolds. *Journal of Biomedical Materials Research Part A* 2006;77A:396–405. [PubMed: 16444679] A novel 3D patterning technique that utilizes a dynamic masking device to decrease processing time in comparison to point-to-point techniques was developed, demonstrating that high throughput does not necessarily lead to a significant loss of resolution.
22. Downing BR, Cornwell K, Toner M, Pins GD. The influence of microtextured basal lamina analog topography on keratinocyte function and epidermal organization. *Journal of Biomedical Materials Research Part A* 2005;72A:47–56. [PubMed: 15543632]
23. Subbiah T, Bhat GS, Tock RW, Pararneswaran S, Ramkumar SS. Electrospinning of nanofibers. *Journal of Applied Polymer Science* 2005;96:557–569.
24. Pham QP, Sharma U, Mikos AG. Electrospinning of polymeric nanofibers for tissue engineering applications: A review. *Tissue Engineering* 2006;12:1197–1211. [PubMed: 16771634]
25. Stitzel J, Liu L, Lee SJ, Komura M, Berry J, Soker S, Lim G, Van Dyke M, Czerw R, Yoo JJ, et al. Controlled fabrication of a biological vascular substitute. *Biomaterials* 2006;27:1088–1094. [PubMed: 16131465]
26. Baker BM, Mauck RL. The effect of nanofiber alignment on the maturation of engineered meniscus constructs. *Biomaterials* 2007;28:1967–1977. [PubMed: 17250888]
27. Kakade MV, Givens S, Gardner K, Lee KH, Chase DB, Rabolt JF. Electric field induced orientation of polymer chains in macroscopically aligned electrospun polymer nanofibers. *Journal of the American Chemical Society* 2007;129:2777–2782. [PubMed: 17302411]
28. Chen RR, Silva EA, Yuen WW, Mooney DJ. Spatio-temporal VEGF and PDGF delivery patterns blood vessel formation and maturation. *Pharmaceutical Research* 2007;24:258–264. [PubMed: 17191092]
29. Rajangam K, Behanna HA, Hui MJ, Han XQ, Hulvat JF, Lomasney JW, Stupp SI. Heparin binding nanostructures to promote growth of blood vessels. *Nano Letters* 2006;6:2086–2090. [PubMed: 16968030]
30. Silva EA, Mooney DJ. Spatiotemporal control of vascular endothelial growth factor delivery from injectable hydrogels enhances angiogenesis. *Journal of Thrombosis and Haemostasis* 2007;5:590–598. [PubMed: 17229044]
31. Richardson TP, Peters MC, Ennett AB, Mooney DJ. Polymeric system for dual growth factor delivery. *Nature Biotechnology* 2001;19:1029–1034.
32. Willerth SM, Johnson PJ, Maxwell DJ, Parsons SR, Doukas ME, Sakiyama-Elbert SE. Rationally designed peptides for controlled release of nerve growth factor from fibrin matrices. *Journal of Biomedical Materials Research Part A* 2007;80A:13–23. [PubMed: 16958043]
33. Holland TA, Bodde EWH, Cuijpers V, Baggett LS, Tabata Y, Mikos AG, Jansen JA. Degradable hydrogel scaffolds for in vivo delivery of single and dual growth factors in cartilage repair. *Osteoarthritis and Cartilage* 2007;15:187–197. [PubMed: 16965923]

34. Hao X, Silva E, Månsson-Broberg A, Grinnemo K, Siddiqui A, Dellgren G, Wårdell E, Brodin L, Mooney D, Sylén C. Angiogenic effects of sequential release of VEGF-A(165) and PDGF-BB with alginate hydrogels after myocardial infarction. *Cardiovascular Research* 2007;75:178–185. [PubMed: 17481597]
35. Huang YC, Riddle K, Rice KG, Mooney DJ. Long-term in vivo gene expression via delivery of PEI-DNA condensates from porous polymer scaffolds. *Human Gene Therapy* 2005;16:609–617. [PubMed: 15916485]
36. Rosi NL, Giljohann DA, Thaxton CS, Lytton-Jean AKR, Han MS, Mirkin CA. Oligonucleotide-modified gold nanoparticles for intracellular gene regulation. *Science* 2006;312:1027–1030. [PubMed: 16709779]
37. D'Amour KA, Bang AG, Eliazar S, Kelly OG, Agulnick AD, Smart NG, Moorman MA, Kroon E, Carpenter MK, Baetge EE. Production of pancreatic hormone-expressing endocrine cells from human embryonic stem cells. *Nature Biotechnology* 2006;24:1392–1401.
38. Hill E, Boontheekul T, Mooney DJ. Regulating activation of transplanted cells controls tissue regeneration. *Proceedings of the National Academy of Sciences of the United States of America* 2006;103:2494–2499. [PubMed: 16477029]
39. Gomez N, Schmidt CE. Nerve growth factor-immobilized polypyrrole: Bioactive electrically conducting polymer for enhanced neurite extension. *Journal of Biomedical Materials Research Part A* 2007;81A:135–149. [PubMed: 17111407]
40. Lahann J, Mitragotri S, Tran TN, Kaido H, Sundaram J, Choi IS, Hoffer S, Somorjai GA, Langer R. A reversibly switching surface. *Science* 2003;299:371–374. [PubMed: 12532011]
41. Raeber GP, Lutolf MP, Hubbell JA. Molecularly engineered PEG hydrogels: A novel model system for proteolytically mediated cell migration. *Biophysical Journal* 2005;89:1374–1388. [PubMed: 15923238]
42. Yamaguchi N, Zhang L, Chae BS, Palla CS, Furst EM, Kiick KL. Growth factor mediated assembly of cell receptor-responsive hydrogels. *Journal of the American Chemical Society* 2007;129:3040. [PubMed: 17315874]
43. Ulijn RV, Bibi N, Jayawarna V, Thornton PD, Todd SJ, Mart RJ, Smith AM, Gough JE. Bioresponsive hydrogels. *Materials Today* 2007;10:40–48.
44. Murphy WL, Dillmore WS, Modica J, Mrksich M. Dynamic Hydrogels: Translating a Protein Conformational Change into Macroscopic Motion. *Angew Chem Int Ed Engl* 2007;46:3066–3069. [PubMed: 17366501]
- 45 ••. Yang ZM, Liang GL, Wang L, Xu B. Using a kinase/phosphatase switch to regulate a supramolecular hydrogel and forming the supramolecular hydrogel in vivo. *Journal of the American Chemical Society* 2006;128:3038–3043. [PubMed: 16506785] Reversibility is often desired in biomaterial design, and a biomimetic technique to reversibly modify gelation was developed in this work
46. Wiseman PW, Brown CM, Webb DJ, Hebert B, Johnson NL, Squier JA, Ellisman MH, Horwitz AF. Spatial mapping of integrin interactions and dynamics during cell migration by Image Correlation Microscopy. *Journal of Cell Science* 2004;117:5521–5534. [PubMed: 15479718]
47. Hu K, Ji L, Applegate KT, Danuser G, Waterman-Storer CM. Differential transmission of actin motion within focal adhesions. *Science* 2007;315:111–115. [PubMed: 17204653]
- 48 •. Zaman MH, Trapani LM, Siemeski A, MacKellar D, Gong HY, Kamm RD, Wells A, Lauffenburger DA, Matsudaira P. Migration of tumor cells in 3D matrices is governed by matrix stiffness along with cell-matrix adhesion and proteolysis. *Proceedings of the National Academy of Sciences of the United States of America* 2006;103:10889–10894. [PubMed: 16832052] Factors that influence cellular motility in 3D matrices were elucidated, leading to an expansion in the design space for future biomaterial development. These findings highlight the important relationship between basic and applied research
- 49 ••. Kong HJ, Boontheekul T, Mooney DJ. Quantifying the relation between adhesion ligand-receptor bond formation and cell phenotype. *Proceedings of the National Academy of Sciences of the United States of America* 2006;103:18534–18539. [PubMed: 17124175] A quantitative understanding of biology is fundamental to biomaterial design; however, few techniques are available to explore the biology of the cell-material interface quantitatively. The authors in this study report a method to

quantify bond number in 3D culture using a FRET based approach, and correlate bond formation to cell function.

50. Kong HJ, Polte TR, Alsberg E, Mooney DJ. FRET measurements of cell-traction forces and nano-scale clustering of adhesion ligands varied by substrate stiffness. *Proceedings of the National Academy of Sciences of the United States of America* 2005;102:4300–4305. [PubMed: 15767572]
51. Okita K, Ichisaka T, Yamanaka S. Generation of germline-competent induced pluripotent stem cells. *Nature*. 2007Epub ahead of print
52. Takahashi K, Yamanaka S. Induction of pluripotent stem cells from mouse embryonic and adult fibroblast cultures by defined factors. *Cell* 2006;126:663–676. [PubMed: 16904174]
53. Maherali N, Sridharan R, Xie W, Utikal J, Eminli S, Arnold K, Stadtfeld M, Yachechko R, Tchieu J, Jaenisch R, et al. In vitro reprogramming of fibroblasts into a pluripotent ES-cell-like state. *Cell Stem Cell* 2007;1:55–70.
54. Wernig M, Meissner A, Foreman R, Brambrink T, Ku M, Hochedlinger K, Bernstein B, Jaenisch R. In vitro reprogramming of fibroblasts into a pluripotent ES-cell-like state. *Nature*. 2007Epub ahead of print
55. Deasy BM, Lu AP, Tebbets JC, Feduska JM, Schugar RC, Pollett JB, Sun B, Urish KL, Gharaibeh BM, Cao BH, et al. A role for cell sex in stem cell-mediated skeletal muscle regeneration: female cells have higher muscle regeneration efficiency. *Journal of Cell Biology* 2007;177:73–86. [PubMed: 17420291]
56. Martin A, Komada MR, Sane DC. Abnormal angiogenesis in diabetes mellitus. *Medicinal Research Reviews* 2003;23:117–145. [PubMed: 12500286]
- 57 ••. Klinger RY, Blum JL, Hearn B, Lebow B, Niklason LE. Relevance and safety of telomerase for human tissue engineering. *Proceedings of the National Academy of Sciences of the United States of America* 2006;103:2500–2505. [PubMed: 16477025]An underappreciated challenge in tissue engineering and regenerative medicine is the varied response to therapies as a function of sex, disease state, and age of the patient. In this study the authors reveal significant decreases in the mechanical properties of engineered vessels formed from cells of aged individuals, as contrasted to vessels formed from cells of younger individuals
58. Reddy ST, Swartz MA, Hubbell JA. Targeting dendritic cells with biomaterials: developing the next generation of vaccines. *Trends in Immunology* 2006;27:573–579. [PubMed: 17049307]

The Cellular Microenvironment

Figure 1. 4D Pseudo-Phase Diagram of Cell Fate

The cellular microenvironment is composed of signals from neighboring cells, physical stimuli, soluble factors including growth factors, and insoluble molecules such as the extracellular matrix. The effects of these variables are plotted as different axes on this 4D diagram of cell fate (e.g. differentiation) and are symbolized in this illustration by the different shapes and colors of the cells located at different positions in space. In advanced tissue engineering and regenerative medicine the biomaterial may direct cell fate through any of the variables. The signals from the biomaterial may change over time as a result of preprogrammed spatio-temporal control or in response to the microenvironment, allowing for the recapitulation of complex signaling pathways.

Figure 2. Tissue Engineering and Regenerative Medicine at Many Length Scales

Many techniques are available to design biomaterials from the nanometer to centimeter length scales, some of which are listed above (A). Examples of biomaterials mentioned in the review can be seen approximately beneath their respective length scale (B–F). An illustration of a heparin-nucleating self-assembled peptide amphiphile (B) [29]. The fatty acid tail segregates to the center of the nanofiber while the heparin binding sequence bonds to heparin leading to charge shielding and gel formation. The nanofibers have a diameter of 6–7.5 nm and further aggregate to higher order structures with diameters of 50 to 100 nm. Mesenchymal stem cells seeded on submicrometer electrospun poly (ϵ -caprolactone) meshes (C) [26]. Anisotropic skeletal myotube formation after 7 days of culture (7 d) on poly (dimethylsiloxane) substrates patterned using soft lithography (D) [15]. Hematoxylin and eosin staining of a micropatterned dermal analog composed of a collagen-glycosaminoglycan membrane laminated to a collagen sponge (E) [22]. Tissue engineered blood vessel produced by seeding smooth muscle cells onto a polyglycolic acid substrate and then culturing the substrate in a pulsatile bioreactor (F) [57]. The vessel is approximately 5.5 cm in length and 3 mm in diameter. The scale bar in C, D, and E is 50 μ m. The scale bar in D added to scale from the control sample. W and D represent the width and depth of the invagination. The original image in F was cut to fit into the figure. Images in B and D reproduced with permission, copyright 2006, American Chemical Society. Image in C reproduced with permission, copyright 2007, Elsevier. Image in E reprinted with permission of John Wiley & Sons, Inc., *Journal of Biomedical Materials Research Part A*, 72A, 2005, 53; copyright 2004, John Wiley & Sons, Inc. Image in F reproduced with permission, copyright 2006, National Academy of Sciences, USA.

Figure 3. Spatial and Temporal Control of Morphogen and Growth Factor Delivery

Polymeric systems allow for independent regulation of the localization, duration, and availability of one or more soluble factors, exemplified above by the delivery of two factors, A and B, with different release kinetics. Factor A is released locally from the biomaterial (circle) within a short duration of time. In contrast, Factor B is released over a large volume for a long period of time.