Published in final edited form as:

J Am Chem Soc. 2007 October 31; 129(43): 12904–12905. doi:10.1021/ja074590d.

Conjugated Polymer Dots for Multiphoton Fluorescence Imaging

Changfeng Wu, Craig Szymanski, Zachary Cain, and Jason McNeill*

Department of Chemistry, Clemson University, Clemson, South Carolina 29634

Multiphoton fluorescence microscopy has recently emerged as a powerful technique for three-dimensional imaging in biological systems.^{1–4} The nonlinear dependence of excitation probability on light intensity results in a highly localized excitation and improved spatial resolution. The small effective excitation volume also reduces background signal due to autofluorescence and the fluorescence of dye molecules outside of the laser focal volume, while the ability to employ near-IR wavelengths for excitation can reduce photo-damage to the sample as well as facilitate imaging of biological specimens due to the near-transparency of many tissues in this spectral range.⁴ The widespread adoption of multiphoton fluorescence imaging and microscopy has been hindered by the bulky and expensive pulsed laser sources typically required for excitation due to the relatively low multiphoton excitation cross sections of available dyes.^{5,6} Interest in the development of brighter probes has led to the design and synthesis of dyes with two-photon action cross sections larger than 1000 Göppert-Mayer units (GM).⁷ Gold nanorods have also been demonstrated as contrast agent for in vitro and in vivo two-photon luminescence imaging, and the two-photon action cross sections were determined to be ~2000 GM.⁸ Colloidal CdSe quantum dots appear to be very promising probes for two-photon microscopy due to their excellent photostability and large two-photon action cross sections (from 2000 to 47 000 GM),⁹ although single particle blinking and a significant fraction of “dark” nanoparticles are drawbacks for some applications.¹⁰

Conjugated polymers are known to possess high absorption coefficients and high fluorescence efficiency, which have led to a wide range of applications in optoelectronic thin film devices.^{11,12} The extraordinary light-gathering power of conjugated polymers is evidenced by the first reported direct determination of the optical absorption cross section of a single molecule at room temperature, in which an optical cross section of the conjugated polymer MEHPPV in the vicinity of $10^7 \text{ M}^{-1} \text{ cm}^{-1}$ was determined.¹³ We have recently developed and characterized highly fluorescent nanoparticles consisting of one or more hydrophobic conjugated polymers.^{14,15} These “CPdot” nanoparticles represent a new class of highly fluorescent probes with potential applications for biosensing and imaging. In this Communication, we determine the two-photon excited fluorescence properties of CPdots and explore their application for multiphoton fluorescence microscopy. Our measurements of the nonlinear optical properties of the CPdots indicate extraordinarily high two-photon action cross sections—in one case as high as $2.0 \times 10^5 \text{ GM}$, the highest reported to date for a particle of comparable size. Detection of two-photon excited fluorescence of single nanoparticles was demonstrated using relatively low laser power, demonstrating the great potential of these CPdots for multiphoton fluorescence imaging applications.

The conjugated polymers employed in this study (Figure 1a) are the polyfluorene derivative poly(9,9-dihexylfluorenyl-2,7-diyl) (PDHF, average MW 55 000), the copolymer poly[{9,9-dioctyl-2,7-divinylene-5-fluorenylene}-alt-co-{2-methoxy-5-(2-ethylhexyloxy)-1,4-phenylene}] (PFPV, average MW 270 000), and the polyphenylenevinylene derivative poly[2-methoxy-5-(2-ethylhexyloxy)-1,4-phenylenevinylene] (MEH-PPV, average MW 200

000). The polymers were purchased from ADS Dyes, Inc. and used without further purification. Stable, aqueous dispersions of CPdots were prepared using a reprecipitation method described previously.^{14,15} The nanoparticle size can be controlled over the range of 5–50 nm by varying the concentration of the precursor solution. Unlike inorganic semiconductor nanoparticles, the particle size does not affect the shape of the absorption and fluorescence spectra of CPdots. Instead, an increase in particle size largely results in an increase in the optical cross section per particle.^{14,15}

The CPdots exhibit one-photon absorption in the wavelength range of 350–500 nm. However, when the output of a mode-locked Ti:sapphire laser (100 mW, 800 nm, 100 fs) is focused into aqueous dispersions of PFPV and MEH-PPV dots (8 ppm, 3 nM), strong fluorescence in the vicinity of the focus is clearly visible (Figure 1b). Power-dependent excitation efficiencies provide further evidence for the two-photon excited fluorescence (data shown in Supporting Information). At a given laser intensity, I , two-photon fluorescence intensity is proportional to $\sigma_{2p}\phi I^2$, where σ_{2p} is the two-photon absorption cross section and ϕ is the fluorescence quantum yield. A convenient measure of the two-photon fluorescence brightness is the two-photon action cross section, $\sigma_{2p}^* = \sigma_{2p}\phi$.^{4,9} A custom-built photon-counting spectrometer was used to determine the two-photon action cross sections as a function of excitation wavelength. The measurements were performed on CPdots of ~20 nm diameter (Figure 1c), consisting of PDHF, PFPV, and MEH-PPV, respectively. The experimentally determined two-photon action cross sections ($\lambda_{ex} = 770$ nm) are 1.4×10^4 , 5.5×10^4 , and 2.0×10^5 GM for PDHF, MEH-PPV, and PFPV dots, respectively (Figure 1d). The two-photon action cross section for MEH-PPV dots is about 1 order of magnitude larger than that of the molecular solution,¹⁶ consistent with the particle size results that indicate 10–20 molecules per particle. Significantly, the results show that, as two-photon fluorescent probes, the PFPV dots are 3–4 orders of magnitude brighter than conventional fluorescent dyes⁵ and an order of magnitude brighter than quantum dots.⁹ It is somewhat surprising that PFPV dots were determined to have the highest brightness of the three polymers, given that under one-photon excitation PDHF dots are brighter than both PFPV and MEH-PPV dots. However, the higher two-photon cross sections of PFPV and MEH-PPV are consistent with theoretical and experimental results indicating that π -conjugated systems with alternating donor- π -donor structures exhibit relatively large two-photon absorption cross sections.^{7,17} The alkoxy side groups in PFPV and MEH-PPV act as electron donors, forming the donor- π -donor motif associated with relatively high two-photon cross sections, while PDHF does not possess alkoxy side groups.

To demonstrate the potential of the CPdots for multiphoton fluorescence imaging, single particles on a glass substrate were imaged using a custom-built confocal fluorescence microscope employing the attenuated output of a mode-locked Ti:sapphire laser (800 nm, 100 fs) for excitation. Figure 2a shows a $5 \mu\text{m} \times 5 \mu\text{m}$ fluorescence image of the PFPV dots sparsely dispersed on a glass coverslip. Each bright spot in Figure 2a corresponds to a single PFPV dot. The high per-particle brightness is evident in the relatively low average laser power (260 μW , at the sample) employed to obtain high contrast images. Typically, pulsed laser light is required to generate sufficient two-photon fluorescence signal for single fluorophore detection. However, on the basis of these results, we estimate it should be possible to obtain two-photon fluorescence images of single CPdot nanoparticles using ~10 mW CW laser illumination provided by an inexpensive semiconductor diode laser. Indeed, focusing several tens of milliwatts of 800 nm CW laser light (*Ti:sapphire laser operating in CW mode*) onto a single layer of nanoparticles generated fluorescence that was readily visible to the unaided eye.

Single conjugated polymer molecules typically exhibit complex photophysics such as fluorescence intermittence (blinking) and photon antibunching.^{18,19} Single particle fluorescence kinetics traces (Figure 2b) indicated no observable blinking for 20 nm PFPV dots, while it was often observed in smaller particles (<10 nm), consistent with a recent single particle

results.²⁰ As fluorescent probes for imaging or single particle tracking, the relatively steady fluorescence of CPdots compares favorably to that of quantum dots, which typically exhibit pronounced blinking on time scales of milliseconds to hundreds of seconds.¹⁰ Analyses of single particle kinetics traces indicate that approximately $\sim 10^6$ photons per particle (~ 10 nm diameter) were detected prior to photobleaching. This is lower than the photostability under one-photon excitation ($\sim 10^7$ photons detected), consistent with prior observations that single fluorophores exhibit lower photostability under two-photon excitation than under one-photon excitation.²¹ Silica encapsulation would likely improve photostability.¹⁴

In summary, we report on a new class of two-photon fluorescent nanoparticles, CPdots, which exhibit the largest two-photon action cross sections reported to date for particles of comparable size. Demonstration of single particle imaging using relatively low laser excitation levels demonstrates the potential utility of CPdots for multiphoton fluorescence microscopy applications and raises the possibility of employing small, inexpensive near-infrared diode lasers for two-photon excited fluorescence imaging.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgment

This material is based upon work supported by the NSF/EPSCoR under Grant Nos. 2001RII-EPS-0132573 and 2004RII-EPS-0447660, NSF CAREER Grant No. CHE-0547846, and NIH Grant No. 1R01GM081040.

References

1. Denk W, Strickler JH, Webb WW. Science 1990;248:73. [PubMed: 2321027]
2. Xu C, Zipfel W, Shear JB, Williams RM, Webb WW. Proc. Natl. Acad. Sci. U.S.A 1996;93:10763. [PubMed: 8855254]
3. Bhawalkar JD, He GS, Prasad PN. Rep. Prog. Phys 1996;59:1041.
4. Zipfel WR, Williams RM, Webb WW. Nat. Biotechnol 2003;21:1368.
5. Xu C, Webb WW. J. Opt. Soc. Am. B 1996;13:481.
6. So PTC, Dong CY, Masters BR, Berland KM. Annu. Rev. Biomed. Eng 2000;2:399. [PubMed: 11701518]
7. Albota M, et al. Science 1998;281:1653. [PubMed: 9733507]
8. Wang HF, Huff TB, Zweifel DA, He W, Low PS, Wei A, Cheng JX. Proc. Natl. Acad. Sci. U.S.A 2005;102:15752. [PubMed: 16239346]
9. Larson DR, Zipfel WR, Williams RM, Clark SW, Bruchez MP, Wise FW, Webb WW. Science 2003;300:1434. [PubMed: 12775841]
10. Yao J, Larson DR, Vishwasrao HD, Zipfel WR, Webb WW. Proc. Natl. Acad. Sci. U.S.A 2005;102:14284. [PubMed: 16169907]
11. Yu G, Gao J, Hummelen JC, Wudl F, Heeger AJ. Science 1995;270:1789.
12. Friend RH, Gymer RW, Holmes AB, Burroughes JH, Marks RN, Taliani C, Bradley DDC, Dos Santos DA, Bredas JL, Loglund M, Salaneck WR. Nature 1999;397:121.
13. Szymanski C, Wu C, Hooper J, Salazar MA, Perdomo A, Dukes A, McNeill JD. J. Phys. Chem. B 2005;109:8543. [PubMed: 16852006]
14. Wu C, Szymanski C, McNeill J. Langmuir 2006;22:2956. [PubMed: 16548540]
15. Wu C, Peng H, Jiang Y, McNeill J. J. Phys. Chem. B 2006;110:14148–14154. [PubMed: 16854113]
16. Oliveira SL, Correa DS, De Boni L, Misoguti L, Zilio SC, Mendonca CR. Appl. Phys. Lett 2006;88:021911.
17. Rumi M, et al. J. Am. Chem. Soc 2000;122:9500.
18. Vanden Bout DA, Yip WT, Hu DH, Fu DK, Swager TM, Barbara PF. Science 1997;277:1074.

19. Kumar P, Lee TH, Mehta A, Sumpter BG, Dickson RM, Barnes MD. J. Am. Chem. Soc 2004;126:3376. [PubMed: 15025436]
20. Grey JK, Kim DY, Norris BC, Miller WL, Barbara PF. J. Phys. Chem. B 2006;110:25568. [PubMed: 17181186]
21. Sanchez EJ, Novotny L, Holtom GR, Xie XS. J. Phys. Chem. A 1997;101:7019.

Figure 1.

(a) Chemical structures of the conjugated polymers. (b) Photograph of the fluorescence from aqueous CPdot dispersions under two-photon excitation of an 800 nm mode-locked Ti:sapphire laser. (c) A typical AFM images of the PFPV dots on a silicon substrate. (d) Semilog plot of two-photon action cross sections ($\sigma_{2p}\phi$) versus the excitation wavelength for CPdots and rhodamine B (reference compound).

Figure 2.

(a) A $5\ \mu\text{m} \times 5\ \mu\text{m}$ fluorescence image of single PFPV dots immobilized on a glass coverslip obtained using two-photon excitation (800 nm). (b) Photobleaching kinetics of single PFPV dots under two-photon excitation. No obvious blinking was observed for ~ 20 nm PFPV dots, while it is often observed for smaller particles (< 10 nm).