Published in final edited form as:

Anal Chem. 2006 November 1; 78(21): 7453–7460. doi:10.1021/ac0609733.

Development of an array of ion-selective microelectrodes aimed for the monitoring of extracellular ionic activities

Olivier T. Guenat^{1, *}, Silvia Generelli², Nicolaas F. de Rooij², Milena Koudelka-Hep², François Berthiaume¹, and Martin L. Yarmush¹

¹ Center for Engineering in Medicine, Massachusetts General Hospital, Harvard Medical School, Boston, MA, USA ² SAMLAB, Institute of Microtechnology, University of Neuchâtel, Switzerland

Abstract

In this study we present the development and the characterization of a generic platform for cell culture able to monitor extracellular ionic activities (K^+ , NH_4^+) for real-time monitoring of cell-based responses, such as necrosis, apoptosis or differentiation. The platform for cell culture is equipped with an array of 16 silicon nitride micropipette-based ion-selective microelectrodes with a diameter of either 2 or 6 μm . This array is located at the bottom of a 200 μm wide and 350 μm deep microwell where the cells are cultured. The characterization of the ion-selective microelectrode arrays in different standard and physiological solutions is presented. Near Nernstian slopes were obtained for potassium- (58.6 ± 0.8 mV/pK, $n=15$) and ammonium-selective microelectrodes (59.4 ± 3.9 mV/pNH₄, $n=13$). The calibration curves were highly reproducible and showed an average drift of 4.4 ± 2.3 mV/h ($n=10$). Long-term behavior and response after immersion in physiological solutions are also presented. The lifetime of the sensors was found to be extremely long with a high recovery rate.

INTRODUCTION

Measurement of different ion concentrations in cell cultures is of central importance for understanding cellular signaling and cell metabolism. Among analytical methods available for investigating extra- and intracellular ionic fluxes ion-selective electrodes (ISEs) and fluorescence-based techniques are the most common ones. The first measurements of intra- and extracellular ionic concentrations were performed using glass-capillary ISEs and date back to early 80's [1,2,3]. Later on, supported by a rapid development of highly efficient fluorophores for many ions of interest, the ISE methodology has been surpassed by fluorescence techniques [4]. The reasons are mainly experimental - tedious and difficult to control preparation of ISE glass micropipettes and impracticality of performing parallel measurements on a number of cells in the culture. Yet, cellular measurements with ISEs which allow assessing free ion activities (contrary to fluorescence where *total ion concentrations* are measured) constitute an interesting complementary methodology to the fluorescence techniques. Furthermore, it is an only alternative for applications where fluorophores are not available, such as for the monitoring of the urea cycle for recording the concentration of NH_4^+ .

To realize microelectrode arrays of various geometries and functionalities, the microfabrication technology is the obvious choice. In cell biology, microfabricated devices are already largely exploited for investigating cell network electrophysiology and applied in other cell-based

assays [5]. In comparison, the development of ISE arrays is far less advanced. In their pioneering work, Buck et al. used a Kapton-based K^+ and pH sensitive microelectrode array for in-vivo monitoring of a beating heart during induced ischemia [6,7]. Other microfabricated arrays of ISEs have been developed for the detection of blood electrolytes [8,9,10,11,12]. In order to monitor the ionic concentration at the cellular level, the dimensions of the ISEs should ideally have cellular or subcellular sizes and the sensors should be organized in a dense array able to record ionic fluxes of neighboring cells. Therefore, localized ion concentration change in closer area around an electrode could be detected in response, for example to local drug delivery. The microfabricated sensors mentioned above are much larger than cell dimensions and are therefore not well suited for this purpose. The approach presented in this paper is a step in this direction.

Recently, we reported the development of arrays of microfabricated silicon nitride micropipettes with diameter ranging between 200 nm and a few microns [13]. These micropipettes were integrated on a cell culture platform and were filled with ion-selective cocktail by means of microchannels to form ion-selective microelectrodes. The microfabrication of this platform equipped with an array of 24 micropipettes whose dimensions were 6 μm in diameter and 50 μm in length, as well as the results of preliminary tests with a Ca^{2+} -selective membrane are described in a previous paper [14]. It is also shown that the micropipette geometry allows achieving a reproducible and clearly defined membrane thickness and active surface as well as ensuring good mechanical anchoring of the membrane. Furthermore, the volume of ion-selective membrane contained in the microchannel connecting the micropipette constitutes a large reservoir for plasticizer, carrier and ionic sites that increases the sensor lifetime (Figure 1).

In this study we extend our research by developing a generic platform for real-time monitoring of extracellular ionic activities (K^+ , NH_4^+) of cell-based responses, such as necrosis and apoptosis, differentiation, etc.. Potassium, which is present at high levels in intact viable cells, leaks out of dying cells; elevated extracellular potassium ranging between 1 and 150 mM K^+ can be used as a marker of cell death. Ammonium is taken up by differentiated hepatocytes and a decrease in extracellular NH_4^+ [15] from 1 mM to 10 μM can be used as a marker of stem cell differentiation into hepatocytes. Another particular interest in NH_4^+ sensors arises from the fact that this analyte is the product of many enzymatically catalyzed reactions. The new platform is equipped with an array of 16 ion-selective microelectrodes located at the bottom of a microchannel where the cells will be cultured (Figure 2). The length of the microelectrodes is 30 μm , with diameters of either 2 or 6 μm . The analytical characteristics of the ISE array with different potassium and ammonium membrane formulations are compared on the basis of the sensitivity, selectivity, stability and reproducibility of the measurements and life time of the microelectrodes.

EXPERIMENTAL SECTION

Design and Fabrication of the Ion-Selective Microelectrodes Array

The array of 16 ion-selective microelectrodes is integrated at the bottom of a cell culture platform that comprises a 200 μm wide and 365 μm deep microwell where the cells are cultured (Figure 2). The microwell widens on both ends to form circular cavities (1 mm in diameter) intended for medium perfusion and cell seeding. A network of smaller microchannels, connected to the microwell, aims to deliver and modulate the hormone/growth factor environment in the cell culture, through holes located at the other extremity of these channels. The backbone of the ISE array consists of an array of silicon nitride micropipettes structured in a silicon substrate, arranged in two rows of 8 and separated by 150 μm . Each micropipette is connected to a 50 μm wide and 20 μm deep microchannel etched in a Pyrex substrate that

is aligned and bonded to the silicon substrate. The micropipettes are filled with ion-selective cocktails via the microchannels by capillary forces (Figure 1).

The micropipettes arrays are fabricated using extensions of previously reported microfabrication technologies [13,14]. Briefly, an array of either 2 or 6 μm in diameter and 30 μm deep holes is etched by deep reactive ion etching (DRIE) in a (100) silicon wafer. Then, a thermal silicon dioxide and a silicon nitride layers are successively deposited. The thickness of the oxide layer, which is used as a sacrificial layer, allows for the reduction of the hole diameter, and thus the precise definition of the final diameter of the micropipette, whereas the thickness of the silicon nitride layer defines the wall thickness of the micropipettes. The wafer topside is then locally etched by a second DRIE until the micropipette tips are exposed. The oxide tips are then removed in buffered HF, while the nitride caps of the tips are etched by RIE, using a SF_6 gas mixture. A thin oxide layer is deposited onto the topside silicon surface as an electrical insulation. A Ta/Pt layer is then deposited on the wafer backside and structured by a lift-off technique, to create the internal electrodes of the ISEs. In parallel, a Pyrex substrate is etched in 20% HF to structure the microchannels that connect the micropipettes. Each microchannel is equipped with a 1 mm in diameter through holes, for the individual filling of the micropipettes. After dicing, the silicon and Pyrex chips are anodically bonded. The dimensions of the silicon chip are $20 \times 18 \text{ mm}^2$, whereas the Pyrex chips are slightly smaller ($15 \times 15 \text{ mm}^2$) allowing the metallic pads located at the bottom of the silicon chip to be contacted by wire bonding. The size of the active surface of the ion-selective membrane at the top of a 2 μm and a 6 μm diameter micropipette is about 3 and 28 μm^2 , respectively.

Prior to filling the micropipettes with the ion-selective cocktail, the device was dehydrated at 150°C in a convection oven for 24 h and then silanized. A vapor phase silanization was carried out by using *N, N* dimethyltrimethylsilylamine during 60 min at 150°C. This silanizing agent is toxic and corrosive and was handled appropriately in a fume hood. Filling of the micropipettes was typically carried out by dispensing 0.7 μL of ion-selective cocktail into each microchannel (Figure 1). Due to capillary forces the membrane cocktail flows through the microchannel and fills the micropipette. If air bubbles were present in the microchannels, the chip was placed in a vacuum chamber for 5 minutes at 50 kPa, to remove them. Two days were allowed for the evaporation of the solvent (cyclohexanone).

Reagents

The ionophores (valinomycin, nonactin), the ionic additives (potassium tetrakis [3,5-bis(trifluoromethyl)phenyl]borate (KTFPB) and sodium tetrakis [3,5-bis(trifluoromethyl)phenyl] borate (NaTFPB)), the membrane matrix high molecular weight poly(vinyl chloride) (PVC), the plasticizer bis(2-ethylhexyl) sebacate (DOS) and the cyclohexanone were of Selectophore quality from Sigma-Aldrich (Fluka), whereas the salts were of puriss p.a. quality from the same company. The silanizing agent *N, N* dimethyltrimethylsilylamine (purum) was also purchased from Sigma-Aldrich (Fluka). D-(+)-glucose anhydrous, MgSO_4 anhydrous (ReagentPlus) and CaCl_2 dihydrate were from Sigma-Aldrich. Ammonium standard solution (0.1 M) was from Thermo Orion (Beverly, MA, USA). Aqueous solutions were prepared with freshly distilled deionized water (18 $\text{M}\Omega\text{-cm}$ specific resistance). Phosphate buffer solution (PBS) was prepared with analytical grade salts from Sigma-Aldrich, whereas Dulbecco's Modified Eagle Medium (DMEM), fetal bovine serum (FBS) and penicillin streptomycin (PS) were all purchased from Invitrogen Corp.

Membrane and ISEs

Five selective compositions were examined in this study, membranes A and B for K^+ -ISEs, and membranes C, D and E for NH_4^+ -ISEs. The formulations are given in wt %:

- A.** valinomycin (5.0), KTFPB (1.0), DOS (89.0), PVC (5.0)

- B. valinomycin (5.0), KTFPB (1.0), DOS (84.0), PVC (10.0)
- C. nonactin (5.0), KTFPB (1.0), DOS (89.0), PVC (5.0)
- D. nonactin (5.0), NaTFPB (0.6), DOS (89.4), PVC (5.0)
- E. nonactin (5.0), NaTFPB (1), NPOE (89.0), PVC (5.0)

The components of each membrane (totaling 200 mg) were dissolved in cyclohexanone (420 μ L). Cyclohexanone was preferred to tetrahydrofuran, which is generally used for microelectrodes applications, since it has a lower evaporation rate and is therefore better suited for filling the microchannels. The ISEs were conditioned in 1 mM chloride solution of the primary ion for at least one day.

Experimental Equipment and EMF Measurements

All solutions used for measurements were obtained by successive dilution of stock solutions. Potassium stock solution (0.2 M KCl) was prepared by dissolving appropriate amounts of KCl in deionized water, whereas a commercially available 0.1 M ammonium stock solution was used. A high glucose medium solution (HGMS) with an approximate osmolarity of 300 mOsM was prepared for ammonium measurements. It was composed of 297 mM D-glucose, 1.8 mM CaCl_2 and 0.8 mM MgSO_4 . The concentrations of calcium chloride and magnesium sulfate in HGMS were similar to those in DMEM. Physiological solutions were made of DMEM, mixed with 1, 5 or 10 % of FBS, and 1 % penicillin streptomycin.

Screening of the electrodes was performed by determining the slope of the calibration curve (EMF versus $\log a_K$ or $\log a_{\text{NH}_4}$) by exposing the ISE array to KCl or NH_4Cl standard solutions with incremented concentrations. Unless otherwise specified, the slopes of the potassium and ammonium calibration curves were calculated in the concentration range between 10^{-4} to 0.1 M KCl and between 10^{-5} to 10^{-2} M NH_4Cl , respectively. For the calculation of activity coefficients, the Debye-Hückel theory was used. The selectivity coefficients for Na^+ and K^+ were determined by the fixed interference method (FIM) [16] with a background level of 150 mM and 5.5 mM chloride solution, respectively. Comparative measurements of the ammonium samples were performed with an Orion ammonium electrode (ammonium sensing module 931801, Thermo Electron Corp., Beverly, MA). Up to sixteen microelectrodes were tested simultaneously using a 16 channels home-made high impedance input ($10^{14} \Omega$) amplifier, connected to a PC and a data acquisition card (DAQCard 6024E, National Instruments) in combination with Labview 7.0 software. A low pass filter stage with a cutoff frequency of 10 Hz was integrated to the amplifier. The chips were placed in a PMMA flow-through cell (Figure 3) that integrated a mini-reference electrode (mini-Ag/AgCl/3 M KCl DR1REF-2, World Precision Instruments, Stevenage, UK), located downstream. The volume of the flow-through cell was about 15 μ L. The flow-through cell and the amplifier were placed in a Faraday cage in order to avoid external EMF perturbations and light interferences [17].

Lifetime measurements were performed under continuous flow measurement by pumping two samples of different concentrations at regular frequency. The permutation was triggered by an electrostatic relay (Finder, Distrelec AG, Switzerland) connected to a two-ways pinch valve (P/N 075 P3MP12-233, BioChem Valve Inc.), placed ahead of the peristaltic pump (Masterflex 7519-20, Cole-Parmer). On the other hand, calibration curve determinations were carried out under stopped-flow conditions. Due to the complex geometrical shape of the microchannels network, the following procedure was experimentally chosen in order to prevent sample contamination with the remaining solution that was measured beforehand and thus to guarantee a good reproducibility of the measurements conditions. First, 0.5 mL of deionized water was flushed through the system at a flow rate of 12.6 $\mu\text{L/s}$ in order to clear the device of any remaining preconditioning solution. Then, 2 mL of sample solution were delivered in the flow-

through cell in the following sequence at the same flow rate: pump 1 mL, wait 20 s, pump 0.5 mL, wait 20 s, pump 0.5 mL. Subsequently, a stabilization time (7 s) was allowed and the EMF potential was then recorded. The potential data values recorded were the mean values of the last 500 points, collected within a 5 s time period. The stability of the potential data values recorded during this period was excellent, with standard deviations in the range of 0.05 % or lower.

In order to keep most of experimental conditions constant, the flow rate of 12.6 $\mu\text{L/s}$ used for the characterization of the system was also used in preliminary cell culture tests. This relatively high flow rate is clearly not well adapted for the cell cultures, therefore, in future work it will be decreased to a few $\mu\text{L/s}$. It must be noted that despite the relative large sample volume used for the characterization of the platform, the small volume of the microwell is appropriate for the localized detection of in-situ ionic secretion or uptake of cells. Thus, the array of microelectrodes will make it possible to record in real time and in parallel the cellular response to local drug delivery through the side channels.

All measurements were carried out at room temperature at $25 \pm 3^\circ\text{C}$. The recorded temperature variation could theoretically affect the slope sensitivity by $\pm 1\%$.

RESULTS AND DISCUSSION

The performance of the ISE array was evaluated by using 30 μm high micropipettes of either 2 or 6 μm in diameter in combination with five ion-selective membranes, two for potassium and three for ammonium, each containing a commercially available ionophore, valinomycin and nonactin, respectively. High molecular weight PVC, the most commonly used polymer for ISE applications for both conventional and microfabricated potentiometric sensors, was selected as membrane matrix [7,18]. It is known that PVC lacks adhesion to solid state sensors, however this was mainly reported for planar microelectrodes [18], where the membrane can eventually peel off in the presence of mechanical pressure and lead to sensor failure. In contrast, the anchor-shaped geometry defined by the micropipette and the semi-cylindrical microchannel, protects the membrane against mechanical constraints, similarly to the pyramidal-shaped microelectrode design reported by Uhlig et al. [8]. The commonly accepted ratio between plasticizer and PVC for ion-selective membranes used for conventional and most solid state sensors is two parts of plasticizer for one part of PVC [19]. In contrast, ion-selective solutions used as membrane phases in pulled glass microelectrodes with micrometer size diameter usually do not contain any polymer matrix or only a small fraction of polymer [2 (p. 44), 20]. By reducing this fraction, the membrane phase's viscosity decreases, which makes filling of the microelectrode easier. The PVC fraction in the membranes investigated was consequently decreased to 10 % (membrane B) and 5 % (membranes A, C, D, E).

Sensitivity and Selectivity of the ISEs Array

After preconditioning, the K^+ -ISE arrays were characterized with solutions ranging from 10^{-6} to 0.2 M KCl with a constant background of 0.15 M NaCl, whereas the NH_4^+ -ISE arrays were investigated with ammonium chloride solutions, ranging from 10^{-7} to 10^{-2} M, either without background electrolyte or mixed with high glucose medium solution (HGMS). The slopes of the calibration curves for each membrane formulation as well as their selectivity towards the main interfering ions are summarized in Table 1.

Sensitivity of the K^+ -selective microelectrode arrays—The 5% PVC potassium-selective microelectrodes, made of 6 μm micropipettes, show a near-Nernstian response ($57.3 \pm 2.0 \text{ mV/pK}^+$) in the range between 10^{-5} to 10^{-1} M with a lower detection limit that is similar to that of commercially available macroelectrodes. The upper detection limit is situated at 100 mM KCl. Consequently, the microelectrodes working range almost completely covers the

concentration range (1 to 150 mM K^+) that was defined for the planned applications. It must be mentioned that the targeted upper limit is theoretical, since the cytoplasmic potassium of dying cells will be diluted in the extracellular matrix. Besides, the discrimination of sodium over potassium, which is of great significance for biological applications, was found to be excellent for all the K^+ -selective membranes. The selectivity coefficient of $\log K^{Pot}_{K,Na}$ (FIM) = -4.6 corresponds to the values reported in the literature [21,22]. The sensitivity, selectivity and reproducibility of 2 μm microelectrodes were found to be comparable to the 6 μm microelectrodes.

The amount of PVC in the membrane plays an important role, as shown in Table 1 by the slightly smaller response of the ISEs filled with membrane B (10% of PVC) in comparison with ISEs filled with membrane A (5 % of PVC). In addition, the lifetime of the microelectrodes containing more PVC was shorter with a sensitivity halved after a week, whereas five other microelectrodes from the same array filled with membrane A presented a slope decrease of only 4 mV/pK $^+$. Thus, all further experiments were restricted to membranes containing 5 % PVC.

As illustrated in Figure 4a, the reproducibility of the calibration curves of microelectrodes from a same array was found to be excellent. Furthermore, it must be outlined that the results obtained with two arrays of 6 μm in diameter microelectrodes presented a very high yield with 15 out of 16 microelectrodes presenting a near Nernstian slope. The reproducibility between the two chips was also very good, attesting the excellent reproducibility and the homogeneous filling of the microfabricated pipettes.

Sensitivity of the NH_4^+ -selective microelectrode arrays—Three membrane formulations that differed as to the type of plasticizer and of ionic additive were used to optimize NH_4^+ -selective microelectrodes. NPOE and DOS were chosen as plasticizers since they have both previously been successfully used for ammonium-selective electrodes [23,21]. Table 1 summarizes the results obtained with the different membranes. Responses were found to be linear to concentrations ranging from 10^{-6} to 10^{-2} M ammonium chloride, with slopes of 44 to 56 mV/p NH_4^+ . Clearly the membranes that contained the plasticizer NPOE produced the microelectrodes with the slopes closest to the Nernstian response. The reasons of the slope difference between NPOE and DOS are not yet clearly understood. A similar effect was observed by Benco et al. [24] who tested a planar ion-selective electrode with an ammonium ionophore based on a cyclic depsipeptide structure in combination with either NPOE or dioctyl phthalate (DOP), an apolar plasticizer similar to DOS. They attributed this result to the higher polarity of NPOE. However, as indicated above, both plasticizers yield successfully for ammonium sensors. Interestingly enough, groups studying NH_4^+ -selective macroelectrodes preferred to use an apolar plasticizer, such as DOS [19,25,26,27], which is usually the first choice for monovalent ions, whereas use of NPOE was mainly reported for NH_4^+ -selective microelectrodes [28,29,30]. On the other hand, there was no significant effect in terms of sensitivity and selectivity between membranes containing either one or the other lipophilic ionic additive (KTFPB and NaTFPB).

Selectivity of the ISE arrays—Table 1 also shows the results of selectivity studies for the main monovalent interfering ions, Na^+ and K^+ . The selectivity coefficients were similar to those obtained with the Orion electrode, i.e. $\log K^{Pot}_{NH_4+,j}$ (FIM) = -3.0 and -0.9 for sodium and potassium, respectively, and comparable to the values found in the literature for both macro- and microelectrodes [21]. Figure 5 illustrates the selectivity of the NPOE plasticized membrane, for potassium, sodium and for the divalent ions present in HGMS. Similarly to the potassium microelectrodes, the reproducibility and the slope of the ammonium electrodes (Figure 4b) were also good, with standard deviations lying within a few percent (6.5 %) of the

averaged value. For example, after a week of use, 13 out of 16 microelectrodes filled with membrane E, presented a response of 59.4 ± 3.9 mV/pNH₄⁺.

Response Time, Long Term Stability and Lifetime

The response time and the long term stability measurements of the microelectrodes were tested in flow-through conditions at a flow rate of 12.6 μ L/s. Figure 6 shows the response for sample solutions from 1 μ M up to 100 mM of primary ion in presence of background electrolytes. The potassium concentration measurements tests were performed in 150 mM NaCl with 2 μ m microelectrodes filled with membrane A, whereas the ammonium concentration transients were determined in HGMS with 6 μ m microelectrodes filled with membrane E. The response times of the smaller electrodes were in the order of $t_{90\%} = 42$ s, whereas $t_{90\%}$ was about 35 s for the larger ones. However, it must be mentioned that the real response time of the microelectrodes is obviously shorter, since under the experimental conditions used, the response time determined is that of the whole system.

Long term stability of the ISE array was determined by regularly alternating two solutions of different concentrations ($c_1 = 1$ mM KCl and $c_2 = 10$ mM KCl, both with 150 mM NaCl background electrolyte) in flow-through mode. In Figure 7, a segment of the results of a long term experiment (potential-time plot) is illustrated for an array of 6 μ m microelectrodes filled with membrane A. The ion-selective microelectrodes follow the changes of potassium with intervals of 2 min and 25 s with high reproducibility. The sensor sensitivity ($\Delta\text{EMF} = \text{EMF}_{c_2} - \text{EMF}_{c_1}$) was stable in the time-frame of the experiment, with values recorded for consecutive concentration changes of 55.4 ± 0.9 mV/pK⁺, i.e. within 2%. A potential drift of 4.4 ± 2.3 mV/h in average was measured from Figure 7. The potential drifts are inherent to sensors prepared like “coated wire” electrodes, with no or extremely small volume of inner filling solution. They are explained by the formation of an aqueous layer between the metallic contact and the membrane that lead to an undefined thermodynamically interfacial potential and thus to poor potential stability [31]. This problem might meanwhile be lessened by performing more frequent calibrations. Similar results were obtained for 2 μ m microelectrodes.

The loss of plasticizer, carrier or ionic site from the membrane leaching into the sample can induce a loss of sensitivity and a slow deterioration of selectivity. This is the primary reason for limited lifetimes of carrier-based sensors. A second reason that limits the lifetime of ISEs is the loss of adhesion of the membrane [32]. An array of 6 μ m microelectrodes filled with membrane A was used for the functional lifetime test. After filling and a first preconditioning in a 1 mM KCl solution during 24 h, a calibration curve was recorded every week according to the procedure described earlier. In between the tests, the array remained conditioned in 1 mM KCl solution. Figure 8 shows that the lifetime of the array is remarkably long. In fact the response of the sensor remained stable for an entire month with the standard deviation staying below 4 %, even reaching a minimum of 1.4 % after 22 days. It must be emphasized that 15 out of 16 electrodes were functioning well during this entire period. After a month, the slope started to deteriorate and one more electrode failed. Besides, the lower detection limit slightly increased from the third week, but remained within the targeted working range during the 52 days of the experiment. This excellent lifetime result can partly be attributed to the large volume of plasticizer, carrier and ionic sites that is situated below the micropipette and probably also to the geometrical configuration of the microelectrode that prevents penetration of water causing hydrolysis of the surface forming a shunt. The optimal performance of the sensor as well as its lifetime is greatly influenced by several factors, such as the conditioning of the sensors as well as their storage. In fact, after a first use the ISE arrays could be kept dry for several weeks and be reused. As an example the ISE array used for the lifetime experiment shown in Figure 8 was kept dry for 25 days, and once rewetted presented a calibration curve of 53.0 ± 1.3 mV/pK⁺ for 13 microelectrodes. The detection limit was of $\log a_K = -4.5$ and

the upper detection limit surprisingly rose from 100 to 200 mM K⁺. That particular array was used for more than three months.

Immersion in physiological solutions

It is intended to grow cells overnight in the microwell where the ISE array is located in normal cell-culture medium that may include serum. For measurements, the medium will be replaced with a serum-free solution that presents an osmolarity similar to that of cytoplasm. This measurement strategy was applied by Stein et al. [33] who used a modified LAPS (light-addressable potentiometric sensor) to monitor the acidification rate of cell populations. The characterization of the microelectrodes response after being immersed overnight in physiological solutions is therefore important.

In measurements of biological samples, the loss of membrane ingredients into the sample is a primary concern. No effects of a likely leaching of membrane components on hepatocyte and cardiomyocyte cell cultures' viability were observed (results not shown). Another critical issue is the vulnerability of small surfaces to the adsorption of proteins. In this assay, after a first standard calibration, the ISE arrays were exposed to different physiological solutions under incubation conditions (37° C, 100% humidity, 5% CO₂). After 24 h, the chip was removed from the incubator and a new calibration curve was recorded. The difference of the slope sensitivity of the two calibration curves and their associated standard deviations were considered to be indicators of the contamination of the membrane due to the presence of proteins and growth factors. Table 2 summarizes the calibration results of K⁺-selective microelectrodes with 6 µm diameter after successive exposures to different physiological solutions. It must be mentioned that the array tested had a history of two and a half months of use and therefore had smaller initial sensitivity. In the first test, immersion in PBS did not seem to affect the microelectrodes response very much. Similarly, in test 2, after immersion in DMEM containing 1 % serum the array response was near-Nernstian, with a slight increase in sensitivity. In contrast, a significant drop of sensitivity was observed in both, tests 1 and 2, after a contact with DMEM containing either 5 or 10 % serum. Moreover, the standard deviations of the calibration curve slopes increased considerably in these latter solutions, indicating that the proteins adsorption on the selective membranes was inhomogeneous. In summary, after exposure to physiological solutions, the ISE arrays still show a linear but sub-Nernstian response that is still exploitable to monitor cell responses. Nevertheless, the extent of proteins adsorption on microelectrodes surface is difficult to quantify [34].

CONCLUSION

This paper describes the performance of an array of K⁺- and NH₄⁺-selective microelectrodes for cell culture testing. The arrays comprise 16 silicon nitride micropipette-based microelectrodes with a diameter of 6 µm or 2 µm, integrated in a 200 µm large and 350 µm deep microwell. Different ion-selective membrane compositions were evaluated with respect to the electrode sensitivity, selectivity, functional lifetime and stability. The results show that the microelectrodes with 5% PVC and respectively valinomycin/DOS and nonactin/NPOE exhibit an adequate linear response range and selectivity for extracellular monitoring of respectively K⁺ and NH₄⁺ ions in cell cultures. Providing a periodic recalibration, the functional lifetime of several weeks is also more than adequate for the envisaged application.

As shown by the preliminary tests, the sensitivity decreases upon exposing the K⁺-selective arrays to physiological solutions containing different concentrations of serum. However, as the decrease of the sensitivity is gradual, the monitoring of cell-based responses, such as apoptosis, necrosis or differentiation should be possible over a period of two to three days.

Acknowledgements

The authors thank the SAMLAB technical team for their help as well as the COMLAB. They also thank Dr. P. van der Wal for his helpful comments about the manuscript. The wire bonding was partly made at the CNS/NSF/NNIN facilities at Harvard University. SGe and OGu thank the Swiss National Science Foundation for respectively SNF project 205321-103961 and the SNF advanced researcher grant PA00A-105032. This work was also partially supported by the National Institutes of Health grant numbers R01DK43371 and P41EB002503, and the Shriners Hospitals for Children.

References

1. Purves, RD. Microelectrodes Methods for Intracellular Recording and Ionophoresis. Academic Press; London: 1981.
2. Ammann, D. Ion-selective Microelectrodes, Principles, Design and Applications. Springer-Verlag; Berlin: 1986.
3. Fry, CH.; Langley, SEM. Ion-selective electrodes for biological systems. Hardwood Academic Publishers; 2001.
4. Voipio, J.; Pasternack, M.; Macleod, K. Ion-selective microelectrodes, Chap. 11, Microelectrode techniques, The Plymouth workshop handbook. 2. Ogden, DC., editor. Company of Biologists; Cambridge, UK: 1994.
5. Urban, GE., editor. BioMEMS. Springer; 2006.
6. Cosofret V, Erdösy M, Johnson TA, Buck RP, Ash RB, Neuman MR. Anal Chem 1995;67:1647–1653.
7. Lindner E, Buck R. Anal Chem 2000;72(9):336A–345A.
8. Uhlig A, Lindner E, Teutloff C, Schnakenberg U, Hintsche R. Anal Chem 1997;69:4032–4038. [PubMed: 9322440]
9. Yoon HJ, Shin JH, Lee SD, Nam H, Cha GS, Strong TD, Brown RB. Sensors and Actuators B 2000;64:8–14.
10. Scheipers A, Wassmus O, Sundermeier C, Eshold J, Weiss Th, Gitter M, Ross B, Knoll M. Anal Chim Acta 2001;439:29–38.
11. Zhu J, Zhu Z, Lai Z, Wang R, Wu X, Zhang G, Zhang Z. Sensors and Materials 2002;14(4):209–218.
12. Gyurcsanyi RE, Rangisetty N, Clifton S, Pendley B, Lindner E. Talanta 2004;63:89–99.
13. Guenat OT, Generelli S, Dadras M, Berdondini L, de Rooij NF, Koudelka-Hep M. Journal of Micromechanics and Microengineering 2005;15:2372–2378.
14. Guenat OT, Dufour JF, van der Wal P, Morf W, de Rooij NF, Koudelka-Hep M. Sensors and Actuators B 2005;105:65–73.
15. Boon L, Meijer AJ. Eur J Biochem 1988;172:465–469. [PubMed: 3350009]
16. Umezawa Y, Bühlmann P, Umezawa K, Tohda K, Amemura S. Pure Appl Chem 2000;72(10):1851–2082.(IUPAC)
17. Dybko A. Sensors 2001;1:29–37.
18. Nam H, Cha GS, Strong TD, Ha J, Sim JH, Hower RW, Martin SM, Brown RB. Micropotentiometric Sensors. Proc of the IEEE 2003;91(6)
19. Bakker E, Bühlmann P, Pretsch E. Chem Rev 1997;97:3083–3132. [PubMed: 11851486]
20. Carden D, Diamond D, Miller A. J Exp Botany 2001;52(359):1353–59. [PubMed: 11432954]
21. Bühlmann P, Pretsch E, Bakker E. Chem Rev 1998;98:1593–1687. [PubMed: 11848943]
22. Bakker E, Bühlmann P, Pretsch E. Electroanalysis 1999;11(13):915–933.
23. Ghauri MS, Thomas JDR. Analyst 1994;119:2323–2326. [PubMed: 7872484]
24. Benco JS, Nienaber HA, McGimpsey WG. Anal Chem 2003;75:152–156. [PubMed: 12530832]
25. Bratov A, Abramova N, Munoz J, Dominguez C, Alegret S, Batroli J. J Electrochem Soc 1997;144(2):617–621.
26. Qin W, Zwickl T, Pretsch E. Anal Chem 2000;72:3236–3240. [PubMed: 10939393]
27. Van der Wal PD, Zielinska-Paciorek R, de Rooij N. Chimia 2003;57:643–645.
28. Bühner T, Peter H, Simon W. Pflügers Arch 1988;412:359–362.
29. De Beer D, van den Heuvel JC. Talanta 1988;35(9):728–730.

30. Cha GS, Meyerhoff ME. *Talanta* 1989;36(12):271–278.
31. Fibbioli M, Morf WE, Badertscher M, de Rooij NF, Pretsch E. *Electroanalysis* 2000;12(16)
32. Cha GS, Liu D, Meyerhoff ME, Cantor HC, Midgley AR, Goldberg HD, Brown RB. *Anal Chem* 1991;63:1666–1672. [PubMed: 1789437]
33. Stein B, George M, Gaub HE, Behrends JC, Parak WJ. *Biosensors and Bioelectronics* 2003;18:31–41. [PubMed: 12445442]
34. Burnett RW, Covington AK, Fogh-Andersen N, Kulpmann WR, Lewenstam A, Maas AH, Muller-Plathe O, VanKessel AL, Zijlstra WG. *Clin Chem Lab Med* 2000;38(4):363–370. [PubMed: 10928658]

Fig. 1.

Cross-section of two ion-selective microelectrodes integrated in the platform. The ion-selective cocktail is introduced in the micropipettes from the back-side of the chip, via a microchannel network. For the sake of clarity, the SiO₂ sacrificial layer is not shown, see [13] for the full fabrication process of the micropipettes.

Fig. 2.

SEM pictures of the platform for extracellular ionic measurement. a) Overall view of the main microchannel that widens on both ends in two holes. Microchannels for drug delivery are adjacent to the main channel. b) The array of ion-selective microelectrodes is located at the bottom of the 200 μm wide and 365 μm deep main microchannel. Inset: close-up of a silicon nitride micropipette with a 2 μm diameter.

Fig. 3. The platform with the ISE array is incorporated in a flow-through manifold with the reference electrode (RE) located downstream. Each microelectrode is connected to a high impedance input amplifier (E_1 , E_2 ,...).

Fig. 4. Calibration curves of two ISE arrays made of 6 μm microelectrodes. a) After three weeks of use, 15 K⁺-selective microelectrodes filled with membrane A were recorded in parallel in 150 mM NaCl (average slope: 56.2 ± 1.2 mV/pK⁺). b) Parallel responses of 10 NH₄⁺-selective microelectrodes filled with membrane C after two weeks of use (average slope: 41.0 ± 2.1 mV/pNH₄⁺) without background electrolyte. The curves are offset for the sake of clarity.

Fig. 5.
EMF responses of NH_4^+ in different solutions containing either monovalent or divalent interfering ions. HGMS contains 297 mM D-glucose, 1.8 mM CaCl_2 and 0.8 mM MgSO_4 .

Fig. 6.

Time dependent EMF responses of several ion-selective microelectrodes recorded under flow-through conditions (12.6 $\mu\text{L/s}$) at the same time. a) The transients were recorded from 2 μm in diameter microelectrodes filled with membrane A in 10^{-6} to 10^{-1} M KCl with 150 mM NaCl background, b) the transients of 6 μm microelectrodes filled with membrane E were measured in 10^{-6} to 10^{-1} M NH_4^+ mixed in HGMS. The curves are offset for the sake of clarity.

Fig. 7. Potential-time transients of 6 μm microelectrodes filled with membrane A under continuous flow condition (12.6 $\mu\text{L/s}$). The concentration of the KCl solutions was alternated between 1 and 10 mM for time intervals of about 2 and a half minutes. The background electrolyte was 150 mM NaCl.

Fig. 8. Lifetime of ISE arrays: an array of 15 K⁺-selective microelectrodes were tested for more than 50 days. Calibration curves were performed in 150 mM NaCl. LOD stands for limit of detection.

Table 1

Characteristics of the ion-selective microelectrodes, made of micropipettes of two different diameters and filled with membranes that differed as to the type of ionophore, ionic additive, plasticizer and amount of PVC used (in % weight). The typical sensitivity, the limit of detection (LOD) and the selectivity reached in the presence of interfering ions (j) are given in the table. The selectivity coefficients for Na^+ and K^+ were determined with a background level of 150 mM and 5.5 mM choride solution, respectively. m , n_f and n_t are the number of array tested, the number of electrodes used to calculate the calibration curve and the total number of electrodes of the array, respectively

Membrane	Ion=i	PVC in %	Plasticizer	Ionic additive	Diameter μm	Slope mV/dec	LOD $\log K_{ij}^{\text{pot}}$	Selectivity $\log K_{ij}^{\text{pot}}$ j=Na ⁺	$\log K_{ij}^{\text{pot}}$ j=K ⁺	Electrodes n_f/n_t	Arrays m
A	K^+	5	DOS	KTFPB	2	$55.4 \pm 1.0^*$	-5.3 [*]	-4.5		12/15	3
B	K^+	10	DOS	KTFPB	6	$57.3 \pm 2.0^*$	-5.4 [*]	-4.6		30/32	2
C	NH_4^+	5	DOS	KTFPB	2	$49.2 \pm 1.4^*$	-5.3 [*]	-4.5		8/15	3
					2	44.0 ± 1.3	-6.0	-		4/7	1
D	NH_4^+	5	DOS	NaTFPB	6	46.6 ± 1.0	-6.0	-2.7	-1.2	11/21	2
E	NH_4^+	5	NPOE	NaTFPB	6	45.9 ± 0.2	-6.0	-2.5	-	3/5	1
					6	$59.4 \pm 3.9^{***}$	-6.0 ^{***}	-2.9	-0.8	13/16	1

* measured with 150 mM NaCl background electrolyte

*** measured in HGMS

Microelectrodes responses after exposure to different physiological solutions during 24 hours at 37° C, 100 % humidity and 10% CO₂.
The initial slope characteristics are sub-Nernstian, since the test was performed with a two and a half months old chip

Table 2

	Slope mV/pK ⁺	SD mV/pK ⁺	n
Test 1	Initial calibration curve	52.7	13
	After 24h in PBS 1x	49.1	13
	After 24h in DMEM	45.5	13
Test 2	After 24h in DMEM + 10% FBS + 1% PS	39.5	13
	Initial calibration curve	53.9	3
	After 24h in DMEM + 1% FBS + 1% PS	57.0	3
	After 24h in DMEM + 5% FBS + 1% PS	53.7	3
	After 24h in DMEM + 10% FBS + 1% PS	54.1	3