Published in final edited form as:

J Biomech. 2009 February 9; 42(3): 286. doi:10.1016/j.jbiomech.2008.10.032.

Influence of Chondroitin Sulfate on the Biochemical, Mechanical and Frictional Properties of Cartilage Explants in Long Term Culture

Liming Bian¹, Michael Kaplun², David Y. Williams¹, Duo Xu¹, Gerard A. Ateshian², and Clark T. Hung¹

¹Cellular Engineering Laboratory, Department of Biomedical Engineering, Columbia University, New York, NY 10027, USA

²Musculoskeletal Biomechanics Laboratory, Department of Mechanical Engineering, Columbia University, New York, NY 10027, USA

Abstract

A recent study (Basalo et al. 2007) has shown that the friction coefficient of bovine articular cartilage is reduced significantly by the supplementation of chondroitin sulfate (CS) at a concentration of 100 mg/ml. This result suggests that intra-articular injection of CS may be used as a prophylactic treatment against the progression of osteoarthritis. The objective of this study was to test the hypothesis that long-term culture of cartilage explants in CS produces no adverse mechanical, biochemical, or cytotoxic effects, while reducing the friction coefficient relative to the control group. Long-term cultures of live bovine articular cartilage explants were performed with incubation in media containing CS of three different concentrations (0, 10 and 100 mg/ml). Frictional tests (cartilage on glass) were performed under constant stress (0.5MPa) for 3600 s and the time-dependent friction coefficient was measured. Samples incubated in a 100mg/ml of CS solution exhibited a significantly lower equilibrium friction coefficient than the control (0.05 ± 0.01 vs. 0.18 ± 0.02 on Day 0, 0.04 ± 0.01 vs. 0.14 ± 0.04 on Day 7 and 0.04 ± 0.01 vs. 0.15 ± 0.06 on Day 14). Samples incubated in 10 mg/ml of CS did not exhibit any significant decrease in the friction coefficient. Cell viability and DNA content were maintained in all groups. However, after 28 days of culture, the Young's modulus and glycosaminoglycan content of explants incubated in 100 mg/ml of CS decreased to 5% and 40% of their initial levels, respectively. Based on this adverse outcome the hypothesis of this study is rejected, dampening our enthusiasm for the use of intra-articular CS injections as a prophylactic treatment in osteoarthritis.

Introduction

In a series of recent studies on cartilage friction, we demonstrated that chondroitin sulfate (CS) serves as an effective boundary lubricant for articular cartilage. First, it was shown that cartilage that was enzymatically degraded with chondroitinase ABC exhibits a significantly higher friction coefficient than normal tissue (Basalo et al. 2005; Basalo et al. 2006), complementing the findings of an earlier study (Kumar et al. 2001); then it was shown that normal cartilage that had been incubated or tested in a saline bath with 100 mg/ml CS, exhibited much lower friction than tissue tested in saline with 10 mg/ml CS, or saline alone (Basalo et al. 2007).

These in vitro findings motivate the consideration of CS, which is a natural constituent of articular cartilage, for intra-articular therapeutic injections for the treatment of painful joint degenerative diseases, and as a potential prophylactic against the progression of cartilage degeneration (Ghosh 1988; Pinals 1992; Kelly 1998), in analogy to hyaluronic acid (Balazs et al. 1993). Prior to proceeding with animal studies, the objective of this study is to first

investigate the influence of high concentrations of exogenous CS on live cartilage explants in long-term culture. The hypothesis is that long-term culture of cartilage explants in high concentration CS produces no adverse mechanical, biochemical, or cytotoxic effects, while reducing the friction coefficient relative to the control group.

To test this hypothesis, we investigate the effect of CS on mechanical and frictional properties, biochemical composition, and chondrocyte viability, during long-term culture of live bovine articular cartilage explants. Explants of articular cartilage are commonly used experimentally to study cartilage function and mechanoregulation (Sah et al. 1989; Asanbaeva et al. 2007). We adopt the protocol of our recent study (Bian et al. 2008) where it was demonstrated that functional properties of cartilage explants, such as mechanical stiffness and biochemical composition, can be sustained at normal levels in a serum-free medium (Byers et al. 2006) for up to 6 weeks.

Materials and Methods

Sample Preparation and Culture

Bovine cartilage plugs were harvested from the femoral condyles of three 2-6 month-old calves. Explant disks of ($\varnothing 6$ mm $\times$ 5 mm) including superficial, middle and depth zone were obtained using a corneal punch. Explants were then cultured in a chemically-defined serum-free medium (DMEM, 1% ITS+ Premix, 50 μ g/ml L-proline, 0.1 μ M dexamethasone, 0.9 mM sodium pyruvate)(Byers et al. 2006)and supplemented with ascorbate 2-phosphate (50 μ g/ml) (37 $^{\circ}$ C, 5% CO₂). The serum-free medium is also referred to as a chondrogenic medium (CM), for its original use in inducing chondrogenesis of stem cells. The three experimental groups were: explants cultured in CM with no chondroitin sulfate (Control), with 10 mg/ml (CS10) and 100 mg/ml of chondroitin sulfate (CS100) (Sigma Chemical). The CS used in this study consists of 89.6% chondroitin-6-sulfate (CS-6) and 10.3% chondroitin-4-sulfate (CS-4) from shark cartilage, a proportion similar to that in human articular cartilage (93.3% CS-6). Media were changed three times a week.

Mechanical Testing

The mechanical properties of explant disks were evaluated at days 0, 7, 14, and 28 of culture, using a custom tabletop testing device (Mauck et al. 2000). The samples were placed in a testing chamber filled with PBS with the articular surface facing up. A loading platen positioned above the sample was moved down by a stepper motor to apply compression. A creep tare load of 0.1N was applied first, to ensure full contact between the loading platen and the sample top surface. The sample was subsequently compressed to 10% tare strain at a strain rate of 0.05% / s, before the onset of the stress relaxation test. The equilibrium Young's modulus (E_Y) was determined under unconfined compression at 10% strain at the end of the stress relaxation which lasted for 2000 seconds. The unconfined dynamic modulus was also measured, after reaching stress-relaxation equilibrium to 10% strain, by superimposing 1% strain amplitude at 0.1, 0.5, and 1 Hz. Tests of static and dynamic compressive properties were selected since the normal physiological loading mode of cartilage is compressive.

Frictional Testing

Friction measurements were performed at room temperature, in a physiological buffered saline (PBS) bath, in a previously described custom-designed testing apparatus (Krishnan et al. 2004). The friction apparatus consists of a sliding stage (Nutech, Deer Park, NY) with a motion control module (ACS Tech 80, Maple Grove, MN) to provide reciprocal translational motion; a stepper micrometer to provide normal load application (Oriental Instruments, Stratford, CT), connected to a linear variable differential transformer to measure specimen deformation (HR100, Shaevitz Sensors, Fair-field, NJ). Normal and frictional loads were measured with a

multiaxial load cell (JR3 Inc., Woodland, CA.). Cartilage specimens were placed within a small recess at the center of the test chamber, with the articular side facing up. Friction measurements (cartilage against a 1mm thick glass slide) were performed in unconfined compression stress-relaxation, at room temperature, with the specimen and glass surface immersed in PBS during the entire duration of the experiment. The friction measurements (cartilage-on-glass) were performed in unconfined compression creep, under reciprocal sliding motion consisting of 100 cycles over a range of ± 4.5 mm, at 1 mm/s. Under this testing configuration, the friction coefficient rises monotonically over time, from a minimum value denoted by $\mu_{\min}$ to a steady-state equilibrium value denoted by μ_{eq} , as shown in previous studies (Krishnan et al. 2004; Basalo et al. 2006). The pausing interval between two consecutive sliding cycles was gradually increased as the friction coefficient increased. This resulted in fewer sliding cycles during the later stage of the test, when the friction was high, helping to reduce tissue wear. A creep load of 6.3N (corresponding to a normal stress of 0.5 MPa) was ramped up in 5 s and held constant for the duration of the friction test (3600 s). The friction force and normal force were averaged over the back and forth portions of each cycle of reciprocal motion. This averaging procedure eliminates the contribution of the tangential force that may arise when the top and bottom faces of the cylindrical sample are not perfectly parallel. The time-dependent friction coefficient was determined from the ratio of the average friction force and normal force within each cycle; $\mu_{\min}$ and μ_{eq} were used in the statistical analyses.

Biochemical Analysis

One-half of each explant disk was weighed wet, lyophilized, reweighed dry, and digested in 0.5mg/ml Proteinase-K (Fisher Scientific; in 50mM Tris buffered saline containing 1mM EDTA, 1mM iodoacetamide and 10 mg/ml pepstatin A) at 56°C for 16 hrs. The PicoGreen assay (Invitrogen, Molecular Probes) was used to quantify the DNA content of the explant disks with Lambda phage DNA (0–1 mg/ml) as a standard (McGowan et al. 2002). The GAG content was measured using dimethylmethylene blue (DMMB, Sigma Chemicals) dye-binding assay with shark chondroitin sulfate (0–50 mg/ml) as a standard (Farndale et al. 1986). The overall collagen content was assessed by measuring the orthohydroxyproline (OHP) content via dimethylaminobenzaldehyde and chloramine T assay. Collagen content was calculated by assuming a 1:7.5 OHP-to-collagen mass ratio (Hollander et al. 1994). The collagen and GAG contents were normalized to the disk wet weight. Cell viability was assessed using the LIVE/DEAD Assay Kit (Molecular Probes) where live cells are stained green with Calcein-AM and dead cells stained red with Propidium homodimer.

Statistical Analysis

Statistica (Statsoft, Tulsa, OK) was used to perform statistical analyses using two-way ANOVA and the Tukey HSD Post Hoc test ($n = 4\sim 6$ per group) for two independent factors: culture duration (day 0, day 7, day 14 and day 28) and treatment (Control, CS10 and CS100). Interactions between these two factors were also analyzed. Shapiro-Wilk test was performed to verify the normality of the data.

Results

The water content of explants remained unchanged over time in culture ($p=0.51$), as a function of treatment ($p=0.11$), or interactions thereof ($p=0.28$), averaging $77.9 \pm 2.6\%$ by weight. After four weeks in culture, the equilibrium Young's modulus and dynamic modulus of the explant disks cultured with media containing no chondroitin sulfate (Control) and 10 mg/ml of CS (CS10) remained stable near initial Day 0 values (0.95 ± 0.26 MPa and 27.8 ± 7.3 MPa, respectively) (Figure 1 A, B). However, the equilibrium modulus of the explant disks cultured with 100 mg/ml of CS in the media (CS100) decreased significantly on Day 14 and dropped

to about 5% of the Day 0 value on Day 28 (Figure 1 A, $p<0.005$). There was also a significant reduction in the dynamic modulus of the CS100 group on Day 28 (Figure 1 B, $p<0.005$).

Frictional testing in a PBS bath indicated that the cartilage explants cultured with 100 mg/ml of CS in the culture medium exhibited significantly lower equilibrium frictional coefficient as compared to the control group ($p<0.05$), whereas 10 mg/ml of CS did not significantly reduce the equilibrium friction coefficient ($p=0.24$) (Figure 1 C). No significant difference in minimum friction coefficient was observed among any of the groups ($p>0.05$).

On Day 28, the GAG content of the CS100 group dropped to 2.2 ± 0.2 % of the disks wet weight, significantly lower than the other two groups ($p<0.005$), whereas the GAG content of the control and CS10 groups stayed nearly constant at the Day 0 level (Figure 1 D). In contrast, the collagen and DNA content of all three groups did not change significantly throughout the 4 week culture and remained at the Day 0 level of 10.4 ± 0.4 % and 0.09 ± 0.04 % of the sample wet weight, respectively (Figure 1 E, F).

Cell viability staining on Day 28 showed that there was negligible cell death, with the great preponderance of cells in all groups remaining viable (Figure 2).

Discussion

The objective of this study was to test the hypothesis that long-term culture of cartilage explants in high concentration CS produces no adverse mechanical, biochemical, or cytotoxic effects, while reducing the friction coefficient relative to the control group. The long-term aim is to use intra-articular CS injections as a prophylactic treatment against the progression of joint degeneration in osteoarthritis. A strong rationale in favor of this treatment modality is the recent observation that CS, which has the benefit of being a molecule native to articular cartilage, is an effective boundary lubricant for cartilage, at a concentration of 100 mg/ml (Basalo et al. 2007).

However, the results of this study demonstrate a significant loss of native (endogenous) GAG in long-term culture of explants in CS at 100 mg/ml, associated with a concomitant reduction in their compressive equilibrium and dynamic moduli. Despite the fact that the equilibrium friction coefficient in the CS100 group is generally lower than in control specimens, and that long-term incubation does not result in cell death, the outcomes for GAG content and mechanical properties lead us to reject the overall hypothesis that incubation has no adverse effects.

The CS concentration of 100 mg/ml adopted in this study was motivated by our earlier finding that improvements in the frictional response occur at this concentration, but not at 10 mg/ml or less (Basalo et al. 2007). For comparison purposes, the native level of GAG in bovine articular cartilage ranges approximately from 40 to 60 mg/ml (Figure 1 C, Control group, assuming the cartilage wet weight is mostly made up of the weight of water, therefore 4 to 6% GAG/wet weight can be considered as 0.04-0.06 gram GAG/ 1 gram water, or 40 to 60 mg GAG/ml.). Therefore, the concentration of CS used here is on the same order, though somewhat larger than native levels.

It is intriguing that 100 mg/ml of exogenous CS leads to a progressive loss of endogenous GAG, even while the chondrocytes remain alive and capable of maintaining the collagen content over time (Figure 1 D, E). This outcome suggests that chondrocytes are maintaining at least part of their normal function and that the loss of endogenous GAG is a result of normal catabolic activity, uncompensated by sufficient GAG synthesis. A potential interpretation of this outcome is that chondrocytes are responding to a feedback mechanism that regulates GAG synthesis in response to the concentration of GAG present in the extracellular matrix, and that

this mechanism is being confounded by the exogenous CS. By this interpretation, chondrocytes fail to recognize the natural degradation and loss of endogenous GAG due to the presence of high concentrations of exogenous CS. The absence of significant differences between the CS10 and Control groups suggests that 10 mg/ml of CS is too low to induce chondrocytes to significantly downregulate their GAG synthesis. This mechanism may be mediated by the large electrostatic charge of sulfated glycosaminoglycans.

No significant differences were observed in $\mu_{\min}$, neither with treatment nor time in culture. This outcome is not unexpected, since the value of $\mu_{\min}$ is regulated mostly by interstitial fluid pressurization (Krishnan et al. 2004), which reduces the friction considerably upon initial loading. Over time, as the interstitial fluid pressure subsides, the friction coefficient increases and its magnitude becomes significantly regulated by boundary friction mechanisms, as evidenced by the influence of CS on μ_{eq} (Basalo et al. 2007).

Previous studies showed that high dosage of exogenous CS (100mg/ml) can reduce friction coefficient when the cartilage still possess physiological levels of endogenous GAG (Scenario 1) (Basalo et al. 2007). Furthermore, when endogenous GAG was significantly lowered by enzymatic digestion, the friction coefficient of cartilage explants increased in the absence of exogenous CS (Scenario 2)(Basalo et al. 2006). In this study, as shown in Figure 1 C-D, the endogenous GAG content of the CS100 group only became significantly lower than the control on Day 28. Hence on Days 7 and 14, when the CS100 group still possessed similar level of endogenous GAG as the control, the presence of exogenous CS (100mg/ml) significantly lowered the friction coefficient (similar to Scenario 1). On the other hand, on Day 28, the counteractive effect of low endogenous GAG negated some reduction in friction coefficient due to the presence of exogenous CS. This resulted in the friction coefficient of the CS100 group being not significantly lower than that of the control.

The results of this study do not validate the interpretation that exogenous CS confounds the chondrocytes' regulatory mechanism for synthesizing PGs, but they provide evidence in support of it. Further support may be achieved in future studies, by investigating whether release of the exogenous CS over subsequent incubation times might induce chondrocytes to recover their GAG synthesis back to control levels. Other experiments may use alternative negatively charged molecules not native to articular cartilage, to investigate whether a feedback mechanism mediated by charge effects indeed exists.

While these basic science issues motivate follow-up studies, the objective of the current study was more practically oriented toward investigating the safety of performing intra-articular injections of CS in an animal model, followed potentially by human studies. The current results suggest that sustained exposure to high concentrations of CS may have harmful consequences to the articular cartilage of diarthrodial joints. There are several animal and a few human in vivo studies of intra-articular injections of CS to date (Dettmer 1979; Hess et al. 1982; Kalbhen 1982; Kalbhen 1983; Olijhoek et al. 1988; Sarkozi et al. 1988; Skrivankova et al. 1991). The pharmaceutical product delivered intra-articularly in these studies, typically Arteparon or GAGPS, is a purified chondroitin sulfate. For example, in a human study (Dettmer 1979) 125 mg of this drug was injected in a 0.5 ml solution in 50 osteoarthritic subjects, at six time points over 3 weeks. According to these studies, intra-articular injections of CS were found to be well tolerated (Hess et al. 1982), reducing pain (Sarkozi et al. 1988). Intra-articular injections of CS were also reported to have a protective effect on the articular surface (Olijhoek et al. 1988), inhibiting cartilage degenerative enzymes (Kalbhen 1982; Kalbhen 1983; Skrivankova et al. 1991).

In addition, several studies showed that CS was able to increase proteoglycan production by chondrocytes (Schwartz et al. 1975; Bassleer et al. 1998). Most of these studies, which used

much lower effective CS concentrations than the current study, did not report adverse effects from these injections, though their experimental designs did not include quantitative measurements of mechanical or frictional properties, or biochemical composition, as performed here. In contrast, a recent study showed that intra-articular injection of CS carried by hydrogel at 100 mg/ml concentration improved the biomechanical and histological properties of the repaired cartilage of chondral defects in a rabbit model (Hui et al. 2007). It seems that the hydrogel carrier may have played a beneficial role in this animal study.

In the current study, the cartilage explants included the superficial, middle and deep zones. It is well established that the cells in different zones have different characteristics (Aydelotte et al. 1988; Wong et al. 1996; Hidaka et al. 2006) and can respond differently to the same external stimuli (Hwang et al. 2007; Li et al. 2007). A recent study showed that chondrocytes in one zone can modulate the behavior of chondrocytes in a different zone (Jiang et al. 2008). Therefore, in future studies, it may be interesting to study the effect of zonal cell interactions on the effect of CS.

In summary, based on the outcome of this study, it is anticipated that intra-articular injections of CS at high concentrations may have a harmful effect on articular cartilage, by enhancing endogenous GAG loss. Though further animal studies may be needed to validate this finding in vivo, the outcome of this in vitro study dampens our enthusiasm for the use of intra-articular CS injections at high concentrations, as a prophylactic treatment in osteoarthritis.

Acknowledgments

This work was supported by National Institutes of Health grants AR43628 (GAA), AR46568 (CTH) and Musculoskeletal Transplant Foundation grant CU07-194 (CTH).

References

- Asanbaeva A, Masuda K, Thonar EJ, Klisch SM, Sah RL. Mechanisms of cartilage growth: modulation of balance between proteoglycan and collagen in vitro using chondroitinase ABC. *Arthritis Rheum* 2007;56(1):188–98. [PubMed: 17195221]
- Aydelotte MB, Kuettner KE. Differences between sub-populations of cultured bovine articular chondrocytes. I. Morphology and cartilage matrix production. *Connect Tissue Res* 1988;18(3):205–22. [PubMed: 3219850]
- Balazs EA, Denlinger JL. Viscosupplementation: a new concept in the treatment of osteoarthritis. *J Rheumatol Suppl* 1993;39:3–9. [PubMed: 8410881]
- Basalo IM, Chahine NO, Kaplun M, Chen FH, Hung CT, Ateshian GA. Chondroitin sulfate reduces the friction coefficient of articular cartilage. *J Biomech* 2007;40(8):1847–54. [PubMed: 17084404]
- Basalo IM, Chen FH, Hung CT, Ateshian GA. Frictional response of bovine articular cartilage under creep loading following proteoglycan digestion with chondroitinase ABC. *J Biomech Eng* 2006;128(1):131–4. [PubMed: 16532626]
- Basalo IM, Raj D, Krishnan R, Chen FH, Hung CT, Ateshian GA. Effects of enzymatic degradation on the frictional response of articular cartilage in stress relaxation. *J Biomech* 2005;38(6):1343–9. [PubMed: 15863119]
- Bassleer CT, Combal JP, Bougaret S, Malaise M. Effects of chondroitin sulfate and interleukin-1 beta on human articular chondrocytes cultivated in clusters. *Osteoarthritis Cartilage* 1998;6(3):196–204. [PubMed: 9682786]
- Bian L, Lima EG, Angione SL, Ng KW, Williams DY, Xu D, Stoker AM, Cook JL, Ateshian GA, Hung CT. Mechanical and biochemical characterization of cartilage explants in serum-free culture. *J Biomech* 2008;41(6):1153–9. [PubMed: 18374344]
- Byers BA, Mauck RA, Tuan RS. Temporal exposure of TGF- β 3 under serum-free conditions enhances biomechanical and biochemical maturation of tissue-engineered cartilage. *Trans ORS* 2006;31:0043.

- Dettmer N. The therapeutic effect of glycosaminoglycan polysulfate (Arteparon) in arthroses depending on the mode of administration (intraarticular or intramuscular). *Z Rheumatol* 1979;38(56):163–81. [PubMed: 473929]
- Farndale RW, Buttle DJ, Barrett AJ. Improved quantitation and discrimination of sulphated glycosaminoglycans by use of dimethylmethylene blue. *Biochim Biophys Acta* 1986;883(2):173–7. [PubMed: 3091074]
- Ghosh P. Anti-rheumatic drugs and cartilage. *Baillieres Clin Rheumatol* 1988;2(2):309–38. [PubMed: 3066497]
- Hess H, Rothhaar J, Thiel W. Clinical studies of intra-articular injections of Arteparon. Retrospective study following the treatment of 754 patients. *Fortschr Med* 1982;100(35):1624–7. [PubMed: 6217139]
- Hidaka C, Cheng C, Alexandre D, Bhargava M, Torzilli PA. Maturation differences in superficial and deep zone articular chondrocytes. *Cell Tissue Res* 2006;323(1):127–35. [PubMed: 16133144]
- Hollander AP, Heathfield TF, Webber C, Iwata Y, Bourne R, Rorabeck C, Poole AR. Increased damage to type II collagen in osteoarthritic articular cartilage detected by a new immunoassay. *J Clin Invest* 1994;93(4):1722–32. [PubMed: 7512992]
- Hui JH, Chan SW, Li J, Goh JC, Li L, Ren XF, Lee EH. Intra-articular delivery of chondroitin sulfate for the treatment of joint defects in rabbit model. *J Mol Histol* 2007;38(5):483–9. [PubMed: 17653606]
- Hwang NS, Varghese S, Lee HJ, Theprungsirikul P, Canver A, Sharma B, Elisseeff J. Response of zonal chondrocytes to extracellular matrix-hydrogels. *FEBS Lett* 2007;581(22):4172–8. [PubMed: 17692846]
- Jiang J, Leong NL, Mung JC, Hidaka C, Lu HH. Interaction between zonal populations of articular chondrocytes suppresses chondrocyte mineralization and this process is mediated by PTHrP. *Osteoarthritis Cartilage* 2008;16(1):70–82. [PubMed: 17644010]
- Kalbhen DA. Chondroprotective and antiarthrotic properties of glycosaminoglycan polysulfate (GAGPS) in gonarthrosis in animal experiments. *Z Rheumatol* 1982;41(5):219–29. [PubMed: 6218713]
- Kalbhen DA. Experimental confirmation of the antiarthritic activity of glycosaminoglycan polysulfate. *Z Rheumatol* 1983;42(4):178–84. [PubMed: 6649925]
- Kelly GS. The role of glucosamine sulfate and chondroitin sulfates in the treatment of degenerative joint disease. *Altern Med Rev* 1998;3(1):27–39. [PubMed: 9600024]
- Krishnan R, Kopacz M, Ateshian GA. Experimental verification of the role of interstitial fluid pressurization in cartilage lubrication. *J Orthop Res* 2004;22(3):565–70. [PubMed: 15099636]
- Kumar P, Oka M, Toguchida J, Kobayashi M, Uchida E, Nakamura T, Tanaka K. Role of uppermost superficial surface layer of articular cartilage in the lubrication mechanism of joints. *J Anat* 2001;199(Pt 3):241–50. [PubMed: 11554503]
- Li Z, Yao S, Alini M, Grad S. Different response of articular chondrocyte subpopulations to surface motion. *Osteoarthritis Cartilage* 2007;15(9):1034–41. [PubMed: 17442595]
- Mauck RL, Soltz MA, Wang CC, Wong DD, Chao PH, Valhmu WB, Hung CT, Ateshian GA. Functional tissue engineering of articular cartilage through dynamic loading of chondrocyte-seeded agarose gels. *J Biomech Eng* 2000;122(3):252–60. [PubMed: 10923293]
- McGowan KB, Kurtis MS, Lottman LM, Watson D, Sah RL. Biochemical quantification of DNA in human articular and septal cartilage using PicoGreen and Hoechst 33258. *Osteoarthritis Cartilage* 2002;10(7):580–7. [PubMed: 12127839]
- Olijhoek G, Drukker J, van der Linden TJ, Terwindt-Rouwenhorst EA. Drug effects on arthrosis. Comparison in rabbits of 3 modes of action. *Acta Orthop Scand* 1988;59(2):186–90. [PubMed: 2452552]
- Pinals RS. Pharmacologic treatment of osteoarthritis. *Clin Ther* 1992;14(3):336–46. discussion 335. [PubMed: 1386287]
- Sah RL, Kim YJ, Doong JY, Grodzinsky AJ, Plaas AH, Sandy JD. Biosynthetic response of cartilage explants to dynamic compression. *J Orthop Res* 1989;7(5):619–36. [PubMed: 2760736]
- Sarkozi AM, Nemeth-Csoka M, Bartosiewicz G. Effects of glycosaminoglycan polysulphate in the treatment of chondrocalcinosis. *Clin Exp Rheumatol* 1988;6(1):3–8. [PubMed: 2456173]

- Schwartz NB, Dorfman A. Stimulation of chondroitin sulfate proteoglycan production by chondrocytes in monolayer. *Connect Tissue Res* 1975;3(2):115–22. [PubMed: 126838]
- Skrivankova B, Podrazky V, Trnavsky K, Julis I. Effect of selected antirheumatic drugs on the metabolism of cartilage and synovial tissue in experimental arthropathy. *Methods Find Exp Clin Pharmacol* 1991;13(8):523–8. [PubMed: 1659645]
- Wong M, Wuethrich P, Eggli P, Hunziker E. Zone-specific cell biosynthetic activity in mature bovine articular cartilage: a new method using confocal microscopic stereology and quantitative autoradiography. *J Orthop Res* 1996;14(3):424–32. [PubMed: 8676256]

Figure 1. Equilibrium Young's modulus (EY) (A), dynamic modulus (B) and equilibrium friction coefficient (μ_{eq}) (C) of the explants. GAG content (D), collagen content (E) and DNA content (F) of the explants normalized by wet weight. * $p < 0.005$ vs. Cont and CS10. Cont: control group; CS10/100: explants culture with 10/100 mg/ml of chondroitin sulfate in the medium.

Figure 2. Viability staining of the cartilage explants in Control (A), CS10 (B) and CS100 (C) group on day 28. Green: live cells; Red: dead cells; DZ: deep zone; MZ: middle zone; SZ: superficial zone.