Published in final edited form as:

Langmuir. 2010 April 6; 26(7): 4620–4622. doi:10.1021/la100364v.

Hexagonal Organic Nanopillar Array from Melamine-Cyanuric Acid Complex

Hai-Feng Ji* and Xiaohe Xu

Department of Chemistry, Drexel University, Philadelphia, PA 19104, Phone: 01-215-895-2562, Fax: 01-215-895-1265

Abstract

We report a well-defined, organic, hexagonal nanopillar array on gold surface. The array was prepared from a cyanuric acid-melamine complex by mean of a sequential mixing on a gold surface. These nanopillars had uniform diameters of 200–400 nm and 1 μ m in length. They were well faceted with hexagonal cross-sections. The nanopillars had a crystalline structure, and the pillars exhibited a layered texture in the longitudinal direction.

Keywords

Nanoassembly; hexagonal; surface crystallization

Formation of multiple hydrogen bonds between complementary organic molecules has recently been exploited in the molecular self-assembly of well-defined artificial supramolecular structures and materials.¹ These molecular assemblies refer to those that are soluble in water or organic media. A system built by triple hydrogen bonds from cyanuric acid (CA) and melamine (M) derivatives is one of the most widely studied H-bonding systems for self assemblies.² It has been reported that the interaction of cyanuric acid with melamine forms a stable, insoluble complex CA·M. This complex was composed of a number of molecular assemblies, one of which was a cyclic CA₃M₃ rosette assembly³ (Figure 1). This CA₃M₃ rosette assembly was the basic structure in a series of reports for the design and synthesis of supramolecular assemblies that were stable in solutions.

With additional weak interactions, such as π – π interactions, hydrophobic interactions, and van der Waals interactions, it is expected that the CA₃M₃ rosettes molecular assemblies can be hierarchically stacked or coordinated into insoluble nano or micro structures in the three-dimensional space. However, the expected hexagonal nanostructures of the CA·M complex were never observed. In this work, we report on an assembling approach for forming an array of well-defined hexagonal nanopillars of CA·M on a gold surface.

The solubility of the CA·M complex is 2.2 mg/L, which corresponds to mixing equal volume of 1.73×10^{-5} M melamine and cyanuric acid. Reports have shown that simple mixing cyanuric acid and melamine or other small triazine compounds did not form well-defined nanostructures⁴ because of a large number of hydrogen-bonded motifs in the complexes, including linear tape and crinkled tape⁵ (Figure 1).

hj56@drexel.edu.

Supporting Information Available: Additional figures.

Under two special conditions, two crystalline CA·M complexes have been formed. The crystal structure of CA·M·3HCl was a tape structure.⁶ The CA·M complex formed from a hydrothermal process had a rosette crystal structure⁷. However, in both cases, the crystals were in plate shapes. No hexagonal structures were observed.

Based on the understanding that the rosette structure is geometrically and enthalpically favored over other structures⁸, our objective was to develop methods to assemble cyanuric acid and melamine to well-defined, hexagonal nanostructures. We first re-examined a solid precipitated from mixing 0.01M of cyanuric acid and 0.01M of melamine at 1:1 ratio in water and found that less than 0.01% of these solids did in fact have hierarchically hexagonal structures (Figure 2), which was the direct evidence of the rosette structure.

Although only trace amounts of the hexagonal structures were observed, their existence indicated that these CA·M hexagonal nanostructures may be mass-produced should the conditions be well-controlled. Initially, we expected that the amounts of these nanostructures would increase at lower concentrations and lower temperatures because of a slower self-assembling process. However, no obvious increase in the amount of the hexagonal structures was observed under these conditions.

When we mixed cyanuric acid and melamine at lower concentrations on a gold surface, we obtained an array of nearly 100% hexagonal nanopillars of the CA·M complex (Figure 3). In this facile and unique approach, a 20- μ L of cyanuric acid (or melamine) solution was first cast on the gold surface; then another 20- μ L of the complementary melamine (or cyanuric acid) in an 1:1 stoichiometry was added to mix the two chemicals directly on the surface. Water was allowed to evaporate at ambient temperature to yield a white coating on the surface. Control experiments showed that evaporation of solutions of pure CA or pure M did not form any ordered structures (Figure S1 in the supplementary materials). However, it should be noted that melamine can form different 2D epitaxial networks on gold, and one of this network is hexagonal.⁹

One of the most distinctive features of these CA·M hexagonal nanopillars was that they formed an array of epitaxial, aligned nanopillars that were vertically oriented on the substrate surface, but with a $20 \pm 5^\circ$ tilt angle. The 20° tilt angle might find support from precedent computational work.¹⁰ These nanopillars had diameters of 200–400 nm and $1 \mu\text{m} \pm 0.3 \mu\text{m}$ in length. They were well faceted with hexagonal cross-sections (Fig. 3). The density of the nanopillars on the gold surface was approximately $0.1/\mu\text{m}^2$ and was not dependent on the mixing sequence of the two chemicals. When the above procedure was repeated three times at the same spot, the nanopillar array was denser and both the diameter and the length of the nanopillars increased as shown in Figure 4. However, when cyanuric acid and melamine at higher concentrations were mixed on the gold surface, irregular CA·M complexes increased (Figure S2 in the supplemental materials). The IR spectra confirmed the nanopillars are made of 1:1 mixture of cyanuric acid and melamine (figure not shown).

It should be noted that evaporation of water step is not necessary. Evaporation of water resulted in the nanopillar array at a higher density, but the nanopillar could be observed within minutes after mixing the two chemicals on the surface. The CA·M complexes nucleate as a thin, hexagonal plate on the gold surface at the onset stage, and grew wider and taller after further solvent evaporated. The nanopillars 1 to 3 in Figure 5 corresponded different nucleation stages of the growth.

The nanopillars in Figure 3 were dispersed onto a transmission electron microscopy (TEM) grid for structural analysis. TEM results showed that the C·M nanopillars (Figure 6) had a crystalline structure, and the pillars exhibited a layered texture in the longitudinal direction. The corresponding electron diffraction pattern (Figure 6 inset) showed diffraction spots with

8.84 Å *d*-spacing in the perpendicular direction and 3.31 Å *d*-spacing in the longitudinal nanopillar direction, which suggested that the molecules were oriented with their long axis perpendicular to the pillar and the π - π stacking direction parallel to the pillar. The 8.84 Å distance between two cyanuric acid molecules in a CA-M-CA arrangement (Figure 1) was modeled by Chem3D.

Owing to the crystalline nature, the solubilities of cyanuric acid and melamine are very low in most organic solvents. This limited our investigation of solvent effects on the morphology of the C·M nanostructures to several polar solvents, such as ethanol, ethylene glycol, and DMSO. Our experiments showed that no hexagonal C·M nanostructures were observed when these solvents were used (Figure S3 in the supplemental materials). These results indicated that, beside the π - π interaction, the hydrophobic effect may also contributed to the formation of the well-defined C·M nanopillar in water. However, the role played by solvent on the crystal growth and the morphology may be more complicated¹¹ and will be further studied in the future.

Substrates played a major role in the growth of the C·M nanopillars on the substrates and it even determined the presence or absence of the nanopillars. The hexagonal nanopillars were formed on the gold and glass surfaces, but not on silicon surfaces. On the glass surface, the density of the C·M hexagonal nanopillars prepared from 1×10^{-4} M solutions was approximately $30 / \mu\text{m}^2$, which was much greater than that of $0.1 / \mu\text{m}^2$ on the gold surface. The C·M nanopillars on the glass surface were shorter (200 nm) and the diameter (50–100 nm) was smaller than those on the gold surface. These nanopillars were not as well faceted as those on the gold surfaces (Figure S4 in the supplemental materials). On the silicon surface, the C·M complex did not aggregated to ordered structures (Figure S5 in the supplemental materials). One possible explanation of these results is that the cyanuric acid and melamine could not nucleate on a silicon surface because of the nonpolar property of the silicon surface. On the other hand, the glass surface provided abundant polar hydroxyl sites for faster nucleation of the C·M complexes than the gold surface. Judging from the above results, the gold surfaces was the most favored nucleation surface for the C·M hexagonal nanopillar structures.

In summary, we developed an array of well-defined hexagonal nanostructures of cyanuric acid-melamine complex by mean of sequential mixing on a gold surface. The hexagonal nanostructures may be used as building blocks for optical electronics, nanoelectronic devices, heterogeneous catalysis, and nanosensors.

The sequential mixing method described herein provides an easy control of nanometer-scale structures and represents a simple but significant advance in the functionality of building blocks for nanoscience and nanotechnology. If this sequential mixing method can indeed be used to grow a variety of nanostructure arrays that are self-assembled from organic, inorganic, and organic-inorganic hybrid materials, we would name it the Crystallization after Mixing on Surfaces (CAMS) method. This is because that the method contains two steps, mixing and crystallization on the surface, simultaneously. For comparison, our preliminary results show that few hexagonal structures on the surface were observed when the two chemicals were mixed in a container before transferring them on to the gold surface; this was probably because the self-assembling process was disrupted during the transfer process. A simple phrase, “sequential mixing”, does not provide all the information of the method. CAMS is coincidentally an acronym of Cyanuric-Acid-Melamine-System (CA-M-S). We expect that the CAMS method could offer wide opportunities for technological applications due to the capability of large-scale fabrication of nanometer-sized systems with controllable morphologies and properties.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

REFERENCES

1. a) Macgillivray LR, Atwood JL. *Nature* 1997;389:467–472. b) Meissner RS, Rebek J Jr, de Mendoza J. *Science* 1995;270:1485–1488. [PubMed: 7491493] c) Zimmerman SC, Zeng F, Reichert DFC, Kolotuchin CV. *Science* 1996;271:1095–1098. [PubMed: 8599085] d) Sijbesma RP, Beijer FH, Brunsveld L, Folmer BJB, Hirschberg JKK, Lange RFM, Lowe JKL, Meijer EW. *Science* 1997;278:1601–1604. [PubMed: 9374454]
2. a) Seto CT, Whitesides GM. *J. Am. Chem. Soc* 1993;115:1330–1340. b) Lehn J-M. *Angew. Chem. Int. Ed. Engl* 1988;27:89–112. c) Change S-K, Hamilton AD. *J. Am. Chem. Soc* 1988;110:1318–1319. d) Doig AJ, Williams DH. *J. Am. Chem. Soc* 1992;114:338–343. e) Seto CT, Mathias JP, Whitesides GM. *J. Am. Chem. Soc* 1993;115:1321–1329. f) Kawasaki T, Tokuhiko M, Kimizuka N, Kunitake T. *J. Am. Chem. Soc* 2001;123:6792–6800. [PubMed: 11448183] g) Yagai S, Nakajima T, Kishikawa K, Kohmoto S, Karatsu T, Kitamura A. *J. Amer. Chem. Soc* 2005;127:11134–11139. [PubMed: 16076221] h) Zerkowski JA, Mathias JP, Whitesides GM. *J. Amer. Chem. Soc* 1994;116:4305–4315.
3. a) Seto CT, Whitesides GM. *J. Am. Chem. Soc* 1993;115:905–916. b) Seto CT, Whitesides GM. *J. Am. Chem. Soc* 1990;112:6409–6411.
4. a) Chen Y, Wang Q, Yan W, Tang H. *Poly. Degrad. Stab* 2006;91:2632–2643. b) Mathias JP, Simanek EE, Zerkowski JA, Seto CT, Whitesides GM. *J. Am. Chem. Soc* 1994;116:4316–4325. c) Zerkowski JA, Seto CT, Wierda DA, Whitesides GM. *J. Am. Chem. Soc* 1990;112:9025–9026.
5. a) Whitesides GM, Simanek EE, Mathias JP, Seto CT. *Science* 1991;254:1312–1319. [PubMed: 1962191] b) MacDonald JC, Whitesides GM. *Chem. Rev* 1994;94:2382. c) Beijer FH, Kooijman H, Spek AL, Sijbesma RP, Meijer EW. *Angew. Chem. Int. Ed. Engl* 1998;37:75–78.
6. Wang Y, Wei B, Wang QJ. *Crystallogr. Spectrosc. Res* 1990;20:79–84.
7. Ranganathan A, Pedireddi VR, Rao CNR. *J. Am. Chem. Soc* 1999;121:1752–1753.
8. a) Mathias JP, Seto CT, Simanek EE, Whitesides GM. *J. Amer. Chem. Soc* 1994;116:1725–1736. b) Vreekamp RH, Van Duynhoven JPM, Huber M, Verboom W, Reinhoudt DN. *Angew. Chem. Int. Ed* 1998;37:1247–1251. c) Kimizuka N, Kawasaki T, Hirata K, Kunitake T. *J. Am. Chem. Soc* 1995;117:6360–6361. d) Kimizuka N, Fujikawa S, Kuwahara H, Kunitake T, Marsh A, Lehn J-M. *J. Chem. Soc., Chem. Commun* 1995:2103–2104. e) Choi IS, Li X, Simanek EE, Akaba R, Whitesides GM. *Chem. Mater* 1999;11:684–690.
9. Silly F, Shaw AQ, Castell MR, Briggs GAD, Mura M, Martsinovich N, Kantorovich L. *J. Phys. Chem. C* 2008;112:11476.
10. Weissbuch I, Lahav M, Leiserowitz L. *Cryst. Growth Des* 2003;3:125.
11. Lahav M, Leiserowitz L. *Chem. Engin. Sci* 2001;56:2245.

Cyclic rosette structure

Crinkled tape

Linear tape

Figure 1.
Possible structures of a complex of cyanuric acid with melamine.

Figure 2. SEM images of 1:1 complexes of melamine (0.01M) and cyanuric acid (0.01 M) that were precipitated from water, pH 7.0. Most of the complexes were in the form of irregular structures as those shown in (A). Less than 0.01% of the complexes had sorts of hexagonal morphologies as shown in (B), (C), and (D).

Figure 3.

Top and side views of SEM images of 1:1 CA-M hexagonal nanopillars on a gold surface. A drop of 20 μL of cyanuric acid at 1×10^{-4} M in water, pH 7.0 was cast on the gold surface followed by an addition of a 20 μL of melamine at 1×10^{-4} M in water, pH 7. The solution was left alone at ambient temperature till the water was evaporated.

Figure 4.

SEM images of 1:1 CA:M hexagonal nanopillars on a gold surface. A drop of 20 μL of cyanuric acid at 1×10^{-4} M in water, pH 7.0, was cast on the gold surface first followed by an addition of a 20 μL of melamine at 1×10^{-4} M in water, pH 7. The substrate was left alone till the water was evaporated. The above procedure was repeated three times. The right figure shows a side view of the nanopillars.

Figure 5.

SEM images of 1:1 CA:M hexagonal nanopillars on a gold surface. A drop of 20 μL of cyanuric acid at 1×10^{-3} M in water, pH 7.0, was cast on the gold surface first followed by an addition of a 20 μL of melamine at 1×10^{-3} M in water, pH 7. The water was removed within 5 minutes after the solutions were mixed.

Figure 6.
TEM image and electron diffraction pattern of a CA-M nanopillar.