Published in final edited form as:

J Biomed Mater Res A. 2010 June 15; 93(4): 1272–1279. doi:10.1002/jbm.a.32620.

***In vitro* electromagnetically stimulated SAOS-2 osteoblasts inside porous hydroxyapatite**

Lorenzo Fassina^{1,5}, Enrica Saino^{2,5}, Maria Sonia Sbarra^{2,5}, Livia Visai^{2,5}, Maria Gabriella Cusella De Angelis^{3,5}, Giovanni Magenes^{1,5}, and Francesco Benazzo^{4,5}

¹Dipartimento di Informatica e Sistemistica, University of Pavia, Pavia, Italy

²Dipartimento di Biochimica, University of Pavia, Pavia, Italy

³Dipartimento di Medicina Sperimentale, University of Pavia, Pavia, Italy

⁴Dipartimento SMEC, IRCCS San Matteo, University of Pavia, Pavia, Italy

⁵Centre for Tissue Engineering (C.I.T., <http://cit.unipv.it/cit>), University of Pavia, Pavia, Italy

Abstract

One of the key challenges in reconstructive bone surgery is to provide living constructs that possess the ability to integrate in the surrounding tissue. Bone graft substitutes, such as autografts, allografts, xenografts, and biomaterials have been widely used to heal critical-size long bone defects due to trauma, tumor resection, congenital deformity, and tissue degeneration. In particular, porous hydroxyapatite is widely used in reconstructive bone surgery owing to its biocompatibility. In addition, the *in vitro* modification of hydroxyapatite with osteogenic signals enhances the tissue regeneration *in vivo*, suggesting that the biomaterial modification could play an important role in tissue engineering.

In this study we have followed a biomimetic strategy where electromagnetically stimulated SAOS-2 human osteoblasts proliferated and built their extracellular matrix inside a porous hydroxyapatite scaffold. The electromagnetic stimulus had the following parameters: intensity of the magnetic field equal to 2 mT, amplitude of the induced electric tension equal to 5 mV, frequency of 75 Hz, and pulse duration of 1.3 ms.

In comparison with control conditions, the electromagnetic stimulus increased the cell proliferation and the surface coating with bone proteins (decorin, osteocalcin, osteopontin, type-I collagen, and type-III collagen).

The physical stimulus aimed at obtaining a better modification of the biomaterial internal surface in terms of cell colonization and coating with bone matrix.

Keywords

hydroxyapatite; electromagnetic stimulation; osteoblast; cell proliferation; bone extracellular matrix; decorin; osteocalcin; osteopontin; type-I collagen; type-III collagen; surface modification; biomimetics

Introduction

One of the key challenges in reconstructive bone surgery is to provide living constructs that possess the ability to integrate in the surrounding tissue. Bone graft substitutes, such as autografts, allografts, xenografts, and biomaterials have been widely used to heal critical-size long bone defects and maxillofacial skeleton defects due to trauma, tumor resection, congenital deformity, and tissue degeneration.

The biomaterials used to build 3D scaffolds for bone tissue engineering are, for instance, the hydroxyapatite,¹ the partially demineralized bone,² and biodegradable porous polymer-ceramic matrices.³

The preceding osteoinductive and osteoconductive biomaterials are ideal in order to follow a typical approach of the tissue engineering, an approach that involves the seeding and the *in vitro* culturing of cells within a porous scaffold before the implantation.

The tissue-engineering method is of great importance. In order to overcome the drawbacks associated with the standard culture systems, such as limited diffusion and inhomogeneous cell-matrix distribution, several bioreactors have been designed: for instance, a rotating vessel, where culture medium and biomaterials are moved by the bioreactor's structure,⁴ a perfusion system, where perfused medium flows through motionless scaffolds,⁵ or an electromagnetic bioreactor, where an electromagnetic wave passes through still medium and immobile biomaterials.⁶ The preceding devices satisfy features of an ideal bioreactor, such as i) supplying of suitable levels of oxygen, nutrients, cytokines, and growth factors, and ii) providing appropriate physical stimuli (e.g. shear stress⁵ or electromagnetic field⁶). The above features could aim at populating, with living bone cells and mineralized extracellular matrix, the volume of a porous biomaterial for reconstructive bone surgery: this living and biocompatible tissue-engineering construct could be implanted together with the insertion of a vascular pedicle.⁷

Gorna and Gogolewski^{8,9} have drawn attention to the ideal features of a bone graft substitute: it should be porous with interconnected pores of adequate size allowing for the ingrowth of capillaries and perivascular tissues; it should attract mesenchymal stem cells from the surrounding bone and promote their differentiation into osteoblasts; it should avoid shear forces at the interface between bone and bone graft substitute; and it should be biodegradable.

In this study, following the preceding "golden rules" of Gorna and Gogolewski, we have elected porous hydroxyapatite¹⁰⁻¹² as cancellous bone graft substitute and, using an electromagnetic bioreactor,⁶ we have attempted to populate it with extracellular matrix and osteoblasts, of which cell function can be electromagnetically modulated.⁶

Hydroxyapatite is widely used in reconstructive bone surgery owing to its biocompatibility. The *in vitro* modification of porous hydroxyapatite, with osteogenic signals of the transforming growth factor- β superfamily and with bone morphogenetic proteins, enhances the tissue regeneration *in vivo*,¹³ suggesting that the modification of hydroxyapatite could play an important role in tissue engineering.

As consequence, aiming, in a future work, at accelerated and enhanced bone regeneration *in vivo*, in the present study of tissue engineering, we show a particular "biomimetic strategy" that consists in the *in vitro* modification of porous hydroxyapatite with proliferated osteoblasts and their extracellular matrix produced *in situ*. In other words, applying an electromagnetic wave,⁶ our aim was to coat the hydroxyapatite internal surface with physiological and biocompatible cell-matrix layers. Using this approach, the *in vitro*

cultured material could be theoretically used, in clinical applications, as an osteointegrable implant.

Materials and Methods

Hydroxyapatite disks

Porous Orthoss® bovine hydroxyapatite disks (diameter, 8 mm; height, 4 mm) were kindly provided by Geistlich Pharma AG (Wolhusen, Switzerland).¹⁰⁻¹² The biomaterial had the following characteristics: internal surface density of 97 m²/g, average porosity equal to 60%, crystal dimensions of 10÷60 nm, and Ca/P ratio equal to 2.03, as in normal human cancellous bone.

Cells

The human osteosarcoma cell line SAOS-2 was obtained from the American Type Culture Collection (HTB85, ATCC, Rockville, MD). The cells were cultured in McCoy's 5A modified medium with L-glutamine and HEPES (Cambrex Bio Science Baltimore, Inc., Baltimore, MD), supplemented with 15% fetal bovine serum, 2% sodium pyruvate, 1% antibiotics, 10⁻⁸ M dexamethasone, and 10 mM β-glycerophosphate (Sigma-Aldrich, Inc., Milwaukee, WI). Ascorbic acid, another osteogenic supplement, is a component of McCoy's 5A modified medium. The cells were cultured at 37°C with 5% CO₂, routinely trypsinized after confluency, counted, and seeded onto the hydroxyapatite disks.

Cell seeding

In order to anchor the hydroxyapatite disks to two standard well-plates, 3% (w/v) agarose solution was prepared and sterilized in autoclave, and during cooling, at 45°C, 100 µl of agarose solution were poured inside the wells to hold the placed hydroxyapatite disks and to fix them after completed cooling.

The well-plates with the biomaterial disks were sterilized by ethylene oxide at 38°C for 8 h at 65% relative humidity. After 24 h of aeration in order to remove the residual ethylene oxide, the disks were ready inside the two culture systems: the "static", that is, the well-plate far from the electromagnetic bioreactor and the "electromagnetic", that is, the well-plate inside the electromagnetic bioreactor.

A cell suspension of 10×10⁶ cells in 400 µl was added onto the top of each disk and, after 0.5 h, 600 µl of culture medium was added to cover the disks. Cells were allowed to attach overnight, then the electromagnetic stimulus was turned on inside a dedicated incubator, whereas the static culture continued in a distinct incubator apart from the electromagnetic signal.

Electromagnetic bioreactor

The electromagnetic bioreactor⁶ consisted of a carrying structure custom-machined in a tube of polymethylmethacrylate: the windowed tube carried a well-plate and two solenoids, the planes of which were parallel (Fig. 1, left panel). In this experimental setup the magnetic field and the induced electric field were perpendicular and parallel to the disks top, respectively. The top of the disks were 5 cm distant from each solenoid plane, and the solenoids were powered by a Biostim SPT pulse generator (Igea, Carpi, Italy).

Given the position of the solenoids and the characteristics of the pulse generator, the electromagnetic stimulus had the following parameters: intensity of the magnetic field equal to 2 ± 0.2 mT, amplitude of the induced electric tension equal to 5 ± 1 mV, frequency of 75 ± 2 Hz, and pulse duration of 1.3 ms (Fig. 1, right panel).

In vivo experiments demonstrated that a continuous exposure to a pulsed electromagnetic field, similar to that used in this study, stimulates the bone repair in the healing process of transcortical holes in adult horses.¹⁴

The electromagnetic bioreactor was placed into a standard cell culture incubator with an environment of 37°C and 5% CO₂. The electromagnetic culture was stimulated 24 h per day for a total of 22 days. The culture medium was changed on days 4, 7, 10, 13, 16, and 19.

Standard well-plate culture

The static culture was placed into an incubator, where the electromagnetic stimulation was not detectable. The duration of the static culture was 22 days and the culture medium was changed on days 4, 7, 10, 13, 16, and 19.

Scanning electron microscopy (SEM) analysis

At the end of the culture period, the disks were fixed with 2.5% (v/v) glutaraldehyde solution in 0.1 M Na-cacodylate buffer (pH=7.2) for 1 h at 4°C, washed with Na-cacodylate buffer, and then dehydrated at room temperature in a gradient ethanol series up to 100%. The samples were kept in 100% ethanol for 15 min, and then critical point-dried with CO₂. The specimens were mounted on aluminum stubs, sputter coated with gold (degree of purity equal to 99%), and then observed with a Leica Cambridge Stereoscan microscope (Leica Microsystems, Bensheim, Germany).

DNA content

At the end of the culture period, the cells were lysed by a freeze-thaw method in sterile deionized distilled water and the released DNA content was evaluated with a fluorometric method (PicoGreen, Molecular Probes, Eugene, OR). A DNA standard curve,⁶ obtained from a known amount of osteoblasts, was used to express the results as cell number per disk.

Set of rabbit polyclonal antisera

L.W. Fisher (<http://csdb.nidcr.nih.gov/csdb/antiserum.htm>, National Institutes of Health, National Institute of Dental and Craniofacial Research, Craniofacial and Skeletal Diseases Branch, Matrix Biochemistry Unit, Bethesda, MD) presented us, generously, with the following rabbit polyclonal antibody immunoglobulins G: anti-osteocalcin, anti-type-I collagen, anti-type-III collagen, anti-decorin, and anti-osteopontin (antiserum LF-32, LF-67, LF-71, LF-136, and LF-166, respectively).¹⁵

Set of purified proteins

Decorin,¹⁶ osteocalcin (immunoenzymatic assay kit, BT-480, Biomedical Technologies, Inc., Stoughton, MA), osteopontin (immunoenzymatic assay kit, 900-27, Assay Designs, Inc., Ann Arbor, MI), type-I collagen,¹⁷ and type-III collagen (Sigma-Aldrich).

Confocal microscopy

At the end of the culture period, the disks were fixed with 4% (w/v) paraformaldehyde solution in 0.1 M phosphate buffer (pH=7.4) for 8 h at room temperature and washed with PBS (137 mM NaCl, 2.7 mM KCl, 4.3 mM Na₂HPO₄, 1.4 mM KH₂PO₄, pH=7.4) three times for 15 min. The disks were then blocked by incubating with PAT (PBS containing 1% [w/v] bovine serum albumin and 0.02% [v/v] Tween 20) for 2 h at room temperature and washed.

L. Fisher's anti-decorin, anti-osteocalcin, anti-osteopontin, anti-type-I collagen, and anti-type-III collagen rabbit polyclonal antisera were used as primary antibody with a dilution

equal to 1:1000 in PAT. The incubation with the primary antibodies was performed overnight at 4°C, whereas the negative controls were based upon the incubation, overnight at 4°C, with PAT instead of the primary antibodies. The disks and the negative controls were washed and incubated with Alexa Fluor 488 goat anti-rabbit IgG (H+L) (Molecular Probes) with a dilution of 1:500 in PAT for 1 h at room temperature.

At the end of the incubation, the disks were washed in PBS, counterstained with Hoechst solution (2 µg/ml) to target the cellular nuclei, and then washed. The images were taken by blue excitation with a confocal microscope (TCS SPII, Leica Microsystems) equipped with a digital image capture system at 100× magnification.

Extraction of the extracellular matrix proteins from the cultured disks and enzyme-linked immunosorbent assay (ELISA)

At the end of the culture period, in order to evaluate the amount of the extracellular matrix constituents over the internal and external hydroxyapatite surface, the disks were washed extensively with sterile PBS (137 mM NaCl, 2.7 mM KCl, 4.3 mM Na₂HPO₄, 1.4 mM KH₂PO₄, pH=7.4) in order to remove the culture medium, and then incubated for 24 h at 37°C with 1 ml of sterile sample buffer (1.5 M Tris-HCl, 60% [w/v] sucrose, 0.8% [w/v] sodium dodecyl sulphate, pH=8.0). At the end of the incubation period, the sample buffer aliquots were removed, and then the disks were centrifuged at 4000 rpm for 15 min in order to collect the sample buffer entrapped into the pores.

The total protein concentration in the two culture systems was evaluated by the BCA Protein Assay Kit (Pierce Biotechnology, Inc., Rockford, IL). The total protein concentration was 862 ± 135 µg/ml in the static culture and 1640 ± 251 µg/ml in the electromagnetic culture ($p < 0.05$).

After matrix extraction, the disks were incubated, once again, for 24 h at 37°C with 1 ml of sterile sample buffer, and no protein content was detected.

Calibration curves to measure decorin, osteocalcin, osteopontin, type-I collagen, and type-III collagen were performed. Microtiter wells were coated with increasing concentrations of each purified protein, from 1 ng to 2 µg, in coating buffer (50 mM Na₂CO₃, pH=9.5) overnight at 4°C. Some of the wells were coated with bovine serum albumin (BSA) as a negative control. In order to measure the extracellular matrix amount of each protein by an ELISA, microtiter wells were coated, overnight at 4°C, with 100 µl of the extracted extracellular matrix (20 µg/ml in coating buffer). After three washes with PBST (PBS containing 0.1% [v/v] Tween 20), the wells were blocked by incubating with 200 µl of PBS containing 2% (w/v) BSA for 2 h at 22°C. The wells were subsequently incubated for 1.5 h at 22°C with 100 µl of the L. Fisher's anti-decorin, anti-osteocalcin, anti-osteopontin, anti-type-I collagen, and anti-type-III collagen rabbit polyclonal antisera (1:500 dilution in 1% BSA). After washing, the wells were incubated for 1 h at 22°C with 100 µl of HRP-conjugated goat anti-rabbit IgG (1:1000 dilution in 1% BSA).

The wells were finally incubated with 100 µl of development solution (phosphate-citrate buffer with *o*-phenylenediamine dihydrochloride substrate). The color reaction was stopped with 100 µl of 0.5 M H₂SO₄ and the absorbance values were measured at 490 nm with a microplate reader (Bio-Rad Laboratories, Inc., Hercules, CA). The amount of extracellular matrix constituents inside the disks is expressed as fg/(cell×disk).

Statistics

The disks number was 24 in each repeated experiment (12 disks in the control culture and 12 disks in the electromagnetic culture). The experiment was repeated 4 times. Results are

expressed as mean $\pm$ standard deviation. In order to compare the results between the two culture systems, one-way analysis of variance (ANOVA) with *post hoc* Bonferroni test was applied, electing a significance level of 0.05.

Results

The human SAOS-2 osteoblasts were seeded onto porous hydroxyapatite disks, and then cultured without or with an electromagnetic stimulus for 22 days. These culture methods permitted the study of the SAOS-2 cells as they modified the biomaterial through the proliferation and the coating with extracellular matrix. The cell-matrix distribution was compared between the two culture systems.

Microscope analysis

In comparison to static condition, SEM images revealed that, due to the electromagnetic stimulus, the osteoblasts proliferated and built their extracellular matrix over the available internal hydroxyapatite surface (Figs. 2 and 3). At the end of the culture period, statically cultured cells were few and, essentially, not surrounded by extracellular matrix, therefore wide biomaterial regions remained devoid of cell-matrix complexes (Fig. 2). In contrast, the physical stimulus caused a wide-ranging coat of the internal surface of the biomaterial: several osteoblasts proliferated and the biomaterial was tending to be hidden by cell-matrix layers (Fig. 3).

The immunolocalization of type-I collagen and the counterstaining of the cellular nuclei showed the stimulation effects in terms of higher cell proliferation and more intense building of the extracellular matrix (Figs. 4 and 5). The immunolocalization of decorin, osteocalcin, osteopontin, and type-III collagen revealed similar results (data not shown).

These observations were confirmed by the measure of the DNA content at the end of the culture period: in the static culture the cell number per disk grew to $45.5 \times 10^6 \pm 4.1 \times 10^4$ and in the electromagnetic culture to $73.0 \times 10^6 \pm 3.6 \times 10^4$ with $p < 0.05$.

Extracellular matrix extraction

In order to evaluate the amount of bone extracellular matrix inside the hydroxyapatite disks, an ELISA of the extracted matrix was performed: at the end of the culture period, in comparison with the static culture, the electromagnetic stimulation significantly increased the internal surface coating with decorin, osteocalcin, osteopontin, type-I collagen, and type-III collagen ($p < 0.05$) (Table 1).

Discussion

The aim of this study was the *in vitro* modification of a porous hydroxyapatite with extracellular matrix and osteoblasts to make the biomaterial more biocompatible for the bone repair *in vivo*.

A discussion about the concept of “biocompatibility” is necessary. When a biomaterial is implanted in a biological environment, a non-physiologic layer of adsorbed proteins mediates the interaction of the surrounding host cells with the material surface. The body interprets this protein layer as a foreign invader that is consequently walled off in an avascular and tough collagen sac. Therefore, the biomedical surfaces should be developed so that the host tissue can recognize them as “self”. Castner and Ratner think the “biocompatible surfaces” of the “biomaterials that heal” as the surfaces with the characters of a “clean, fresh wound”:18 these “self-surfaces” could obtain a physiological inflammatory reaction leading to normal healing. Along the path of Castner and Ratner,

under the hypothesis that an *in vitro* neo-formed bone matrix should be more “self” and more effective than naked hydroxyapatite, in this study we have followed a biomimetic strategy where the seeded osteoblasts built a biocompatible surface made of *in vitro* neo-formed bone matrix.¹⁹

To enhance the coating of the biomaterial internal surface, an electromagnetic wave was applied to the seeded biomaterial.^{6,19} The electromagnetic stimulus increased the cell proliferation around 1.6-fold; a similar result has been obtained with the same physical stimulation applied to SAOS-2 osteoblasts seeded onto a polymeric biomaterial.⁶ Furthermore, the electromagnetic field significantly enhanced the synthesis of type-I collagen, decorin, osteopontin, osteocalcin, and type-III collagen, which are fundamental constituents of the physiological bone matrix: in particular type-I collagen is the most important and abundant structural protein of the bone matrix; decorin is a proteoglycan considered a key regulator for the assembly and the function of many extracellular matrix proteins with a major role in the lateral growth of the collagen fibrils, delaying the lateral assembly on the surface of the fibrils; osteopontin is an extracellular glycosylated bone phosphoprotein secreted at the early stages of the osteogenesis before the onset of the mineralization, it binds calcium, it is likely to be involved in the regulation of the hydroxyapatite crystal growth, and, through specific interaction with the vitronectin receptor, it promotes the attachment of the cells to the matrix; osteocalcin is secreted after the onset of mineralization and it binds to bone minerals.

The preceding results could be explained with a signaling model. The electromagnetic stimulation raises the net Ca^{2+} flux in the osteoblast cytosol and the release of the intracellular Ca^{2+} .²⁰⁻²² According to Pavalko’s signaling model, the increase of the cytosolic Ca^{2+} concentration is the starting point of signaling pathways, which cause the secretion of prostaglandins enhancing the osteoblast proliferation, and which target specific bone matrix genes.²⁰

In this study the electromagnetic stimulus was a physical method to obtain the biomimetic modification of the material, whose internal surface was coated by osteoblasts and by a layer of neo-formed bone matrix. The use of a cell line showed the potential of the electromagnetic stimulation; nevertheless, appropriately tuning the parameters of the electromagnetic wave and the culture time, a better result could be obtained with autologous bone marrow stromal cells instead of SAOS-2 osteoblasts for total immunocompatibility with the patient.

In future work *in vivo*, we intend to compare naked hydroxyapatite with the extracellular matrix coated one, in order to assess, or not, the supposed advantages of our biomimetic strategy. If advantages will be shown, we could theorize that the cultured “self-surface” could be used fresh (i.e. rich in autologous cells and matrix) or after sterilization with ethylene oxide (i.e. rich only in autologous matrix as a simple, storable, tissue-engineering product for bone repair¹⁹).

Acknowledgments

The authors thank L.W. Fisher, K. Martin, S. Setti, R. Cadossi, A. Mortara, D. Picononi, and P. Vaghi. Hydroxyapatite disks were kindly provided by Geistlich Pharma (Wolhusen, Switzerland). The Biostim SPT pulse generator was a gift from Igea (Carpi, Italy). This work was supported by Fondazione Cariplo Grants (2004.1424/10.8485 and 2006.0581/10.8485) to F. B., by PRIN Grant (2006) from Italian Ministry of Education, University and Research to L. V., and by FIRB Grant (RBIP06FH7J) from Italian Ministry of Education, University and Research to M.G. C. De A..

References

1. Nishikawa M, Myoui A, Ohgushi H, Ikeuchi M, Tamai N, Yoshikawa H. Bone tissue engineering using novel interconnected porous hydroxyapatite ceramics combined with marrow mesenchymal cells: quantitative and three-dimensional image analysis. *Cell Transplant*. 2004; 13:367–376. [PubMed: 15468678]
2. Mauney JR, Blumberg J, Pirun M, Volloch V, Vunjak-Novakovic G, Kaplan DL. Osteogenic differentiation of human bone marrow stromal cells on partially demineralized bone scaffolds *in vitro*. *Tissue Eng*. 2004; 10:81–92. [PubMed: 15009933]
3. Devin JE, Attawia MA, Laurencin CT. Three-dimensional degradable porous polymer-ceramic matrices for use in bone repair. *J Biomater Sci Polym Ed*. 1996; 7:661–669. [PubMed: 8639475]
4. Botchwey EA, Pollack SR, Levine EM, Laurencin CT. Bone tissue engineering in a rotating bioreactor using a microcarrier matrix system. *J Biomed Mater Res*. 2001; 55:242–253. [PubMed: 11255176]
5. Fassina L, Visai L, Asti L, Benazzo F, Speziale P, Tanzi MC, Magenes G. Calcified matrix production by SAOS-2 cells inside a polyurethane porous scaffold, using a perfusion bioreactor. *Tissue Eng*. 2005; 11:685–700. [PubMed: 15998210]
6. Fassina L, Visai L, Benazzo F, Benedetti L, Calligaro A, De Angelis MG, Cusella, Farina A, Maliardi V, Magenes G. Effects of electromagnetic stimulation on calcified matrix production by SAOS-2 cells over a polyurethane porous scaffold. *Tissue Eng*. 2006; 12:1985–1999. [PubMed: 16889527]
7. Akita S, Tamai N, Myoui A, Nishikawa M, Kaito T, Takaoka K, Yoshikawa H. Capillary vessel network integration by inserting a vascular pedicle enhances bone formation in tissue-engineered bone using interconnected porous hydroxyapatite ceramics. *Tissue Eng*. 2004; 10:789–795. [PubMed: 15265296]
8. Gorna K, Gogolewski S. Biodegradable polyurethanes for implants. II. *In vitro* degradation and calcification of materials from poly(ϵ -caprolactone)-poly(ethylene oxide) diols and various chain extenders. *J Biomed Mater Res*. 2002; 60:592–606. [PubMed: 11948518]
9. Gorna K, Gogolewski S. Preparation, degradation, and calcification of bio-degradable polyurethane foams for bone graft substitutes. *J Biomed Mater Res*. 2003; 67:813–827.
10. Stephan EB, Jiang D, Lynch S, Bush P, Dziak R. Anorganic bovine bone supports osteoblastic cell attachment and proliferation. *J Periodontol*. 1999; 70:364–369. [PubMed: 10328646]
11. Cohen RE, Mullarky RH, Noble B, Comeau RL, Neiders ME. Phenotypic characterization of mononuclear cells following anorganic bovine bone implantation in rats. *J Periodontol*. 1994; 65:1008–1015. [PubMed: 7853123]
12. Artzi Z, Nemcovsky CE, Tal H. Efficacy of porous bovine bone mineral in various types of osseous deficiencies: clinical observations and literature review. *Int J Periodontics Restorative Dent*. 2001; 21:395–405.
13. Ripamonti U, Ferretti C, Heliotis M. Soluble and insoluble signals and the induction of bone formation: molecular therapeutics recapitulating development. *J Anat*. 2006; 209:447–468. [PubMed: 17005018]
14. Cane V, Botti P, Soana S. Pulsed magnetic fields improve osteoblast activity during the repair of an experimental osseous defect. *J Orthop Res*. 1993; 11:664–670. [PubMed: 8410466]
15. Fisher LW, Stubbs JT III, Young MF. Antisera and cDNA probes to human and certain animal model bone matrix noncollagenous proteins. *Acta Orthop Scand Suppl*. 1995; 266:61–65. [PubMed: 8553864]
16. Vogel KG, Evanko SP. Proteoglycans of fetal bovine tendon. *J Biol Chem*. 1987; 262:13607–13613. [PubMed: 3654632]
17. Rossi A, Zuccarello LV, Zanaboni G, Monzani E, Dyne KM, Cetta G, Tenni R. Type I collagen CNBr peptides: species and behavior in solution. *Biochemistry*. 1996; 35:6048–6057. [PubMed: 8634246]
18. Castner DG, Ratner BD. Biomedical surface science: Foundations to frontiers. *Surf Sci*. 2002; 500:28–60.

19. Fassina L, Visai L, De Angelis MG, Cusella, Benazzo F, Magenes G. Surface modification of a porous polyurethane through a culture of human osteoblasts and an electromagnetic bioreactor. *Technol Health Care*. 2007; 15:33–45. [PubMed: 17264411]
20. Pavalko FM, Norvell SM, Burr DB, Turner CH, Duncan RL, Bidwell JP. A model for mechanotransduction in bone cells: the load-bearing mechanosomes. *J Cell Biochem*. 2003; 88:104–112. [PubMed: 12461779]
21. Fitzsimmons RJ, Ryaby JT, Magee FP, Baylink DJ. Combined magnetic fields increased net calcium flux in bone cells. *Calcif Tissue Int*. 1994; 55:376–380. [PubMed: 7866919]
22. Li JK, Lin JC, Liu HC, Sun JS, Ruaan RC, Shih C, Chang WH. Comparison of ultrasound and electromagnetic field effects on osteoblast growth. *Ultrasound Med Biol*. 2006; 32:769–775. [PubMed: 16677936]

Fig. 1.

Electromagnetic bioreactor (left panel) and electromagnetic signal (right panel). The windowed tube carried a well-plate and two solenoids, the planes of which were parallel (left panel). The electromagnetic stimulus had the following parameters: intensity of the magnetic field equal to 2 ± 0.2 mT, amplitude of the induced electric tension equal to 5 ± 1 mV, frequency of 75 ± 2 Hz, and pulse duration of 1.3 ms (right panel).

Fig. 2. SEM images of the static culture, bar equal to 20 μm (left panel) and to 10 μm (right panel). The osteoblasts are in the “backscattered depressions” near the juxtaposed asterisks: at the end of the culture period, statically cultured cells were few and, essentially, not surrounded by extracellular matrix, therefore wide biomaterial regions remained devoid of cell-matrix complexes.

Fig. 3.

SEM images of the electromagnetic culture, bar equal to 30 µm (left panel) and to 10 µm (right panel). During the culture period, the physical stimulus caused a wide-ranging coat of the internal surface of the biomaterial: several osteoblasts proliferated and the biomaterial was tending to be hidden by cell-matrix layers (asterisks).

Fig. 4.

Immunolocalization of type-I collagen (left panel, green) and cellular nuclei (right panel, blue) in the static culture, bar equal to 80 μ m. During the culture period, the osteoblasts built a scanty amount of extracellular matrix. The immunolocalization of decorin, osteocalcin, osteopontin, and type-III collagen revealed similar results.

Fig. 5.

Immunolocalization of type-I collagen (left panel, green) and cellular nuclei (right panel, blue) in the electromagnetic culture, bar equal to 80 μm . During the culture period, the osteoblasts built a wide amount of extracellular matrix. The immunolocalization of decorin, osteocalcin, osteopontin, and type-III collagen revealed similar results.

Table. 1

Amount of extracellular matrix constituents inside hydroxyapatite.

	Matrix protein total coating after 22 days of culture in fg/(cell×disk)		
	Static culture	Electromagnetic culture	Electromagnetic/Static
Decorin	6.38 ± 0.12	13.28 ± 0.22	2.08-fold
Osteocalcin	1.47 ± 0.35	4.26 ± 0.37	2.89-fold
Osteopontin	1.23 ± 0.43	2.95 ± 0.53	2.39-fold
Type-I collagen	2.22 ± 0.54	14.76 ± 0.71	6.64-fold
Type-III collagen	3.47 ± 0.17	10.99 ± 0.65	3.16-fold

Table note: p<0.05 in all “Static” vs. “Electromagnetic” comparisons.