Published in final edited form as:

J Biomech. 2010 June 18; 43(9): 1835–1839. doi:10.1016/j.jbiomech.2010.02.023.

A fast quadrature-based numerical method for the continuous spectrum biphasic poroviscoelastic model of articular cartilage

Michael Stuebner and Mansoor A. Haider

Department of Mathematics, North Carolina State University, Box 8205, Raleigh, NC 27695-8205, USA

Abstract

A new and efficient method for numerical solution of the continuous spectrum biphasic poroviscoelastic (BPVE) model of articular cartilage is presented. Development of the method is based on a composite Gauss-Legendre quadrature approximation of the continuous spectrum relaxation function that leads to an exponential series representation. The separability property of the exponential terms in the series is exploited to develop a numerical scheme that can be reduced to an update rule requiring retention of the strain history at only the previous time step. The cost of the resulting temporal discretization scheme is $O(N)$ for N time steps. Application and calibration of the method is illustrated in the context of a finite difference solution of the one-dimensional confined compression BPVE stress-relaxation problem. Accuracy of the numerical method is demonstrated by comparison to a theoretical Laplace transform solution for a range of viscoelastic relaxation times that are representative of articular cartilage.

Keywords

collagen; proteoglycan; stress relaxation; discrete spectrum

1. INTRODUCTION

In modeling viscoelastic deformation of articular cartilage, the consideration of both flow-dependent and flow-independent dissipation mechanisms necessitates the use of a linear biphasic poroviscoelastic (BPVE) model (Mak, 1986). Intrinsic dissipation in cartilage extracellular matrix is represented using a constitutive law in which stress depends on the strain history via a hereditary integral with a continuous relaxation spectrum (Fung, 1993), and BPVE models have been used to analyze cartilage viscoelasticity in a variety of settings (Desmaris and Aissaoui, 2008; DiSilvestro and Suh, 2001, 2002; Setton et al., 1993). Direct solution of the BPVE governing equations can be costly due to the dependence of the current solution on the entire strain history. Commonly, a discrete spectrum approximation is used to approximate the continuous spectrum relaxation function. This technique has a key advantage in that the exponential terms in the discrete spectrum series are separable functions, leading to an update rule that requires retention of the strain history at only the previous time step. However, accurate

Corresponding author: Mansoor Haider, mhaider@ncsu.edu, tel: (919) 515-3100, fax: (919) 515-3798, Address: Department of Mathematics, Box 8205, North Carolina State University, Raleigh, NC 27695-8205.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

reproduction of the continuous spectrum relaxation function using an exponential series can be difficult to achieve and parameters in the representation can be non-unique (Fung, 1993).

An alternate approach is to use analytical properties of the continuous spectrum constitutive law to derive new approximations that can accelerate numerical solution of the BPVE model. In a prior study (Haider and Schugart, 2006), integration by parts was used to develop an alternate BPVE formulation with an error estimate that enabled retention of a fixed portion of the strain history without loss of accuracy. While exhibiting a significant cost reduction relative to direct solution of the continuous spectrum BPVE model, the cost was still much greater than discrete spectrum BPVE models. In this study, we present a new quadrature-based method for the BPVE model that has computational efficiency similar to BPVE models based on a discrete spectrum approximation while, simultaneously, exhibiting accuracy comparable to the continuous spectrum BPVE model.

2. METHODS

2.1 1D BPVE Model

We illustrate our numerical method in the context of a finite difference solution of the one-dimensional (1D) confined compression BPVE stress relaxation problem in the range of infinitesimal strain. In this case, an analytical Laplace transform solution is available for comparison (Mak, 1986). The 1D BPVE model can be reduced to:

$$\frac{1}{\kappa} \frac{\partial u}{\partial t} = \frac{\partial \sigma}{\partial z}, \quad 0 < z < h, \quad 0 < t < t_f, \quad (1)$$

where $u(z, t)$ is the axial (z) displacement, h is the cylindrical sample height. κ is the hydraulic permeability and t_f denotes the duration of the experiment. In (1) σ represents the axial normal stress, i.e. $\sigma = \sigma_{zz}$, and is viscoelastic:

$$\sigma(z, t) = H_A \int_{-\infty}^t G(t - \tau) \frac{\partial}{\partial \tau} \left(\frac{\partial u}{\partial z}(z, \tau) \right) d\tau, \quad (2)$$

where H_A is the “drained” aggregate modulus of the solid phase and $G(t)$ is the reduced relaxation function (Fung, 1993). For articular cartilage, as well as many other soft tissues, a continuous spectrum relaxation function is employed: (Fung, 1993; Neubert, 1963):

$$G(t) = 1 + c \int_{\tau_1}^{\tau_2} \frac{e^{-\frac{t}{s}}}{s} ds. \quad (3)$$

Typically, the relaxation times τ_1 and τ_2 in (3) are separated by several orders of magnitude.

2.2 Discrete spectrum approximation and separability

The computational cost for direct temporal discretization of (1–3) with N time steps is $O(N^2)$, due to the history dependence in the viscoelastic constitutive law (2). The discrete spectrum approximation of (3) is written as:

$$G(t) \approx G^{DS}(t) \equiv G_\infty + \sum_{i=0}^{N_{DS}} G_i K_i^{DS}(t), \quad \text{where: } K_i^{DS}(t) = e^{-\frac{t}{\tau_i}}, i=0, \dots, N_{DS}. \quad (4)$$

In (4), G_i are discrete moduli, v_i are discrete relaxation times and $G_\infty = 1$. For this approximate BPVE model, nonuniqueness in the representation (4) can be addressed by assuming that

$G_i = \bar{G} \equiv \frac{G_0 - 1}{N_{DS} + 1}$, where $G_0 = G_{DS}(0) = G_\infty + \sum_{i=0}^{N_{DS}} G_i$, and by assigning v_i with values that are equally distributed, on a logarithmic scale, in the interval between τ_1 and τ_2 (Suh and Bai, 1998). The result is an approximate model (4) that has the same number of parameters as the continuous spectrum model (3), but with a significant loss in accuracy. Numerical solutions of (1–2), in which (3) has been approximated by (4), have the separability property, i.e.

$K_i^{DS}(t+r) = e^{-\frac{r}{v_i}} K_i^{DS}(t)$. Specifically, in a time-marching scheme with time step Δt , it follows from (4) that:

$$G^{DS}(t+\Delta t) \equiv G_\infty + \sum_{i=0}^{N_{DS}} G_i K_i^{DS}(t+\Delta t) = G_\infty + \sum_{i=0}^{N_{DS}} G_i e^{-\frac{\Delta t}{v_i}} K_i^{DS}(t), \quad (5)$$

thus yielding an update rule for the relaxation function that can be exploited to reduce cost for numerical solution of (1) from $O(N^2)$ to $O(N)$ in time (see, e.g., Suh and Bai (1998)).

2.3 A new quadrature-based formulation

A disadvantage of the approximation (4) is that accuracy in representation of (3) is difficult to achieve without the introduction of a significant number of additional parameters. We now demonstrate that the integral in (3) can also be represented via an exponential series based on Gauss-Legendre quadrature, and also has the separability property described in §2.2. Consider an equal partition, in the logarithmic sense, of the interval $[\tau_1, \tau_2]$ with $N_{int} + 1$ partition points

$\{s_j\}_{j=0}^{N_{int}}$ given by $s_j = \tau_1^{1-\frac{j}{N_{int}}} \tau_2^{\frac{j}{N_{int}}}$ ($j = 0, \dots, N_{int}$). Denote the length of the j th subinterval by l_j .

On the j th sub-interval $[s_{j-1}, s_j]$ ($j = 1, \dots, N_{int}$), introduce N_Q points $s_{jk} = s_{j-1} + \frac{l_j}{2}(\xi_k + 1)$, ($k = 1, \dots, N_Q$), where ξ_k correspond to the abscissas for N_Q -point Gauss-Legendre quadrature on the standard interval $\zeta \in [-1, 1]$, with corresponding weights w_k . Based on these definitions, the composite Gauss-Legendre quadrature approximation of the continuous spectrum relaxation function in (3) is:

$$G(t) = 1 + c \int_{\tau_1}^{\tau_2} \frac{e^{-\frac{t}{s}}}{s} ds \approx G^Q(t) \equiv 1 + c \sum_{j=1}^{N_{int}} \frac{l_j}{2} \sum_{k=1}^{N_Q} \frac{w_k}{s_{jk}} K_{jk}^Q(t) \quad \text{where: } K_{jk}^Q(t) = e^{-\frac{t}{s_{jk}}}. \quad (6)$$

Since (6) is an exponential series, the separability property of $K_{jk}^Q(t)$, i.e.

$K_{jk}^Q(t+r) = e^{-\frac{r}{s_{jk}}} K_{jk}^Q(t)$, can be used to write:

$$G^Q(t+\Delta t) \equiv 1 + c \sum_{j=1}^{N_{int}} \frac{l_j}{2} \sum_{k=1}^{N_Q} \frac{w_k}{s_{jk}} K_{jk}^Q(t+\Delta t) = 1 + c \sum_{j=1}^{N_{int}} \frac{l_j}{2} \sum_{k=1}^{N_Q} \frac{w_k}{s_{jk}} e^{-\frac{\Delta t}{s_{jk}}} K_{jk}^Q(t). \quad (7)$$

Equation (7) provides an update rule that can be used to develop a numerical solution of (1) that is $O(N)$ in time in that it requires retention of the strain history at only the previous time step. The primary advantage of our new formulation is that it derives an exponential series approximation of the continuous spectrum relaxation function (3) via Gauss-Legendre quadrature, thus increasing the potential for maximizing accuracy while, simultaneously, minimizing computational cost.

2.4 Discretization and Implementation

The temporal discretization scheme described in §2.3 is developed in the case where the governing equations are nondimensionalized by taking h as the unit of length, the biphasic gel relaxation time $\frac{h^2}{\kappa H_A}$ (Mow et al., 1980) as the unit of time, and H_A as the unit of stress. Assuming no external loading for $t < 0$, and letting $v = \frac{\partial u}{\partial t}$, the governing equations (1–2) are approximated, using our quadrature based relaxation function (6), as:

$$v(z, t) = \int_0^t G^Q(t - \tau) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau, \quad 0 < z < 1, \quad 0 < t < \frac{\kappa H_A}{h^2} t_f. \quad (8)$$

Introduce $z_m = m\Delta z$, $m = 0 \dots M$, where $\Delta z = 1/M$ and $t_n = n\Delta t$, $n = 0 \dots N$, where $\Delta t = \frac{\kappa H_A}{h^2} \frac{t_f}{N}$, and let $v_m^n \equiv v(z_m, t_n)$. Using (6) in (8), the solution after one time step is:

$$v_m^1 = \int_0^{\Delta t} \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau + c \sum_{j=1}^{N_{int}} \sum_{k=1}^{N_Q} I_{jk}(z, \Delta t), \quad \text{where: } I_{jk}(z, t) \equiv \int_0^t \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(t - \tau) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau \quad (9)$$

For later times ($n = 1, 2, \dots, N$), we write:

$$v_m^{n+1} = \int_0^{(n+1)\Delta t} \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau + c \sum_{j=1}^{N_{int}} \sum_{k=1}^{N_Q} I_{jk}(z, (n+1)\Delta t). \quad (10)$$

Due to the separability property of $K_{jk}^Q(t)$, we can derive the following update rule ($n = 1, 2, \dots, N$):

$$\begin{aligned} I_{jk}(z, (n+1)\Delta t) &= \int_0^{(n+1)\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q((n+1)\Delta t - \tau) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau \\ &= \int_0^{n\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(n\Delta t - \tau + \Delta t) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau + \int_{n\Delta t}^{(n+1)\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(n\Delta t - \tau + \Delta t) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau \\ &= e^{-\frac{\Delta t}{s_{jk}}} \int_0^{n\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(n\Delta t - \tau) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau + \int_{n\Delta t}^{(n+1)\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(n\Delta t - \tau + \Delta t) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau. \end{aligned} \quad (11)$$

Using the definition of $I_{jk}(z, t)$ from (9) in (11), we obtain:

$$I_{jk}(z, (n+1)\Delta t) = e^{-\frac{\Delta t}{s_{jk}}} I_{jk}(z, n\Delta t) + \int_{n\Delta t}^{(n+1)\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(n\Delta t - \tau + \Delta t) \frac{\partial^2 v}{\partial z^2}(z, \tau) d\tau.$$

Via the transformation $\tilde{\tau} = \tau - n\Delta t$, the integral in the last expression can be transformed to yield the following update rule ($n = 1, 2, \dots, N$):

$$I_{jk}(z, (n+1)\Delta t) = e^{-\frac{\Delta t}{s_{jk}}} I_{jk}(z, n\Delta t) + \int_0^{\Delta t} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(\Delta t - \tilde{\tau}) \frac{\partial^2 v}{\partial z^2}(z, n\Delta t + \tilde{\tau}) d\tilde{\tau}, \quad (12)$$

which requires retention of the strain history at only the previous time step.

Based on this new approach to temporal discretization, we obtain a numerical scheme that is $O(N)$ with respect to time and consists of equations (9–10) and (12). The scheme is complete once a spatial operator (e.g. based on finite differences or finite elements) is chosen for approximating $\frac{\partial^2 v}{\partial z^2}$, an integration rule is chosen for approximating the time integrals, and initial and boundary conditions are prescribed. In our implementation, (second order) central finite differences were used in space and the trapezoidal rule was used for time integration. The resulting scheme leads to a tridiagonal linear system for rapid solution of v_m^n , $m = 1, \dots, M$ at each time step n . Displacements u_m^n are recovered from velocities v_m^n via the update rule $u_m^n = u_m^{n-1} + \frac{1}{2}(v_m^n + v_m^{n-1})\Delta t$, $n = 1, \dots, N$.

3. RESULTS

Viscoelastic relaxation times in (3) were considered for the cases $\tau_1 = 0.01, 0.1, 1.0$ s and $\tau_2 = 10, 100, 200$ s with $c = 1$. Based on mean parameter values from DiSilvestro and Suh (2001), material and geometric parameters were set as $H_A = 1.29$ MPa, $\kappa = 1.72 \times 10^{-15}$ m⁴/(Ns) and $h = 1.28$ mm. In their study, mean values of short- and long-term relaxation times in $G^{DS}(t)$ were reported as 0.62s and 85.1s, respectively.

For a particular strain history, it is evident that accuracy of our numerical scheme (9–10) and (12) depends on the following error measure:

$$E(t) \equiv |G^Q(t) - G(t)| = c \left| \sum_{j=1}^{N_{int}} \sum_{k=1}^{N_Q} \frac{l_j}{2} \frac{w_k}{s_{jk}} K_{jk}^Q(t) d\tau - \int_{\tau_1}^{\tau_2} \frac{e^{-\frac{t}{s}}}{s} ds \right|, \text{ for } t \in [0, \Delta t]. \quad (13)$$

Given Δt , $G(t)$ can be readily evaluated in terms of exponential integral functions on the domain $[0, \Delta t]$ for the nine cases considered, as demonstrated (in physical units) for the case $\Delta t = 0.25$ s (Fig. 1). Values of $G(t)$ are then employed in $E(t)$ (13) to calibrate choices of N_{int} and N_Q for a given set of material and geometric parameters. We illustrate the process of calibrating N_{int} for the case $N_Q = 2$ when $t_f = 3600$ s and $\Delta t = 0.25$ s in Figure 2 for the cases with the largest ($\tau_1 = 0.01$ s, $\tau_2 = 200$ s) and smallest ($\tau_1 = 1.0$ s, $\tau_2 = 10$ s) errors. In the former case, with $N_{int} = 10$, $E(t)$ ranged between 0.019 and 0.039 while $G(t)$ varied between 7.11 and 10.81 for a relative error of less than 0.55%. Similarly, in the latter case, with $N_{int} = 10$, $E(t)$ ranged between $2.15 \cdot 10^{-5}$ and $3.54 \cdot 10^{-5}$ while $G(t)$ varied between 3.09 and 3.30 for a relative error of less than 0.0011%.

The quadrature-based numerical method (9–10) and (12) was used to simulate the 1D confined compression stress relaxation problem (1–3) with a no-flux boundary condition ($z = h$) and a free-draining boundary ($z = 0$). A ramp-and-hold displacement was prescribed as $u(0, t) = v_0 t$ for $0 < t < t_0$ and $u(0, t) = v_0 t_0$ for $t_0 < t \leq t_f$ with $v_0 = h/10$ and $t_f = 3600$ s. Numerical parameters were taken as $M = 40$, $N_Q = 2$ and $\Delta t = 0.25$ s, representing a total of 14,400 time steps over the duration of the experiment. To assess accuracy, the number of quadrature intervals was varied as $N_{int} = 2, 5, 10$. Prior to implementation, the governing equations were nondimensionalized, as described in §2.4. The numerical scheme was implemented in C++ and all computations were performed on a dual-2.8 GHz Quad Core Intel Xeon equipped Macintosh Pro computer.

Accuracy of the new scheme was assessed by comparison to a theoretical Laplace transform solution (Mak, 1986-Eqs. (24–25)). Numerical inversion of Laplace transform representations was performed using a MATLAB implementation (Hollenbeck, 1998) of deHoog's algorithm

(deHoog et al., 1982). In all cases, accuracy of computed displacements in the layer was excellent with $N_{int} = 5$, and two representative cases are shown in Figure 3. In general, accuracy of the numerical scheme improved as the difference between τ_1 and τ_2 decreased. Based on the displacement solution, a four-point finite difference approximation to the surface stress was also computed and compared with the theoretical solution. Stress responses were sensitive to τ_2 and two representative cases are shown in Figure 4. Accuracy of the numerical scheme was very good in the case $N_{int} = 5$ and excellent as N_{int} was increased to 10. For all cases considered in this study, numerical solutions on the domain $[0s, 3600s]$ were obtained in less than one second.

4. DISCUSSION

A new numerical method for the BPVE model of articular cartilage was developed based on a composite Gauss-Legendre quadrature approximation of the continuous spectrum relaxation function. The quadrature representation consists of a series of exponential terms and their separability property was exploited to develop a time discretization resulting in an update rule requiring retention of strain history at only the previous time step. This technique provides an alternate approach to approximating the continuous spectrum relaxation function using an exponential series that significantly enhances accuracy while minimizing computational cost. The method assigns coefficients and relaxation times in the exponential series based on the partition, abscissas and weights in the composite quadrature. For each case considered, accurate results were obtained in less than one second with the derived update rule yielding a computational cost proportional to $N = 14,400$ time steps (i.e. when $t_f = 3600s$, $\Delta t = 0.25s$). In contrast, the cost for direct solution of the full continuous spectrum numerical solution would be proportional to $N(N+1)/2 \approx 1 \cdot 10^8$ time steps.

The numerical method presented in this study will aid applications where material parameters in a BPVE cartilage model have fixed values or ranges, allowing for calibration of the quadrature technique to achieve the desired accuracy. While accuracy was demonstrated in the context of the 1D BPVE confined compression stress relaxation problem, all key aspects of the new method relate to the temporal discretization of the governing equations. The technique outlined in §2.3 is independent of the numerical method used for spatial discretization and can be extended to nonlinear strains. Consequently, we believe that our new quadrature-based temporal approximation scheme can significantly improve the accuracy and efficiency of finite element methods for the BPVE model of articular cartilage and such techniques will be considered in future studies by our group.

Acknowledgments

This work has been supported by funding from the National Science Foundation (DMS-0636590) and the National Institutes of Health (AG15768).

References

1. Desmarais M, Aissaoui R. Modeling of knee articular cartilage dissipation during gait analysis. *Journal of Mechanics in Medicine and Biology* 2008;8:377–394.
2. deHoog FR, Knight JH, Stokes AN. An improved method for numerical inversion of Laplace transforms. *SIAM Journal of Scientific and Statistical Computing* 1982;3:357–366.
3. DiSilvestro MR, Suh JK. Cross-validation study of the biphasic poroviscoelastic model of articular cartilage in unconfined compression, indentation and confined compression. *Journal of Biomechanics* 2001;34:519–525. [PubMed: 11266676]
4. DiSilvestro MR, Suh JK. Biphasic poroviscoelastic characteristics of proteoglycan-depleted articular cartilage: simulation and degeneration. *Annals of Biomedical Engineering* 2002;30:792–800. [PubMed: 12220079]

5. Fung, YC. Biomechanics: Mechanical Properties of Living Tissues. 2. Springer; New York: 1993.
6. Haider MA, Schugart RC. A numerical method for the continuous spectrum biphasic poroviscoelastic model of articular cartilage. *Journal of Biomechanics* 2006;39:177–183. [PubMed: 16271602]
7. Hollenbeck, KH. INVLAP.M: A matlab function for numerical inversion of Laplace transforms by the de Hoog algorithm. 1998. <http://www.mathtools.net/files/net/invlap.zip>
8. Mak AK. The apparent viscoelastic behavior of articular cartilage-the contributions from the intrinsic matrix viscoelasticity and interstitial fluid flows. *Journal of Biomechanical Engineering* 1986;108:123–130. [PubMed: 3724099]
9. Mow VC, Kuei SC, Lai WM, Armstrong CG. Biphasic creep and stress relaxation of articular cartilage in compression: theory and experiments. *Journal of Biomechanical Engineering* 1980;102:73–84. [PubMed: 7382457]
10. Neubert HKP. A simple model representing internal damping in solid materials. *Aeronautical Quarterly* 1963;14:187–197.
11. Setton LA, Zhu W, Mow VC. The biphasic poroviscoelastic behavior of articular cartilage: role of the surface zone in governing the compressive behavior. *Journal of Biomechanics* 1993;26:581–592. [PubMed: 8478359]
12. Suh JK, Bai S. Finite element formulation of biphasic poroviscoelastic model for articular cartilage. *Journal of Biomechanical Engineering* 1998;120:195–210. [PubMed: 10412380]

Figure 1.

The reduced relaxation function $G(t)$ shown on the domain $[0, \Delta t]$ of the error measure $E(t)$ in (13) for the nine cases considered: (a) $\tau_1 = 0.01s$, (b) $\tau_1 = 0.1s$, (c) $\tau_1 = 1s$.

Figure 2.

Illustration of error measure $E(t)$ in (13) for calibration of the number of quadrature intervals N_{int} . For the range of material parameters considered, the best case $\tau_1 = 1.0s$, $\tau_2 = 10s$ (solid) and the worst case $\tau_1 = 0.01s$, $\tau_2 = 200s$ (dashed) are shown. Numbers on curves indicate the value of N_{int} for each case considered.

Figure 3.

Illustration of accuracy for displacement computations using the quadrature-based BPVE numerical method. The numerical solution in cases $N_{int} = 2$ (dashed) and $N_{int} = 5$ (solid) are compared to the theoretical solution (circles) at depths $z/h = 0.2, 0.4, 0.6, 0.8$ [top to bottom] in the cases: (a) $\tau_1 = 0.01s, \tau_2 = 200s$ and (b) $\tau_1 = 0.1s, \tau_2 = 200s$.

Figure 4. Illustration of accuracy for surface stress computations using the quadrature-based BPVE numerical method. The numerical solution in cases $N_{int} = 2, 5, 10$ are compared to the theoretical solution (circles) in the cases: (a) $\tau_1 = 0.01s$, $\tau_2 = 200s$ and (b) $\tau_1 = 0.1s$, $\tau_2 = 100s$.