Published in final edited form as:

Soft Matter. 2010 January 1; 6(7): 1419–1425. doi:10.1039/b919581e.

Curvature-driven molecular demixing in the budding and breakup of mixed component Worm-like Micelles

Sharon M. Loverde^{a,b,d,f}, Vanessa Ortiz^c, Randall D. Kamien^{d,e}, Michael L. Klein^{a,f}, and Dennis E. Discher^{b,e}

^aDepartment of Chemistry, 231 S. 34th Street #218, University of Pennsylvania, Philadelphia, PA, 19104; Tel: 215 573 0990; sloverde@seas.upenn.edu

^bDepartment of Chemical and Biomolecular Engineering, University of Pennsylvania, Philadelphia, PA, 19104. discher@seas.upenn.edu

^cDepartment of Chemical and Biological Engineering, University of Wisconsin, Madison, 2014 Engineering Hall, 1415 Engineering Drive, Madison, WI 53706-1691

^dDepartment of Physics and Astronomy, University of Pennsylvania

^eLaboratory for Research on the Structure of Matter, University of Pennsylvania

^fDepartment of Chemistry, Temple University, Philadelphia, PA, 19122

Abstract

Amphiphilic block copolymers of suitable proportions can self-assemble into surprisingly long and stable worm-like micelles, but the intrinsic polydispersity of polymers as well as polymer blending efforts and the increasing use of degradable chains all raise basic questions of curvature-composition coupling and morphological stability of these high curvature assemblies. Molecular simulations here of polyethylene glycol (PEG) based systems show that a systematic increase in the hydrated PEG fraction, in both monodisperse and binary blends, induces budding and breakup into spherical and novel ‘dumbbell’ micelles – as seen in electron microscopy images of degradable worm-like micelles. Core dimension, d , in our large-scale, long-time dissipative particle dynamics (DPD) simulations is shown to scale with chain length, N , as predicted theoretically by the Strong Segregation Limit ($d \sim N^{2/3}$), but morphological transitions of binary mixtures are only crudely predicted by simple mixture rules. Here we show that for weakly demixing diblock copolymers, the coupling between local interfacial concentration and mean curvature can be described with a simple linear relationship. The computational methods developed here for PEG-based assemblies should be useful for many high curvature nanosystems.

Introduction

The worm-like micelle is a classic ‘one-dimensional’ self assembly, but compared to vesicles or spherical micelles that can also assemble from amphiphiles, worm-like micelles are less stable to perturbations. While assembly of amphiphiles in water invariably minimizes solvent-phobic contacts in the core of the micelle and maximizes solvent-philic contacts within the corona, the vesicle/worm/sphere morphologies are typically understood at a first level in terms of a packing parameter $p = v/al_c$ that is determined by molecular

volume v of the packed hydrophobic segment, contour length l_c of the hydrophobic segment ($l_c \geq d/2$), and interfacial area a of the hydrophilic segment¹. The range of p allowable for a given morphology is then calculated from core volume and interfacial area [eg. sphere:

$$p = (\pi/6 d^3) (\pi d^2 l_c)^{-1} = 0 - 1/3], \text{ and the cylinder-shaped worm-like micelle proves by such}$$

determinations to have a 2–3 fold narrower range of $p (= 1/3 - 1/2)$ compared to either

spherical micelles or vesicle bilayers ($p = 1/2 - 1$). Despite the implied susceptibility to transitions of worm-like micelles, their unique elongated shape is increasingly being exploited in application. Worms made from low molecular weight surfactants have served as templates for inorganic frameworks² and as additives in oil recovery fluids². Polymer-based worm micelles have taken advantage of the increased stability that arises from increasing the hydrophobic contacts with novel applications in nano-electronics and drug delivery^{4,5,6,7,8}. Morphological transitions sometimes facilitate application and generally motivate deeper insight.

Degradable polymers provide one means to control morphological transitions, but degradation reactions generally add complexity. Micelles and vesicles⁸ have been made from the hydrophobic and hydrolysable polyesters poly(caprolactone) (PCL)[†] and poly(lactic acid) (PLA) as well as redox-sensitive chains such as poly(propylenesulfide) (PPS)⁹ in tandem with hydrophilic polyethylene glycol (PEG) (equivalent to PEO, polyethylene oxide). Worm-like micelles of such block copolymers appear surprisingly useful in their ability to reptate through the blood stream and permeate tumor tissues to target anticancer drugs¹⁰. Fragmentation into spherical micelles seems to be part of the mechanism with the hydrophobic chains degrading into heterogeneous mixtures, raising fundamental questions about copolymer dispersity and micellar stability.

Here we refine and extend mesoscopic Dissipative Particle Dynamics^{11,12} (DPD) methods that are suited to long time-scales (up to msec) and long polymer chains (>kDa), and we show that the parallelized DPD techniques provide an accurate means to assess both structures and transitions of polymer-based assemblies. DPD is already known to accurately capture the properties of short chain self-assemblies^{13,14} and polymer solutions¹⁴. However, DPD can also exploit parameterizations from coarse-grained molecular dynamics (CG-MD) of diblock copolymers that not only fit all-atom models but also accurately predict structures and properties of these versatile soft materials^{15,16,17,18}. Simulations here reveal the dynamic breakup of a worm-like micelle as the packing parameter is effectively decreased in both homogeneous and heterogeneous assemblies. In the latter, we test a common assumption of component additivity and then elaborate the coupling of curvature to component concentration. While such processes have been explored to some extent for a few assemblies of lipids^{19,20,21,22} or peptides²³, polymers and worm-like micelles display complex phase behavior with component polydispersity²⁴. The simulations here probe general issues underlying the non-ergodic behavior of polymer nano-assemblies: diffusional timescales for lateral segregation within an assembly, and the coupled interplay of composition and curvature in micellar assemblies.

[†]For a degradable polymer like PCL, the degradation product after hydrolysis, 6-Hydroxycaproic acid, (6-HPA) is water soluble and diffuses away over experimental timescales. From separate atomistic simulations, we estimate $\chi_{\text{PEO-PCL}} = 0.146$, which corresponds to a relative interfacial tension between PEO and PCL of 2.7 mN/m, assuming a strongly segregated interface. This is a factor of ten smaller than the 30 mN/m interfacial tension measured experimentally for PEO-PEE bilayers³⁹, which implies a comparably larger interfacial width w .

Computational Methods

The parallelized simulation code LAMMPS²⁵, was used for all simulations. The long time and length scales, as well as the correct hydrodynamics, are essential to accurate simulation of polymer morphologies relevant to applications such as drug solubilization and delivery. The DPD models for hydrophilic PEO and hydrophobic poly(ethylene) (PEE) used here were previously developed using a density mapping approach^{16,17}. DPD refers to the use of a momentum-conserving Langevin thermostat, in combination with a soft, repulsive force interacting between the component beads, or monomers. The force acting on each component bead i , f_i , consists of three contributions (conservative, dissipative, and random forces) due to neighboring beads j within a cutoff radius $r < r_c$,

$$\begin{aligned} f_i &= \sum_j F_{ij}^C + F_{ij}^D + F_{ij}^R \\ F_{ij}^C &= a_{ij}(1 - r_{ij})\hat{r}_{ij} \\ F_{ij}^D &= -\gamma\omega_D(r_{ij})(\hat{r}_{ij} \cdot v_{ij})\hat{r}_{ij} \\ F_{ij}^R &= \sigma\omega_R(r_{ij})\xi_{ij}\hat{r}_{ij} \end{aligned} \quad (1)$$

where $\omega_D(r_{ij}) = \omega_R(r_{ij})^2 = (1 - r_{ij})^2$, and ξ_{ij} is a random variable with zero mean and unit variance.

The magnitudes of the random (σ) and dissipative (γ) forces are chosen such that the fluctuation-dissipation relation is obeyed ($\sigma^2 = 2k_B T \gamma$). The mass, length scales (r_c), and time-scales, in addition to the self-repulsion parameters a_{ii} , are set by choosing a mapping of 3 water molecules per DPD bead. This reproduces the compressibility and diffusion of water¹¹. It follows that the simulation length scale is related to real space, such that $r_c = 6.46$ Å, and the relation between simulation (τ) and real time is such that $\tau = 87.98$ ps¹¹. All simulations here were performed with a timestep δt of .02 τ .

Average system sizes are on the order of 1300–1800 polymers with up to 2 million water beads, with time-scales ranging from several μ s up to 40 μ s.[‡] Single polymers (~40–140 monomers per polymer chain) can quickly aggregate, but equilibration of the micellar size distribution is not computationally accessible due to the large entropic repulsion of the chains between micellar structures²⁶. True equilibrium in long chain polymeric systems is a subtle question^{26,27}. Large micellar aggregates was pre-assembled and the stability of structures were assessed using DPD, to compare with experimental conditions. The micellar aggregates were prepared by ‘growing’ the chains from the interfacial bead inwards and outwards respectively on a cylindrical radius. Approximate core density is known (.82g/cm³), so that this radius could be estimated accordingly after scaling with chain length was determined. Equilibration was determined by relaxation of the micellar core density, as well as the end-to-end distance and radius of gyration of the polymer chains.

Results

Cryo-TEM images in Fig. 1a suggest that the breakup of worm micelles resembles the Rayleigh instability of a fluid stream in which interfacial perturbations propagate. The worm-like micelles of PEO-PCL ($M_n=11,500$ kg/mol) are initially many microns long but hydrolysis of the PCL chains promotes a progressive transition to spherical micelles and ‘dumbbells’²⁸. Degradation of ~30% of the PCL has been estimated as a bulk average

[‡]A summary of system sizes is found in Sup. Table 1. Please note that the largest system sizes: approximately 1800 polymers, 200,000 waters, were used for scaling results. Smaller system sizes were used to study kinetic behavior.

degradation that is necessary for budding and breakup of worms, but the reaction is heterogeneous and imaging experiments simply lack the resolution to address whether short chains localize to regions of high curvature²⁸ – thus motivating the DPD studies here. Simulation snapshots in Fig. 1b–f demonstrate that a mixture of copolymers with differing hydrophobic lengths undergo a transition similar to those seen in experiments. Water molecules that surround the assembly are not shown, but the hydrated PEO corona is loose and brushy per Fig. 1b with red or yellow indicating hydrophobic chains of different length. In cryo-TEM experiments, the corona is largely invisible because the PEO is also highly hydrated. Simulation snapshots in Fig. 1c–f show just the dense micelle core (as in cryo-TEM) with blue and gold now indicating the hydrophobic chains of different length. The two different sized chains ‘appear’ dispersed throughout the core, as opposed to being strictly localized to a particular curvature. Nonetheless, at some critical concentration elaborated below, segregation can be documented and undulations grow with time in the core of the worm and a sphere (or dumbbell) eventually pinches off from the worm’s end-cap as shown.

The worm-to-sphere transition is a classic order-to-order transition in block copolymer melts²⁹. It is also known that such transitions, if driven by a change of relative miscibility or temperature can proceed via a metastable state that is impeded by high energy barriers and slow molecular diffusion³⁰. However, large scale mesoscopic simulations based on both detailed atomistic models, and experimental observables – as here in dilute polymer solution – can add insight into many molecular aspects of the metastable state.

To validate the simulation physics, we step back and carefully assess the molecular weight scaling of worm-like micelle structure. In general, diblock copolymers are characterized by the total number of monomers, N_{total} , and the hydrophilic mass fraction f_{EO} ($0 \leq f_{\text{EO}} \leq 1$). The number of EO monomers, N_{EO} , plus the number of hydrophobic monomers, N_{h} , gives $N_{\text{total}} = N_{\text{EO}} + N_{\text{h}}$, and one can calculate $f_{\text{EO}} = N_{\text{EO}}m_{\text{EO}} / (N_{\text{EO}}m_{\text{EO}} + N_{\text{h}}m_{\text{h}})$, where the m_i ’s are monomer masses that establish the total molecular weight of the polymer M_{tot} . Degradation of hydrophobic blocks, such as PCL, with time leads to a decrease in N_{h} and a net increase in f_{EO} . Phase diagrams for vesicles/worms/spheres in the $(f_{\text{EO}}, M_{\text{tot}})$ -plane have been determined in extensive experiments on the strongly segregating block copolymers³ simulated here, and, based on the experimental phase boundaries, an empirical correlation with the molecular packing parameter p incorporates a weak dependence on M_{tot} that can be written in a two-variable Pade’ approximant form (i.e. as a Chisholm approximant):

$$f_{\text{EO}} \approx (0.2 - 0.01M_{\text{tot}})/(-0.03 + p - 0.01M_{\text{tot}}). \quad (2)$$

This correlation for M_{tot} up to ~10 kg/mol is specifically obtained from the following correspondences: (i) $p = 0.5$ corresponds to where pure vesicles transition to vesicle-worm coexistence, (ii) $p = 0.33$ corresponds to where pure spheres transition to sphere-worm coexistence, and (iii) $p = \frac{1}{2} (0.5 + 0.33)$ corresponds to the the middle of the pure worm-like micelle phase. For $M_{\text{tot}} \approx 10$ kg/mol (of relevance to Fig. 1a), worm-like micelles are detected experimentally for $f_{\text{EO}} \approx 0.25$ to 0.50, with spheres – but not worms – seen in experiments for $f_{\text{EO}} > 0.50$. In the simulations below, which are among the largest and longest for atomistics-rooted DPD of polymers, we show that worm-like micelles can be kinetically stable for relatively long times (> microseconds) well above this phase boundary for both single component and binary systems.

Scaling and stability of single component worm-like micelles

First, the structural effects of increasing N_{total} at constant $f_{\text{EO}} = 0.5$ were studied with monodisperse diblock copolymer. Both experiment and theory provide scaling results for

comparison. From simulations, density profiles of hydrophilic and hydrophobic monomers in the worm-like morphology depend on distance from the central axis of the micelle (Fig. 2a). As the length of the diblock increases, the corona swells with water. Correspondingly, the polymer corona density decreases, the interfacial width between PEO and the hydrophobic block increases, and the radius of the micellar hydrophobic core scales as $\sim N_h^{0.59} (+/-0.02)$ (Fig. 2b). Experimental measurements of hydrophobic core diameter d by cryo-TEM show a very similar scaling of $d \sim N_h^{0.61}$ ³¹. The radial width of the corona, R_{corona} , scales differently with the total length of the polymer as $\sim N_{total}^{0.73}$ as shown here by simulation.

Mean-field arguments for the strong segregation limit (SSL) balance interfacial tension against chain entropy in predicting $d \sim N_h^{2/3}$; while for fully stretched chains, $d \sim N_h$. The SSL appears more similar to the simulation results. Significant end effects can also be seen for larger copolymer lengths: the end-caps become significantly more bulbous as the corona swells. This bulb formation at high molecular weights is in agreement with the experimental observation that as M_{tot} of the diblock is increased at constant f_{EO} , the preferred morphology changes from a worm to a sphere³².

The worm-to-sphere transition with increasing f_{EO} depends weakly on both N_{total} and the Flory-Huggins interaction parameter, χ , that specifies the relative incompatibility between blocks and that sets the cohesive energy scale for self-assembly (i.e. χN_{total})³³. Simulation results for different copolymers are therefore likely to appear similar, and at least for limited studies of PEO-PCL thus far the $N_h^{2/3}$ scaling of SSL indeed also applies⁸. Additional SSL arguments³³ predict that the interfacial width varies as $w \sim (2/3\chi)^{1/2} C^{-1/2}$, where C is the concentration of polymer. In our simulations, an increase in polymer length leads to swelling of the corona and a decrease in C_{EO} with a width of the interface, w , consistent with $C_{EO}^{-0.5}$ (Fig. 2a and Supp Fig. E.). Consistency with SSL would also dictate a C_{EO} -dependence of interfacial tension γ ³⁴, $\gamma \sim (\chi/6)^{1/2} C^{3/2}$. Since γ stabilizes structure, such insights from SSL motivate the systematic analyses below of the worm-to-sphere transition.

Stability of the worms in DPD simulation of the monodisperse copolymers was assessed by preparing individual micelles of length N_h of the hydrophobic block while holding constant the hydrophilic block length, N_{EO} (Fig 3). An increase in temperature from ambient (293 K) to a temperature 20% higher (352 K) – showed no significant temperature effect on the metastability limit, consistent with experimental phase diagrams for these types of block copolymers³⁰.

Increases in f_{EO} lead to an increase in fluctuations in the core (colored in gold) and a strong probability of breakup for $f_{EO} \geq 0.72$ ($\equiv f^*$). The instability typically initiates from a bulbous end of the worm, propagates as fluctuations in the core, and pinches off or buds after ~ 2 μ sec (See Sup. Table 1). In one budding event, two interconnected or entangled spherical micelles fission from the core simultaneously. Interestingly, in the cryo-TEM images of Fig. 1a, two spherical micelles are seen to be interconnected as “dumbbells” at an experimental frequency of about 1:6 (dumbbell : sphere ratio). After the initial pinch-off in simulation, the time-scale for additional fission is greater than several μ sec; and only one of five simulated worm-like micelles appeared stable for ~ 40 μ sec.

For higher $f_{EO} = 0.82$, which should strongly favor spherical micelles, short length-scale fluctuations proliferate in the core, and the evolution should be less affected by chain-length limits to curvature-driven diffusion. A shorter time-scale for pinch-off as above (~ 400 ns) indeed supports this argument. While micelle fusion/fission is promoted by fewer chain entanglements of shorter chains²⁷, the process still takes $\sim \mu$ sec to generate distinct

dumbbells and spheres (ratio 1:3). Simulations yield dumbbell : sphere ratios that appear remarkably similar to experimental ratios.

Copolymer mixtures in worm-like micelles: Stability and breakup

Block copolymers made with degradable hydrophobic chains lose hydrophobic mass M_h and thereby increase f_{EO} with time⁸. Degradation reactions such as hydrolysis of PCL are heterogeneous in cleaving different polymer chains at different sites, so that copolymer polydispersity tends to increase with time. With simpler binary mixtures of two different miscible copolymers (A and B), additivity in mole fraction (Φ) is usually a first assumption²², with the phase behavior expected to reflect a mixing rule:

$$\langle f_{EO} \rangle = \Phi f_{EO,A} + (1 - \Phi) f_{EO,B} \quad (3)$$

If such additivity applies to the DPD simulations here, the worm-to-sphere transitions for single component and multi-component systems should prove similar. To test this additivity and also emulate degradation processes, sphere-preferring $f_{EO} = 0.82$ copolymer chains (PEO₄₀-PEE₇) were mixed into the otherwise stable worm-like micelles (of PEO₄₀-PEE₃₂ with $f_{EO} = 0.5$) and then morphological stability was assessed. Below 30 mol% of the sphere-forming copolymer, no perturbations were obvious up to ~20 μ sec. However, at 30 mol% ($\langle f_{EO} \rangle \approx 0.6$), peristaltic undulations along the worm micelle and perturbations in the end-caps were apparent even though the assemblies appeared stable (Fig. 4a). For mixtures of 40 mol% sphere-former and above ($\langle f_{EO} \rangle \geq 0.63$), perturbations in the micellar density profiles were extreme and, with time, radial undulations on a length scale of spherical micelle dimensions precede budding and breakup into spherical micelles per Fig. 1. Interestingly, individual unimers of PEO₄₀-PEE₇, but not of PEO₄₀-PEE₃₂, are expelled just prior to the first spherical micelle fission process. While this indicates that the free energy of transfer for unimers is lower for the short chain than the micelle fission energy, it also suggests that the critical $\langle f_{EO} \rangle^*$ for the transition will be somewhat over-estimated with this short, fully segregating copolymer. The fact that f^* for the single component system is similar to but different from $\langle f_{EO} \rangle^*$ motivates a deeper, analytical understanding of block copolymer mixtures – as pursued theoretically in the final section below.

Coupling of curvature to concentration

Mean field models of the worm-to-sphere transition for charged diblock copolymers can reproduce – with some key assumptions – the phase behavior of diblock copolymer micelles as a function of charge fraction on the polymer and salt concentration in solution³⁵. Such models have been based in part on a ‘metastable unduloid’ phase observed experimentally with poly(acrylic acid)-poly(styrene) PAA-PS³⁶, but the transition in shape is assumed *ad hoc* to occur in three stages: neck contraction, scission, and finally budding with end relaxation. Scission should expose unfavorable contacts with water, and the simulations here indeed show that hydrophobic contacts are exposed at the breaking point – with the noted liberation of unimers providing obvious evidence. Furthermore, with increasing mol% of the sphere-former, the average core size decreases before breakup and the worm elongates (Fig. 4, inset). The volume decreases by up to ~20%, and the number of spherical micelles that bud off increases (from three to six). The density profile of the core of the mixed micelle shows that the short hydrophobic tails localize close to the interface and reduce the core density by a factor of $\sim 7/10$. In other words, the free volume for the longer hydrophobic chains increases, which is consistent with theory³⁷, but insight into molecular demixing has been lacking.

The line tension between domains in vesicles composed of *strongly* segregating amphiphiles is one of the main driving forces for curvature and budding^{38,39}. Oftentimes, concentration can even act in the reverse manner — to stabilize new phases, such as concentrated hydrogels containing lipids that act to reduce the symmetry of the multilamellar phase through dislocation defects⁴⁰. With amphiphiles that de-mix *weakly* as simulated here (Fig. 1), the degree of local correlations between curvature and molecular concentration during the evolution of the ‘metastable unduloid’ structure (Fig. 4) are of utmost interest. Fig. 5 demonstrates the procedure to extract correlations between local diblock concentrations at the interface and mean curvature, H . For timescales during which undulations were significant, up until timescales immediately preceding pinching and break-off of the initial spherical micelle, we find the location of the interface for each axial worm slice—defined by the average position of the interfacial copolymer beads in each slice. The interfacial profile between the hydrophilic PEO and hydrophobic PEE along the worm axis is then fit with a polynomial of degree six. Next, we calculate the interfacial polymer concentration ($N_{\text{poly}}/A_{\text{interface}}$) along the worm axis for each of the diblocks. The mean curvature, H , is then calculated as,

$$H = \frac{1}{2} [(1/g)(1+g'^2)^{-1/2} - (g'')(1+g'^2)^{-3/2}] \quad (4)$$

where g is the polynomial fit to the interface. And, lastly, the cross-correlation between ϕ and H is then calculated as

$$\chi_{\phi,H}(d) = \frac{\sum_z [(H_z - \bar{H})(\phi_{z+d} - \bar{\phi})]}{\sqrt{\sum_z (H_z - \bar{H})^2} \sqrt{\sum_z (\phi_{z+d} - \bar{\phi})^2}} \quad (5)$$

A positive correlation between PEO₄₀-PEE₇ and mean curvature is shown in Fig. 5 while PEO₄₀-PEE₃₂ is anti-correlated with mean curvature. Moreover, the cross correlation function along the axis of the worm shows strong fluctuations. The shorter chains thus prefer the more bulbous regions and the endcaps, as opposed to the thinner radial regions of the worm.

We assume the local mean curvature is a linear superposition of the two mean curvatures, H_1 and H_2 , from the unmixed states:

$$H(\phi) = \phi H_1 + (1 - \phi) H_2 \quad (6)$$

H_1 ($1/3.87 \text{ nm}^{-1}$) and H_2 ($1/14.4 \text{ nm}^{-1}$), are spherical and cylindrical mean curvatures of single component micelles as obtained by simulations as shown in Fig. 3. We plot the mean curvature, H , vs. ϕ (where ϕ is the normalized interfacial concentration of PEO₄₀-PEE₇), for a range of timescales during which undulations were significant in Fig. 6. ϕ is calculated for local axial worm slices, excluding the tips of the worm micelle[‡], assuming a projected cylindrical surface area. At all interfacial concentrations of PEO₄₀-PEE₇, the behavior of ϕ is clearly linear with H , and supports a spontaneous curvature that depends as a linear superposition of the two equilibrium mean curvatures, H_1 and H_2 . This linear relationship

[‡]It is found that there are deviations from this behavior at high concentrations of the minority component along the length of the micelle, which is the end-cap region, that does not fit this linear behavior, and may be subject to the finite size effects.

between interfacial concentration, ϕ , and mean curvature holds for both mol fractions $\Phi = 30$ mol % and 40 mol % simulations, one in which a kinetically stable worm exhibits interfacial fluctuations, the other in which the fluctuations lead to budding and break-up.

Sorting of lipids²⁰ or membrane proteins, such as CTB (Cholera Toxin subunit B), through curvature, is suggested to be dependent on their ability to sense membrane shape⁴¹. Theory suggests that non-linear corrections are necessary near a critical demixing point⁴². Here we show that, for a simple diblock copolymer mixture in a kinetically evolving micelle, differing purely in terms of the packing parameter of the chains, the micellar shape is coupled to the local interfacial concentration in a simple linear relationship.

Conclusions

Equilibrium properties and scaling behavior of polymer based worm-like micelles were elaborated together with analyses of the kinetic stability of both monodisperse and mixed assemblies. The scaling of an isolated worm micelle core with the length of hydrophobic tail of the copolymer at constant hydrophilic fraction, $d \sim N_h^{0.59}$, agrees well with experimental results, and is consistent with scaling within the Strong Segregation Limit. The PEG corona swells with increased copolymer length, and an increase in hydrophilic fraction to $f_{EO} = 0.72$, destabilizes the worm-like micelle to Rayleigh-like budding from the end-caps.

In a mixture, the diffusive properties of the copolymers at the interface suggest reptation dynamics (see supplementary results), and we find that the shorter copolymer localizes close to the interface and acts to reduce the overall core density. Flexibility of the worm micelle before break-up can be determined from careful modeling of curvature-driven segregation and seems consistent with experiment. A metastable mixed copolymer worm also disassembles through dynamic undulation and budding, providing novel insight into the type of breakup that has already been exploited in delivery of anticancer drugs¹⁰. Dissipative Particle Dynamics simulations accurately capture many of the complex processes and transformations across relevant time and length-scales, and so DPD seems a useful method for molecular-scale investigations of the many PEG-based systems being developed for a wide range of applications.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

We thank David Christian, Russell DeVane, Axel Kohlmeyer, Preston Moore, Diego Pantano and Karthik Rajagopal for helpful discussions. The NSF Teragrid provided computational resources. Cryo-TEM images of Fig. 1a were taken by the Bates group (Univ. Minn.). This research was supported in part by NSF, MRSEC DMR05-20020, and an NIH postdoctoral fellowship for S.M.L. references

Notes and references

1. Israelachvili, JN. Intermolecular and Surface Forces. Academic Press; 1992.
2. Bagshaw SA, Prouzet E, Pinnavaia TJ. Science 1995;269:1242–1244. [PubMed: 17732109]
3. Taylor KC, Nasr-El-Din HA. Journal of Petroleum Science and Engineering 1998;19:265–280.
4. Jain S, Bates FS. Science 2003;300:460–464. [PubMed: 12702869]
5. Karaborni S, Esselink E, Hilbers PAJ, Smit B, Karthaus J, van Os NM, Zana R. Science 1994;266:254–256. [PubMed: 17771445]
6. Wang XS, Guerin G, Wang H, Wang Y, Mannes I, Winnik MA. Science 2007;317:644–647. [PubMed: 17673656]

7. Cui HG, Chen ZY, Zhong S, Wooley KL, Pochan DJ. *Science*. 2007
8. Geng Y, Discher DE. *Polymer* 2006;47:2519–2525.
9. Napoli A, Valentini M, Tirelli N, Muller M, Hubbell JA. *J. Nature Materials* 2004;3:183–189.
10. Geng Y, Dalhaimer P, Cai S, Tsai R, Tewari M, Minko T, Discher DE. *Nature Nanotechnology* 2007;2:249–255. 11.
11. Groot RD, Warren PB. *Journal of Chemical Physics* 1997;107:4423–4435. Groot, RD. *Novel Methods in Soft Matter Simulations*. Berlin Heidelberg: Springer-Verlag; 2004. *Applications of Dissipative Particle Dynamics*.
12. Wijmans CM, Smit B, Groot RD. *Journal of Chemical Physics* 2001;114:7644–7654.
13. Grafmuller A, Shillcock J, Lipowsky R. *Physical Review Letters* 2007;98
14. Rekvig L, Hafskjold B, Smit B. *Journal of Chemical Physics* 2004;120:4897–4905. [PubMed: 15267351]
15. Srinivas G, Discher DE, Klein ML. *Nature Materials* 2004;3:638–644.
16. Ortiz V, Nielsen SO, Discher DE, Klein ML, Lipowsky R, Shillcock J. *Journal of Physical Chemistry B* 2005;109:17708–17714.
17. Ortiz V, Nielsen SO, Klein ML, Discher DE. *Journal of Polymer Science Part B-Polymer Physics* 2006;44:1907–1918.
18. Srinivas G, Pitera JW. *Nano Letters* 2008;8:611–618. [PubMed: 18189443]
19. Cooke DM, Shi AC. *Macromolecules* 2006;39:6661–6671.
20. Cooke IR, Deserno M. *Biophysical Journal* 2006;91:487–495. [PubMed: 16807230]
21. van Meer G. *Embo Reports* 2005;6:418–419. [PubMed: 15864292] Kumar VV. *PNAS* 1991;88:444–448. [PubMed: 1988944]
22. Kumar VV. *PNAS* 1991;88:444–448. [PubMed: 1988944]
23. Reynwar BJ, Ilya G, Harmandaris VA, Mueller MM, Kremer Kurt, Derseeno Markus. *Nature* 2007;447:461–464. [PubMed: 17522680]
24. Davis KP, Lodge TP, Bates FS. *Macromolecules* 2008;41:8289–8291.
25. Plimpton S. *Journal of Computational Physics* 1995;117:1–19.
26. Semenov AN. *Zhurnal Eksperimentalnoi I Teoreticheskoi Fiziki* 1985;88:1242–1256.
27. Dormidontova EE. *Macromolecules* 1999;32:7630–7644.
28. Geng Y, Discher DE. *Journal of the American Chemical Society* 2005;127:12780–12781. [PubMed: 16159254]
29. Ryu CY, Lodge TP. *Macromolecules* 1999;32:7190–7201.
30. Hajduck DA, Takenouchi H, Hillmyer MA, Bates FS, Vigild ME, Almdal K. *Macromolecules* 1997;30:3788–3795.
31. Dalhaimer P, Bates FS, Discher DE. *Macromolecules* 2003;36:6873–6877.
32. Dalhaimer P, Bermudez H, Discher DE. *Journal of Polymer Physics, Part B* 2004;4:168–176.
33. Schick, MJ. *Nonionic Surfactants: Physical Chemistry*. N.Y.: Marcel Dekker, Inc., N.Y.; 1987.
34. Noolandi J, Hong KM. *Macromolecules* 1983;16:1443–1448.
35. Bendejacq D, Joanicot M, Ponsinet V. *European Physical Journal E* 2005;17:83–92.
36. Grason GM, Santangelo CD. *European Physical Journal E* 2006;20:335–346. 37.
37. Szleifer I, Kramer D, Ben-Shaul A, Roux D, Gelbart WM. *Physical Review Letters* 1988;60:1966–1969. 38 W. [PubMed: 10038189]
38. Huttner B, Zimmerberg J. *Current Opinion in Cell Biology* 2001;13:478–484. [PubMed: 11454455]
39. Baumgart T, Hess ST, Webb WW. *Nature* 2003;425:821–824. [PubMed: 14574408]
40. Warriner HE, Idziak SHJ, Slack NL, Davidson P, Safinya CR. *Science* 1996;271:969–973. [PubMed: 8584932]
41. Tian A, Baumgart T. *Biophysical Journal* 2009;96:2676–2688. [PubMed: 19348750]
42. Seifert U. *Physical Review Letters* 1993;70:1335–1338. [PubMed: 10054350]

Fig. 1. Mechanism of worm-to-sphere transition. (a) Cryo-TEM images show the breakup of worm-like micelles of PEO-PCL ($M_n=11,500$ kg/mol), with undulation and budding²⁸. Arrows in the bottom image highlight breakup events. (b)→(f) Simulation results for a binary copolymer micelle, which details the transition dynamics. The random starting configuration of the corona (b) or core (c) with red and yellow or blue and gold respectively indicate polymers with two different length hydrophobic chains. Undulations develop (d) with bud formation (e) and pinch off of a spherical micelle (f).

Fig. 2. Effects of diblock molecular weight on worm-like micelle structure. (a) Density profile of PEO and PEE in the worm-like morphology relative to the center of mass of the worm core. With increasing hydrophilic length of polymer at constant f_{EO} , the corona swells and polymer density in the corona decreases. (b) Scaling of radial core size, R_{core} , with the length of hydrophobic beads, N_h , and width of the corona, R_{corona} , with the total length of the polymer, $N = N_{total}$. Scaling of the core agrees well with experimental results ($R_{core} \sim N_h^{0.59}$)²⁹.

Fig. 3. Stability of single component worm-micelles with increasing f_{EO} . (a)–(d) Progressive shortening of the hydrophobic block while keeping the length of the hydrophilic block constant leads to increasing undulations in the core diameter, leading to instability and breakup at (c) $f_{EO} = 0.72$. The hydrophilic corona is represented in blue while the hydrophobic core is shown in gold. Instability propagates as fluctuations in the core thickness that initiate at the end of the worm, leading to bud formation at $2.4 \mu s$ and ‘pinching’ of a spherical micelle at $2.8 \mu s$. Two interconnected spherical micelles give a ‘dumbbell’ micelle. The same process at shorter times occurs at (d) $f_{EO} = 0.82$, but with multiple, shorter length-scale fluctuations in the core diameter.

Fig. 4.

Effects of mixing on worm-like micelle stability. Radial undulations that precede break-up and budding into spherical micelles, as a function of concentration of PEO₄₀-PEE₇ ($f_{EO} = 0.82$) in a PEO₄₀-PEE₃₂ worm. The hydrophobic blocks of the sphere- and worm-formers are shown in orange and blue, respectively. (a) At 30% mol PEO₄₀-PEE₇, the worm assembly remains stable for the total length of the simulation of 20 μ sec. (b)–(d) At 40% mol PEO₄₀-PEE₇ or higher, increasing undulations and core thickness fluctuations, as observed here, lead to eventual breakage of the worm morphology (as shown in Fig. 1) within the time of the simulation. Also shown, average hydrophobic core radius, R_{core} , and worm contour length before break-up as a function of sphere-former concentration.

Fig. 5.

Sample polynomial fit and associated calculations for correlation between concentration and mean curvature, H . From top to bottom: (a) sample interfacial axial worm profile and associated polynomial fit at $t = 789$ ns for 40 mol% as shown in Figure 4, (b) interfacial polymer concentration, N_{poly}/A for PEO $_{40}$ -PEE $_{7}$ and PEO $_{40}$ -PEE $_{32}$ along the axial worm profile at $t = 789$ ns for 40 mol%, (c) mean curvature, H , and, finally, cross correlation between concentration and (d) mean curvature, H , as a function of the axial distance along the worm.

Fig. 6. Mean curvature, H , vs. ϕ (where ϕ is the normalized interfacial concentration of PEO₄₀-PEE₇) and fit, using calculated mean curvatures, H_I , spherical mean curvature, and H_2 , cylindrical mean curvature from simulations of single component polymer assemblies as shown in Fig. 3. We show that a concentration averaged mean curvature is a good approximation for the local curvature. From this fit to Eqn. 7, we calculate the bending modulus, κ , of the mixed micelle before breakup as 2.9 $k_B T$. This plot is for the main body of the worm micelle, excluding the end-caps, where higher interfacial concentrations are found.