Hybrid total hip arthroplasty using specifically-designed stems for patients with developmental dysplasia of the hip. A minimum five-year follow-up study

Hiroshi Ito · Hiromasa Tanino · Yasuhiro Yamanaka ·
Toshiki Nakamura · Takeo Matsuno

Received: 14 May 2010 / Revised: 1 July 2010 / Accepted: 1 July 2010 / Published online: 24 July 2010
© Springer-Verlag 2010

Abstract A 4-U hybrid total hip arthroplasty (THA) system was specifically designed for patients with developmental dysplasia of the hip (DDH). Straight stem with an appropriate offset and various size variations are advantages. We followed 128 hips in 124 patients, 13 men and 111 women, for a mean of 6.5 years (range, 5.0–7.5 years). Two acetabular and femoral components in two patients had been revised for infection, one acetabular component had been revised for recurrent dislocation, and one femoral component had been revised for periprosthetic femoral fracture. None of the acetabular or femoral components were revised for loosening or were found to be loose at follow-up. The Harris hip score increased from a preoperative average of 42 points to 88 points at the most recent follow-up. Primary THA using the 4-U system had a good mid-term result in patients with DDH. This system could be applied for all patients including those with the narrowest and deformed femurs.

Introduction

Total hip arthroplasty (THA) for osteoarthritis secondary to developmental dysplasia of the hip (DDH) presents specific problems that include femoral head deformity, short femoral neck, excessive anteversion of the neck, narrow and straight medullary canal, and insufficient acetabular bone stock [4, 5, 10, 19, 27]. Patients with

DDH are smaller than average Europeans or Americans and thus need smaller and straighter femoral stems [19, 27]. Appropriate fit of the stem in the femur was sometimes disturbed by proximal curve and large distal diameter of the standard stem, even if we used a small implant of the available standard THA systems.

The hybrid THA combines insertion of an acetabular component without cement and a femoral component with cement [12, 25]. We designed and developed an original hybrid THA system for patients with DDH. Our study evaluated whether this system was appropriate for patients with DDH.

4-U Hip System

The name ‘4-U’ (Nakashima Medical, Japan) represents four capital letters of the words: universal, upgraded, unique and ultimate. The shape and size variations of the stem are unique characteristic features of this system. Original three-dimensional (3D) CT data was obtained from patients with DDH, and anatomical femoral shapes were evaluated [11]. Configurations of the 4-U stem were designed to fit every measured femoral canal appropriately (Fig. 1a, b). The shape of the stem below the proximal collar was designed straight and the femoral neck was designed long enough to restore the anatomical length of offset between the longitudinal axis of the stem and the centre of the femoral head. Seven stems from No. 1 to No. 7 are available (Table 1, Fig. 1c). Long, standard and short neck lengths are available for each stem with monoblock. The femoral head is modular and two lengths of 0 mm and 3.5 mm are also available.

The No. 1 smallest stem has the unique characteristic feature of this system, which was designed to fit to the smallest femoral canal. The largest offset of the No. 1 stem

H. Ito (✉) · H. Tanino · Y. Yamanaka · T. Nakamura · T. Matsuno
Department of Orthopaedic Surgery,
Asahikawa Medical University,
Midorigaoka Higashi 2-1-1-1,
Asahikawa 078-8510, Japan
e-mail: itohiro@asahikawa-med.ac.jp

Fig. 1 Photograph and measurements of the femoral component. **a** Anteroposterior photograph showing the 4-U No. 1 long neck stem. **b** Lateral photograph showing the same stem. **c** Measurements of the femoral component. L1: length of the stem, L2: offset, L3: neck length, L4: proximal anteroposterior width

is 40 mm, which is longer than the available equivalent small cemented stems including Exeter smallest stem (Stryker-Howmedica-Osteonics, Allendale, New Jersey, USA) with 34 mm of the largest offset. The bending strength of No. 1 long neck stem is 15,200 N, indicating that the No. 1 long neck stem could endure various stresses caused by daily activity of patients [18]. The stem is made of cobalt-chromium alloy with the average surface roughness of 2.0 μm in the proximal half and 1.0 μm in the distal half, which is equivalent to the matte finish component.

The acetabular component is a titanium alloy (Ti-6Al-4 V) hemisphere with fibre-metal porous-coating. The outer shell has multiple screw holes, with diameters ranging from 40 to 62 mm in 2-mm increments. Both standard and 10° elevated polyethylene liners are available for 22, 26 and 28 mm-diameter head. The minimum thickness of the liner is 5.7 mm.

The purpose of this study was to evaluate early to intermediate-term results after primary hybrid THA using this system for the treatment of osteoarthritis secondary to DDH.

Patients and methods

Between September 2002 and August 2004, 144 total hip arthroplasties using 4-U Hip System were performed in 140 patients for treatment of advanced osteoarthritis secondary to DDH. Of these, 16 patients (16 hips) were excluded from the study: three patients (three hips) died before a minimum five-year follow-up; eight patients (eight hips) were contacted by telephone and known to have well-functioning THAs but did not have radiographs for review; and five patients (five hips) had no data available after the early postoperative period. The remaining 128 hips in 124 patients were available for clinical and radiological review. The average duration of follow-up was 6.5 years (range, 5.0–7.5 years). The average age at the time of the index operation was 62.5 years (range, 30–87 years). The average weight was 54 kg (range, 35–88 kg) and the average height was 152 cm (range, 132–169 cm). The average body mass index was 23.9 (range, 16.0–34.8). Thirteen patients were men and 111 were women. There were 68 right hips and 60 left hips. According to the

Table 1 Each size of the femoral component (see Fig. 1c)

Number	Length of the stem(L1, mm)	Offset(L2, mm)	Neck length(L3, mm)	Proximal anteroposterior width (L4, mm)
1	94	27 / 32 / 37	27 / 34 / 41	9
2	104	29 / 34 / 39	30 / 37 / 44	10
3	113	31 / 36 / 41	32 / 39 / 46	11
4	123	33 / 38 / 43	35 / 42 / 49	12
5	127	33 / 38 / 43	35 / 42 / 49	13
6	131	33 / 38 / 43	35 / 42 / 49	14
7	140	35 / 40 / 45	37 / 44 / 51	16

classification system of Hartofilakidis et al. [10], 109 hips were type-1 (dysplasia), 13 were type-2 (low dislocation), and six were type-3 (high dislocation).

All of the procedures were performed through the posterolateral approach without trochanteric osteotomy. The acetabular component was inserted with a line-to-line fit. An average of 3.1 screws (range, 2–5 screws) was used for fixation. The average outer diameter of the acetabular component was 52 mm (range, 40–60 mm). The diameter of the prosthetic femoral head was 22 mm in 82 hips and 26 mm in 46 hips. All polyethylene liners used in this study period were conventional, not highly cross-linked. The average polyethylene liner thickness was 10.9 mm (range, 5.7–15.7 mm). The standard polyethylene liner was used in 115 hips and the 10° elevated liner was used in 13. The initial depth of the standard liner was 50% of the femoral head diameter. The initial dislocation rate was high and this shallow liner seemed related to high dislocation rate. A circumferential 1-mm rim was added to all the polyethylene standard liners from April 2004.

The smallest, No. 1, was used in nine hips, No. 2 in 12 hips, No. 3 in 35 hips, No. 4 in 58 hips, No. 5 in 13 hips and No. 6 in one hip. All final femoral rasps used in this study for canal preparation over-rasped by 0.5 mm. Simplex cement (Stryker-Howmedica-Osteonics, Mahwah, New Jersey) was prepared and inserted into the femoral canal using a cement gun. A methylmethacrylate plug was used in all hips.

Clinical evaluations were made using the Harris hip scoring system [8]. An anteroposterior radiograph and a true lateral radiograph were made pre-operatively and at each follow-up examination. Anteversion of the acetabular component was measured [22]. The acetabular interface on the anteroposterior radiograph was divided into three zones [3]. The acetabular component was classified as migrated if there was a change of at least 4 mm in the horizontal or vertical position of the centre of the component [24]. Linear head penetration into the polyethylene liner was measured [15].

Cementing of the femoral stem was classified as Grade A, B, C-1, C-2, and D [17]. The dimensions and location of radiolucent lines at the bone-cement interface of the femoral component and osteolytic lesions were recorded [7]. The thickness of the femoral cement mantle was measured in 12 zones of the femur. The canal filling ratio of the femoral component was defined as the percentage of component width to intramedullary width at the midpoint of the component on an anteroposterior radiograph taken within one month of surgery [13]. Loosening of the femoral component was defined using the criteria described by Harris et al. [9].

The study design was approved by the Ethics Committee of Asahikawa Medical College (09-10-13, #607).

Statistical analyses were performed using SPSS software (SPSS Inc., Chicago, Illinois, USA). Clinical, radiographic, and surgical factors were evaluated using chi-square tests or Mann-Whitney U test where appropriate. Preoperative and postoperative Harris hip scores were compared using the Wilcoxon signed-rank test. Probability values less than 0.05 were considered significant. The Pearson linear correlation coefficient was used to assess correlations between wear and various measurements. Kaplan-Meier survival curves with end points defined as revision for any reason and aseptic loosening of the acetabular and femoral component were calculated. All survivorship data were reported with 95% confidence interval (CI).

Results

The 4-U Hip System could be used in all patients including those with the narrowest and deformed femurs. At the most recent follow-up, two acetabular and femoral components in two patients had been revised for infection at two and 22 months postoperatively. One acetabular component had been revised for recurrent dislocation 30 months postoperatively. One femoral component had been revised for periprosthetic femoral fracture 6.2 years postoperatively. None of the acetabular or femoral components were revised for loosening or found to be definitely loose on radiographs (Figs. 2 and 3). Kaplan-Meier analysis revealed that the survival rate was 100% with aseptic loosening of the acetabular or femoral component as the end point and 96% (95% CI: 94–98%) with revision for any reason as the end point.

The Harris hip score increased from a preoperative average of 42 points (range, 26–76 points) to 88 points (range, 40–100 points) at the most recent follow-up for patients who did not have a subsequent revision ($p < 0.001$): 88 points (range, 40–100 points) in type-1 hips, 92 points (range, 85–100 points) in type-2 hips and 83 points (range, 70–90 points) in type-3 hips ($p = 0.175$).

The average angle of abduction of acetabular components at the latest follow-up was 44.9° (range, 35–62°). The average anteversion of the acetabular components was 14.1° (range, 0–30°) and the average combined anteversion of the acetabular and femoral components was 46.9° (range, 18–80°). None of the acetabular components showed radiographic migration, rotation, or a continuous radiolucent line. Radiolucent lines were observed around six (5%) acetabular components. These lines were all 1 mm wide or less and no sockets showed a continuous radiolucent line. Small pelvic osteolytic lesions were observed adjacent to the acetabular component in two (1.5%) hips. The average rate of head penetration into the polyethylene liner was

Fig. 2 Preoperative and follow-up radiographs of the left hip of a 62-year-old woman. **a** Preoperative radiograph showing high dislocation of the left hip. **b** Postoperative radiograph taken one day after surgery. No. 1 standard stem was inserted. **c** Radiograph taken at seven-year follow-up examination showing no radiolucent lines. Although the acetabular component was fixed at a high location of the pelvis, enough offset of the stem has avoided impingement between the acetabulum and the femur. The patient reported no hip pain and the clinical result was good

0.09 mm (range, 0.01–0.40 mm) per year. There was a significant correlation between wear and abduction angle of the socket ($p=0.023$). There were no correlations between wear and patient age ($p=0.128$), gender ($p=0.192$), body weight ($p=0.257$), polyethylene thickness ($p=0.369$), diameter of the femoral head ($p=0.134$), anteversion angle of the socket ($p=0.136$), anteversion angle of the stem ($p=0.128$), and position of the hip centre ($p=0.418$).

None of the femoral components showed definite or probable loosening at the most recent follow-up. The position of inserted femoral components was neutral in 115, varus in nine and valgus in four. The cementing of the femoral component was grade A in 56, grade B in 64, grade C-1 in six, and grade C-2 in two. Grade C-1 was given mainly due to the presence of small voids and grade C-2 due to the presence of a thin mantle of cement. The average

cement thickness around the femoral component was >2 mm except for zone 5 (Table 2). Radiolucent lines were observed around three (2%) femoral components. All radiolucent lines were seen at the bone–cement interface located in zone 1. No radiolucent lines were observed at the implant–cement interface. No hips showed femoral osteolysis other than two hips with postoperative infection. The average canal filling ratio was 80% (range, 63–95%).

Fourteen hips (11%) dislocated posteriorly. All dislocations occurred in the initial 106 hips with the original liner, and no dislocation occurred in 22 hips with the modified liner from April 2004. One hip had undergone revision of the acetabular component for recurrent dislocation as described. The remaining dislocations were successfully treated without reoperation. There was no significant relationship between dislocation and patient age ($p=$

Fig. 3 Preoperative and follow-up radiographs of the right hip of a 52-year-old woman. **a** Preoperative radiograph showing low dislocation of the left hip. **b** Postoperative radiograph taken one week after surgery. No. 3 standard stem was inserted. **c** Radiograph taken at 7.5-year follow-up examination showing no radiolucent lines. The patient had a good clinical result

Table 2 Analysis of the cement thickness of the femoral component

Femoral zone	Cement thickness, mm
1	2.3 (0.6)
2	2.2 (0.9)
3	2.8 (0.8)
5	1.5 (1.2)
6	2.6 (0.9)
7	2.5 (1.0)
8	2.2 (0.6)
9	2.3 (0.7)
10	3.7 (1.8)
12	3.0 (1.1)
13	2.8 (0.9)
14	2.9 (0.6)

SD standard deviation

The values are given as the mean (SD) cement thickness (in mm)

0.162), gender ($p = 0.182$), weight ($p = 0.150$), diameter of the femoral head ($p = 0.985$), use of elevated liner ($p = 0.692$), abduction angle ($p = 0.306$) and anteversion angle ($p = 0.299$) of the acetabular component, combined anteversion angle of the acetabular and femoral components ($p = 0.299$), and the hip centre ($p = 0.456$).

There was no intraoperative periprosthetic fracture, nerve palsy, or clinically evident pulmonary embolisms.

Discussion

The 4-U femoral component has several unique features including straight stem, long femoral neck, and size variations providing the surgeon with a wide choice. This system could be used in all patients and implanted even in hips with the narrowest or deformed femur. The clinical and radiographic results of the 4-U Hip System for patients with DDH continue to be encouraging. From September 2002, we have consecutively used the 4-U Hip System for patients with DDH. The No. 1 smallest stem was used in nine (7%) hips, indicating that the small and straight stem has been needed for some patients with DDH. We believe that one of the main factors contributing to the excellent survival and outcome of this implant is the smaller, straighter design and adequate offset of the femoral component [2].

The ideal thickness of the cement mantle for the femoral component is controversial. Thin or incomplete cement mantles have been reported to be responsible for irregular stress distribution, cement mantle fracture, stem debonding, osteolysis, and aseptic loosening [6, 23]. At least 2-mm cement mantle thickness was recommended with use of

sufficient intraoperative over-rasping or over-reaming of the femur [28]. On the other hand, the thin cement mantle technique was introduced by Postel [21]. Langlais et al. showed good clinical results with a thin cement mantle technique using Charnley-Kerboull and the Ceraver Osteal cemented femoral components [14]. These stems were intended to fully fill the medullary canal of the femur. They emphasised that a marked increase in pressure at the cement–bone interface would be produced by vigorous insertion of a canal-filling stem into doughy cement, and stronger initial mechanical interlocking at the cement–bone interface could be obtained. Skinner et al. also reported good clinical results with a thin cement mantle technique [26]. We believe that the tighter fit of the femoral component is technically important for patients with a narrow femoral canal, and our results support these previous studies.

Although one of the main concerns of using shorter and smaller stems is the failure or breakage of implants, this has not been observed in our study. To date, we have implanted more than 1,000 4-U stems, and we have not encountered any implant fractures. The implant is clinically safe and can be used for suitable patients with DDH.

Cementless femoral components have no room for the cement mantle, and intraoperative fractures have been reported [1, 20]. Perka et al. reported the high incidence of intraoperative fractures using cementless stems for patients with DDH [20]. Intraoperative fracture is not a common complication in cemented femoral components and was not observed in this study.

Mallory et al. reported that dislocations after THA occurred frequently in patients with DDH [16]. The present dislocation rate of 11% was equivalent or higher compared to those of the previous series of DDH [1, 12, 20, 25]. It is apparent that the technique described by Pradhan [22] for evaluating acetabular version cannot distinguish anteversion from retroversion but only the degree of version; however, anteversion of the acetabular component was intraoperatively confirmed by visual inspection for all patients. Our posterior approach without repair of the external rotators and the posterior part of the capsule might have been a factor leading to the high dislocation rate. Due to this relatively high dislocation rate, we had a minor design change for the depth of the polyethylene liner in April 2004 as described above. This design change seems to have reduced the dislocation rate. Another disadvantage of this system was that we used only conventional polyethylene in the period of this study, which is now being changed to highly cross-linked polyethylene.

We conclude that the 4-U Hip System provides an appropriate fit of the femoral component among size variations, and satisfactory clinical results for patients with

DDH. This system could be used in all our DDH patients including those with the narrowest and deformed femurs. We believe that use of an appropriate shape and size of the femoral component, and technical tight fit within the cement are important factors to achieve good clinical results. On the basis of our results, we continue to use this system.

Conflict of interest and funding No benefits or funds were received in support of this study.

References

1. Biant LC, Bruce WJ, Assini JB, Walker PM, Walsh WR (2009) Primary total hip arthroplasty in severe developmental dysplasia of the hip: ten-year results using a cementless modular stem. *J Arthroplasty* 24:27–32
2. Bicanic G, Delimar D, Delimar M, Pecina M (2009) Influence of the acetabular cup position on hip load during arthroplasty in hip dysplasia. *Int Orthop* 33:397–402
3. DeLee JG, Charnley J (1976) Radiographical demarcation of cemented sockets in total hip replacement. *Clin Orthop Relat Res* 121:20–32
4. Delimar D, Bićanić G, Pećina M, Korzinek K (2004) Acetabular roof reconstruction with pedicled iliac graft: early clinical experience. *Int Orthop* 28:319–320
5. Delimar D, Cicak N, Klobucar H, Pećina M, Korzinek K (2002) Acetabular roof reconstruction with pedicled iliac graft. *Int Orthop* 26:344–348
6. Ebramzadeh E, Sarmiento A, McKellop HA, Linas A, Gogan W (1994) The cement mantle in total hip arthroplasty: analysis of long-term radiographic results. *J Bone Joint Surg Am* 76:77–87
7. Gruen TA, McNeice GM, Amstutz HC (1979) “Modes of failure” of cemented stem-type femoral components: a radiographic analysis of loosening. *Clin Orthop Relat Res* 141:17–27
8. Harris WH (1969) Traumatic arthritis of the hip after dislocation and acetabular fracture: treatment by mold arthroplasty. *J Bone Joint Surg Am* 51:737–755
9. Harris WH, McCarthy JC Jr, O'Neill DA (1982) Femoral component loosening using contemporary techniques of femoral cement fixation. *J Bone Joint Surg Am* 64:1063–1067
10. Hartofilakidis G, Stamos K, Karachalios T, Ioannidis TT, Zacharakis N (1996) Congenital hip disease in adults: classification of acetabular deficiencies and operative treatment with acetabuloplasty combined with total hip arthroplasty. *J Bone Joint Surg Am* 78:683–692
11. Higa M (2003) Development of a new femoral component in total hip arthroplasty. PhD Dissertation, Hokkaido University, Sapporo, Japan, pp 75–86
12. Ito H, Matsuno T, Minami A, Aoki Y (2003) Intermediate-term results after hybrid total hip arthroplasty for the treatment of dysplastic hips. *J Bone Joint Surg Am* 85:1725–1732
13. Kobayashi S, Terayama K (1992) Factors influencing survivorship of the femoral component after primary low-friction hip arthroplasty. *J Arthroplasty* 7 Suppl:327–338
14. Langlais F, Kerboul M, Sedel L, Ling RSM (2003) Annotation: the ‘French paradox’. *J Bone Joint Surg Br* 85:17–20
15. Livermore J, Ilstrup D, Morrey B (1990) Effect of femoral head size on wear of the polyethylene acetabular component. *J Bone Joint Surg Am* 72:518–528
16. Mallory TH, Lombardi AV Jr, Fada RA, Herrington SM, Eberle RW (1999) Dislocation after total hip arthroplasty using the anterolateral abductor split approach. *Clin Orthop Relat Res* 358:166–172
17. Mulroy WF, Estok DM, Harris WH (1995) Total hip arthroplasty with use of so-called second-generation cementing techniques: a fifteen-year-average follow-up study. *J Bone Joint Surg Am* 77:1845–1852
18. Kuramoto K (2003) Strength test of the femoral neck. Technical Report of Nakashima Medical Co. Okayama
19. Noble PC, Kamaric E, Sugano N et al (2003) Three-dimensional shape of the dysplastic femur: implications for THR. *Clin Orthop Relat Res* 417:27–40
20. Perka C, Fischer U, Taylor WR, Matziolis G (2004) Developmental hip dysplasia treated with total hip arthroplasty with a straight stem and a threaded cup. *J Bone Joint Surg Am* 86:312–319
21. Postel M (1987) The routine operation. In: Postel M, Kerboul M, Evrard J, Courpied JP (eds) Total hip replacement. Springer, Berlin, pp 26–33
22. Pradhan R (1999) Planar anteversion of the acetabular cup as determined from plain anteroposterior radiographs. *J Bone Joint Surg Br* 81:431–435
23. Ramaniraka NA, Rakotomanana LR, Leyvraz P-F (2000) The fixation of the cemented femoral component: effects of stem stiffness, cement thickness and roughness of the cement/bone surface. *J Bone Joint Surg Br* 82:297–303
24. Russotti GM, Harris WH (1991) Proximal placement of the acetabular component in total hip arthroplasty: a long-term follow-up study. *J Bone Joint Surg Am* 73:587–592
25. Shen B, Yang J, Wang L et al (2009) Midterm results of hybrid total hip arthroplasty for treatment of osteoarthritis secondary to developmental dysplasia of the hip—Chinese experience. *J Arthroplasty* 24:1157–1163
26. Skinner JA, Todo S, Taylor M et al (2003) Should the cement mantle around the femoral component be thick or thin? *J Bone Joint Surg Br* 85:45–51
27. Sugano N, Noble PC, Kamaric E et al (1998) The morphology of the femur in developmental dysplasia of the hip. *J Bone Joint Surg Br* 80:711–719
28. Valdivia GG, Dunbar MJ, Parker DA et al (2001) Three-dimensional analysis of the cement mantle in total hip arthroplasty. *Clin Orthop Relat Res* 393:38–51