Published in final edited form as:

Bioorg Med Chem Lett. 2011 November 1; 21(21): 6370–6375. doi:10.1016/j.bmcl.2011.08.103.

Synthesis of Lipids for Development of Multifunctional Lipid-Based Drug-Carriers

Guodong Zhu, Yahya Al Hamhoom, Brian S. Cummings, and Robert D. Arnold*

^aDepartment of Pharmaceutical and Biomedical Sciences, College of Pharmacy, University of Georgia, Athens, GA 30602-2352

Abstract

A simple approach to synthesize phospholipids to modulate drug release and track lipid-based particulate drug-carriers is described. We synthesized two ether lipids, **1** *1-O*-hexadecyl-2-pentadenoyl-*sn*-glycerol-3-phosphocholine (C₃₁PC) and **2** *1-O*-hexadecyl-2-pentadenoyl-*sn*-glycerol-3-phosphomethanol (C₃₁PM), and examined their ability to alter enzymatically triggered release of 6-carboxyfluorescein from liposomes incubated in TRIS buffer or fetal bovine serum solutions. Further, we demonstrated that odd-chain lipids, *e.g.*, C₃₁PC, could be identified in rat plasma without interference of endogenous lipids. This approach can be adapted to synthesize a variety of lipids for use in developing and optimizing multifunctional drug-carriers.

Keywords

liposomes; phospholipids; secretory phospholipase A₂; synthesis

Lipid based drug-carriers, such as liposomes, can alter the pharmacokinetics and improve the efficacy of a variety of therapeutic agents¹. However, mechanisms to “control” or “tune” their drug release kinetics and track drug-carrier disposition *in vivo* are limited. A variety of physical and physiological approaches have been examined to control drug release from drug-carriers, including exposure to light^{2–4}, heat^{5–7}, and use of ultrasound^{8, 9}. However, the clinical use of these strategies has been limited because of their ability to induce rapid “burst” drug-release profiles and the inaccessibility of some tissue to light or heat.

Enzymatic approaches exploiting elevated expression of enzymes, such as esterases, in some disease states have the potential to modulate drug-release selectively. Secretory phospholipase A₂ (sPLA₂) is an esterase that preferentially hydrolyzes glycerophospholipids, such as phosphatidylcholine, at the *sn*-2 ester bond, releasing a fatty acid (FA) and a lysophospholipid (LP)¹⁰. Recent studies demonstrated that the expression and catalytic activity of sPLA₂ is increased in prostate^{11–14}, breast^{15–17} and pancreatic^{18–20} cancers.

© 2011 Elsevier Ltd. All rights reserved.

*Corresponding Author: College of Pharmacy, 215 W. Green Street, Rm 220, Athens, GA, 30602-2352, Phone: 706-542-6813, Fax: 706-542-5358, rarnold@rx.uga.edu.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Conflicts of Interest: No conflicts of interest. Financial interests are disclosed in Acknowledgement section.

We, and others, have developed sPLA₂ responsive liposomes (SPRL) with enhanced drug release^{21–24}. sPLA₂-mediated degradation of phospholipids results in the formation of FA and LP; these increase membrane fluidity and result in a transition of the lipid bilayer from a gel-like to a liquid-crystalline phase. Alterations in membrane fluidity are believed responsible for the enhanced diffusion and release of contents entrapped within the aqueous-core of liposomes, however, the complete mechanism is not fully known. Our recent studies have used electrospray ionization mass spectrometry to examine the selectivity of sPLA₂ for various lipids and quantify sPLA₂-mediated degradation of prototype liposomes formulations²⁴. Lipid degradation was correlated to enhanced release of 6-CF, a fluorescent probe. We, and others, have hypothesized that slight modifications of existing lipids or synthesis of novel lipids and lipid-prodrugs could be used to further tune drug release and improve sPLA₂-activity²¹.

The specificity and activity of sPLA₂ is greatest for phospholipids with anionic head groups and shorter FA acyl chains^{25–27}. However, optimal formulations need to balance drug retention properties with their circulation half-life, tissue distribution, and drug release kinetics. The use of high-phase transition, saturated phospholipids with neutral head groups have been shown, in combination with cholesterol (CHOL) and hydrophilic coatings (*e.g.*, polyethylene glycol), to produce long-circulating, sterically-stabilized liposomes (SSL). Unfortunately, the clinical utility of these formulations is limited, in part, because some drugs, such as doxorubicin or vincristine, are entrapped stably and the rate of drug release is slow, whereas for other drugs, such as topotecan or paclitaxel, the rate of release is fast²⁸. The synthesis of novel lipids, based on existing lipids, may allow for the modulation, or tuning, of drug release.

Another challenge associated with evaluating sPLA₂-mediated liposome degradation and drug release is the ability to quantify the degradation of lipids from *in vivo* samples. The majority of lipids used to prepare drug-carriers cannot be separated from similar lipids found endogenously. Therefore, we sought to synthesize and use lipids containing odd FA acyl chain lengths, not commonly found *in vivo*, thus, permitting direct assessment of liposome tissue distribution and their degradation.

The aim of this study was to develop a simple and rapid approach to synthesize glycerophospholipids with *sn*-1 ether and *sn*-2 ester linked FA that could be used to tune drug-release and be identified in biological samples without interference from endogenous lipids. Specifically we synthesized two ether lipids, **1** *1*-*O*-hexadecyl-2-pentadecenyl-*sn*-glycerol-3-phosphocholine (C₃₁PC) and **2** *1*-*O*-hexadecyl-2-pentadecenyl-*sn*-glycerol-3-phosphomethanol (C₃₁PM), and examined their ability to alter enzymatically triggered release of 6-carboxyfluorescein (6-CF) from liposomes incubated in TRIS buffer or fetal bovine serum (FBS) solutions, and evaluated their ability to be identified from lipids found endogenously in plasma.

Using *R*-(*O*)-benzyl glycidol as a starting material, intermediate **6** (Scheme 1) was synthesized²⁹ by a three-step reaction, *i.* regioselective opening of epoxide ring with ether³⁰, *ii.* Steglich esterification to its *sn*-2 position with fatty acid³¹ and *iii.* deprotection reaction of benzyl group using Lewis acid boron tribromide^{25, 32}.

Intermediate **6** was then used as the starting material for the synthesis of both *1*-*O* lipids **1** and **2** (Table 1) by conjugating either phosphocholine or phosphomethanol (Scheme 2). H₂/Pd-C has been used successfully to deprotect the benzyl group, resulting in high product yield. However, this method is limited in that it can only be applied for saturated lipid synthesis. Therefore, we used alternative methods to remove the benzyl group. First chlorosulfonyl isocyanate (CSI) was tried³³, but the result was not desirable. The failure of

this reaction may have resulted from the low selectivity of CSI for ether bonds or the instability of intermediate **6** in the resulting harsh chemical environment, *i.e.*, use of sodium hydroxide and the long reaction time (up to 21 hr). The instability of intermediate **6** is most likely the result of acyl migration that is accelerated at elevated temperatures and the non-neutral pH environment of this reaction. With this in mind, we adapted an existing method using boron tribromide (BBr₃)³³. The reaction was performed at -78°C and was completed in 5 min³². BBr₃ displayed high selectivity over the benzyl ether group, resulting in an almost complete (~100%) formation of **6** from **5**. Furthermore, the short reaction time has also been shown to reduce acyl migration³⁴. The primary drawback of this reaction is the use of large quantities of DCM solvent, *i.e.*, 0.1 g of **5** needs 100 mL of DCM to dissolve at -78°C.

Synthesis of *1-O-hexadecyl-2-pentadenoyl-sn-glycerol-3-phosphocholine* (**1**)³⁵ and *1-O-hexadecyl-2-pentadenoyl-sn-glycerol-3-phosphomethanol* (**2**)³⁶ were completed using the conditions developed by Hirth, G³⁷. Initial purification by chromatography using a TMD-8 resin column and a silica gel column according to the literature did not initially produce a pure product. However, purity was achieved using a gradient method in flash chromatography. It should be mentioned in the preparation of *1-O-hexadecyl-2-pentadenoyl-sn-glycerol-3-phosphomethanol* (**2**) NaHCO₃ was used in place of water because of the resulting formation of the sodium salt form of **2** facilitated purification, compared to its free acid form.

The effect of incorporation of **1** or **2** on the release of 6-CF from prototypical SSL samples (0.05 µmol/mL) was determined in the presence and absence of sPLA₂, as previously described by us²⁴; SSL formulations contained 1,2-distearoyl-*sn*-glycero-3-phosphatidylcholine (DSPC), cholesterol and 1,2-distearoyl-*sn*-glycero-3-phosphoethanolamine-*N*-[poly(ethylene glycol)₂₀₀₀] (DSPC:CHOL:PEG) in a 9:5:1 mole ratio. Incorporation of 10 or 30 lipid mol% of C₃₁PM resulted in enhanced sPLA₂-mediate release of 6-CF compared to SSL formulations (Fig. 2A). Preparations using 90% or 30 lipid mol% C₃₁PC had greater and equal release to those incorporating 10 lipid mol% DSPG (Fig. 2B). DSPG is an anionic lipid that is degraded rapidly by sPLA₂, but results in liposome formulations that display poor drug retention²⁴. Together, these data suggest that shortening of FA acyl chains from C18:0/18:0 to C15:0/16:0, using an ester/ether linked acyl-chains and controlling the percentage of C₃₁PM or C₃₁PC can be used to tune the release from SSL-like formulations. This represents an advancement over the use of other anionic lipids, such as DSPG, that are very sensitive to sPLA₂, but have bulky head groups that decrease their stability and an anionic charge that can reduce the circulation half-life of liposomes.

Serum can alter release from SSL and SPLR formulations²⁴. The effect of 10% (v/v) fetal bovine serum (FBS) on sPLA₂-mediated 6-CF release was determined (Fig. 3). The addition of 10 or 30 mol% of C₃₁PM to SSL formulations reduced the overall rate of 6-CF release compared to SSL formulations in the presence and absence of 10 mol% DSPE (Fig. 3A). This is not unexpected given the higher phase transition (*T*_m 52.2 °C, Table 1) of hydrated C₃₁PM compared to DSPC (49.6 °C). Inclusion of DSPE (10 mol%) was similar to the C₃₁PM (10 mol%). DSPE had the greatest phase transition temperature (74 °C, Table 1), that would be expected to improve membrane stability, but also has a bulkier head group relative the phosphomethanol head group on C₃₁PM. Further, C₃₁PM is anionic, its relatively small head group may be protected from sPLA₂-mediated degradation, relative to other bulkier anionic lipids such as DSPE and DSPG. SSL formulations containing 10 mol% DSPG or 10 mol% C₃₁PC had similar release profiles (Fig 3B). Whereas, incorporation of C₃₁PC at 30 and 90 mol% resulted in a stepwise decrease in 6-CF release, relative to 10 mol % DSPG (Fig 3B). Although the mechanisms underlying these effects are not fully known, DSPG is an anionic lipid with a phase transition of 54.8 °C, Table 1), whereas C₃₁PC is

zwitterionic in nature. Most importantly is that the shorter acyl-chain FA used in **1** and **2** showed concentration dependent alterations in 6-CF release, suggesting that the rate and extent of release may be modulated.

These studies suggest that this approach can be used to synthesize lipids and modulate the release of intra-luminal constituents from liposomes. Although each formulation will have to be tailored to the physicochemical properties of a target drug(s), this approach provides a platform for making lipid modifications based on drug-carrier release kinetics.

Another challenge optimizing lipid based drug-carriers is our ability to track their disposition *in vivo* due to the presence of endogenous lipids. To overcome this challenge we synthesized odd chain lipids, not normally found in nature. Although a variety of fluorescent and radio-labeled probes exist, their effect on membrane fluidity and particulate disposition is not well known and these probes are generally not approved for human use. This is one reason why a goal of this work was to prepare lipids that were multifunctional, *i.e.*, ability to tune release and be identified in biological samples.

SSL formulations in the presence and absence of C₃₁PC (10 mol%) were spiked into rat plasma, extracted using a modified Bligh-Dyer assay³⁸, and lipids were identified *via* their unique ion-pairs by LC/MS/MS using mixed reaction monitoring (MRM) mode as previously described by us²⁴. As expected, analysis of blank plasma demonstrated background levels of ion-pairs corresponding to DSPC (791→608 *m/z*) and C₃₁PC (707→523 *m/z*) (Fig. 4). Spiking of plasma with DSPC (Fig. 4B), C₃₁PC (Fig. 4C) and SSL formulations containing DSPC and C₃₁PC in a 9:1 mole ratio (Fig. 4D) resulted in an increased intensity for peaks corresponding to both ion-pairs. These data suggest that odd-chain lipids, *e.g.*, C₃₁PC, can be identified in rat plasma without interference of endogenous lipids. Further, the presence of a C15:0 FA on C₃₁PC may facilitate the tracking of its degradation and metabolism *in vivo*. Currently, determining liposome degradation *in vivo* is difficult without the use of tracers or radiolabels due to the high endogenous levels of even-chained lipids and their fatty acid metabolites found in biological tissues.

In conclusion a simple approach is presented that permits synthesis of a variety of ether phospholipids from a few intermediates while decreasing acyl migration. We demonstrated the synthesis of two odd-chain ether lipids with a PC or PM head-group could be used to alter drug release. We also demonstrated that the odd chain lipid was able to be identified after extraction from complex biological samples, *e.g.*, plasma. These data suggest that this approach may be used to make slight modifications to existing or creation of novel lipids to tune release of therapeutic agents from lipid based particulate carriers and track their lipids *in vivo*. Further, we believe this approach can be extended to use incorporation of other head groups with functional groups suitable for attaching targeting species (*e.g.*, antibodies or peptides) or imaging probes.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Abbreviations

sPLA ₂	secretory phospholipase A ₂
C ₃₁ PC	1- <i>O</i> -hexadecyl-2-pentadenoyl- <i>sn</i> -glycerol-3-phosphocholine
C ₃₁ PM	1- <i>O</i> -hexadecyl-2-pentadenoyl- <i>sn</i> -glycerol-3-phosphomethanol

ESI-MS	electrospray ionization-mass spectrometry
PC	phosphatidylcholine
PM	phosphatidylmethanol
PG	phosphatidylglycerol
PE	phosphatidylethanolamine
DPPC	1,2-dipalmityl- <i>sn</i> -glycero-3-phosphatidylcholine
DSPC	1,2-distearoyl- <i>sn</i> -glycero-3-phosphatidylcholine
DSPG	1,2-distearoyl- <i>sn</i> -glycerol-3-phosphatidylglycerol
DSPE	1,2-distearoyl- <i>sn</i> -glycero-3-phosphatidylethanolamine
SSL	sterically-stabilized liposome
6-CF	6-carboxyfluorescein
LP	lysophospholipid
FA	fatty acid
DSPE-PEG	1,2-distearoyl- <i>sn</i> -glycero-3-phosphoethanolamine- <i>N</i> -[poly(ethyleneglycol) ₂₀₀₀]
CSI	chlorosulfonyl isocyanate
BBr₃	boron tribromide
DCM	dichloride methylene
THF	tetrahydrofuran
DMF	dimethylformamide
HPLC	high performance liquid chromatography
SPRL	sPLA ₂ responsive liposome

Acknowledgments

We thank Jeremy L Grove, Jennifer A Haley, and Dr. Yang Geng for their technical assistance related to the synthesis. We also thank Dr. Timothy Long for helpful discussions. This research was funded in part by Georgia Cancer Coalition Distinguished Scholar Grants to RDA/BSC, an NIH NIBIB (EB08153) to RDA/BSC, a University of Georgia Graduate Fellowship Stipend Award to GZ, a King Khalid University Fellowship to YA, and an American Foundation for Pharmaceutical Education–Wyeth New Investigator Grant to RDA.

References

1. Drummond DC, Meyer O, Hong KL, Kirpotin DB, Papahadjopoulos D. Pharmacological Reviews. 1999; 51:691. [PubMed: 10581328]
2. Bondurant B, Mueller A, O'Brien DF. Biochim Biophys Acta. 2001; 1511:113. [PubMed: 11248210]
3. Shum P, Kim JM, Thompson DH. Adv Drug Deliv Rev. 2001; 53:273. [PubMed: 11744172]
4. Spratt T, Bondurant B, O'Brien DF. Biochim Biophys Acta. 2003; 1611:35. [PubMed: 12659943]
5. Yatvin MB, Weinstein JN, Dennis WH, Blumenthal R. Science. 1978; 202:1290. [PubMed: 364652]
6. Kong G, Anyarambhatla G, Petros WP, Braun RD, Colvin OM, Needham D, Dewhirst MW. Cancer Res. 2000; 60:6950. [PubMed: 11156395]
7. Needham D, Anyarambhatla G, Kong G, Dewhirst MW. Cancer Res. 2000; 60:1197. [PubMed: 10728674]

8. Huang SL, MacDonald RC. *Biochim Biophys Acta*. 2004; 1665:134. [PubMed: 15471579]
9. Schroeder A, Avnir Y, Weisman S, Najajreh Y, Gabizon A, Talmon Y, Kost J, Barenholz Y. *Langmuir*. 2007; 23:4019. [PubMed: 17319706]
10. Cummings BS, McHowat J, Schnellmann RG. *J Pharmacol Exp Ther*. 2000; 294:793. [PubMed: 10945826]
11. Dong Q, Patel M, Scott KF, Graham GG, Russell PJ, Sved P. *Cancer Lett*. 2006; 240:9. [PubMed: 16182442]
12. Kallajoki M, Alanen KA, Nevalainen M, Nevalainen TJ. *Prostate*. 1998; 35:263. [PubMed: 9609549]
13. Jiang J, Neubauer BL, Graff JR, Chedid M, Thomas JE, Roehm NW, Zhang S, Eckert GJ, Koch MO, Eble JN, Cheng L. *Am J Pathol*. 2002; 160:667. [PubMed: 11839587]
14. Graff JR, Konicek BW, Deddens JA, Chedid M, Hurst BM, Colligan B, Neubauer BL, Carter HW, Carter JH. *Clin Cancer Res*. 2001; 7:3857. [PubMed: 11751475]
15. Yamashita S, Yamashita J, Ogawa M. *Br J Cancer*. 1994; 69:1166. [PubMed: 8198986]
16. Yamashita S, Ogawa M, Sakamoto K, Abe T, Arakawa H, Yamashita J. *Clin Chim Acta*. 1994; 228:91. [PubMed: 7988039]
17. Yamashita S, Yamashita J, Sakamoto K, Inada K, Nakashima Y, Murata K, Saishoji T, Nomura K, Ogawa M. *Cancer*. 1993; 71:3058. [PubMed: 8490834]
18. Kiyohara H, Egami H, Kako H, Shibata Y, Murata K, Ohshima S, Sei K, Suko S, Kurano R, Ogawa M. *Int J Pancreatol*. 1993; 13:49. [PubMed: 8384235]
19. Kuopio T, Ekfors TO, Nikkanen V, Nevalainen T. *J. Apmis*. 1995; 103:69.
20. Oka Y, Ogawa M, Matsuda Y, Murata A, Nishijima J, Miyauchi K, Uda K, Yasuda T, Mori T. *Enzyme*. 1990; 43:80. [PubMed: 1702053]
21. Jensen SS, Andresen TL, Davidsen J, Hoyrup P, Shnyder SD, Bibby MC, Gill JH, Jorgensen K. *Molecular Cancer Therapeutics*. 2004; 3:1451. [PubMed: 15542784]
22. Davidsen J, Vermehren C, Frokjaer S, Mouritsen OG, Jorgensen K. *International Journal of Pharmaceutics*. 2001; 214:67. [PubMed: 11282239]
23. Linderöth L, Peters GH, Jorgensen K, Madsen R, Andresen TL. *Chemistry and Physics of Lipids*. 2007; 146:54. [PubMed: 17270166]
24. Zhu G, Mock JN, Aljuffali I, Cummings BS, Arnold RD. *J Pharm Sci*. 2011; 100:3146. [PubMed: 21455978]
25. Andresen TL, Davidsen J, Begtrup M, Mouritsen OG, Jorgensen K. *J Med Chem*. 2004; 47:1694. [PubMed: 15027860]
26. Andresen TL, Jensen SS, Kaasgaard T, Jorgensen K. *Curr Drug Deliv*. 2005; 2:353. [PubMed: 16305438]
27. Jensen SS, Andresen TL, Davidsen J, Hoyrup P, Shnyder SD, Bibby MC, Gill JH, Jorgensen K. *Mol Cancer Ther*. 2004; 3:1451. [PubMed: 15542784]
28. Drummond DC, Noble CO, Hayes ME, Park JW, Kirpotin DB. *Journal of Pharmaceutical Sciences*. 2008; 97:4696. [PubMed: 18351638]
29. A syringe-septum technique was used for moisture-sensitive reactions. THF was prepared freshly by distilling with sodium and benzophenone ketyl. Other solvents like DFM, D., Et₃N, and pyridine were mixed with 3 Å molecular sieves before use. Reagents were purchased from Sigma-Aldrich Chemical Co. and used without further purification. Silica gel (35–70 µm, 200–430 mesh) was used for column chromatography. Products were visualized on TLC using either iodine vapor or Hanessian's stain method. Low resolution MS was obtained on a HPLC-LC/MSD trap XCT Ultra Plus system (Agilent), high resolution MS was obtained on a LCT Premier Orthogonal Acceleration TOF Mass Spectrometer and 400 MHz ¹H NMR spectra were used for chemical identifications. A Mettler Toledo DSC 1 Star System was used to determine melting temperature of DSPC, DPPC, and products **1** and **2**. DSPC, DSPG, DSPE, and DSPE-PEG were purchased from Avanti Polar Lipids Inc. (Alabaster, USA). sPLA2 was purchased from Cayman Chemical Company (Ann Arbor, MI) and Genway Biotech Inc (San Diego, CA). F-12k cell culture media and FBS were purchased from Hyclone (Rockford, Illinois). CHOL was purchased from Sigma-Aldrich (St. Louis, Missouri). Acetonitrile and methanol were of HPLC grade from Fisher Scientific (Pittsburgh, PA). All other chemicals and solvents were of analytical grade, obtained

from commercial sources and used without further purification. All experiments used ultrapure water ($> 3\text{M}\Omega$) obtained from a Millipore Milli-Q synthesis system (Billerica, MA).

30. Synthesis of **4** was initiated by washing a dispersion of NaH (0.0765 g, 3.20 mmol) in (60% mineral oil) using a 50 mL N_2 protected flask with dry petroleum ether (20 mL $\times 3$)²⁸. Cetyl alcohol (0.74 g, 3.05 mmol) was added followed by dry THF (10 mL) at 0°C. The reaction mixture was refluxed at 80°C for 1 h. (*R*)-*O*-benzyl glycidol (**3**) (0.25 g, 1.53 mmol) was added followed by addition of DMF (25 mL) drop-wise over 5 min. The reaction mixture was stirred overnight at 80°C. The mixture was cooled to room temperature and the reaction stopped by addition of water (2.5 mL) and solvents removed under vacuum. The residue was dissolved with diethyl ether, washed in brine 3 times and dried over Na_2SO_4 . The product was purified using two rounds of column chromatography using ether/DCM (1:4) then ether/hexane (1:1). **1-O-hexadecyl-3-O-benzyl-sn-glycerol (4)** has a *R_f* 0.31 (ether/hexane 1:4), ^1H NMR (400 MHz, CDCl_3): δ 7.35 (m, 5H, Ph), δ 4.57 (s, 2H, CH_2Ph), δ 4.00 (quintet, 1H, CH), δ 3.52 (m, 6H, CH_2CHCH_2 , O- CH_2), δ 1.73 (s, OH), δ 1.57 (quintet, 2H, β - CH_2), δ 1.26 (br, s, 26H, $13\times\text{CH}_2$), δ 0.887 (t, 3H, CH_3), and ESI-MS⁺ of 407.1 *m/z* (MW=406.3).
31. Three g of **4** (7.4 mmol), g. p. a. m., 0.17 g DMAP (1.48 mmol), 150 mL DCM and 3.1 g DCC (14.8 mmol) were added to a flame-dried, N_2 protected 250 mL flask. The reaction was cooled to 0°C for 15 min and allowed to stand at room temperature for 24 hr. The reaction was stopped by adding 5 mL acetic acid and stirred for 0.5 hr. The sample was stored at a -20°C overnight and the resulting precipitate removed by filtering. The solvent was evaporated and the resulting residues were dissolved in EtOAc, washed with 1 M HCl (30 mL $\times 3$), sat. NaHCO_3 (30 mL $\times 3$), brine (30 mL $\times 3$) and dried over Na_2SO_4 . The intermediate **5** was purified using column chromatography using petroleum ether/DCM (1:4) as a mobile phase. Product yield was 69%. **1-O-hexadecyl-2-pentadenoyl-3-O-benzyl-glycerol (5)** has a *R_f* 0.25 (petroleum ether/DCM 1:4), a 631.3 *m/z* (MW=630.5) by ESI-MS and ^1H NMR (400 MHz, CDCl_3): δ 7.33 (m, 5H, Ph), δ 5.18 (quintet, 1H, CH), δ 4.54–4.56 (AB, 2H, CH_2Ph), δ 3.63 (d, 2H, CH_2CHCH_2), δ 3.58 (d, 2H, CH_2CHCH_2), δ 3.42 (m, 2H, $\text{OCH}_2\text{C}_{15}\text{H}_{31}$), δ 2.34 (t, 2H, CH_2COO), δ 1.62 (quintet, 2H, β - CH_2), δ 1.53 (quintet, 2H, β - CH_2), δ 1.26 (br, s, 48H, $24\times\text{CH}_2$), δ 0.887 (t, 6H, $\text{CH}_3\times 2$), and ESI-MS⁺ of 631.3 *m/z* (MW=630.5).
32. Intermediate **5** (0.2 g, 0.32 mmol) was added to a flame-dried, N_2 protected 250 mL flask with 200 mL DCM. The flask was bathed into a mixture of dry ice and acetone, which produced a temperature of -78°C. BBr_3 (1 M BBr_3 in DCM, 0.64 mmol) was injected into the flask and allowed to stand for 5 min. The reaction was quenched with 20 mL sat. NaHCO_3 and 20 mL diethyl ether. The solvent was then washed with saturated NaHCO_3 (30 mL $\times 3$), water (30 mL $\times 3$), brine (30 mL $\times 3$) and dried over Na_2SO_4 . Product **6** was concentrated under vacuum yielding a crude white solid. **1-O-hexadecyl-2-pentadenoyl-sn-glycerol (6)** had a *R_f* 0.71 (DCM/diethyl ether, 10:1), ^1H NMR (400 MHz, CDCl_3): δ 5.00 (quintet, 1H, CH), δ 3.81 (d, 2H, CH_2CHCH_2), δ 3.63 (m, 2H, CH_2CHCH_2), δ 3.45 (m, 2H, $\text{OCH}_2\text{C}_{15}\text{H}_{31}$), δ 2.36 (t, 2H, CH_2COO), δ 1.63 (quintet, 2H, β - CH_2), δ 1.56 (quintet, 2H, β - CH_2), δ 1.26 (br, s, 48H, $24\times\text{CH}_2$), δ 0.886 (t, 6H, $\text{CH}_3\times 2$), and ESI-MS⁺ of 541.3 *m/z* (MW=540.9).
33. Kim JD, Han G, Zee OP, Jung YH. Tetrahedron Letters. 2003; 44:733.
34. Pluckthun A, Dennis EA. Biochemistry. 1982; 21:1743. [PubMed: 7082643]
35. To a flame-dried, N. p. m. f., first 18 μL POCl_3 (0.19 mmol) and 1.5 mL DCM were added. Then 3 mL DCM with 27 μL Et_3N (0.19 mmol) and **6** (0.16 mg, 0.14 mmol) were added to the flask drop-wise over 20 min. This mixture was stirred for 1 hr at room temperature. After this, 0.2 mL pyridine (1.2 mmol) and 128 mg choline tosylate (0.223 mmol) were added. The reaction was allowed to stand for 24 hr at room temperature. 0.2 mL water was added to quench the reaction. The reaction mixture was concentrated and then passed through a TMD-8 resin column using THF/ H_2O (9:1) as mobile phase. The resulting crude product was purified on a silica gel column using three mobile phases in a row (100 mL DCM: MeOH=85:15, 200 mL MeOH and then 100 mL DCM: MeOH: H_2O , 65:25:4). Product yield (from **5** to **1**, two steps) was 42%. **1-O-hexadecyl-2-pentadenoyl-sn-glycerol-3-phosphocholine (1)** has a *R_f* 0.35 (DCM: MeOH: H_2O , 65:25:4), ^1H NMR (400 MHz, CDCl_3): δ 5.13 (quintet, 1H, CH), δ 4.36 (s, 2H, $\text{POCH}_2\text{CH}_2\text{N}^+$), δ 3.98 (m, 2H, CH_2CHCH_2), δ 3.88 (s, 2H, $\text{POCH}_2\text{CH}_2\text{N}^+$), δ 3.55 (m, 4H, CH_2CHCH_2 , $\text{OCH}_2\text{C}_{15}\text{H}_{31}$), δ 3.44 (s, 9H, $\text{N}^+(\text{CH}_3)_3$), δ 2.32 (t, 2H, CH_2COO), δ 1.60 (quintet, 2H, β - CH_2),

σ 1.53 (quintet, 2H, β -CH₂), σ 1.26 (br, s, 48H, 24 $\times$ CH₂), σ 0.887 (t, 6H, CH₃ $\times$ 2), and HRMS via TOF ES MS+ 706.5803 m/z (MW=706.0).

36. To a solution of MOPOCL (3.4 mmol) and TMP (1.82 mmol) in dried toluene (2 mL) under N₂ protected at -20°C , 0.4 g of **6** (0.74 mmol) in toluene (10mL) was added drop wise. This mixture was stirred for 24 hr at room temperature. After this, 2 mL saturated NaHCO₃ was added and stirred for 2 hr. This reaction mixture was concentrated by azeotropic distillation (with ethanol and toluene). The resulting crude product was purified on a silica gel column (DCM:MeOH, 4:1). Product yield (from **5** to **2**, two steps) was 40%. **1-O-hexadecyl-2-pentadenoyl-sn-methanol-3-phosphocholine (2)** has a R_f 0.4 (DCM:MeOH=4:1), ¹H NMR (400 MHz, CDCl₃): σ 5.18 (quintet, 1H, CH), σ 4.00 (d, 2H, CH₂CHCH₂), σ 3.61-3.57 (m, 5H, CH₂CHCH₂, POCH₃), σ 3.40 (m, 2H, OCH₂C₁₅H₃₁), σ 2.32 (t, 2H, CH₂COO), σ 1.60 (quintet, 2H, β -CH₂), σ 1.52 (quintet, 2H, β -CH₂), σ 1.26 (br, s, 48H, 24 $\times$ CH₂), σ 0.887 (t, 6H, CH₃ $\times$ 2), and TOF MS+, 657.5034 m/z , M+Na⁺ adduct (MW=633.5).
37. Hirth G, Barner R. Helvetica Chimica Acta. 1982; 65:1059.
38. Bligh EG, Dyer WJ. Canadian Journal of Biochemistry and Physiology. 1959; 37:911. [PubMed: 13671378]

Fig. 1.
Structure of ether lipids

Fig. 2. sPLA₂-mediated release of 6-CF from **A.** prototype SSL and C₃₁PM (10 and 30 mol%) modified SSL and **B.** C₃₁PC (100 or 30 mol%) and DSPG (10 mol%) modified SSL formulations. Liposome samples were treated with 0 (control) or 2.5 μ g/mL sPLA₂ for 0 to 48 hr at 25°C in TRIS buffer (pH 7.4) and 6-CF release was determined by quantifying fluorescent at an excitation wavelength of 480 nm and an emission intensity at 510 nm. Data are represented as the mean $\pm$ SEM of a least 3 separate experiments, (n=5/study).

Fig. 3.

Effect of 10% fetal bovine serum on sPLA₂-mediated 6-CF release from **A.** SSL, and DSPE (10 mol%) and C₃₁PM (10 and 30 mol%) modified SSL formulations and **B.** C₃₁PC (10, 30, and 90 mol%) and DSPG (10 mol%) modified SSL. The effect of serum on sPLA₂-mediated release of 6-CF from formulations was determined over 216 hr at 37 °C by quantifying fluorescent at an excitation wavelength of 480 nm and an emission intensity at 510 nm. Data are represented as the mean ± SEM of a least 3 separate experiments.

Fig. 4.

Mass spectra of blank rat plasma **A.** or plasma spiked DSPC **B.**, P_{31} PC **C.** or SSL formulation containing DSPC and C_{31} PC in a 9:1 mole ratio **D.** DSPC (791→608 m/z) and C_{31} PC (707→523 m/z) were identified based on their ion-pair as determined using MRM.

Scheme 1.

Synthesis of intermediate 6

(a) R¹OH, NaH, THF, DMF, 16 hr, 80°C(b) R²COOH, DCC, DMAP, DCM, 24 hr, room temperature(c) BBr₃, DCM, 5 min, -78°C

Scheme 2.

Synthesis of products 1 and 2

(a) (i) $POCl_3$, Et_3N , DCM, 1 hr, room temperature; (ii) pyridine, choline tosylate, 16 hr, room temperature; (iii) H_2O , 1 hr

(b) (i) $MeOPOCl_2$, TMP, 24 hr, room temperature; (ii) sat. $NaHCO_3$, 2 hr

Table 1Structures of existing and novel sPLA₂-targeted ether lipids.

Compound	R ¹ (linkage)	R ² (linkage)	R ³	T _m °C*
DSPC	18:0 (ester)	18:0 (ester)	Choline	49.6
DPPC	16:0 (ester)	16:0 (ester)	Choline	38.9
DSPE	18:0 (ester)	18:0 (ester)	Ethanolamine	74.3
DSPG	18:0 (ester)	18:0 (ester)	Glycerol	54.8
1	16:0 (ester)	15:0 (ester)	Choline	34.4
2	16:0 (ether)	15:0 (ester)	Methanol	52.2

(1) *1-O-C₃₁PC*; (2) *1-O-C₃₁PM*,* T_m was determined using individual lipids hydrated in dd-water at 40 mM.