Dynamic Compressive Loading Enhances Cartilage Matrix Synthesis and Distribution and Suppresses Hypertrophy in hMSC-Laden Hyaluronic Acid Hydrogels

Liming Bian, Ph.D.,¹ David Y. Zhai, B.S.E.,¹ Emily C. Zhang,¹
Robert L. Mauck, Ph.D.,^{1,2} and Jason A. Burdick, Ph.D.¹

Mesenchymal stem cells (MSCs) are being recognized as a viable cell source for cartilage repair, and there is growing evidence that mechanical signals play a critical role in the regulation of stem cell chondrogenesis and in cartilage development. In this study we investigated the effect of dynamic compressive loading on chondrogenesis, the production and distribution of cartilage specific matrix, and the hypertrophic differentiation of human MSCs encapsulated in hyaluronic acid (HA) hydrogels during long term culture. After 70 days of culture, dynamic compressive loading increased the mechanical properties, as well as the glycosaminoglycan (GAG) and collagen contents of HA hydrogel constructs in a seeding density dependent manner. The impact of loading on HA hydrogel construct properties was delayed when applied to lower density (20 million MSCs/ml) compared to higher seeding density (60 million MSCs/ml) constructs. Furthermore, loading promoted a more uniform spatial distribution of cartilage matrix in HA hydrogels with both seeding densities, leading to significantly improved mechanical properties as compared to free swelling constructs. Using a previously developed *in vitro* hypertrophy model, dynamic compressive loading was also shown to significantly reduce the expression of hypertrophic markers by human MSCs and to suppress the degree of calcification in MSC-seeded HA hydrogels. Findings from this study highlight the importance of mechanical loading in stem cell based therapy for cartilage repair in improving neocartilage properties and in potentially maintaining the cartilage phenotype.

Introduction

MESENCHYMAL STEM CELLS (MSCs) have emerged as a clinically relevant cell source for regenerative medicine, particularly for cartilage repair. MSCs undergo chondrogenesis and deposit a cartilage specific matrix in pellet cultures and in a variety of natural and synthetic scaffold materials in the presence of the appropriate growth factors.^{1–3} Mechanical signals have been identified as one of the key factors regulating embryonic limb development and adult musculoskeletal repair. More specifically, the rate of cartilage formation, mechanical properties, and cartilage matrix content of the formed cartilage is significantly reduced in immobilized embryos.^{4,5} As cartilage matures with load bearing use, matrix content and crosslinking increases substantially;^{6,7} however, these properties fail to increase when the tissue is removed from the load bearing environment.⁸ Previous studies have established that mechanical loading not only regulates the normal maintenance of articular cartilage *in vivo*^{9,10} and *in vitro*^{11–15} but also promotes cartilage matrix biosynthesis.^{16,17} Furthermore, recent studies have demonstrated that dynamic compression can enhance the

expression of chondrogenic markers and cartilage matrix synthesis by MSCs encapsulated in various scaffold materials, including agarose,¹⁸ alginate,¹⁹ and fibrin gels.²⁰

Previously, we demonstrated that the natural polysaccharide hyaluronic acid (HA) provides a stable 3D environment that is conducive to MSC chondrogenesis when processed into hydrogel form.^{21,22} We also showed that hydrogel crosslink density controls the distribution of cartilage matrix, with a lower density leading to more uniform matrix²³ and that the controlled degradation of HA hydrogels could be used to modulate tissue distribution, as degradation opens up molecular porosity to allow for produced matrix to distribute throughout the hydrogel.²² Beyond tailoring the hydrogel component, recent studies also showed that mechanical loading promotes improved matrix distribution in engineered cartilage with an MSC-seeded agarose scaffold, leading to improved mechanical properties.²⁴ Likewise, the MSC seeding density influences MSC chondrogenesis,^{25,26} with higher seeding densities and transient transforming growth factor (TGF) exposure improving properties in agarose and HA gels.²⁷ Therefore, it is of great interest to evaluate the effect of dynamic compressive loading on MSC

¹Department of Bioengineering, University of Pennsylvania, Philadelphia, Pennsylvania.

²McKay Orthopedic Research Laboratory, Department of Orthopedic Surgery, University of Pennsylvania, Philadelphia, Pennsylvania.

chondrogenesis and cartilage matrix production and distribution in HA scaffolds, in an attempt to improve overall neocartilage properties towards clinical utility.

While MSCs form cartilage-like tissue *in vitro* under chondrogenic induction with TGF- β s, and this transformation may be improved by dynamic loading and increased seeding density, transplantation to the uncontrolled *in vivo* environment commonly results in extensive calcification of the formed ECM.^{28–30} For example, we recently showed, using alginate microsphere delivery of TGF- β 3, and direct subcutaneous implantation of human MSC seeded HA gels, considerable ectopic mineralization within 4 weeks.³⁰ Another recent study reported that the delivery of TGF- β 1 with MSCs results in increased subchondral trabecular bone formation in a rabbit osteochondral repair site.³¹ Mechanical signals may impact MSC transition to an osteogenic phenotype; loading regulates growth plate and articular chondrocyte hypertrophy via the IHH-PTHrP (India hedgehog, parathyroid hormone-related protein) pathway.^{32–35} However, it is difficult to accurately assess the effect of mechanical loading on hypertrophic differentiation of MSCs *in vivo*. A recent study demonstrated that MSC hypertrophy can be induced *in vitro* by withdrawing transforming growth factor beta 3 (TGF- β 3), reducing the concentration of dexamethasone, and adding thyroid hormone (T3), providing a simplified *in vitro* model to study MSC hypertrophy.³⁶ Therefore, the second objective of this study was to investigate the effect of dynamic compressive loading on the hypertrophic conversion of chondrogenic human MSCs in HA. Findings from this study provide important insight into stem cell based therapy for cartilage repair and regeneration.

Material and Methods

Macromer synthesis

Methacrylated HA (MeHA) was synthesized as previously reported.³⁷ Briefly, methacrylic anhydride (methacrylic anhydride, 94%, FW: 154.17, Sigma-Aldrich, Haverhill, MA) was added to a solution of 1 wt% HA (sodium hyaluronate powder, research grade, MW ~74 kDa, Lifecore, Chaska, MN) in deionized water, adjusted to a pH of 8 with 5 N NaOH, and reacted on ice for 24 h. The macromer solution was purified via dialysis (MW cutoff 6–8 k) against deionized water for a minimum of 48 h with repeated changes of water. The final product was obtained by lyophilization, and stored at -20°C in powder form prior to use. The final macromer products were confirmed by ^1H NMR to have a methacrylation of ~27%. Lyophilized MeHA (1.5 wt%) was dissolved in phosphate buffered saline (PBS) containing 0.05 wt% 2-methyl-1-[4-(hydroxyethoxy) phenyl]-2-methyl-1-propanone (I2959, Ciba) for polymerization.

Sample preparation and *in vitro* culture

Human MSCs (Lonza, Basel, Switzerland) were expanded to passage 3 in growth media consisting of α -MEM with 16.7% FBS and 1% pen/strep. MSCs (20 or 60 million cells/ml) were photoencapsulated in 1.5 wt% MeHA hydrogel disks ($\varnothing$ 5 mm, 2.6 mm thickness) and cultured in chondrogenic medium (DMEM, 1% ITS+ Premix, 50 $\mu\text{g}/\text{ml}$ L-proline, 0.1 μM dexamethasone, 0.9 mM sodium pyruvate, penicillin/streptomycin, 50 $\mu\text{g}/\text{ml}$ ascorbate) supplemented with 10 ng/

ml TGF- β 3 (R&D Systems, Minneapolis, MN), which was changed three times per week.³⁸ To induce hypertrophy, constructs were first cultured in chondrogenic media for 2 weeks. Media was then switched to hypertrophic induction media (+ T3: 1 nM dexamethasone, 1 nM triiodothyronine [T3] and 10 mM β -glycerophosphate [β -gly]) or control media ($-$ T3: without T3 or β -gly) from day 15 until day 30 of culture.³⁶ Hypertrophic cultures were maintained as free swelling (FS) or exposed to dynamic loading conditions (DL), as described below. Cell viability was assessed using the LIVE/DEAD Assay Kit (Invitrogen, Carlsbad, CA), where live cells are stained green with calcein-AM and dead cells stained red with ethidium homodimer.

Mechanical loading

Compressive loading was applied as described previously.^{39,40} Briefly, the loading protocol consisted of a 10% peak compressive sinusoidal strain at 1 Hz frequency, superimposed on a 5% compressive tare strain. Loading was carried out in unconfined compression via impermeable loading platens, for 4 hours/day and 5 days/week. Dynamic compressive loading (DL) was carried out at 37°C and 5% CO_2 in a humidified incubator. FS control cultures were positioned adjacent to the loading device during this period. DL was applied starting from day 3 and continued until the end of the study.

Mechanical testing

At set time points, samples were removed from the culture and the bulk mechanical properties of constructs were evaluated using a custom table top testing device as described previously.⁴¹ Briefly, samples were first equilibrated in creep to a tare load of 2 g by an impermeable loading platen in a loading chamber filled with PBS. From this offset, stress relaxation tests were performed with a single compression ramp at a speed of 10%/min until reaching 10% strain. The equilibrium Young's modulus (E_y) was determined by the equilibrium load obtained after 1000 sec of relaxation under unconfined compression at 10% strain.

Gene expression analysis

For gene expression analysis, samples were homogenized in Trizol Reagent (Invitrogen) with a tissue grinder, RNA was extracted according to the manufacturer's instructions, and the RNA concentration was determined using an ND-1000 spectrophotometer (Nanodrop Technologies, Wilmington, DE). One microgram of RNA from each sample was reverse transcribed into cDNA using reverse transcriptase (Superscript II, Invitrogen) and oligoDT (Invitrogen). Polymerase chain reaction (PCR) was performed on an Applied Biosystems 7300 real-time PCR system using Taqman primers and probes specific for GAPDH (glyceraldehyde-3-phosphate dehydrogenase, housekeeping gene) and other genes of interest. Sequences of the primers and probes used are listed in Table 1. The relative gene expression was calculated using the $\Delta\Delta C_T$ method, where fold difference was calculated using the expression $2^{\Delta\Delta C_T}$. Each sample was internally normalized to GAPDH, and each group was normalized to the expression levels of MSCs at the time of encapsulation (i.e., after expansion and before differentiation). Relative

TABLE 1. SEQUENCES OF PRIMERS AND PROBES USED FOR REAL-TIME PCR; SEQUENCES RELATED TO GENE TYPE X COLLAGEN ARE PROPRIETARY TO APPLIED BIOSYSTEMS INC. AND WERE NOT DISCLOSED

Gene	Forward primer	Reverse primer	Probe
GAPDH	AGGGCTGCTTTTAACTCTGGTAAA	GAATTTGCCATGGGTGGAAT	CCTCAACTACATGGTTTAC
COL I	AGGACAAGAGGCATGTCTGGTT	GGACATCAGGCGCAGGAA	TTCCAGTTCGAGTATGGC
COL II	GGCAATAGCAGGTTACGTACA	CGATAACAGTCTTGCCCCACTT	CTGCACGAAACATAC
Aggrecan	TCGAGGACAGCGAGGCC	TCGAGGGTGTAGCGTGTAGAGA	ATGGAACACGATGCCTTTCACCACGA

PCR, polymerase chain reaction, GAPDH, glyceraldehyde-3-phosphate dehydrogenase; COL, collagen.

expression levels greater than 1 represent up-regulation with culture, while relative expression levels less than 1 represent down-regulation of that gene compared to that of initially encapsulated MSCs.

Biochemical analysis

One-half of each construct was weighed wet, lyophilized, reweighed dry, and digested in 0.5 mg/ml Proteinase-K (Fisher Scientific, Hampton, NH) at 56°C for 16 h. The PicoGreen assay (Invitrogen) was used to quantify the DNA content of the constructs with lambda phage DNA (0–1 mg/ml) as a standard.⁴² For each sample, both the mass of the entire gel and the half gel used for the DNA assay were measured. The total amount of deoxyribonucleic acid (DNA) per sample was calculated by scaling the amount of DNA detected in the half gel by a weight ratio (total weight/half weight). The glycosaminoglycan (GAG) content was measured using the dimethylmethylene blue (DMMB, Sigma-Aldrich) dye-binding assay with shark chondroitin sulfate (0–50 mg/ml) as a standard.⁴³ The overall collagen content was assessed by measuring the orthohydroxyproline (OHP) content via dimethylaminobenzaldehyde and chloramine T assay. Collagen content was calculated by assuming a 1:7.5 OHP-to-collagen mass ratio.⁴⁴ The collagen and GAG contents were normalized to the disk wet weight. Calcium content was quantified using a commercial kit (BioVision, San Francisco, CA).

Histological analysis

The remaining halves of the constructs were fixed in 4% formalin for 24 h, embedded in paraffin, and processed using standard histological procedures. The histological sections (8 µm thick) were stained with alcian blue (pH=1.0) (proteoglycans) or picrosirius red (collagen), or were immunostained for targets of interest using the Vectastain ABC and DAB Substrate kits (Vector Labs, Burlingame, CA). Briefly, sections were predigested in 0.5 mg/ml hyaluronidase for 30 min at 37°C and incubated in 0.5 N acetic acid for 4 h at 4°C to swell the samples prior to overnight incubation

with primary antibodies at dilutions of 1:100, 1:200, and 1:3 for chondroitin sulfate (mouse monoclonal anti-chondroitin sulfate, Sigma-Aldrich), and type I (mouse monoclonal anti-collagen type 1, Sigma-Aldrich) and type II collagen antibodies (mouse monoclonal anti-collagen type II, Developmental Studies Hybridoma Bank, Iowa City, IA), respectively. Non-immune controls underwent the same procedure without primary antibody incubation.

Statistical analysis

All data are presented as mean ± standard deviation. Statistica (Statsoft, Tulsa, OK) was used to perform statistical analyses using two-way analysis of variance (ANOVA) and Tukey's honestly significant difference (HSD) post hoc test of the means ($n=4$ samples per group) with culture duration and experimental groups as independent factors.

Results and Discussion

Effect of dynamic compression on cartilage matrix production by MSCs in HA hydrogels

After 70 days of culture under either FS or DL conditions, MSCs encapsulated at both low (20 million cells/ml) and high (60 million cells/ml) seeding densities remained highly viable (>95%) (Fig. 1). While there were no differences between groups at day 30, by day 70 DL constructs seeded at a low density (20DL) exhibited significant increases in Young's modulus (28.3 ± 7.8 kPa vs. 8.2 ± 3.0 kPa), dynamic modulus (467 ± 62 kPa vs. 225 ± 22 kPa), GAG ($1.2 \pm 0.1\%$ vs. $0.7 \pm 0.2\%$) and collagen content ($1.3 \pm 0.2\%$ vs. $0.8 \pm 0.2\%$) compared to the free swelling (20FS) group (FIG. 2 A, B, C, D; Table 2). In contrast, in higher seeding density conditions (60DL), loading significantly increased the Young's modulus (32.0 ± 5.3 kPa vs. 12.4 ± 3.8 kPa), dynamic modulus (476 ± 56 kPa vs. 329 ± 93 kPa), GAG ($1.5 \pm 0.1\%$ vs. $1.1 \pm 0.2\%$) and collagen content ($0.9 \pm 0.2\%$ vs. $0.5 \pm 0.1\%$) at day 30 compared to free swelling construct (60FS). By day 70, constructs continued to increase in each of these parameters, but DL showed no

FIG. 1. Viability staining of mesenchymal stem cells (MSCs) seeded at 20 or 60 million cells/ml in hyaluronic acid (HA) hydrogels after 70 days of *in vitro* culture under free swelling (FS) or dynamic loading (DL) culture conditions. Green: live cells. Red: dead cells. Scale bar = 100 µm. Color images available online at www.liebertonline.com/tea

FIG. 2. Young's modulus (A), dynamic modulus (1Hz) (B), glycosaminoglycan (GAG) (C) and collagen (D) contents normalized to wet weight (w.w.), and GAG (E) and collagen (F) contents normalized to DNA (ng/ng). 20/60FS: constructs seeded with 20 or 60 million cells/ml and cultured under free swelling conditions; 20/60DL: constructs seeded with 20 or 60 million cells/ml and cultured under dynamic loading conditions, * $p < 0.05$ vs. FS group at the same culture time ($n = 4$), † $p < 0.05$ vs. 20FS/DL group at the same culture time ($n = 4$).

impact at this later time point (Fig. 2 A, B, C, D; Table 2). On day 30, constructs at both MSC densities in free swelling condition (20FS, 60FS) had similar mechanical properties and biochemical content, whereas these parameters were statistically higher for the high density free swelling group

(60FS) on day 70 (E_Y : 55.5 ± 8.3 kPa vs. 8.2 ± 3.0 kPa; dynamic modulus: 671 ± 87 kPa vs. 225 ± 22 kPa; GAG: $2.3 \pm 0.4\%$ vs. $0.7 \pm 0.2\%$; collagen: $1.7 \pm 0.2\%$ vs. $0.8 \pm 0.2\%$) (Fig. 2 A, B, C, D; Table 2). Under FS condition the high seeding density group (60FS) had lower GAG (31.7 ± 10.1 vs. 72.2 ± 6.2) and

TABLE 2. YOUNG'S MODULUS (E_Y), DYNAMIC MODULUS (1Hz), GLYCOSAMINOGLYCAN (GAG) AND COLLAGEN CONTENTS NORMALIZED TO WET WEIGHT (w.w.); AND GAG AND COLLAGEN CONTENTS NORMALIZED TO DNA (ng/ng); AND CONSTRUCT VOLUME NORMALIZED TO INITIAL VOLUME ON DAY 0; 20/60FS: CONSTRUCTS SEEDDED WITH 20 OR 60 MILLION CELLS/ML AND CULTURED UNDER FREE SWELLING (FS) CONDITIONS; 20/60DL: CONSTRUCTS SEEDDED WITH 20 OR 60 MILLION CELLS/ML AND CULTURED UNDER DYNAMIC LOADING (DL) CONDITIONS

		20FS	20DL	60FS	60DL
E_Y (kPa)	Day 30	6.3 ± 0.7	11.8 ± 3.3	12.4 ± 3.8	$32.0 \pm 5.3^{*†}$
	Day 70	8.2 ± 3.0	$28.3 \pm 7.8^*$	$55.5 \pm 8.3^\dagger$	$59.2 \pm 8.5^\dagger$
Dynamic modulus (kPa)	Day 30	190 ± 28	218 ± 14	329 ± 93	$476 \pm 56^{*†}$
	Day 70	225 ± 22	$467 \pm 62^*$	$671 \pm 87^\dagger$	$758 \pm 106^\dagger$
GAG/w.w.	Day 30	$0.8 \pm 0.1\%$	$0.8 \pm 0.1\%$	$1.1 \pm 0.2\%$	$1.5 \pm 0.1\%^{*†}$
	Day 70	$0.7 \pm 0.2\%$	$1.2 \pm 0.1\%^*$	$2.3 \pm 0.4\%^\dagger$	$2.1 \pm 0.2\%^\dagger$
Collagen/w.w.	Day 30	$0.3 \pm 0.0\%$	$0.3 \pm 0.0\%$	$0.5 \pm 0.1\%$	$0.9 \pm 0.2\%^{*†}$
	Day 70	$0.8 \pm 0.2\%$	$1.3 \pm 0.2\%^*$	$1.7 \pm 0.2\%^\dagger$	$1.6 \pm 0.2\%^\dagger$
GAG/DNA	Day 30	72.2 ± 6.2	76.5 ± 12.8	$31.7 \pm 10.1^\dagger$	$53.0 \pm 5.0^*$
	Day 70	62.3 ± 19.9	$105.7 \pm 4.9^*$	79.5 ± 18.6	89.9 ± 14.3
Collagen/DNA	Day 30	28.0 ± 3.8	31.3 ± 4.6	$15.7 \pm 2.7^\dagger$	$30.1 \pm 7.9^*$
	Day 70	90.8 ± 11.8	109.5 ± 18.8	58.3 ± 5.9	$67.7 \pm 10.0^\dagger$
Normalized volume	Day 30	$130.5 \pm 2.3\%$	$124.9 \pm 7.5\%$	$115.0 \pm 7.1\%^\dagger$	$119.6 \pm 5.7\%$
	Day 70	$118.9 \pm 4.2\%^{\dagger}$	$108.6 \pm 1.1\%^{*†}$	$109.4 \pm 8.7\%$	$114.8 \pm 11.5\%$

* $p < 0.05$ vs. FS group at the same culture time ($n = 4$), † $p < 0.05$ vs. 20FS/DL group at the same culture time ($n = 4$), ‡ $p < 0.05$ vs. 20FS/DL group on Day 30 ($n = 4$). Data presented as mean $\pm$ standard deviation.

collagen (15.7 ± 2.7 vs. 28.0 ± 3.8) contents per cell than the low seeding density group (20FS) on day 30, but not on day 70 (Fig. 2 E, F; Table 2). DL significantly increased the GAG (day 30: 60FS @ 31.7 ± 10.1 vs. 60DL @ 53.0 ± 5.0 ; day 70: 20FS @ 62.3 ± 19.9 vs. 20DL @ 105.7 ± 4.9) and collagen (day 30: 60FS @ 15.6 ± 2.7 vs. 60DL @ 30.1 ± 7.9 ; day 70: 20FS @ 90.8 ± 11.8 vs. 20DL @ 109.5 ± 18.8) contents per cell in high and low seeding density constructs on day 30 and 70, respectively (Fig. 2 E, F; Table 2). High seeding density constructs exhibited less volumetric swelling compared to the low seeding density groups under free swelling conditions on day 30 (20FS @ $130.5 \pm 2.3\%$ vs. 60FS @ $115.0 \pm 7.1\%$) (Table 2). The swelling of low seeding density constructs decreased over time under both free swelling and dynamic loading conditions (day 30: 20FS @ $130.5 \pm 2.3\%$, 20DL @ $124.9 \pm 7.5\%$ vs. day 70 20FS @ $118.9 \pm 4.2\%$, 20DL @ $108.6 \pm 1.1\%$) (Table 2). Loading reduced swelling of low seeding density constructs on day 70 (20FS @ $118.9 \pm 4.2\%$ vs. 20DL @ $108.6 \pm 1.1\%$) (Table 2). Although the expression of type II collagen and aggrecan was significantly upregulated in all groups compared to unencapsulated cells, there were no significant differences between FS and DL groups in the gene expression of aggrecan, type II and type I collagen on days 14, 42, and 70 of culture (Fig. 3).

Recent *in vitro* studies demonstrated successful chondrogenesis of MSCs photoencapsulated in HA hydrogels, formed through the crosslinking of HA modified with methacrylate groups.^{21–23} However, despite the advantages of HA as a scaffold material, the properties of the formed cartilage were inferior to that of native tissue. In this study, the results indicate that dynamic compressive loading enhances the synthesis of cartilage-specific extracellular matrix (ECM) by human MSCs seeded at both low and high density in HA hydrogels, leading to superior mechanical function of these constructs compared to free swelling controls.

An optimal cell seeding density is critical to the tissue engineering of cartilage, especially when MSCs are used. During development, the initial step of cartilage formation requires recruitment of and condensation of progenitor cells. The density of this condensation is directly related to the extent of the subsequent chondrogenic differentiation.⁴⁵ On the other hand, cartilage cell density generally varies with distance from articular surface and with age. Adult human femoral condylar cartilage of has an overall density of ~ 15 million cells/ml,⁴⁶ whereas levels in fetal and juvenile cartilage can be many fold higher. In this study, two different seeding densities were investigated, one similar to adult cartilage and another threefold higher. Although there was no difference in mechanical stiffness and cartilage matrix content between the

high and low seeding density constructs under free swelling conditions on day 30, the high seeding density constructs (60FS) eventually developed significantly higher mechanical properties and cartilage matrix content compared to the low seeding density constructs (20FS) on day 70.

Several previous studies showed lower cartilage matrix synthesis per cell at high seeding densities and a lack of difference between high and low MSC seeding density in bulk mechanical properties and cartilage matrix content under FS condition; however, these studies only included a shorter culture period of 3–5 weeks.^{27,47} In addition, the HA hydrogel scaffold used in this study may be more favorable to matrix remodeling and distribution compared to the scaffold materials used in these other studies. The GAG synthesis per cell in the high density group also increased to similar levels compared to the low density group on day 70. These results indicate that our HA scaffold supports chondrogenesis of MSCs at high seeding density, resulting in enhanced functional properties of the engineered cartilage compared to those of low seeding density constructs. A potential practical advantage of a high MSC seeding density in clinical translation is that tissue engineered constructs can attain mechanical functionality in a shorter period, which would expedite any *in vitro* culture prior to *in vivo* implantation.

The reduced volumetric swelling of high seeding density constructs compared to the low seeding density ones on day 30 is likely due to higher collagen content and more cellular contraction. As the low seeding density constructs matured over time with increasing collagen content, the swelling decreased. Dynamic loading further reduced swelling of low seeding density constructs on day 70 by increasing collagen deposition in the hydrogels. While a difference in total collagen content was detected between free swelling and dynamically loaded groups at certain time points, there was no significant difference in the gene expression of type II collagen evaluated at the selected time points. The biosynthetic pathway of collagen synthesis is very complex including steps such as mRNA processing, translation on the rough endoplasmic reticulum and post-translational modifications. The discrepancy between gene expression and actual protein production may be due to changes in one or several of these steps.

Effect of dynamic compression on cartilage matrix distribution by MSCs in HA hydrogels

DL also significantly enhanced the spatial distribution of proteoglycans and collagen in HA hydrogels as evidenced by alcian blue and picrosirius red staining, respectively (Fig. 4, 5). 60DL and 20DL constructs exhibited significantly more

FIG. 3. Expression of aggrecan, type II collagen and type I collagen in fold change (relative to day 0) after 14, 42, and 70 days of the culture ($n=4$) for either 20 or 60 million cells/ml encapsulation density and under FS or DL culture conditions.

FIG. 4. Alcian blue staining (pH=1.0) (proteoglycans) of all groups after 30 and 70 days of culture; 4 $\times$ images show the entire construct cross-section, bar=500 μ m; 20 $\times$ images show peripheral or central regions of construct, bar=100 μ m. Color images available online at www.liebertonline.com/tea

diffuse staining compared to their free swelling counterparts, especially in the central area of the construct, on day 30 and 70, respectively (Fig. 4, 5). This is especially evident in the collagen production. Immunohistological staining against chondroitin sulfate and type II collagen showed similar trends (data not shown).

In addition to elevated levels of GAG and collagen, the improved mechanical properties in the loaded constructs may also result from a more uniform matrix distribution between encapsulated cells. In contrast to previous studies performed with agarose scaffolds, dynamic loading initiated soon after MSC encapsulation (3 days after) did not hinder chondrogenesis or slow maturation in these MSC-seeded HA hydrogels.^{24,48} However, histology staining also revealed more cartilage matrix deposition in the periphery of the constructs compared to the interior under FS conditions, especially in high seeding density constructs. This uneven spatial distribution of cartilage matrix is likely due to diffusion limitations into the HA hydrogels, as reported previously.^{49,50} Previous studies showed that DL not only enhances chondrogenesis but may also increase nutrient transport into the hydrogel constructs, leading to significantly enhanced production and distribution of cartilage matrix.^{24,51} Histological staining showed that DL mitigated these large-scale spatial heterogeneities in matrix distribution within HA hydrogels, possibly by enhancing nutrient transport. The earlier response to loading by high density constructs compared to low density constructs could indicate a more pronounced beneficial effect of loading-induced

transport of nutrients or TGF- β 3 in high density constructs, which would likely suffer from more severe nutrient limitations at earlier time points compared to lower seeding densities. Findings from this study showed that these beneficial effects of mechanical loading are preserved in photocrosslinked HA hydrogels with varying MSC seeding densities. However, loading seemed to have diminishing effects on high density constructs over time. This indicates that a high seeding density of MSCs in HA hydrogels may enhance matrix distribution and therefore result in superior mechanical properties compared to low seeding density, independent of loading after long term culture.

Effect of dynamic compression on hypertrophy of chondrogenically induced MSCs

When compared to FS group, the expression of the primary hypertrophic markers, including type X collagen, matrix metalloproteinase 13, and alkaline phosphatase (ALP), were significantly decreased by dynamic loading in both the presence (+ T3) or absence (– T3) of hypertrophic factors (T3, β -gly) (Fig. 6). Quantification of calcium content and Von Kossa staining showed that while no calcification was observed in the absence of T3 and β -gly, DL significantly reduced the degree of calcification in MSC-laden HA hydrogels in the presence of these factors (Fig. 7).

In addition to improving overall construct properties, DL suppressed hypertrophic conversion and calcium deposition within chondrogenically induced MSC-seeded HA

FIG. 5. Picrosirius red staining (collagen) of all the groups after 30 and 70 days of culture; 4 $\times$ images show entire construct cross-section, bar = 500 μ m; 20 $\times$ images show peripheral or central regions of the construct, bar = 100 μ m. Color images available online at www.liebertonline.com/tea

constructs. To our knowledge, this is the first study to demonstrate the inhibitory effect of mechanical loading on MSC hypertrophy in tissue engineered cartilage under bioreactor culture. Interestingly, in the absence of T3 and β -glycerophosphate there is no calcification observed despite significant upregulation of hypertrophic markers such as alkaline phosphatase and type X collagen (FS-T3, DL-T3). Mineralization was only observed when T3 and β -glycerophosphate was supplemented in the media (FS+T3, DL+T3). Furthermore, the mineralization was mostly located in the periphery of the engineered cartilage constructs. Thus, while DL could act to dislodge forming calcification at these edges, this is unlikely to be the mechanism given the sharp decline in hypertrophic gene expression we observed with

loading. In contrast to these *in vitro* findings, constructs previously implanted subcutaneously in nude mice for a similar duration showed extensive calcification throughout the entire construct.³⁰ Thus, there is a dependence on culture environment on the distribution of calcification.

Mechanical signals have been shown to regulate the expression of IHH, PTHrP, TGF- β , and its receptor.^{32–35,52} The IHH-PTHrP negative feedback pathway regulates hypertrophic differentiation of both articular and growth plate chondrocytes to maintain the zonal structure of cartilage.^{53–56} Our unpublished data and previous work also showed that TGF- β is an inhibitor of MSC hypertrophy.⁵⁷ These mechanically responsive molecular pathways could have contributed to the observed suppression in the gene expression of

FIG. 6. Expression of selected hypertrophic markers in fold change on day 28 for cells at the 20 million cells/ml seeding density, * $p < 0.05$ vs. FS+T3/-T3 group ($n = 4$).

FIG. 7. Calcium content (**A**) and Von Kossa staining (**B**) of the HA hydrogels on day 30 for cells at the 20 million cells/ml seeding density, $*p < 0.05$ vs. FS+T3 group ($n=4$); bar=500 μ m. Color images available online at www.liebertonline.com/tea

hypertrophic markers and mineralization by MSCs. However, mechanical loading failed to completely arrest the hypertrophic differentiation of MSCs. In this study, a loading regimen of 4 h per day was adopted due to its proved efficacy in promoting cartilage matrix production and distribution by MSCs. To further avert hypertrophy, longer loading durations could be pursued. Future studies to establish optimal loading regimens are warranted. A previous study by our group also showed that co-culture of MSCs and a small fraction of articular chondrocytes in HA hydrogels not only enhanced chondrogenesis of MSCs, but also reduced the expression of hypertrophic markers by MSCs.⁵⁸ Thus, there may be a synergistic effect of coculture and mechanical loading on stabilizing the chondrogenic phenotype of MSCs.

The clinical implication of these findings is that joint loading, or *in vitro* loading in bioreactors in cases where constructs are to be pre-cultured before implantation, may enhance the maturation of engineered cartilage and inhibit hypertrophic differentiation of MSCs, resulting in superior outcomes compared to immobilization of joint. However, it should be noted that the highest mechanical stiffness of engineered cartilage achieved in this study is still well below that of the native cartilage tissue. On the other hand, for animal trials it is still to be determined what level of mechanical maturity will be required for the engineered cartilage implants to survive in load bearing joints. Additional factors, including the size and type of defects and the mobility of the operated joints after surgery, may also influence the survival of the implants. In regional defects of limited dimensions the implants will be subjected to partially confined loading due to lateral constraint from the surrounding native tissue and will likely exhibit higher resistance to compression than that measured in unconfined testing as reported in this study.

Conclusions

Our findings demonstrate that dynamic compressive loading significantly enhances cartilage matrix production and distribution by human MSCs in HA hydrogels, leading to improved properties. These outcomes were dependent on both the overall culture time and the density of cells initially encapsulated within the hydrogels. Furthermore, the expression of major hypertrophic genes and matrix mineralization were significantly reduced with daily compressive loading. These findings not only indicate the importance of mechanical preconditioning in achieving mature tissue engineered carti-

lage using MSCs prior to implantation, but also highlight the potential benefit of joint loading in the stabilization and development of implanted engineered cartilage *in vivo*.

Acknowledgment

This work was supported by National Institutes of Health grant R01 EB008722.

Disclosure Statement

No competing financial interests exist.

References

1. Erickson, I.E., Huang, A.H., Chung, C., Li, R.T., Burdick, J.A., and Mauck, R.L. Differential maturation and structure-function relationships in mesenchymal stem cell- and chondrocyte-seeded hydrogels. *Tissue Eng Part A* **15**, 1041, 2009.
2. Chung, C., and Burdick, J.A. Engineering cartilage tissue. *Adv Drug Deliv Rev* **60**, 243, 2008.
3. Williams, C.G., Kim, T.K., Taboas, A., Malik, A., Manson, P., and Elisseeff, J. *In vitro* chondrogenesis of bone marrow-derived mesenchymal stem cells in a photopolymerizing hydrogel. *Tissue Eng* **9**, 679, 2003.
4. Hosseini, A., and Hogg, D.A. The effects of paralysis on skeletal development in the chick embryo. II. Effects on histogenesis of the tibia. *J Anat* **177**, 169, 1991.
5. Mikić, B., Isenstein, A.L., and Chhabra, A. Mechanical modulation of cartilage structure and function during embryogenesis in the chick. *Ann Biomed Eng* **32**, 18, 2004.
6. Williamson, A.K., Chen, A.C., Masuda, K., Thonar, E.J., and Sah, R.L. Tensile mechanical properties of bovine articular cartilage: variations with growth and relationships to collagen network components. *J Orthop Res* **21**, 872, 2003.
7. Erickson, I.E., van Veen, S.C., Sengupta, S., Kestle, S.R., and Mauck, R.L. Cartilage Matrix Formation by Bovine Mesenchymal Stem Cells in Three-dimensional Culture Is Age-dependent. *Clin Orthop Relat Res*, **469**, 2744, 2011.
8. Williamson, A.K., Masuda, K., Thonar, E.J., and Sah, R.L. Growth of immature articular cartilage *in vitro*: correlated variation in tensile biomechanical and collagen network properties. *Tissue Eng* **9**, 625, 2003.
9. Palmoski, M., Perricone, E., and Brandt, K.D. Development and reversal of a proteoglycan aggregation defect in normal canine knee cartilage after immobilization. *Arthritis Rheum* **22**, 508, 1979.
10. Setton, L.A., Mow, V.C., and Howell, D.S. Mechanical behavior of articular cartilage in shear is altered by transection of the anterior cruciate ligament. *J Orthop Res* **13**, 473, 1995.

11. Gray, M.L., Pizzanelli, A.M., Grodzinsky, A.J., and Lee, R.C. Mechanical and physicochemical determinants of the chondrocyte biosynthetic response. *J Orthop Res* **6**, 777, 1988.
12. Guilak, F., Meyer, B.C., Ratcliffe, A., and Mow, V.C. The effects of matrix compression on proteoglycan metabolism in articular cartilage explants. *Osteoarthritis Cartilage* **2**, 91, 1994.
13. Sah, R.L., Kim, Y.J., Doong, J.Y., Grodzinsky, A.J., Plaas, A.H., and Sandy, J.D. Biosynthetic response of cartilage explants to dynamic compression. *J Orthop Res* **7**, 619, 1989.
14. Valhmu, W.B., Stazzone, E.J., Bachrach, N.M., Saed-Nejad, F., Fischer, S.G., Mow, V.C., *et al.* Load-controlled compression of articular cartilage induces a transient stimulation of aggrecan gene expression. *Arch Biochem Biophys* **353**, 29, 1998.
15. Buschmann, M.D., Kim, Y.-J., Wong, M., Frank, E., Hunziker, E.B., and Grodzinsky, A.J. Stimulation of aggrecan synthesis in cartilage explants by cyclic loading is localized to regions of high interstitial fluid flow. *Arch Biochem Biophys* **366**, 1, 1999.
16. Kim, Y.J., Sah, R.L., Grodzinsky, A.J., Plaas, A.H., and Sandy, J.D. Mechanical regulation of cartilage biosynthetic behavior: physical stimuli. *Arch Biochem Biophys* **311**, 1, 1994.
17. Grodzinsky, A.J., Levenston, M.E., Jin, M., and Frank, E.H. Cartilage tissue remodeling in response to mechanical forces. *Annu Rev Biomed Eng* **2**, 691, 2000.
18. Mauck, R.L., Byers, B.A., Yuan, X., and Tuan, R.S. Regulation of cartilaginous ECM gene transcription by chondrocytes and MSCs in 3D culture in response to dynamic loading. *Biomech Model Mechanobiol* **6**, 113, 2007.
19. Campbell, J.J., Lee, D.A., and Bader, D.L. Dynamic compressive strain influences chondrogenic gene expression in human mesenchymal stem cells. *Biorheology* **43**, 455, 2006.
20. Pelaez, D., Huang, C.Y., and Cheung, H.S. Cyclic compression maintains viability and induces chondrogenesis of human mesenchymal stem cells in fibrin gel scaffolds. *Stem Cells Dev* **18**, 93, 2009.
21. Chung, C., and Burdick, J.A. Influence of three-dimensional hyaluronic acid microenvironments on mesenchymal stem cell chondrogenesis. *Tissue Eng Part A* **15**, 243, 2009.
22. Chung, C., Beecham, M., Mauck, R.L., and Burdick, J.A. The influence of degradation characteristics of hyaluronic acid hydrogels on in vitro neocartilage formation by mesenchymal stem cells. *Biomaterials* **30**, 4287, 2009.
23. Erickson, I.E., Huang, A.H., Sengupta, S., Kestle, S., Burdick, J.A., and Mauck, R.L. Macromer density influences mesenchymal stem cell chondrogenesis and maturation in photocrosslinked hyaluronic acid hydrogels. *Osteoarthritis Cartilage* **17**, 1639, 2009.
24. Huang, A.H., Farrell, M.J., Kim, M., Mauck, R.L. Long-term dynamic loading improves the mechanical properties of chondrogenic mesenchymal stem cell-laden hydrogel. *Eur Cell Mater* **19**, 72, 2010.
25. Kavalkovich, K.W., Boynton, R.E., Murphy, J.M., and Barry, F. Chondrogenic differentiation of human mesenchymal stem cells within an alginate layer culture system. *In Vitro Cell Dev Biol Anim* **38**, 457, 2002.
26. Hui, T.Y., Cheung, K.M., Cheung, W.L., Chan, D., and Chan, B.P. In vitro chondrogenic differentiation of human mesenchymal stem cells in collagen microspheres: influence of cell seeding density and collagen concentration. *Biomaterials* **29**, 3201, 2008.
27. Huang, A.H., Stein, A., Tuan, R.S., and Mauck, R.L. Transient exposure to transforming growth factor beta 3 improves the mechanical properties of mesenchymal stem cell-laden cartilage constructs in a density-dependent manner. *Tissue Eng Part A* **15**, 3461, 2009.
28. Pelttari, K., Winter, A., Steck, E., Goetzke, K., Hennig, T., Ochs, B.G., *et al.* Premature induction of hypertrophy during in vitro chondrogenesis of human mesenchymal stem cells correlates with calcification and vascular invasion after ectopic transplantation in SCID mice. *Arthritis Rheum* **54**, 3254, 2006.
29. Scotti, C., Tonnarelli, B., Papadimitropoulos, A., Scherberich, A., Schieren, S., Schauerte, A., *et al.* Recapitulation of endochondral bone formation using human adult mesenchymal stem cells as a paradigm for developmental engineering. *Proc Natl Acad Sci USA* **107**, 7251, 2010.
30. Bian, L., Zhai, D.Y., Tous, E., Rai, R., Mauck, R.L., and Burdick, J.A. Enhanced MSC chondrogenesis following delivery of TGF-beta3 from alginate microspheres within hyaluronic acid hydrogels in vitro and in vivo. *Biomaterials* **32**, 6425, 2011.
31. Guo, X., Park, H., Young, S., Kretlow, J.D., van den Beucken, J.J., Baggett, L.S., *et al.* Repair of osteochondral defects with biodegradable hydrogel composites encapsulating marrow mesenchymal stem cells in a rabbit model. *Acta Biomater* **6**, 39, 2010.
32. Wu, Q.-q., Zhang, Y., and Chen, Q. Indian hedgehog is an essential component of mechanotransduction complex to stimulate chondrocyte proliferation. *J Biol Chem* **276**, 35290, 2001.
33. Tang, G.H., Rabie, A.B., and Hagg, U. Indian hedgehog: a mechanotransduction mediator in condylar cartilage. *J Dent Res* **83**, 434, 2004.
34. Tanaka, N., Ohno, S., Honda, K., Tanimoto, K., Doi, T., Ohno-Nakahara, M., *et al.* Cyclic mechanical strain regulates the PTHrP expression in cultured chondrocytes via activation of the Ca²⁺ channel. *J Dent Res* **84**, 64, 2005.
35. Chen, X., Macica, C.M., Nasiri, A., Broadus, A.E. Regulation of articular chondrocyte proliferation and differentiation by indian hedgehog and parathyroid hormone-related protein in mice. *Arthritis Rheum* **58**, 3788, 2008.
36. Mueller, M.B., and Tuan, R.S. Functional characterization of hypertrophy in chondrogenesis of human mesenchymal stem cells. *Arthritis Rheum* **58**, 1377, 2008.
37. Smeds, K.A., Pfister-Serres, A., Miki, D., Dastgheib, K., Inoue, M., Hatchell, D.L., *et al.* Photocrosslinkable polysaccharides for in situ hydrogel formation. *J Biomed Mater Res* **54**, 115, 2001.
38. Byers, B.A., Mauck, R.L., Chiang, I.E., and Tuan, R.S. Transient exposure to transforming growth factor beta 3 under serum-free conditions enhances the biomechanical and biochemical maturation of tissue-engineered cartilage. *Tissue Eng Part A* **14**, 1821, 2008.
39. Lima, E.G., Bian, L., Ng, K.W., Mauck, R.L., Byers, B.A., Tuan, R.S., *et al.* The beneficial effect of delayed compressive loading on tissue-engineered cartilage constructs cultured with TGF-beta3. *Osteoarthritis Cartilage* **15**, 1025, 2007.
40. Mauck, R.L., Soltz, M.A., Wang, C.C., Wong, D.D., Chao, P.H., Valhmu, W.B., *et al.* Functional tissue engineering of articular cartilage through dynamic loading of chondrocyte-seeded agarose gels. *J Biomech Eng* **122**, 252, 2000.
41. Mauck, R.L., Soltz, M.A., Wang, C.C.-B., Wong, D.D., Chao, P.-H.G., Valhmu, W.B., *et al.* Functional tissue engineering of

- articular cartilage through dynamic loading of chondrocyte-seeded agarose gels. *J Biomech Eng* **122**, 252, 2000.
42. McGowan, K.B., Kurtis, M.S., Lottman, L.M., Watson, D., and Sah, R.L. Biochemical quantification of DNA in human articular and septal cartilage using PicoGreen and Hoechst 33258. *Osteoarthritis Cartilage* **10**, 580, 2002.
 43. Farndale, R.W., Buttle, D.J., and Barrett, A.J. Improved quantitation and discrimination of sulphated glycosaminoglycans by use of dimethylmethylene blue. *Biochimica et biophysica acta* **883**, 173, 1986.
 44. Hollander, A.P., Heathfield, T.F., Webber, C., Iwata, Y., Bourne, R., Rorabeck, C., *et al.* Increased damage to type II collagen in osteoarthritic articular cartilage detected by a new immunoassay. *J Clin Invest* **93**, 1722, 1994.
 45. Ahrens, P.B., Solorsh, M., Reiter, R.S. Stage-related capacity for limb chondrogenesis in cell culture. *Dev Biol* **60**, 69, 1977.
 46. Stockwell, R.A. The interrelationship of cell density and cartilage thickness in mammalian articular cartilage. *J Anat* **109**, 411, 1971.
 47. Ponticello, M.S., Schinagl, R.M., Kadiyala, S., and Barry, F.P. Gelatin-based resorbable sponge as a carrier matrix for human mesenchymal stem cells in cartilage regeneration therapy. *J Biomed Mater Res* **52**, 246, 2000.
 48. Thorpe, S.D., Buckley, C.T., Vinardell, T., O'Brien, F.J., Campbell, V.A., Kelly, D.J. Dynamic compression can inhibit chondrogenesis of mesenchymal stem cells. *Biochemical and Biophysical Research Communications* **377**, 458, 2008.
 49. Kelly, T.N., Ng, K.W., Wang, C-CB., Ateshian, G.A., and Hung, C.T. Spatial and temporal development of chondrocyte-seeded agarose constructs in free-swelling and dynamically loaded cultures. *J Biomech* **39**, 1489, 2006.
 50. Bian, L., Angione, S.L., Ng, K.W., Lima, E.G., Williams, D.Y., Mao, D.Q., *et al.* Influence of decreasing nutrient path length on the development of engineered cartilage. *Osteoarthritis Cartilage* **17**, 677, 2009.
 51. Albrow, M.B., Chahine, N.O., Li, R., Yeager, K., Hung, C.T., and Ateshian, G.A. Dynamic loading of deformable porous media can induce active solute transport. *J Biomech* **41**, 3152, 2008.
 52. Huang, C.Y., Reuben, P.M., and Cheung, H.S. Temporal expression patterns and corresponding protein inductions of early responsive genes in rabbit bone marrow-derived mesenchymal stem cells under cyclic compressive loading. *Stem Cells* **23**, 1113, 2005.
 53. Zhang, M., Xie, R., Hou, W., Wang, B., Shen, R., Wang, X., *et al.* PTHrP prevents chondrocyte premature hypertrophy by inducing cyclin-D1-dependent Runx2 and Runx3 phosphorylation, ubiquitylation and proteasomal degradation. *J Cell Sci* **122**, 1382, 2009.
 54. Guo, J., Chung, U.I., Yang, D., Karsenty, G., Bringham, F.R., and Kronenberg, H.M. PTH/PTHrP receptor delays chondrocyte hypertrophy via both Runx2-dependent and -independent pathways. *Dev Biol* **292**, 116, 2006.
 55. St-Jacques, B., Hammerschmidt, M., and McMahon, A.P. Indian hedgehog signaling regulates proliferation and differentiation of chondrocytes and is essential for bone formation. *Genes Dev* **13**, 2072, 1999.
 56. Vortkamp, A., Lee, K., Lanske, B., Segre, G.V., Kronenberg, H.M., and Tabin, C.J. Regulation of rate of cartilage differentiation by Indian hedgehog and PTH-related protein. *Science* **273**, 613, 1996.
 57. Mello, M.A., and Tuan, R.S. Effects of TGF-beta1 and triiodothyronine on cartilage maturation: in vitro analysis using long-term high-density micromass cultures of chick embryonic limb mesenchymal cells. *J Orthop Res* **24**, 2095, 2006.
 58. Bian, L., Zhai, D.Y., Mauck, R.L., and Burdick, J.A. Coculture of human mesenchymal stem cells and articular chondrocytes reduces hypertrophy and enhances functional properties of engineered cartilage. *Tissue Eng Part A* **17**, 1137, 2011.

Address correspondence to:

Jason A. Burdick, Ph.D.
 Department of Bioengineering
 University of Pennsylvania
 240 Skirkanich Hall
 210 S. 33rd Street
 Philadelphia, PA 19104

E-mail: burdick2@seas.upenn.edu

Received: August 15, 2011

Accepted: October 10, 2011

Online Publication Date: December 1, 2011