Evaluation of defects generation in crystalline silicon ingot grown by cast technique with seed crystal for solar cells

Tomihisa Tachibana,^{1,a)} Takashi Sameshima,¹ Takuto Kojima,² Koji Arafune,³ Koichi Kakimoto,⁴ Yoshiji Miyamura,⁵ Hirofumi Harada,⁵ Takashi Sekiguchi,⁵ Yoshio Ohshita,² and Atsushi Ogura¹

¹*School of Science and Technology, Meiji University, Kawasaki 214-8571, Japan*

²*Toyota Technological Institute, Nagoya 468-8511, Japan*

³*University of Hyogo, Hyogo 671-2280, Japan*

⁴*Kyusyu University, Fukuoka 816-8580, Japan*

⁵*National Institute of Materials Science, Ibaraki 305-0044, Japan*

(Received 21 June 2011; accepted 7 March 2012; published online 5 April 2012)

Although crystalline silicon is widely used as substrate material for solar cell, many defects occur during crystal growth. In this study, the generation of crystalline defects in silicon substrates was evaluated. The distributions of small-angle grain boundaries were observed in substrates sliced parallel to the growth direction. Many precipitates consisting of light elemental impurities and small-angle grain boundaries were confirmed to propagate. The precipitates mainly consisted of Si, C, and N atoms. The small-angle grain boundaries were distributed after the precipitation density increased. Then, precipitates appeared at the small-angle grain boundaries. We consider that the origin of the small-angle grain boundaries was lattice mismatch and/or strain caused by the high-density precipitation. © 2012 American Institute of Physics. [<http://dx.doi.org/10.1063/1.3700250>]

I. INTRODUCTION

The photovoltaic industry has been developing rapidly throughout the world. In this industry, crystalline silicon is widely used as a substrate material because of its cost efficiency. However, silicon substrates for solar cells have many degradation factors affecting the conversion efficiency, such as light elemental and metallic impurities as well as grain boundaries. Grain boundaries, including both coincident and random grain boundaries, act as the minority carrier recombination centers in multi-crystalline silicon solar cells. The structures and properties of these degradation factors have been investigated.^{1–5} In addition, growth techniques for obtaining large grains and to suppress impurities and crystalline defects have been proposed.^{6–8} Fabricating an ingot that has relatively large grains with few grain boundaries has thus become possible. However, even in large grains, intra-grain defects that also deteriorate the conversion efficiency of solar cells may occur. These defects include small-angle grain boundaries, dislocations, and impurity precipitates. These intra-grain defects have been evaluated by photoluminescence (PL) and electron-beam-induced current (EBIC) in terms of minority carrier recombination characteristics.^{9–15} Additionally, the effects and properties of metallic impurities at grain boundaries and dislocations have been reported.^{16–20} Oxygen is another major impurity in conjunction with iron that may occur at small-angle grain boundaries, deteriorating the minority carrier lifetime.^{21,22} In order to improve the characteristics of silicon substrates for solar cells, such intra-grain defects must be reduced. However, clarifying the generation of these defects is difficult

because many crystalline defects occur in multi-crystalline silicon.

We consider that the generation of small-angle grain boundaries is related to light element impurities. However, the role of the impurities in defect generation is unclear. In this study, we evaluated the generation of small-angle grain boundaries in crystalline silicon substrates fabricated with a cast seeding technique.^{23,24} Using this growth technique, we obtained a single crystalline region in an ingot. Thus, we could evaluate the generation and propagation properties of the crystalline defects related to impurity precipitates without the influence of other factors such as crucible and grain boundaries.

FIG. 1. Cross-sectional view of substrate sliced parallel to growth direction.

^{a)}E-mail: t_tachi@meiji.ac.jp.

FIG. 2. EBIC image at crystalline defects in region I.

II. EXPERIMENTAL PROCEDURE

A boron-doped crystalline silicon ingot was grown with a cast seeding technique. A (100) Czochralski silicon cylinder with a diameter of ~ 90 mm was used as a seed crystal. Prior to growth, the seed crystal was treated with chemical etching to remove the surface oxide and any damaged layers. The source materials were melted at 1550°C in the furnace and the ingot was grown at 15 mm/h. The calculated carbon concentration in the ingot is estimated to nearly reach the solubility limit of 10^{17} atoms/cm³. The grown ingot was cylindrical, with a diameter and a height of ~ 100 mm. The thickness of remained seed crystal was ~ 30 mm. The ingot was sliced parallel to the growth direction for the evaluation. Thus, the distribution of intra-grain defects could be observed along the growth direction. The sliced substrates were etched using a mixture of HF and HNO₃ to remove the slicing damaged surface layer. Then, the substrate was mechanically polished and chemically etched for the evaluation.

The distributions of crystalline defects were evaluated using scanning electron microscopy (SEM) and EBIC. The precipitation elements were confirmed by energy dispersive

X-ray spectroscopy (EDX). The misorientation angles of small-angle grain boundaries were analyzed using electron backscattering diffractometry (EBSD). The acceleration voltage for the SEM, EBIC, and EDX measurements was 20.0 kV, using an SU-70 (HITACHI High-Technologies).

III. RESULTS AND DISCUSSION

The cross-sectional view of grown ingot is shown in Fig. 1. The dashed line indicates the interface between the un-molten seed crystal and a single crystal grown from the seed. A relatively large single crystal was grown from the seed crystal. Additionally, a multi-crystalline region with relatively large grain size propagated around the single crystalline region. Thus, we observed the generation and propagation of crystalline defects in the single crystalline region grown from the seed crystal. The evaluation region was divided into the regions I to IV with discriminative defects as indicated in Fig. 1.

In region I, the crystalline defects and precipitates were observed using SEM and EBIC. The EBIC image at a typical crystalline defect and the SEM image of a typical precipitate are shown in Figs. 2 and 3, respectively. A typical defect is a region surrounded by grain boundaries (Fig. 2). The right- and left-edge grain boundaries showed much stronger EBIC contrast, while the top and bottom edges had relatively weak contrast. These grain boundaries were all defined as $\Sigma 3$ by the EBSD measurement. Thus, the difference of EBIC contrast may be attributed to the structure of each grain boundary. Twenty-five types of $\Sigma 3$ grain boundaries have been reported with different boundary planes, including symmetric- and asymmetric-tilt grain boundaries.^{25,26} The asymmetric-tilt $\Sigma 3$ grain boundaries act as stronger minority carrier recombination centers. Thus, the right and left edges of the crystalline defect are considered

FIG. 3. (a) SEM image of precipitation in region I and atomic distributions of (b) Si, (c) C, and (d) N.

FIG. 4. (a) EBIC image at the precipitates observed in region III, (b) high resolution SEM image, and atomic distributions of (c) Si, (d) C, and (e) N.

to consist of asymmetric-tilt $\Sigma 3$ grain boundaries, while the others were probably symmetric-tilt $\Sigma 3$. An SEM image of the precipitate observed in region I is shown in Fig. 3(a), and the atomic distributions consisting of Si, C, and N observed by EDX are shown in Figs. 3(b)–3(d), respectively. This particular precipitate is relatively larger than that observed for the conventional cast technique. EDX measurements confirmed that the main elements of the precipitate were Si and C. Thus, we considered this might be a SiC precipitate. These precipitations were not observed at the $\Sigma 3$ grain boundaries. Additionally, the distributions of the $\Sigma 3$ grain boundaries were broader than those of the precipitations. Thus, no obvious relationships between the precipitations and the crystalline defects were shown. In region II, few crystalline defects and precipitations were observed. We assumed that a kind of denuded zone existed in terms of the precipitations and the crystalline defects in region II. Thus, we consider that the crystalline defects and the precipitations in region I might have originated in the seeding process, such as through thermal shock or insufficient melting durations for the feed stocks to keep the seed un-molten.

In region III, the precipitations appeared again. An EBIC image of the precipitates observed in this region is shown in Fig. 4(a). The precipitations seem to start from one point and propagate along a V-shape. An SEM image and the atomic distributions consisting of Si, C, and N are shown in Figs. 4(b)–4(e), respectively. The precipitates consisted of C and N as well as Si, showing a different configuration from those observed in region I. We consider that the precipitates observed in region III might be SiC, Si_3N_4 , or SiCN. Therefore, we assume that the source of the precipitations observed in regions I and III would be different. The precipitations observed in region III might be the impurities incorporated in the melt during the crystal growth procedure.

In region IV, high-density dark lines were observed as shown by the EBIC image in Fig. 5(a). These dark lines define the small-angle grain boundaries by EBSD. EBSD diagram is shown in Fig. 5(b). The misorientation angles at most of the small-angle grain boundaries were less than 5° . The density of the small-angle grain boundaries increased through the crystal growth procedure. In addition, precipitations tended to be observed at the small-angle grain

FIG. 5. (a) EBIC image and (b) EBSD diagram at small-angle grain boundaries in region IV.

FIG. 6. (a) SEM image of precipitates at small-angle grain boundaries and atomic distributions of (b) Si, (c) C, and (d) N.

boundaries in region IV, unlike in region III. A SEM image of the precipitates and the atomic distributions of Si, C, and N at the small-angle grain boundaries are shown in Figs. 6(a)–6(d). The constituent elements of the precipitates were almost the same as those observed in region III (Fig. 4). The small-angle grain boundaries appeared after increase of the precipitations. Thus, we consider that the precipitations were the possible origins of the small-angle grain boundaries.

The precipitations should promote lattice mismatch and/or the strain field. When the precipitation density was sufficiently low, the lattice mismatch and/or the strain might not be causes of the defect generation because they could be relaxed through the crystal growth procedure. However, after the precipitation density significantly increased, the dislocation could have been generated to relax the lattice mismatch and/or the strain. Then, dislocations caused the small-angle grain boundaries through the crystal growth procedure. After the generation of the small-angle grain boundaries, preferential precipitation sites appeared, so the precipitates should occur at the small-angle grain boundaries. Consequently, we consider that the precipitations of light element atoms, such as C and N, could be the origin of the defect generation.

Dislocations are an origin of the small-angle grain boundaries and occur due to the thermal or shear stress during the solidification in the growth process.^{27–30} We observed the generation and propagation of small-angle grain boundaries related to light elemental impurities. Thus, we assume that there are several origins of the small-angle grain boundaries consisting of dislocations and that they are generated both during and after solidification. Therefore, small-angle grain boundary generation should be suppressible by controlling the light element precipitation. The present study also

showed that the light element impurities could be the origins of crystalline defect generation, so their incorporation and precipitation also need to be controlled.

IV. CONCLUSION

We evaluated the generation and propagation of crystalline defects in a silicon ingot. In order to confirm the distribution of defects without the effect of grain boundaries, the substrate was grown by a cast seeding technique and was sliced parallel to the growth direction. First, precipitates related to both C and N began to occur and propagated from one point. The precipitation density increased through the crystal growth procedure. Then, small-angle grain boundaries appeared. We consider that the lattice mismatch and/or the strain field caused by the precipitation were the origins of the small-angle grain boundaries. After the small angle-grain boundary generation, the precipitations tended to occur at the defects. The density of the small-angle grain boundaries increased through the crystal growth procedure. Thus, we consider the precipitation of light element impurities induced during crystal growth is one of the origins of intra-grain defects.

ACKNOWLEDGMENTS

This work was supported by the New Energy and Industrial Technology Development Organization (NEDO) under the Ministry of Economy, Trade and Industry (METI).

¹J. Chen, T. Sekiguchi, S. Nara, and D. Yang, *J. Phys.: Condens. Matter* **16**, S211 (2004).

²K. Arafune, E. Ohishi, H. Sai, Y. Terada, Y. Ohshita, and M. Yamaguchi, *Jpn. J. Appl. Phys.* **45**, 6153 (2006).

- ³Y. Ohshita, Y. Nishikawa, M. Tachibana, V. K. Tuong, T. Sasaki, N. Kojima, S. Tanaka, and M. Yamaguchi, *J. Cryst. Growth* **275**, e491 (2005).
- ⁴T. Tachibana, J. Masuda, A. Ogura, Y. Ohshita, and K. Arafune, *Electrochem. Solid-State Lett.* **13**, B79 (2010).
- ⁵K. Hartman, M. Bertoni, J. Serdy, and T. Buonassisi, *Appl. Phys. Lett.* **93**, 122108 (2008).
- ⁶Y. Nose, I. Takahashi, W. Pan, N. Usami, K. Fujiwara, and K. Nakajima, *J. Cryst. Growth* **311**, 228 (2009).
- ⁷K. Arafune, E. Ohishi, H. Sai, Y. Ohshita, and M. Yamaguchi, *J. Cryst. Growth* **308**, 5 (2007).
- ⁸T. F. Li, K. M. Yeh, W. C. Hsu, and C. W. Lan, *J. Cryst. Growth* **318**, 219 (2011).
- ⁹H. Sugimoto, K. Araki, M. Tajima, T. Eguchi, I. Yamaga, M. Dhamrin, K. Kamisako, and T. Saitoh, *J. Appl. Phys.* **102**, 054506 (2007).
- ¹⁰H. Sugimoto, M. Inoue, M. Tajima, A. Ogura, and Y. Ohshita, *Jpn. J. Appl. Phys.* **45**, L641 (2006).
- ¹¹T. Tachibana, J. Masuda, K. Imai, A. Ogura, Y. Ohshita, K. Arafune, and M. Tajima, *Jpn. J. Appl. Phys.* **48**, 121202 (2009).
- ¹²J. Chen and T. Sekiguchi, *Jpn. J. Appl. Phys.* **46**, 6489 (2007).
- ¹³J. Chen, T. Sekiguchi, R. Xie, P. Ahmet, T. Chikyo, D. Yang, S. Ito, and F. Yin, *Scr. Mater.* **52**, 1211 (2005).
- ¹⁴N. Usami, K. Kutsukake, K. Fujiwara, I. Yonenaga, and K. Nakajima, *Appl. Phys. Express* **1**, 075001 (2008).
- ¹⁵K. Kutsukake, N. Usami, T. Ohtaniuchi, K. Fujiwara, and K. Nakajima, *J. Appl. Phys.* **105**, 044909 (2009).
- ¹⁶T. Buonassisi, A. A. Istratov, M. D. Pickett, M. A. Marcus, and E. R. Weber, *Appl. Phys. Lett.* **89**, 042102 (2006).
- ¹⁷A. A. Istratov, T. Buonassisi, M. D. Pickett, M. Heuer, and E. R. Weber, *Mater. Sci. Eng. B* **134**, 282 (2006).
- ¹⁸T. Buonassisi, A. A. Istratov, S. Peters, C. Ballif, J. Isenberg, S. Riepe, W. Warta, R. Schindler, G. Willeke, Z. Cai, B. Lai, and E. R. Weber, *Appl. Phys. Lett.* **87**, 121918 (2005).
- ¹⁹J. Chen, T. Sekiguchi, D. Yang, F. Yin, K. Kido, and S. Tsurekawa, *J. Appl. Phys.* **96**, 5490 (2004).
- ²⁰R. Krain, S. Herlufsen, and J. Schmidt, *Appl. Phys. Lett.* **93**, 152108 (2008).
- ²¹M. Tajima, M. Ikebe, Y. Ohshita, and A. Ogura, *J. Electron. Mater.* **39**, 747 (2010).
- ²²M. Inoue, H. Sugimoto, M. Tajima, Y. Ohshita, and A. Ogura, *J. Mater. Sci.: Mater. Electron.* **19**, S132 (2008).
- ²³N. Stoddard, R. Sidhu, G. Rozgonyi, I. Witting, and P. V. Dollen, 3rd Internal Workshop on Crystalline Silicon Solar Cells, 2009.
- ²⁴N. Stoddard, B. Wu, I. Witting, M. Wagener, Y. Park, G. Rozgonyi, and R. Clark, *Solid State Phenomena* **131–133**, 1 (2008).
- ²⁵B. Chen, J. Chen, T. Sekiguchi, M. Saito, and K. Kimoto, *J. Appl. Phys.* **105**, 113502 (2009).
- ²⁶M. A. Tschoop and D. L. McDowell, *Philos. Mag.* **87**, 3147 (2007).
- ²⁷X. J. Chen, S. Nakano, L. J. Liu, and K. Kakimoto, *J. Cryst. Growth* **310**, 4330 (2008).
- ²⁸X. J. Chen, S. Nakano, and K. Kakimoto, *J. Cryst. Growth* **318**, 259 (2010).
- ²⁹I. Takahashi, N. Usami, K. Kutsukake, G. Stokkan, K. Morishita, and K. Nakajima, *J. Cryst. Growth* **312**, 897 (2010).
- ³⁰N. Usami, R. Yokoyama, I. Takahashi, K. Kutsukake, K. Fujiwara, and K. Nakajima, *J. Appl. Phys.* **107**, 013511 (2010).