**ON THE THEORETICAL RELATIONSHIP BETWEEN FLOW
STRESS AND LARGE NATURAL STRAINS IN TENSILE TESTS
ON STEEL CYLINDERS***

By T. Y. THOMAS

INDIANA UNIVERSITY, BLOOMINGTON, INDIANA

Communicated May 22, 1967

(1) *Introduction.*—In his work on large plastic flow and fracture, Bridgman¹ was led to the following set of equations for the principal stresses in the minimum section of neck of a circular steel cylinder subjected to a tensile force in the direction of its axis and an imposed hydrostatic pressure p , namely,

$$\sigma_{11} = -p + F \log \left(\frac{a^2 + 2aR - r^2}{2aR} \right), \quad (1)$$

$$\frac{\sigma_{22}}{r^2} = -p + F \log \left(\frac{a^2 + 2aR - r^2}{2aR} \right), \quad (2)$$

$$\sigma_{33} = -p + F + F \log \left(\frac{a^2 + 2aR - r^2}{2aR} \right), \quad (3)$$

relative to the usual system of cylindrical coordinates x^1, x^2, x^3 or r, θ, z such that the z axis coincides with the axis of the cylinder. The remaining components σ_{ij} of the stress tensor are equal to zero over the minimum section of the neck. The quantity a is the radius of the minimum section of the neck and R is the radius of curvature, at the point P , of the necked profile, i.e., the curve of intersection MPN of a plane through the central axis and the outer boundary of the cylinder after necking

(see Fig. 1). Finally, the quantity F in the equations (1), (2), and (3) is a constant which is called the *flow stress* by Bridgman. I have examined Bridgman's derivation of the equations (1), (2), and (3) and I have frankly been impressed with the mathematical ingenuity he displayed and with the care he took to justify his procedures with appropriate experimental evidence. There is little doubt in my mind

but that these relations express the stress field over the minimum section of the neck to a high degree of approximation.

To determine the flow stress F one has merely to equate the integral of the stress component σ_{33} over the minimum section of the neck to the applied load. This gives the relation

$$F \left(1 + 2 \frac{R}{a} \right) \log \left(1 + \frac{1}{2} \frac{a}{R} \right) = \frac{\text{load}}{\pi a^2} \quad (4)$$

in which it is observed that the hydrostatic pressure p does not appear due to the fact that the contribution of this pressure to the above integral is cancelled by its contribution to the actual load. After the measurements of a , R , and the load have been made, the flow stress F can be determined from the equation (4).

We shall be concerned in this paper with the theoretical relationship between the flow stress F and the *natural strain* defined as the logarithm of the ratio A_0/A where A_0 and A are the areas of the initial cross section of the cylinder and the minimum section of the neck, respectively. Table 1 gives the experimentally determined relationships between the flow stress and the natural strain for steels in the 11-0, 12-0, and 13-0 series; the corresponding graphs are shown in Figure 2. These graphs are linear to within experimental error and are typical of the relationship between flow stress and natural strain as found by tests on a large variety of steels. To determine the possible effect of hydrostatic pressure on the stress-strain curves, Bridgman later conducted a number of tests on steels in the 9-7 and 9-8 series which he refers

TABLE 1

Spec.	Hydrostatic pressure (psi)	Natural strain, $\log(A_0/A)$	Flow stress (psi)
11-0-1	359,000	0.22	159,000
11-0-2	360,000	0.88	190,000
11-0-3	267,000	1.73	242,000
11-0-4	370,000	2.39	274,000
12-0-1	325,000	0.27	188,000
12-0-2	345,000	0.95	233,000
12-0-3	340,000	1.71	283,000
12-0-4	352,000	2.54	337,000
13-0-1	340,000	0.33	223,000
13-0-2	370,000	0.82	261,000
13-0-3	365,000	1.51	303,000
13-0-4	360,000	2.05	348,000

TABLE 2

Spec.	Hydrostatic pressure (psi)	Natural strain, $\log(A_0/A)$	Flow stress (psi)
9-7-5	385,000	1.250	222,000
9-7-7	365,000	2.190	270,000
9-7-8	370,000	2.766	316,000
9-7-9	352,000	2.367	285,000
9-7-10	355,000	1.732	246,000
9-7-11	365,000	2.146	278,000
9-7-12	369,000	3.289	325,000
9-7-5	Atmos.	1.332	195,000
9-7-7	Atmos.	2.262	239,000
9-7-8	Atmos.	2.786	254,000
9-7-9	Atmos.	2.580	238,000
9-7-10	Atmos.	1.755	207,000
9-7-11	Atmos.	2.176	225,000
9-7-12	Atmos.	3.317	264,000

to as tempered pearlite and tempered martensite, respectively. The behavior of these two steels was found to be qualitatively the same and we shall therefore list only the requisite data from the tests on tempered pearlite in Table 2. After the samples were tested at the large hydrostatic pressures shown in Table 2, they were again tested at atmospheric pressure. Figure 3, in which the dotted lines connect points obtained from the two above-mentioned tests on the same sample, shows the resulting graphs. Bridgman has interpreted these graphs as indicating that a hy-

FIG. 2.

FIG. 3.

drostatic pressure will produce an increase in the flow stress which is proportionally greater at large strains than at small strains. However, I do not believe that his interpretation is correct. This matter will be discussed later on the basis of our theory of the relationship between flow stress and natural strain.

(2) *The Basic Flow Equations.*—Our problem is now to construct an appropriate system of flow equations, and in this connection the following set of assumptions will be made.

(α) *The flow is incompressible.*

(β) *The time derivatives of the components of the stress deviator are proportional to the corresponding components of the rate of strain tensor.*

(γ) *The coefficient in the above proportionality is a constant which depends on the plastic properties of the material.*

Assumption (α) is equivalent to the condition

$$g^{ij}v_{i;j} = 0 \quad (5)$$

in which the v_i are the covariant components of the velocity, the g^{ij} are the contravariant components of the metric tensor, and the semicolon denotes covariant differentiation. The condition of incompressibility expressed by (5) is ordinarily assumed in dealing with plastic flow and appears to be satisfied in general to within the required degree of approximation. It follows from (5) that the components of the rate of strain tensor which are defined by

$$\epsilon_{ij} = 1/2(v_{i;j} + v_{j;i}) \quad (6)$$

are identical with the components of its deviator. This fact obviously indicates that the influence of the stress field on the plastic flow will be exerted primarily through the deviator of the stress tensor. Assumption (β) provides us with a system of equations of this character, namely,

$$\frac{D\sigma_{ij}^*}{Dt} = \varphi \epsilon_{ij} \quad (7)$$

in which the σ_{ij}^* are the components of the stress deviator and the quantity φ is a constant in accordance with Assumption (γ). The left members of the equations (7) are the components of the *absolute time derivative* of the stress deviator; they reduce to the ordinary time derivatives in a system of rectangular coordinates. Absolute time differentiation must be employed in general in writing the equations (7) in order to secure their invariance under coordinate transformations, for example, the transformation from a rectangular system to the system of cylindrical coordinates used in the discussion of the present problem. The equation of incompressibility (5) and the five independent equations (7) constitute a set of six equations for the characterization of the plastic flow.

To ensure the realization of plastic flow which is assumed in the above discussion, one may formally impose the condition

$$(\sqrt{1 + k^2} + k)s_1 - (\sqrt{1 + k^2} - k)s_3 \geq 2K \quad (8)$$

in view of the results in several previous articles;² here s_1 and s_3 are the algebraically greatest and least of the principal stresses and the quantities k and K are

elastic moduli. In this connection it may be observed that (8) cannot reduce to an equality since this would require the flow stress F to be constant during the necking process in contradiction to Bridgman's observations.

It will be seen from the derivations in the following section that the above flow equations lead to a very simple theoretical explanation of Bridgman's experimental results on flow stress and natural strain. But this is no more than one has a right to expect in view of the linear relationship between these quantities as shown by the graphs in Figs. 2 and 3. Indeed any theory of the relationship between flow stress and natural strain which is not of extreme simplicity should, in my opinion, be regarded with considerable skepticism.

(3) *Derivation of the Theoretical Relationship between Flow Stress and Natural Strain.*—It may be helpful to the reader if we recall that the components σ_{ij}^* of the stress deviator are given by the general formula

$$\sigma_{ij}^* = \sigma_{ij} - \frac{1}{3}(g^{km}\sigma_{km})g_{ij} \quad (9)$$

in which there is a summation on the repeated indices k and m over the values 1, 2, 3; this well-known summation convention is used in the above equation (5) and in the following equations in this article. The nonvanishing covariant components g_{ij} and contravariant components g^{ij} of the metric tensor have the values

$$g_{11} = g_{33} = g^{11} = g^{33} = 1; \quad g_{22} = r^2; \quad g^{22} = 1/r^2 \quad (10)$$

in the cylindrical coordinate system with which we are here concerned; also the only nonvanishing Christoffel symbols in the cylindrical system are the symbols Γ_{12}^2 and Γ_{22}^1 and these have the values $1/r$ and $-r$, respectively. Finally, let us recall the following formulas of differentiation, namely,

$$\frac{D\sigma_{ij}^*}{Dt} = \frac{d\sigma_{ij}^*}{dt} - \sigma_{kj}^*\Gamma_{im}^k v^m - \sigma_{ik}^*\Gamma_{jm}^k v^m, \quad (11)$$

$$v_{i;j} = \frac{\partial v_i}{\partial x^j} - v_k \Gamma_{ij}^k, \quad (12)$$

in which the v^m are the contravariant components of the velocity whose covariant components appear in the equation of incompressibility (5) and the above equations (12).

Let us next observe that

$$\begin{aligned} v_1 &= g_{1j}v^j = v^1, \\ v_2 &= g_{2j}v^j = r^2v^2, \\ v_3 &= g_{3j}v^j = v^3, \end{aligned}$$

on account of (10); these are the usual equations relating the covariant and contravariant components of a vector. But it is clear from symmetry that v^2 will vanish everywhere and that v^3 must vanish in the minimum section of the neck; hence in this section of the neck it follows that

$$v_1 = v^1; \quad v_2 = v_3 = v^2 = v^3 = 0. \quad (13)$$

We shall also have occasion to use the following explicit form of the equation of in-

compressibility, namely,

$$\frac{\partial v_1}{\partial r} + \frac{v_1}{r} + \frac{\partial v_3}{\partial z} = 0 \quad (14)$$

which is readily obtained from (5) when we make the substitution (12) and take account of the rotational symmetry of the flow.

A consideration of two of the equations (7), e.g., those obtained by assigning the values 1,1 and 3,3 to the indices, will suffice for our purpose. Making use of (6) and the various relations (9), . . . , (14) the above two equations become

$$\frac{d}{dt} \left(2\sigma_{11} - \frac{\sigma_{22}}{r^2} - \sigma_{33} \right) = 3\varphi \frac{\partial v_1}{\partial r}, \quad (15)$$

$$\frac{d}{dt} \left(2\sigma_{33} - \sigma_{11} - \frac{\sigma_{22}}{r^2} \right) = 3\varphi \frac{\partial v_3}{\partial z} = -3\varphi \left(\frac{\partial v_1}{\partial r} + \frac{v_1}{r} \right), \quad (16)$$

in the minimum section of the neck of the cylinder; we observe here in particular the use made of the incompressibility condition (14) in obtaining the final form of the equation (16). Adding the equations (15) and (16), we have

$$\frac{d}{dt} \left(\sigma_{11} + \sigma_{33} - \frac{2\sigma_{22}}{r^2} \right) = -3\varphi \frac{v_1}{r}. \quad (17)$$

But the contravariant velocity component v^1 is given by the derivative dr/dt and hence the covariant velocity component v_1 is likewise equal to this derivative on account of the first relation (13). Hence (17) becomes

$$\frac{d}{dt} \left(\sigma_{11} + \sigma_{33} - \frac{2\sigma_{22}}{r^2} \right) = -3 \frac{\varphi}{r} \frac{dr}{dt}. \quad (18)$$

Now suppose that the cylinder necks down in the time t from its initial radius r_0 to the radius a which has entered into the preceding discussion as the radius of the minimum section of the neck (see Fig. 1). Integrating (18) between these limits, we have

$$\int_0^t \frac{d}{dt} \left(\sigma_{11} + \sigma_{33} - \frac{2\sigma_{22}}{r^2} \right) dt = -3 \int_0^t \frac{\varphi}{r} \frac{dr}{dt} dt = -3\varphi \int_{r_0}^a \frac{dr}{r} \quad (19)$$

since φ is constant by assumption. But

$$-3\varphi \int_{r_0}^a \frac{dr}{r} = 3\varphi \log \frac{r_0}{a} = \frac{3}{2} \varphi \log \frac{r_0^2}{a^2} = \frac{3}{2} \varphi \log \frac{A_0}{A}, \quad (20)$$

where the quantity $\log (A_0/A)$ is the natural strain defined in section 1. The integral in the left member of (19) gives

$$\sigma_{11}(a) + \sigma_{33}(a) - \frac{2\sigma_{22}(a)}{a^2} - \sigma_{11}(r_0) - \sigma_{33}(r_0) + \frac{2\sigma_{22}(r_0)}{r_0^2} \quad (21)$$

in which the various terms are evaluated as indicated. Putting $r = a$ in the equations (1), (2), and (3) we obtain

$$\sigma_{11}(a) = -p; \quad \frac{\sigma_{22}(a)}{a^2} = -p; \quad \sigma_{33}(a) = F - p \quad (22)$$

from which the values of the first three terms in (21) are determined. At the start of the necking process the radius of the cylinder is r_0 and the stress field consists of a hydrostatic pressure p superimposed on a simple tension in the direction of the axis of the cylinder; hence the stress components $\sigma_{11}(r_0)$, $\sigma_{22}(r_0)$, and $\sigma_{33}(r_0)$ are given by

$$\sigma_{11}(r_0) = -p; \quad \frac{\sigma_{22}(r_0)}{r_0^2} = -p; \quad \sigma_{33}(r_0) = \tau - p \quad (23)$$

where τ is the *tensile strength* of the cylinder. Making the substitutions (22) and (23) the expression (21) now reduces to $F = \tau$. Hence the equation (19) becomes

$$F = \text{tensile strength} + \frac{3}{2} \varphi \log \frac{A_0}{A} \quad (24)$$

when account is also taken of the relation (20). But from the result in our foregoing article² we know that

$$\text{tensile strength} = gp + h$$

where the quantities g and h are given in terms of the elastic moduli k and K of the cylinder by the equations

$$g = 2k(\sqrt{1 + k^2} - k); \quad h = 2K(\sqrt{1 + k^2} - k).$$

It remains only to substitute the above expression for the tensile strength into the equation (24) to obtain the result that

$$F = gp + h + \frac{3}{2} \varphi \log \frac{A_0}{A}. \quad (25)$$

Equation (25) is the equation relating the flow stress F and the natural strain $\log(A_0/A)$ when the cylinder is pulled at the hydrostatic pressure p .

(4) *Comparison between Theory and Experiment.*—The variation of tensile strength with hydrostatic pressure is small and will frequently be within the experimental error even for comparatively large pressures. It follows that there must also be a correspondingly small variation of flow stress with pressure as we see from the equation (24). The tensile strengths during the pullings of each of the steels in the 11-0, 12-0, and 13-0 series can therefore be regarded as effectively constant and hence the experimental graphs must approximate straight lines as shown in Figure 2 in accordance with equation (24) or (25). The slope of each of these graphs will be given by $3\varphi/2$ where φ is the plastic modulus of the samples in the series under consideration and the tensile strengths will be given by the F intercepts. Similar remarks apply to the upper graph in Figure 3 obtained from tests on virgin samples of tempered pearlite under the large hydrostatic pressures shown in Table 2.

The situation is somewhat different in the case of the lower graph in Figure 3. In fact the cylinders would have fractured well before the large strains were reached if one had attempted to carry out these tests using virgin material at atmospheric pressure. It is clear therefore that the mechanical properties of the samples were altered by the prestraining and hence the values of the moduli k , K , and φ of the samples must also have been changed. Recognizing this fact and assigning the

appropriate values to these moduli, the theoretical graph obtained from the equation (25) will be a straight line which will closely approximate the experimental graph as shown in Figure 3.

According to the equation (25) the flow stress F varies linearly both in the hydrostatic pressure and the natural strain. Bridgman (ref. 1, p. 69) appears to have arrived at this result for strains in the intermediate range but he was not able to assert its validity under all conditions since he could not distinguish, solely on the basis of his observational data, between effects due to pressure and those due to changes in mechanical properties produced by prestraining.

* Supported by the U. S. Army Research Office (Durham).

¹ Bridgman, P. W., *Studies in Large Plastic Flow and Fracture*, Metallurgy and Metallurgical Engineering Series (New York: McGraw-Hill, 1952).

² Thomas, T. Y., "Theoretical effect of large hydrostatic pressures on the tensile strength of materials," these PROCEEDINGS, 57, 1195 (1967). Other references will be found in this article.