Published in final edited form as:

Biomed Mater. 2012 April ; 7(2): 024108. doi:10.1088/1748-6041/7/2/024108.

Critical Factors Affecting Cell Encapsulation in Superporous Hydrogels

Esha S Desai¹, Mary Y Tang¹, Amy E Ross², and Richard A Gemeinhart^{1,2,3,4}

¹Department of Biopharmaceutical Sciences, University of Illinois, 833 South Wood Street (MC 865), Chicago, IL 60612-7231.

²Department of Bioengineering, University of Illinois, Chicago, IL 60607-7052.

³Department of Ophthalmology and Visual Science, University of Illinois, Chicago, IL 60612-4319.

Abstract

We recently showed that superporous hydrogel scaffolds promote long-term stem cell viability and cell driven mineralization when cells were seeded within the pores of pre-fabricated SPH scaffolds. The possibility of cell encapsulation within SPH hydrogel matrix during its fabrication was further explored in this study. The impact of each chemical component used in the SPH fabrication and each step of the fabrication process on cell viability was systematically examined. Ammonium persulfate, an initiator, and sodium bicarbonate, the gas-generating compound, were the two components having significant toxicity toward encapsulated cells at the concentrations necessary for SPH fabrication. Cell survival rates were $55.7 \pm 19.3\%$ and $88.8 \pm 9.4\%$ after 10 minute exposure to ammonium persulfate and sodium bicarbonate solutions, respectively. In addition, solution pH change via the addition of sodium bicarbonate had significant toxicity toward encapsulated cells with cell survival of only $50.3 \pm 2.5\%$. Despite toxicity of chemical components and the SPH fabrication method, cells still exhibited significant overall survival rates within SPHs of $81.2 \pm 6.8\%$ and $67.0 \pm 0.9\%$, respectively, 48 and 72 hours after encapsulation. This method of cell encapsulation holds promise for use *in vitro* and *in vivo* as a scaffold material for both hydrogel matrix encapsulation and cell seeding within the pores.

Keywords

Porous; hydrogels; scaffolds; cell encapsulation; tissue engineering; macroporous polymers

1. Introduction

Hydrogels are three-dimensional, hydrophilic, physically or chemically crosslinked polymer networks that have shown potential in tissue engineering applications. Their resemblance to extracellular matrix and ability to absorb large amounts of water makes them conducive for cell growth and differentiation [1]. Their permeability allows the passage of nutrients by diffusion, while simultaneously providing an outlet for waste disposal. Hydrogels can be made of many different polymers and polymerized using different techniques, yielding a variety of mechanical and chemical properties to suit the specific application [2].

Cells can be incorporated into a nonporous hydrogel scaffold either by attachment to the surface (figure 1A) or encapsulation (figure 1B). There are multiple advantages to encapsulating cells within the hydrogel polymer matrix. Certain polymers, including

⁴Author to whom any correspondence should be addressed. rag@uic.edu.

poly(ethylene glycol) diacrylate-based systems, exhibit poor cell attachment, rendering cell growth on the surface difficult. The scaffold acts as a mechanical barrier, protecting encapsulating cells from the immune system in the *in vivo* environment [3]. The encapsulation process also ensures a uniform distribution of cells within the scaffold [4]. However, one of the disadvantages of encapsulating cells within a hydrogel is that the conditions of polymerization, such as the initiators used, are known to exhibit cytotoxicity [5] and thick constructs restrict oxygen and nutrient transport [6].

One approach to overcoming transport limitations is to make porous hydrogels, including superporous hydrogels (SPHs). SPHs absorb water in a very short period of time due to the presence of continuously interconnected pores with diameters in the micron to millimeter scale [7]. The large pore size and a highly inter-connected pore network [8] leave short diffusion path lengths (~100 μm) making it possible to reach equilibrium swelling within minutes [9]. In addition, these short diffusion lengths within the hydrogel matrix would be expected to allow significant transport of nutrients and oxygen. SPHs were recently used as a scaffold for human mesenchymal stem cells and shown to exhibit mineralization in the presence of osteogenic media when grown on the interior pore surface of the SPH [10] (figure 1C). SPHs also have potential for the challenging task of vascularizing engineered tissue. Acellular SPHs implanted in mice were vascularized within the pores within two weeks [11]. However, the functionality and versatility of SPHs could be enhanced if cells could be encapsulated within the hydrogel matrix (figure 1D). Of particular interest is the potential to co-culture cells of different types necessary for the formation of heterogeneous tissues.

Based upon the multitude of publications that have clearly shown that cells can be easily and reproducibly incorporated into poly(ethylene glycol) diacrylate (PEGDA) hydrogels [5, 12–15], the hypothesis that cells could survive the encapsulation process in SPHs was investigated (figure 1D). It was thought that a fabrication process should be possible for creation of three-dimensional porous scaffolds if the parameters for foaming could be controlled. Thus, in the present study, the effect of the concentration of each critical chemical component and the foaming mechanism were examined. The current study also provides an understanding of the parameters that must be controlled to allow cell encapsulation within superporous hydrogels. Despite the relative toxicity of some of the components, cells survive polymerization and encapsulation within superporous hydrogels.

2. Materials and Methods

2.1. Materials

Chemicals were purchased from Fischer Scientific (Pittsburgh, Philadelphia) as reagent grade and used as received unless otherwise specified. PEGDA (MW= 3,400 g/mol) was purchased from Glycosan Biosystems (Salt Lake City, Utah), citric acid from spectrum chemicals, and Pluronic® F-127 (PF127) from Sigma (St. Louis, Missouri).

2.2. Fibroblast Culture

NIH-3T3 fibroblast cells (fibroblasts derived from *Mus musculus*; CRL-1658) were obtained from American Type Culture Collection (ATCC; Manassas, Virginia). Cells were cultured in 150 cm^2 flasks (Corning Inc., Corning, NY) using Dulbecco's modified essential medium (DMEM; Mediatech, Manassas, Virginia) supplemented with 5% bovine serum (Mediatech, Manassas, Virginia) at 37°C and in the presence of 5% carbon dioxide. The medium was changed twice weekly. Prior to confluence, cells were trypsinized using 0.5% trypsin-EDTA (Mediatech, Manassas, Virginia), counted using a Coulter counter, and plated

on 48 well plates (Corning Inc., Corning, NY) at a density of 10^5 cells/mL unless otherwise noted.

2.3. Cell Viability

For cells grown on culture plates, the CellTiter 96[®] AQueous non-radioactive cell proliferation assay (MTS assay) [16] was purchased from Promega (Madison, Wisconsin) and performed as per the manufacturer's protocol. A standard curve was obtained by plotting cell number seeded against measured absorbance value. The controls used for background absorbance were acellular SPHs in Dulbecco's phosphate buffered saline (DPBS; Invitrogen) and empty wells. The MTS assay was found to be unsuitable for encapsulated cell measurement due to background interference caused by the hydrogel. However, the MTS assay has been previously shown to be applicable to measure viability of cells adhering to the surface of the hydrogels [10].

Therefore, for encapsulated cells, total DNA was used to quantify the number of cells present. The Quant-iT[™] picogreen[®] dsDNA assay kit [17] was purchased from Molecular Probes (Carlsbad, California) and the manufacturer's protocol followed after homogenizing the hydrogel samples in DPBS. A standard curve was obtained using cells directly encapsulated in PEGDA hydrogels (without foaming) and then homogenized. In addition, it was confirmed that dead cells, i.e. ethanol treated, showed limited background in the assay.

2.4. Epifluorescent Microscopy

The LIVE/DEAD[®] cell viability assay kit, comprised of ethidium homodimer [18] and calcein acetomethoxy ester (calcein AM), was purchased from Invitrogen (Carlsbad, California) and the assay performed as per manufacturer's protocol. Optical images were obtained using an Olympus IX-70 inverted microscope and captured using a Retiga 1300 CCD camera. Images were then processed using the IPLab software.

2.5. Component cytotoxicity

NIH-3T3 cells were treated with each of the components used in the macromer mix for SPH fabrication and incubated for 10 minutes, 24 hours, 48 hours, or 72 hours. The treatment groups were compared to the control group consisting of cells incubated with 250 μ L of medium in order to assess cell viability using MTS assay and LIVE/DEAD staining. As noted, cells in both treated and control groups were washed in DPBS with calcium and magnesium prior to viability determination.

2.6. pH Cytotoxicity

NIH-3T3 cells were treated with medium pre-adjusted to a pH of 5 and then either 100 mg/mL of sodium bicarbonate or 5 M sodium hydroxide added until medium pH rose to an alkaline pH of 8. This pH change was conducted within the span of 10 minutes in order to simulate the pH transition in the foaming step in the SPH fabrication process. Two control groups consisting of cells at the original densities in medium adjusted to either pH 5 or 8 were used for comparison. Following treatment, medium was aspirated and cells were washed in DPBS with Ca and Mg prior to viability determination or microscopic imaging.

In order to test the toxicity of precursor solution for SPH fabrication in combination with sudden pH change, NIH-3T3 cells (1×10^5 cells/mL) were suspended in medium containing the precursor solution. This precursor solution consisted of PEGDA replaced with poly(ethylene glycol) (PEG; MW 4,000) which prevented polymerization and allowed for cell recovery. A second experimental group was established with similar conditions except for sodium bicarbonate being substituted with 10 μ L of 5.0M sodium hydroxide (no foam, but pH change). Both treatment groups were compared to the control (substituted with an

equivalent amount of DPBS with Ca and Mg for the precursor solution) for viability determination or microscopic imaging.

2.7. Synthesis of SPHs

Stock solutions of PEGDA, tetramethylethylenediamine (TEMED), PF127, citric acid were prepared and combined as previously described [10] and a cell suspension solution of 1×10^6 cells/mL in medium was added to the precursor mix. Ammonium persulfate (APS) was then added to the precursor solution and the entire macromer solution vortexed to obtain a homogeneous solution. This solution was heated by holding the vial in a water bath at 37°C for 2 min with intermittent vortexing of the vial. To ensure proper foaming, the solution was confirmed to be at a pH of approximately 5. Sodium bicarbonate was then added immediately to the vial and the solution allowed to stand for 5 minutes in order to obtain complete polymerization. A wet, sterile spatula was used to remove the newly formed SPHs. These SPHs were allowed to swell in medium for 30 min.

As comparator groups, two nonporous hydrogels (NPH) were formed. First, sodium hydroxide (non-foaming; 10 μL of 5.0M) was substituted for sodium bicarbonate in order to adjust the pH and allow for the formation of nonporous hydrogels (NPH-A/T). In this case, all components were equivalent with only the absence of foaming and the particles of sodium bicarbonate. With this comparator, we were able to examine hydrogel formed without foaming, while maintaining the pH change. In the second NPH (NPH-I), a conventional formulation [12, 19] was used in which PEGDA and Irgacure® 2959 were the only components of the precursor mixture, i.e. no PF127, citric acid, APS, or TEMED were added. Irgacure® 2959 (0.075 (w/v) %) was used as the photoinitiator with exposure to UV light at wavelength of 365 nm ($5 \text{ mW}/\text{cm}^2$) for 10 minutes. With this comparator, we were able to assess the system compared to a conventional PEGDA hydrogel system of similar composition.

2.8. Statistical Analysis

Data was analyzed using one-way ANOVA followed by post-hoc unpaired t-tests when appropriate. All results are reported as mean plus or minus ($\pm$) standard deviation. To confirm the reproducibility of the data, a minimum of three identical, independent replicates were performed.

3. Results and Discussion

To investigate if cells can survive the fabrication of SPHs, the effect of each chemical constituent in the precursor solution was separately tested on NIH-3T3 cells. These experiments were designed based on the actual SPH fabrication conditions that the cells would be exposed to for varying periods of time. Our experimental evaluation also took into account the possibility of unreacted macromer and initiator remaining in solution after polymerization. The pH for all cell treatment solutions was maintained at 5 for the 10 minute experiment, replicating the original precursor solution pH (before polymerization) during SPH fabrication, and at normal cell culture pH for the remainder of the time points. In addition to the conditions described in this manuscript, other concentrations were examined over this time period. The majority of the components of the SPH show toxicity, but these same components are typically used for other PEGDA encapsulation systems with limited toxicity during polymerization. The primary new components, citric acid, Pluronic PF127, and sodium bicarbonate are the primary contributors to individual toxicity.

3.1 Component Cytotoxicity

3.1.1. PEGDA Cytotoxicity—As the predominant component of hydrogels, PEGDA was used in the synthesis of SPHs at a final concentration of 15 (w/v) % [10]. In order to test for the influence of PEGDA on cell growth, cells were treated with 15% (w/v) % PEGDA at varying time points (figure 2, **row 1**). Compared to untreated controls, there was statistically significant toxicity and morphological changes observed when NIH-3T3s were incubated with 15% (w/v) % PEGDA at 24 hr, 48 hr, and 72 hr ($p < 0.001$). However, during the formation of SPHs, the cells were exposed to 15% (w/v) % PEGDA for only 10 minutes and for this condition the was not substantial (greater than 75% viability) toxicity.

3.1.2. TEMED Cytotoxicity—After confirmation of minimal PEGDA toxicity on cells at 10 min. exposure, each of the other chemical components in the precursor solution was then separately examined. TEMED was used at a concentration of 0.90 (w/v) % in the synthesis of SPHs. As an initiation catalyst, TEMED is known to accelerate the scission of APS yielding sulphate, hemi-TEMED and hydroxyl radicals, which initiate polymerization [20]. There was no significant toxicity observed (figure 2, **row 2**) when cells were treated with 0.9 (w/v) % TEMED for 10 minutes when compared to the untreated control. However, at incubation times of 24, 48, and 72 hrs, massive cell death and a rounded, non-adherent morphology from the few remaining live cells was observed. This demonstrated that exposure to TEMED for an extended period of time is a significant source of toxicity. This is particularly a concern since TEMED is not consumed during the polymerization process. As will be discussed further, it is recommended that the initiator system be changed from APS/TEMED to a less toxic initiator system.

3.1.3. APS Cytotoxicity—APS was used at a concentration of 0.70 (w/v) % in the formula of SPHs and is an initiation partner with TEMED. Cells treated with 0.70 (w/v)% APS also showed significant toxicity (figure 2, **row 3**) at all time points, *i.e.* 10 min, 24 hrs, 48 hrs, and 72 hrs, with morphological changes occurring in remaining living cells. The most possible explanation for such toxicity is the decomposition of APS which releases reactive free radicals which can cause cell damage and subsequent death [21]. However, it is important to note that during the encapsulation process, cells are exposed to a lower initiator concentration. Despite this toxicity and as this will be discussed later, it is expected that the free radicals are, at least in part, consumed by the growing polymer chains leading to the observed higher survival rate for encapsulated cells. As is now clear, the APS/TEMED initiator pair has substantial toxicity toward cells and the TEMED, which is not consumed in the reaction, has lasting toxicity. There is clear need to identify more appropriate initiators.

3.1.4. Citric Acid Cytotoxicity—The buffering agent citric acid was used to adjust the pH to 5 at a concentration of 2.4 (w/v) % during SPH fabrication. There was a statistically significant difference in cell viability with 2.4 (w/v) % citric acid treatment at 10 min, 24, 48 and 72 hr compared to the DPBS control group (figure 2, **row 4**). Morphologically, there is clear rounding of cells and permeabilization of the cells (as shown by red, DNA-stained, cells) beginning at 10 minutes and at later times any remaining live cells appeared rounded and loosely adherent. There is an apparent discrepancy between the MTS data and microscopic observations. If one thinks about the mitochondrial activity measure in the MTS activity, a cell that has been perturbed (pharmacologically) will take some time to respond and decrease mitochondrial activity. In this case, there is apparent cell toxicity by the live/dead assay since most cells are permeable and many were morphologically altered. Also, the MTS assay examined the entire well which allows local regions of live cells, which may not be visualized or captured in a representative image, to be counted as alive. In this way, the MTS assay is unbiased compared to imaging techniques.

The pH of medium was originally adjusted to 7.4 when cells were treated with citric acid over 24, 48, and 72 hr. However the pH cannot be maintained because incubation with citric acid over longer periods of time caused a drop back to acidity. It is believed that this acidic pH may be one cause of cellular death. However, based on metabolic activity (MTS), cell morphology, and permeability after 72 hours, citric acid itself was also deemed toxic towards NIH-3T3s. Tighter control on pH may minimize this effect, but a system where the pH does not have to be acidic would allow for the removal of this component altogether. Citric acid is not one of the more critical components, but it is clear that it has influence on cell survival.

3.1.5. Pluronic Cytotoxicity—Pluronic® stabilizes the foam during SPH formation by spontaneously adsorbing at the air-water interface, reducing surface energy, and thus preventing foam collapse before polymerization can take place. Pluronic® has already been shown to be a superior stabilizer for a variety of monomer systems {e.g.: acrylamide (AM), hydroxyethyl methacrylate (HEMA), hydroxypropyl methacrylate (HPMA), potassium salt of 3-sulfopropyl acrylate (SPAK)} used in SPH fabrication compared to other alternatives including albumin, gelatin, Pluronic® 105, Silwet®, sodium dodecyl sulfate, Span®, Triton®, Tween® [7]. Cells treated with 0.6% (w/v) Pluronic, the same used in the formation of SPH, showed neither cell death nor significant morphological changes at most time points (10 min, 24 hrs, and 48 hrs) (figure 2, **row 5**). It should be noted that at 72 hrs there was no observable toxicity, but significant morphologic changes that indicate possible negative implications. The toxicity of Pluronic® has been shown to be concentration dependant [22]. Pluronic® caused little hindrance to cell proliferation in the concentration range of 0.1 to 5 (w/v) % for 5 days after treatment [22]. However, HMEC-1 (endothelial), L6 (muscle) cell lines and human liver carcinoma cells (HepG2) treated with 10 (w/v) % Pluronic were less viable than untreated cells and Pluronic in the range of 15 to 20 (w/v) % caused complete cell death [22]. These concentration levels are well above the levels used in SPH fabrication. Therefore, it can be concluded that Pluronic® at the concentration used in our SPH fabrication system is a not a cause of cellular toxicity.

3.1.6. Sodium Bicarbonate Cytotoxicity—Sodium bicarbonate has two functions in the SPH formulation; the primary of which is to generate gas for foam creation which is then stabilized by surfactant, *i.e.* Pluronic®. It is the escape of carbon dioxide during this reaction that gives the SPH its interconnected network. Sodium bicarbonate also neutralizes the pH of the reaction mixture to a point where TEMED can become active as a co-initiator with APS [7]. The concentration of sodium bicarbonate used in the formation of our SPHs was 200 mg/mL and in this experiment, significant cell death and morphological changes occurred upon sodium bicarbonate treatment/incubation (figure 2, **row 6**). At 10 min, most cells were still alive as indicated by a few cells exhibiting red fluorescent staining and this was further supported by the MTS assay indicating that more than 50% of control viability. Cells treated with sodium bicarbonate were slower growing at 24 hrs as indicated by a significant drop in MTS value, but maintained their morphology. Some dead (red) cells were also observed at this time. However, with longer incubation times, cells became rounded and non-adherent leading to death to the majority at 72 hours. Clear sodium bicarbonate crystals are visible on the culture plate, and these are the predominant feature at later times. It has been reported in literature that concentrations of 2.1, 4.2, and 8.4 mg/mL of sodium bicarbonate does not affect viability of endothelial derived EA.hy 926 cell line for 6 hr [23]. However, the concentration of sodium bicarbonate used in our experiment was significantly higher. At such high exposure levels, it can be concluded that sodium bicarbonate is a significant source of cell toxicity.

3.2. pH Cytotoxicity

During the SPH fabrication process, cells were first suspended in a solution buffered at pH 5 (compared to typical cell culture medium which maintains a pH in the range of 7.0 to 8.0). To continue to understand how each step involved in superporous hydrogel influences cell survival, we examined how cells respond to this lowered pH (figure 3). For short periods, there is limited influence of the decreased pH on cell viability. At longer times (> 24 hours), there is clear cell toxicity, but some cells still exhibit normal morphology. Since the pH alone does not have immediate impact, the influence of the change in pH was examined.

On addition of sodium bicarbonate, there occurs a sudden change from acidic to alkaline conditions (pH 8). To examine this, we seeded cells in tissue culture media adjusted (with HCl) to pH 5 and treated the cells with either sodium bicarbonate or sodium hydroxide to reach normal pH for culture (figure 4). In this case (figure 4), cells were rounded since they were plated and examined after 10 minutes accounting for the abnormal morphology and live (green), rounded cells. There was statistically greater toxicity ($p < 0.001$) for the sodium bicarbonate treatment, but both groups exhibited at least 40% toxicity after 10 minutes. Two reasons can be proposed for the greater toxicity with sodium bicarbonate: the large particles have surface-induced toxicity and the chemical species themselves are more toxic. While the sodium bicarbonate addition step is critical to the fabrication of SPHs, because it contributes to the porous nature of the gels, this sudden change in pH was significantly toxic to cells and was similar in toxicity compared with an single component. We are currently examining other methods of gas formation that does not mandate the rapid pH change to avoid this significant problem.

3.3. Chemical Foaming Cytotoxicity

The gas foaming process may be deleterious to cell viability. For this experiment, PEGDA was substituted with PEG in order to prevent the polymerization of the precursor solution and which would then allow us to study the foaming process alone without the difficulty of assessing or confounding responses of cells growing within the hydrogel matrix. In one group, cells were treated with a precursor solution of PEG, APS with TEMED, citric acid and sodium bicarbonate that had the ability to produce foam but which could not polymerize. Sodium hydroxide was substituted for sodium bicarbonate in the second experimental group with all other conditions maintained. This prevented the foaming process (similar to the procedure used in the NPH-A/T formation). Approximately 70% cell death was observed in the group treated with SPH precursor solution compared to approximately 50% cell death in the group treated with NPH-A/T precursor solution (figure 4). Therefore, it can be concluded that the majority of cell toxicity was due to the composition of the macroporous hydrogels with additional cell death resulting from the rapid change in pH and the limited further toxicity foaming process itself. The foaming process is one of minimal contributing factors toward toxicity.

3.4. Effect of Cell Encapsulation on Viability

In order to determine the effect of encapsulation within the hydrogel matrix on cell viability, NIH-3T3 cells were encapsulated within either SPHs or NPHs and observations taken over the span of 7 days (figure 5). At the end of 24 hr there were $0.95 \pm 0.07 \times 10^6$ viable cells/SPH which in the next 6 days reduced ($p < 0.001$) to $2.26 \pm 0.18 \times 10^5$ viable cells/SPH. Possible reasons for cell death, as already mentioned, are toxicity of APS or sodium bicarbonate, foaming technique, or rapid change in pH of the precursor solution from acidic to alkaline during the fabrication or encapsulation processes. In the case of cells encapsulated in NPH-A/T hydrogels, viability was approximately $1.07 \pm 0.02 \times 10^6$ cells/NPH at the end of 24 hr which dropped ($p < 0.001$) to $1.19 \pm 0.163 \times 10^5$ cells/NPH over the next 6 days. While the causes of cell death were similar to the reasons listed for SPH encapsulation, there was a

two-fold decrease in living cells when encapsulated in NPH compared to SPH. This confirms the importance of hydrogel pore availability in promoting cell viability by allowing for both attachment and the exchange of nutrients, release of waste materials, etc [24]. We conclude that for successful encapsulation using this cell line, SPHs may be more suitable than NPHs formed using this method ($p < 0.001$). We confirmed this by using the same formula and also a formula which has been widely investigated in the literature using Irgacure® as the initiator [12, 15, 19, 25, 26]. For the earliest time point, our porous hydrogel maintains the cells similarly to that of the similarly polymerized hydrogel (NPH-A/T), but by 72 hours the Irgacure® polymerized hydrogels stabilize the cell population ($1.09 \pm 0.01 \times 10^6$; $p < 0.001$ compared to SPH and NPH-A/T) while the SPHs have substantial cell loss. We hope, in the near future, to utilize the information learned through this study to improve the foaming system to eliminate the pH change and possibly the polymerization initiators. It should be noted, however, that this study was a significant success as it is counterintuitive that the cells would survive to a much higher extent when the SPH was formed than when each of the components was examined individually or even in combination.

A method for cell encapsulation in hydrogels has been developed that can be easily utilized by any investigator. Although there is only moderate advantage in terms of survival when compared to the equivalent nonporous hydrogels, much was learned from this study that can be used in the future for improving and utilizing the method for pore formation and cell encapsulation. There was much surprise that the system would allow the cell survival observed since we did foresee much of the toxicity associated with specific components. Since we clearly observed survival, we are encouraged to investigate methods that will not utilize the pH change associated with sodium bicarbonate gas formation. We are also investigating alternate initiators. Although Irgacure is widely utilized in hydrogel formation in tissue engineering, it is not possible to use in the foaming systems due to the opaque nature of the foam. We are currently investigating each of these two alternatives to better produce superporous hydrogels and hope to report these in the near future. There are other systems that do not utilize the harsh chemistries of the foaming and polymerization, but these systems have other limitations, including mechanical strength and structural limitations, that can be overcome with our newly developed system forming macroporous hydrogels.

Further, this technology can also be modified to contain many of the attributes currently possible with conventional non-porous hydrogel systems to augment the properties. The system described can be altered to incorporate alternate adhesion molecules [27, 28], chemistries [29–32], mechanics [33, 34], and biodegradability [35, 36]. These altered systems will be investigated as alternate foaming and initiation methods are also investigated to improve on cell survival. When combined with recent evidence that macroscopic SPH structures can be used to culture and differentiate mesenchymal stem cells [10] and that the structures are vascularized [11], there is great potential for applying this technology to tissue engineering and protein delivery.

An important potential application of this system is to create vascularized engineered tissue. The field of tissue engineering has only brushed the surface of being able to vascularized large tissues [37]. More research has recently been involved in allowing greater porosity for vascularization even in hydrogel scaffolds due to slow degradation [38–41]. By creating systems that will allow greater cell seeding and rapid vascular ingrowth, scaffolds may be better positioned to be the temporary support that the name scaffold implies. Cells would then have the ability to populate and remodel the scaffold in a much more rapid manner. In addition, the ability to rapidly and reproducibly seed cells in the pores may allow a scaffold that can be rapidly remodeled.

4. Conclusions

Based on the results and observations it can be concluded that the initiator ammonium persulfate and the mechanism for generation of foam using sodium bicarbonate as a foaming agent are toxic to cells. The acid-neutralization subjects cells to the drastic change in pH from an acidic to alkaline pH, which leads to significant cell death. However, the foaming technique can be used for cell encapsulation in superporous hydrogels with survival rates comparable to nonporous hydrogels at 48 hours. Alternate methods of foaming and crosslinking must be explored to optimize cell survival.

Acknowledgments

The authors thank Ernie Gemeinhart, Milind Gandhi, and Vandana Keskar for significant and helpful discussion. This investigation was funded, in part, by R01 NS055095 and was conducted, in part, in a facility constructed with support from Research Facilities Improvement Program Grant C06 RR15482 from the National Center for Research Resources, NIH.

References

1. Nicodemus GD, Bryant SJ. Cell encapsulation in biodegradable hydrogels for tissue engineering applications. *Tissue Eng. Part B-Rev.* 2008; 14:149–165. [PubMed: 18498217]
2. Peppas NA, Huang Y, Torres-Lugo M, Ward JH, Zhang J. Physicochemical, foundations and structural design of hydrogels in medicine and biology. *Annu. Rev. Biomed. Eng.* 2000; 2:9–29. [PubMed: 11701505]
3. Murua A, Portero A, Orive G, Hernández RM, de Castro M, Pedraz JL. Cell microencapsulation technology: Towards clinical application. *J. Control. Release.* 2008; 132:76–83. [PubMed: 18789985]
4. Bryant SJ, Anseth KS. Controlling the spatial distribution of ecm components in degradable peg hydrogels for tissue engineering cartilage. *J. Biomed. Mater. Res. Part A.* 2003; 64A:70–79.
5. Bryant SJ, Nuttelman CR, Anseth KS. Cytocompatibility of uv and visible light photoinitiating systems on cultured nih/3t3 fibroblasts in vitro. *J. Biomater. Sci.-Polym. Ed.* 2000; 11:439–457. [PubMed: 10896041]
6. Bryant SJ, Anseth KS. The effects of scaffold thickness on tissue engineered cartilage in photocrosslinked poly(ethylene oxide) hydrogels. *Biomaterials.* 2001; 22:619–626. [PubMed: 11219727]
7. Chen J, Park H, Park K. Synthesis of superporous hydrogels: Hydrogels with fast swelling and superabsorbent properties. *J. Biomed. Mater. Res.* 1999; 44:53–62. [PubMed: 10397904]
8. Gemeinhart RA, Park H, Park K. Pore structure of superporous hydrogels. *Polym. Adv. Technol.* 2000; 11:617–625.
9. Gemeinhart, RA.; Guo, C. Fast swelling hydrogels. Boca Raton, FL: CRC Press; 2004.
10. Keskar V, Marion NW, Mao JJ, Gemeinhart RA. In vitro evaluation of macroporous hydrogels to facilitate stem cell infiltration, growth, and mineralization. *Tissue Engineering Part A.* 2009; 15A: 1695–1707. [PubMed: 19119921]
11. Keskar V, Gandhi M, Gemeinhart E, Gemeinhart R. Initial evaluation of vascular ingrowth into superporous hydrogels. *J Tissue Eng Regen Med.* 2009; 3:486–490. [PubMed: 19526620]
12. Elisseeff J, Anseth K, Sims D, McIntosh W, Randolph M, Langer R. Transdermal photopolymerization for minimally invasive implantation. *Proc. Natl. Acad. Sci. U. S. A.* 1999; 96:3104–3107. [PubMed: 10077644]
13. Elisseeff J, McIntosh W, Anseth K, Riley S, Ragan P, Langer R. Photoencapsulation of chondrocytes in poly(ethylene oxide)- based semi-interpenetrating networks. *J. Biomed. Mater. Res.* 2000; 51:164–171. [PubMed: 10825215]
14. Cruise GM, Scharp DS, Hubbell JA. Characterization of permeability and network structure of interfacially photopolymerized poly(ethylene glycol) diacrylate hydrogels. *Biomaterials.* 1998; 19:1287–1294. [PubMed: 9720892]

15. Mann BK, Gobin AS, Tsai AT, Schmedlen RH, West JL. Smooth muscle cell growth in photopolymerized hydrogels with cell adhesive and proteolytically degradable domains: Synthetic ecm analogs for tissue engineering. *Biomaterials*. 2001; 22:3045–3051. [PubMed: 11575479]
16. Barltrop JA, Owen TC, Cory AH, Cory JG. 5-(3-carboxymethoxyphenyl)-2-(4,5-dimethylthiazolyl)-3-(4-sulphophenyl)tetrazolium, inner salt (mts) and related analogs of 3-(4,5-dimethylthiazolyl)-2,5-diphenyltetrazolium bromide (mtt) reducing to purple water-soluble formazans as cell-viability indicators. *Bioorg. Med. Chem. Let.* 1991; 1:611–614.
17. Singer VL, Jones LJ, Yue ST, Haugland RP. Characterization of picogreen reagent and development of a fluorescence-based solution assay for double-stranded DNA quantitation. *Anal. Biochem.* 1997; 249:228–238. [PubMed: 9212875]
18. Gaugain B, Barbet J, Oberlin R, Roques BP, Le Pecq JB. DNA bifunctional intercalators. I. Synthesis and conformational properties of an ethidium homodimer and of an acridine ethidium heterodimer. *Biochemistry*. 1978; 17:5071–5078. [PubMed: 31902]
19. Elisseeff J, Anseth K, Sims D, McIntosh W, Randolph M, Yaremchuk M, Langer R. Transdermal photopolymerization of poly(ethylene oxide)-based injectable hydrogels for tissue-engineered cartilage. *Plast. Reconstr. Surg.* 1999; 104:1014–1022. [PubMed: 10654741]
20. Baskaran S, Grande D, Sun XL, Yayon A, Chaikof EL. Glycosaminoglycan-mimetic biomaterials. 3. Glycopolymers prepared from alkene-derivatized mono- and disaccharide-based glycomonomers. *Bioconjugate Chem.* 2002; 13:1309–1313.
21. Williams CG, Kim TK, Taboas A, Malik A, Manson P, Elisseeff J. In vitro chondrogenesis of bone marrow-derived mesenchymal stem cells in a photopolymerizing hydrogel. *Tissue Eng.* 2003; 9:679–688. [PubMed: 13678446]
22. Khattak SF, Bhatia SR, Roberts SC. Pluronic f127 as a cell encapsulation material: Utilization of membrane-stabilizing agents. *Tissue Eng.* 2005; 11:974–983. [PubMed: 15998236]
23. Hirsch C, Haller C. Effect of extracellular hypertonicity and alkalosis on endothelial-derived ea.Hy 926 cells in vitro. *European Journal of Medical Research.* 2004; 9:71–77. [PubMed: 15090292]
24. Hwang CM, Sant S, Masaali M, Kachouie NN, Zamanian B, Lee SH, Khademhosseini A. Fabrication of three-dimensional porous cell-laden hydrogel for tissue engineering. *Biofabrication.* 2010; 2 035003.
25. Alhadlaq A, Mao JJ. Tissue-engineered osteochondral constructs in the shape of an articular condyle. *Journal of Bone and Joint Surgery-American Volume.* 2005; 87A:936–944.
26. Clark PA, Moioli EK, Sumner DR, Mao JJ. Porous implants as drug delivery vehicles to augment host tissue integration. *Faseb J.* 2008; 22:1684–1693. [PubMed: 18198217]
27. Kang CE, Gemeinhart EJ, Gemeinhart RA. Cellular alignment by grafted adhesion peptide surface density gradients. *J. Biomed. Mater. Res.* 2004; 71:403–411.
28. Hern DL, Hubbell JA. Incorporation of adhesion peptides into nonadhesive hydrogels useful for tissue resurfacing. *J. Biomed. Mater. Res.* 1998; 39:266–276. [PubMed: 9457557]
29. Wang DA, Williams CG, Li QA, Sharma B, Elisseeff JH. Synthesis and characterization of a novel degradable phosphate-containing hydrogel. *Biomaterials.* 2003; 24:3969–3980. [PubMed: 12834592]
30. Nuttelman CR, Benoit DSW, Tripodi MC, Anseth KS. The effect of ethylene glycol methacrylate phosphate in peg hydrogels on mineralization and viability of encapsulated hmscs. *Biomaterials.* 2006; 27:1377–1386. [PubMed: 16139351]
31. Gemeinhart RA, Bare CM, Haasch RT, Gemeinhart EJ. Osteoblast-like cell attachment to and calcification of novel phosphonate-containing polymeric substrates. *J. Biomed. Mater. Res.* 2006; 78A:433–440.
32. Chaterji S, Gemeinhart RA. Enhanced osteoblast-like cell adhesion and proliferation using sulfated polymeric scaffold. *J. Biomed. Mater. Res.* 2007; 83A:990–998.
33. Putnam AJ, Cunningham JJ, Pillemer BBL, Mooney DJ. External mechanical strain regulates membrane targeting of rho gtpases by controlling microtubule assembly. *American Journal of Physiology-Cell Physiology.* 2003; 284:C627–C639. [PubMed: 12409284]
34. Engler AJ, Sen S, Sweeney HL, Discher DE. Matrix elasticity directs stem cell lineage specification. *Cell.* 2006; 126:677–689. [PubMed: 16923388]

35. West JL, Hubbell JA. Polymeric biomaterials with degradation sites for proteases involved in cell migration. *Macromolecules*. 1999; 32:241–244.
36. Lutolf MP, Lauer-Fields JL, Schmoekel HG, Metters AT, Weber FE, Fields GB, Hubbell JA. Synthetic matrix metalloproteinase-sensitive hydrogels for the conduction of tissue regeneration: Engineering cell-invasion characteristics. *Proc. Natl. Acad. Sci. U. S. A.* 2003; 100:5413–5418. [PubMed: 12686696]
37. Johnson PC, Mikos AG, Fisher JP, Jansen JA. Strategic directions in tissue engineering. *Tissue Eng.* 2007; 13:2827–2837. [PubMed: 18052823]
38. Stosich MS, Bastian B, Marion NW, Clark PA, Reilly G, Mao JJ. Vascularized adipose tissue grafts from human mesenchymal stem cells with bioactive cues and microchannel conduits. *Tissue Eng.* 2007; 13:2881–2890. [PubMed: 17824832]
39. Spiller KL, Laurencin SJ, Charlton D, Maher SA, Lowman AM. Superporous hydrogels for cartilage repair: Evaluation of the morphological and mechanical properties. *Acta Biomaterialia*. 2008; 4:17–25. [PubMed: 18029236]
40. Dalton PD, Woodfield T, Hutmacher DW. Snapshot. *Biomaterials*. 2009; 30:2421–2423.
41. Scott EA, Nichols MD, Kuntz-Willits R, Elbert DL. Modular scaffolds assembled around living cells using poly(ethylene glycol) microspheres with macroporation via a non-cytotoxic porogen. *Acta Biomaterialia*. 2010; 6:29–38. [PubMed: 19607945]

Figure 1. Schematic representation of (A) cells seeded upon (green) a non-porous hydrogel network (blue), (B) cells seeded within (yellow) a non-porous hydrogel network, (C) cells seeded within the porous network of superporous hydrogels, and (D) cells encapsulated within the hydrogel network of a superporous hydrogel (not to scale).

Figure 2. Component Cytotoxicity

The effect of 15% PEGDA (row 1), 0.9% TEMED (row 2), 0.7% APS (row 3), 2.4% citric acid (row 4), 0.6% Pluronic® PF127 (row 5), and 200 mg/mL sodium bicarbonate (row 6) on cell viability (% control) as assessed by (graphs left) the MTS assay ($n = 3$, mean $\pm$ S.D.) and by (columns 2 through 5) the LIVE (green)-DEAD (red) cell assay with representative micrographs of cells exposed to the specified component for (column 2) 10 min at pH of 5.0 (column 3) 24 hours, (column 4) 48 hours, and (column 5) 72 hours at pH of 7.4 where †† and ††† indicate a statistically significant difference of $p < 0.01$ and $p < 0.001$ compared to untreated controls as determined by one-way ANOVA followed by post hoc unpaired Student's t-test. Scale bars in all images are 50 μm.

Figure 3. Effect of pH 5.0 on cell viability

Toxicity was assessed by (graph left) the MTS assay ($n = 3$, mean $\pm$ S.D.) and by (columns 2 through 5) the LIVE (green)-DEAD (red) cell assay with representative micrographs of cells exposed to pH 5.0 for (column 2) 10 min, (column 3) 24 hours, (column 4) 48 hours, and (column 5) 72 hours where † and ††† indicate a statistically significant difference of $p < 0.05$ and $p < 0.001$ compared to untreated controls as determined by one-way ANOVA followed by post hoc unpaired Student's t-test. Scale bars in all images are 50 μm .

Figure 4. Effect of foaming on cell viability

Toxicity was determined by MTS assay after incubating cells at pH 5 in (black bars) medium or (gray bars) precursor solution (PEG, APS, TEMED, and Pluronic® F-127) for 10 min, either sodium hydroxide (10 μ L; NaOH) or sodium bicarbonate (100 mg; NaHCO₃) were then added to foam or change pH of the solution ($n = 3$, mean $\pm$ S.D.) where ††† indicates statistically significant difference ($p < 0.001$) compared to untreated controls, § indicates statistically significant difference ($p < 0.05$) comparing medium and precursor solution conditions, and ‡‡ and ‡‡‡ indicates statistically significant difference ($p < 0.01$ and 0.001 , respectively) comparing NaHCO₃ and NaOH treated groups as determined by one way ANOVA and post-hoc unpaired Student's t-test. Cells grown in culture media were also imaged by (columns 2 through 5) the LIVE (green)-DEAD (red) cell assay. Scale bars in all images are 50 μ m.

Figure 5. Cell survival after encapsulation

Cell survival encapsulated as determined by DNA using picogreen assay within superporous hydrogels (SPH), nonporous hydrogels synthesized with APS and TEMED (NPH-A/T), and nonporous hydrogels synthesized with Irgacure® 2959 (NPH-I) at (black bars) 24 hr and (gray bars) 72 hr post seeding ($n = 3$, mean $\pm$ S.D.) where $\dagger$ and $\dagger\dagger$ indicate statistically significant difference ($p < 0.05$ and < 0.01 , respectively) compared to untreated controls, $\ddagger$, $\ddagger\ddagger$, and $\ddagger\ddagger\ddagger$ indicate statistically significant difference ($p < 0.05$, 0.01 , and 0.001 , respectively) compared to different times within the hydrogel group, and $\S\S$ and $\S\S\S$ indicate statistically significant difference ($p < 0.01$ and 0.001 , respectively) compared to other hydrogel groups at a specified time. Representative images of NIH-3T3 cells encapsulated within hydrogels as determined by LIVE- DEAD cell assay at 24 hours and 72 hours in superporous hydrogels (SPH) or non-porous (NPH-A/T) hydrogels. The scale bar is $50\text{ }\mu\text{m}$ in all the images. Green fluorescence indicates live cells while red fluorescence indicates dead cells.