Published in final edited form as:

J Phys Org Chem. 2012 January 1; 25(1): 42–49. doi:10.1002/poc.1866.

Encapsulation and convex-face thiozonolysis of triatomic sulfur (S_3) with carbon nanotubes

Álvaro Castillo^a, Leda Lee^a, and Alexander Greer^{a,*}

^aDepartment of Chemistry and Graduate Center, City University of New York, Brooklyn College, Brooklyn, NY 11210, USA

Abstract

Nanotubes are a class of host cavities increasingly used to encapsulate unstable molecules, yet none have been exploited to host reactive sulfur species, such as thiozone (S_3). In this paper, density functional theory and (ONIOM) calculations were used to compute single-walled carbon nanotube (SWNT)–thiozone combinations for the inclusion of S_3 into the hollow nanotube space and to rationalize when 1,2,3-thiozonide formation can take place. Nanotube diameter selectivity for the isomerization of the C_{2v} form of S_3 to the D_{3h} form proved to be elusive. Acyclic C_{2v} S_3 was ~6 kcal/mol more stable than cyclic D_{3h} S_3 whether it was free or encapsulated within an SWNT. 1,2,3-Thiozonide formation took place on the convex side of nanotubes of low tube radii, such as the armchair (4,4) and (5,5) SWNTs. In terms of the reaction mode of C_{2v} S_3 , the 1,3-dipolar addition reaction was preferred compared with the [2 + 2] cycloaddition and chelotrope paths.

Keywords

carbon nanotubes; ONIOM; thiozonide; thiozone confinement

INTRODUCTION

In this paper, our goal was to compute various carbon nanotube–thiozone combinations for the inclusion of thiozone (S_3) into a hollow nanotube space to rationalize when 1,2,3-thiozonide formation can take place and to examine the thiozonolysis mechanism. C_{2v} symmetric S_3 (**1**) has been detected by UV–visible, microwave, and infrared spectroscopy^[1–5] and has been observed in the atmospheres of Venus and Io because of volcanic activity (Scheme 1).^[6–9] The D_{3h} form of S_3 (**2**) has thus far eluded experimental observation. There is rather sparse use of S_3 in organic synthesis^[10] because of its instability compared with cyclic S_8 .^[11–15] even though its generation is seemingly straightforward in the disproportionation of S_2 O.^[16] Previous papers also suggested the facile production of S_3 in the decomposition of natural product benzopentasulfanes.^[17–20]

Although nanotubes have not yet been used to encapsulate sulfur allotropes such as thiozone,^[21–24] literature nanotube calculations have revealed convex-surface diameter-dependent reactions with higher reactivity for the lower radii nanotubes.^[25–33] For example, density functional theory (DFT) calculations on singlet oxygen with ($n,0$) zigzag SWNTs showed an increased exothermicity with nanotubes of reduced diameters, and that type

(metallic, chiral, non-metallic) did not play a role in this diameter–reactivity relationship.^[34,35] Recent DFT calculations using GGA-PW91/DNP to model the addition of methylamine to C₆₀, C₅₀, (5,5) SWNT, and (10,10) SWNT revealed a similar curvature dependence,^[36] although the addition of benzenediazonium salts to SWNTs was controlled by the optical band gap of the tube rather than the pyramidalization of the carbon atoms.^[37] DFT (ONIOM) methods have showed that the 1,3-dipolar cycloadditions of formoazomethine ylide and fulminic acid took place only on the smallest-diameter SWNTs.^[29–33]

For a theoretical project, we considered armchair, zigzag, and chiral singlet-walled carbon nanotube (SWNT) hosts and possible interior and exterior reactions of S₃ (Fig. 1). Here, we describe three classes of S₃ calculations: (i) free and (ii) SWNT-encapsulated S₃ (including a qualitative model that predicts an inner nanotube storage capacity of thiozone) and (iii) S₃ sulfuration of convex aromatic surfaces producing 1,2,3-thiozonide structures reminiscent of organic trisulfanes^[38] and molozonides.^[25–28] For simplicity, our study neglected possible S₃ reactions at nano-tube end caps, regions around the rim,^[39] such as the COOH functionality introduced onto SWNTs or defect sites.^[40–44] (Scheme 2 illustrates how the nomenclature of carbon nano-tubes is related to an unfolded graphene sheet, in which armchair nanotubes result when the *m* and *n* integers are equal, zigzag nanotubes take the form (*n*,0), and chiral nanotubes result when *m* ≠ *n* 0)^[45,46]

COMPUTATIONAL METHODS

Geometry optimizations were performed with the Gaussian 09 program package (Gaussian, Inc., Wallingford, CT, USA)^[47] using standard protocols^[48,49] and the M06-2X,^[50] B3P86,^[51–53] or SVWN^[54,55] functionals with either basis set “a” [6-31G(d)], “b” [6-311 + G(3d)], or “c” (STO-3G). Calculations were also conducted at the ONIOM(B3P86/a or b:SVWN/c) levels.^[56,57] Geometries were optimized to minima or maxima on the potential energy surface, and the IRC calculations were performed on the transition-state structures. All calculated values included thermal corrections for enthalpy.

RESULTS AND DISCUSSION

Calculated structures of thiozone

Here, we summarize data on thiozone. Table 1 gives the calculated properties and energetics of S₃ obtained from various theoretical methods. Except for SCF/DZ + P and M06-2X/cc-type, all calculations employed in Table 1 favor the C_{2v} form of S₃ to the D_{3h} form by 2.8 to 7.9 kcal/mol.^[59–65] Reaching **2** from **1** is a high-barrier process (24.8 to 36.9 kcal/mol); as reported before,^[66] the cyclization is symmetry forbidden attributed to the gain of a bond in **2** and the loss of a p bond in **1**. Ruedenberg *et al.* computed that the interconversion of **1** and **2** occurred via a C_{2v} transition state that lied in the vicinity of a conical intersection.^[67,68] To our surprise, the M06-2X method was not reliable; the near-isoenergetic S₃ values predicted make it difficult to justify the use of this method to make predictions for new nanotube–thiozone combinations in the paper. Even the inclusion of tight *d* polarization basis set functions on the M06-2X calculations did not produce relative energies similar to the coupled-cluster and CI calculations or bond lengths similar to the FT-microwave structure. On the other hand, the B3P86/6-311 + G (2d) calculations provided reasonable energetics and a good geometry when compared with the available experimental structure for C_{2v} S₃. The B3P86/6-311 + G(2d) computed S1–S2 bond length had a 0.01 Å discrepancy and S1–S2–S3 bond angle 0.7° discrepancy to the experimental structure.^[58]

Nanotube-encapsulated thiozone

Here, we investigated thiozone within the SWNT interiors. ONIOM calculations were carried out where the treatment separated the dinaphtho[2,1,8,7-*hijk*:2',1',8',7'-*stuv*]ovalene and the S₃ unit from the rest of the nanotube (Fig. 2). The junction between B3P86 and SVWN was at the remaining carbon atoms around the perimeter of the ovalene unit: for example, the 78 carbon atoms for the armchair (4,4) SWNT, the 198 carbon atoms for armchair (8,8) SWNT, and the 150 carbon atoms for graphene. The ONIOM ground-state structures and energetics of encapsulated **1** and **2** are listed in Table 2.

We find that **1** is more stable than **2** within the SWNTs. The opposite was never found. Expected nanotube polarization effects^[69] to stabilize confined dipolar **1** had essentially no detectable effect. Although the smallest diameter nanotube analyzed was the (4,4), and with a diameter of 5.4 Å, the C and S atomic radii^[70] was judged to be too small to encapsulate **2**. The S1–S2–S3 bond angle was more linear for **1**@(4,4) SWNT compared with free **1**. For **1**@(5,5) SWNT, the C_{2v} S₃ molecule was aligned parallel to the tube, it along the z-axis, not perpendicular to the x-axis or y-axis (Fig. 3). The S₃ molecule can adopt the different orientations within the (5,5), (6,6), (7,7), and (8,8) SWNTs. Because the rotation depended on the space available for the S₃ molecule, C₂ rotation is facile within the (7,7), and (8,8) SWNTs along the z-axis or x-axis, in contrast to the (5,5) SWNT (~40–50 kcal/mol) and the (6,6) SWNT (~20 kcal/mol) (Fig. 4). The computations yielded no addition of S₃ to the inner wall of nanotubes undoubtedly because of the acute inverse pyramidalization that would be necessary to produce a thiozonide. Even along the z-axis, the thiozone does not react with the flat surface. An open-shell stepwise pathway to a biradical intermediate was sought, but no structure optimized to a C–S bonded compound or to a three-membered ring SWNT-1-persulfide structure with a linear sulfur linkage. DFT calculations also indicate that alkyl radicals do not react with the inner walls of carbon nanotubes because of the high-energy cost to produce a “negative” distortion of the tube geometries.^[71]

In the absence of molecular-dynamics simulations of S₃ molecules within the nanotubes, we speculate a qualitative picture based on the previous static computed structures. Because of the large radii, undoubtedly many S₃ molecules can reside within the (6,6), (7,7), and (8,8) SWNTs, which could oligomerize to other sulfur allotropes or plug the nanotubes. The coupling product cyclic S₆ does not fit within the (5,5) SWNT; however, there was sufficient but limited space for cyclic S₈ within the (6,6) SWNT (Fig. 5). *Catena*-sulfur could form,^[72,73] and our ONIOM inner-tube S₃ dimerization results agree with the previous assessment for a triplet S₆ chain product^[74–77] whose egress or translational motion would likely be restricted by reptation.^[78] A previous study reported that the intercalation of CdI₂ and molten elemental sulfur guests led to a CdS@SWNT composite but in larger diameter tubes, 1–1.4 nm,^[79] than those studied here.

Whereas the encapsulated thiozone does not react with the interior of the nanotube, there is theoretical evidence for the thiozonolysis of the exterior nanotube surface.

Mode of attack of thiozone

Any claim that a nanotube can host thiozone requires an inert interior and that the exterior reactivity can in principle be controlled. Here, we investigate an exterior sulfuration reaction. Because C₆₀ has greater curvature than any nanotube studied here, it served as a model compound to examine thiozonation paths (Figs. 6 and 7). Figure 6 shows three routes for the addition of **1** to C₆₀; they include the 1,3-dipolar addition to form 3',4',5'-trithiacyclopenta[1,9](C₆₀)[5,6]fullerene **5** (path A), the [2 + 2] cycloaddition to form the 3',4'-dithiacyclobuta-1-sulfide [1,9](C₆₀)[5,6]fullerene **6** (path B), and the chelotrope addition to form the 3'-thiacyclopropa-1,1-disulfide[1,9](C₆₀)[5,6]fullerene **7** (path C). Path A

involves symmetrical formation of the C1–S1 and C2–S3 bonds of **TS4/5** to give thiozonide **5**. The C₆₀S₃ thiozonide **5** has C_s symmetry and C1–S1 and C2–S3 bond lengths of 1.87 Å (Fig. 7). Path B involves formation of the C1–S1 and C2–S2 bonds of **TS4/6** to give 1,2-dithietane-1-sulfide **6**. Dithietane **6** has a branched S2=S3 bond that is 1.92 Å in length. Path C involves formation of the C1–S2 and C2–S2 bonds of **TS4/7** to give C_{2v} symmetric thiirane-1,1-disulfide **7**. Compound **7** has S1–S2 and S2–S3 bond lengths of 1.94 Å and a structure analogous to a thiirane sulfone.^[81]

As expected, the 1,3-dipolar addition of S₃ at the 6,6 site was preferred compared with the [2 + 2] cycloaddition and chelotrope paths. The computed barriers of paths A–C were 5.6 kcal/mol, 28.0 kcal/mol, and 42.6 kcal/mol, respectively. Path A was exothermic by 21.2 kcal/mol. In contrast, path B was endothermic by 1.4 kcal/mol, and path C was endothermic by 29.7 kcal/mol. Unlike the endergonic 1,3-dipolar cycloaddition of azomethine ylide to various nanostructures,^[82] at 298 K, the ΔG_{rxn} of path A was –5.9 kcal/mol suggesting that the trisulfane product may be stable at room temperature. The results are understandable in terms of a 1,3-dipole process (of Huisgen known for 50 years) for species such as ozone.^[83] In this regard, there is some similarity to the fullerene/ozone system, previous PBE/TZ calculations showed the addition of ozone to C₆₀ at the 6,6 site to be exothermic by 31.5 kcal/mol and to C₇₀ at the a,b site to be exothermic by 30.6 kcal/mol.^[84–86] The 1,2,3-trithiane ring of C₆₀S₃ **5** has an envelope conformation with a pucker angle of 121.0° and a barrier to ring inversion of ΔH[‡] = 20.3 kcal/mol at the B3P86/b level (Fig. 8A). 1,2,3-Trisulfane arenes, such as trithiolane (6b,12b-epitrithioacenaphtho[1,2-a] acenaphthylene) showed barriers to ring inversion of ΔH[‡] = 13.9 kcal/mol by dynamic NMR analyses (Fig. 8B).^[87–89] The structural features of the enveloped-shaped **5** are similar to that of molozonides, and both reactions have large barriers for back dissociation of S₃ or O₃. Harpp and Smith reported the S–S bond cleaving process of a trisulfide, which required phosphorus compounds to lead to sulfur extrusion.^[38]

Thiozonation of the convex face of single-walled carbon nanotubes

Next, ONIOM calculations were used to examine the exterior thiozonolysis of armchair (*n,n*) SWNTs (*n*=4–8) (Table 3 and Fig. 9). There were multiple reactive sites on the SWNTs; however, we selected a reaction where the orientation of the S1 and S3 atoms of S₃ were added at a 6,6 site orthogonal midway along the length of the nanotube. Not surprisingly, the smaller radii nanotubes enhanced the stability of the thiozonide product. Calculated values were also included for graphene and C₆₀. Only the 1,3-dipolar cycloaddition step was examined because the [2+2] route to the four-membered ring dithiacyclobutasulfide should be a high-energy process (*vide supra*). The ONIOM geometries of **5** and **9–12** were substantially different from **13** and **14**. In the former, the C–S bond distances were less than 2.0 Å; in the latter, they were ~4.0 Å.

The *abcd* dihedral angle change (used to gauge the magnitude of change in sp³ character of the trisulfane product versus the sp² character of the initial all-carbon precursor) also showed a curvature-dependent thiozonation. Thiozonides were formed for **5**, **9–12**, and S₃ was physisorbed for **13** and **14**. Greater curvature of the arene host led to the enhanced stability of the thiozonide product. The thiozonation was exothermic for C₆₀ and for the SWNTs of diameters less than ~6.8 Å and reagent *abcd* dihedral angles less than ~157° in the series examined. For **13** and **14**, only weakly associated S₃ adducts were found.

It can be noted that a low-energy path to cleavage of the S–S and C–S bonds in **5** was not found, **5** did not decompose to Criegee-like intermediates [thione (R₂C=S) and thiosulfine (R + 2C=S –S[–])], and C₆₀S₃ thiozonide **5** converts to the four-membered ring 1,2-dithietane-1-sulfide (**6**) in a high-energy process (53.6 kcal/mol). By comparison, fullerene

molozonides are labile^[90] and decompose by Criegee carbonyl/carbonyl-O-oxide pairs.^[91] The carbonyl oxygen attacks the carbonyl-O-oxide carbon, leading to O₂ departure and sp³ sp² epoxide or oxidoannulene formation (such as the *a,b*-isomer and *c,c*-isomer, respectively, in C₇₀).

CONCLUSION

The calculations of free and nanotube-encapsulated thiozone predict the existence of both **1** and **2**, with the former having greater stability. There was no reactivity of S₃ with the nanotube interior itself. The (5,5) SWNT was unique among the thiozone-trapped CNTs; **1** was situated coaxially inside, although the difficulty of translational motion of S₃ (or the reptative motion of S₆ or S₉ chain products) was not computed. Larger-diameter SWNTs [(*n,n*) *n* = (6–8)] have hollow spaces to trap many S₃ molecules, where there was restricted or insufficient space for cyclic S₆ in the (5,5) SWNT and cyclic S₈ in the (6,6) SWNT. Thiozonolysis was predicted to trisulfurate convex arene surfaces, such as the (4,4) and (5,5) SWNTs, because of greater convexity than the (6,6), (7,7), and (8,8) SWNTs. The 1,3-dipolar addition of S₃ was preferred compared with the [2 + 2] cycloaddition and chelotrope paths.

Acknowledgments

The project described was supported by Award Number SC1GM093830 from the National Institute of General Medical Sciences. The content is solely the responsibility of the authors and does not necessarily represent the official views of the National Institute of General Medical Sciences or the National Institutes of Health. Computational support was provided by the CUNY Graduate Center computational facility and the College of Staten Island CUNY High Performance Computing Facility.

REFERENCES

- [1]. Thorwirth S, McCarthy MC, Gottlieb CA, Thaddeus P, Gupta H, Stanton JF. *J. Chem. Phys.* 2005; 123:1.
- [2]. Burrow PL, Birks JW. *Anal. Chem.* 1997; 69:1299. [PubMed: 21639338]
- [3]. Hassanzadeh P, Andrews L. *J. Phys. Chem.* 1992; 96:6579.
- [4]. Brabson GD, Mielke Z, Andrews L. *J. Phys. Chem.* 1991; 95:79.
- [5]. Meyer B, Oommen TV, Stroyerh T. *J. Mol. Spectrosc.* 1972; 42:335.
- [6]. Lyons JR. *J. Sulfur Chem.* 2008; 29:269.
- [7]. Moses JI, Zolotov MY, Fegley B. *Icarus.* 2002; 156:76.
- [8]. Spencer JR, Jessup KL, McGrath MA, Ballester GE, Yelle R. *Science.* 2000; 288:1208. [PubMed: 10817990]
- [9]. Lewis JS, Kreimendahl FA. *Icarus.* 1980; 42:330.
- [10]. Nakayama J. *J. Sulfur Chem.* 2009; 30:393.
- [11]. Denk MK. *Eur. J. Inorg. Chem.* 2009:1358.
- [12]. Rene-Boisneuf L, Scaiano JC. *Chem. Mater.* 2008; 20:6638.
- [13]. Steudel, R. *Chemistry of the Non-Metals.* W. de Gruyter, Pub.; New York: 1977. p. 204
- [14]. Casal HL, Scaiano JC. *J. Photochem.* 1985; 30:253.
- [15]. Tebbe FN, Wasserman E, Peet WG, Vatvars A, Hayman AC. *J. Am. Chem. Soc.* 1982; 104:4971.
- [16]. Ishii A, Nakabayashi M, Nakayama J. *J. Am. Chem. Soc.* 1999; 121:7959.
- [17]. Mahendran A, Vuong A, Aebischer D, Gong Y, Bittman R, Arthur G, Kawamura A, Greer A. *J. Org. Chem.* 2010; 75:5549. [PubMed: 20704430]
- [18]. Brzostowska EM, Paulynice M, Bentley R, Greer A. *Chem. Res. Toxicol.* 2007; 20:1046. [PubMed: 17580913]
- [19]. Brzostowska EM, Greer A. *J. Am. Chem. Soc.* 2003; 125:396. [PubMed: 12517151]
- [20]. Greer A. *J. Am. Chem. Soc.* 2001; 123:10379. [PubMed: 11603989]

- [21]. Costa PMFJ, Gautam UK, Bando Y. D. Golberg Carbon. 2010; 49:342.
- [22]. Kobayashi K, Suenaga K, Saito T, Shinohara H, Iijima S. Adv. Mater. 2010; 22:3156. [PubMed: 20574949]
- [23]. Wang Y, Huang Y, Yang B, Liu R. Carbon. 2008; 46:276.
- [24]. Nishide D, Dohi H, Wakabayashi T, Nishibori E, Aoyagi S, Ishida M, Kikuchi S, Kitauro R, Sugai T, Sakata M. Chem. Phys. Lett. 2006; 428:356.
- [25]. Yim W-L, Johnson KJ. J. Phys. Chem. C. 2009; 113:17636.
- [26]. Maranzana A, Serra G, Giordana A, Tonachini G, Barco G, Causa M. J. Phys. Chem. A. 2005; 109:10929. [PubMed: 16331937]
- [27]. Chen Z, Ziegler KJ, Shaver J, Hauge RH, Smalley RE. J. Phys. Chem. B. 2006; 110:11624. [PubMed: 16800455]
- [28]. Kar T, Akdim B, Duan X, Pachter R. Chem. Phys. Lett. 2004; 392:176.
- [29]. Osuna S, Houk KN. Chem. Eur. J. 2009; 15:13219. [PubMed: 19876972]
- [30]. Sabirov D, Khursan S, Bulgakov R. Russ. Chem. Bull. 2008; 57:2520.
- [31]. Ogrin D, Chattopadhyay J, Sadana AK, Billups WE, Barron AR. J. Am. Chem. Soc. 2006; 128:11322. [PubMed: 16939233]
- [32]. Park S, Srivastava D, Cho K. Nano Lett. 2003; 3:1273.
- [33]. Astakhova TY, Vinogradov GA, Gurin OD, Menon M. Russ. Chem. Bull. 2002; 51:764.
- [34]. Zhang Y-F, Liu Z-F. J. Phys. Chem. B. 2004; 108:11435.
- [35]. Chan S-P, Chen G, Gong XG, Liu Z-F. Phys. Rev. Lett. 2003; 90:086403. [PubMed: 12633446]
- [36]. Lin T, Zhang W-D, Huang J, He CJ. J. Phys. Chem. B. 2005; 109:13755. [PubMed: 16852723]
- [37]. Doyle CD, Rocha J-DR, Weisman RB, Tour JM. J. Am. Chem. Soc. 2008; 130:6795. [PubMed: 18454527]
- [38]. Harpp DN, Smith RA. J. Am. Chem. Soc. 1982; 104:6045.
- [39]. Fort EH, Donovan PM, Scott LT. J. Am. Chem. Soc. 2009; 131:16006. [PubMed: 19831347]
- [40]. Del Canto E, Flavin K, Movia D, Navois C, Bittencourt C, Giordani S. Chem. Mater. 2011; 23:67.
- [41]. Denis PA. J. Phys. Chem. C. 2009; 113:5612.
- [42]. Denis PA. Int. J. Quantum Chem. 2009; 109:772.
- [43]. Denis PA, Faccio R. Chem. Phys. Lett. 2008; 460:486.
- [44]. Liu J, Rinzler AG, Dai H, Hafner JH, Bradley RK, Boul PJ, Lu A, Iverson T, Shelimov K, Huffman CB, Rodriguez-Macias F, Shon YS, Lee TR, Colbert DT, Smalley RE. Science. 1998; 280:1253. [PubMed: 9596576]
- [45]. Dresselhaus MS, Dresselhaus G, Saito R. Solid State Commun. 1992; 84:201.
- [46]. Dillon AC. Chem. Rev. 2010; 110:6856. [PubMed: 20839769]
- [47]. Frisch, MJ.; Trucks, GW.; Schlegel, HB.; Scuseria, GE.; Robb, MA.; Cheeseman, JR.; Scalmani, G.; Barone, V.; Mennucci, B.; Petersson, GA.; Nakatsuji, H.; Caricato, M.; Li, X.; Hratchian, HP.; Izmaylov, AF.; Bloino, J.; Zheng, G.; Sonnenberg, JL.; Hada, M.; Ehara, M.; Toyota, K.; Fukuda, R.; Hasegawa, J.; Ishida, M.; Nakajima, T.; Honda, Y.; Kitao, O.; Nakai, H.; Vreven, T.; Montgomery, JA., Jr.; Peralta, JE.; Ogliaro, F.; Bearpark, M.; Heyd, JJ.; Brothers, E.; Kudin, KN.; Staroverov, VN.; Kobayashi, R.; Normand, J.; Raghavachari, K.; Rendell, A.; Burant, JC.; Iyengar, SS.; Tomasi, J.; Cossi, M.; Rega, N.; Millam, NJ.; Klene, M.; Knox, JE.; Cross, JB.; Bakken, V.; Adamo, C.; Jaramillo, J.; Gomperts, R.; Stratmann, RE.; Yazyev, O.; Austin, AJ.; Cammi, R.; Pomelli, C.; Ochterski, JW.; Martin, RL.; Morokuma, K.; Zakrzewski, VG.; Voth, GA.; Salvador, P.; Dannenberg, JJ.; Dapprich, S.; Daniels, AD.; Farkas, Ö.; Foresman, JB.; Ortiz, JV.; Cioslowski, J.; Fox, DJ. Gaussian, Inc.; Wallingford, CT: 2009.
- [48]. Jensen, F. Introduction to Computational Chemistry. 2nd edn. Wiley; Chichester, UK: 2007. p. 177-203.
- [49]. Cramer, CJ. Essentials of Computational Chemistry. 2nd edn. Wiley; Chichester, U.K.: 2004. p. 249-300.
- [50]. Zhao Y, Truhlar DG. J. Chem. Theory Comput. 2008; 4:1849.
- [51]. Becke AD. Phys. Rev. A. 1988; 38:3098. [PubMed: 9900728]

- [52]. Perdew JP. Phys. Rev. B Condens. Matter. 1986; 33:8822. [PubMed: 9938299]
- [53]. Becke AD. J. Chem. Phys. 1993; 98:5648.
- [54]. Slater, JC. The Self-Consistent Field for Molecular and Solids, Quantum Theory of Molecular and Solids. Vol. Vol. 4. McGraw-Hill; New York: 1974.
- [55]. Vosko SH, Wilk L, Nusair M. Can. J. Phys. 1980; 58:1200.
- [56]. Matsubara T, Maseras F, Koga N, Morokuma K. J. Phys. Chem. 1996; 100:2573.
- [57]. Svensson M, Humbel S, Froese RDJ, Matsubara T, Sieber S, Morokuma K. J. Phys. Chem. 1996; 100:19357.
- [58]. McCarthy MC, Thorwirth S, Gottlieb CA, Thaddeus P. J. Am. Chem. Soc. 2004; 126:4096. [PubMed: 15053585]
- [59]. Rice JE, Amos RD, Handy NC, Lee TJ, Schaefer HF. J. Chem. Phys. 1986; 85:963.
- [60]. Mille-ori S, Alparone A. J. Phys. Chem. A. 2001; 105:9489.
- [61]. Goddard JD, Chen X, Orlova GJ. J. Phys. Chem. A. 1999; 103:4078.
- [62]. Koch W, Natterer J, Heinemann CJ. Chem. Phys. 1995; 102:6159.
- [63]. Francisco JS, Lyons JR, Williams IH. J. Chem. Phys. 2005; 123:054302. [PubMed: 16108634]
- [64]. Azizi Z, Roos BO, Veryazov V. Phys. Chem. Chem. Phys. 2006; 8:2727. [PubMed: 16763705]
- [65]. Oyedepo GA, Wilson AK. J. Phys. Chem. A. 2010; 114:8806. [PubMed: 20560594]
- [66]. Flemmig B, Wolczanski PT, Hoffmann R. J. Am. Chem. Soc. 2005; 127:1278. [PubMed: 15669867]
- [67]. Ivanic J, Atchity GJ, Ruedenberg K. J. Chem. Phys. 1997; 107:4307.
- [68]. Glezakou V-A, Elbert ST, Xantheas SS, Ruedenberg K. J. Phys. Chem. A. 2010; 114:8923. [PubMed: 20666489]
- [69]. Halls MD, Schlegel HB. J. Phys. Chem. B. 2002; 106:1921.
- [70]. Bondi A. J. Phys. Chem. 1964; 68:441.
- [71]. Yumura T. Phys. Chem. Chem. Phys. 2011; 13:337. [PubMed: 21031224]
- [72]. Denk MK. Eur. J. Inorg. Chem. 2009:1358.
- [73]. Otto AH, Steudel R. Eur. J. Inorg. Chem. 1999:2057.
- [74]. Jones RO, Ballone P. J. Chem. Phys. 2004; 121:7535.
- [75]. Jones RO, Ballone P. J. Chem. Phys. 2003; 118:9257.
- [76]. Hunsicker S, Jones RO, Ganteför G. J. Chem. Phys. 1995; 102:5917.
- [77]. Jones RO. J. Chem. Phys. 1986; 84:318.
- [78]. Lei X, Doubleday CE, Zimmt MB, Turro NJ. J. Am. Chem. Soc. 1986; 108:2444. [PubMed: 22175598]
- [79]. Eliseev AA, Chernysheva MV, Verbitskii NI, Kiseleva EA, Lukashin AV, Tretyakov YD, Kiselev NA, Zhigalina OM, Zakalyukin RM, Vasiliev AL, Krestinin AV, Hutchison JL, Freitag B. Chem. Mater. 2009; 21:5001.
- [80]. Lawler HM, Areshkin D, Mintmire JW, White CT. Phys. Rev. B Condens. Matter. 2005; 72:233403.
- [81]. Steudel Y, Steudel R, Wong MW. Chem. Eur. J. 2002; 8:217. [PubMed: 11822453]
- [82]. Denis PA, Iribarne F. Int. J. Quantum Chem. 2010; 110:1764.
- [83]. Houk KN. Helv. Chim. Acta. 2010; 93:1241.
- [84]. Heymann D, Bachilo SM, Weisman RB, Marriott T, Cataldo F. Fullerenes Nanotubes Carbon Nanostruct. 2002; 10:37.
- [85]. Sabirov DS, Khursan SL, Bulgakov RG. J. Molec. Graph. Model. 2008; 27:124. [PubMed: 18455456]
- [86]. Heymann D. Fullerenes Nanotubes Carbon Nanostruct. 2004; 12:715.
- [87]. Sugihara Y, Abe K, Nakayama J. Heteroatom Chem. 1999; 10:638.
- [88]. Yomoji N, Takahashi S, Chida S-I, Ogawa S, Sato R. J. Chem. Soc. Perkin Trans. 1993; 1:1995.
- [89]. Kimura T, Hanzawa M, Tsujimura K, Takahashi T, Kawai Y, Horn E, Fujii T, Ogawa S, Sato R. Bull. Chem. Soc. Jpn. 2002; 75:817.

- [90]. Bil A, Latajka Z, Morrison CA. J. Phys. Chem. A. 2009; 113:9891. [PubMed: 19685915]
- [91]. Criegee R. Angew. Chem. Int. Ed Engl. 1975; 87:745.

Figure 1. Schematic of (a) **1** encapsulated inside a single-walled carbon nanotube (SWNT) and (b) an SWNT 1,2,3-thiozonide

Figure 2.
The dinaphtho[2,1,8,7-*hijk*:2',1',8',7'-*stuv*]ovalene unit used in the B3P86 portion of the ONIOM calculations

Figure 3.

The S_3 molecule preferentially lies along the z-axis of the armchair (5,5) single-walled carbon nanotube, which is flat. There was a high energy (~ 40 – 50 kcal/mol) for the rotation of S_3 within this nanotube

Figure 4. Side-on view of rotation **1** within the (6,6) single-walled carbon nanotube. Conformer (c) was less stable by ~20 kcal/mol compared with (a) or (b)

Figure 5. End-on view of (a) cyclic S_6 at (5,5) single-walled carbon nanotube (SWNT) and (b) cyclic S_8 at (6,6) SWNT

Figure 6. ONIOM(B3P86/b:SVWN/c)//ONIOM(B3P86/a:SVWN/c) computed energetics of the S₃ [60]fullerene sulfuration, which includes thermal corrections for enthalpy at 298 K (in kcal/mol). The values for free energy are in italics

Figure 7. ONIOM(B3P86/a:SVWN/STO-3G) optimized geometries of minima and transition structures (bond distances are in Å, angles are in deg). The B3P86 layer is in ball-and-stick model, and the single-walled carbon nanotube layer is in tube model. The gray atoms are carbon, and the yellow atoms are sulfur

Figure 8.

Ring-flipping inversion of C₆₀S₃ and trithiolane (6b,12b-epitrithioacenaphtho[1,2-a]acenaphthylene). The puckering angle is a measure of deviation of the ring from planarity as defined as the angle formed by the center sulfur and the midpoint of the plane made by the flanking two carbon–sulfur bonds

Figure 9. Schematic representation of the (n,n) single-walled carbon nanotubes ($n=4-8$) and the ΔH_{rxn} (kcal/mol) for the formation of thiozonides connected orthogonally along the x-axis or y-axis. Energetics were computed at the ONIOM(B3P86/b:SVWN/c)//ONIOM(B3P86/a:SVWN/c) level. NR = no reaction

Scheme 1.
Cyclic and acyclic forms of thiozone

Scheme 2.

Nomenclature of single-walled carbon nanotubes derived from a graphene segment with indexed lattice points (adapted from Dresselhaus *et al.*^[45])

Table 1

Calculated properties and energetics of the open C_{2v} and cyclic D_{3h} forms of $S_3^{a,b,c}$

Method	$\angle S_1-S_2-S_3$ (°)		Barrier height ^d	Rel. energy of $D_{3h}-C_{2v}^a$		Ref.
	S1-S2 (Å)	S1-S2-S3 (°)		S1-S2 (Å)	$D_{3h}-C_{2v}^a$	
Experiment	(1.917)	(117.4)	—	—	—	McCarthy <i>et al.</i> ^[58]
SCF/DZ + P	1.907	117.2	—	2.083	-9.3	Rice <i>et al.</i> ^[59]
B3LYP/cc-pVTZ	1.960	117.5	—	2.127	7.4	Millefiori and Alparone ^[60]
B3LYP/LanL2DZG(d)	1.956	117.5	24.8	2.130	7.9	Goddard <i>et al.</i> ^[61]
B3P86/6-311 + G(2d)	1.927	118.1	26.4	2.097	6.6	Goddard <i>et al.</i> ^[61]
M06-2X/b	1.936	118.0	28.9	2.102	2.8	This work
M06-2X/cc-pV5Z	1.900	117.6	—	2.063	-1.3	This work
M06-2X/cc-pV(Q + d)Z	1.896	117.7	29.4	2.062	-0.9	This work
M06-2X/cc-pV(5 + d)Z	1.896	117.7	30.1	2.062	-0.9	This work
MRC1 + Q/ANO6532	1.937	117.8	36.9	2.094	6.8	Koch <i>et al.</i> ^[62]
CCSD(T)/ANO6532	1.932	117.3	—	2.093	5.6	Koch <i>et al.</i> ^[62]
CCSD(T)/cc-pV5Z	1.918	117.3	—	2.077	4.8	Francisco <i>et al.</i> ^[63]
CASPT2/ANO-QZP	1.924	117.3	—	2.083	6.7	Azizi <i>et al.</i> ^[64]
MR-ccCA-AQCC(S-DT)	—	—	—	—	5.3	Oyedepo and Wilson ^[65]

^aEnergies in kcal/mol.

^bExperimental values in parentheses.

^cThe computed S1-S2-S3 angle in D_{3h} S_3 was 60° in all cases.

Table 2

Calculated properties and energetics of 1 and 2 encapsulated in nanotubes^{a,b,c}

SWNT	✧		✧		Rel. energy S ₃ D _{3h} -C _{2v} ^d	Nanotube diameter (Å) ^d
	S1-S2 (Å)	S1-S2-S3 (°)	S1-S2 (Å)	S1-S2-S3 (°)		
(4,4) ^c	1.933	121.2	—	—	—	5.4
(5,5)	1.934	116.6	2.056	59.5	13.2	6.8
(6,4)	1.932	116.9	2.060	59.7	8.9	6.8
(9,0)	1.928	117.6	2.064	60.2	9.8	7.1
(8,2)	1.934	117.3	2.067	60.3	10.1	7.2
(7,4)	1.927	117.6	2.073	59.8	7.2	7.6
(6,6)	1.926	117.7	2.089	59.5	7.2	8.2
(7,7)	1.927	118.0	2.091	60.0	7.6	9.5

^aEnergies in kcal/mol; length of the nanotube = 1.2 nm.

^bCalculated by ONIOM(B3P86/b:SVWN/c)//ONIOM(B3P86/a:SVWN/c).

^cD_{3h} S₃; S₂-S₃ = 1.92 Å; S₂-S₃-S₁ = 67.3°.

^dNanotube diameters taken from Lawler *et al.*[80].

Table 3

Calculated structural parameters of thiozonides or thiozone adducts of [60]fullerene, single-walled carbon nanotubes (SWNTs), and graphene^{a,b}

Thiozonide	C1-S1 (Å)	S1-S2-S3 (Å)	<i>abcd</i> in reagent (°)	<i>abcd</i> in product (°)
$C_{60}S_3$ 5	1.86	92.5	138.4	115.2
(4,4) SWNT S_3 9	1.91	93.0	156.4	130.3
(5,5) SWNT S_3 10	1.93	93.0	156.9	132.0
(6,6) SWNT S_3 11	1.94	92.9	160.8	133.2
(7,7) SWNT S_3 12	1.96	93.0	163.4	134.1
(8,8) SWNT S_3 13	3.96	117.6	165.3	—
graphene/ S_3 14	4.01	118.4	180.0	—

^aOptimized at the ONIOM(B3P86/a:SVWN/c) level. The B3P86/a portion of the ONIOM calculation included S_3 and the dinaphthovalene core, and SVWN/c was used on the remaining portion of the molecule.

^bLength of the SWNTs = 1.2 nm.