Published in final edited form as:

Soft Matter. 2012 July 21; 8(27): 7197–7206. doi:10.1039/C2SM25533B.

A Novel Technique for Micro-patterning Proteins and Cells on Polyacrylamide Gels

Xin Tang^a, M. Yakut Ali^a, and M. Taher A. Saif^{a,b,*}

^aDepartment of Mechanical Science and Engineering, College of Engineering, University of Illinois at Urbana-Champaign, Urbana, Illinois, USA, 61801

^bMicro and Nanotechnology Laboratory, University of Illinois at Urbana-Champaign, Urbana, Illinois, USA, 61801

Abstract

Spatial patterning of proteins (extracellular matrix, ECM) for living cells on polyacrylamide (PA) hydrogels has been technically challenging due to the compliant nature of the hydrogels and their aqueous environment. Traditional micro-fabrication process is not applicable. Here we report a simple, novel and general method to pattern a variety of commonly used cell adhesion molecules, i.e. Fibronectin (FN), Laminin (LN) and Collagen I (CN), etc. on PA gels. The pattern is first printed on a hydrophilic glass using polydimethylsiloxane (PDMS) stamp and micro-contact printing (μ CP). Pre-polymerization solution is applied on the patterned glass and is then sandwiched by a functionalized glass slide, which covalently binds to the gel. The hydrophilic glass slide is then peeled off from the gel when the protein patterns detach from the glass, but remain intact with the gel. The pattern is thus transferred to the gel. The mechanism of pattern transfer is studied in light of interfacial mechanics. It is found that hydrophilic glass offers strong enough adhesion with ECM proteins such that a pattern can be printed, but weak enough adhesion such that they can be completely peeled off by the polymerized gel. This balance is essential for successful pattern transfer. As a demonstration, lines of FN, LN and CN with widths varying from 5–400 μ m are patterned on PA gels. Normal fibroblasts (MCF) are cultured on the gel surfaces. The cell attachment and proliferation are confined within these patterns. The method avoids the use of any toxic chemistry often used to pattern different proteins on gel surfaces.

Keywords

Cells patterning on hydrogel; Interfacial fracture mechanics; AFM adhesion study; Hydrophilicity effect

1. Introduction

In case of *in vitro* tissue engineering and scaffold designs, the precise spatio-temporal control and organization of cells is critical to represent the proper microenvironment (μ -environment) around the cells, mimicking *in vivo* physical and chemical cues^{1–10}. Soft lithography techniques have been demonstrated to be an inexpensive and efficient technique for patterning a range of substrates starting from metal-coated glass^{5, 11–13} or bare glass^{4, 14–16} and polystyrene substrates to flexible PDMS substrates^{17, 18} and biomaterials (e.g. chitosan and collagen)^{19–21}. The term ‘soft lithography’ implies that these techniques involve stamps fabricated from an elastomer/soft material (e.g. PDMS). The stamp is generally obtained using a master mold manufactured via standard photolithographic

*Corresponding author: Prof. M. Taher A. Saif (saif@uiuc.edu).

procedure followed in semiconductor industries. This PDMS stamp can be inked with suitable molecules e.g. extracellular matrix (ECM), self-assembled monolayer (SAM) to print on substrates. The precisely defined ECM micro-patterns allow to study the effect of geometric cues on various important cell functionalities including cell adhesion and spreading^{19, 22, 23}, cell proliferation and differentiation^{1, 24}, cell fate switching between apoptosis and growth², cell polarity^{5, 25}, migration^{16, 26–28}, cellular internal compartment organization^{16, 25, 29} and the orientation of the axis of division^{30, 31}. Increasing evidence suggests that appropriate substrate stiffness can give rise to specific cellular responses^{9, 32–40}. For example, HCT-8 cancer cells showed a metastasis like phenotype (MLP) only when they were cultured on substrates having physiologically relevant stiffness (21–47 kPa), but not on very soft (1 kPa) and very stiff (3.6 GPa) substrates³³. Cells sense and respond to the mechanical signals of the μ -environment^{32, 33, 35, 38–41}. Substrates with easily tunable stiffness, such as PA gels, allow studies of cell response to mechanical microenvironments that are physiologically relevant. PA gels, being optically transparent, can be interrogated easily by available imaging techniques^{42, 43}. However, patterning of extracellular proteins on soft gels is challenging due to their aqueous environments. Specifically, printing of patterns on PA gel surface using ECM-inked stamps in aqueous environments may cause diffusion of the ECM proteins into the medium, resulting in low quality printing. Direct μ CP of ECM patterning on already polymerized hydrogels have been achieved in the past^{19, 44–47}. However, it's worthy noting that some of these techniques require functionalization of the inert gel surface with hazardous chemicals, e.g. hydrazine hydrate agent^{44, 48} for ECM conjugation. The usage of hydrazine hydrate agent makes the process potentially dangerous since hydrazine hydrate has been identified as a hazardous chemical in case of physical contact and of inhalation. Severe over-exposure to hydrazine hydrate can even result in death. In addition, for effective pattern transfer using μ CP method, the softness of the substrate should not be much lower compared to the stamp material¹³. ECM patterning of very soft substrates using a stamp is a challenge since the soft substrate can deform and conform to the topography of the stamp. This will yield a blurred pattern. In the method presented, this challenge is overcome. Here the ECM protein pattern is first transferred onto a glass slide, and the gel is poured onto glass in pre-cured state. Thus the gel is not exposed to any topography, and the question of gel deformation does not arise. Hence, the method works for PA gels with a broad range of stiffness.

Here, we report a novel and simple two-step method to pattern cell adherent ECM proteins on PA gels. The method utilizes a hydrophilic glass substrate that is patterned via μ CP of ECM (FN, LN or CN in this case) using a PDMS stamp. The patterned glass substrate is covered with a droplet of liquid phase PA gel solution, which is then sandwiched by another functionalized glass slide that adheres to the gel. After curing the gel at 37 °C, the glass plates are separated from each other, when the gel remains attached to the functionalized glass and peels off the protein patterns from the hydrophilic glass. Thus, the protein pattern is transferred to the gel. The process avoids any functionalization of the inert gel surface for attachment of the protein pattern using the hazardous chemicals. The mechanics of the pattern transfer is also studied in light of fracture and interface mechanics. It is found that the hydrophilicity of the glass where the proteins are first printed is essential for pattern transfer to PA gel. Hydrophilic glass offers strong enough adhesion with FN such that a pattern can be printed, but weak enough adhesion such that FN can be completely peeled off by the polymerized gel. This balance is essential for successful pattern transfer.

Materials and Methods

2.1. Microfabrication and soft lithography

A Si master with geometric patterns was fabricated using standard photolithographic technique as shown in Fig. 1a1–1a4. The patterns were designed using AutoCAD

(Autodesk, Inc., CA). Chrome masks were manufactured by Fine line Imaging (Colorado Springs, CO). The Si wafer was cleaned, degreased, blown dry with N₂ gas and baked at 110°C (4 min). Descumming of the Si wafer was performed using O₂/Ar plasma (flow rate ratio of 2:1) at Reactive Ion Etcher (March Instruments, Concord, CA) for 1 min at 100 W. The Si wafer was then spin-coated (maximum spin speed of 4000 rpm) with a thin layer of SU-8 negative photoresist (SU-8 2002, MicroChem, Newton, MA). After soft baking at 110°C for 4 min on a flat hot plate, the wafer was brought in hard contact with the chrome mask and was exposed to UV light for 7s using a flood exposure system (ABM, Inc., Fig. 1a1). After the post exposure bake at 95°C for 2 min, the wafer was developed using SU-8 developer (MicroChem, Newton, MA) for 10s (Fig. 1a2) and hard baked at 150 °C for 18 min. Finally the wafer was treated with molecular vapor deposition (MVD) of FDTS (heptadecafluoro-1H, 1H, 2H, 2H-hydradecyltrichlorosilane) using MVD System (Applied MST, San Jose, CA) to ensure easy removal of the cured PDMS stamp in the subsequent steps (Fig. 1a3–1a4)^{49–52}. PDMS prepolymer was obtained via mixing Silicone elastomer and curing agent at 10:1 ratio (Dow Corning, Midland, MI) and degassing the mixture in a vacuum jar for 45 min^{52–54}. The prepolymer solution was poured over the Si master mold (Fig. 1b1) and cured in the oven at 70°C for 12 h. The elastomeric stamp was then peeled off carefully (Fig. 1b2) and cut in 2 × 2 cm² pieces for μ CP.

2.2. Micro-contact printing (μ CP) and protein pattern transfer

Fibronectin (FN), laminin (LN) and collagen type I (CN) (from BD Biosciences, NJ) were respectively diluted in PBS solution to a concentration of 50 μ g/ml. For FN, the diluted solution was oxidized to contain aldehyde groups by using sodium periodate (NaIO₄) to facilitate the FN conjugation to PA gel solution^{44, 55}. The PDMS stamp obtained via soft lithography was then inked with the oxidized FN solution for 20 min at room temperature. Then, the excess solution was blown off (Fig. 1b3–1b4). The stamp was brought into complete conformal contact with a glass substrate for 45 min at 37°C (Fig. 1b5). Small weights (25 g) were placed over the PDMS stamp to aid complete protein pattern transfer from PDMS to intermediate glass. Two different types of glass cover slips were used: (1) cover slips as received from the manufacturer (No. 1, 2.5 × 2.5 cm², Corning life Sciences, Netherlands) without any surface treatment; (2) cover slips after immersion in piranha bath (96% H₂SO₄+30% H₂O₂ in 3:1 molar ratio) for over 1 day, which makes the glass hydrophilic. Wet treatment of glass in piranha creates both hydroxyl (–OH) and sulfhydryl (–SH) groups on glass surface responsible for the increased surface hydrophilicity^{49, 56–58}. The surface hydrophilicity characteristics for both the as-received glass slide and the ones after piranha treatment were quantified by performing the static contact angle measurements. A CAM200 Goniometer from KSV NIMA (Finland) was used and 7 μ l droplets of DI water were dispensed on the surfaces to measure the static contact angles. The contact angles of DI water on slides before and after piranha treatment were 42°±3° and 0°, respectively (Fig. 6 insets). A drop of PA gel solution (20 μ L) was placed on the cover slip with the protein patterns. An activated glass cover slip which can covalently bind to gel (see Section 2.3) was placed (floated) on the drop. The drop spread between the cover slips due to capillarity and was sandwiched with uniform thickness^{59–61} (Fig. 1b6). Curing of the PA gel was performed for 45 mins at two different temperatures (room temperature, 24°C, and elevated temperature, 37°C) to explore the effect of curing temperature on the efficacy of protein pattern transfer (Fig. 1b7). The cover slips were manually peeled from each other. During peeling, detachment proceeded from one edge of the sandwich. The gel remained adherent to the activated glass slide. The protein patterns were fully peeled off from the piranha-treated glass, and partially from the as-received glass. The patterns were monitored by both phase contrast and immunofluorescence microscopy. The patterning of laminin and collagen type I was done similarly, except the proteins were not oxidized.

2.3. PA gel and functionalized glass preparation

PA gel preparation and slide activation for the covalent gel attachment were performed following the protocols described elsewhere⁴². In brief, gel solutions were obtained by mixing 8% w/v acrylamide solution (Sigma, St. Louis, MO) and 0.27% N, N'-methylenebisacrylamide (bis) solution (Midwest Scientific, MO) in 10 mM HEPES-buffered saline (Lonza, Walkersville, MD). 1:200 ammonium persulfate (10% w/v) and 1:2000 N, N, N', N'-tetramethylethylenediamine (TEMED) (both from Bio-Rad Laboratories, Hercules, CA) were used as the initiator and catalyst for polymerization process, respectively. AFM (Asylum Research, Santa Barbara, CA) with a pre-calibrated silicon nitride tip was used to characterize the stiffness of PA gels in phosphate-buffered saline (PBS; Lonza, Walkersville, MD) solution^{62, 63}. The nominal stiffness of the PA gels was 20 kPa^{33, 36}. Glass slides were chemically activated to ensure covalent binding of the hydrogel as described earlier⁴². Briefly, slides were treated with 3- Aminopropyltrimethoxysilane (ATS) from Sigma, MO for 7 min at room temperature. Followed by the removal of the ATS completely with DI water rinse, slides were treated with 0.5% Glutaraldehyde (70% Glutaraldehyde from Polysciences, Inc, diluted in PBS) solution for 30 min.

2.4. Cell Culture and Trypan Blue Live-dead Assay

Normal fibroblast cells (ATCC, Manassas, VA) were cultured in a medium with 90% Dulbecco's Modified Eagle's Medium (DMEM; ATCC) and 10% fetal bovine serum (FBS; ATCC)^{33, 36, 64}. The 0.4% trypan blue solution (Sigma-Aldrich, St. Louis, MO) was applied in the cell medium to test the biocompatibility of the micro-patterned gel substrate with cells.

2.5. Immuno-fluorescent-staining of Fibronectin (FN)

PDMS, intermediate glass and PA gel with FN patterns were immunolabeled right after the protein transfer in each step. After rinsing with PBS 3 times, the substrates with FN were blocked with Image-iT FX signal enhancer (Invitrogen, CA) for 30 min to eliminate non-specific proteins binding. Samples were incubated in monoclonal anti-human fibronectin (Sigma-Aldrich, MO) at a 1:100 dilution in PBS at room temperature for 45 min. The substrates were then incubated for 30 min alexa fluorTM 488 goat anti-mouse IgG (Invitrogen, CA) at a 1:200 dilution in PBS at room temperature. The immunolabeled samples were mounted in ProLong gold antifade reagent (Invitrogen, CA) to prevent photobleaching. All the samples were imaged either using the Zeiss LSM 710 confocal scanning laser microscope (Carl Zeiss, Inc.,) at 63 $\times$, NA 1.4 oil immersion objective or Olympus IX81 microscope.

2.6. Functionalization of AFM particle tip for protein (FN) attachment

In order to determine the adhesion strength between fibronectin and glass substrates, a particle tip AFM probe was used. The Silicon Nitride (Si₃N₄) AFM cantilevers with a well-defined spherical SiO₂ particle tip (1 μ m diameter coated with a 30 nm gold layer) were chosen (Novascan Technologies, Inc., Ames, IA). The gold-coated microsphere was functionalized to ensure its attachment with FN through FN-MUA-EDC+NHS-Au covalent bonding. The functionalization process consists of: (a) self-assembly of a layer of MUA (11-mercaptopundecanoic acid) on the gold coated probe by soaking it in a 1 mM MUA (in PBS) solution for 30 min, (b) immersion of the probe in a mixer of 75 mM EDC (1-ethyl-3-(3-dimethylaminopropyl) carbodiimide hydrochloride) and 15 mM NHS (N-hydroxysuccinimide) in PBS for 15 min, and (c) exposure of the probe to the 50 μ g/ml fibronectin solution in PBS for an hour⁶⁵. MUA, EDC and NHS were obtained from Sigma-Aldrich, MO.

2.7. Adhesion force measurement experiments using particle tip AFM

All adhesion force measurement experiments were performed using AFM (MFP 3D, Asylum Research, Santa Barbara, CA) and in PBS solution. The particle AFM probes were properly functionalized as described in previous section. Prior to the experiments, functionalized probes were stored at 4°C. Multiple functionalized probes were prepared at the same time to check the consistency between experiments. The spring constant (k) of the AFM cantilevers was specified by the manufacturer as 0.12 N/m^{66–68}. Calibration using the thermal tuning method^{69, 70} yielded the nominal value of $k = 0.123$ N/m. All experiments were performed with the parameters tabulated in Table S1 and at room temperature. The probes were inspected with an Olympus IX81 microscope to confirm their integrity before experiments. The force measurements were carried out at randomly selected locations for every sample and a 5×2 array of force curves were obtained for each location. In order to measure the adhesion strength between FN and glass (piranha treated hydrophilic glass and as received glass), a drop of PBS solution was deposited on the glass surface. The AFM tip covalently bonded with FN was immersed in the drop and brought in contact with the glass surface. To ensure the complete contact between FN and glass, the AFM tip was bent on the glass surface until reaching a compressive force of 12 nN. The tip was then retracted while the AFM cantilever deflection was monitored to calculate the force of interaction between the tip and the glass. The maximum force prior to detachment was considered as a measure of adhesion between the glass and FN. All of the AFM parameters were kept constant during the adhesion experiments.

3. Results

3.1. Micro-patterning Fibronectin (FN), Laminin (LN) and Collagen I (CN) on PA Gels

Figs. 2a and 2b show the patterns and surface topography of the Si master measured by profilometer (Alpha-step IQ, KLA Tencor). The nominal thickness of the SU-8 photoresist layer is 1.98 ± 0.05 μm . The structures are well defined as is evidenced from their sharp edges and flat surfaces (Fig. 2b). Micrographs of the well-defined geometric patterns on silicone elastomers (PDMS) are shown in Fig. 2c. As a demonstration, a typical immunofluorescent micrograph of the FN patterns transferred onto PA gel are displayed in Fig. 2d3, where one of the glass slides was functionalized for bonding with PA gel, the other was as-received (not piranha treated). Patterning of laminin and collagen type I on gel was carried out similarly. The pattern consists of parallel FN lines, 25 μm wide with 25 μm spacing between them. However, there are discontinuities in FN line patterns along the center region on the gel surface, i.e., not all the proteins were transferred successfully. To investigate at which step the protein patterns lost their integrity, immuno-fluorescence staining of FN patterns were performed on PDMS, glass and PA gels. Images from PDMS and glass substrates revealed uniform and 100% deposition of FN patterns (no defects) (Fig. 2d1 and 2d2). The discontinuous regions appeared only on the PA gel (Fig. 2d3). Based on these step-wise examinations, we believe that the loss of patterns integrity occurs when the as-received glass slide is peeled off from the gel. The effectiveness of the pattern transfer to the gel during the peeling process is determined by the relative adhesion between FN and glass vs. adhesion between FN and gel. If FN-glass adhesion is weaker than that between FN and gel, FN will stay with the gel. Otherwise, only part of the FN pattern can be transferred to the gel. In the following sections, we explain this partial pattern transfer using the concepts of fracture and interface mechanics.

3.2. Gel/glass Separation Experiments Reveal 3 types of Defects

To explore the mechanism of defects, we designed and performed a series of gel-glass separation experiments with the peeling force applied at directions as shown in Figs. 3a and 3b. In all cases, the peeling force is orthogonal to the glass surface. But the location of the

force is such that the peeling proceeds either along the pattern lines (Fig. 3a) or perpendicular to the lines (Fig. 3b). We found, for wide (100 μm) patterns, FN fails to transfer to the gel in the mid region of the patterns. The FN-free region is at the center of the pattern when the peeling proceeds along the pattern lines (Fig. 3a and 4a1), but is shifted from the center towards the edge (along the direction of peeling) when peeling is orthogonal to the lines (Fig. 3b and 4b2). Narrow line patterns (5 μm wide) have regions where patterns are either completely transferred to gel or they completely remained on glass (Fig. 3c).

3.3. Interfacial Fracture Mechanics Interpretation of FN Defects

The peeling of glass from gel can be considered as an interface fracture problem, where an advancing crack separates the two. Pattern transfer involves detachment or debonding of FN from intermediate glass. Such detachment processes have been studied in the literature as an interface fracture between two solids forming the interface^{71–74}. In the case of the gel-glass system, we note the following: (1) gel is significantly more compliant than glass, i.e., there is a large elastic modulus mismatch between the two materials; (2) adhesion between FN and gel is likely to be stronger compared to that between FN and glass. Recall that FN is oxidized to contain the aldehydes group which allows covalent conjugation of FN with the gels; (3) the thickness of FN layer is on the order of few nanometers (Fig. 5c and 5d), orders smaller than the gel layer thickness which is on the order of 100 μm . Thus FN and gel can be considered as one combined layer. Failure of pattern transfer implies that part of the gel remains with the glass together with FN during the peeling process (Fig. S2); (4) the spaces between the FN patterns do not adhere to the gel, i.e., these regions detach from the glass surface during peeling without any resistance. In the current pattern, they are the linear spaces between the FN lines and have the same widths as the FN pattern widths (e.g., 10 μm wide linear space when the FN line is 10 μm wide). These regions act as entrapped cracks and generate crack tip stresses on the FN-coated bonded regions during peeling.

During peeling, a force is applied orthogonal to the glass. As a result, the gel stretches orthogonal to the glass and tends to shrink laterally, in-plane to the glass, due to Poisson's effect. However, the glass substrate, being much harder than gel, restrains the lateral shrinking resulting in shear stresses along the glass-gel interface. The stress gets intensified at the tip of the cracks, i.e., the cracks are loaded in mode II (shear mode) in addition to mode I (opening mode)^{75, 76}. Thus, the crack tips are loaded in mixed mode^{77, 78}. If the compliance of the gel and the glass were similar, then the crack would be loaded in pure mode I only, and thus the debonding or the crack growth would proceed along the interface resulting in complete pattern transfer. Due to mode mixity, the crack tip tends to kink into the gel to propagate along the maximum resultant mode I (opening) direction. Two competing factors determine this kinking, namely, the interface toughness (depends on the strength of adhesion between FN and glass) and the gel toughness. Interface toughness also depends on the degree of mode mixity. In general, the higher the ratio of mode II to mode I components, the higher is the interface toughness. If the interface strength is weak, then the crack is expected to grow along the interface. If the strength is higher, the crack will kink into the gel and run parallel to the interface. For an intermediate strength, the crack may grow along the interface and then kink due to local interfacial imperfections (Fig. 5c). We believe, when the FN is patterned on as-received glass, the adhesion is in the last category resulting in partial pattern transfer. For a given compliance mismatch between glass and gel, one potential parameter to adjust is the adhesion between FN and intermediate glass. The adhesion needs to be weak enough for interfacial crack growth, but strong enough for the pattern to be defined. We achieve this goal by using piranha-treated hydrophilic glass. A quantitative measure of adhesion between glass and FN using AFM, discussed below, shows a seven-fold reduction in adhesion strength when piranha-treated glass is used. Consequently, with appropriate adhesion strength between the FN and glass, the pattern

transfer was free from defects. Earlier, AFM was used to understand the effect of hydrophilicity of different substrates on the adhesion of different proteins (except FN)^{79, 80}. The findings demonstrated, in general, an inverse relationship between the adhesion force and the surface hydrophilicity.

3.4. AFM measurement of FN-glass adhesion—increased surface hydrophilicity of glass substrate greatly reduces the adhesion

Fig. 6a and 6b show the typical AFM force-distance curves obtained for the slides without and with piranha treatment, respectively. The maximum pulling-off force of the AFM cantilevers from the substrates was used as a measure of adhesion strength between glass and FN (Table S2, Fig. 6c). The maximum adhesive force for regular glass slide was 48.05 ± 0.94 nN, whereas that for a treated one was 7.57 ± 1.58 nN (Fig. 6d). The hydrophilic glass shows approximately seven folds lower adhesion compared to the as-received glass. These observations of decrease in adhesion force corresponding to the increase in hydrophilicity are consistent with earlier data available for other kinds of protein-substrate interactions^{79–82}.

3.5. Patterning with hydrophilic glass (gel polymerization at 37 °C)

Micro-patterning of PA gels with FN were repeated using piranha-treated glass to reduce FN-glass adhesion. Polymerization of the PA gel was carried out at 37 °C. Fig. 7a-f shows both the phase contrast and immunofluorescent staining images of the FN patterns of different widths transferred onto PA gels. The patterns show no defect irrespective of the pattern widths. Similarly, the peeled-off intermediate glass did not reveal any notable FN residues. When polymerization was carried out at 24 °C, and hydrophilic glass was used, the FN patterns on PA gels were still not completely transferred (Fig. S3). Alternatively, the FN patterns on PA gels were incomplete with as-received glass and at 37 °C curing (Fig. S2). Both hydrophilic glass and polymerization at 37 °C are needed to achieve the complete FN pattern transfer. We used same procedure for patterning LN and CN, following the procedure outlined above for FN.

3.6 Culturing living cells on different ECM patterns

To demonstrate that the newly micro-patterned ECM zones (FN, LN and CN) were able to produce high quality spatial organization of cells, normal fibroblast cells (MKF) were plated and cultured on PA gel surface with patterns of varied widths. The cells were imaged on day 3 as illustrated in Fig. 8. Clearly, the cells adhered to ECM patterns only, and they form well-defined linear clusters. To test the biocompatibility of the micro-patterned gel substrate with cells, we applied 0.4% trypan blue solution in the cell medium. We found that the cells within the patterns are viable (Fig. 8c, f, i).

4. Discussions and Conclusion

Compared to existing micro-patterning techniques, the advantages of our patterning method are two-fold. Firstly, this method overcomes the difficulties associated with the direct micro-patterning of compliant PA gel using PDMS stamping. Note that micro contact printing generally involves only one step, transfer of pattern from PDMS stamp to certain substrates. Here, printing involves two steps: PDMS stamp to glass, and glass to PA gel. We investigated the latter step using interfacial mechanics. We did not investigate the first step mechanistically. Secondly, it avoids the use of harsh toxic chemicals (e.g. hydrazine hydrate) to functionalize the polymerized gel surface as the current pattern transfer is initiated in the liquid phase of PA gel, thus making the process simpler and safer.

Based on the protein adhesion physics studies, less wettable (hydrophobic) surfaces are generally considered to be more protein adherent due to strong hydrophobic interactions compared to the more wettable (hydrophilic) surfaces. The less protein adherent characteristics of the hydrophilic surfaces are attributed to the repulsive solvation forces originating from strongly bound H₂O on the substrate^{83, 84}. Our study suggests that the pattern transfer process can be explained as a fracture mechanics problem where the transfer is considered as a debonding of the protein layer from the substrate. This debonding occurs through the growth of an interface crack between the substrate and the protein. If the protein-glass adhesion is too strong, then the interface crack kinks into the gel material during peeling, leaving the pattern on the substrate. If the adhesion is too weak, then the protein cannot be patterned on the substrate in the first place. Hence, the degree of hydrophilicity or hydrophobicity of the substrate where the protein is temporarily patterned depends on the nature of the protein. If the protein needs a hydrophobic surface for minimal adhesion necessary for patterning on the surface, then the surface must be treated accordingly. If the adhesion is too high with a hydrophobic surface, then the surface may need to be hydrophilic to achieve the minimal adhesion necessary for patterning on the surface. In all cases, however, it is clear that there needs to be some form of binding between the gel material and the protein. The binding must be strong enough such that the protein can be detached from the substrate, and that the pattern is stable on the gel surface. In the present study, the underlying mechanism of defect minimization in pattern transfer was the reduction of adhesion between glass and FN through enhanced surface hydrophilicity, and increased conjugation between PA gel and FN through curing (gel polymerization) at 37 °C. Our successful cell culture on micro-patterned PA gels indicates that ECM properties are not altered after the transfer and patterning. All the materials and reagents used in the technique are commercially available. Hence, implementation of the technique avoids any chemical synthesis. This straightforward technique of micro-patterning ECM and cells on PA gels may serve as a useful tool in cell mechanics research.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

This work was supported by NSF 10-02165, 07-25831 and National Science Foundation (NSF) Science and Technology Center (STC) Emerging Behaviors in Integrated Cellular Systems (EBICS) Grant CBET-0939511. X. T. was funded from NSF Grant 0965918 IGERT: Training the Next Generation of Researchers in Cellular and Molecular Mechanics and BioNanotechnology. M.Y. A. was funded from NIH National Cancer Institute Alliance for Nanotechnology in Cancer 'Midwest Cancer Nanotechnology Training Center' Grant R25 CA154015A. We thank Dr. Glennys Mensing, Mr. Michael R. Hansen, Mr. Alex Gurga and Dr. Kathy Motsegood, at the Micro-Nano-Mechanical Systems (MNMS) cleanroom, UIUC, for the valuable discussions on micro-fabrication. Atomic force microscopy (AFM) experiments were carried out with the help of Dr. Scott MacLaren at the Frederick Seitz Materials Research Laboratory (MRL), UIUC. Immunostaining and confocal microscopy imaging were carried out at the Institute for Genomic Biology (IGB), UIUC with the help of Dr. Mayandi Sivaguru. Assistance in gels preparations by Mr. Joe Laskowski and Mr. Stephan Lane are gratefully acknowledged.

References

1. Nelson CM, Jean RP, Tan JL, Liu WF, Sniadecki NJ, Spector AA, Chen CS. Proceedings of the National Academy of Sciences. 2005; 102:11594–11599.
2. Chen CS, Mrksich M, Huang S, Whitesides GM, Ingber DE. Science. 1997; 276:1425–1428. [PubMed: 9162012]
3. Desgrosellier JS, Cheresch DA. Nat Rev Cancer. 2010; 10:9–22. [PubMed: 20029421]
4. Gallant ND, Capadona JR, Frazier AB, Collard DM, García AJ. Langmuir. 2002; 18:5579–5584.

5. James J, Goluch ED, Hu H, Liu C, Mrksich M. Cell Motility and the Cytoskeleton. 2008; 65:841–852. [PubMed: 18677773]
6. Desai RA, Khan MK, Gopal SB, Chen CS. Integrative Biology. 2011; 3:560–567. [PubMed: 21298148]
7. Huang S, Ingber DE. Nature Cell Biology. 1999; 1:E131–E138.
8. LeDuc PR, Messner WC, Wikswo JP. Annual Review of Biomedical Engineering. 2011; 13:369–396.
9. Li D, Zhou J, Chowdhury F, Cheng J, Wang N, Wang F. Regenerative Medicine. 2012; 6:229–240. [PubMed: 21391856]
10. Ouyang M, Huang H, Shaner NC, Remacle AG, Shiryaev SA, Strongin AY, Tsien RY, Wang Y. Cancer Research. 2010; 70:2204–2212. [PubMed: 20197470]
11. Raghavan S, Chen CS. Advanced Materials. 2004; 16:1303–1313.
12. Whitesides GM, Ostuni E, Takayama S, Jiang X, Ingber DE. Annual Review of Biomedical Engineering. 2001:3.
13. Falconnet D, Csucs G, Grandin HM, Textor M. Biomaterials. 2006; 27:3044–3063. [PubMed: 16458351]
14. Nishizawa M, Takoh K, Matsue T. Langmuir. 2002; 18:3645–3649.
15. Thakar RG, Ho F, Huang NF, Liepmann D, Li S. Biochemical and Biophysical Research Communications. 2003; 307:883–890. [PubMed: 12878194]
16. Xia N, Thodeti CK, Hunt TP, Xu Q, Ho M, Whitesides GM, Westervelt R, Ingber DE. The FASEB Journal. 2008; 22:1649–1659.
17. Gopalan SM, Flaim C, Bhatia SN, Hoshijima M, Knoell R, Chien KR, Omens JH, McCulloch AD. Biotechnology and Bioengineering. 2003; 81:578–587. [PubMed: 12514807]
18. Ahmed WW, Wolfram T, Goldyn AM, Bruellhoff K, Rioj BA, Möller M, Spatz JP, Saif TA, Groll J, Kemkemer R. Biomaterials. 2009; 31:250–258. [PubMed: 19783042]
19. Wang N, Ostuni E, Whitesides GM, Ingber DE. Cell Motility and the Cytoskeleton. 2002; 52:97–106. [PubMed: 12112152]
20. Chen CS, Jiang X, Whiteside GM. MRS Bulletin. 2005; 30:194–201.
21. Csucs G, Michel R, Lussi JW, Textor M, Danuser G. Biomaterials. 2003; 24:1713–1720. [PubMed: 12593952]
22. Poellmann MJ, Harrell PA, King WP, Johnson AJW. Acta Biomaterialia. 2010; 6:3514–3523. [PubMed: 20371305]
23. Rape AD, Guo W-h, Wang Y-l. Biomaterials. 2010; 32:2043–2051. [PubMed: 21163521]
24. Ruiz SA, Chen CS. Stem Cells. 2008; 26:2921–2927. [PubMed: 18703661]
25. Théry M, Racine V, Piel M, Pépin A, Dimitrov A, Chen Y, Sibarita JB, Bornens M. Proceedings of the National Academy of Sciences. 2006; 103:19771–19776.
26. Jiang X, Bruzewicz DA, Wong AP, Piel M, Whitesides GM. Proceedings of the National Academy of Sciences. 2005; 102:975–978.
27. Mahmud G, Campbell CJ, Bishop KJM, Komarova YA, Chaga O, Soh S, Huda S, Kandere-Grzybowska K, Grzybowski BA. Nature Physics. 2009; 5:606–612.
28. Parker KK, Brock AL, Brangwynne C, Mannix RJ, Wang N, Ostuni Emanuele, Geisse Nicholas A, Adams Josephine C, Whitesides George M, Ingber DE. The FASEB Journal. 2002; 16:1195–1204.
29. Roca-Cusachs P, Alcaraz J, Sunyer R, Samitier J, Farré R, Navajas D. Biophysical Journal. 2008; 94:4984–4995. [PubMed: 18326659]
30. Théry M, Racine V, Pépin A, Piel M, Chen Y, Sibarita JB, Bornens M. Nature Cell Biology. 2005; 7:947–953.
31. Théry M, Jiménez-Dalmaroni A, Racine V, Bornens M, Jülicher F. Nature. 2007; 447:493–496. [PubMed: 17495931]
32. Georges PC, Janmey PA. Journal of Applied Physiology. 2005; 98:1547–1553. [PubMed: 15772065]
33. Tang X, Kuhlenschmidt TB, Zhou J, Bell P, Wang F, Kuhlenschmidt MS, Saif TA. Biophysical Journal. 2010; 99:2460–2469. [PubMed: 20959086]

34. Bajaj P, Tang X, Saif TA, Bashir R. Journal of Biomedical Materials Research Part A. 2010; 95:1261–1269. [PubMed: 20939058]
35. Discher D, Janmey P, Wang YL. Science. 2005; 310:1139–1143. [PubMed: 16293750]
36. Tang X, Bajaj P, Bashir R, Saif TA. Soft Matter. 2011; 7:6151–6158.
37. Lo C-M, Wang H-B, Dembo M, Wang Y-I. Biophysical Journal. 2000; 79:144–152. [PubMed: 10866943]
38. Engler AJ, Carag-Krieger C, Johnson CP, Raab M, Tang HY, Speicher DW, Sanger JW, Sanger JM, Discher DE. Journal of Cell Science. 2008; 121:3794–3802. [PubMed: 18957515]
39. Engler AJ, Sen S, Sweeney HL, Discher DE. Cell. 2006; 126:677–689. [PubMed: 16923388]
40. Poh YC, Chowdhury F, Tanaka TS, Wang N. Biophysical Journal. 2010; 99:L19–L21. [PubMed: 20643049]
41. Vogel V, Sheetz M. Nature Reviews Molecular Cell Biology. 2006; 7:265–275.
42. Wang, Y-I; Pelham, R. Methods in Enzymology. 1998; 298:489–496. [PubMed: 9751904]
43. Cha C, Jeong JH, Tang X, Zill AT, Prakash YS, Zimmerman SC, Saif TA, Kong H. Bioconjugate Chemistry. 2011; 22:2377–2382. [PubMed: 22053983]
44. Damljjanovic V, Lagerholm BC, Jacobson K. Biotechniques. 2005; 39:847–851. [PubMed: 16382902]
45. Wang YC, Ho CC. The FASEB journal. 2004; 18:525–527.
46. Gu Z, Tang Y. Lab on a Chip. 2010; 10:1946–1951. [PubMed: 20436969]
47. Gu Z, Huang S, Chen Y. Angewandte Chemie International. 2009; 48:952–955.
48. Aratyn-Schaus Y, Oakes PW, Stricker J, Winter SP, Gardel ML. Journal of Visualized Experiments. 2010:1–6. [PubMed: 20164822]
49. Madou, MJ. Fundamentals of microfabrication: the science of miniaturization. CRC Press; 2002.
50. LeDuc P, Ostuni E, Whitesides G, Ingber D. Methods in Cell Biology. 2002; 69:385–401. [PubMed: 12071006]
51. Jo BH, Lerberghe LMV, Motsegood KM, Beebe DJ. Journal of Microelectromechanical Systems. 2000; 9:76–81.
52. Hu H, Yeom J, Mensing G, Chen Y, Shannon MA, King WP. Nanotechnology. 2012; 23
53. Millet LJ, Stewart ME, Nuzzo RG, Gillette MU. Lab on Chip. 2010; 10:1525–1535.
54. Millet LJ, Stewart ME, Sweedler JV, Nuzzo RG, Gillette MU. Lab Chip. 2007; 7:987–994. [PubMed: 17653340]
55. Fischer B, Thomas K, Dorner F. Annuals of Hematology. 1998; 76:159–166.
56. Dixit P, Chen X, Miao J, Preisser R. Thin Solid Films. 2008; 516:5194–5200.
57. Wang T, Lu H, Lou P. Biomaterials. 2008; 29:4447–4454. [PubMed: 18752845]
58. Dixit P, Chen X, Miao J, Divakaran S, Preisser R. Applied Surface Science. 2007; 253:8637–8646.
59. Saif T. Journal of Fluid Mechanics. 2002; 473:321–347.
60. Li H, Guo X, Nuzzo RG, Hsia J. Journal of the Mechanics and Physics of Solids. 2010; 58:2033–2042.
61. Guo X, Li H, Ahn BY, Duoss EB, Hsia KJ, Lewis JA, Nuzzo RG. Proceedings of the National Academy of Sciences of the United States of America. 2009; 106:20149–20154. [PubMed: 19934059]
62. Radmacher M. Methods in cell biology. 2002; 68:67–90. [PubMed: 12053741]
63. Engler AJ, Rehfeldt F, Sena S, Discher DE. Methods in cell biology. 2007; 83:521–545. [PubMed: 17613323]
64. Tang, X.; Cappa, T.; Kuhlenschmidt, T.; Kuhlenschmidt, M.; Saif, T. Specific and non-specific adhesion in cancer cells with various metastatic potentials. Johnson, AW.; Harley, B., editors. Springer Science; 2011. ch. Specific and Non-Specific Adhesion in Cancer Cells with Various Metastatic Potentials
65. Yang, S.; Saif, T. Experimental mechanics. 2009.
66. Minary-Jolandan M, Yu MF. Biomacromolecules. 2009; 10:2565–2570. [PubMed: 19694448]
67. Minary-Jolandan M, Yu MF. Journal of Applied Physics. 2008; 103:0735161–0735165.

68. Minary-Jolandan M, Yu MF. ACS Nano. 2009; 3:1859–1863. [PubMed: 19505115]
69. Florin EL, Rief M, Lehmann H, Ludwig M, Dornmair C, Moy VT, Gaub HE. Biosensors and Bioelectronics. 1995; 10:895–901.
70. Kuznetsova TG, Starodubtseva MN, Yegorenkov NI, Chizhik SA, Zhdano RI. Micro. 2007; 38:824–833.
71. Evans A, Bartlett A, He MY. Acta Metallurgica. 1989; 37:3249–3254.
72. Evans A, Hutchinson J. Acta Metallurgica. 1989; 37:909–916.
73. He MY, Bartlett A, Evans AG, Hutchinson JW. Journal of the American Ceramic Society. 1991; 74:767–771.
74. He M-Y, Hutchinson JW. Journal of Applied Mechanics. 1989; 56:270–278.
75. Suo Z. Materials Science and Engineering: A. 1989; A107:135–143.
76. Cao HC, Evans A. Mechanics of materials. 1989; 7:295–304.
77. Akisanya AR, Fleck NA. International journal of fracture. 1992; 55:29–45.
78. Akisanya AR, Fleck NA. International journal of fracture. 1992; 58:93–114.
79. Sethuraman A, Han M, Kane RS, Belfort G. Langmuir. 2004; 20:7779–7788. [PubMed: 15323531]
80. Xu LC, Siedlecki CA. Biomaterials. 2007; 28:3273–3283. [PubMed: 17466368]
81. Sigal GB, Mrksich M, Whitesides GM. Journal of the American Chemistry Society. 1998; 120:3464–3473.
82. Wu Y, Simonovsky FI, Ratner BD, Horbett TA. J Biomed Mater Res A. 2005; 74:722–738. [PubMed: 16037938]
83. Israelachvili J, Wennerstrom H. Nature. 1996; 379:219–225. [PubMed: 8538786]
84. Noh H, Vogler EA. Biomaterials. 2006; 27:5801–5812. [PubMed: 16928398]

Figure 1.

(a1–a4) Schematic diagram illustrating the basic steps of optical lithography process for Si master fabrication. After development, the SU-8 photoresist surface was treated with FDTs vapor to aid the removal of the cured PDMS stamp. The right side legend shows the color representing the specific components. (b1) and (b2) Soft lithography to make the PDMS stamp by casting PDMS pre-polymer against the Si master. (b3) and (b4) Microcontact printing of fibronectin on treated/untreated glass cover slip. (b5), (b6) and (b7) Activated glass cover slip is floated over the precursor gel solution on the protein micro-patterned slide. The polymerization was performed at 37 °C. (b8) The top cover slip is peeled off once the polymerization is complete.

Figure 2.

(a1–a4) Micrographs of SU-8 line-array micropatterns on Si wafer. Scale bar: $250\ \mu\text{m}$; (b) Typical 1D surface profile of the Si/SU8 master, measured by the profilometer. The thickness of SU-8 layer is $2\ \mu\text{m}$; (c) PDMS stamp with well-defined line-array micropatterns of different line widths, $100\ \mu\text{m}$ (c1), $50\ \mu\text{m}$ (c2), $10\ \mu\text{m}$ (c3) and $5\ \mu\text{m}$ (c4), respectively. Scale bar: $100\ \mu\text{m}$; (d) Fluorescence microscopy images of the immunofluorescent-stained fibronectin line patterns on PDMS (d1), intermediate glass (d2) and PA hydrogels (d3), respectively. Mid region of the pattern is missing on gel in (d3). Scale bar: $10\ \mu\text{m}$.

Figure 3.

(a) Phase contrast image of 100 μm fibronectin line patterns transferred to polyacrylamide gels with the intermediate glass peeled from the front. Peeling proceeds along the line patterns (see Fig 4). Scale bar: 100 μm . (b) Phase contrast image of 100 μm fibronectin line patterns transferred to polyacrylamide gels with the intermediate glass peeled from the side such that peeling proceeds orthogonal to the line patterns. Scale bar: 100 μm . (c) Phase contrast image of 5 μm fibronectin line patterns transferred to polyacrylamide gels with the intermediate glass peeled from front or side part. Scale bar: 50 μm . (d) Phase contrast micrograph of the intermediate glass slide after peeling off. The pattern was 100 μm wide. The image shows clear evidence of fibronectin residues on glass. Scale bar: 100 μm . In all insets: Immunofluorescent-staining of FN.

Figure 4. Normal peeling forces (90° w.r.t gel/glass interface) are applied at different positions for wide line pattern, i.e. 100 μm . The cracks propagate along 2 different directions, respectively. (a1) Peeling force is applied as shown. (a2) cracks propagate along the line patterns. The entrapped cracks propagate inward from the sides. (a3) The resulting FN patterns on gel and FN residues on intermediate glass slides. (b1–b2) cracks propagate orthogonally to the line patterns. (b3) The resulting FN patterns on gel and FN residues on intermediate glass slides.

Figure 5.
(a, b) Alpha-profiler shows the FN profile across 100 and 5 μm line patterns on intermediate glass slide respectively.

Figure 6.

Experimental results from AFM experiments. (a) Representative force-distance curves for as received glass cover slip without any modification. Inset: Contact angle is 42°. (b) Representative force-distance curves for the more wettable glass cover slip after piranha treatment. Inset: Contact angle is 0°. (c) Bar chart for the maximum adhesion forces. The results indicate a 7 times decrease in adhesion strength for the more wettable sample.

Figure 7.

Phase contrast images of the FN patterns (on PA gels) with different line widths that were transferred with the hydrophilic glass slides. The line pattern widths are (a) 100 μm , (b) 10 μm , and (c) 5 μm , respectively. The results demonstrated significant improvement in the efficacy of the approach irrespective of the patterns width ($\sim 100\%$). The immuno-fluorescent staining of FN patterns images (on PA gels) with different line width, (d) 100 μm , (e) 15 μm , and (f) 5 μm , respectively, prove that the FN patterns are completely transferred without major central defects. Scale bars were shown on each image.

Normal Fibroblasts (MKF) **Figure 8.**

Fibroblasts (MKF) were cultured on micro-patterns with varied line widths and extracellular matrices. The cells are well confined inside the patterns. (a, b) MKF cultured on 400 and 100 μm fibronectin (FN) line patterns on 3rd culture day; (d, e) MKF cultured on 100 and 10 μm laminin (LN) line patterns on 3rd culture day; (g, h) MKF cultured on 1000 and 30 μm collagen I (CN) line patterns on 5th culture day. (c, f, i) The trypan blue live-dead assay experiments show cells are alive and compatible with the micro-patterned gel substrate.