Published in final edited form as:

ACS Macro Lett. ; 1(8): 1071–1073. doi:10.1021/mz3003775.

Strain-Promoted Crosslinking of PEG-based Hydrogels via Copper-Free Cycloaddition

Jukuan Zheng[†], Laura A. Smith Callahan[†], Jinkun Hao[‡], Kai Guo[†], Chrys Wesdemiotis^{†,||}, R. A. Weiss[‡], and Matthew L. Becker^{†,§,*}

[†]Department of Polymer Science, The University of Akron, Akron, OH, 44325

[‡]Department of Polymer Engineering, The University of Akron, Akron, OH, 44325

^{||}Department of Chemistry, The University of Akron, OH, 44325

[§]Center for Biomaterials in Medicine, Austen Bioinnovation Institute in Akron, Akron, OH 44308

Abstract

The synthesis of a 4-dibenzocyclooctynol (DIBO) functionalized polyethylene glycol (PEG) and fabrication of hydrogels via strain-promoted, metal-free, azide-alkyne cycloaddition is reported.

The resulting hydrogel materials provide a versatile alternative in which to encapsulate cells that are sensitive to photochemical or chemical crosslinking mechanisms.

Keywords

hydrogel; click chemistry; human mesenchymal stem cell; cycloaddition

Polymeric hydrogels are used widely in a number of regenerative medicine applications¹⁻³. Hydrogels are ideal materials for implantation because they generally introduce low levels of foreign matter into the host and afford high levels of metabolite and biomolecule transport⁴. Injectable hydrogels that form in situ hold additional promise as they are able to adapt to complicated defect sites relative to preformed hydrogels⁵. The crosslinking mechanisms in hydrogels can be either chemical or physical⁶⁻¹⁶. Both have advantages and disadvantages^{4,12,17}. The onset of gel formation in covalently crosslinked hydrogels is typically dependent on chemical or photochemical processes to initiate network formation from monomeric precursors. Chemical methods include various click reactions,¹⁸ thiolene additions,⁷ metal-catalyzed azide-alkyne cycloadditions,^{6,19} Michael additions²⁰ and Diels-Alder reactions¹⁴. However, the use of radical initiating systems, ultraviolet (UV) light, and the presence of residual metal catalysts, organic solvents, and the incomplete conversion of the functional groups may lead to biocompatibility problems in sensitive cell types. Because many chemical crosslinkers are toxic and result in noninjectable gels, physical hydrogels are preferred for many biomedical applications. However, the assembly of polymers into physical hydrogels for cell encapsulation typically requires the use of an external trigger including a change in pH, temperature, or ionic concentration to induce gelation^{4,16,21-24}. The experimental demands for each of these gelation and functionalization strategies places distinct constraints on the utility and versatility of the respective hydrogel and make direct clinical translation very difficult.

*Corresponding Author, Professor Matthew L. Becker, becker@uakorn.edu.

Supporting Information

The details about the synthesis of DIBO, DIBO-functionalized PEG, and the rheology experiments can be found in the supporting information. "This material is available free of charge via the Internet at <http://pubs.acs.org>."

Metal free, strain-promoted azide-alkyne “click” cycloaddition reactions have been applied to cell imaging²⁵⁻²⁷ as well as hydrogels systems due to its highly efficient conversion, orthogonality, and bio-friendly characteristics.^{9,11,13} In this work, we describe the fabrication of a covalently crosslinked hydrogel via a strain-promoted cycloaddition reaction between 4-dibenzocyclooctynol (DIBO) functionalized poly(ethylene glycol) (PEG) and a 3-arm glycerol oxythiolate triazide. The DIBO-functionalized PEG was synthesized using a 4-nitrophenyl chloroformate activated 4-dibenzocyclooctynol and poly(ethylene glycol) bis amine. ¹H NMR (SI) and MALDI-TOF (Figure 1) results demonstrate the complete conversion of the amine group to dibenzocyclooctynol. Concentration control is critical to achieving complete conversion.

Glycerol oxythiolate triazide was synthesized using glycerol oxythiolate as the starting material. The hydroxyl groups were derivatized with methane sulfonyl chloride and further substituted using sodium azide in a two-step process. The desired product was purified by column chromatography and substantiated with ¹H NMR (SI) and MALDI-TOF (Figure 2). Purified mat mechanical properties. To demonstrate the gelation of the two precursors in aqueous solution, a stoichiometric mixture of DIBO-functionalized PEG was dissolved in 50 uL ultrapure water, based on the calculation of 1:1 molar ratio for the DIBO group and azide group, 1.1 mg glycerol oxythiolate triazide is dissolved in 50 uL ultrapure water and these two solutions were mixed. Within 5 minutes, the solution gelled when agitated gently (Scheme 1). FTIR of the freeze-dried hydrogels confirms the disappearance of the azide groups (SI).

To assess whether the gel is suitable for injectable gel applications, an oscillatory shear rheology experiment was performed to study the gelation kinetics under applied mechanical forces (Figure 3). Measurements were made at 24 °C with a TA Instruments ARES-G2 rheometer equipped with 8 mm parallel plates and using a frequency of 10 rad/s (1.6 Hz) and a strain amplitude of 10%. To maintain hydration of the hydrogel sample during the experiment, the lower plate fixture included a solvent trap filled with an aqueous solution of DIBO-PEG and glycerol oxythiolate triazide (1:1). The large scatter in the data at times less than 600 s is a consequence of the very low viscosity of the solution before sufficient crosslinking was achieved. As a consequence, the torque values are too low to obtain reliable readings from the force transducer. However, after 600 s the torque magnitude was sufficiently high, and both G' (the elastic part of the complex modulus, G^*) and G'' (the viscous component of G^*) increased exponentially with time.

At the beginning of the experiment, the solution is a viscous liquid and it is expected that $G'' > G'$. The crossover of G' and G'' near $t \sim 1000$ represents the gel point, where the crosslinking reaction has proceeded sufficiently in that the material transforms from a viscous liquid to a viscoelastic solid²⁸. After about 2.5 h, the dynamic moduli reached equilibrium values, indicating that the crosslinking reaction was complete. The gel was fully hydrated throughout the experiment and at the end of the reaction the gel contained 96.1 % water and the plateau modulus, GN' was ~ 0.8 kPa. This corresponds to a crosslink density of 8.6 mol/m^3 , which was calculated using the classical theory of rubber elasticity. The loss factor $\tan \delta$ (G''/G') decreased from a value of ~ 1 , which is typical of a viscous liquid to a value of ~ 0.25 at the end of the reaction, which is consistent with the formation of a viscoelastic solid ($\tan \delta$ is zero for an elastic solid). This reaction was also shown to be strain sensitive.

Human mesenchymal stem cells (hMSCs) were used to test the influence of the hydrogel crosslinking on cell viability (Figure 4). hMSCs (passage 5, 500,000 cells, Lonza, Basel, Switzerland) were suspended in 25 μL of 20 wt% DIBO-PEG in α -MEM basal Media (Lonza). 25 μL of 2.56 wt% glycerol oxythiolate triazide in α -MEM basal Media was added

to the cell suspension. The samples were mixed via gentle pipetting and placed in a mold to solidify. After 5 min, the hydrogels were transferred by spatula to a 12-well plate and cultured in α -MEM basal Media for 24 h in a 37 °C, 5% CO₂ incubator. A live dead assay (Invitrogen, Carlsbad, CA) was performed. 1.5 μ L of 1 mg/mL Calcein AM and 0.1 μ L of 2 mM ethidium homodimer-1 was added per mL of culture media and the samples were incubated for 10 minutes. The samples were then washed with media and viewed on a 1 $\times$ 81 $\times$ microscope (Olympus, Center Valley, PA). The encapsulation of cells and presence of media additives did not affect the gelation process. The dominant green fluorescence from live cells in the live/dead cell staining after 24 h of culture demonstrates the excellent biocompatibility of these hydrogels (>95%). Tri-arm molecules not converted to the azide do not gel as expected and hMSCs mixed with the individual components do not exhibit toxicity (data not shown) under identical concentration conditions.

In conclusion, we have made a covalently crosslinked hydrogel that is versatile and biocompatible based on a metal free, strain-promoted azide-alkyne cycloaddition process. These results demonstrate an effective strategy to encapsulate cells within hydrogels where gelation is based on the cumulative effects of specific molecular-recognition interactions between strained cyclooctyne units and azide terminated PEG chains. The potential variability in the molecular mass of the respective components, number of branch units and compatibility with both hMSCs and cell media provides versatility in applications where syringe injectable materials or in situ formation of hydrogels are necessary.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The authors gratefully acknowledge support from the National Science Foundation (RAW, CBET-1066517) and the National Institute of Health (MLB, P41 EB0063536).

References

1. Drury JL, Mooney DJ. *Biomaterials*. 2003; 24:4337–4351. [PubMed: 12922147]
2. Langer R, Tirrell DA. *Nature*. 2004; 428:487–492. [PubMed: 15057821]
3. Lee KY, Mooney DJ. *Chem Rev*. 2001; 101:1869–1879. [PubMed: 11710233]
4. Aizawa Y, Owen SC, Shoichet MS. *Prog Polym Sci*. 2012; 37:645–658.
5. Jin R, Teixeira LSM, Krouwels A, Dijkstra PJ, van Blitterswijk CA, Karperien M, Feijen J. *Acta Biomaterialia*. 2010; 6:1968–1977. [PubMed: 20025999]
6. Nimmo CM, Shoichet MS. *Bioconjugate Chemistry*. 2011; 22:2199–2209. [PubMed: 21995458]
7. Salinas CN, Anseth KS. *Macromolecules*. 2008; 41:6019–6026.
8. Pritchard CD, O'Shea TM, Siegwart DM, Calo E, Anderson DG, Reynolds FM, Thomas JA, Slotkin Jr, Woodard EJ, Langer R. *Biomaterials*. 2011; 32:587–597. [PubMed: 20880573]
9. DeForest CA, Polizzotti BD, Anseth KS. *Nature Materials*. 2009; 8:659–664.
10. DeForest CA, Sims EA, Anseth KS. *Chem Mater*. 2010; 22:4783–4790. [PubMed: 20842213]
11. DeForest CA, Anseth KS. *Nature Chemistry*. 2011; 3:925–931.
12. Hennink WE, van Nostrum CF. *Advanced Drug Delivery Reviews*. 2002; 54:13–36. [PubMed: 11755704]
13. Xu J, Fillon TM, Prifti F, Song J. *Chem Asian J*. 2011; 6:2730–2737. [PubMed: 21954076]
14. Tan H, Rubin JP, Marra KG. *Macromolecular Rapid Communications*. 2011; 32:905–911. [PubMed: 21520481]
15. Wang Z-C, Xu X-D, Chen C-S, Yun L, Song J-C, Zhang X-Z, Zhuo R-X. *ACS Applied Materials & Interfaces*. 2010; 2:1009–1018. [PubMed: 20423120]

16. Yamaguchi N, Zhang L, Chae B-S, Palla CS, Furst EM, Kiick KL. *J Amer Chem Soc.* 2007; 129:3040. [PubMed: 17315874]
17. Aguado BA, Mulyasmita W, Su J, Lampe KJ, Heilshorn SC. *Tissue Engineering Part A.* 2012; 18:806–815. [PubMed: 22011213]
18. Iha RK, Wooley KL, Nystrom AM, Burke DJ, Kade MJ, Hawker CJ. *Chem Rev.* 2009; 109:5620–5686. [PubMed: 19905010]
19. van Dijk M, van Nostrum CF, Hennink WE, Rijkers DTS, Liskamp RMJ. *Biomacromolecules.* 2010; 11:1608–1614. [PubMed: 20496905]
20. Bencherif SA, Washburn NR, Matyjaszewski K. *Biomacromolecules.* 2009; 10:2499–2507. [PubMed: 19711888]
21. Kim IL, Mauck RL, Burdick JA. *Biomaterials.* 2011; 32:8771–8782. [PubMed: 21903262]
22. Niece KL, Czeisler C, Sahni V, Tysseling-Mattiace V, Pashuck ET, Kessler JA, Stupp SI. *Biomaterials.* 2008; 29:4501–4509. [PubMed: 18774605]
23. Pochan DJ, Schneider JP, Kretsinger J, Ozbas B, Rajagopal K, Haines L. *J Amer Chem Soc.* 2003; 125:11802–11803. [PubMed: 14505386]
24. Seal BL, Panitch A. *Biomacromolecules.* 2003; 4:1572–1582. [PubMed: 14606882]
25. Ning X, Guo J, Wolfert MA, Boons G-J. *Angew Chem Int Ed.* 2008; 47:2253–2255.
26. Chang PV, Prescher JA, Sletten EM, Baskin JM, Miller IA, Agard NJ, Lo A, Bertozzi CR. *Proc Natl Acad Sci USA.* 2010; 107
27. Laughlin ST, Bertozzi CR. *ACS Chemical Biology.* 2009; 4
28. Winter HH, Chambon F. *J Rheology.* 1986; 30:367–382.

Figure 1. MALDI-TOF mass spectrum of DIBO-PEG (cationized with NaTFA); monoisotopic mass-to-charge ratios (m/z) are marked in the upper spectrum. The measured m/z values agree with the desired structure.

Figure 2. MALDI-TOF mass spectrum of glycerol oxythiolate triazide (cationized with NaTFA); monoisotopic mass-to-charge ratios (m/z) are marked in the upper spectrum. The measured m/z values agree with the desired structure.

Figure 3. Modulus-time dependence of hydrogels during the process of oscillation shear

Figure 4.

A Live-Dead assay was used to assess the viability (>95%) of human mesenchymal stem cells that were crosslinked in situ and cultured in hydrogels for 24 h. Live cells are stained green and dead cells are stained red. The scale bar is 50 μm .

SCHEME 1.

DIBO-PEG and glycerol oxythiolate triazide form hydrogel networks when mixed in situ. The rate of network formation can be influenced by the rate and amplitude of strain.