Published in final edited form as:

Electrophoresis. 2008 December ; 29(23): 4669–4676. doi:10.1002/elps.200800353.

Hydrophobically Modified Polyacrylamide Block Copolymers for Fast, High-Resolution DNA Sequencing in Microfluidic Chips

Ryan E. Forster¹, Thomas N. Chiesl^{2,3}, Christopher P. Fredlake², Corin V. White², and Annelise E. Barron^{2,4,*}

¹Department of Materials Science and Engineering, Northwestern University, Evanston, IL USA

²Department of Chemical and Biological Engineering, Northwestern University, Evanston, IL USA

Abstract

By using a microfluidic electrophoresis platform to perform DNA sequencing, genomic information can be obtained more quickly and affordably than the currently employed capillary array electrophoresis (CAE) instruments. Previous research in our group has shown that physically cross-linked, hydrophobically modified polyacrylamide (HMPAM) matrices separate double-stranded DNA (dsDNA) more effectively than linear polyacrylamide (LPA) solutions. Expanding upon this work, we have synthesized a series of linear polyacrylamide-co-dihexylacrylamide (LPA-co-DHA) block copolymers specifically designed to electrophoretically sequence single-stranded DNA (ssDNA) quickly and efficiently on a microfluidic device. By incorporating very small amounts of *N,N*-dihexylacrylamide, a hydrophobic monomer, these copolymer solutions achieved up to ~10% increases in average DNA sequencing read length over LPA homopolymer solutions of matched molar mass. Additionally, the inclusion of the small amount of hydrophobe does not significantly increase the polymer solution viscosities, relative to LPA solutions, so that channel loading times between the copolymers and the homopolymers are similar. The resulting polymer solutions are capable of providing enhanced sequencing separations in a short period of time without compromising the ability to rapidly load and unload the matrix from a microfluidic device.

Keywords

Linear polyacrylamide; Microchip electrophoresis; Polymer solutions; DNA sequencing; Viscosity

1 Introduction

The need for rapid, accurate, and affordable methods to analyze and sequence human genomic DNA has spurred technological advancements in an effort to realize personalized healthcare. The development of CAE systems, for example, allowed for the complete sequencing of the human genome ahead of schedule[1, 2]. Optimization of these systems and materials have demonstrated the capability to sequence up to 1300 bases in approximately 2 hours[3], and commercial instruments can regularly achieve read lengths on

*To whom correspondence should be addressed: Stanford University, Department of Bioengineering, W300B James H. Clark Center, Stanford, CA 94305, aebarron@stanford.edu, Tel: (650) 721-1151, Fax: (650) 723-9801.

³Present address: College of Chemistry, University of California, Berkeley, CA USA

⁴Present address: Department of Bioengineering, 318 Campus Drive, Clark Center Drive Room S170, Stanford University, Stanford, CA 94305 USA

Conflicts of interest

The authors declare no conflicts of interest.

the order of 700–1000 bases. In order to sequence repeat-rich genomes, these long read lengths are necessary [4, 5]. And although genome centers utilizing many CAE systems in parallel are capable of analyzing very large amounts of genomic material, the costs in terms of money and time for CAE are too high for widespread use of complete genome sequencing for routine medical care.

To reduce the overall cost of sequencing DNA, the current trend in Sanger-based technologies is shifting towards utilizing microfluidic devices for both sample preparation and DNA separation by electrophoresis[6–12]. Integrated microfluidic sequencing systems were pioneered by the Mathies group [13] and further sequencing studies have shown that on single-channel chips, up to 600 bases can be sequenced in under 7 minutes[14], and 96-microchannel array chips are capable of sequencing an excess of 100,000 bases per hour when using post-purified and amplified DNA samples[15]. This combination of increased sequencing speed, along with reduced sample and reagent requirements and on-chip integration of sample preparation steps will lower the overall cost to sequence a genome and advance the development of point-of-care field devices for testing patients and detecting various harmful biological agents.

Linear polymer solutions are commonly used for DNA separations on capillaries and microfluidic chips because they can easily be loaded into and removed from the separation channel [16–20]. To achieve read lengths of 500–700 bases on microfluidic devices, polymers in excess of 1 MDa and polymer solution concentrations of ~ 4% (w/v) are typical, which can lead to very viscous matrices. Increasing the molar mass of the separation polymer can increase DNA sequencing read lengths[21], however, this also increases the solution viscosity and therefore the amount of time required to load the separation matrix into a microchannel[22–24].

Here, we describe the synthesis of hydrophobically modified block copolymers composed primarily of a hydrophilic acrylamide backbone structure with small, randomly placed blocks of *N,N*-dihexylacrylamide, and the formulation of these materials into DNA sequencing matrices[25–27]. We show that with the addition of only ~ 0.1 mol% of the hydrophobic monomer, this system can give improvements of up to 10% in DNA sequencing read length over linear polyacrylamide homopolymers of equivalent molar mass. This improvement in performance is attributed to the physical cross-linking that takes place between the hydrophobic blocks in the copolymers, forming a more robust network structure. However, the physical associations can be broken and reformed through the application of shear forces when loading the copolymer into a microfluidic channel, so that the matrix loading time is essentially unaffected by the presence of the hydrophobic blocks in the copolymer[26, 28].

2 Materials and methods

2.1 Monomer synthesis

The hydrophobic *N,N*-dihexylacrylamide (DHA) monomer utilized in this study was synthesized in our lab as described previously[27], using a process similar to one originally described by McCormick *et al.* [29]. The reagents dihexylamine, triethylamine, acryloyl chloride, and methylene chloride were all purchased from Sigma-Aldrich (Milwaukee, WI) and were used as received. The dihexylamine was initially dissolved at 10 mM in 120 mL of methylene chloride along with an equimolar concentration of triethylamine, and added into a round-bottom flask, which was placed in an ice bath throughout the reaction process. In a separate beaker, acryloyl chloride was dissolved at 10 mM into 120 mL of methylene chloride and subsequently added drop-wise into the amine solution, at a rate of approximately 0.5 mL/min, under a nitrogen atmosphere. Once the acryloyl chloride

solution was completely incorporated, the mixture was allowed to react for an additional hour before purification. The reaction product was purified by performing three aqueous extractions in series utilizing 1M HCl, 0.5M NaOH, and finally deionized (DI) water. Following the final extraction, the methylene chloride phase was removed with a rotary evaporator attached to a dry ice/acetone/methanol cold trap, leaving behind the pure *N,N*-dihexylacrylamide monomer.

2.2 Polymer and copolymer synthesis and characterization

All of the polymerizations took place under nitrogen in 500 mL 3-neck flasks attached to a temperature controlled recirculating water bath. The LPA and poly-*N*-hydroxyethylacrylamide (pHEA) utilized in this study were both synthesized *via* standard aqueous-phase free radical polymerization methods. For the LPA homopolymers, acrylamide monomer (Amresco, Inc., Solon, OH) was dissolved at 4% (w/w) in DI water along with approximately 1–3% (w/w) of isopropyl alcohol (IPA) (Fisher Scientific, Waltham, MA, USA), which acts as a chain transfer agent, to obtain the desired average molar mass. PHEA was synthesized using a similar procedure where HEA monomer (Cambrex, Inc, East Rutherford, NJ USA) was dissolved at 2% (w/w) in DI water along with 0–0.2% (w/w) of IPA. For both reactions, the solution was degassed for at least 30 minutes with nitrogen and heated to 50 °C prior to initiation. The polymerizations were initiated with 0.004–0.005 g of 4'-Azobis(4-cyanovaleric acid) (ACVA) per 100 g of monomer solution, and allowed to react for 6 hours. The resulting polymers were dialyzed in 100 kDa molecular weight cutoff membranes against DI water for two weeks, with 15–20 water changes to remove any unreacted monomer and low molar mass material. Following dialysis, the polymers were frozen at –80 °C and recovered by lyophilization.

HMPAM block copolymers cannot be synthesized by standard aqueous-phase free-radical polymerization techniques. The *N,N*-dialkylacrylamide monomers are not soluble in aqueous environments, therefore micellar free-radical polymerization was used to achieve the desired structure. A second phase consisting of sodium dodecyl sulfate (SDS) micelles was used to incorporate the hydrophobic monomer into the copolymer backbone and also allows the average number of hydrophobic molecules included into each block to be controlled[25, 30]. The LPA-co-DHA used for sequencing was synthesized by dissolving acrylamide monomer at 4% (w/w) in DI water along with 0.1 mol% of DHA monomer, and approximately 1–3% (w/w) chain transfer agent, IPA, to obtain the desired molecular weight. Approximately 0.46 g of SDS (Sigma, St. Louis, MO, USA) was added per 100 g of monomer solution to obtain a desired average hydrophobic block size of 5 units. Prior to initiation, the solution was allowed to mix for 30 minutes, degassed for an additional 30 minutes with nitrogen and heated to 50 °C. The polymerization was initiated with 0.005 g of ACVA per 100 g of monomer solution, and allowed to react for 5–6 hours. The resulting polymers were precipitated with acetone, to help remove the SDS present in the reaction mixture, redissolved in DI water, and dialyzed in 100 kDa molecular weight cutoff membranes against DI water for two weeks with 15–20 water changes to remove any unreacted monomer, SDS, and low molar mass material. Following dialysis, the copolymers were frozen at –80 °C and recovered by lyophilization.

To determine the average polymer molar mass, polydispersity index, and root mean square radius of gyration, the polymers were fractionated *via* tandem gel permeation chromatography with a Waters 2690 Alliance Separations Module (Waters Corp., Milford, MA) outfitted with Shodex OHPak SB-806 HQ, SB-804 HQ, and SB-802.5 HQ columns (New York, NY USA) connected in series. The fractionated polymer solution was sent through a DAWN DSP Laser Photometer Multi-angle laser light scattering (MALLS) instrument followed by an Optilab DSP refractive index detector (both instruments from Wyatt Technology Corp, Santa Barbara, CA). The resulting data were analyzed using

ASTRA (Wyatt Technologies Corp) based on a known sample concentration, 100% mass recovery, and known system constants. Both LPA and pHEA were dissolved at 1 mg/ml in a buffer containing 0.1M NaCl, 50mM NaH₂PO₄ and 200 ppm NaN₃, while the LPA-co-DHA was dissolved at 5 mg/ml in a 33% methanol buffer, due to the moderately hydrophobic nature of the copolymer.

2.3 Viscosity and microfluidic chip loading measurements

Rheological tests were performed on a Paar Physica MCR 300 Rheometer (Ashland, VA, USA) outfitted with a 50-mm, 2° cone-and-plate fixture held at 25 °C by a recirculating water bath (Julabo USA Inc., Allentown, PA, USA) connected to a TEK 150PA-C model Peltier controller. Approximately 1.14 mL of the polymer solution was injected between the cone and plate fixture and analyzed using a shear rate sweep from 0.1 to 1000 sec⁻¹ and a shear stress sweep from 0.01 to 100 Pa utilizing a logarithmic ramp and collecting 7 points per decade. The resulting data were analyzed to remove any points below the torque limit of the machine and overlaid to create a complete series of data from ~0.01 to 1000 sec⁻¹.

Load times of the polymer solutions into the 8-cm glass microfluidic chips were determined using a modified hydraulic press applying ~200 psi of pressure *via* an attached nitrogen tank. The amount of time required to fill up the entire chip with the polymer solution was recorded for each of the sequencing polymer matrices utilized in this study.

2.4 Microchip electrophoresis

The M13 sequencing ladder and ssDNA ET-900 Ladder (both from Amersham GE Healthcare, Piscataway, NJ) were analyzed on a microchip electrophoresis system custom-built in-house, which is capable of multi-color laser-induced fluorescence (LIF) detection. This system has been previously described in detail by Chiesl *et al.*[27], and consists of electrical and optical subsystems that can be used in conjunction with a temperature-control plate capable of maintaining the microchips at 50 °C for sequencing experiments.

The T8050 borosilicate glass microfluidic chips used in this study were purchased from Micronit Microfluidics (Enschede, The Netherlands) and consist of a single channel that has an effective DNA separation length of 7.5 cm. Each channel is 50 µm wide, 20 µm deep and utilizes a 100 µm offset T injection scheme. Prior to use, the channels were dynamically coated with a 0.10% (w/w) solution of pHEA to reduce electroosmotic flow and bioanalyte adsorption onto the channel walls[31, 32].

The DNA separation experiments were performed using LPA and LPA-co-DHA solutions of 2–4% (w/w) dissolved in 1x TTE (49 mM Tris, 49 mM TAPS, and 2 mM EDTA) with 7 M urea. Each test consisted of a 60-second pre-electrophoresis of the primary separation channel at an electric field of ~187 V/cm. This was followed by a 40 second injection of the sample at 400 V/cm. The plug of DNA was then separated at 187 V/cm in the primary channel with pullback fields of 150 V/cm being applied to the sample and sample waste wells to prevent leakage of sample into the separation channel. The resulting data were analyzed using NNIM Basecaller (NNIM, LLC, Salt Lake County, UT) and Sequencher V 4.05 (Gene Codes Corp., Ann Arbor, MI).

2.5 Single-molecule fluorescent imaging of electrophoresing DNA

Individual molecules of λ-DNA (Invitrogen, San Diego, CA) fluorescently labeled with YOYO-1 were imaged *via* a lab-built epifluorescence videomicroscopy system as previously described[28, 33]. The voltage (~100 V/cm) for electrophoresis of the DNA was obtained using a modified Micronit Microfluidics electrophoresis kit. The imaging setup was composed of a Nikon TE2000 U inverted epifluorescence microscope (Nikon Instruments

Inc., Melville, NY) with a Nikon CFI 100x/N.A. 1.4 oil immersion objective. Fluorescence was obtained with a 100-watt Hg broadband lamp focused through a blue light excitation filter cube (460–500 nm) (Chroma Technology, Rockingham, VT) and reflected off of a dichroic beam splitter through the objective. The resulting fluorescence returns through the dichroic beam splitter and a 510 nm long pass filter. The signal is amplified with a VS4-1845 Generation 3 image intensifier (Videoscope International, Dulles, VA) and collected on a 0.5" CCD TM-6710-CL camera (JAI Pulnix, Sunnyvale, CA). The videos of the DNA molecules were collected at 30 frames/sec onto a computer utilizing XCAP-STD software and a PIXCI control board (EPIX Inc., Buffalo Grove, IL).

3 Results and discussion

3.1 DNA sequencing with HMPAMs

HMPAMs were originally developed in our group by Chiesl *et al.* to be utilized as a sort of hydrophobic “guard column” for the removal of proteins from crude biological samples while allowing DNA to pass through unhindered[27]. During this study it was observed that dsDNA was separated with greater resolution using HMPAMs compared to an LPA of matched molar mass[28]. Here, we expand upon that work by analyzing the DNA sequencing capability of specially tailored hydrophobically modified copolymers when compared to equivalent molar mass homopolymers of LPA. A series of copolymers were synthesized with average molar masses of 1.4 MDa, 2.8 MDa, and 7.3 MDa, each containing ~ 0.10 mol % of DHA; and polymer solutions were formulated at concentrations ranging from 2–4% (w/w) in 1x TTE aqueous buffers with 7M urea. Copolymers containing ~0.10 mol % DHA were synthesized for this study because Chiesl *et al.* showed that there is no discernable improvement in dsDNA separation resolution obtained in HMPAMs by exceeding this value. Additionally, increasing the hydrophobe content increases the viscosity of the copolymer separation matrix, making it more difficult to quickly load and unload the copolymer solutions from the microfluidic channels[28]. Matched molar mass LPAs were synthesized at 1.4 MDa and 2.8 MDa and 4 % (w/w) solutions of the polymers were formulated for comparison with the copolymer solutions. The physical properties of the polymers utilized in this study are shown in Table 1. The sequencing performance of the LPA and LPA-co-DHA polymer solutions were determined using a ssDNA M13 DNA sequencing standard in glass microfluidic chips dynamically coated with pHEA. The average read length was obtained by taking the average of 4 sequencing runs with the 4% solutions and the average of 2 sequencing runs with the 2% and 3% solutions (at 98.5% accuracy when compared to the known M13 DNA sequence).

As can be seen in Table 2, the average sequencing read length increases significantly as the polymer concentration is changed from 2% to 4%, and the longest sequencing lengths are obtained in the 4% solutions. It was also observed that the maximum average sequencing length increased slightly from 554 bases to 583 bases with the increase in molar mass from 1.4 MDa to 7.3 MDa with the longest observed run yielding over 600 bases, as shown in Figure 1. This small variation in read length with such a large increase in polymer molar mass is beneficial from a quality control perspective. If a small variation in molecular weight has a large impact on the sequencing performance, the synthesis requirements become much more stringent, and batches of expensive polymer could easily be wasted. If the final average molar mass does not significantly impact the sequencing capability, less polymer would be wasted, and less rigorous synthesis protocols would be necessary.

Interestingly, a ~10% increase in average sequencing read length (554 bases vs. 508 bases) was obtained with the 1.4 MDa LPA-co-DHA when compared to an LPA at the same molar mass. The improvement in sequencing read length appears to decrease at the higher molecular weight, as the 2.8 MDa LPA-co-DHA copolymer provides an average read length

only ~ 4% greater than the 2.8 MDa LPA (561 bases vs. 541 bases). The 4% solutions tested in this study achieved their separations rapidly, taking only 10–11.5 minutes to sequence 550–600 bases. Previously published sequencing results on microfluidic devices have typically ranged from 15–30 minutes, with recent chip-based sequencing data from Fredlake *et al.* showing 600-base reads that are complete within 6.5 minutes[6, 7, 14].

We hypothesize that the increase in sequencing read length obtained in the HMPAM copolymer networks is due to the intermolecular and intramolecular physical crosslinking that occurs between the hydrophobic blocks on the copolymer chains. This effect is believed to allow HMPAMs to mimic a larger molar mass homopolymer solution, because the strong physical associations between the polymer strands create a more robust network, resulting in more resistance to the migration of large DNA molecules, and hence longer average sequencing read lengths. This also explains the diminishing returns we observe in DNA sequencing performance of the copolymer in comparison to the homopolymer as the molecular weight increases, because the ability of a polymer solution to sequence DNA does not improve indefinitely with an increase in polymer molar mass.

3.2 Rheological characterization

The ability to reduce the time required for each sample analysis and therefore the overall cost of sequencing DNA is almost as important as increasing the number of bases that can be sequenced per lane in a microfluidic device. Hydrophobic block copolymers typically have higher viscosities than their homopolymer counterparts due to the impact of physical cross-linking[25], which could be a hindrance when using these materials in microfluidic devices. However, these polymer matrices require extremely small amounts of hydrophobe (0.1%) to achieve the desired increase in sequencing length over their homopolymer counterparts, and thus, have very similar channel loading times as LPA polymers with the same molar mass.

As shown in Figure 2b, the average loading time for a 4% 1.4 MDa LPA solution was ~1 minute. For a LPA-co-DHA copolymer solution with the same molar mass, the loading time was increased by only ~15 seconds. This is largely attributed to the small amount of hydrophobe present in the copolymer, as well as the ability of the physical cross-links between the hydrophobic groups to break and re-form when pressure is applied and removed, and the large amount of shear thinning observed with these polymer solutions. Figure 2a shows the pronounced shear thinning typically observed with these sequencing matrices, which occurs when the entangled chains align themselves in the direction of the fluid flow. This phenomenon is observed when the solutions are placed under a large amount of shear[26, 28], such as when the solutions are loaded into the microfluidic channels under high pressure. The combination of these factors results in polymer solutions that provide very high-resolution separations over a short distance, and can be loaded and unloaded from a microfluidic device quickly and easily.

3.3 Mobility measurements correlated with single-molecule DNA imaging

DNA mobility measurements coupled with single-molecule fluorescent DNA imaging techniques were used to investigate the DNA migration mechanisms that might contribute to the observed sequencing results. The electrophoretic mobilities of ssDNA molecules are plotted against DNA fragment size for separations in 4% (w/w) polymer solutions in Figure 3. The slopes of the linear regions of the mobility plots, which indicate when the DNA is primarily electrophoresing *via* unoriented biased reptation[34], were determined by fitting a power-law to the data with a minimum R^2 value of 0.999. The slopes of the 4% 1.4 MDa LPA-co-DHA and LPA polymer solutions were –0.58 and –0.56 respectively, and the slopes of the 4% 2.8 MDa LPA-co-DHA and LPA polymer solutions were –0.62 and –0.61

respectively. This decrease in DNA mobility is likely a result of the increased number entanglements created by the larger molar mass polymers as well as the physical cross-links between the hydrophobic groups. The DNA must push through this robust network of polymer strands, resulting in lower electrophoretic mobilities, and an increase in read lengths due to the greater number of interactions the DNA will have with the sieving matrix over a given distance.

To help confirm these findings, single-molecule DNA imaging was used to observe the predominant migration mechanisms of double-stranded λ -DNA when electrophoresing through the 4% (w/w) 1.4 MDa LPA and LPA-co-DHA polymer solutions. These polymers were selected for comparison because they had the most significant variation in DNA sequencing capability, and would present the greatest opportunity for observing differences in migration behavior. Two of the DNA migration videos utilized in this study can be found in the supplemental information.

λ -DNA is a significantly larger molecule (~50 kbp) than a typical sequencing fragment, which is in the range of 0.1–1 kbp, and is also double-stranded whereas sequencing fragments are single-stranded DNA. However, the flexibility of the respective molecules as they migrate through the polymer matrix allows for an applicable comparison between the two. ssDNA is very flexible, with a persistence length equivalent to approximately 15 bases[35], while the structure of dsDNA makes it much stiffer, with a persistence length equivalent to approximately 150 bases[36]. This order-of-magnitude difference in their respective Kuhn lengths allows for an adequate, if simply qualitative, comparison between the fluorescently labeled dsDNA and a ssDNA sequencing fragment. Single-stranded DNA cannot be observed during electrophoresis because dyes such as YOYO cannot intercalate; and dsDNA molecules that are smaller than the genome of phage λ also cannot be observed.

As would be expected of a highly entangled polymer solution capable of sequencing long contiguous regions of DNA, the primary mechanism observed in both solutions was reptation. Reptation takes place when the polymer chains are highly entangled such that a network of pores is created with average diameters smaller than the radius of gyration of the coiled DNA molecule. In order to pass through this network the DNA must elongate in a snake-like fashion and migrate through the porous structure. The principal observed difference between the 1.4 MDa LPA and LPA-co-DHA solutions is that on average, the λ -DNA tends to remain in its elongated form for a greater period of time in the LPA-co-DHA copolymer system. Spending a greater amount of time in the elongated configuration instead of the coiled form can contribute to both the increased sequencing potential, and the slight decrease in mobility. This is because when a DNA molecule is reptating, it moves more slowly than its coiled counterpart as it interacts with the polymer network; however, because it interacts with the entangled polymer solution to a greater degree, the overall separation ability of the DNA sieving solution is improved. It should be noted that the “inchworm chain migration dynamics” previously observed by Chiesl *et al.* in HMPAM copolymer solutions were not seen here because the concentrations of these sequencing matrices are significantly greater, 4 % (w/w) vs. 0.75 % (w/w), which forces the DNA molecules to reptate through a network of smaller pores[28].

4 Concluding remarks

By modifying an acrylamide-based sequencing matrix with small, randomly incorporated blocks of hydrophobic *N,N*-dihexylacrylamide monomers, we have shown that an increase in average DNA sequencing read length of up to ~10 % can be achieved when compared with LPA homopolymers of equivalent molar mass. When considering the number of sequencing runs that are required to fully analyze a complex mammalian genome, an

increase in read length of this degree can have a very significant impact on both the cost and time required to perform the necessary number of sequencing runs.

The HMPAM copolymer solutions are slightly more viscous than their homopolymer counterparts due to the physical cross-linking between the hydrophobic blocks, but because only ~0.1 mol % hydrophobe is necessary to achieve the improved sequencing capability and large amounts of shear thinning are observed with these sequencing matrices, the times required to load the polymer solutions into a microfluidic chip are nearly identical. The result is a copolymer solution that can consistently achieve microchip-based DNA sequencing read lengths above 550 bases, with the longest read lengths in excess of 600 bases, in a single microfluidic channel. Excellent sequencing capabilities such as these will be essential for both multiplexed genome sequencing devices as well as for single-channel microfluidic chips that will be utilized in medical and forensic analyses.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

Financial support was provided by the NSF through the Northwestern University Nanoscale Science and Engineering Center, grant EEC-0647560, and by the National Institutes of Health, grant 5R01HG003583, *via* Microchip Biotechnologies, Inc. The work was also supported by research grant # 2 R01 HG001970-07 from the National Human Genome Research Institute of the National Institutes of Health. The views expressed in this paper are solely the responsibility of the authors and do not necessarily represent the official views of the National Human Genome Research Institute or the National Institutes of Health.

Abbreviations

HMPAM	hydrophobically modified polyacrylamide
dsDNA	double-stranded DNA
ssDNA	single-stranded DNA
DHA	<i>N,N</i> -dihexylacrylamide
pHEA	poly- <i>N</i> -hydroxyethylacrylamide
CAE	capillary array electrophoresis
LPA	linear polyacrylamide
SDS	sodium dodecyl sulfate
LIF	laser induced fluorescence

References

1. Mathies RA, Huang XC. *Nature*. 1992; 359:167–169.
2. Kheterpal I, Scherer JR, Clark SM, Radhakrishnan A, et al. *Electrophoresis*. 1996; 17:1852–1859. [PubMed: 9034766]
3. Zhou HH, Miller AW, Sosic Z, Buchholz B, et al. *Analytical Chemistry*. 2000; 72:1045–1052. [PubMed: 10739210]
4. Chaisson M, Pevzner P, Tang HX. *Bioinformatics*. 2004; 20:2067–2074. [PubMed: 15059830]
5. Warren RL, Sutton GG, Jones SJM, Holt RA. *Bioinformatics*. 2007; 23:500–501. [PubMed: 17158514]
6. Liu SR, Ren HJ, Gao QF, Roach DJ, et al. *Proceedings of the National Academy of Sciences of the United States of America*. 2000; 97:5369–5374. [PubMed: 10792056]

7. Salas-Solano O, Schmalzing D, Koutny L, Buonocore S, et al. *Analytical Chemistry*. 2000; 72:3129–3137. [PubMed: 10939377]
8. Shi YN. *Electrophoresis*. 2006; 27:3703–3711. [PubMed: 16960837]
9. Waters LC, Jacobson SC, Kroutchinina N, Khandurina J, et al. *Analytical Chemistry*. 1998; 70:158–162. [PubMed: 9463271]
10. Blazej RG, Kumaresan P, Mathies RA. *Proceedings of the National Academy of Sciences of the United States of America*. 2006; 103:7240–7245. [PubMed: 16648246]
11. Toriello NM, Liu CN, Blazej RG, Thaitrong N, Mathies RA. *Analytical Chemistry*. 2007; 79:8549–8556. [PubMed: 17929900]
12. Easley CJ, Karlinsey JM, Bienvenue JM, Legendre LA, et al. *Proceedings of the National Academy of Sciences of the United States of America*. 2006; 103:19272–19277. [PubMed: 17159153]
13. Woolley AT, Hadley D, Landre P, deMello AJ, et al. *Analytical Chemistry*. 1996; 68:4081–4086. [PubMed: 8946790]
14. Fredlake CP, Hert DG, Kan CW, Chiesl TN, Root BE, Forster RE, Barron AE. *Proceedings of the National Academy of Sciences of the United States of America*. 2008; 105:476–481. [PubMed: 18184818]
15. Paegel BM, Emrich CA, Weyemayer GJ, Scherer JR, Mathies RA. *Proceedings of the National Academy of Sciences of the United States of America*. 2002; 99:574–579. [PubMed: 11792836]
16. Ruizmartinez MC, Berka J, Belenkii A, Foret F, et al. *Analytical Chemistry*. 1993; 65:2851–2858. [PubMed: 8250265]
17. Buchholz BA, Doherty EAS, Albarghouthi MN, Bogdan FM, et al. *Analytical Chemistry*. 2001; 73:157–164. [PubMed: 11199960]
18. Salas-Solano O, Carrilho E, Kotler L, Miller AW, et al. *Analytical Chemistry*. 1998; 70:3996–4003. [PubMed: 9784744]
19. Bashkin J, Marsh M, Barker D, Johnston R. *Applied and Theoretical Electrophoresis*. 1996; 6:23–28. [PubMed: 9072077]
20. Chang HT, Yeung ES. *Journal of Chromatography B-Biomedical Applications*. 1995; 669:113–123.
21. Wu CH, Quesada MA, Schneider DK, Farinato R, et al. *Electrophoresis*. 1996; 17:1103–1109. [PubMed: 8832178]
22. Daoud M, Cotton JP, Farnoux B, Jannink G, et al. *Macromolecules*. 1975; 8:804–818.
23. Heo Y, Larson RG. *Journal of Rheology*. 2005; 49:1117–1128.
24. Raspaud E, Lairez D, Adam M. *Macromolecules*. 1995; 28:927–933.
25. Volpert E, Selb J, Candau F. *Macromolecules*. 1996; 29:1452–1463.
26. Volpert E, Selb J, Candau F. *Polymer*. 1998; 39:1025–1033.
27. Chiesl TN, Shi W, Barron AE. *Analytical Chemistry*. 2005; 77:772–779. [PubMed: 15679343]
28. Chiesl TN, Putz KW, Babu M, Mathias P, et al. *Analytical Chemistry*. 2006; 78:4409–4415. [PubMed: 16808448]
29. McCormick CL, Nonaka T, Johnson CB. *Polymer*. 1988; 29:731–739.
30. Branham KD, Davis DL, Middleton JC, McCormick CL. *Polymer*. 1994; 35:4429–4436.
31. Albarghouthi MN, Buchholz BA, Huiberts PJ, Stein TM, Barron AE. *Electrophoresis*. 2002; 23:1429–1440. [PubMed: 12116153]
32. Albarghouthi MN, Stein TM, Barron AE. *Electrophoresis*. 2003; 24:1166–1175. [PubMed: 12707908]
33. Chiesl TN, Forster RE, Root BE, Larkin M, Barron AE. *Analytical Chemistry*. 2007; 79:7740–7747. [PubMed: 17874850]
34. Slater GW, Noolandi J. *Biopolymers*. 1986; 25:431–454.
35. Tinland B, Pernodet N, Weill G. *Electrophoresis*. 1996; 17:1046–1051. [PubMed: 8832170]
36. Viovy JL. *Rev Mod Phys*. 2000; 72:813–872.

Figure 1. Electropherogram of an M13 ssDNA sequencing standard where 606 bases were successfully sequenced on a 7.5-cm effective length glass microfluidic chip using a 4% (w/w) 7.3 MDa LPA-co-DHA copolymer. (Experimental conditions, 50°C, 187 V/cm separation voltage, results at 98.5% accuracy.)

Figure 2.
a) Representative viscosity data vs. shear rate for the sequencing matrices utilized in this study. b) Comparison of the total loading times obtained on an 8-cm glass microfluidic chip using 200 psi of pressure.

Figure 3. Mobility data obtained with a 25-bp ssDNA ET ladder comparing LPA-co-DHA copolymers and LPA homopolymers of matched molar mass. (Experimental conditions identical to those used in Figure 1.)

Table 1

Properties of the acrylamide-based polymers and copolymers utilized in this microfluidic chip DNA sequencing study

Polymer	Hydrophobe Concentration (mol%)	M _w (MDa)	R _g (nm)	PDI
LPA	0	1.5	58	1.7
	0	2.8	79	1.7
LPA-co-DHA	0.1	1.4	52	1.6
	0.1	2.8	63	2.0
	0.1	7.3	77	1.4
pHEA	0	3.7	76	1.3

Table 2

ssDNA sequencing results obtained with LPA-co-DHA copolymers and LPA homopolymers of matched molar mass

Sequencing Polymer	High	Low	Average
~1.4 MDa LPA-co-DHA, ~0.1 mol% DHA			
2%	40	22	31 ± 13
3%	426	309	368 ± 83
4%	568	535	554 ± 16
~2.8 MDa LPA-co-DHA, ~0.1 mol% DHA			
2%	414	287	351 ± 90
3%	493	429	461 ± 45
4%	576	533	561 ± 20
~7.3 MDa LPA-co-DHA, ~0.1 mol% DHA			
2%	407	319	363 ± 62
3%	508	456	482 ± 37
4%	606	568	583 ± 19
~1.4 MDa LPA			
4%	524	495	508 ± 12
~2.8 MDa LPA			
4%	560	529	541 ± 15

^aExperimental conditions, 7.5-cm effective length glass microfluidic chip, 50°C, 187 V/cm separation voltage, n=4 for 4% (w/w) solutions, n=2 for 2 and 3% (w/w) solutions, results at 98.5% accuracy.