Published in final edited form as:

Angew Chem Int Ed Engl. 2011 March 7; 50(11): 2601–2605. doi:10.1002/anie.201006134.

Stabilization of Virus-Like Particles with Poly(2-oxazoline)s**

Dr. Florian Manzenrieder,

Department of Chemistry and The Skaggs Institute for Chemical Biology, The Scripps Research Institute, 10550 North Torrey Pines Road, La Jolla, CA 92037 (USA), Fax: (+) 1-858-784-8850, Homepage: <http://www.scripps.edu/chem/finn/>

Dr. Robert Luxenhofer,

Professur für Makromolekulare Chemie, Department Chemie, Technische Universität Dresden, Zellescher Weg 19, 01069 Dresden (Germany)

Dr. Marco Retzlaff,

Department of Biology and BioX Program, Stanford University, 318 Campus Drive, Stanford, CA 94305 (USA)

Prof. Rainer Jordan, and

Professur für Makromolekulare Chemie, Department Chemie, Technische Universität Dresden, Zellescher Weg 19, 01069 Dresden (Germany)

Prof. M.G. Finn

Department of Chemistry and The Skaggs Institute for Chemical Biology, The Scripps Research Institute, 10550 North Torrey Pines Road, La Jolla, CA 92037 (USA), Fax: (+) 1-858-784-8850, mgfinn@scripps.edu, Homepage: <http://www.scripps.edu/chem/finn/>

Since the introduction of virus like particles (VLPs), as nanoscale building blocks,^[1] they have become a favored material to fill the gap between supramolecular chemistry and microfabricated systems for medicine, materials science, and biotechnology. One great advantage of VLPs is their precisely defined structures, forming capsules for the packaging of proteins, catalysts, small molecules and other entities,^[2] as well as for the display of functional molecules on their outer surfaces.^[3] The stabilities of chemically modified particles are often approximately the same as the underivatized scaffolds, but in some cases stability is decreased.^[4]

Viruses and virus-like particles are often more resistant to denaturation and proteolytic cleavage than other proteins. Additional stability is sometimes accomplished in nature by the formation of covalent connections between individual capsid subunits.^[5] Certain mimics of this strategy have proven successful,^[4d] but others have not.^[4c, 4e] We describe here an alternative approach in which a capsid surface is covered by polymer chains to which multiple connections are made, thereby crosslinking protein cage subunits. Polymers have most often been attached at one end to viruses and virus-like particles for the purpose of extending *in vivo* circulation lifetime, diminishing nonspecific adsorption, or passivating the immune response (Figure 1a).^[4b, 6] Recent attention has been paid to the entrainment or

**This work was supported by the NIH (CA112075, RR021886), the Skaggs Institute for Chemical Biology, the W.M. Keck Foundation, the International Graduate School of Science and Engineering and the CompInt (TU Munchen), the Postdoc-Programme of the German Academic Exchange Service (DAAD) (fellowship for F.M.), the King Abdullah University of Science and Technology (KAUST Award No. KUK-F1-029-32, partial salary support for R.L.), and the Deutsche Forschungsgemeinschaft (grant to M.R.). We thank Dr. Malcolm Wood for assistance with TEM images and Prof. H. Kitagishi, Dr. S.D. Brown, Mr. V. Hong and Dr. J.-K. Rhee for helpful discussions.

Correspondence to: M.G. Finn.

Supporting information for this article is available on the WWW under <http://www.angewandte.org> or from the author.

growth of polymers inside protein nanoparticles (Figure 1b),^[4h, 7] and the polymerization of shells around nanoparticles for the purpose of materials synthesis (Figure 1c).^[8] We describe here the first example of attachment of polymer chains to protein cages by discrete covalent contacts at multiple points (Figure 1d), similar to the stabilization of liposomes by a polymer net.^[9] An elegant report by Douglas and coworkers describes the construction of anchored crosslinked polymeric materials inside such a particle.^[10]

Poly(2-oxazoline)s have advantageous properties of versatile controlled syntheses by means of living cationic polymerization, aqueous-phase solubility, and chemical stability that make them attractive for a variety of biomedical and materials applications.^[11] Several years ago we pioneered their derivatization with copper-catalyzed azide-alkyne cycloaddition (CuAAC) click chemistry,^[12] for which they are very well suited.^[13] By incorporating several “clickable” functional groups in the polymer chain, we hoped that virus-based hybrid structures could be constructed by crosslinking capsid coat proteins with POx chains.

For the protein component we chose the icosahedral virus-like particle (VLP) formed from 180 copies of the coat protein of bacteriophage Q β expressed recombinantly in *E. coli*.^[14] The 132 amino acid subunit forms a noncovalently interlocked dimer; each subunit has four exposed amino groups on its outer surface that are accessible for covalent modification. The particle is further stabilized by intra- and inter-subunit disulfide bonds located at the five- and sixfold axes of symmetry, respectively.^[4d] For the experiments described here, the standard Q β VLP was derivatized with azido-*N*-hydroxysuccinimide ester reagent **1** at a concentration previously observed to acylate almost all of the 720 amino groups available on the exterior surface of the capsid (Figure 2a).^[15]

A series of complementary POx polymers was designed to allow comparison of single- and multiple-point attachment methods (Figure 2). The monomers 2-methyl-2-oxazoline (MeOx) and 2-ethyl-2-oxazoline (EtOx) were used along with 2-(pent-4-ynyl)-2-oxazoline (PynOx) to provide alkyne linkage points on a hydrophilic polymer.^[13a] Propargyl-MeOx₆₀ (**P1**) and propargyl-EtOx₆₀ (**P2**) were prepared with a single alkyne at the terminus, whereas P(EtOx₂₀-PynOx_{2.5}) (**P3**) and P(MeOx₄₅-PynOx₅) (**P4**) incorporated alkynes randomly in approximately 10% of the polymer pendant groups. All polymers carried a terminal amine moiety to allow for additional modification with a functional molecule such as a fluorescent dye or targeting moiety. As expected for cationic ring opening polymerization,^[16] the polymers were well-defined with low dispersities ($M_w/M_n = 1.25$). All polymers were fully characterized by ¹H NMR, GPC and MALDI-TOF mass spectrometry (Supporting Information).

Using a fluorogenic coumarin azide,^[17] we optimized the conditions for CuAAC bioconjugation to the polymeric alkyne POx using accelerating ligand **3**, as described in Supporting Information. It was necessary to increase the concentrations of Cu and ligand fivefold over that normally used for bioconjugation^[12c] to achieve maximal rates, perhaps because of competitive binding of Cu ions by the POx chains. End-labeled **P5** was also prepared to quantify polymer attachment to Q β particles by virtue of fluorescein UV-visible absorption, but the dye was found to induce particle aggregation (Supporting Information).

Size-exclusion chromatography (SEC) analysis showed a progressive decrease in elution volume for the Q β -**P4** particles with the use of increasing concentrations of **P4** in the CuAAC reaction (Figure 3a), indicating a gradual increase in hydrodynamic radii of polymer-coated capsids by virtue of the attachment of greater numbers of polymer chains. By this measure, maximum polymer loading was achieved in reactions using between 400 and 800 equivalents of POx per particle. This was corroborated by dynamic light scattering (DLS), showing a similar increase of the hydrodynamic diameter, to a maximum of

approximately 38 nm, with increasing concentration of the POx reagent in the attachment reaction (Figure 3b). This value represents the addition of a 5 nm thick polymer shell to the particle surface, since native Q β has a diameter of approximately 27 nm. Similar data were obtained for Q β -**P1**, Q β -**P2**, and Q β -**P3** conjugates (Table 1 and Supporting Information), showing that particle size can be controlled by the nature and amount of polymers grafted to the surface by click conjugation. The polymer-coated nanoparticles also appeared as well-formed icosahedra by transmission electron microscopy (TEM), as shown in Figure 3d-i and Supporting Information.

The number of attached POx chains in each case was determined by UV-visible spectroscopy, taking advantage of the differential absorbance of VLP and polymer at 258 and 220 nm, respectively (Table 1 and Supporting Information). Denaturing gel electrophoresis showed bands corresponding to coat proteins conjugated to zero, one, two, three, and four POx chains (Figure 3c), with a distribution consistent with the total number of POx molecules attached per capsid measured by the UV-visible absorbance assay.

Of the random copolymers, **P3** contained approximately 2.5 alkyne moieties per polymer chain whereas **P4** had 5 reactive groups. In each case, the number of alkyne groups presented by the attached chains ($298 \times 2.5 = 745$ for **P3**, and $144 \times 5 = 720$ for **P4**) are in good agreement with the total number of azides presented on the capsid surface (720). Therefore, a highly efficient click reaction cascade apparently occurs, in which the formation of an initial triazole is followed by the rapid intramolecular CuAAC reaction of the remaining alkynes on the polymer chain with the azides on the scaffold to which it is attached. This is expected since the overall particle concentration is low, and therefore a large increase in local azide/alkyne concentration occurs upon POx attachment.

Very few azide and alkyne groups should therefore remain on the Q β conjugates of **P3** and **P4**. Indeed, subsequent CuAAC reaction of the Q β -**P4**₁₄₄ adduct with an excess of fluorescent azide (BODIPY-N₃) or alkyne (Alexa568 alkyne) gave rise to no attachment of the former and very little (< 3% of the possible 700-720 azides) of the latter. Therefore, either all of the POx alkynes were reacted or were inaccessible even to small molecules, while a small number of unreacted azides remained on the particle surface or within the capsid. SDS-PAGE analysis of denatured particles supported these findings (Figure 3c). While the discrete 14-kDa subunit was observed for the VLP and its azide derivative **2**, no bands were observable for the Q β -**P3**₂₉₈ and Q β -**P4**₁₄₄ conjugates. This is consistent with extensive protein-polymer crosslinking, essentially converting each 180-subunit particle into a single hyperbranched core-shell molecule that cannot enter the electrophoresis gel.

The telechelic polymers **P1** and **P2** provided significantly different results. A greater number of the **P1** chains were grafted under identical CuAAC conditions (244 vs. 146 per particle). Although both polymers are of similar length and hydration properties,^[18] the larger hydrodynamic diameter of the Q β -**P1**₂₄₄ conjugate (Table 1) is consistent with its higher grafting density (requiring more radial extension of the POx chains) and a stronger expected interaction of **P2** with the Q β surface due to the amphiphilic character of PEtOx (**P2**).^[19]

To determine the effects of the chemical modifications on the stability of secondary structure elements of the coat proteins, we performed far-UV circular dichroism (CD) studies. A scan of underivatized Q β particles at 20 °C (Figure 4a, black line) shows a strong CD signal at 218 nm, characteristic of proteins rich in β -sheet structures.^[20] At 100 °C, all secondary structure information was lost for the underivatized VLP (Figure 4a, gray line) due to thermally induced unfolding and precipitation of the coat protein. The thermal stability of the particles was thereby assessed by following the changes in the CD signal at 218 nm over a temperature gradient (Figure 4b). Unfolding occurred within a small

temperature range, indicating a fast, cooperative-like process (Figure 4b). Denaturation of the VLP was irreversible, as the cooling of denatured samples did not result in the reconstitution of secondary structure elements (Figure 4b). The thermal transition experiment was used to calculate the melting temperature ($T_{M,app}$) for each modified VLP (Figure 4b,d,e, and Supporting Information Figure S10), with the underivatized VLP showing a high value (85 °C) expected for such a robust particle.

The importance of the characteristic inter-subunit disulfide linkages^[4d] of Q β was demonstrated by disulfide reduction and quenching of the resulting free cysteines by carboxymethylation. The resulting particles (Figure 4e, “WT reduced”) were significantly less resistant to heating, showing a melting temperature of 61 °C, similar to those of related bacteriophages without stabilizing disulfide bonds (MS2, 58-61 °C; reduced PP7 virus, approx. 65 °C).^[4d, 21] Interestingly, acetylation of surface lysines of particles containing intact disulfide bridges (Q β azide **2**) also decreased the melting temperature (to 73 °C; Figure 4e and Supporting Information).

“POxylation” of the particles markedly enhanced their thermal stability, with $T_{M,app}$ values increasing to well above that of the wild-type VLP (Figure 4e), as judged by the persistence of the native protein fold at high temperatures. Enhanced resistance to thermal denaturation of secondary structural elements was observed for the attachment of both end-functionalized (**P1**, **P2**) and multiply-functionalized (**P4**, and to a lesser extent, **P3**) particles (Figure 4c-e). Because we could not carry out CD measurements at temperatures higher than 110 °C, the Boltzmann fitting of these curves gave lower limits of the $T_{M,app}$ values for two cases that retained strong CD signals at 218 nm to the maximum temperature (Q β -**P2**₁₄₆ and Q β -**P4**₁₄₄). Notably, no protein precipitation was observed in the POx-functionalized samples after heating.

Information about tertiary and quaternary structure was provided by electron microscopy after heat treatment. Thermal denaturation at 90 °C of the Q β -WT and Q β -azide (**2**) particles as indicated by CD (Figure 4a,b) was accompanied by the appearance of large irregular assemblies in TEM images (Figure 4f, Supporting Information Figure S6), consistent with loss of capsid integrity. The Q β -**P1**₂₄₄ and Q β -**P2**₁₄₆ conjugates appeared by CD spectroscopy to retain significant secondary structure at 90 °C (Figure 4c,d), but TEM revealed the particles to be disassembled into wormlike aggregates and spherical micelles, respectively (Figure S6). In contrast, the crosslinked Q β -**P3**₂₉₈ and Q β -**P4**₁₄₄ particles remained intact upon heating at 90 °C and 100 °C, respectively (Figures 4f and S7), demonstrating overall structural stability under extreme conditions. These data support the expectation that the noncovalent subunit-subunit interaction is the “weak link” in these particles, since heat-induced particle disassembly can occur without loss of the coat protein fold, as long as a telechelic POx polymer is attached to stabilize the latter (**P1** and **P2** adducts). Multiple-point polymer attachment and crosslinking is apparently necessary to preserve the packing of these proteins with each other to make the particle stable at elevated temperatures.

Poly(2-oxazoline)s are shown here to be compatible with Q β VLP ligation in two different morphologies, giving rise either to end-attached polymer-decorated particles or to fully crosslinked shell structures. The latter are remarkably thermally stable, surviving temperatures in excess of 100 °C with little apparent loss of integrity. The CuAAC click reaction is efficient in joining densely-packed azide and alkyne groups to each other, as we have observed in the context of adhesive materials.^[22] The size of VLP-polymer constructs can be controlled by changing polymer chain length and attachment density. The ease, versatility, and functional group tolerance of the synthesis of poly(2-oxazoline) materials^[23]

and their click chemistry attachment to monodisperse VLP scaffolds make this type of system of interest for both materials development and biological application.

Experimental Section

Complete experimental details, including the preparation and characterization of VLPs, polymers, and conjugates, are available in Supporting Information.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

References

- (a) Douglas T, Young MJ. *Nature*. 1998; 393:152.(b) Whaley SR, English dS, Hu EL, Barbara PF, Belcher AM. *Nature*. 2000; 405:665. [PubMed: 10864319] (c) Wang Q, Lin T, Tang L, Johnson JE, Finn MG. *Angew Chem Int Ed*. 2002; 41:459.
- (a) Uchida M, Klem MT, Allen M, Suci P, Flenniken M, Gillitzer E, Varpness Z, Liepold LO, Young M, Douglas T. *Adv Mater*. 2007; 19:1025.(b) Ueno T, Suzuki M, Goto T, Matsumoto T, Nagayama K, Watanabe Y. *Angew Chem Int Ed*. 2004; 43:2527.(c) Varpness Z, Peters JW, Young M, Douglas T. *Nano Lett*. 2005; 5:2306. [PubMed: 16277473] (d) Comellas-Aragones M, Engelkamp H, Claessen VI, Sommerdijk NAJM, Rowan AE, Christainen PCM, Maan JC, Verduin BJM, Cornelissen JJLM, Nolte RJM. *Nat Nanotech*. 2007; 2:635.(e) Miller RA, Preseley AD, Francis MB. *J Am Chem Soc*. 2007; 129:3104. [PubMed: 17319656]
- (a) Destito G, Schneemann A, Manchester M. *Curr Top Microbiol Immunol*. 2009; 327:95. [PubMed: 19198572] (b) Kickhoefer VA, Han MM, Raval-Fernandes S, Poderycki MJ, Moniz RJ, Vaccari D, Silvestry M, Stewart PL, Kelly KA, Rome LH. *ACS Nano*. 2009; 3:27. [PubMed: 19206245] (c) Koudelka KJ, Destito G, Plummer EM, Trauger SA, Siuzdak G, Manchester M. *PLoS Path*. 2009; 5:e1000417.(d) Manolova V, Flace A, Bauer M, Schwarz K, Saudan P, Bachmann MF. *Eur J Immunol*. 2008; 38:404.(e) Kurata N, Shishido T, Muraoka M, Tanaka T, Ogino C, Fukuda H, Kondo A. *J Biochem*. 2008; 144:701. [PubMed: 18838435]
- (a) Wang Q, Kaltgrad E, Lin T, Johnson JE, Finn MG. *Chem Biol*. 2002; 9:805. [PubMed: 12144924] (b) Raja KS, Wang Q, Gonzalez MJ, Manchester M, Johnson JE, Finn MG. *Biomacromolecules*. 2003; 4:472. [PubMed: 12741758] (c) Meunier S, Strable E, Finn MG. *Chemistry & Biology*. 2004; 11:319. [PubMed: 15123261] (d) Ashcroft AE, Lago H, Macedo JMB, Horn WT, Stonehouse NJ, Stockley PG. *J Nanosci Nanotechnol*. 2005; 5:2034. [PubMed: 16430137] (e) Caldeira JC, Peabody DS. *J Nanobiotechnology*. 2007; 510.1186/1477(f) Zochowska M, Paca A, Schoehn G, Andrieu J-P, Chroboczek J, Dublet B, Szolajska E. *PLoS One*. 2009; 4:e5569. [PubMed: 19440379] (g) Esfandiary R, Kickhoefer VA, Rome LH, Joshi SB, Middaugh CR. *J Pharm Sci*. 2009; 98:1376. [PubMed: 18683860] (h) Comellas-Aragones M, De la Escosura A, Dirks AJ, Van der Ham A, Fuste-Cune A, Cornelissen JJLM, Nolte RJM. *Biomacromolecules*. 2009; 10:3141. [PubMed: 19839603]
- Wikoff WR, Liljas L, Duda RL, Tsuruta H, Hendrix RW, Johnson JE. *Science*. 2000; 289:2129. [PubMed: 11000116]
- (a) Smith AE, O'Riordan CR, Francis GE, Parkes V, Delgado C. *PCT Int Appl*. 1998(b) Green NK, Herbert CW, Hale SJ, Mautner V, Harkins R, Hermiston T, Ulbrich K, Fisher KD, Seymour LW. *Gene Therapy*. 2004; 11:1256. [PubMed: 15215884] (c) Sen Gupta S, Raja KS, Kaltgrad E, Strable E, Finn MG. *Chem Commun*. 2005:4315.(d) Steinmetz NF, Manchester M. *Biomacromolecules*. 2009; 10:784. [PubMed: 19281149]
- (a) Hu Y, Zandi R, Anavitarte A, Knobler CM, Gelbart WM. *Biophys J*. 2008; 94:1428. [PubMed: 17981893] (b) Minten IJ, Ma YJ, Hempenius MA, Vancso GJ, Nolte RJM, Cornelissen JJLM. *Org Biomol Chem*. 2009; 7:4685. [PubMed: 19865705]
- (a) Shenton W, Douglas T, Young M, Stubbs G, Mann S. *Adv Mater*. 1999; 11:253.(b) Dickerson MB, Naik RR, Sarosi PM, Agarwal G, Stone MO, Sandhage KH. *J Nanosci Nanotechnol*. 2005; 5:63. [PubMed: 15762162] (c) Niu Z, Bruckman M, Li S-W, Lee LA, Lee B, Pingali SV, Thiyagarajan P, Wang Q. *Langmuir*. 2007; 23:6719. [PubMed: 17474763]

9. Aliev KV, Ringsdorf H, Schlarb B, Leister KH. *Macromol Rapid Commun.* 1984; 5:345.
10. (a) Abedin MJ, Liepold L, Suci P, Young M, Douglas T. *J Am Chem Soc.* 2009; 131:4346. [PubMed: 19317506] (b) Lucon J, Abedin MJ, Uchida M, Liepold L, Young M, Douglas T. *Chem Commun.* 2010; 46:264.
11. (a) Hoogenboom R. *Angew Chem Int Ed.* 2009; 48:7978.(b) Luxenhofer R, Schulz A, Roques C, Shu L, Bronich TK, Batrakova EV, Jordan R, Kabanov AV. *Biomaterials.* 2010; 31:4972. [PubMed: 20346493]
12. (a) Tornøe CW, Christensen C, Meldal M. *J Org Chem.* 2002; 67:3057. [PubMed: 11975567] (b) Rostovtsev VV, Green LG, Fokin VV, Sharpless KB. *Angew Chem Int Ed.* 2002; 41:2596.(c) Hong V, Presolski SI, Ma C, Finn MG. *Angew Chem Int Ed.* 2009; 48:9879.
13. (a) Luxenhofer R, Jordan R. *Macromolecules.* 2006; 39:3509.(b) Fijten MWM, Haensch C, van Lankvelt BM, Hoogenboom R, Schubert US. *Macromol Chem Phys.* 2008; 209:1887.
14. (a) Golmohammadi R, Fridborg K, Bundule M, Valegard K, Liljas L. *Structure.* 1996; 4:543. [PubMed: 8736553] (b) Kozlovska TM, Cielens I, Dreilinnä D, Dislers A, Baumanis V, Ose V, Pumpens P. *Gene.* 1993; 137:133. [PubMed: 7506687]
15. (a) Hong V, Udit AK, Evans RA, Finn MG. *ChemBioChem.* 2008; 9:1481. [PubMed: 18504727] (b) Strable E, Prasuhn DE Jr, Udit AK, Brown S, Link AJ, Ngo JT, Lander G, Quispe J, Potter CS, Carragher B, Tirrell DA, Finn MG. *Bioconjugate Chem.* 2008; 19:866.(c) Prasuhn DE Jr, Singh P, Strable E, Brown S, Manchester M, Finn MG. *J Am Chem Soc.* 2008; 130:1328. [PubMed: 18177041]
16. Stepto RFT. *Polymer International.* 2009; 59:23.
17. Sivakumar K, Xie F, Cash BM, Long S, Barnhill HN, Wang Q. *Org Lett.* 2004; 6:4603. [PubMed: 15548086]
18. Rehfeldt F, Tanaka M, Pagnoni L, Jordan L. *Langmuir.* 2002; 18:4908.
19. Foreman MB, Coffman JP, Murcia MJ, Cesana S, Jordan R, Smith GS, Naumann CA. *Langmuir.* 2003; 19:326.
20. (a) Ausar SF, Foubert TR, Hudson MH, Vedvick TS, Middaugh CR. *J Biol Chem.* 2006; 281:19478. [PubMed: 16675449] (b) Kissmann J, Ausar SF, Foubert TR, Brock J, Switzer MH, Detzi EJ, Vedvick TS, Middaugh CR. *J Pharm Sci.* 2008; 97:4208. [PubMed: 18300304]
21. Kovacs EW, Hooker JM, Romanini DW, Holder PG, Berry KE, Francis MB. *Bioconjugate Chem.* 2007; 18:1140.
22. (a) Diaz DD, Punna S, Holzer P, McPherson AK, Sharpless KB, Fokin VV, Finn MG. *J Polym Sci Pol Chem.* 2004; 42:4392.(b) Le Baut N, Diaz DD, Punna S, Finn MG, Brown H. *Polymer.* 2007; 48:239.
23. (a) Cesana S, Auernheimer J, Jordan R, Kessler H, Nuyken O. *Macromol Chem Phys.* 2006; 207:183.(b) Luxenhofer R, Bezen M, Jordan R. *Macromol Rapid Commun.* 2008; 29:1509.(c) Taubmann C, Luxenhofer R, Cesana S, Jordan R. *Macromol Biosci.* 2005; 5:603. [PubMed: 15997438]

Figure 1.
Various ways in which polymers have been combined with protein nanoparticles.

Figure 2.

(a) Preparation of POx-coated Q β virus-like particles. Two general architectures of core-shell nanoparticles are produced, deriving from polymers with a single attachment point or from polymers with multiple attachment points. (b) Telechelic (**P1**, **P2**) and random copolymer (**P3-P5**) poly(2-oxazoline)s with terminal and pendant alkyne groups, respectively.

Figure 3.

(a) Retention volume shift in SEC of the products derived from increasing amounts of **P4** in the coating reaction (25 to 1600 equiv. with respect to Q β particles). (b) Hydrodynamic diameter increase of the Q β -POx (**P4**) conjugates, as measured by dynamic light scattering. (c) Denaturing polyacrylamide gel electrophoresis analysis of purified conjugates. Lanes: 1 = starting Q β VLPs, 2 = Q β -N₃ (**2**), 3 = Q β -**P3**₂₉₈, 4 = Q β -**P4**₁₄₄, 5 = Q β -**P1**₂₄₄, 6 = Q β -**P2**₁₄₆. (d-i) TEM images (magnification 245000 $\times$) of VLPs; scale bars = 100 nm: (d) wild-type Q β , (e) Q β azide **2**, (f) Q β -**P1**₂₄₄, (g) Q β -**P2**₁₄₆, (h) Q β -**P3**₂₉₈, (i) Q β -**P4**₁₄₄.

Figure 4. Stability assay of Q β -POx conjugates. (a-d) far-UV CD spectroscopy: (a) underivatized Q β virus-like particles at 20 °C (black) and after denaturation by heating at 100 °C (gray). (b) A cycle of gradual heating (O) and cooling (Δ) showing irreversible unfolding of the Q β VLP protein, resulting in a loss of CD signal at 218 nm. A Boltzmann equation (solid line) was used to calculate the apparent melting temperature (see Supporting Information for details). (c and d) Analogous to A and B for Q β -P2 $_{146}$ particles. (e) Calculated apparent melting temperatures ($T_{M,app}$) for each modified capsid measured and calculated as in B. (f) TEM images (magnification 92000 $\times$, scale bars = 200 nm) of VLPs heated to 90 °C for 10 min, intact Q β -P4 $_{144}$ (top) and disrupted Q β -N3 (2) (bottom).

Table 1Summary of the analysis of the Q β -POx-core-shell particles.

Construct	diameter (nm) ^a	Δ SEC (mL) ^b	alkynes/POx	chains/particle ^c
Q β -P1 ₂₄₄	43.6	2.1	1	244
Q β -P2 ₁₄₆	35.6	1.7	1	146
Q β -P3 ₂₉₈	35.8	1.0	2.5	298
Q β -P4 ₁₄₄	37.6	1.4	5	144

(a) measured by dynamic light scattering;

(b) change in retention volume on Superose 6 column relative to that of the starting VLP;

(c) average values, calculated from UV-visible spectroscopy; experimental error = 10%.