Published in final edited form as:

Mech Mater. 2012 November ; 54: 70–83. doi:10.1016/j.mechmat.2012.07.004.

A symmetry invariant formulation of the relationship between the elasticity tensor and the fabric tensor

Maarten Moesen^{a,c,*}, Luis Cardoso^b, and Stephen C. Cowin^b

^aDepartment of Metallurgy and Materials Engineering, Katholieke Universiteit Leuven, Kasteelpark Arenberg 44, PB 2450, 3001 Leuven, Belgium

^bThe New York Center for Biomedical Engineering, The Departments of Biomedical & Mechanical Engineering, The School of Engineering of The City College, and The Graduate School of The City University of New York, NY 10031, USA

^cPrometheus, Division of Skeletal Tissue Engineering, Katholieke Universiteit Leuven, O&N 1, Herestraat 49, PB 813, 3000 Leuven, Belgium

Abstract

The fabric tensor is employed as a quantitative stereological measure of the structural anisotropy in the pore architecture of a porous medium. Earlier work showed that the fabric tensor can be used additionally to the porosity to describe the anisotropy in the elastic constants of the porous medium. This contribution presents a reformulation of the relationship between fabric tensor and anisotropic elastic constants that is approximation free and symmetry-invariant. From specific data on the elastic constants and the fabric, the parameters in the reformulated relationship can be evaluated individually and efficiently using a simplified method that works independent of the material symmetry. The well-behavedness of the parameters and the accuracy of the method was analyzed using the Mori–Tanaka model for aligned ellipsoidal inclusions and using Buckminster Fuller’s octet-truss lattice. Application of the method to a cancellous bone data set revealed that employing the fabric tensor allowed explaining 75–90% of the total variance. An implementation of the proposed methods was made publicly available.

Keywords

Anisotropy; Elastic constants; Fabric tensor; Orthogonal basis; Parameters; Cancellous bone

1. Introduction

In textured materials, the elastic constants depend not only on the elastic constants of the constituent phases, but also on their microstructural arrangement. The influence of the latter increases with increasing stiffness contrast between the phases. Porous materials, for example, can be orders of magnitude less stiff than their matrix material. In addition, the macroscopic material symmetry of a porous material can differ considerably from the microscopic material symmetry of the matrix due to external loads influencing the microstructure during the formation process. For example, it is well known that geological materials have material symmetries associated with the stress state experienced by the material during its formative state. Sedimentary deposits are generally organized by the

direction of gravity at the time of their formation. Manmade composites are generally designed to survive in specific stress states and therefore can generally be considered as having a material symmetry designed for the external loads they will experience. Plant and animal tissue are known to functionally adapt their microstructure to external loads. To be able to describe the influence of microstructure on mechanical properties, it is necessary to introduce some important geometrical determinants of microstructure. The theory in the remainder is particularly developed for porous materials, but may also be applicable to other textured materials (e.g. with large stiffness contrasts).

For porous materials, the most important geometrical determinant is the matrix volume fraction (also called relative density) ϕ_m , which is closely related to the porosity ϕ_p by $\phi_p = 1 - \phi_m$. The volume fraction determines, in relation to the internal deformation mechanisms (Gibson and Ashby, 1997), the order of magnitude of the mechanical properties. It cannot describe the mechanical or structural anisotropy.

The structural anisotropy can be partially quantified by a fabric tensor. The fabric tensor $\mathbf{A}$ is a symmetric, positive definite, second order tensorial measure of the structural arrangement of a porous medium. The eigenvectors of $\mathbf{A}$ are the principal axes of material symmetry of the porous medium. The eigenvalues of $\mathbf{A}$ provide a measure of the distribution of (matrix or porous) volume fraction in the direction of the principal axes of material symmetry. The invariants, properties and determination of the fabric tensor $\mathbf{A}$ are further discussed in Section 2.

Cowin (1985) derived the most general form of the fourth order elasticity tensor $\mathcal{C}$ of a porous medium as a function of the fabric tensor $\mathbf{A}$, the matrix volume fraction ϕ_m and the elastic constants E_m and ν_m of its matrix material, which is assumed to be isotropic. The theory is thus based on the notion that the mechanical anisotropy of the porous medium is due only to the geometry of the microstructure represented by fabric tensor $\mathbf{A}$. In case the fabric tensor has three distinct eigenvalues, the theory predicts orthotropic material symmetry, which is thus the lowest possible symmetry under the given assumptions. If two eigenvalues are equal, the material is transversely isotropic. Three equal eigenvalues result in isotropic material symmetry.

Cowin's work is thus sufficiently general to describe the usual material symmetries of textured materials. Nevertheless, it is possible that transitions between these material symmetries occur over time, e.g. under the influence of different methods of formation and variations in constituent concentrations. Therefore it is desirable for textured materials to have a method of analysis for relating the elastic constants to the fabric measurements that works independently of whether the material symmetry is orthotropy, transverse isotropy or isotropy. The method proposed by Cowin (1985) did not have this desirable feature. The practical applicability of the analysis in Cowin (1985) is also limited by a second issue. The second issue, recently discovered by one of us (Moesen), was that the approximate solution for the orthotropic case, Eq. 12 in Cowin (1985), contained linearly dependent equations. The linear dependency does not invalidate the theory as it was caused by neglecting higher order terms in the correct system described by Eq. 6 in Cowin (1985).

This work resolves these issues by proposing in Section 3 an orthogonal tensor basis $\mathcal{Q}^{(i)}(\mathbf{A})$ ($i = 1 \dots 9$) that is only function of the eigenvalues of the fabric tensor $\mathbf{A}$. The basis permits

the description of the elasticity tensor $\mathcal{C} = \sum_{i=1}^9 p_i \mathcal{Q}^{(i)}$ in terms of nine parameters $p_i(E_m, \nu_m, \phi_m, II_{\mathbf{A}}, III_{\mathbf{A}})$ that are only function of the matrix properties, the volume fraction, and the fabric tensor's invariants. The parameters p_i will be shown to be easily computable. The definition of the basis tensors $\mathcal{Q}^{(i)}$, and hence the physical meaning of parameters p_i , remains

the same regardless of whether the material symmetry is orthotropic, transverse isotropic or isotropic. The method is applied to two analytical models and to a database of cancellous bone in Section 4. The results are discussed in Sections 5 and 6 to address the limitations and possibilities of the proposed method.

2. Fabric tensor

Without loss of generality, the fabric tensor $\mathbf{A}$ is assumed in this work to be in its principal coordinate system, in which it has the representation

$$\mathbf{A} = \begin{bmatrix} A_{11} & 0 & 0 \\ 0 & A_{22} & 0 \\ 0 & 0 & A_{33} \end{bmatrix}. \quad (1)$$

The positive eigenvalues A_{11} , A_{22} , and A_{33} are further assumed to be ordered such that $A_{11} \geq A_{22} \geq A_{33}$. The eigenvalues are related to the tensor invariants $I_{\mathbf{A}}$, $II_{\mathbf{A}}$ and $III_{\mathbf{A}}$ by equations

$$I_{\mathbf{A}} = A_{11} + A_{22} + A_{33} = \text{tr}(\mathbf{A}), \quad (2)$$

$$II_{\mathbf{A}} = A_{11}A_{22} + A_{22}A_{33} + A_{33}A_{11} \quad \text{and} \quad (3)$$

$$III_{\mathbf{A}} = A_{11}A_{22}A_{33} = \det(\mathbf{A}). \quad (4)$$

The fabric tensor is commonly computed from directional data. Directional data can be obtained by using stereographic or image analysis methods (Odgaard, 1997) such as Mean Intercept Length (Whitehouse, 1974), Volume Orientation (VO) (Odgaard et al., 1990), Star Length Distribution (SLD) (Smit et al., 1998), or Intercept Segment Deviation (ISD) (Chiang et al., 2006). The experimental procedure for the fabric measurement of cancellous bone is described by Whitehouse (1974), Harrigan and Mann (1984), Turner and Cowin (1987) and Turner et al. (1990). The work of these authors, and (Odgaard et al., 1997; van Rietbergen et al., 1998; van Rietbergen et al., 1996; Matsuura et al., 2008) others, has shown that the fabric tensor is a good measure of the pore structure anisotropy in cancellous bone tissue (Cowin, 1997).

Other ways of obtaining directional data are by measuring the contact normals between grains in granular materials (Oda et al., 1982), or the fiber orientation in fiber reinforced composites (Advani and Tucker, 1987).

Kanatani (1984) presented a rigorous framework for computing fabric tensors from directional data and orientation distribution functions. Part of this theory was rediscovered in a different context by Advani and Tucker (1987). The theory proposes three useful kinds of fabric tensors. The first kind, called moment tensors, corresponds to the usual notion of a fabric tensor. The moment tensor $N_{i_1 i_2 \dots i_n}$ is defined as the weighted average of the tensorial product of the N orthonormal direction vectors $\mathbf{n}^{(\alpha)}$:

$$N_{i_1 i_2 \dots i_n} = \sum_{\alpha=1}^N \frac{w_{\alpha}}{w_{\text{tot}}} n_{i_1}^{(\alpha)} n_{i_2}^{(\alpha)} \dots n_{i_n}^{(\alpha)}, \quad (5)$$

with weights w_α and total weight $w_{tot} = \sum_{\alpha=1}^N w_\alpha$. Note that this definition is not restricted to second order fabric tensors as it defines a series of moment tensors with order r . The moment tensors with uneven order become zero under the assumption that opposite direction vectors $\mathbf{n}^{(a)}$ and $-\mathbf{n}^{(a)}$ are equivalent. Furthermore, because direction vectors are orthonormal, the trace of a second order moment tensor $N_{ii} = 1$, and any contraction of a higher order tensor lowers the rank, i.e. $N_{ijklmm} = N_{ijkl}$.

The second kind of fabric tensor $F_{i_1 \dots i_r}$ is defined as the tensor that most closely approximates the microstructure's orientation distribution function $f(\mathbf{n})$:

$$f(\mathbf{n}) \approx \frac{1}{4\pi} F_{i_1 \dots i_r} n_{i_1} \dots n_{i_r}. \quad (6)$$

$f(\mathbf{n})$ has the properties that

$$\int f(\mathbf{n}) d\mathbf{n} = 1 \quad \text{and} \quad \int n_{i_1} \dots n_{i_r} f(\mathbf{n}) d\mathbf{n} = N_{i_1 i_2 \dots i_r}, \quad (7)$$

integrating over all directions on the unit sphere. As the number of degrees of freedom increase with increasing tensor order r , higher orders of fabric tensor $F_{i_1 \dots i_r}$ will more closely represent an arbitrary orientation distribution function $f(\mathbf{n})$.

The question: "which information is added with increasing order?" leads us to the third kind of fabric tensor $D_{i_1 \dots i_r}$, which is the most useful for the purposes of this work. $D_{i_1 \dots i_r}$ is defined as the orthogonal decomposition of $F_{i_1 \dots i_r}$ such that

$$f(\mathbf{n}) \approx \frac{1}{4\pi} (D + D_{ij} n_i n_j + D_{ijkl} n_i n_j n_k n_l + \dots). \quad (8)$$

The orthogonality implies that every term in expansion (8) excludes all information contained in lower order terms. Each term thus contains only the additional information provided by the degrees of freedom of that term. The first two terms of the expansion are computed as

$$D = 1, \quad (9)$$

$$D_{ij} = \frac{15}{2} \left(N_{ij} - \frac{1}{3} \delta_{ij} \right), \quad (10)$$

in which δ_{ij} is the Kronecker symbol. It can be verified that invariant $I_D = \sum_{i=1}^3 D_{ii} = 0$. Additionally, if D_{ij} is in its principal coordinate system, it can be shown using the Cayley–Hamilton theorem that each eigenvalue D_{ii} satisfies the equation

$$D_{ii}^3 - III_D D_{ii} = 0, \quad (11)$$

with $i = 1 \dots 3$. This equation allows making substantial simplifications in the theory developed in the following section.

3. Theory

3.1. Matrix and vector notation

Before deriving the actual theory, we introduce two convenient tensor notations. The first notation represents three-dimensional symmetric second and fourth order tensors by six-dimensional vectors and matrices. It is further called matrix notation. The notation is in principle due to Lord Kelvin (Thomson, 1856; Thomson, 1878), but was expressed in contemporary linear algebra notation by Rychlewski (1984) and Mehrabadi and Cowin (1990). To express tensor components in matrix notation, we define an index function ι and a factor function ϕ as follows:

$$\iota(i, j) \rightarrow m : \{(1, 1) \rightarrow 1, (2, 2) \rightarrow 2, (3, 3) \rightarrow 3, (2, 3) \rightarrow 4, (3, 1) \rightarrow 5, (1, 2) \rightarrow 6, (3, 2) \rightarrow 4, (1, 3) \rightarrow 5, (2, 1) \rightarrow 6\}, \quad (12)$$

$$\phi(i, j) = \begin{cases} 1 & i=j, \\ \sqrt{2} & i \neq j. \end{cases} \quad (13)$$

Using these functions, second order tensor A_{ij} is represented by vector A_m as

$$A_m = A_{\iota(i,j)} = \phi(i, j) A_{ij}. \quad (14)$$

Note that matrix notation can be distinguished from tensor notation by the number of indices, if the order of the tensor is known from the context. Likewise, fourth order tensor C_{ijkl} is represented by matrix C_{mn} as

$$C_{mn} = C_{\iota(i,j)\iota(k,l)} = \phi(i, j)\phi(k, l) C_{ijkl}. \quad (15)$$

For example, $A_3 = A_{33}$, $A_4 = \sqrt{2}A_{23}$, $C_{23} = C_{2233}$, $C_{25} = \sqrt{2}C_{2231}$ and $C_{66} = 2C_{1212}$. In this notation all tensors of a certain order are represented similarly. Therefore this notation is more practical than the well-known matrix notation introduced by Voigt (1928), where stress and strain tensors have different coefficients. Additionally, in Voigt's matrix notation for a fourth order tensor representing the elasticity tensor, the matrix components do not constitute a genuine tensor. In contrast, the matrices in Kelvin's notation are on themselves six-dimensional tensors. This leads to the major advantage of Kelvin's matrix notation, which is that certain operations are naturally isomorphic to matrix operations. For example, the double contraction $\boldsymbol{\sigma} = \mathcal{C} : \mathbf{e}$ ($\sigma_{ij} = C_{ijkl} e_{kl}$) can be computed as the matrix-vector product $\sigma_m = C_{mn} e_n$, and the inverse of tensor $\mathcal{C}$ can be computed as a conventional matrix inverse.

The second notation represents the nine components of an orthotropic fourth order tensor in its symmetry coordinate system by a 9-dimensional vector. The components of this vector are determined such that the vector product ($\cdot$) between two orthotropic tensors $\mathcal{A}$ and $\mathcal{B}$, respectively $\mathbf{a}$ and $\mathbf{b}$ in vector notation, is equivalent to the quadruple tensor contraction ($::$):

$$\mathcal{A} : \mathcal{B} = a_{ijkl} b_{ijkl} = a_m b_m = \mathbf{a} \cdot \mathbf{b}. \quad (16)$$

The resulting relations between vector notation, matrix notation and tensor notation are shown in Table 1.

3.2. Original formulation

Eq. (6) in Cowin (1985) expresses the components of the orthogonal elasticity tensor in terms of the fabric tensor's eigenvalues A_{ij} (no sum on i) and nine parameters $a_i(\phi_m, I_A, II_A, III_A)$, $b_i(\phi_m, I_A, II_A, III_A)$ and $c_i(\phi_m, I_A, II_A, III_A)$ with $i = 1 \dots 3$ as follows

$$\begin{bmatrix} C_{1111} \\ C_{2222} \\ C_{3333} \\ C_{2233} \\ C_{1133} \\ C_{1122} \\ C_{2323} \\ C_{3131} \\ C_{1212} \end{bmatrix} = \begin{bmatrix} 1 & 2A_{11} & 2A_{11}^2 & A_{11}^2 & 2A_{11}^3 & A_{11}^4 & 2 & 4A_{11} & 4A_{11}^2 \\ 1 & 2A_{22} & 2A_{22}^2 & A_{22}^2 & 2A_{22}^3 & A_{22}^4 & 2 & 4A_{22} & 4A_{22}^2 \\ 1 & 2A_{33} & 2A_{33}^2 & A_{33}^2 & 2A_{33}^3 & A_{33}^4 & 2 & 4A_{33} & 4A_{33}^2 \\ 1 & A_{22}+A_{33} & A_{22}^2+A_{33}^2 & A_{22}A_{33} & A_{22}A_{33}^2+A_{22}^2A_{33} & A_{22}^2A_{33}^2 & 0 & 0 & 0 \\ 1 & A_{11}+A_{33} & A_{11}^2+A_{33}^2 & A_{11}A_{33} & A_{11}A_{33}^2+A_{11}^2A_{33} & A_{11}^2A_{33}^2 & 0 & 0 & 0 \\ 1 & A_{11}+A_{22} & A_{11}^2+A_{22}^2 & A_{11}A_{22} & A_{11}A_{22}^2+A_{11}^2A_{22} & A_{11}^2A_{22}^2 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 & 0 & 0 & 1 & A_{22}+A_{33} & A_{22}^2+A_{33}^2 \\ 0 & 0 & 0 & 0 & 0 & 0 & 1 & A_{11}+A_{33} & A_{11}^2+A_{33}^2 \\ 0 & 0 & 0 & 0 & 0 & 0 & 1 & A_{11}+A_{22} & A_{11}^2+A_{22}^2 \end{bmatrix} \begin{bmatrix} a_1 \\ a_2 \\ a_3 \\ b_1 \\ b_2 \\ b_3 \\ c_1 \\ c_2 \\ c_3 \end{bmatrix} \quad (17)$$

Two important observations can be made regarding Eq. (17). Firstly, columns 1 and 7 are constant and linearly independent. In particular, these columns define the tensors corresponding to Lamé's constants of an isotropic material, so that parameter a_1 corresponds to λ and parameter c_1 to the shear modulus G . Secondly, the other columns contain no constant term and are only function of the eigenvalues A_{ij} .

Cowin's original work imposed no restriction on fabric tensor A_{ij} . In a special case Cowin (1985) did suggest setting $\text{tr}(\mathbf{A}) = 1$, a restriction that was imposed in most later works. However, from the two observations above the restriction of using only its deviatoric part D_{ij} appears meaningful. Indeed, columns 1 and 7 adequately describe the behavior in case of isotropic symmetry, which in the orthogonal decomposition (Eq. (8)) is represented by the isotropic term (Eq. (9)). Using the deviatoric part D_{ij} therefore makes the other columns reflect only the deviation from the isotropic case. This restriction implies no loss of generality and has several positive consequences, which are elaborated in the following section.

3.3. Continuity at the orthotropy to isotropy transition

In the introduction it was stated that an alternative set of parameters is desired that guarantees continuous mechanical behavior at the transition from one case of structural symmetry to another. The previous section proposed a restriction to the deviatoric part D_{ij} of the fabric tensor (Eq. 9) to deconfound the transition between isotropy and lower symmetry. To see the effect of this, the properties of the eigenvalues D_{ij} (no sum on i) and corresponding invariants are analyzed for the three cases of structural symmetry.

In the principal coordinate system, eigenvalues A_{ij} and D_{ij} are related by Eq. (10) if the fabric tensor A_{ij} replaces N_{ij} in Eq. (10). This equation maintains the equality and ordering relations imposed on the eigenvalues of $\mathbf{A}$ in the line following Eq. (1), thus $D_{11} \geq D_{22} \geq D_{33}$. In case of structural isotropy, all eigenvalues are zero as they are equal and $\text{tr}(\mathbf{D}) = 0$. In case of lower symmetry, the latter equation causes the smallest eigenvalue D_{11} to be negative and the largest eigenvalue D_{33} to be positive due to the ordering relation. Therefore D_{22} determines the sign of invariant $III_{\mathbf{D}}$ as shown in Table 2. Invariant $II_{\mathbf{D}}$ is strictly negative, except when $D_{11} = D_{22} = D_{33} = 0$, in which case $II_{\mathbf{D}} = 0$. Condition $II_{\mathbf{D}} = 0$ thus corresponds to the case of structural isotropy. By means of Eq. (11) it can be shown that the condition $4II_{\mathbf{D}}^3 + 27III_{\mathbf{D}}^2 = 0$ corresponds to the case of structural transversal anisotropy. Interestingly, a result by [p. 831] Kalman and White (2001) implies that because the eigenvalues are real, the term $4II_{\mathbf{D}}^3 + 27III_{\mathbf{D}}^2 \leq 0$.

Returning to the use of D_{ij} in Eq. (17), it is clear that in case of structural isotropy all columns except 1 and 7 become zero. This yields the desired continuity for transitions from lower symmetry to isotropy.

3.4. Continuity at the orthotropy to transversal anisotropy transition

Where continuity at the transition from orthotropy to isotropy is established almost trivially by using D_{ij} , establishing continuity from orthotropy to transversal anisotropy proceeds in two steps.

The first step consists of selecting a suitably ordered basis for the orthotropic and transversal anisotropic case. For this, the linear dependencies between the columns of Eq. (17) were studied as a function of the number of equal eigenvalues. When two eigenvalues are equal, it was found that there are 51 combinations of 5 linearly independent columns. From these we selected combination [1 7 | 2 4 8] as a basis for the transversal anisotropic case, as it minimized the polynomial degree of the eigenvalues. The mark ‘|’ indicates that the basis vectors after the mark correspond to a lower case of symmetry. The nine columns were confirmed to form a basis for the orthotropic case with three distinct eigenvalues. Because the order of the columns affects the final result, a large number of trials were performed. Finally the ordering [1 7 | 2 8 4 | 3 5 6 9] was selected as it provided the simplest set of final equations in terms of largest number of zeros and recurring factors.

The second step consists of a Gram-Schmidt orthogonalization of the selected basis. First the columns in Cowin’s original system (Eq. 17) are converted to vector notation by multiplying rows 4 to 6 by $\sqrt{2}$ and rows 7 to 9 by 2 as indicated in the last column of Table 1. This conversion adds physical (tensorial) meaning to vector products and norms, and therefore vector notation will be used throughout the entire orthogonalization process. The resulting column vectors $\mathbf{a}^{(k)}$ are then reordered as follows to form the basis $\mathbf{B}$:

$$\mathbf{B} = [\mathbf{a}^{(1)} \quad \mathbf{a}^{(7)} \quad \mathbf{a}^{(2)} \quad \mathbf{a}^{(8)} \quad \mathbf{a}^{(4)} \quad \mathbf{a}^{(3)} \quad \mathbf{a}^{(5)} \quad \mathbf{a}^{(6)} \quad \mathbf{a}^{(9)}]. \quad (18)$$

The reordering of these components is accomplished by letting $\mathbf{b}^{(k)}$ represent the k th column of $\mathbf{B}$. The Gram-Schmidt process orthogonalizes every column vector $\mathbf{b}^{(k)}$ relative to the other vectors $\mathbf{b}^{(i)}$ with $i < k$ to obtain a corresponding orthogonalized basis vector $\mathbf{q}^{(k)}$ by subtracting $\mathbf{b}^{(k)}$ ’s projection on all previously orthogonalized basis vectors $\mathbf{q}^{(i)}$ with $i = 1 \dots k - 1$:

$$\mathbf{q}^{(k)} = \mathbf{b}^{(k)} - \sum_{i=1}^{k-1} \frac{\mathbf{b}^{(k)} \cdot \mathbf{q}^{(i)}}{\mathbf{q}^{(i)} \cdot \mathbf{q}^{(i)}} \mathbf{q}^{(i)}. \quad (19)$$

The resulting basis is shown in vector notation in Eqs. (20), (22) and (24)–(27). These equations are the main algebraic result of this work. The squared norms of the basis are given by Eqs. (21), (23) and (28). Invariants $II_{\mathbf{D}}$ and $III_{\mathbf{D}}$ are abbreviated to respectively II and III .

$$[\mathbf{q}^{(1)} \quad \mathbf{q}^{(2)}] = \begin{bmatrix} 1 & \frac{4}{3} \\ 1 & \frac{2\sqrt{2}}{3} \\ 1 & \frac{2\sqrt{2}}{3} \\ \sqrt{2} & -\frac{2\sqrt{2}}{3} \\ \sqrt{2} & -\frac{2\sqrt{2}}{3} \\ \sqrt{2} & -\frac{2\sqrt{2}}{3} \\ 0 & 2 \\ 0 & 2 \\ 0 & 2 \end{bmatrix}, \quad (20)$$

$$\|\mathbf{q}^{(1)}\|^2=9, \|\mathbf{q}^{(2)}\|^2=20. \quad (21)$$

The effect of the orthogonalization process on the two isotropic basic vectors is demonstrated by Eq. (20). By converting the latter back to matrix or tensor notation, it can be seen that $\mathbf{q}^{(1)}$ represents the spherical projection tensor, and $\mathbf{q}^{(2)}$ is a multiple of the deviatoric projection tensor. In general, for every basis vector $\mathbf{q}^{(i)}$ a parameter p_i can be determined that represents the contribution of $\mathbf{q}^{(i)}$ to the vector notation components of the elasticity tensor $\mathcal{C}$ in its material symmetry coordinate system. The procedure for determining the p_i will be explained in Section 3.5.

For an isotropic material, p_1 corresponds to its bulk modulus K and p_2 to its shear modulus G . This result is a consequence of imposing Eq. (16) on the vector notation.

$$[\mathbf{q}^{(3)} \quad \mathbf{q}^{(4)} \quad \mathbf{q}^{(5)}] = \begin{bmatrix} 2D_{11} & \frac{4}{3}D_{11} & D_{11}^2 + \frac{6}{7}\frac{III_s}{II}D_{11} + \frac{28}{105}II \\ 2D_{22} & \frac{4}{3}D_{22} & D_{22}^2 + \frac{6}{7}\frac{III_s}{II}D_{22} + \frac{28}{105}II \\ 2D_{33} & \frac{4}{3}D_{33} & D_{33}^2 + \frac{6}{7}\frac{III_s}{II}D_{33} + \frac{28}{105}II \\ -\sqrt{2}D_{11} & \frac{4\sqrt{2}}{3}D_{11} & \sqrt{2}\left(D_{11}^2 + \frac{6}{7}\frac{III_s}{II}D_{11} + \frac{91}{105}II\right) \\ -\sqrt{2}D_{22} & \frac{4\sqrt{2}}{3}D_{22} & \sqrt{2}\left(D_{22}^2 + \frac{6}{7}\frac{III_s}{II}D_{22} + \frac{91}{105}II\right) \\ -\sqrt{2}D_{33} & \frac{4\sqrt{2}}{3}D_{33} & \sqrt{2}\left(D_{33}^2 + \frac{6}{7}\frac{III_s}{II}D_{33} + \frac{91}{105}II\right) \\ 0 & -2D_{11} & -\frac{9}{7}\frac{III_s}{II}D_{11} + \frac{2}{5}II \\ 0 & -2D_{22} & -\frac{9}{7}\frac{III_s}{II}D_{22} + \frac{2}{5}II \\ 0 & -2D_{33} & -\frac{9}{7}\frac{III_s}{II}D_{33} + \frac{2}{5}II \end{bmatrix}, \quad (22)$$

$$\|\mathbf{q}^{(3)}\|^2 = -12II, \|\mathbf{q}^{(4)}\|^2 = -\frac{56}{3}II, \quad (23)$$

$$\|\mathbf{q}^{(5)}\|^2 = 2\frac{56II^3 + 135III^2}{35II}.$$

Eq. (22) yields orthogonal basis vectors in case the structure is not isotropic. When the structure becomes isotropic, the basis vectors become zero in a continuous way, as can be

seen from the equations and from the norms in Eq. (23). Note that $\lim_{D_{11} \rightarrow 0, D_{22} \rightarrow 0, D_{33} \rightarrow 0} \frac{III_s}{II} = 0$.

$$\mathbf{q}^{(6)} = \begin{bmatrix} 2D_{ii}^2 + 3\frac{III_s}{II}D_{ii} + \frac{4}{3}II \\ -\sqrt{2}\left(D_{ii}^2 + \frac{3}{2}\frac{III_s}{II}D_{ii} + \frac{2}{3}II\right) \\ 0 \end{bmatrix}, \quad (24)$$

$$\mathbf{q}^{(7)} = \begin{bmatrix} 2\frac{54II^2IIID_{ii}^2 + (27III^2II - 8II^4)D_{ii} + 81III^3 + 48II^3III}{56II^3 + 135III^2} \\ \sqrt{2}\frac{108II^2IIID_{ii}^2 + (54III^2II - 16II^4)D_{ii} - 81III^3 + 60II^3III}{56II^3 + 135III^2} \\ -2\frac{(108III^2II + 16II^4)D_{ii} + 81III^3 + 12II^3III}{56II^3 + 135III^2} \end{bmatrix}, \quad (25)$$

$$\mathbf{q}^{(8)} = \begin{bmatrix} \frac{II(4I^3+27III^2)(3D_{ii}^2+4II)}{6(8I^3-27III^2)} \\ \sqrt{2} \frac{II(4I^3+27III^2)(3D_{ii}^2+II)}{6(8I^3-27III^2)} \\ -\frac{(4I^3+27III^2)(9IIID_{ii}+2II^2)}{6(8I^3-27III^2)} \end{bmatrix}, \quad (26)$$

$$\mathbf{q}^{(9)} = \begin{bmatrix} 0 \\ 0 \\ -(2D_{ii}^2+3\frac{IIIs}{II}D_{ii}+\frac{4}{3}II) \end{bmatrix}, \quad (27)$$

$$\|\mathbf{q}^{(6)}\|^2 = \frac{4I^3+27III^2}{II},$$

$$\|\mathbf{q}^{(7)}\|^2 = 2 \frac{(27III^2 - 8I^3)(4I^3+27III^2)}{56I^3+135III^2}, \quad (28)$$

$$\|\mathbf{q}^{(8)}\|^2 = \frac{II(4I^3+27III^2)^2}{6(8I^3-27III^2)},$$

$$\|\mathbf{q}^{(9)}\|^2 = \frac{2(4I^3+27III^2)}{3II}.$$

Finally Eqs. (24)–(27) provide additional orthogonal basis vectors for the case of three distinct eigenvalues. These equations are condensed by representing in a single row a set of three rows by indicating elements of the set using the index i that appears in the D_{ii} with $i = 1 \dots 3$. Note that every norm in Eq. (28) contains the factor $4I^3 + 27III^2$, implying that the norms become zero when two eigenvalues become equal. Note also in the expressions for $\|\mathbf{q}^{(5)}\|^2$ and $\|\mathbf{q}^{(7)}\|^2$ that $56I^3 + 135III^2 = 5(4I^3 + 27III^2) + 36I^3$ and that both summands in this expression are negative, ensuring that $\|\mathbf{q}^{(5)}\|^2$ and $\|\mathbf{q}^{(7)}\|^2$ are positive.

Concluding, at each transition between symmetries the nine orthogonal basic vectors, corresponding to nine orthotropic fourth-order tensors, are continuous and well-defined. The actual determination of the corresponding parameters p_i and their relation to the parameters defined in Cowin's original paper, are the subjects of the following sections.

3.5. Determination of parameters p_i

In the previous section we derived as a function of eigenvalues D_{ii} a set of mutually orthogonal vectors $\mathbf{q}^{(i)}$. Each vector represents according to Table 1 the components of an orthotropic fourth-order tensor in its symmetry coordinate system. Similarly, the components of elasticity tensor $\mathcal{C}$ which is assumed to share the same symmetry coordinate system, can be represented by vector $\mathbf{c}$. Since the $\mathbf{q}^{(i)}$ form a 9-dimensional orthogonal basis of rank r , $\mathbf{c}$ can be expressed in terms of this basis as

$$\mathbf{c} = \sum_{i=1}^r p_i \mathbf{q}^{(i)} = \sum_{i=1}^9 p_i \mathbf{q}^{(i)}. \quad (29)$$

The parameters p_i are thus defined as the coefficients of $\mathbf{c}$ in the orthogonal basis. They can be computed straightforwardly because of the orthogonality as

$$p_i = \frac{\mathbf{c} \cdot \mathbf{q}^{(i)}}{\|\mathbf{q}^{(i)}\|^2}, \quad \text{with } i \leq r = \text{rank}([\mathbf{q}^{(1)} \dots \mathbf{q}^{(9)}]). \quad (30)$$

Note that if $i > r$, $\mathbf{q}^{(i)} = \mathbf{0}$ and the parameter p_i is undefined. This is not a deficiency of the method, but rather a logical consequence of the basis being of lower rank for higher symmetries. When the symmetry case, hence the rank r , is correctly identified (see Section 3.7), it is rather advantageous that the well-defined parameters ($i \leq r$) can be computed efficiently, individually, and without any change to the method or to their physical meaning.

Up to this point, the orthogonal basis and elasticity tensor were expressed using 9-dimensional vectors. Although preferable for computational purposes, these vectors do not have genuine tensorial nature. Since all non-zero components in the symmetry coordinate system are known, it is possible using Table 1 to reconstruct tensor $\mathcal{C}$ from vector $\mathbf{c}$, and to construct for every vector $\mathbf{q}^{(i)}$ a tensor $\mathcal{Q}^{(i)}$ in the corresponding symmetry coordinate system. Because of Eq. (16), the tensors $\mathcal{Q}^{(i)}$ are orthogonal with respect to the quadruple contraction: $\mathcal{Q}^{(i)} :: \mathcal{Q}^{(j)} = 0$ for $i, j = 1 \dots r$, $i \neq j$ and $\mathcal{Q}^{(i)} :: \mathcal{Q}^{(i)} = \|\mathbf{q}^{(i)}\|^2$ for $i = 1 \dots r$. This allows writing Eqs. (29) and (30) in tensorial form as

$$\mathcal{C} = \sum_{i=1}^r p_i \mathcal{Q}^{(i)} \quad \text{with} \quad (31)$$

$$p_i = \frac{\mathcal{C} :: \mathcal{Q}^{(i)}}{\mathcal{Q}^{(i)} :: \mathcal{Q}^{(i)}}.$$

Concluding, the parameters p_i are the coefficients of an orthogonal tensor basis of rank r .

3.6. Relation with the original formulation

To establish the relation between the new parameters p_i and the parameters a_i , b_i and c_i proposed by Cowin (1985), we need to have a further look at the orthogonalization process. This process factorizes $\mathbf{B}$ (see Eq. (18)) into the orthogonal basis and an upper triangular matrix $\mathbf{R}$: $\mathbf{B} = [\mathbf{q}^{(1)} \dots \mathbf{q}^{(9)}] \mathbf{R}$. Based on this relation it is easily shown that $[p_1 \dots p_9]^T = \mathbf{R} [a_1 \ c_1 \ a_2 \ c_2 \ b_1 \ a_3 \ b_2 \ b_3 \ c_3]^T$. $\mathbf{R}$ thus describes the relation between both bases and their coefficients. Its components are

$$\mathbf{R} = \begin{bmatrix} 1 & \frac{2}{3} & 0 & 0 & 0 & -\frac{4I}{3} & 0 & \frac{4I^2}{9} & -\frac{8I}{9} \\ 0 & 1 & 0 & 0 & -\frac{I}{5} & 0 & \frac{3III}{5} & \frac{I^2}{15} & -\frac{4I}{15} \\ 0 & 0 & 1 & \frac{4}{3} & 0 & -\frac{3III}{2I} & -\frac{2I}{3} & \frac{III}{14} & -\frac{2II}{3} \\ 0 & 0 & 0 & 1 & -\frac{9III}{14I} & 0 & -\frac{2I}{7} & \frac{3III}{14} & -\frac{3II}{7} \\ 0 & 0 & 0 & 0 & 1 & 0 & -\frac{108I^2 III}{56I^3 + 135III^2} & \frac{II(28I^3 + 675III^2)}{6(56I^3 + 135III^2)} & \frac{35(4I^3 + 27III^2)}{3(56I^3 + 135III^2)} \\ 0 & 0 & 0 & 0 & 0 & 1 & 0 & -\frac{2I}{3} & \frac{4}{3} \\ 0 & 0 & 0 & 0 & 0 & 0 & 1 & \frac{18I^2 III}{27III^2 - 8I^3} & \frac{36II III}{27III^2 - 8I^3} \\ 0 & 0 & 0 & 0 & 0 & 0 & 0 & 1 & \frac{2}{II} \\ 0 & 0 & 0 & 0 & 0 & 0 & 0 & 0 & 1 \end{bmatrix}. \quad (32)$$

For higher symmetries (i.e. rank $r = 2$ or $r = 5$) $\mathbf{R}$ is not invertible, but the restriction to its first r columns and rows is.

3.7. Numerical implementation

The proposed methods were implemented in MATLAB, documented, and collected in a publicly available package (Moesen, 2011). In this section we would like to point out the most important computational issues. Firstly, the orthogonalization can be performed both numerically and analytically. The analytical method evaluates Eqs. (20)–(28) directly, and is therefore the most accurate and efficient. The numerical method starts from Cowin's original system and performs a numerical orthogonalization based on a stable QR factorization. Secondly, identifying the proper case of symmetry allows improving the efficiency by limiting the rank r of the orthogonal basis. Because of rounding errors, it is advisable to test for equality of the eigenvalues D_{ij} rather than testing the invariant expressions $II=0$ and $4I^3 + 27III^2 = 0$. Thirdly, when directly evaluating the analytical

formulas, degeneracies such as a division by zero in the evaluation of $\frac{III}{II}$ when $II=0$ can be prevented by appropriate tests based on the rank r . Finally, it is advisable to use the parameters p_i as these are better defined and computed very efficiently. The original coefficients a_i , b_i and c_i are ill-defined if rank $r < 9$ and require an additional backward substitution using $\mathbf{R}$.

4. Examples

4.1. Mori–Tanaka model with aligned porous inclusions

As a first example, the parameter determination method was applied to the model of Mori and Tanaka (1973) with aligned, porous ellipsoidal inclusions in an isotropic matrix. The matrix was assigned a Young's modulus of 1 GPa and a Poisson's ratio of 0.3. The porosity was 99%. For this porosity, the model is known to overestimate the elastic constants of typical porous materials. Indeed, Weng (1990) showed that the MT model with sphere-shaped inclusions coincides with the upper bound of Hashin and Shtrikman (1963). It thus represents the maximum elastic constants that a porous material theoretically can attain in case of structural and material isotropy. Nevertheless, the MT model is an appropriate theoretical model for evaluating the parameter determination method, because it respects the symmetry modes predicted by Cowin's theory.

The ellipsoidal inclusions were aligned with the coordinate axes. The radius r_x was fixed at 1, while r_y and r_z were allowed to vary on a logarithmic scale consisting of 65 levels between 1=10 and 10. The radii of the ellipsoids were assumed to be representative of the eigenvalues of the fabric tensor.

The model was run for all (4225) combinations of r_y and r_z . Fig. 1 shows a surface plot of the obtained parameters. The axes of the plots are on a logarithmic scale. The bulk modulus p_1 and shear modulus p_2 attain a maximum at the point of isotropy, but vary by less than 0.5% throughout the domain. Parameters p_3 to p_5 have an interesting three-lobed structure. Note that the surface is not shown at the point of isotropy (the origin), as here the parameters are not defined. Near this point, no noteworthy discontinuity was observed. Parameters p_6 and p_9 have very similar three-lobed surfaces that appear continuous near all points with higher symmetry, i.e. the x -axis ($r_z = r_x$), the y -axis ($r_y = r_x$) and the $y = x$ bisector ($r_y = r_z$).

This is not true for parameters p_7 and p_8 , which show erratic peaks near the origin. This could not be explained from a theoretical point of view, but it should be noted that near the origin the basis tensors are near-zero with multiplicity three and four respectively. The magnitudes of the squared norms are plotted in Fig. 2. The near-zero basis tensors may induce a blow-up of the approximation error of the model. This hypothesis is supported by Fig. 3, which shows the relative magnitude of parameters p_7 and p_8 to the elasticity tensor $\mathcal{C}$. The relative magnitude is defined as the ratio $\|\mathbf{q}^{(i)}\|^2 / (\mathcal{C} :: \mathcal{C})$, which sums to one for $i = 1 \dots 9$. Note that the relative magnitude of parameters p_7 and p_8 is almost zero in the erratic region. Quantitatively, the absolute magnitude of terms $i = 7$ and $i = 8$ in Eq. (31) was in the neighborhood of the origin in the order of magnitude of the approximation error of the Mori–Tanaka model.

Finally, we reconstructed in every data point the elasticity tensor from parameters p_i using Eq. (31) and compared it with the original elasticity tensor predicted by the Mori–Tanaka model. In every data point a relative accuracy of 10^{-11} was obtained. This demonstrates that the proposed method can represent the elasticity tensor accurately for a model that respects the underlying symmetry assumptions of the theory.

4.2. Octet-truss model

A second example to which the parameter evaluation method was applied was the octet-truss structure described by Deshpande et al. (2001).

The octet-truss structure, which consists entirely of beams oriented along $\langle 110 \rangle$ directions, is shown in Fig. 4. Because of the high connectivity (12) in the junctions between beams, the beams deform primarily by axial compression and tension, making the octet-truss structure particularly stiff in the $\langle 111 \rangle$ directions. The elasticity tensor was shown to have cubic symmetry for a cubic unit cell. For this cell, the second order fabric tensor is isotropic, but the fourth order fabric tensor is not. The octet-truss structure is thus an example of a material that requires a fourth-order description of the fabric. Therefore it can provide insight in the behavior of the proposed method when the material does not respect the underlying symmetry assumptions of the theory.

The octet-truss structure was modeled using Euler–Bernoulli beam finite elements having a radius such that the porosity was 99%. Since the beams were relatively thin, the overlap between them at junctions was neglected. For the same reason, the fabric tensors were computed based on the direction vector of every beam, weighted by its volume. The constituent material was assumed to be isotropic with a Young's modulus of 1 GPa and a Poisson's ratio of 0.3. Structural anisotropy was introduced by affinely scaling the unit cell. Its width a_x was fixed at 2, while a_y and a_z were allowed to vary on a logarithmic scale consisting of 65 levels between 1 and 4. For each unit cell, the fabric tensor was computed using Kanatani's method and the elasticity tensor was computed by an in-house homogenization code. This code was validated against FE models (Moesen, 2009, ch. 5) and against the analytical solution for the case that $a_x = a_y = a_z$ (Deshpande et al., 2001).

Fig. 5 shows the surface plots for parameters p_1 to p_9 . The axes of the plots are on a logarithmic scale where -1 represents scaling by $1/2$ and 1 represents scaling by 2 . For the octet-truss structure, parameter $p_1 = 1.111 \text{ MPa} \approx 1/9 E_m \phi_m$ and $p_2 = 0.6675 \text{ MPa} \approx 1/15 E_m \phi_m$ throughout the entire domain. Parameter $p_3 = 0.4444 \text{ MPa} \approx 4/9 E_m \phi_m$ and $p_4 = 0.191 \text{ MPa}$, except in the origin where they are not defined. Near the origin, parameters p_5 and p_8 have a negative peak. The peaks for parameter p_7 are both negative and positive. These parameters are not constant but show some curvature away from the peaks (not well visible). Parameter p_6 is zero throughout the entire domain. Parameter p_9 has a continuous concave appearance.

Fig. 6 shows the approximation error between the elasticity tensor of the octet-truss structure and the elasticity tensor predicted by the parameter evaluation method. The error is markedly higher for the cases of transversal structural symmetry, and maximal for the case of isotropic structural symmetry. This was expected, as in these cases the actual material symmetry of the structure is lower than the symmetry predicted by the theory. The theory thus cannot capture entirely the mechanical behavior of the octet-truss structure. The fact that Fig. 6 resembles this supports the correctness of the parameter evaluation method.

It is troublesome, however, that the error in Fig. 6 is not continuous between the different cases of symmetry. In particular for every point with orthotropic material symmetry it drops to less than 10^{-10} . This indicates that the octet-truss model is over-fit by the additional degrees of freedom that become available for lower symmetries. Other indications are the consistent peaks for parameters p_5 and p_8 , and their higher relative magnitude near (but not in) points with higher symmetry, as shown in Fig. 7. Note in this figure also the discontinuities in slope (p_5) and value (p_8) radiating out from the origin. Since over-fitting is hard to detect if no data is available that corresponds to cases of higher symmetry, the theory should only be applied to materials that are known to be well-described by their second order fabric tensor, such as cancellous bone.

4.3. Cancellous bone

In previous studies (Kabel et al., 1999; van Rietbergen and Huiskes, 2001), the elastic constants of 141 human cancellous bone specimens were obtained using micro-finite-element methods and compared to predictions from the analytical model developed by Cowin (1985). Briefly, normal cancellous bone material was collected at six anatomical locations from 56 individuals. Numerical analysis was based on high-resolution three-dimensional computer reconstructions of cancellous bone specimens from which the complete elastic characteristics and trabecular morphology, represented by the fabric tensor (measured via the mean intercept length) were calculated. The fabric measure was analyzed individually using the tensorial relationships derived by Cowin (1985). The Cowin model could explain 86–95% of the variance (Fig. 8). These same data were analyzed by a different method in Yang et al. (1998).

In this study, we computed the set of nine orthogonal parameters p_i ($i = 1 \dots 9$) using the data sets of FE-derived elastic constants and fabric measurements from MIL. Then, relationships between the p_i parameters and the volume fraction were obtained by curve fitting using the robust regression technique built in MATLAB. Fig. 9 shows nine panels with each of the p_i parameters as functions of the volume fraction. Interestingly, parameters p_1 , p_2 , p_3 and p_4 exhibited a clear dependence on the volume fraction, while parameters p_5 through p_9 have a larger variance and thus a slight dependence on the volume fraction.

Fig. 9 also shows the equations of parameters p_i as power law functions of the volume fraction. Once determined, we examined the ability of such relationships to predict the elastic constants determined from FE micromechanical models. The comparison between the

elastic constants derived from the FE model and this new analytical model is shown in Fig. 10.

Since parameters p_5 to p_9 are less sensitive to the volume fraction, the effect of neglecting terms of higher order was investigated. Fig. 11 shows the correlation between the elastic constants calculated from FE model and the analytical model when fourth (p_8) order and third (p_7) order terms were neglected. The correlations when neglecting also second order terms are shown in Fig. 12.

In summary, the model based on the complete set of p_i parameters could explain 75–90% of the variance on FE-derived elastic constants. When third and fourth order terms were neglected, the remaining parameters (p_1 – p_6 , p_9) could explain 81–89% of the elastic constants. The constant and first order terms (p_1 – p_4) explained 83–89% of the elastic constants. Therefore the latter are the most influential on the correlation between FE-derived elastic constants and analytical model elastic constants. Overall, these results indicate that both (Cowin, 1985) model and the one presented here are almost equally effective to predict the elastic constants of human cancellous bone. The advantage of the analytical model presented in this study is that it is symmetry invariant, and avoids the discontinuity exhibited by Cowin (1985) model when two or three fabric eigenvalues are the same.

5. Discussion

To represent compactly the components of an elasticity tensor $\mathcal{C}$ in its material coordinate system, closed-form analytical expressions (Eq. (20), (22) and (24)–(27)) were proposed that define an orthogonal basis $\mathcal{Q}^{(i)}$ ($i = 1 \dots 9$) as function of the deviatoric part of fabric tensor $\mathbf{A}$. The basis was shown to be well-defined for every material symmetry admissible by the theory. At a transition towards higher material symmetry, the appropriate $\mathcal{Q}^{(i)}$ become zero in a continuous way, lowering the rank of the basis accordingly. Because of the orthogonality, the parameters p_i can be computed efficiently and individually by means of a simple projection (Eq. 31).

It should be remarked that the proposed basis is not unique as it depends on the order of the columns of Eq. (17) before orthogonalization. The order should, however, respect the linear (in)dependency relations in case of three and two equal eigenvalues D_{ii} . Within these bounds, each different ordering results in an equivalent set of parameters p_i and a proper orthogonal basis. Nevertheless, the complexity of the basis can differ significantly as function of the ordering, especially for Eqs. (24)–(27). Of all orderings tried, the selected ordering had the highest number of zero terms, recurrent factors and the lowest complexity.

Furthermore it is worthwhile to recapitulate two major assumptions of the theory. Firstly it is assumed that the matrix material is isotropic and homogeneous and that the microstructure is adequately described by its volume fraction and second order fabric tensor. Secondly, it is assumed that the principal coordinate system of the fabric tensor is aligned with the planes of material symmetry. Although these assumptions do not apply to all porous materials, they have been shown to apply e.g. to cancellous bone (Harrigan and Mann, 1984; Odgaard, 1997).

The symmetry-invariance of the method was validated by applying the method to two model-based data sets. The resulting parameters p_i were well-behaved and continuous near symmetry transitions, except when the theoretical assumptions were not satisfied, or when large relative errors occurred due to the norm of higher-order basis tensors becoming very small. Large relative errors were also observed to induce a large variance for the higher-order parameters for the cancellous bone data set in datapoints that were nearly

(transversally) isotropic. The influence of this variance could be minimized by using robust regression techniques. These effects were not observed with the original method (Cowin, 1985; van Rietbergen and Huiskes, 2001), probably because in the latter the higher order terms were neglected. A further advantage of this method is that every parameter can be evaluated individually due to the orthogonality property, which also implies that ill-conditioning of the data for one parameter does not affect the results for other parameters. Finally, correlations for the cancellous bone data revealed that the higher order parameters contributed little to the predictions and that the zeroth and first order parameters p_1 – p_4 explained already 83–89% of the total variance.

The parameters for the cancellous bone data were approximated using power-law functions as function of the volume fraction only. This formulation presumed no interdependence of porosity and fabric, as seen in the experimental data on cancellous bone where the correlation coefficient between the two geometric measures is very low (Souzanchi et al., 2012). Although the current formulation explained 75–90% of the total variance, the actual formulation may be more complex and may also involve invariants I_D and III_D of the deviatoric part of the fabric tensor. More accurate formulations can be investigated in future work.

6. Conclusion

This work improved (Cowin, 1985) framework for investigating the relationship between the elasticity tensor and the fabric tensor. The improved framework is symmetry-invariant: regardless of material symmetry, it defines a single, well-defined orthogonal tensor basis and corresponding parameters that can be computed easily and efficiently. Its accuracy and precision were demonstrated using numerical models. When applied to a cancellous bone data set, the framework explained 75–90% of the total variance.

Acknowledgments

This work was part of project “Design and modeling of cellular solids” (IWT/OZM/080436), funded by the government agency for Innovation by Science and Technology in Flanders, Belgium. It was further supported by the National Science Foundation (PHY-0848491 and MRI-0723027), NIH Grant No AG34198, and the PSC-CUNY Research Award Program of the City University of New York. The authors thank Bert van Rietbergen (T.U. Eindhoven, Netherlands) for kindly providing the cancellous bone data. M.M. would like to thank Stepan Lomov and Larissa Gorbatikh for useful discussions and Jeroen Heulens and Oksana Shishkina for their advice regarding the symbolic computations.

References

- Advani S, Tucker C. The use of tensors to describe and predict fiber orientation in short fiber composites. *Journal of Rheology*. 1987; 31(8):751–784.
- Chiang MYM, Wang X, Landis FA, Dunkers J, Snyder CR. Quantifying the directional parameter of structural anisotropy in porous media. *Tissue Engineering*. 2006; 12(6):1597–1606. [PubMed: 16846355]
- Cowin SC. The relationship between the elasticity tensor and the fabric tensor. *Mechanics of Materials*. 1985; 4:137–147.
- Cowin SC. Remarks on the paper entitled ‘fabric and elastic principal directions of cancellous bone are closely related’. *Journal of Biomechanics*. 1997; 30(11–12):1191–1192. [PubMed: 9456391]
- Deshpande V, Fleck N, Ashby M. Effective properties of the octettruss lattice material. *Journal of the Mechanics and Physics of Solids*. 2001; 49(8):1747–1769.
- Gibson, LJ.; Ashby, MF. *Cellular Solids: Structure and Properties*. second ed.. Cambridge: Cambridge University Press; 1997. <http://www.loc.gov/catdir/description/cam028/96031571.html>
- Harrigan TP, Mann RW. Characterization of microstructural anisotropy in orthotropic materials using a 2nd rank tensor. *Journal of Materials Science*. 1984; 19(3):761–767.

- Hashin Z, Shtrikman S. A variational approach to the theory of the elastic behaviour of multiphase materials. *Journal of the Mechanics and Physics of Solids*. 1963; 11(2):127–140.
- Kabel J, van Rietbergen B, Odgaard A, Huiskes R. Constitutive relationships of fabric, density, and elastic properties in cancellous bone architecture. *Bone*. 1999; 25(4):481–486. [PubMed: 10511116]
- Kalman D, White J. Polynomial equations and circulant matrices. *American Mathematical Monthly*. 2001; 108(9):821–840.
- Kanatani K. Distribution of directional-data and fabric tensors. *International Journal of Engineering Science*. 1984; 22(2):149–164.
- Matsuura M, Eckstein F, Lochmueller E-M, Zysset PK. The role of fabric in the quasi-static compressive mechanical properties of human trabecular bone from various anatomical locations. *Biomechanics and Modeling In Mechanobiology*. 2008; 7(1):27–42. [PubMed: 17235622]
- Mehrabadi M, Cowin S. Eigentensors of linear anisotropic elastic-materials. *Quarterly Journal of Mechanics and Applied Mathematics*. 1990; 43:15–41.
- Moesen, M. Ph.D thesis. Belgium: Katholieke Universiteit Leuven; 2009. Modeling of the geometry and mechanical behavior of bone scaffolds.
- Moesen M. Mmtensor – micromechanical tensor computations in matlab. 2011 <<http://www.mathworks.com/matlabcentral/fileexchange/>>.
- Mori T, Tanaka K. Average stress in matrix and average elastic energy of materials with misfitting inclusions. *Acta Metallurgica*. 1973; 21(5):571–574.
- Oda M, Konishi J, Nemat-Nasser S. Experimental micromechanical evaluation of strength of granular materials: effects of particle rolling. *Mechanics of Materials*. 1982; 1:269–283.
- Odgaard A. Three-dimensional methods for quantification of cancellous bone architecture. *Bone*. 1997; 20(4):315–328. [PubMed: 9108351]
- Odgaard A, Jensen EB, Gundersen HJG. Estimation of structural anisotropy based on volume orientation – a new concept. *Journal of Microscopy-Oxford*. 1990; 157:149–162.
- Odgaard A, Kabel J, vanRietbergen B, Dalstra M, Huiskes R. Fabric and elastic principal directions of cancellous bone are closely related. *Journal of Biomechanics*. 1997; 30(5):487–495. [PubMed: 9109560]
- Rychlewski J. On hooke law. *Pmm Journal of Applied Mathematics and Mechanics*. 1984; 48(3):303–314.
- Smit TH, Schneider E, Odgaard A. Star length distribution: a volume-based concept for the characterization of structural anisotropy. *Journal of Microscopy-Oxford*. 1998; 191:249–257.
- Souzanchi M, Palacio-Mancheno P, Borisov Y, Cardoso L, Cowin S. Microarchitecture and bone quality in the human calcaneus; Local variations of fabric anisotropy. *Journal of Bone and Mineral Research*. 2012
- Thomson W. Elements of a mathematical theory of elasticity. *Philosophical Transactions of the Royal Society*. 1856; 166:481–498.
- Thomson, W. Elasticity. Edinburgh: Adam and Charles Black; 1878.
- Turner C, Cowin S. Dependence of elastic-constants of an anisotropic porous material upon porosity and fabric. *Journal of Materials Science*. 1987; 22(9):3178–3184.
- Turner C, Cowin S, Rho J, Ashman R, Rice J. The fabric dependence of the orthotropic elastic-constants of cancellous bone. *Journal of Biomechanics*. 1990; 23(6):549–561. [PubMed: 2341418]
- van Rietbergen, B.; Huiskes, R. Elastic constants of cancellous bone. In: Cowin, S., editor. *Bone Mechanics Handbook*. Vol. ch. 15. Boca Raton, FL: CRC Press; 2001. p. 1-24.
- van Rietbergen B, Odgaard A, Kabel J, Huiskes R. Direct mechanics assessment of elastic symmetries and properties of trabecular bone architecture. *Journal of Biomechanics*. 1996; 29(12):1653–1657. [PubMed: 8945668]
- van Rietbergen B, Odgaard A, Kabel J, Huiskes R. Relationships between bone morphology and bone elastic properties can be accurately quantified using high-resolution computer reconstructions. *Journal of Orthopaedic Research*. 1998; 16(1):23–28. [PubMed: 9565069]
- Voigt, W. *Lehrbuch der Kristallphysik*. Leipzig: Teubner; 1928.
- Weng G. The theoretical connection between mori tanaka theory and the hashin shtrikman walpole bounds. *International Journal of Engineering Science*. 1990; 28(11):1111–1120.

- Whitehouse WJ. Quantitative morphology of anisotropic trabecular bone. *Journal of Microscopy-Oxford*. 1974; 101:153–168.
- Yang GY, Kabel J, van Rietbergen B, Odgaard A, Huiskes R, Cowin SC. The anisotropic hooke's law for cancellous bone and wood. *Journal of Elasticity*. 1998; 53(2):125–146. [PubMed: 11543211]

Fig. 1. Parameters p_1 to p_9 determined for the Mori-Tanaka model.

Fig. 2. The squared norms $\|\mathbf{q}^{(i)}\|^2$ with $i = 1 \dots 9$ determined for the Mori–Tanaka model.

Fig. 3.

The magnitudes of the ratios $p_i^2 \|\mathbf{q}^{(i)}\|^2 / (\mathcal{E} : : \mathcal{E})$ for $i = 1 \dots 9$ for the Mori–Tanaka model.

Fig. 4.
Unit cell of the octet-truss lattice.

Fig. 5.
Parameters p_1 to p_9 determined for the octet-truss model.

Fig. 6.
Relative approximation error for the octet-truss model.

Fig. 7.

The magnitudes of the ratios $p_i^2 \|\mathbf{q}^{(i)}\|^2 / (\mathcal{C} : : \mathcal{C})$ for $i = 1 \dots 9$ for the octet-truss model.

Fig. 8.

Correlations of the predicted versus calculated entries, C_{iiii} , C_{iiij} and C_{ijij} , obtained when using the analytical model developed in Kabel et al. (1999) based on the original set of parameters k_i obtained by Cowin (1985).

Fig. 9.

Orthogonal parameters p_i ($i = 1 \dots 9$) as function of the volume fraction derived from the analytical model developed in this study and data set in Kabel et al. (1999). Dashed lines represent 95%t confidence intervals on the predictions by the mentioned power-law equations.

Fig. 10.

Correlations of the predicted versus calculated entries, C_{iiii} , C_{iiij} and C_{ijkl} obtained when using the analytical model developed in this study. All parameters p_1 to p_9 were taken into account.

Fig. 11.

Correlations of the predicted versus calculated entries, C_{iiii} , C_{iiij} and C_{ijij} obtained when using the analytical model developed in this study. Third and fourth order terms were neglected.

Fig. 12.

Correlations of the predicted versus calculated entries, C_{iiii} , C_{iiij} and C_{ijij} , obtained when using the analytical model developed in this study. Only the first order terms (p_1 to p_4) were considered.

Table 1

Relations between vector, matrix and tensor notation of elasticity tensors with orthotropic symmetry.

Vector	Matrix	Tensor
C_1	C_{11}	C_{1111}
C_2	C_{22}	C_{2222}
C_3	C_{33}	C_{3333}
C_4	$\sqrt{2}C_{23}$	$\sqrt{2}C_{2233}$
C_5	$\sqrt{2}C_{13}$	$\sqrt{2}C_{1133}$
C_6	$\sqrt{2}C_{12}$	$\sqrt{2}C_{1122}$
C_7	C_{44}	$2C_{2323}$
C_8	C_{55}	$2C_{3131}$
C_9	C_{66}	$2C_{1212}$

Table 2

The sign of the invariants of **D** as a function of its eigenvalues. ‘/’ indicates that the corresponding situation cannot occur.

Sign	$II_D < 0$	$II_D = 0$
$III_D < 0$	$D_{22} > 0$	/
$III_D = 0$	$D_{22} = 0$	$D_{11} = D_{22} = D_{33} = 0$
$III_D > 0$	$D_{22} < 0$	/