Published in final edited form as:

ACS Macro Lett. 2013 January 15; 2(1): 40–44. doi:10.1021/mz300522n.

Redox-Responsive, Core Cross-Linked Polyester Micelles

Zhonghai Zhang^{†,‡,§}, Lichen Yin^{†,§}, Chunlai Tu[†], Ziyuan Song[†], Yanfeng Zhang[†], Yunxiang Xu[†], Rong Tong[†], Qin Zhou^{†,‡}, Jie Ren^{‡,*}, and Jianjun Cheng^{†,*}

[†]Department of Materials Science and Engineering, University of Illinois at Urbana–Champaign, 1304 W. Green Street, Urbana, IL, 61801, USA

[‡]Institute of Nano- and Bio-polymeric Materials, School of Material Science and Engineering, Tongji University, Shanghai, 200092, China

[§]Department of Pharmaceutical Science, Guangdong Pharmaceutical University, Guangzhou, Guangdong, China

Abstract

Monomethoxy poly(ethylene glycol)-*b*-poly(Tyr(alkynyl)-OCA), a biodegradable amphiphilic block copolymer, was synthesized by means of ring-opening polymerization of 5-(4-(prop-2-yn-1-yloxy)benzyl)-1,3-dioxolane-2,4-dione (Tyr(alkynyl)-OCA) and used to prepare core cross-linked polyester micelles via click chemistry. Core cross-linking not only improved the structural stability of the micelles but also allowed controlled release of cargo molecules in response to the reducing reagent. This new class of core cross-linked micelles can potentially be used in controlled release and drug delivery applications.

Polymeric micelles have been extensively used for drug delivery because they can enhance drug solubility, prolong *in vivo* circulation time, and target specific tissues.¹ Conventional polymeric micelles, which are in thermodynamic equilibrium with their constituent unimers in aqueous solution, dissemble at concentrations below their critical micelle concentrations

*Corresponding Author: jianjunc@illinois.edu.

§Author Contributions

These authors contributed equally.

ASSOCIATED CONTENT

Supporting Information. Experimental details including GPC analysis, FTIR and CMC studies. This material is available free of charge via the Internet at <http://pubs.acs.org>.

Notes

The authors declare no competing financial interest.

(CMCs). Undesired micelle disintegrations lead to premature release of the encapsulated cargos before imparting specific functions. When micelles are used in drug delivery and administered *in vivo* systemically, micelle disintegration as a result of significant dilution in blood before their reaching the target tissues may result in reduced therapeutic efficacy and undesired side effects.²

One effective approach to solve this problem is to stabilize micellar structures by cross-linking.³ Micelle shell cross-linking approaches have been attempted and the resulting micelles were more stable than un-cross-linked (UCL) micelles upon dilution.^{2b, 3b, c, 4} However, cross-linking of hydrophilic shells may affect the surface mobility, and a highly diluted solution is often required to avoid undesired inter-micellar cross-linking.⁵ Shell cross-linking can also alter the stealthiness of the micelles.⁶ To avoid these problems, core cross-linked (CCL) micelles have been developed as an effective alternative. Most of the existing CCL micelles are based on non-degradable polymeric cores such as polyacrylate or polyacrylamide.⁷ Considering the requirement for biocompatibility and biodegradability in clinical applications, CCL micelles composed entirely of polyesters would be ideal candidates as drug delivery vehicles. The choice of the cross-linkers is also important because they directly affect the stability and properties of the resulting CCL micelles. Cross-linkers that respond to external triggers such as redox agents or changes in pH would allow control over the design and disassembly of CCL micelles and the release of encapsulated drugs.

Biocompatible and biodegradable aliphatic polyesters, such as poly(lactic acid), poly(glycolic acid), poly(ϵ -caprolactone), and poly(lactic-co-glycolic acid), have been widely used as hydrophobic cores of copolymer micelles for the encapsulation and delivery of lipophilic drugs.⁸ However, these polyesters lack side-chain functionality, which prevents core cross-linking of their micelles. It is thus synthetically challenging to modify these conventional polyesters to allow formation of micelles with cross-linkable cores. Effort has been devoted to the synthesis of side chain functionalized polyesters via ring-opening polymerizations (ROPs).⁹ *O*-carboxyanhydrides (OCAs) derived from amino acids is a particularly interesting class of monomers subject to ROP for the synthesis of functional polyesters; significant progress has been made through the work of Bourissou, Dove and others.^{9–10} In this paper, we report the synthesis of 5-[4-(prop-2-yn-1-yloxy)benzyl]-1,3-dioxolane-2,4-dione Tyr(alkynyl)-OCA, **1**, Scheme 1) and monomethoxy poly(ethylene glycol) (mPEG)-initiated ROP of **1** to prepare poly(**1**), a side-chain functionalized polyester with pendant alkynyl groups. Poly(**1**) was then used to prepare CCL micelles by cross-linking of the polyester alkynyl side chains in the hydrophobic cores via Cu(I)-catalyzed azide-alkyne cycloadditions (CuAAC, so-called “click chemistry”). The reaction is highly chemo-selective, and can proceed readily under mild conditions without producing by-products.¹¹ By utilizing bis-(azidoethyl) disulfide, a redox-responsive cross-linker, we developed CCL micelles with responsiveness toward reducing reagents, thus allowing trigger-induced micelle disruption and controlled release of the encapsulated cargo molecules.

Monomer **1**, a colorless crystalline solid, was synthesized from Boc-L-tyrosine (Boc-L-Tyr-OH) on a multigram scale in ~30% yield (Scheme S1). mPEG-*b*-poly(**1**) was synthesized by ROP of **1** with mPEG (MW = 5000 g/mol) as the macroinitiator and 4-dimethylaminopyridine (DMAP) as the catalyst. The monomer conversion exceeded 95%, evidenced by the complete disappearance of the anhydride FTIR band of **1** (1810 cm⁻¹) in the polymerization solution (Figure S1). Gel permeation chromatography (GPC) analysis revealed that the M_n values of the resulting mPEG-*b*-poly(**1**) copolymers at different monomer to initiator (M/I) ratios agreed well with the expected MWs and that all the copolymers showed narrow molecular weight distributions (MWDs = M_w/M_n , <1.12; Table

1 and Figure S2). These results demonstrated that DMAP-catalyzed ROP of **1** was effective for the synthesis of amphiphilic copolymers to be used for the study of CCL micelles.

Amphiphilic mPEG-*b*-poly(**1**) was first used to prepare UCL micelles consisting of a hydrophobic poly(**1**) core and a hydrophilic mPEG shell. The CMC of mPEG-*b*-poly(**1**), an effective indicator of micellar stability, was determined with Nile Red (NR) as a fluorescence probe.¹² All the micelles had low CMC values (Table 2, Figures S3 and S4), and the CMC values decreased with increasing poly(**1**) block length, indicating that longer poly(**1**) blocks facilitated the formation of micelles owing to increased hydrophobic interactions in the core. Upon identifying the CMCs of mPEG-*b*-poly(**1**), we next prepared the micelles using nanoprecipitation method and measured the mean hydrodynamic diameters by dynamic light scattering (DLS, Table 2). The particle diameter increased proportionally to the length of the hydrophobic block (poly(**1**)), indicating a longer poly(**1**) block led to the formation of a larger core with enhanced micelle assembly stability.¹³ The morphology of the UCL and CCL micelles was further analyzed by TEM. As shown in Figure S5, both UCL and CCL micelles were well dispersed and adopted spherical shapes; the diameters accorded well with those obtained from the DLS measurement.

We then prepared CCL micelles by introducing 1,4-diazidobutane (**2**, Schemes 1 and S2), a hydrophobic cross-linker, into the hydrophobic core of the micelles followed by **2**-mediated cross-linking of the poly(**1**) blocks by means of click chemistry. We designed a ¹H NMR experiment to test whether cross-linking could occur in the micelle core to form CCL micelles. mPEG-*b*-poly(**1**) and **2** were dissolved in DMF and then water was added to the DMF solution to allow micelles to form. During this process, the hydrophobic cross-linker **2** should migrate into the hydrophobic micelle core which remained swollen in the presence of DMF. CuCl₂ and ascorbic acid sodium salt were subsequently added to initiate the click reaction. After removing the copper and DMF by dialysis in deionized water and removing the water by lyophilization, we dissolved the obtained materials in DMSO-*d*₆, a solvent that can dissolve both the mPEG and the poly(**1**) block. The ¹H NMR spectrum showed only the hydrophilic proton peaks of mPEG and but not the poly(**1**) block, substantiating formation of CCL micelles and well maintained micelle structure in DMSO (Figure 1b). To validate this conclusion, we prepared and processed micelles using exactly the same materials and conditions without adding CuCl₂ and ascorbic acid sodium salt. No click-chemistry induced core cross-linking should happen and the resulting micelles (i.e., the excepted UCL micelles) should not be stable in DMSO-*d*₆. As expected, the ¹H NMR spectrum of the latter materials was identical to that of mPEG-*b*-poly(**1**) in DMSO-*d*₆ in which both mPEG and poly(**1**) proton peaks were clearly visible (Figure 1a).

To further demonstrate the cross-linking of the hydrophobic core, we evaluated the change in the diameters of both UCL- and CCL micelles upon addition of DMF, a solvent to both mPEG and poly(**1**). The diameters and PDIs of the CCL and UCL micelles in water were first determined by dynamic light scattering (DLS) and found to be nearly identical (Table 2). Upon dilution with 10-fold DMF, the mPEG-*b*-poly(**1**)₂₀ UCL micelles (mPEG-*b*-poly(**1**)₂₀) were completely disrupted, evidenced by the disappearance of the solution DLS signal (Figure 2a). In contrast, the mPEG-*b*-poly(**1**)₂₀ CCL micelles well maintained their structure upon dilution with 10-fold DMF, and the particle diameter increased dramatically to 101 nm from 37 nm of the untreated CCL micelles (Figure 2b), owing to swelling of the core. These results confirmed that cross-linking of the mPEG-*b*-poly(**1**) core allowed the resulting micelles to withstand dissolution in DMF.

In some cases, excessively stabilized cross-linked micelles cannot effectively release their payloads at the target site, thus compromising the therapeutic efficacy.¹⁴ To make the cross-linking reversible, we used bis(azidoethyl) disulfide (**3**, Scheme S3), a disulfide-containing

cross-linker and an analogue of **2**, to prepare CCL micelles so that they would release cargo molecules in response to external triggers,¹⁵ such as reducing reagent. The resulting CCL micelles using **3** as the cross-linker were similarly prepared as previously described for the CLL prepared with cross-linker **2**. Both CCL micelles had similar particle diameters and stabilities.

To explore the redox-responsive cargo-release profiles, we encapsulated NR as a model hydrophobic drug into the disulfide cross-linked micelles (mPEG-*b*-poly(**1**)₂₀, CCL1) and monitored NR release at a concentration (6.0×10^{-3} mg/mL) below the CMC (15.9×10^{-3} mg/mL, Figure S4). In the absence of the reducing agent D,L-dithiothreitol (DTT), the fluorescence intensity of NR remained unchanged (Figure 3), suggesting that the stable micelles tightly restricted NR in their hydrophobic cores. However, in the presence of 10 mM DTT, the fluorescence intensity of NR decreased by 90% within 4 h (Figure 3), indicating that the micelle structure had been disrupted by cleavage of the disulfide cross-linker. These results implied that the disulfide cross-linked micelles could encapsulate hydrophobic cargo molecules at concentrations below the CMC and selectively release the cargo in response to changes in the redox environment.

To fine tune the release profile of the CCL micelles, we synthesized CCL micelles containing various ratios of cross-linkers **2** and **3**. Specifically, we prepared CCL2, CCL3, CCL4, and CCL5, which had the cross-linker **2/3** molar ratios of 2:8, 5:5, 8:2 and 10:0, respectively. NR release from the micelles was decreased as the content of **3** decreased (Figure 3), evidenced by the observation that the NR fluorescence intensities of CCL2, CCL3, and CCL4 decreased by 60%, 15%, and 10%, respectively, within 3 h of treatment with 10 mM DTT. No NR was released from the CCL5 micelles. These results suggested that micelles containing inadequate amounts of redox-responsive cross-linker **3** were not completely disrupted, and the results again substantiated the importance of **3** in triggering redox-responsive cargo release. This study also suggested that adjusting the cross-linker **2/3** feed ratio is a promising approach of modulating drug release profiles to meet specific therapeutic requirements.

In summary, we developed CCL micelles through ROP of *O*-carboxyanhydrides bearing alkyne groups followed by core cross-linking with the use of click chemistry. The CCL micelles not only were structurally stable but also allowed the controlled release of cargo molecules when a redox-responsive cross-linker was introduced. This new class of CCL micelles therefore has potential as a delivery system for the controlled release of pharmaceutical agents.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

This work was supported by the NIH (R21 1R21EB013379 and a Director's New Innovator Award 1DP2OD007246) and the NSF (CHE-1153122). ZH acknowledges support from the China Scholarship Council (No. 2011626096).

REFERENCES

1. (a) Arimura H, Ohya Y, Ouchi T. *Biomacromolecules*. 2005; 6:720–725. [PubMed: 15762635] (b) Gref R, Minamitake Y, Peracchia MT, Trubetskoy V, Torchilin V, Langer R. *Science*. 1994; 263:1600–1603. [PubMed: 8128245] (c) Kataoka K, Harada A, Nagasaki Y. *Adv Drug Deliver Rev*. 2001; 47:113–131. (d) Liu JY, Pang Y, Huang W, Zhu XY, Zhou YF, Yan DY. *Biomaterials*. 2010;

- 31:1334–1341. [PubMed: 19883937] (e) Matsumoto S, Christie RJ, Nishiyama N, Miyata K, Ishii A, Oba M, Koyama H, Yamasaki Y, Kataoka K. *Biomacromolecules*. 2009; 10:119–127. [PubMed: 19061333] (f) Torchilin VP. *Pharm Res-Dord*. 2007; 24:1–16. (g) Bae JW, Pearson RM, Patra N, Sunoqrot S, Vukovic L, Kral P, Hong S. *Chem Commun*. 2011; 47:10302–10304. (h) Wang WP, Yang ZM, Patanavanich S, Xu B, Chau Y. *Soft Matter*. 2008; 4:1617–1620. (i) Zhang LF, Radovic-Moreno AF, Alexis F, Gu FX, Basto PA, Bagalkot V, Jon SY, Langer RS, Farokhzad OC. *Chemmedchem*. 2007; 2:1268–1271. [PubMed: 17600796] (j) Pyun J. *Polym Rev*. 2007; 47:231–263. (k) Luo CH, Liu Y, Li ZB. *Soft Matter*. 2012; 8:2618–2626. (l) Ma WF, Xu SA, Li JM, Guo J, Lin Y, Wang CC. *J Polym Sci Pol Chem*. 2011; 49:2725–2733.
2. (a) Koo AN, Lee HJ, Kim SE, Chang JH, Park C, Kim C, Park JH, Lee SC. *Chem Commun*. 2008:6570–6572. (b) Rijcken CJ, Snel CJ, Schiffelers RM, van Nostrum CF, Hennink WE. *Biomaterials*. 2007; 28:5581–5593. [PubMed: 17915312]
3. (a) Li YP, Xiao K, Luo JT, Xiao WW, Lee JS, Gonik AM, Kato J, Dong TA, Lam KS. *Biomaterials*. 2011; 32:6633–6645. [PubMed: 21658763] (b) Weaver JVM, Tang YQ, Liu SY, Iddon PD, Grigg R, Billingham NC, Armes SP, Hunter R, Rannard SP. *Angew Chem Int Edit*. 2004; 43:1389–1392. (c) Zhang SY, Zhao Y. *J Am Chem Soc*. 2010; 132:10642–10644. [PubMed: 20681683] (d) Guo A, Liu GJ, Tao J. *Macromolecules*. 1996; 29:2487–2493. (e) O'Reilly RK, Hawker CJ, Wooley KL. *Chem Soc Rev*. 2006; 35:1068–1083. [PubMed: 17057836]
4. (a) Jiang GH, Wang Y, Zhang R, Wang RJ, Wang XH, Zhang M, Sun XK, Bao SY, Wang T, Wang S. *Acs Macro Lett*. 2012; 1:489–493. (b) Jiang XZ, Zhang GY, Narain R, Liu SY. *Langmuir*. 2009; 25:2046–2054. [PubMed: 19140708] (c) Kakizawa Y, Harada A, Kataoka K. *J Am Chem Soc*. 1999; 121:11247–11248. (d) Kim Y, Liemawala ED, Pourgholami MH, Morris DL, Stenzel MH. *Macromolecules*. 2012; 45:5451–5462. (e) Tan H, Zhang Y, Wang M, Zhang ZX, Zhang XH, Yong AM, Wong SY, Chang AYC, Chen ZK, Li X, Choolani M, Wang J. *Biomaterials*. 2012; 33:237–246. [PubMed: 21963283] (f) Thurmond KB, Kowalewski T, Wooley KL. *J Am Chem Soc*. 1996; 118:7239–7240.
5. (a) Hu XL, Chen XS, Wei JZ, Liu S, Jing XB. *Macromol Biosci*. 2009; 9:456–463. [PubMed: 19089869] (b) Koo AN, Min KH, Lee HJ, Lee SU, Kim K, Kwon IC, Cho SH, Jeong SY, Lee SC. *Biomaterials*. 2012; 33:1489–1499. [PubMed: 22130564] (c) Thurmond KB, Kowalewski T, Wooley KL. *J Am Chem Soc*. 1997; 119:6656–6665.
6. Cajot S, Lautram N, Passirani C, Jerome C. *Journal of Controlled Release*. 2011; 152:30–36. [PubMed: 21457741]
7. (a) Jiang XZ, Liu SY, Narain R. *Langmuir*. 2009; 25:13344–13350. [PubMed: 19928937] (b) Jiang XZ, Zhang JY, Zhou YM, Xu J, Liu SY. *J Polym Sci Pol Chem*. 2008; 46:860–871. (c) Oberoi HS, Laquer FC, Marky LA, Kabanov AV, Bronich TK. *Journal of Controlled Release*. 2011; 153:64–72. [PubMed: 21497174] (d) Peng Y, Liu HW, Zhang XY, Liu SY, Li YS. *Macromolecules*. 2009; 42:6457–6462. (e) Wan XJ, Liu T, Liu SY. *Langmuir*. 2011; 27:4082–4090. [PubMed: 21366220] (f) O'Reilly RK, Joralemon MJ, Hawker CJ, Wooley KL. *New J Chem*. 2007; 31:718–724.
8. (a) Albertsson AC, Varma IK. *Biomacromolecules*. 2003; 4:1466–1486. [PubMed: 14606869] (b) Bordes P, Pollet E, Averous L. *Prog Polym Sci*. 2009; 34:125–155. (c) Ha CS, Gardella JA. *Chem Rev*. 2005; 105:4205–4232. [PubMed: 16277374] (d) Okada M. *Prog Polym Sci*. 2002; 27:87–133. (e) Seyednejad H, Gawlitta D, Kuiper RV, de Bruin A, van Nostrum CF, Vermonden T, Dhert WJA, Hennink WE. *Biomaterials*. 2012; 33:4309–4318. [PubMed: 22436798] (f) Sodergard A, Stolt M. *Prog Polym Sci*. 2002; 27:1123–1163. (g) Sokolsky-Papkov M, Agashi K, Olaye A, Shakesheff K, Domb AJ. *Adv Drug Deliver Rev*. 2007; 59:187–206. (h) Tong R, Cheng JJ. *J Am Chem Soc*. 2009; 131:4744–4754. [PubMed: 19281160] (i) Tong R, Yala LD, Fan TM, Cheng JJ. *Biomaterials*. 2010; 31:3043–3053. [PubMed: 20122727] (j) Uhrich KE, Cannizzaro SM, Langer RS, Shakesheff KM. *Chem Rev*. 1999; 99:3181–3198. [PubMed: 11749514] (k) Farokhzad OC, Jon SY, Khademhosseini A, Tran TNT, LaVan DA, Langer R. *Cancer Res*. 2004; 64:7668–7672. [PubMed: 15520166] (l) Sunoqrot S, Bae JW, Pearson RM, Shyu K, Liu Y, Kim DH, Hong S. *Biomacromolecules*. 2012; 13:1223–1230. [PubMed: 22439905] (m) Yu Y, Zou J, Yu L, Ji W, Li YK, Law WC, Cheng C. *Macromolecules*. 2011; 44:4793–4800. (n) Zou J, Yu Y, Yu L, Li YK, Chen CK, Cheng C. *J Polym Sci Pol Chem*. 2012; 50:142–148.
9. Pounder RJ, Dove AP. *Polymer Chemistry*. 2010; 1:260–271.
10. (a) du Boullay OT, Bonduelle C, Martin-Vaca B, Bourissou D. *Chem Commun*. 2008:1786–1788. (b) du Boullay OT, Marchal E, Martin-Vaca B, Cossio FP, Bourissou D. *J Am Chem Soc*. 2006;

- 128:16442–16443. [PubMed: 17177360] (c) Kolitz M, Cohen-Arazi N, Hagag I, Katzhendler J, Domb AJ. *Macromolecules*. 2009; 42:4520–4530. (d) Lu YB, Yin LC, Zhang YF, Zhang ZH, Xu YX, Tong R, Cheng JJ. *Acs Macro Lett*. 2012; 1:441–444. [PubMed: 23359651] (e) Pounder RJ, Fox DJ, Barker IA, Bennison MJ, Dove AP. *Polym Chem-Uk*. 2011; 2:2204–2212.
11. Rostovtsev VV, Green LG, Fokin VV, Sharpless KB. *Angew Chem Int Edit*. 2002; 41:2596–2599.
 12. Chen CJ, Liu GY, Liu XS, Pang SP, Zhu CS, Lv LP, Ji J. *Polym Chem-Uk*. 2011; 2:1389–1397.
 13. Wang DL, Su Y, Jin CY, Zhu BS, Pang Y, Zhu LJ, Liu JY, Tu CL, Yan DY, Zhu XY. *Biomacromolecules*. 2011; 12:1370–1379. [PubMed: 21366351]
 14. Li YL, Zhu L, Liu ZZ, Cheng R, Meng FH, Cui JH, Ji SJ, Zhong ZY. *Angew Chem Int Edit*. 2009; 48:9914–9918.
 15. (a) Chan Y, Wong T, Byrne F, Kavallaris M, Bulmus V. *Biomacromolecules*. 2008; 9:1826–1836. [PubMed: 18564874] (b) Wang YC, Li Y, Sun TM, Xiong MH, Wu JA, Yang YY, Wang J. *Macromol Rapid Comm*. 2010; 31:1201–1206.

Figure 1. ¹H NMR spectra of (a) UCL mPEG-*b*-poly(**1**) and (b) mPEG-*b*-poly(**1**) cross-linked with **2** in DMSO-*d*₆.

Figure 2. Distributions of hydrodynamic diameters of (a) UCL and (b) CCL micelles in water (○) before and (●) after 10-fold dilution with DMF.

Figure 3. Release of NR from CCL micelles with various proportions of cross-linkers **2** and **3** in the presence or absence of DTT at micelle concentrations below the CMC.

Scheme 1.

Preparation of CCL Micelles. I. 4-dimethylaminopyridine, dichloromethane; II. cross-linker 2, CuCl₂, ascorbic acid sodium salt; III. cross-linker 3, CuCl₂, ascorbic acid sodium salt; IV. D,L-dithiothreitol (10 mM), under CMC.

Table 1ROP of Tyr(alkynyl)-OCA (1) by mPEG_{5k}.^a

Entry	[M]/[I]	$M_{n,cal} (\times 10^{-3})$ g/mol) ^b	$M_{n,GPC} (\times 10^{-3})$ g/mol) ^c	M_w/M_n ^c
1	20	9.0	8.5	1.12
2	30	11.1	12.0	1.06
3	50	15.1	16.1	1.02

^aAll reactions were performed in a glovebox at room temperature with mPEG_{5k} (MW = 5000 g/mol) as the macroinitiator and DMAP as the catalyst ([mPEG_{5k}]/[DMAP] = 1/1) in dichloromethane. Monomer conversion was monitored by FTIR analysis of the OCA anhydride peak (1810 cm⁻¹) till it exceeded 95%.

^bCalculated from the M/I with 100% monomer conversion.

^cDetermined by GPC.

Table 2

Properties of UCL and CCL Micelles in Water.

Sample	UCL micelles			CCL micelles			
	Diameter (nm)	PDI	CMC ($\times 10^{-3}$ mg/mL)	Diameter (nm) ^a	PDI ^a	Diameter (nm) ^b	PDI ^b
mPEG _{5k} - <i>b</i> -poly(1) ₂₀	35	0.17	15.9	37	0.22	39	0.20
mPEG _{5k} - <i>b</i> -poly(1) ₃₀	41	0.29	10.3	43	0.24	44	0.26
mPEG _{5k} - <i>b</i> -poly(1) ₅₀	47	0.28	4.8	49	0.30	52	0.27

^a CCL micelles were prepared with **2** as the cross-linker.

^b CCL micelles were prepared with **3** as the cross-linker. The molar ratio of cross-linker to alkynyl group was kept constant at 0.6.