Published in final edited form as:

Biomacromolecules. 2013 April 8; 14(4): 1140–1148. doi:10.1021/bm400019d.

β -Sheet Nanocrystalline Domains Formed from Phosphorylated Serine-Rich Motifs in Caddisfly Larval Silk: A Solid State NMR and XRD Study

J. Bennett Addison^{*,†}, Nicholas N. Ashton[‡], Warner S. Weber[†], Russell J. Stewart[‡], Gregory P. Holland[†], and Jeffery L. Yarger^{*,†}

[†]Department of Chemistry and Biochemistry, Arizona State University, Tempe, Arizona 85287-1604, USA.

[‡]Department of Bioengineering, University of Utah, Salt Lake City, Utah 84112, USA.

Abstract

Adhesive silks spun by aquatic caddisfly (order Trichoptera) larvae are used to build both intricate protective shelters and food harvesting nets underwater. In this study, we use ¹³C and ³¹P solid-state Nuclear Magnetic Resonance (NMR) and Wide Angle X-ray Diffraction (WAXD) as tools to elucidate molecular protein structure of caddisfly larval silk from the species *Hesperophylax consimilis*. Caddisfly larval silk is a fibroin protein based biopolymer containing mostly repetitive amino acid motifs. NMR and X-ray results provide strong supporting evidence for a structural model in which phosphorylated serine repeats (pSX)₄ complex with divalent cations Ca²⁺ and Mg²⁺ to form rigid nanocrystalline β -sheet structures in caddisfly silk. ¹³C NMR data suggests that both phosphorylated serine and neighboring valine residues exist in a β -sheet secondary structure conformation while glycine and leucine residues common in GGX repeats likely reside in random coil conformations. Additionally, ³¹P chemical shift anisotropy (CSA) analysis indicates that the phosphates on phosphoserine residues are doubly ionized, and are charge-stabilized by divalent cations. Positively charged arginine side chains also likely play a role in charge stabilization. Finally, WAXD results finds that the silk is at least 7–8% crystalline, with β -sheet inter-plane spacings of 3.7 and 4.5 Å.

Introduction

Caddisfly larvae (order Trichoptera) spin silk under water. In addition to building nets for food capture, the larvae use the silk to stitch together debris into elaborate structures for protection and camouflage (Figure 1A, 1B).^{1–4} The ability of the silk to adhere to virtually any surface underwater has attracted researchers, as it could serve as a model for new biocompatible water-borne adhesives.^{5,6} Caddisfly silk is not well characterized at the molecular level, however its close relation to the well-studied domesticated silkworm moth (order Lepidoptera) provides a starting point for understanding secondary and tertiary hierarchical structures. The silks produced by the two orders are homologous. On the protein level, both silkworm and caddisfly fibers are composed of heavy chain fibroin (H-fibroin, 250–500 kDa) and light-chain fibroin (L-fibroin, 25 kDa), which are covalently linked in a 1:1 molar ratio through a disulfide bridge.^{7–9} While very different from the sticky sericin layer that coats silkworm silk, caddisfly silk also contains a carbohydrate-rich peripheral

^{*}To whom correspondence should be addressed, bennettaddison@gmail.com; jyarger@gmail.com.

Supporting Information Available

Supporting information is available free of charge via the Internet at <http://pubs.acs.org>.

layer engulfing the fiber.¹⁰ Additional similarities are observed at the amino acid level. Partial H-fibroin primary protein sequences have been determined for both orders, revealing common repetitive stretches including GPXGX, GGX and (SX)_n motifs.^{8,9,11} Repeat regions identified in the partial H-fibroin sequence for the caddisfly species *L. decipiens* have been color-coded and aligned in Figure 2 to illustrate important protein motifs. The prevalent (SX)₄ repeats shown in red and the GGX regions in blue are found in species of each of the three suborders of trichoptera.¹² Comparison of the primary protein sequences reveals that glycine is the most commonly found residue in both fibers, and serine is the second and third most common residue in caddisfly and silkworm silks, respectively.^{10,12} Alanine however, a dominant residue in silkworm silks, is poorly represented in caddisfly silk. This contrast is intriguing because alanine plays an important structural role in silkworm and spider silks.^{13–15}

Another interesting difference is that caddisfly silks contain a substantial amount of phosphorus, an element that is effectively absent from silkworm silks.^{5,12,16} In addition to estimating that nearly 60% of serine residues in caddisfly silk are phosphorylated, a study by Stewart et al.¹² showed that the phosphorylation appears to be localized to the highly conserved (SX)₄ repeat motifs where X residues are typically hydrophobic or basic. In particular, each alternating serine residue in the D-repeat seen in Figure 2 is phosphorylated.¹² The introduction of multiple negatively charged phosphates to (SX)₄ repeat motifs implies an electrostatic-driven structural arrangement. The additional observation that caddisfly silk is relatively high in divalent cations Ca²⁺ and Mg²⁺ led to a proposed model in which alternating phosphorylated serine residues interact with divalent cations to form rigid β -sheet structures in caddisfly silk.¹²

There are many arguments in favor of phosphorylated (SX)₄ motifs forming nanocrystalline β -sheets in caddisfly silks.^{12,17} First, poly(A) and poly(GA) repeat regions are absent from the caddisfly H-fibroin sequence. These motifs are primarily responsible for the impressive mechanical properties of terrestrial silks because they form three-dimensional crystalline β -sheet nanostructures within the fibers.^{13,18,19} Previous X-ray diffraction studies on caddisfly silk fibers suggest a significant crystalline component,^{10,20,21} therefore some repeat regions other than poly(A) or poly(GA) must be responsible for this hierarchical structure. Second, serine residues in the highly prevalent (SX)₄ repeat motifs are heavily phosphorylated. The incorporation of multiple localized negative charges may explain why the silk contains high levels of calcium and magnesium cations.¹² Third, the H-fibroin sequence shows a conserved proline-glycine motif (underlined and bolded in Figure 2) shortly after every (SX)₄ motif.^{8,9} Prolines are often found at the beginning and end of β -strands, and are prevalent in β -turn secondary structures in other well-characterized silks.²² The prevalence and conserved location of proline residues in the caddisfly silk H-fibroin sequence could be explained if (SX)₄ repeat regions formed β -sheet nanostructures. Additionally, valine and isoleucine are often found as the X residue in (SX)₄ motifs. As hydrophobic beta-branched amino acids, the bulkiness of valine and isoleucine near the peptide backbone significantly favors a β -sheet environment as opposed to α -helical secondary structures.^{23,24} Computer modeling of the motif of interest also identified a significant boost in strength when the serines are phosphorylated and when calcium cations are present.²⁵ The introduction of calcium to multi-phosphorylated peptides has been previously shown to induce β -sheet conformations; this mechanism may be relevant to the formation of neurofilament tangles in Alzheimer's disease patients.^{26–28} In caddisfly silk, this molecular arrangement possibly serves as a structural replacement for sheet-forming poly(A) and poly(GA) repeats in spider and silkworm silks. In this study, we put this hypothesis to test by using solid-state NMR and wide angle X-ray diffraction (WAXD) to probe the molecular structure of caddisfly larval silk.

Materials and Methods

Materials

In the late spring, fifth instar larvae of the species *Hesperophylax consimilis* were collected from the upper Red Butte creek in Salt Lake county Utah. The larvae were transported in ice water back to the lab. The animals were kept in 11°C dechlorinated tap water which was filtered and bubbled.

For use as a larval food source, yeast were grown in yeast minimal media (10 g/L ^{13}C -glucose, 0.9 g/L yeast nitrogen base without amino acids, and 2.5 g/L ^{15}N ammonium sulfate). Yeast cells were collected by centrifugation, dried, and used to make food pellets. Food pellets were prepared using 40mg/ml of 300 bloom gelatin and 300mg/ml of dry yeast (^{13}C , ^{15}N) in DI water. This mixture was heated to 100°C and cooled on ice. The resultant food pellet was insoluble in the chilled aquarium water, an important requirement. Fifty caddisfly larvae were removed from their cases and provided 1mm³ blocks of polytetrafluoroethylene (PTFE) as construction material. After 3 days the larvae rebuilt their cases with the PTFE. They were removed from their PTFE cases and placed back into their original stone cases and allowed to feed on the previously prepared food pellet. After three days, the larvae were once again removed from their cases, washed in dechlorinated tap water, introduced into a second aquarium with clean dechlorinated tap water, provided PTFE, and allowed to build for 3 days. The PTFE cases were removed and set aside for future use. The same larvae were placed back in their cases and allowed to feed, starting the cycle over again. This was repeated an additional 9 times resulting in 10 harvesting of PTFE cases. With a pair of fine forceps, the ^{13}C , ^{15}N enriched silk was carefully separated from the PTFE, rinsed in dechlorinated tap water, and stored in tap water at 11°C until further use. For all experiments conducted on naturally-abundant silk, identical harvesting techniques were used except fish food pellets were used for feeding.

Phosphoserine salts were prepared by dissolving L-O-Phosphoserine (Sigma Aldrich) in ultrapure water (EMD), adding equimolar amounts of cation-chloride salts, and adjusting the solution to pH = 7 with NaOH. The solvent was slowly evaporated at room temperature overnight.

Scanning Electron Microscopy

The silk sample was removed from the buffer solution and mounted onto the sample holder with the aid of double-sided carbon tape. It was then Au/Pd coated in a Denton vacuum sputter coater desk II for 180 seconds at a deposition rate of 5 nm/min using a current of 20 milliamps under a pressure of 200 millitorr. This results in a deposition of approximately 15 nm to prevent charging the sample. The SEM was performed using a XL30 Environmental SEM-FEG built by FEI. The secondary electron (SE) detector was used for imaging. Measurements were collected under a vacuum pressure of less than 9×10^{-5} mbar and with a beam current of 5.00 kV. The beam diameter at the sample was 21 Angstroms with a current of 98 pA.

Solid-State NMR

All ^{13}C solid-state NMR experiments were conducted on a 400 MHz Varian Wide-Bore spectrometer equipped with a 3.2 mm triple-resonance MAS probe. The enriched silk was originally packed in its natural (hydrated) environment in a 3.2 mm zirconium rotor fitted with a Torlon cap and drive tip. The sample was spun at the magic angle at 8.5 kHz, a spinning speed chosen such that the carbonyl spinning side band would not overlap with any glycosidic resonances near 75 ppm. ^{13}C chemical shifts were referenced externally to TMS at 0 ppm by setting the downfield adamantane resonance to 38.56 ppm. $^1\text{H} \rightarrow ^{13}\text{C}$ Cross-

Polarization (CP) conditions were matched by using a square 70 kHz contact pulse on the ^{13}C channel, which was matched to the -1 Hartmann-Hahn side band of a 1 ms ramped ($\sim 15\%$) CP spin-lock pulse on the proton channel. Two-pulse phase-modulated²⁹ (TPPM) proton decoupling at 100 kHz was applied during acquisition using a 7° phase angle, and a 5 second relaxation delay separated each of 4096 transients. Direct Detection under Magic Angle Spinning (DD-MAS) experiments were performed using a $3.5\ \mu\text{s}$ $\pi/2$ pulse on the ^{13}C channel, and 20,480 transients were averaged. A fast (1 second) relaxation delay was chosen to highlight resonances with fast relaxation properties. 100 kHz TPPM proton decoupling was applied during acquisition.

Two dimensional ^{13}C - ^{13}C correlation experiments were performed using the Dipolar Assisted Rotational Resonance (DARR) experiment.^{30,31} Assisted transfer of magnetization was established using a continuous wave (CW) radio-frequency pulse on the ^1H channel for 50 ms at the second rotational resonance condition. The acquisition parameters used were 64 scan averages, 2 second recycle delay, 50 kHz spectral width and 1024 complex points collected in the direct dimension, and 25 kHz spectral width and 64 complex points collected in the indirect dimension. 100 kHz TPPM decoupling was applied to the ^1H channel during acquisition.

The $^1\text{H} \rightarrow ^{31}\text{P}$ - ^{13}C double cross-polarization (DCP) experiment was conducted on dry caddisfly silk with a 3.2 mm Varian triple resonance MAS probe.^{32,33} The sample was spun at a slow speed (5 kHz MAS) to favor the zero-quantum transition during the second polarization transfer step.³⁴ The highly sensitive DCP conditions were carefully calibrated using crystalline L-O-Phosphoserine (Sigma Aldrich). The experimental parameters for the initial $^1\text{H} \rightarrow ^{31}\text{P}$ CP step were a $3\ \mu\text{s}$ ^1H $\pi/2$ pulse, a 1 ms ramped ^1H spin-lock pulse centered at 80 kHz radio frequency (rf) field strength, and a ^{31}P square contact pulse matched to the -1 spinning side band of the Hartmann-Hahn profile. Then ^{31}P transverse magnetization was transferred to ^{13}C using a 5 ms ramped spin-lock pulse centered at 80 kHz RF field strength on the ^{31}P channel, and a square contact pulse on the ^{13}C channel matched to the -2 side band of the Hartmann-Hahn profile, during which a 133 kHz continuous wave RF field was applied to the proton channel to ensure that all ^{13}C transverse magnetization was obtained only through nearby ^{31}P nuclei. Two-pulse phase modulated (TPPM) decoupling at 100 kHz RF field strength and 7° phase angle was applied to the ^1H channel during acquisition. Acquisition parameters were 100 kHz spectral width, 2048 complex points, 65,536 scan averages and a 1 second recycle delay.

^{31}P solid-state NMR experiments were conducted on a 400 MHz Bruker Avance III instrument equipped with a 4 mm double resonance MAS probe. ^{31}P chemical shifts were referenced externally to crystalline ammonium phosphate at 0.8 ppm. All samples were spun at the magic angle at 4 kHz. Typical $^1\text{H} \rightarrow ^{31}\text{P}$ CP experiments were performed with a 2 ms CP contact time, 20 ms acquisition time and a 5 second relaxation delay. Static CP spectra were observed using a Hahn spin-echo refocusing period of $20\ \mu\text{s}$. All experiments were collected using 80 kHz TPPM proton decoupling during acquisition. Data Fitting: All ^{31}P chemical shift anisotropy (CSA) parameters were extracted from the spectra according to the Herzfeld-Berger³⁵ convention using DMFIT software.³⁶

Wide Angle X-ray Diffraction

Caddisfly larval silk was mounted onto a cardboard washer for WAXD measurements using a small amount of super glue at either end. WAXD measurements were collected using the synchrotron x-ray research facility at the Advanced Photon Source (APS) at Argonne National Laboratory. The BioCARS beamline 14 BM-C (bending magnet) was used with an approximate x-ray wavelength of 0.9787 angstroms and fixed energy of 12.668 keV. The detector used was the ADSC Quantum-315 with a beam size of approximately $130 \times 340\ \mu\text{m}$

(FWHM). The fiber samples were aligned parallel to the axis of the beamstop with a sample to detector distance of 300 mm and a beamstop to detector distance of 50 mm. Five trials with an exposure time of 60 seconds each were collected per sample with 5 similar backgrounds and then background subtracted to remove air scattering. Cerium dioxide (CeO_2) was used as a calibrant in the FIT2D x-ray processing software to analyze the 2D diffraction patterns.

Results and discussion

Caddisfly larval silk from the species *Hesperophylax consimilis* was studied using solid-state NMR and wide angle X-ray diffraction, and all experimental results refer to data collected on this species. *H. consimilis* larvae utilize silk to construct protective casings from available debris, as seen in Figure 1A and 1B. Unlike the cylindrical silk fibers produced by spiders, caddisfly fibers appear in the SEM micrograph as a fusion of two fibers into a flat ribbon (Figure 1C). The protein-based biopolymer is composed of both H and L-fibroin protein. The H-fibroin sequence is not described in the literature for the species *H. consimilis*, thus the partial H-fibroin sequence for the closely related species *L. decipiens* is shown in Figure 2. Repetitive (SX)₄ motifs illustrated in Figure 2 have been identified in multiple caddisfly species through gene sequencing,^{8,9} and tandem Mass-Spectrometry data on silk from *H. consimilis* larvae confirm that identical repeat sequences seen in Figure 2 are present in the *H. consimilis* H-fibroin protein.¹² As previously mentioned, one striking observation is the apparent lack of poly(A) and poly(GA) repeat motifs found in silkworm H-fibroin sequences. Instead, heavily phosphorylated runs of (SX)₄ highlighted in red are a dominant repetitive motif found in caddisfly silk.

Solid-State NMR on Caddisfly Silk

In order to investigate the molecular structure of caddisfly silk and any links to the primary protein sequence, both ^{13}C and ^{31}P solid-state NMR techniques were utilized. $^1\text{H} \rightarrow ^{13}\text{C}$ CP-MAS spectra for naturally-abundant caddisfly silk exhibits relatively poor signal to noise, as seen in Figure 3, thus advanced analysis of the silk is difficult to impossible without isotopic enrichment. Caddisfly larvae were fed with (^{13}C , ^{15}N) yeast, and the resulting silk was collected and analyzed. The signal to noise ratios observed for the naturally-abundant and enriched silks were used to estimate the amount of isotopic enrichment at 6 to 8% (Supplemental Figure 2). ^{13}C NMR data from isotopically enriched caddisfly silk are shown in Figure 4. The data was collected with the silk hydrated in the same water from which it was obtained, therefore preserving its native environment. Many overlapping resonances make interpretation and chemical shift assignments challenging, but some information can nevertheless be extracted from the $^1\text{H} \rightarrow ^{13}\text{C}$ CP-MAS and DD-MAS spectra in Figure 4. The assortment of resonances near 75 ppm and 105 ppm are characteristic of carbohydrates, and are assigned to a carbohydrate-rich surface coating of the silk. Consistent with this assignment, TEM micrograph images obtained from histological sections of the fibers show a clear peripheral carbohydrate layer.¹⁰ Spider silks are also thought to have peripheral surface coatings, but the proposed lipid and/or carbohydrate layer of spider silk is only 10–100 nm thick.³⁷ This makes the overall mole percentage small and therefore hard to detect using solid-state NMR. While the surface of spider silk fibers is smooth, atomic force micrographs of caddisfly silks show small (~150 nm) spherical subunits.^{17,25} The lumpy topography of the caddisfly silk surface provides additional contact area for adhering to surfaces due to an increased area-to-volume ratio. The contrast between the CP and DD-MAS experiments in Figure 4 is useful because resonances that exist in a mobile, water-solvated environment will typically show short T_1 relaxation times relative to rigid regions. Hydrated residues therefore exhibit enhanced signal intensity in the DD-MAS spectrum when using short (1 second) recycle times.

Additionally, sharpened signals are observed for hydrated residues due to the longer T_2 relaxation times. The contrast between unmodified and phosphorylated serine $C\beta$ resonances at 62 and 64 ppm, respectively, is a very significant result. When comparing the $^1H \rightarrow ^{13}C$ CP-MAS spectrum to the DD-MAS spectrum, one notices that the degree of sharpening is significantly more pronounced for unmodified serine $C\beta$, suggesting higher mobility. This supports the idea that phosphorylated serine residues reside in nanocrystalline β -sheet structures while unmodified serine residues are found in less rigid secondary structures. This is a commonly observed phenomenon when studying wet spider silks to show differences between rigid and mobile motifs. In spider silks, the alanine $C\beta$ resonance at 21 ppm associated with rigid poly(A) β -sheet regions is strongly observed during CP but has significantly reduced signal when using DD-MAS techniques with a fast relaxation delay because of its long T_1 relaxation time.^{38,39} Conversely, alanine in a disordered helical conformation exhibits short T_1 and long T_2 relaxation times. As a result, narrowed line widths are observed for the mobile alanine environments in the DD-MAS experiment on wet spider silks.

Interpretation of the one-dimensional (1D) solid-state NMR data is limited because of the many overlapping resonances. In order to extract accurate chemical shifts for specific amino acid resonances in caddisfly silk, two dimensional (2D) ^{13}C - ^{13}C correlation NMR was necessary. The chemical shifts of amino acid backbone and side-chain resonances are very sensitive to secondary structure, and can be used to identify helical, turn and β -sheet components of a protein.⁴⁰⁻⁴⁴ Figure 5 shows expanded regions of a ^{13}C - ^{13}C Dipolar Assisted Rotational Resonance (DARR) experiment using 50 ms mixing time. Off-diagonal cross peaks resulting from magnetization exchange between ^{13}C nuclei can be observed. The strong signals observed from glycine, valine, leucine and isoleucine residues are assigned and are compared to known chemical shifts from the literature (Table 1). The glycine $C\alpha$ -CO correlation seen in Figure 5A is fairly strong, allowing for accurate chemical shift measurements. Both chemical shift values for glycine $C\alpha$ and CO agree nearly perfectly with an average random coil conformation, suggesting that a large range of backbone dihedral angles are available such that glycine does not adopt any identifiable secondary structure in caddisfly silk. Leucine residues are also often seen in GGX repeats, and assigned chemical shifts again agree with a random coil conformation. The data does not necessarily mean that there is no secondary structure in this region. Fast dynamic averaging may play a role, and the chemical shifts of many helical conformations overlap with random coil shifts. Interestingly, glycine-heavy GGX motifs are well known for forming 3_1 -helical structures in spider and silkworm silks.⁴⁵⁻⁴⁷ 3_1 -helical structures may indeed be prevalent in caddisfly fibers, but the current NMR data better supports a random coil configuration or very loose helical structure. Conversely, the ^{13}C chemical shifts extracted for valine resonances prevalent in (SX)₄ motifs seem to agree with β -sheet secondary structure. Fortunately, the off-diagonal cross peaks observed for valine are sufficiently strong even though it only accounts for approximately 4% of the total amino acid content.¹²

Although expected to make up a large percentage (~15%) of the total amino acid content in caddisfly silk, the chemical shifts for serine and phosphoserine cannot confidently be extracted from the 2D ^{13}C - ^{13}C correlation NMR experiment. This is possibly a result of inconsistent isotope uptake and/or metabolism between various amino acids; it is clear from Figure 3 that isotopic enrichment is not the same for all amino acids. Selective enrichment of amino acids in spider silks has been challenging even when only a single enriched amino acid is provided, thus we cannot expect consistent isotopic uptake when feeding labeled yeast extract to the caddisfly larvae.⁴⁸ Confidently identifying phosphoserine chemical shifts would be exceptionally useful towards supporting or opposing the proposed model. We therefore used a $^1H \rightarrow ^{31}P$ - ^{13}C double cross polarization (DCP) experiment to selectively

observe ^{13}C nuclei that are in dipolar contact with ^{31}P nuclei. Figure 6 compares ^{13}C NMR spectra of dried caddisfly silk under standard CP conditions (red) and under DCP conditions (black) at 5 kHz MAS. The silk in this experiment had been dried and therefore no longer in its natural environment. Nonetheless, ^{13}C NMR data (Supplemental Figure 3) suggests that the silk is structurally identical before dehydration and after re-hydration, thus no structural changes occur upon dehydration. The DCP experiment confirms that serine is in fact phosphorylated, and selects the phosphoserine $\text{C}\alpha$ and $\text{C}\beta$ chemical shifts. The values for phosphoserine $\text{C}\alpha$ and $\text{C}\beta$ are listed in Table 1. Comparison to chemical shifts listed in the literature reveals that the caddisfly silk phosphoserine $\text{C}\alpha$ resonance is shifted upfield and $\text{C}\beta$ downfield with respect to random coil. This observed trend is indicative of a β -sheet secondary structure, therefore the data is in agreement with a sheet-based model for $(\text{pSX})_4$ motifs in caddisfly silk.

The DCP experiment revealed additional useful information towards understanding the molecular structure of caddisfly silk. Arginine side chain resonances, especially those closer to the positively charged guanidinium group, are also observed in the DCP experiment. This suggests that arginine residues play a significant role in stabilizing negatively charged phosphate groups in caddisfly silk. While the arginine assignments listed in Table 1 align with random coil conformations, it should be noted that distant side chain resonances are not very sensitive to secondary structure and therefore should not be used here to suggest local environments.⁴² The DCP experiment also suggests that tyrosine may be phosphorylated in caddisfly silks. Secondary structure motifs involving phosphotyrosine may be prevalent in caddisfly silks, but selective isotopic labeling of tyrosine may be necessary before a full investigation would be possible.

$^1\text{H} \rightarrow ^{31}\text{P}$ cross-polarization NMR data also provided important structural information about caddisfly silk. In liquid state NMR, molecular motion is sufficiently fast to average out chemical shielding information. However in solid samples where molecular motion is limited, the chemical shielding tensor is not averaged over the spatial dimensions and can therefore yield important information on the local environment about a nucleus. Understanding the phosphorus environment in caddisfly silk would be substantially helpful towards characterizing the phosphorylated $(\text{SX})_4$ motifs. Here we use solid-state NMR techniques to extract environment-dependent Chemical Shift Anisotropy (CSA) information for the ^{31}P nuclei found in caddisfly silk. Using $^1\text{H} \rightarrow ^{31}\text{P}$ cross-polarization NMR with and without magic angle spinning, CSA parameters were extracted from caddisfly silk and from four preparations of phosphorylated serine (Figure 7 and Table 2) using the Herzfeld-Berger convention.³⁵ The data are shown in blue, and the resulting fits in red. The first and most evident finding is that caddisfly silk observes a negative skew parameter; the CSA is asymmetric favoring the right. This is consistent with trends observed by C. Gardien et al. in which the phosphate on L-O-Phosphoserine is doubly ionized.⁴⁹ This point is exemplified when comparing the caddisfly spectra to the CSA pattern of protonated L-phosphoserine from Sigma Aldrich. The presence of cations near the phosphorus resonance can also affect the CSA pattern,⁵⁰ so de-protonated phosphoserine was prepared in the presence of calcium, magnesium and sodium cations. Extracted CSA parameters, summarized in Table 2, reveal that divalent cations calcium and magnesium behave virtually identically in terms of their interaction with phosphoserine. Sodium appears to significantly increase the σ_{33} parameter and in turn the $\Delta\sigma$ and span values. Additionally, the isotropic ^{31}P chemical shift moves downfield in the presence of sodium when compared to the spectra with calcium or magnesium. Molecular level reasoning for the observed differences are not clear; necessary computer simulations of the CSA have not yet been performed. Nevertheless, comparison of all determined CSA parameters shows that the phosphorus environment of caddisfly silk is most similar to that of phosphoserine in the

presence of divalent cations. This observation is consistent with (pSX)₄ repeat motifs in divalent cation-phosphoserine β -sheet structures.

WAXD on Caddisfly Silk

The 2D wide-angle X-ray diffraction (WAXD) pattern on a vertically aligned caddisfly silk bundle is seen in Figure 8. The blue diffraction band shows increased intensity along the equatorial plane, an observation consistent with β -sheet nanocrystals aligned parallel to the fiber axis.^{51,52} Although not as intense as the diffraction patterns observed for spider and silkworm silks, which can be greater than 25% crystalline,^{52–54} the observed pattern for caddisfly silk suggests the presence of a significant crystalline component. The percent of silk fibroin protein in a crystalline conformation was estimated from the data, and inter-plane distances were extracted. Radial integration finds that repeat spacings of 3.7 and 4.5 angstroms are observed in increased intensity along the equatorial plane (Figure 9). The peak positions were obtained by using four Gaussian fits, one at 3.7 angstroms, one at 4.5 angstroms and 2 broader Gaussians for the remainder of the data. If the repetitive unit cell of the crystalline region is orthorhombic, as assumed for spider and silkworm silks, we can assign the 4.5 angstrom reflection to inter-sheet spacings because it is analogous to the reflections observed from poly(A) nanocrystalline β -sheet regions in both spider and silkworm silks.^{51,52,55} An additional equatorial reflection at 3.7 angstroms is seen in the caddisfly fiber diffraction pattern, however we cannot confidently identify its source. Interestingly, unpublished WAXD results from black widow egg sac fibers show a similar reflection near 3.7 angstroms that also has not been assigned. The crystallite unit in caddisfly silk seems to be vastly different than those observed in other biological fibers, thus we are not entirely surprised that we cannot yet fully interpret and assign the diffraction pattern. We have current efforts to collect better, higher-resolution diffraction data on caddisfly silk, and are working on solving the dimensions of the repetitive unit cell. Nevertheless, in this present study it is sufficient to state that the equatorial reflections clearly demonstrate that caddisfly silk contains crystalline regions oriented with respect to the fiber axis.

The amount of crystallinity was estimated in two different ways. First, radial integration of 15 degrees on either side of the equator, the region assumed to be the component relating to crystallinity, is compared to radial integration occurring at 45 degrees from the equator and the meridian integration. Subtracting the total integration of the amorphous halo from the equatorial integration gives the component thought to be crystalline, yielding approximately 7–8% crystallinity (Supplemental Figure 1). Secondly, integration along an angle of 45 degrees, the equator, and the meridian yields differing intensities of the shoulder at 3.7 angstroms. The equatorial integration was selected to determine the peak position based on maximum intensity. A Gaussian fitting protocol was used to determine peak positions and intensity integrations iteratively until there were no changes. The peak positions were then held constant and the remaining integration areas were fit. These results show 7% crystallinity based on integration of the full WAXD pattern (Supplemental Figure 1). We note here that each silk fiber in the bundle could not be perfectly aligned vertically along the beam axis, thus 7–8% crystallinity is likely a low estimate; previous WAXD results estimated 12% crystallinity for caddisfly silk from the species *S. marmorata*.²¹ Regardless, the absence of poly(A) or poly(GA) motifs from the H-fibroin primary protein sequence in caddisfly silk means that the observed crystallinity must come from some other hierarchical structure.

Figure 10 shows an illustration of the proposed structural motif, in which negatively charged phosphorylated serine residues from (pSX)₄ repeat regions complex with divalent cations to form β -sheet structures in caddisfly silk.¹² A 2-dimensional sheet is formed when the repeats extend both above and below the illustration in Figure 10, stabilized by hydrophobic

Van der Waals interactions between the larger valine and isoleucine side chains. If one additionally imagines standard backbone hydrogen bonding with (pSX)₄ motifs both towards and away from the reader, 3-dimensional crystalline blocks are created. Phosphorylated (SX)₄ repeats in caddisfly silk therefore likely serve as a structural replacement for poly(A) and poly(GA) crystalline β -sheet structures found in spider and silkworm fibers.

Caddisfly silk is a very complicated and imperfectly understood material. We can only speculate if and how the described (pSX)₄ nanostructure contributes to the adhesive properties of the caddisfly silk fiber. The mechanisms with which the fibers adhere to debris underwater is not the subject of this paper, although electrostatic interactions between charged residues and surfaces may play an important role. While we argue that the phosphorylated (SX)₄ repeats in caddisfly silk are incorporated into nanocrystalline β -sheet regions within the silk fibers, perhaps some of these charged repeats remain available for surface binding.

Conclusions

Phosphorylated (SX)₄ repeats in Trichopteran silks were recently suggested as a structural replacement for the β -sheet-forming poly(GA) motifs found in Lepidopteran silks.¹² Here we have presented solid-state NMR and WAXD results on caddisfly larval silk. X-ray diffraction data identifies a significant (at least 7–8%) crystalline component, with an inter-sheet distance of 4.5 angstroms. Solid-state NMR was used to probe the composition of both the crystalline and amorphous domains. Conformation-sensitive ¹³C chemical shifts were identified from ¹³C-¹³C DARR and ¹H-³¹P-¹³C DCP NMR. Chemical shifts from many amino acids, including glycine, leucine, valine, serine and phosphoserine, are compared to the chemical shifts from model peptides with known secondary structures. The data indicates that both valine and phosphoserine residues, commonly found in (pSX)₄ repeat regions, likely exist in β -sheet rich environments. The contrast between the ¹³C CP-MAS and DD-MAS spectra on hydrated silk additionally suggests that phosphorylated serine exists in a less mobile environment than unmodified serine, further supporting the idea of rigid calcium-phosphoserine regions. Glycine and leucine residues however, often seen in GGX repeats, exist predominantly in a random or disordered conformation. ³¹P Chemical Shift Anisotropy (CSA) data was extracted from caddisfly silk and from different preparations of L-O-Phosphoserine. The CSA parameters summarized in Table 2 support a structural motif in which divalent cations Ca²⁺ and Mg²⁺ complex with negatively charged phosphoserine residues.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The Department of Defense Air Force Office of Scientific Research (AFOSR) under Award No. FA9550-10-1-0275 and the National Science Foundation, Division of Materials Research under Award No. DMR-0805197 supported this work. Use of the Advanced Photon Source was supported by the U.S. Department of Energy, Basic Energy Sciences, Office of Science, under Contract No. DE-AC02-06CH11357 and DOE-EPSCoR under contract number DE-SC0004791. Use of the BioCARS Sector 14 was supported by the National Institutes of Health, National Center for Research Resources, under grant number RR007707. Prof. Russell Stewart would like to acknowledge funding from the U.S. Army Research Office, Life Sciences Division. We would like to thank Dr. Brian Cherry for his help with NMR experiments, and both the Magnetic Resonance Research Center and LeRoy Eyring Center for Solid State Science at Arizona State University for NMR and SEM instrumentation, respectively.

References

1. Kjer KM, Blahnik RJ, Holzenthal RW. *Zoologica Scripta*. 2002; 31:83–91.
2. Morse JC. Annual review of entomology. 1997; 42:427–450.
3. LaFontaine, G. Caddisflies. The Lyons Press; 1989.
4. Wiggins, GB. The caddisfly family Phryganeidae (Trichoptera). University of Toronto Press Incorporated; 1998.
5. Stewart RJ, Wang CS, Shao H. *Advances in Colloid and Interface Science*. 2011; 167:85–93. [PubMed: 21081223]
6. Brubaker CE, Messersmith PB. *Langmuir*. 2012; 28:2200–2205. [PubMed: 22224862]
7. Shimura K, Kikuchi A, Ohtomo K, Katagata Y, Hyodo A. *The Journal of Biochemistry*. 1976; 80:693–702.
8. Yonemura N, Sehnal F, Mita K. *Biomacromolecules*. 2006; 7:3370–3378. [PubMed: 17154465]
9. Yonemura N, Mita K, Tamura T, Sehnal F. *Journal of molecular evolution*. 2009; 68:641–653. [PubMed: 19449053]
10. Engster MS. *Cell and Tissue Research*. 1976; 169:77–92. [PubMed: 1277288]
11. Sehnal F, Zurovec M. *Biomacromolecules*. 2004; 5:666–674. [PubMed: 15132645]
12. Stewart RJ, Wang CS. *Biomacromolecules*. 2010; 11:969–974. [PubMed: 20196534]
13. Marsh RE, Corey RB, Pauling L. *Biochimica et Biophysica Acta*. 1955; 16:1–34. [PubMed: 14363226]
14. Rathore O, Sogah DY. *J. Am. Chem. Soc.* 2001; 123:5231–5239. [PubMed: 11457385]
15. Simmons A, Ray E, Jelinski L. *Macromolecules*. 1994; 27:5235–5237.
16. Chen W-Q, Priewalder H, Pradeep John JP, Lubec G. *PROTEOMICS*. 2010; 10:369–379. [PubMed: 20029844]
17. Ashton NN, Taggart DS, Stewart RJ. *Biopolymers*. 2012; 97:432–445. [PubMed: 21953029]
18. Altman GH, Diaz F, Jakuba C, Calabro T, Horan RL, Chen J, Lu H, Richmond J, Kaplan DL. *Biomaterials*. 2003; 24:401–416. [PubMed: 12423595]
19. Lotz B, Cesari FC. *Biochimie*. 1979; 61:205–214. [PubMed: 465571]
20. Tsukada M, Khan M, Inoue E, Kimura G. *International Journal of Biological Macro-molecules*. 2010; 46:54–58.
21. Wang Y, Sanai K, Wen H, Zhao T. *Molecular biology reports*. 37:2885–2892. [PubMed: 19842062]
22. Creager MS, Butler EB, Lewis RV, Yarger JL, Holland GP. *Chemical Communications*. 2010; 46:6714–6716. [PubMed: 20733981]
23. Williams RW, Chang A, Juretić D, Loughran S. *Biochimica et Biophysica Acta*. 1987; 916:200–204. [PubMed: 3676331]
24. Johansson J, Nerelius C, Willander H, Presto J. *Biochemical and biophysical research communications*. 2010; 402:515–518. [PubMed: 20971069]
25. Strzelecki JW, Strzelecka J, Mikulska K, Tszydel M, Balter A, Nowak W. *Central European Journal of Physics*. 2011; 9:482–491.
26. Lang E, Szendrei GI, Elekes I, Lee VM-Y, Otvos L Jr. *Biochemical and biophysical research communications*. 1992; 182:63–69. [PubMed: 1731800]
27. Hollosi M, Urge L, Perczel A, Kajtar J, Teplan I, Otvos J, Fasman GD. *Journal of Molecular Biology*. 1992; 223:673–682. [PubMed: 1542114]
28. Holly S, Laczko I, Fasman GD, Hollosi M. *Biochemical and biophysical research communications*. 1993; 197:755–762. [PubMed: 8267612]
29. Bennett AE, Rienstra CM, Auger M, Lakshmi KV, Griffin RG. *The Journal of Chemical Physics*. 1995; 103:6951.
30. Takegoshi K, Nakamura S, Terao T. *Chemical Physics Letters*. 2001; 344:631–637.
31. Takegoshi K, Nakamura S, Terao T. *The Journal of Chemical Physics*. 2003; 118:2325–2341.
32. Schaefer J, McKay RA, Stejskal EO. *Journal of Magnetic Resonance*. 1979; 34:443–447.
33. Stejskal EO, Schaefer J, McKay RA. *Journal of Magnetic Resonance (1969)*. 1984; 57:471–485.

34. Ciesielski W, Kassassir H, Potrzebowski MJ. Solid State Nuclear Magnetic Resonance. 2011; 39:151–157. [PubMed: 21440422]
35. Herzfeld J, Berger AE. Journal of Chemical Physics. 1980; 73:6021–6030.
36. Massiot D, Fayon F, Capron M, King I, Le Calvé S, Alonso B, Durand JO, Bujoli B, Gan Z, Hoatson G. Magnetic Resonance in Chemistry. 2002; 40:70–76.
37. Hardy JG, Scheibel TR. Journal of Polymer Science Part A: Polymer Chemistry. 2009; 47:3957–3963.
38. Yang Z, Liivak O, Seidel A, LaVerde G, Zax D, Jelinski L. J. Am. Chem. Soc. 2000; 122:9019–9025.
39. Holland GP, Jenkins JE, Creager MS, Lewis RV, Yarger JL. Biomacromolecules. 2008; 9:651–657. [PubMed: 18171016]
40. Shoji A, Ozaki T, Saito H, Tabeta R, Ando I. Macromolecules. 1984; 17:1472–1479.
41. Asakura T. Protein Science. 2002; 11:2706–2713. [PubMed: 12381852]
42. Kricheldorf HR, Mueller D. Macromolecules. 1983; 16:615–623.
43. Wishart D, Bigam C, Holm A, Hodges R, Sykes B. Journal of biomolecular NMR. 1995; 5:67–81. [PubMed: 7881273]
44. Bienkiewicz EA, Lumb KJ. Journal of biomolecular NMR. 1999; 15:203–206. [PubMed: 10677823]
45. Asakura T, Yang M, Kawase T, Nakazawa Y. Macromolecules. 2005; 38:3356–3363.
46. van Beek JD. Proceedings of the National Academy of Sciences. 2002; 99:10266–10271.
47. Holland GP, Creager MS, Jenkins JE, Lewis RV, Yarger JL. J. Am. Chem. Soc. 2008; 130:9871–9877. [PubMed: 18593157]
48. Creager MS, Izdebski T, Brooks AE, Lewis RV. Comparative Biochemistry and Physiology-Part A: Molecular & Integrative Physiology. 2011
49. Gardiennet-Doucet C, Assfeld X, Henry B, Tekely P. The Journal of Physical Chemistry A. 2006; 110:9137–9144. [PubMed: 16854026]
50. Duncan TM, Douglas DC. Chemical Physics. 1984; 87:339–349.
51. Warwicker JO. Journal of Molecular Biology. 1960; 2:350–362. [PubMed: 13783274]
52. Sampath S, Isdebski T, Jenkins JE, Ayon JV, Henning RW, Orgel JPRO, Antipoa O, Yarger JL. Soft Matter. 2012; 8:6713–6722. [PubMed: 23569461]
53. Liu Y, Shao Z. Biomacromolecules. 2008; 9:1782–1786. [PubMed: 18529075]
54. Hu X, Kaplan D, Cebe P. Macromolecules. 2006; 39:6161–6170.
55. Riekkel C, Bränden C, Craig C, Ferrero C, Heidelbach F, Müller M. International Journal of Biological Macromolecules. 1999; 24:179–186. [PubMed: 10342763]

Figure 1.

H. Fibroin

D: V **SISRSVSI**ERIVT **PG**VYTKI **SRSSSVSV**EGGRRR **GP**WGYGRG
 E: LSGSGDLDGL **GGVGG**L**GG**L**GG**L**GG**RR **GP**WGRGYG
 F: SSGTVSVSVSVSEEGRRR **GP**WGRRGK
 D: V **SISRSVSI**ERIVT **PG**VYTQI **SRSSSVSV**EGGRRR **GP**WGRGYG
 F: PTGSVSVSVSVSEEGRRR **GP**WGYGRRLGG
 E: LSGSGDLDGL **GGVGG**L**GG**L**GG**L**GG**RR **GP**WVRGYG
 F: SSVSVSVSVSEEGRRR **GP**WGRGK
 D: V **SISRSGSI**ERIVT **PG**VYTKI **SRSSSVSV**EGGRRR **GP**WGRGYG
 F: SSGSVSVSVSEEGRRR **GP**WGRRGK
 D: V **SISRSVSI**ERIVT **PG**IYTKI **SRSSSVSV**EGGRRR **GP**WGYGRG
 E: LGGLSGSGDLDGL **GGVGG**L**GG**L**GG**L**GG**RR **GP**WGRGYG
 F: SSGSVSVSLSEGGVRRR **GP**WGRRGK
 D: V **SISRSVSI**ERIVT **PG**SYSKI **SRSSSVSV**EGGIRR **GP**WGR

Figure 2.

Figure 3.

Figure 4.

Figure 5.

Figure 6.

Figure 7.

Figure 8.

Figure 9.

Figure 10.

Table 1

^{13}C chemical shifts observed from caddisfly silk are compared to shifts from model polypeptides with known secondary structures.^{40–44} Caddisfly silk chemical shifts were extracted from either the ^{13}C - ^{13}C DARR experiment (Figure 6) or the DCP experiment (Figure 7). Only assignments that could be made with any confidence are listed. All values are relative to TMS at 0 ppm.

Residue	Caddisfly silk	β -sheet	α -helix	random coil
Gly C=O	173.5	171.8	174.9	173.2
Gly C α	43.3	42.0	46.0	43.4
Ile C=O		172.7	174.9	174.7
Ile C α	58	57.8	63.9	59.4
Ile C β		39.4	34.8	37.1
Ile C γ 1	16			15.7
Ile C γ 2				25.5
Ile C δ	12.1			11.2
Leu C=O		170.3	175.7	175.9
Leu C α	53.8	50.5	55.7	53.4
Leu C β	40.1	43.3	39.5	40.7
Ser C=O		172.9	174.6	171.5
Ser C α	56.3	55.2	59.2	56.6
Ser C β	62	63.1	60.7	62.1
p-Ser C=O				174.2
p-Ser C α	54.8			56.8
p-Ser C β	64.3			63.9
Val C=O	173.7	171.8	174.9	174.6
Val C α	59	58.4	65.5	60.5
Val C β	32.7	32.4	28.7	31.2
Arg C γ	25.1			25.1
Arg C δ	41.7			41.7
Arg C ϵ	157 – 159			157.9

Table 2

³¹P Chemical Shift Anisotropy parameters have been extracted from each spectra in Figure 7 using DMFIT software.³⁶ The negative skew parameter is indicative of a phosphate carrying a -2 charge. σ^{33} parameter changes significantly for monovalent versus divalent cations. The CSA parameters obtained from caddisfly silk are most similar to those from phosphoserine in complex with divalent cations. Using the Herzfeld Berger convention, the span (span = The σ^{11} - The σ^{33}) describes the breadth of the spectrum, while the skew (skew = $3(\sigma^{22} - \sigma^{iso})/\text{span}$) describes the axial symmetry of the CSA tensor.³⁵

Sample	Δ (ppm)	η	σ^{11} (ppm)	σ^{22} (ppm)	σ^{33} (ppm)	span (ppm)	skew	σ^{iso} (ppm)
Caddisfly, Static	50.01	0.39	-32.88	-13.48	51.84	84.72	-0.54	1.83
Caddisfly, MAS	58.36	0.54	-43.38	-11.9	59.89	103.27	-0.39	1.54
P-Ser + CaCl ₂ , Static	62.3	0.29	-39.11	-20.98	63.4	102.51	-0.65	1.10
P-Ser + CaCl ₂ , MAS	65.05	0.4	-44.91	-18.59	65.83	110.74	-0.52	0.78
P-Ser + MgCl ₂ , Static	62.26	0.28	-39.54	-22.23	62.51	102.05	-0.66	0.25
P-Ser + MgCl ₂ , MAS	64.34	0.38	-44.08	-19.4	64.77	108.85	-0.55	0.43
P-Ser + 2NaCl, Static	71.03	0.24	-38.64	-21.35	76.56	115.2	-0.7	5.52
P-Ser + 2NaCl, MAS	71.59	0.4	-44.41	-15.9	77.23	121.64	-0.53	5.64
P-Serine, Static	-55.35	0.92	52.86	2.02	-55.58	108.44	0.06	-0.23
P-Serine, MAS	-56.54	0.92	54.08	2.29	-56.63	110.71	0.06	-0.09