Published in final edited form as:

Phys Chem Chem Phys. 2013 May 14; 15(18): . doi:10.1039/c3cp51071a.

Recovering degraded quasi-solid-state dye-sensitized solar cells by applying electrical pulses

Xi Zhang^a, Xuezhen Huang^a, and Hongrui Jiang^{a,b}

Hongrui Jiang: hongrui@engr.wisc.edu

^aDepartment of Electrical and Computer Engineering, University of Wisconsin-Madison, Madison, WI, 53706, USA. Fax: 608-262-1267; Tel: 608-265-9418

^bMaterials Science Program, University of Wisconsin-Madison, Madison, WI, 53706, USA

Abstract

We discovered a method of applying forward pulsed bias to recover the degradation of quasi-solid-state dye-sensitized solar cells (DSSCs). Up to 30.7% of the power conversion efficiency (η) of a degraded poly (vinylidene fluoride) (PVDF) based DSSC was recovered by a double-pulse. The recovered η remained higher than that before the double-pulse treatment for at least 28 days. It is deduced that the blocking of ion-transport channels in the quasi-solid-state electrolyte causes degradation of the DSSCs. This study will shed light on the efficiency enhancement and long-term stability of quasi-solid-state DSSCs.

1. Introduction

Dye-sensitized solar cells (DSSCs) have attracted tremendous attention in recent years, because of its low cost and high efficiency.¹⁻³ The DSSCs with highest power conversion efficiency (η) are based on liquid electrolytes, and the recently reported efficiency was over 12%.⁴ However, the liquid electrolytes limit the long-term stability of DSSCs. Much effort has been made to replace the liquid electrolytes by solid-state materials, including inorganic hole conductors/p-type semiconductors,⁵⁻⁷ organic hole conductors,⁸⁻¹¹ nano-composite materials,^{12,13} and gel and polymer electrolytes.¹⁴⁻¹⁷ Among these materials, polymer electrolytes have obtained growing interests from the perspective of practical applications owing to their excellent characteristics such as easy fabrication, low cost, good stability and flexibility.¹⁸⁻²⁰ The stability is a crucial issue for the commercial use of such DSSCs. Nevertheless, very few studies have been on the stability and degradation mechanisms of these cells. There is still no report on the recovery of degraded DSSCs. Hence the study of the degradation mechanism and exploring methods to solve the problem are of great significance.

In this study, a proper pulsed electrical bias (around 2.5 V) is applied to poly (vinylidene fluoride) (PVDF) based DSSCs to force the redistribution of triiodide (I_3^-) and iodide (I^-) in the electrolyte. Usually such kind of pulses could cause damage to DSSCs, since a voltage which is much greater than the open-circuit voltage (V_{oc}) could induce a large dark current. Nonetheless, if the pulse width is well controlled, the damage could be avoided. We have found that the efficiency of a degraded solid DSSC could be significantly recovered without damage to the cell after a proper positive double-pulse due to the recovery in the short-circuit photocurrent density (J_{sc}). Such recovery could last in atmosphere in dark for a long period, at least 28 days. This pulsed-bias method could be practically applied in the actual

usage of DSSCs. Furthermore, the recovery of degraded DSSCs by this method also indicates that the blocking of the diffusion of I^-/I_3^- in such quasi-solid-state electrolyte is a key factor of the degradation mechanism.

2. Experimental

2.1. DSSC fabrication

8- μm -thick TiO_2 films were fabricated on conductive fluorine-doped tin oxide (FTO; resistance: 12~14 Ω/square ; transmittance: 82%~84%; MTI Co., USA) glass substrates using a screen printing method²¹ with a paste consisting of 15~20 nm TiO_2 particles (SOLARONIX, Ti-Nanoxide T/SP, Switzerland). The area of the active region on the FTO glass was 0.12 cm^2 . After sintering at 500°C for 1 h, a 2- μm -thick TiO_2 scattering layer composed of 50~100 nm TiO_2 particles (SOLARONIX, Ti-Nanoxide R/SP, Switzerland) was deposited. The films were subsequently sintered again at 500°C for 1 h before being dipped into 0.05 M TiCl_4 aqueous solution at 70°C for 30 min, followed by calcinations at 450°C for 30 min to stain the TiO_2 films. The TiCl_4 -pretreated films were cooled down to 120°C before being soaked into the dye solutions (0.3mM N719 in acetonitrile/tertbutanol, v/v = 1:1) for 24 h. The counter electrode was Pt-coated FTO with two drilled holes for filling the electrolyte. Pt layer was deposited on the FTO glass by an electrodeposition process in H_2PtCl_6 solution (0.5 M). A 25- μm -thick surlyn (SOLARONIX, Switzerland) film was used as a spacer between the photoelectrode and the counter electrode for each DSSC. The redox electrolyte contained 0.1 M LiI, 0.05 M I_2 , 0.6 M 1,2-dimethyl-3-propylimidazolium iodide, and 2 wt% PVDF (Kynar 301F, $M_w = 3.8 \times 10^5$) using acetonitrile/ dimethyl sulfoxide (v:v = 4:1) as solvent. The electrolyte solution was repeatedly injected into the space between the photoelectrode and the counter electrode and dried on a hot plate at 40°C until the porous nano- TiO_2 was fully filled and the solvent was sufficiently removed. Three quasi-solid-state DSSCs were fabricated and tested in this study: C1, C2, and C3. Only for C1, the two holes were sealed with the surlyn film and a glass slide by heating. C2 and C3 were not sealed to accelerate their degradation.

2.2. Photovoltaic measurement and applying pulses

The current-voltage (J - V) measurements of the three DSSCs were performed by using a Keithley 2400 source meter under an illumination of simulated AM 1.5G solar light (Oriel 94022A equipped with a 150 W Xe lamp and an AM 1.5G filter). To apply the pulse while keeping the capability to measure the current, we again utilized the Keithley 2400 source meter for the electrical pulses. The source meter was controlled by a computer program to generate pulses with a constant 185 ms width. The shapes of the output pulses were recorded by an Agilent DSO5014A oscilloscope.

2.3. Characterization and stability tests

The morphology of the nano- TiO_2 photoelectrode covered by the gel electrolyte was characterized by using a scanning electron microscope (SEM, Zeiss LEO 1530). The transient photocurrent curves were recorded by an Agilent 34411A 6 $\frac{1}{2}$ digital multimeter. The electrochemical impedance spectroscopy (EIS) was measured by an SP-200 potentiostat (Biologic, USA), with the frequency ranging from 100 Hz to 200 kHz. The DSSCs were kept at open circuit under AM 1.5G illumination for the EIS test. For the long-term stability tests, J - V curves of C1 and C3 under AM 1.5G were recorded intermittently during a long period. When C1 and C2 were not tested, they were kept in atmosphere in dark, under 25°C temperature and 30% humidity.

3. Method and mechanism

When a positive pulsed electrical bias (counter electrode with positive potential, photoelectrode with zero potential) is applied to a DSSC, electrons are injected from the conduction band of the TiO_2 photoelectrode to the redox level of the electrolyte.²² The following reaction then occurs at the $\text{TiO}_2/\text{dye}/\text{electrolyte}$ interface:

where plenty of I^- ions are produced near this interface. Meanwhile, I_3^- ions in the same amount are produced near the counter electrode via a reverse reaction of Eq. (1), as shown in Fig. 1. The net effect of the positive pulse is therefore the increased concentration of I^- near the TiO_2 photoelectrode, while the concentration of I_3^- near the counter electrode is increased. After the pulse, the concentration gradient drives the ions to diffuse back to the initial equilibrium.

When DSSCs operate under illumination, the I^- ions near the photoelectrode provide the electrons to the lowest unoccupied molecular orbital (LUMO) energy level of the dye to contribute to the photocurrent. For typical liquid electrolytes with a high conductivity, the concentration of I^- does not influence on the photocurrent of the DSSCs. However for quasi-solid-state and other viscous electrolytes, their diffusion coefficients are too low to maintain a sufficiently large flux of I^-/I_3^- transport, which limits the photocurrent.²³ The photocurrent of a quasi-solid-state DSSC increases with I^-/I_3^- concentration.^{24,25} Therefore, the immediate J_{sc} of a quasi-solid-state DSSC after the positive pulse should be improved if the pulse does not bring any damage to the cell. Afterwards, the electrolyte will return to the initial equilibrium, and J_{sc} should drop back to the initial value before the pulse.

As shown in Fig. 2a, the PVDF-based electrolyte covers the TiO_2 nanoparticles and fills in their interspace. In such quasi-solid-state polymer electrolyte, framework materials provide the liquid-like channels for the transport of I^-/I_3^- .^{23,26} If a DSSC is degraded by the blockage of such channels, the large transient current during the pulse may open up some of them to recover the performance, as shown in Fig. 2c. If this hypothesis is true, the performance of the DSSC should still be better when reaching the equilibrium after a period, compared with that before the pulse.

To set the parameters of the pulse in the experiments, the total quantity of I atoms in the electrolyte should be considered, according to Eq. (1). The number of the injected electrons via the pulse should be fewer than or at most comparable with the total number of I atoms in the electrolyte. If the injected electrons significantly outnumbers the I atoms, the excessive electrons may cause some irreversible damage to the cell. Hence the control of the parameters of the pulse is crucial. In our experiments, the basic pulse parameters are shown in Fig. 2b, with a constant 185-ms pulse width. During the pulse period, the currents near the rising and falling edges were recorded, respectively, typically around 40~45 mA for C1, C2, and C3 with 2.5 V pulse height. Using an average current of 40 mA, the total number of injected electrons (N_{inj}) can be estimated to be 4.6×10^{16} . The total number of I atoms in electrolyte (N_{I}) can be calculated to be 1.4×10^{16} , with $[\text{I}_2] = 0.05 \text{ M}$ and an estimation of 50% porosity of TiO_2 films. Thus N_{inj} is sufficient and relatively comparable with N_{I} .

4. Results and discussion

In the first study, two single 185-ms pulses separated by 2 s were applied to enhance the pulse effect. The measured double-pulse with 2.5 V in height is shown in Fig. 2b, called P1. The transient currents at the beginning and the end of the pulse applied to the DSSC were recorded by the Keithley 2400 source meter. For C1, the average current under the 2.5 V

pulse was measured to be about 40 mA. J - V curves of C1 before and after P1 are shown in Fig. 3a. J - V curve of C1 before P1 was first recorded. After P1, J - V was recorded immediately (2 s after P1), showing a great improvement in J_{sc} by about 25%. However, the J - V curve at the low voltage region is a little steep, indicating a nonequilibrium state of the cell. After 2 min, J - V was recorded again (also in Fig. 3a), showing a decreased but flatter photocurrent. This is due to the diffusion of I^-/I_3^- as shown in Fig. 1. Here, J_{sc} of C1 is still greater than that before P1. V_{oc} was not affected by the pulses during the process.

In order to understand the mechanism of the increase in the photocurrent, EIS under AM 1.5G illumination at open-circuit was performed, and the Nyquist plots of C1 before and after P1 are shown in Fig. 3b. The three semi-circles in each curve refer to the impedances at the Pt electrode (Z_1), the TiO_2 /dye/electrolyte interface (Z_2), and in the electrolyte (Z_3), respectively.^{27,28} Simulation of the two spectra in Fig. 3b was performed by a Z-View software, and all the impedances were obtained, shown in Fig. S1 and Table S1 (ESI[†]). After P1, Z_2 was greatly reduced, indicating that the conductivity at the TiO_2 /dye/electrolyte interface was greatly improved. This result confirms the increase in the I^- concentration at the TiO_2 /dye/electrolyte interface by the pulses, as previously discussed. The change in Z_1 and Z_3 by P1, on the other hand, are not remarkable. The series resistances of the two curves, located at about 33 Ω , were almost unchanged either. Therefore, the region acted upon by the pulses in the DSSC is essentially at the TiO_2 /dye/electrolyte interface.

C2 was tested to investigate the impact of the pulse height by varying the pulse height. Three double-pulses with pulse heights of 2.5 V (P1), 2.8 V (P2), and 3.2 V (P3) were applied to C2 in sequence and the photocurrent after each of them was measured, as shown in Fig. 4. C2 was in dark initially. When the AM 1.5G radiation was turned on, the photocurrent dropped quickly in tens of seconds to a stable state and flattened. The measured J_{sc} corresponded to the flat photocurrent. The light was shut down after about 250 s, when P1 was applied to C1, before the light was turned on again. Both the initial and the stable photocurrents were improved respectively from before the pulse was applied. Similar procedures were followed before applying P2 and P3. After P2, the photocurrent was further improved, where the average transient current induced by 2.8 V pulses in dark was up to 55 mA. After P3, the improvement of photocurrent was even greater: the initial photocurrent was over 2 mA (17 mA cm⁻²), and the stable current was 1.2 mA (10 mA cm⁻²). With the height of the double-pulse increased from 2.5 V to 3.2 V, the pulse-induced dark current in C2 increased from 45 mA to 68 mA correspondingly. This experiment shows that the higher the pulse height, the larger the photocurrent.

As to the impact of the pulse height on η , J - V was measured before and after the three double-pulses, and the performance parameters are shown in Table S2 (ESI[†]). Several minutes after P3, η decreased from 1.90% to 1.83%. Therefore, C2 was partially damaged after P1 to P3. After several days, C2 was severely damaged with η dropping close to 0. The tests on C2 show that higher pulses such as P3 could cause an irreversible damage. For our DSSCs, the dark current during each pulse was controlled under 50 mA by adjusting the pulse height.

To study the long-term stability of such DSSCs, the J - V curves of C1 and C3 during a long period were recorded. It is well known that quasi-solid-state DSSCs have a great stability.^{29,30} In our study, the well-sealed C1 kept stable for at least 147 days, as shown in Fig. S2 (ESI[†]). It was thus difficult to observe any recovery effect by the pulses. On the other hand, the result implies that the applied pulses did not deteriorate the performance of C1. The result of C3 was shown in Fig. 5. Since the holes on the counter electrode were not

[†]Electronic Supplementary Information (ESI) available. See DOI: 10.1039/b000000x/

sealed, C3 degraded rapidly during the first 19 days - all the 4 parameters in Fig. 5b kept dropping from the 5th day to the 19th day. After 19 days, η of C3 dropped from 3.32% to 1.76%, indicating a loss of 47.0% in η due to degradation. On the 19th day, P1 was applied to C3. Then a J - V measurement was immediately performed. Similar to the case of C1, there was a great improvement in J_{sc} , which increased η to 3.27%. Meanwhile, V_{oc} increased slightly and the fill factor (FF) dropped slightly. After a half day when C3 reached a stable state, η dropped to 2.30%. This corresponds to a 30.7% of recovery as compared to the degraded η , or a 16.3% of the initial value of η of the fresh C3. Then after another 22 days, η dropped slowly to 1.93%, still greater than the value before applying P1 (1.76%). These results are consistent with our previous hypotheses: first, the channel-blocking effect is an important degradation mechanism in such quasi-solid-state DSSCs, since it could be recovered by the pulse method; second, the well-controlled electrical pulses do not damage the DSSCs. Therefore this pulse method is an effective tool to recover the degraded quasi-solid-state DSSCs. In such PVDF-based DSSCs, the electrolyte conducts by the movement of I^-/I_3^- ions through the matrix channels formed by PVDF. One of the probable degradation reasons of such DSSCs is that some of the ion transport channels are blocked. During the pulse period, part of the blocked channels may be opened up by the large current of I^-/I_3^- ions enforced by the electrical field.

On the 46th day, the same double-pulse was applied to C3 again, and a similar effect was observed: η increased and remained stable in the following 15 days. Such repeatability further proves the significance of this pulse method for recovering the degraded quasi-solid-state DSSCs. The success of P1 for C3 further shows that well-controlled pulse height would not damage the cell. During all the 61 days of test shown in Fig. 5b, FF kept dropping gradually, and the applied pulses had no positive effect on it. V_{oc} and J_{sc} could be improved by the pulses, and the tendency of η was primarily attributed to J_{sc} , since the change of V_{oc} was not significant. Overall, η was partially recovered.

The degradation of dyes is a key factor influencing the stability of DSSCs.^{31–35} Usually such degradation is active when DSSCs are illuminated and/or heated (typically above 60°C). In our study of long-term stability, the DSSCs were mostly kept in dark at room temperature except during testing. Therefore this dye degradation should be limited in our study. The degradation of Pt counter electrode could also be another factor.^{36–38} However, the pulse method in this study does not have any recovery effect on this kind of degradation. Self-degradation in quasi-solid-state DSSCs has been reported due to shrinkage of the polymer electrolytes with high-humidity atmosphere.³⁹ The applied pulses could not effectively repair the shrinkage, and the humidity in our study was not too high. No obvious shrinkage was observed in our degraded cells. Nonetheless, the moisture could be one probable factor that acts onto the inside of the ion-channels and causes the blocking. More future work is still needed to verify the details in the channel-blocking process.

5. Conclusion

In conclusion, we have found that applying forward pulsed biases could effectively recover the degradation of quasi-solid-state DSSCs. In a long-term J - V measurement, up to 30.7% of the degraded η was recovered by a well-controlled double-pulse. The recovery by the application of the pulses could last more than 28 days. It is believed that the blockage of ion-transport channel at the interface of TiO_2 /dye/electrolyte is an important factor that causes the degradation, and the applied pulses could open the blockage to recover the degraded DSSCs. The recovery of η is mainly from the improvement in the photocurrent, which could be greatly improved when the height of the applied double-pulse increases. However, the height of the double-pulse needs to be well controlled, since the DSSCs might be damaged if the pulse-induced dark current is too large. This finding provides not only a practical method

to recover the degraded quasi-solid-state DSSCs, but also an effective tool to study their degradation mechanism. In the future, the long-term stability of the well-sealed quasi-solid-state DSSCs and their degradation mechanism, as well as this approach of ours using forward biased pulses to recover the degraded η , will be further investigated.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

This work was supported by the US National Institute of Health (Grant No. 1DP2OD008678-01). The authors thank B. Aldalali for assistance in fabricating the printing screen, and Prof. S. Jin and Dr. L. Li for EIS measurements. This research utilized US National Science Foundation supported shared facilities at the University of Wisconsin.

Notes and References

- O'Regan B, Grätzel M. *Nature*. 1991; 353:737.
- Chiba Y, Islam A, Watanabe Y, Komiyama R, Koide N, Han L. *Jpn J Appl Phys*. 2006; 45:L638.
- Yu Q, Wang Y, Yi Z, Zu N, Zhang J, Zhang M, Wang P. *ACS nano*. 2010; 4:6032. [PubMed: 20923204]
- Yella A, Lee HW, Tsao HN, Yi C, Chandiran AK, Nazeeruddin MK, Diau EWG, Yeh CY, Zakeeruddin SM, Grätzel M. *Science*. 2011; 334:629. [PubMed: 22053043]
- Tennakone K, Perera V, Kottegoda I, Kumara G. *J Phys D: Appl Phys*. 1999; 32:374.
- Meng QB, Takahashi K, Zhang XT, Sutanto I, Rao TN, Sato O, Fujishima A. *Langmuir*. 2003; 19:3572.
- Chung I, Lee B, He J, Chang RPH, Kanatzidis MG. *Nature*. 2012; 485:486. [PubMed: 22622574]
- Bach U, Lupo D, Comte P, Moser JE, Weissortel F, Salbeck J, Spreitzer H, Grätzel M. *Nature*. 1998; 395:583.
- Saito Y, Fukuri N, Senadeera R, Kitamura T, Wada Y, Yanagida S. *Electrochem Commun*. 2004; 6:71.
- Hirata N, Kroeze JE, Park T, Jones D, Haque SA, Holmes AB, Durrant JR. *Chem Commun*. 2006:535.
- Wang H, Zhang X, Gong F, Zhou G, Wang ZS. *Adv Mater*. 2012; 24:121. [PubMed: 22135079]
- Stergiopoulos T, Arabatzis IM, Katsaros G, Falaras P. *Nano Lett*. 2002; 2:1259.
- Kaneko M, Hoshi T. *Chem Lett*. 2003; 32:872.
- Wang L, Fang S, Lin Y, Zhou X, Li M. *Chem Commun*. 2005:5687.
- Wang P, Zakeeruddin SM, Moser JE, Nazeeruddin MK, Sekiguchi T, Grätzel M. *Nat Mater*. 2003; 2:402. [PubMed: 12754500]
- Stergiopoulos T, Arabatzis IM, Katsaros G, Falaras P. *Nano Lett*. 2002; 2:1259.
- Kim JH, Kang MS, Kim YJ, Won J, Park NG, Kang YS. *Chem Commun*. 2004:1662.
- Wu JH, Hao SC, Lan Z, Lin JM, Huang ML, Huang YF, Fang LQ, Yin S, Sato T. *Adv Funct Mater*. 2007; 17:2645.
- Li Q, Wu J, Tang Z, Xiao Y, Huang M, Lin J. *Electrochimica Acta*. 2010; 55:2777.
- Fan K, Peng T, Chen J, Zhang X, Li R. *J Mater Chem*. 2012; 22:16121.
- Wang ZS, Kawauchi H, Kashima T, Arakawa H. *Coord Chem Rev*. 2004; 248:1381.
- Zhu K, Jang SR, Frank AJ. *J Phys Chem Lett*. 2011; 2:1070.
- Hagfeldt A, Boschloo G, Sun L, Kloo L, Pettersson H. *Chem Rev*. 2010; 110:6595. [PubMed: 20831177]
- Kubo W, Murakoshi K, Kitamura T, Yoshida S, Haruki M, Hanabusa K, Shirai H, Wada Y, Yanagida S. *J Phys Chem B*. 2001; 105:12809.
- Li MY, Feng SJ, Fang SB, Xiao XR, Li XP, Zhou XM, Lin Y. *Electrochim Acta*. 2007; 52:4858.

26. Yang Y, Zhou CH, Xu S, Hu H, Chen BL, Zhang J, Wu SJ, Liu W, Zhao XZ. J Power Sources. 2008; 185:1492.
27. Han LY, Fukui A, Chiba Y, Islam A, Komiya R, Fuke N, Koide N, Yamanaka R, Shimizu M. Appl Phys Lett. 2004; 84:2433.
28. Wang Q, Moser JE, Grätzel M. J Phys Chem B. 2005; 109:14945. [PubMed: 16852893]
29. Yu Z, Qin D, Zhang Y, Sun H, Luo Y, Meng Q, Li D. Energy Environ Sci. 2011; 4:1298.
30. Yu Q, Yu C, Guo F, Wang J, Jiao S, Gao S, Li H, Zhao L. Energy Environ Sci. 2012; 5:6151.
31. Agrell HG, Lindgren J, Hagfeldt A. Sol Energy. 2003; 75:169.
32. Tanaka H, Takeichi A, Higuchi K, Motohiro T, Takata M, Hirota N, Nakajima J, Toyoda T. Sol Energy Mater Sol Cells. 2009; 93:1143.
33. Ke L, Dolmanan SB, Shen L, Pallathadk PK, Zhang Z, Lai DMY, Liu H. Sol Energy Mater Sol Cells. 2010; 94:323.
34. Natalia M, Alessandro T. Energy Environ Sci. 2011; 4:4473.
35. Yoshida C, Nakajima S, Shoji Y, Itoh E, Momiyama K, Kanomata K, Hirose Fumihiko. J Electrochem Soc. 2012; 159:H881.
36. Lee CH, Lee KM, Tung YL, Wu JM. J Electrochem Soc. 2012; 159:B430.
37. Xue G, Guo Y, Yu T, Guan J, Yu X, Zhang J, Liu J, Zou Z. Int J Electrochem Sci. 2012; 7:1496.
38. Syrokostas G, Siokou A, Leftheriotis G, Yianoulis P. Sol Energy Mater Sol Cells. 2012; 103:119.
39. Lee JY, Bhattacharya B, Kim YH, Jung HT, Park JK. Sol Stat Commun. 2009; 49:307.

Fig. 1.

Schematic of the ion distribution in the electrolyte before and after the application of the positive pulse in a typical DSSC. The region on the left represents the dye-loaded TiO_2 nanoparticles surrounded by electrolyte, while the middle region between TiO_2 photoelectrode and Pt counter electrolyte represents the pure electrolyte.

Fig. 2. (a) SEM image of nano-TiO₂ photoelectrode covered by gel electrolyte. (b) Double 185-ms electrical pulses (P1) generated by the source meter, measured by an oscilloscope. (c) Some of the blocked ion-transport channels in this quasi-solid-state electrolyte are opened up by the applied pulse.

Fig. 3.

(a) J - V curves under AM 1.5G and (b) Nyquist plots of C1 before and after P1. EIS measurements were performed under AM 1.5G illumination and with + 0.74 V bias on C1 (open-circuit).

Fig. 4. Transient photocurrent curves of C2 under AM 1.5G illumination: before and after +2.5 V (P1), +2.8 V (P2), and +3.2 V (P3) double-pulses. The average dark currents induced by each pulse are also shown.

Fig. 5.

(a) Measured J - V curves of C3 during the first 40 days. The holes on the counter electrode of C3 were not sealed. (b) The corresponding evolution of the four photovoltaic performance parameters in 61 days, during which the pulses were applied twice: on the 19th day and 46th day, respectively.