Published in final edited form as:

Compos Struct. 2013 June ; 100: 404–412. doi:10.1016/j.compstruct.2012.12.034.

Optimal Design of Honeycomb Material Used to Mitigate Head Impact

Vincent Caccese^{a,*}, James R. Ferguson^b, and Michael Edgecomb^a

^aUniversity of Maine, Department of Mechanical Engineering, Orono, ME USA

^bAlba-Technic, LLC, Winthrop, ME USA

Abstract

This paper presents a study of the impact resistance of honeycomb structure with the purpose to mitigate impact forces. The objective is to aid in the choice of optimal parameters to minimize the thickness of the honeycomb structure while providing adequate protection to prevent injury due to head impact. Studies are presented using explicit finite element analysis representing the case of an unprotected drop of a rigid impactor onto a simulated floor consisting of vinyl composition tile and concrete. Analysis of honeycomb material to reduce resulting accelerations is also presented where parameters such as honeycomb material modulus, wall thickness, cell geometry and structure depth are compared to the unprotected case. A simplified analysis technique using a genetic algorithm is presented to demonstrate the use of this method to select a minimum honeycomb depth to achieve a desired acceleration level at a given level of input energy. It is important to select a minimum material depth in that smaller dimensions lead toward more aesthetic design that increase the likelihood of that the device is used.

Keywords

Honeycomb structure; Head Impact; Explicit Finite Element Analysis; Optimization

1. Introduction

The head is the most vulnerable part of the body to impact and, when unprotected, impact levels can reach upwards of 300 g (gravitational acceleration); which is dangerous to life. Head impact can occur due to traffic accidents, body contact sports and falls, among other causes. Some typical types of injuries can be skull fracture, brain injury due to excessive translational and/or angular acceleration and lacerations. Injury due to head impact can be lessened by energy absorbing protection systems. To that end, a study of honeycomb structure used to absorb normal head impact is summarized herein. A head impact protective system needs to be designed with specific criteria in mind including input energy (or velocity) level, thickness, stiffness, weight and cost among others. Use of higher impact energy levels in the design typically requires the resistive system to become thicker and/or stiffer. Excessive thickness in some cases may lead to stigmatizing designs and objection to

© 2013 Elsevier Ltd. All rights reserved.

*Corresponding Author: Vincent Caccese, Ph.D. P.E., Department of Mechanical Engineering, 5711 Boardman Hall, Rm 212, University of Maine, Orono, ME 04469, tel: (207) 581-2131, fax:(207) 581-2379, vince_caccese@umit.maine.edu.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

wearing the device. If thickness is limited, the system can be made stiffer to avoid a bottoming out effect where the impacted object or surface virtually contacts the head. Stiffening of the impact resisting system also causes an undesirable increase in acceleration magnitude along with the associated increase in forces. Alternatively, underestimation of the input impact energy will result in a more flexible design with decreased accelerations but premature bottoming out may occur at a higher than estimated impact level. Bottoming out also cause's acceleration levels to increase significantly, increasing the likelihood of injury. Accordingly, a fine tradeoff is required between design input impact energy, thickness and stiffness of the system.

Energy absorbing mechanisms such as plastic deformation and material fracture can be used advantageously to mitigate severe impact. This is the case with many impact resistant devices, for example, motorcycle helmets are designed to withstand large amounts of energy but deform permanently [1,2]. In some head protection devices, however, it is desirable to have impact resisting mechanisms that do not undergo permanent deformations so that the device can be reused effectively after impact. This is especially true in helmets used for contact sports where they may undergo numerous impacts even during a single sports event. Equipment such as sports protective devices are rarely, if ever, discarded after moderate or even severe impacts. Accordingly, it is highly desirable to have a material that can absorb high amounts of energy elastically so that the protective device can respond effectively during the next impact event. Honeycomb structure made of highly elastic material such as urethanes or silicones, when impacted normal to the surface, have the potential capacity to absorb energy through elastic buckling, which is the subject of this paper.

2. Head Protection Measures

Traumatic brain injuries typically occur when the head comes into direct contact with another object, which imparts forces and associated stress and strain on the head. In addition to skull fractures, focal injuries can occur when the brain accelerates relative to the skull as a result of the imparted energy to the head. This action can cause a variety of contusions (bruising) to the brain tissue including gliding contusions which are associated with the increase in normal and shear stresses at the interface of the skull and brain [3]. Lacerations, which are more common in open (fractured skull) injuries, are characterized by a tear of the brain tissue and are sometimes found near contusions, but typically arise from greater forces. Acute subdural hematomas (ASDH) are commonly caused by rupturing of the veins due to relative motion between the brain and the skull and carry a particularly high rate of mortality at 74%, with little clinical treatment available [4]. There is potential, however, for TBI to arise without direct contact with another body and is instead due solely to acceleration of the head. In these types of injuries, the brain's inertia causes damaging strains throughout its tissue. One type of such injury is diffuse axonal injury (DAI). DAI is believed to result from angular acceleration of the head, which causes the outer tissue of the brain to move relative to the inner tissue resulting in widespread damaging tissue strains [4]. Angular acceleration is thought to be a major contributor to TBI, especially in contact sports [5]. Other types of brain injury include brain swelling and increased intracerebral pressure. These injuries are caused by various mechanisms and tend to affect the brain in a diffuse manner by limiting the blood supply to the brain (ischemic/hypoxic damage). In a study by Raiker [6] of 263 patients over 65 it was found that falls were the leading cause of injury followed by road accidents as pedestrians.

Many head injury predictors have been suggested and studied over the years to determine which most accurately and consistently predicts head injury in humans [7]. These include the Head Injury Criterion (HIC), Gadd severity Index (SI), peak resultant translational acceleration of the center of gravity (COG) of the head, peak resultant rotational

acceleration of the COG of the head, linear impact velocity, angular impact velocity, Generalized Acceleration Model for Brain Injury Threshold (GAMBIT), Head Impact Power (HIP), peak force, time duration limits of several of the above. The Association for the Advancement of Automotive Medicine developed an Abbreviated Injury Scale (AIS) to classify the severity of injuries [8]. AIS was first created in 1969 and is one of the most common anatomic scales for traumatic injuries. The scale ranges from 0 for no injury to 6 for maximum severity of injury.

The Head Injury Criteria (HIC) is used to measure the likelihood of head injury due to impact. Head Injury Criterion is currently, the most widely accepted predictor of head injury. The HIC was developed following the Wayne State Tolerance Curve (WSTC), which plots resultant translational acceleration (in multiples of Earth's gravitational constant, g) of a head versus time duration at that acceleration. In 2000, the NHTSA evoked limits that reduced the maximum time for calculating the HIC to 15 milliseconds (HIC_{15}) [9]. The HIC is a mathematical model that predicts head injury severity, the formula for which is given in Equation (1).

$$HIC = \left\{ \left[\frac{1}{(t_2 - t_1)} \int_{t_1}^{t_2} a(t) dt \right]^{25} \cdot (t_2 - t_1) \right\}_{\max} \quad (1)$$

where:

t_1 and t_2 are two times during the acceleration-time history.

$a(t)$ = resultant translational acceleration of the head in g 's

The HIC criteria is computed from an acceleration signature measured in g 's during impact using Equation (1) where $(t_2 - t_1)$ is selected to maximize the HIC value. The maximum time duration of $(t_2 - t_1)$ is typically limited to a value of 15ms, and the resulting computation is termed the HIC_{15} . According to Mertz, et al. [10], an HIC of 700 represents a 5% percent risk of a severe injury. One in six people will suffer a life-threatening injury to their brain at an HIC of 1000. Chinn et al. [11] studied motorcycle helmet safety and found that of all the parameters analyzed, the HIC provided the best head injury severity prediction with a correlation coefficient of $r = 0.8$. The study reported that a HIC of 1000 corresponds to an Abbreviated Injury Scale (AIS) of 2 (moderate), while a value of 1500 corresponds to AIS of 3 (serious).

It has been shown that peak resultant translational acceleration of the head exceeding 300 g is "dangerous to life" regardless of time duration of that acceleration event. Nahum et al. [12] suggested that resultant linear accelerations of the head from 200–250 g correspond to an AIS of 4 (severe), 250–300 g correspond to an AIS of 5 (critical), and those greater than 300 g correspond to an AIS of 6 (fatal). Skull fracture has been shown to correlate more strongly with peak force than with pulse duration, loading rate, or resultant translational acceleration of the head. Studies aimed at determining a threshold for peak force of the skull found that skull fractures occur anywhere from 4,000–15,000 N [13]. A study of 31 cadaver heads dropped onto a flat surface found that the average force required for fracture was 12,400 N [14]. Additionally, it has been shown that the skull's peak force threshold decreases with reduced surface area of the impacting force, suggesting that fracture is more a function of stress than force alone. Fracture thresholds tend to be higher for males than females and for frontal impacts than lateral impacts. This current study will focus on the use of relatively flexible elastic honeycomb structure to reduce accelerations caused by impact due to normal loads similar to a frontal impact event.

3. Response of honeycomb material for impact protection

Honeycomb materials are cellular structures that can come in a variety of patterns. One of the most popular types is the hexagonal honeycomb with either regular hexagonal walls or wall that are not regular and allow for a bias. The geometry of a regular hexagonal honeycomb structure is depicted in Fig. 1. When fabricated using a process such as molding, the cell walls are typically made of a uniform thickness. The geometry of a regular honeycomb is defined by the mean cell size, c , which is the average distance from wall to wall, the mean leg distance of the cell wall, a , the cell wall thickness, t , and overall depth, d . Another method of fabrication is a corrugating folding process where half of the honeycomb pattern is pressed into a ribbon or plate of material. An adjacent ribbon is placed and the walls are fused together by an appropriate means for the material being fabricated. This process results in 2/6 of the walls being of thickness $2t$.

4. Effective Honeycomb Properties

A first order approximation for the effective compressive modulus of the honeycomb E_h can be estimated based upon the solid cell wall material modulus, E_s , using the law of mixtures. This relationship can be expressed in terms of a solid ratio, SR , which is defined as the area of solid material, A_s , enclosed by the perimeter of a unit cell divided by the mean area, A_m , enclosed by the cell. For a regular hexagonal shaped honeycomb with cell walls of equal thickness, the area of solid material, A_s , and the mean area A_m , are expressed in Equations (2) and (3), respectively.

$$A_s = 3 \cdot a \cdot t_w - \frac{\sqrt{3}}{2} \cdot t_w^2 \quad (2)$$

$$A_m = \frac{3\sqrt{3}}{2} \cdot a^2 \quad (3)$$

For the regular hexagon with equal walls, the solid ratio, SR , can then be expressed as ratio of A_s to A_m in terms of the ratio t_w/a .

$$SR = \frac{2}{\sqrt{3}} \cdot \frac{t_w}{a} - \frac{1}{9} \left(\frac{t_w}{a} \right)^2 \quad (4)$$

The effective modulus of the honeycomb can be expressed using the law of mixtures in terms of the solid ratio and the modulus of the solid material as:

$$E_h = SR \cdot E_s \quad (5)$$

for the case of a regular hexagon with thin equal thickness walls where the second term in Equation 4 can be neglected. The expression reported by Fan et al. [15] for this case then results where:

$$\frac{E_h}{E_s} = 1.155 \frac{t_w}{a} \quad (6)$$

In the case of a regular hex structure with one-third the walls equal to $2t$ the solid area becomes:

$$A_s = 4 \cdot a \cdot t_w - \frac{(2 + \sqrt{3})}{3} \cdot t_w^2 \quad (7)$$

The solid ratio becomes:

$$SR = \frac{8 \cdot \sqrt{3}}{9} \cdot \frac{t_w}{a} - \frac{(4 \cdot \sqrt{3} + 6)}{27} \cdot \left(\frac{t_w}{a}\right)^2 \quad (8)$$

If the hex shape is such that two of the six walls are double thick and the walls are thin compared to the cell size then Equation (9) results where:

$$\frac{E_h}{E_s} = 1.540 \cdot \frac{t_w}{a} \quad (9)$$

4.1 Honeycomb buckling

Buckling of the cell walls is a critical structural response in the impact resistance of the honeycomb material subject to normal impact. Elastic buckling of the cell walls in compression can be estimated using Bleich's plate buckling expression given as:

$$\sigma_{cs} = K \cdot \frac{\pi^2 E_s}{12 \cdot (1 - \nu^2)} \cdot \left(\frac{t_w}{a}\right)^2 \quad (10)$$

In this case σ_{cs} is the actual stress placed upon the top of the cell wall (solid material only) and K is the buckling factor that depends upon the geometry and boundary conditions at the cell edges. Multiplying the critical buckling stress by the solid ratio gives the buckling stress acting over the effective area of the honeycomb material, σ_{ch} .

$$\sigma_{ch} = SR \cdot \sigma_{cs} \quad (11)$$

For a thin walled honeycomb of constant wall thickness this expression can be written as

$$\sigma_{ch} = 1.044 \cdot K \cdot E_s \cdot \left(\frac{t_w}{a}\right)^3 \quad (12)$$

With the buckling constant $K = 5.0$ the product of the first two terms is 5.2 and the expression reported in paper by Fan et al. [15] results.

Choice of proper buckling factor, K , is critical for prediction of the buckling stress. If it is assumed that the cell depth is large compared to the cell size and that the loaded edges are simply supported, a value of $K=4.0$ is appropriate if it is assumed that the boundary at the cell intersections are simply supported and $K=6.97$ is appropriate if it is assumed that the restraint created by the adjacent cell is rigid with respect to lateral rotation resulting in a clamped boundary condition. In reality, the actual condition will be somewhere between the two cases. Furthermore, the cell depth typically will not be long compared to the cell size. The theoretical buckling equations indicate that a significant decrease in buckling capacity can be achieved by reduction in the ratio of t_w to a . A physical limitation of the cell wall thickness is when the half-thickness becomes greater than the cell height divided by 2, ($c/2$)

or when $t_w/a = 0.866$. The thin assumption is violated well before this constraint occurs. To address some of the concerns in a theoretical buckling model, Fan et al. [15] compared experiment to non-linear finite element analysis (FEA) with honeycomb cell buckling and showed that the FEA models gave a good approximation of the experimentally obtained results. An FEA can account for the actual cell geometry and can include interactions to model boundary conditions.

5. Finite element impact modeling

A finite element model was developed to simulate an impact on honeycomb material. The details are based upon a physical study performed by Ferguson et al. [16] using an Instron Dyna-tup impact test machine. Figure 2 gives a schematic of the test where the honeycomb test material was subject to impact from a relatively rigid tup. The tup was specially designed with a shape appropriate for a human head. The base of the test consisted of a relatively massive block with a vinyl composition tile (VCT) tile cover used to simulate a hospital floor. The test material was placed on the VCT tile. Data included the acceleration versus time of the tup and HIC_{15} computation. The force versus time history was also measured by the load cell of the test machine which is positioned between the tup and the mass loading block. Accelerations of the tup were measured at even increments in time and are subsequently compared to analytical results.

A finite element model representative of the drop test is used for model validation and to analytically compare the relative material response of the honeycomb structure. In this process the base block and attached VCT tile are modeled as linear-elastic materials. The impactor tup is considered to be a linear elastic aluminum material and is given an initial velocity representative of the drop height so that the appropriate impulse is imparted to an unprotected base block or to the study material. A geometric nonlinear model of the honeycomb material is used to capture the buckling effects.

The finite element model of the drop test simulation consists of several basic components including: 1) an upper cross head section; 2) a load cell section; 3) a steel plate; 4) the aluminum tup; 5) the vinyl composition tile (VCT); 6) the base block; and 7) an adhesive layer between the VCT and base block. These components are shown in Figure 3. The upper cross head section was used for added mass so that the combined mass dropped would equal the desired mass of 6.35kg (mass of the tup on the dyantup machine) or 5.5 kg (used to study the influence of the dropped mass). The load cell section was treated as relatively rigid and was used as the location where the acceleration measurements are taken. The steel plate is used as an interface to mitigate stress concentrations between the load cell section and the aluminum tup. Properties of the VCT and base block are selected to represent the response due to an unprotected drop and were selected to simulate the physical testing as much as possible.

The mesh associated with the complete model including honeycomb can be seen in Figure 4. The solid honeycomb material is modeled using 4-noded shell elements, which is available in ABAQUS explicit. The mesh size used in the analysis was based upon a convergence study and was selected based upon accuracy and efficiency of the results. The contact interface between the tup and honeycomb along with the VCT and honeycomb, both include rigid normal contact and frictional sliding contact with a coefficient of friction of 0.25. Studies showed that results were relatively insensitive to an increase in friction coefficient.

5.1 Unprotected impact

The modeling process commenced by simulating an unprotected drop of the relatively stiff head shaped tup onto a VCT/base with no protective material such as the honeycomb

structure in place. The goal of this study was to provide a baseline that results in similar response to that observed in the experiment. Target values recorded in the experiment for a 70mm drop of a 6.35kg mass are a maximum acceleration of 240g's, HIC_{15} of 434 and impact period of 1.4ms. Based upon preliminary results, a baseline model using an adhesive layer of 0.64 mm thick with a modulus of elasticity of 0.3GPa sandwiched between a VCT layer with a modulus of 3GPa and the base block material with a modulus of 2.5GPa was found to simulate experimental results with reasonable accuracy. At a drop height of 70 mm (4.36 J), the peak acceleration was approximately 246g's with a HIC_{15} of 533 for the 6.35kg mass, which is a reasonable approximation to the experimental data obtained. The impact period was 1.7ms. The honeycomb impact analysis is not highly sensitive to the base material properties (VCT+adhesive+base), at least for low modulus of elasticity honeycomb materials studied, as the base is relatively rigid.

Using the recommended unprotected baseline model, two additional studies were conducted on the half symmetry model where the input energy and the dropped mass was varied as 5.5kg and 6.35kg to accommodate different head sizes. The result of peak acceleration, HIC, peak force and impact period versus impact energy can be seen in Figure 5. For the 5.5kg model, the maximum accelerations at the same impact energy levels were higher when compared to the 6.35kg model. At an input energy of 4.36 J, the maximum acceleration was approximately 281g compared to 246g in the higher mass case; as the lower mass head has a higher impact velocity. The corresponding HIC value was 640, also the impact period was 1.48 which is lower than in the 6.35kg model with a period of 1.7 ms, also explaining the increase in acceleration.

6. Honeycomb Impact

Impact analysis of the honeycomb used parameters in the analysis that include: the material properties, cell wall thickness, cell wall span, and the honeycomb total depth. Designation of various models studied is given in Table 1, where the d suffix in the designation indicates damping included. The deformation resulting from the baseline honeycomb finite element model is shown in Figure 6 where the impact typically results in a bending/buckling deformation, which is shown in the figure on a half-symmetry model. Observed are 7 cells (14 in the full model) that are completely engaged and another 8 cells (16 in the full model) that are partly engaged. This deformation pattern indicates that increasing the load distribution, if done cautiously, has potential to increase the energy absorption.

The acceleration time history resulting from an explicit analysis is shown in Figure 7a where it displays the results from baseline model M1 with no damping. Observed in the figure is a noisy acceleration response due to the honeycomb buckling and post buckling; where it is compared to a smoothed curve filtered using a 4th order Butterworth filter with a cutoff frequency of 1650 Hz. The addition of damping was implemented in the analysis to reduce the high frequency ringing. A Fourier analysis was used to detect the principal frequency of 15kHz that was predominating in the high-frequency noise so that frequency could be critically damped. Material damping was applied to the honeycomb in the form of stiffness proportion Rayleigh damping, which gave the desired results of reducing this noise from the response. The equation to find the Rayleigh damping coefficient, β , is given as:

$$\beta = \frac{2\zeta}{\omega} \quad (13)$$

where ζ is the damping ratio and ω is the frequency. To critically damp frequencies above 15 kHz, a value for β of 2.12×10^{-5} was selected. Figure 7b shows the effect of damping on the model, which caused a substantial reduction in the high frequency oscillations. To that end stiffness proportional Rayleigh damping was used in subsequent analyses. An adverse

effect of adding damping is that it causes an increase in run time in an explicit analysis and in this case damping caused the run time to nearly double.

6.1 Baseline Honeycomb Model Results

Figure 8 shows the results for a study of the baseline model of the honeycomb impact where the impact energy is varied. With a honeycomb solid material modulus of 100MPa and a shell wall thickness of 0.8mm, the energy to cause bottoming out is approximately 23.4 J. After bottom out, the peak accelerations rise with a much greater slope and the subsequent model response is similar to the unprotected case.

A plot of the influence of the honeycomb solids modulus vs. peak acceleration is given in Figure 9 at three different input energy levels of 4.4J, 12.5J and 20.2J (drop height of 75, 200 and 325mm). The honeycomb modulus ranged up to 1GPa. Bottoming out of the honeycomb controlled the lower limit on the honeycomb modulus. A comparison between the unprotected case and models with honeycomb modulus of 100MPa and 250MPa at the three input levels can be seen in Table 2. The honeycomb causes a significant reduction in acceleration compared to the unprotected model. In general, a lower peak acceleration is achieved by using a honeycomb with a lower modulus of elasticity. However, bottoming out at lower impact energy levels is more prone in honeycomb with lower honeycomb modulus as indicated by the lower termination point on curves. Thus there is a tradeoff between stiffness and thickness that must be considered. Stiffer material will cause an increase in acceleration, whereas a more flexible material will cause bottom out at lower energy at an equal thickness. When bottom out occurs acceleration may increase dramatically.

6.2 Effect of Honeycomb depth, d

A study was performed on the baseline model to assess the influence of the honeycomb depth, d . This was accomplished by maintaining a constant honeycomb modulus and determining the influence of d relative to the input energy. Figure 10 shows the results for a honeycomb with a solids modulus of 100MPa at the baseline cell size of $a=3.36$ mm. As observed, reduced thickness results in a honeycomb more prone to bottoming out. Until bottoming out, little difference is observed with respect to depth. This is due to the fact that the depth of the honeycomb has little influence on the buckling resistance of the honeycomb, which is controlled primarily by the t_w/a ratio as given in Equation (10). Once the honeycomb is near bottoming out; the peak acceleration in the thinner material increases and the analysis becomes unstable. If a higher input energy level is desired, a thicker honeycomb needs to be considered due to the accelerations being marginally close in the lower drop heights.

6.3 Effect of Honeycomb Cell Wall Thickness, t_w

An additional study was performed to assess the effect of changing the honeycomb wall thickness, t_w . This study was conducted using the parameters listed for baseline case B1 (see Table 4.1) except that t_w was varied. A solids modulus of 100MPa was used throughout. Figure 11 shows the results for three cell wall thicknesses of 4mm, 6mm and 8mm. Observed in general is that thickening the honeycomb wall causes a stiffness increase and buckling capacity increase that results in larger accelerations, but a higher amount of energy to cause bottom out. Initially, the peak accelerations of the thicker walled honeycomb are significantly higher due to the honeycomb having a higher axial stiffness. In addition, the higher t_w/a ratio as given in Equation (10) will increase the buckling resistance. A reduced thickness allows the honeycomb to buckle at lower input energy, which will also lead to a reduced acceleration. In higher input energy cases, a thicker honeycomb wall is more desirable since it has more resistance to bottoming out as observed by the steep increase in peak acceleration in the figure.

6.4 Effect of Cell Size

The honeycomb overall cell geometry also plays an important role in how the honeycomb responds to the impact loading. A study was performed where the cell leg distance, a , in Figure 2 was modified while keeping the cell geometry a regular hexagon. The values used for the leg distance were based on the baseline model D1 where, $a=3.36\text{mm}$ with a solids modulus of 100MPa . The leg distance value was multiplied by $3/2$ and $2/3$ resulting in leg sizes of 5.04 mm and 2.24 mm , respectively. These models are designated as G2d and G3d, respectively. Figure 12 shows the outcome of this study where in general it is observed that increasing the cell size causes a reduction in peak acceleration at lower input energy levels but results in less energy to cause bottoming out. Increasing the size of the cell decreases the effective buckling strength on the face of the honeycomb. A smaller cell size equates to a stiffer response and better resists bottoming out.

7. Optimization

The optimization process uses a genetic algorithm with multiple objectives to minimize the peak acceleration during impact and the material thickness for a given level of impact energy. This is accomplished using an energy method approach computed using a simplified analysis method, which is guided by the FEA results. The impact response is dependent on a set of variable input parameters chosen using the genetic algorithm methodology. The simplified model is based upon a linear spring subjected to a drop and includes the buckling effect and a check for bottoming out. The spring is assumed to have non-linear mechanical properties that capture the nature of the material being impacted as guided by the FEA. Non-linearity includes an approximation of the buckling effect and bottom out. The bottoming out of the material is estimated in this simplified model using the solid ratio of the material assuming that at the bottom the material compresses by the amount Δ_b given as:

$$\Delta_b = (1 - SR) \cdot d \quad (14)$$

After bottom out, the material is assumed to act like a thin solid of modulus equal to the solid honeycomb modulus of elasticity and thickness equal to the wall thickness. This will greatly increase the stiffness of the material as demonstrated in the explicit dynamic analysis results.

Figure 13 demonstrates the effect of bottoming out on a system that is elastic until bottom out and shows the influence of the effective spring stiffness, k_s , on the peak acceleration. Stiffnesses of 1.0 MN/m to 4.0 MN/m are compared with a constant honeycomb depth of 6.4 mm . This result demonstrates that a stiffer honeycomb will tend to result in higher accelerations at lower level inputs while achieving a higher energy level at bottom out indicated by the X in the figures. This figure also shows a curve with a spring stiffness of $2.55 \times 10^7\text{ N/m}$, which results in an acceleration of $240g$'s at a drop height of 70mm , modeling the results of the unprotected drop test.

Figure 14 shows the energy level, spring stiffness and honeycomb depth required to achieve certain peak acceleration. For a given input energy, the curves can be used estimate the spring stiffness required to limit the thickness and the peak acceleration to a prescribed value. Peak acceleration levels of $75g$ and $150g$ peak are shown on the figure. As an example, if one desires to limit the acceleration to $75g$'s at an input energy level of 20 J , a choice of spring stiffness of 0.5MN/m would require a honeycomb depth of approximately 11.5 mm to avoid bottoming out.

The genetic algorithm analytical approach used in the optimization method predicts the peak acceleration for a given geometry, material combination and energy level input. This is used as a preliminary design tool used to limit the number of design choices from multi-millions of possibilities to several. A set of parameters are selected to initiate the optimization process based upon feasible geometric design and materials which can be acquired. Parameters used include the honeycomb material properties, the material thicknesses, the honeycomb cell geometry and wall thickness. The genetic algorithm then randomly selects a population, which is a set of designs using these parameters. The effectiveness of each design is evaluated by predicting the response using a nonlinear structural/material model. The method selects the best designs in the population to meet the objectives. The designs are then varied over numerous generations until a set of designs, which best fit the criteria emerge. This occurs on what is known as a pareto-optimal front.

A typical result from a trial genetic algorithm optimization is shown in Figure 15. Each curve represents a different input energy level from 10 to 50 joules in 10 joule increments. The dot on each curve represents an individual set of design parameters, which can be traced back as a function of the algorithm. The genetic algorithm program summarizes each design on the optimal front in a table that can be subsequently viewed. Once an input energy level and limit on the peak acceleration is chosen, designs that match the given criteria can then be selected and an optimal minimum thickness established. Once this preliminary design step has been accomplished, the designs can then subject to more detailed analysis using explicit dynamic finite element analysis and testing. For example, in this case of a rigid impactor on VCT with honeycomb absorbing material in between, an unprotected drop at 20J input level results in an acceleration of about 320g. The curve shows that to reduce the acceleration below 100g would require a minimum thickness of 11 mm of honeycomb material.

8. Conclusions

Honeycomb structure have some useful characteristics for mitigation of head impact trauma. Their response is primarily through elastic buckling of the cell walls. In many impact resistant designs it is desirable to select an elastic material that reforms to its original shape post impact. Design of the proper honeycomb parameters such as the cell size, wall thickness, modulus and honeycomb depth must consider the input energy and the system characteristics for the input, if the honeycomb depth and mass are to be minimized. A tradeoff must occur between stiffness and depth as a stiffer material will delay the bottoming out of the material while increasing acceleration prior to bottom out. At lower input energy levels a more flexible system is indicated, which can be achieved by reducing the material modulus and or wall thickness. At higher input energy levels more honeycomb depth is required to avoid bottom out. There is however a limit to the depth of the material that can be used in practice, which is governed by the aesthetics and the function of the device being designed. If the material thickness becomes exceptionally high then objections to the device may cause non-use, which obviously is of no benefit. Therefore, the minimum thickness that will function properly is the desirable design choice to promote use of the device.

Acknowledgments

The authors gratefully acknowledge support for these efforts through the National Institutes of Health/National Institute on Aging under grant number NIH 5R44AGO33936-03. Dr. Lyndon Joseph is the cognizant program officer. Also acknowledged is support from the Maine Technology Institute MTAF program for funding of the laboratory facility and Maine Space Grant Consortium Fellowship and Scholarship program under grant No SG-11-15.

Nomenclature

a	mean leg distance of honeycomb cell wall
c	mean size of honeycomb cell
d	honeycomb overall depth
g	gravitational constant
t_w	honeycomb cell wall thickness
α	honeycomb interior angle
HIC	head injury criteria
a(t)	acceleration magnitude
t1,t2	time
E_s	solids modulus of honeycomb material
E_h	effective modulus of honeycomb
SR	solid ratio
A_s	area of solid honeycomb material
A_m	mean area of honeycomb cell
K	buckling coefficient
σ_{cs}	critical buckling stress of the solid wall
σ_{ch}	critical buckling stress of the honeycomb
Δ_b	bottom out distance
β	stiffness proportion Rayleigh damping factor
ω	frequency
ζ	damping ratio

References

1. Caserta GD, Iannucci L, Galvanetto U. Shock absorption performance of a motorbike helmet with honeycomb reinforced liner. *Composite Structures*. 2011; 93:2748–2759.
2. Gilchrist A, Mills NJ. Modelling of the impact response of motorcycle helmets. *Int J Impact Eng*. 1994; 45:201–18.
3. Zoghi-Moghadam M, Sadegh AM. Global/local Head Models to Analyze Cerebral Blood Vessel Rupture Leading to ASDH and SAH. *Computer Methods in Biomechanics and Biomedical Engineering*. 2009; 12:1–12. [PubMed: 18821190]
4. Hardman JM, Manoukian A. Pathology of Head Trauma. *Euroimaging Clinics of North America*. 2002; 12:175–187.
5. King, AI.; Yang, KH.; Zhang, L.; Hardy, W.; Viano, DC. Is Head Injury Caused by Linear or Angular Acceleration?. *Proceedings of the International Research Conference on the Biomechanics of Impact (IRCOBI)*; 2003; Lisbon Portugal. Sep.
6. Rakier A, Guilburd JN, Soustiel JF, Zaaroor M, Feinsod M. Head Injuries in the Elderly. *Brain Injury*. 1995; 9:187–194. [PubMed: 7787838]
7. Digges, K. Injury Measurements and Criteria. Limitations and Requirements; Ohio, USA. 26–28 October 1998; and published in RTO MP-20
8. Lesko MM, Woodford M, White L, O'Brien SJ, Childs C, Lecky FE. Using Abbreviated Injury Scale (AI) codes to classify Computed Tomography (CT) features in the Marshall System. *BMC Med Res Method*. 2010; 10:72.10.1186/1471-2288-10-72

9. Eppinger, R.; Sun, E.; Kuppa, SR. Supplement: Development of Improve Injury Criteria for the Assessment of Advanced Automotive Restraint Systems –II. I-ITSA; 2000 Mar.
10. Mertz, I-II.; Prasad, P.; Irwin, NL. Injury risk curves for children and adults in frontal and rear collisions (SAE 9733 18). Proceedings of the 41 st Stapp Car Crash Conference (P-3IS); Warrendale, PA: Society of Automotive Engineers; 1997. p. 13-30.
11. Chinn, B.; Canale, B.; Derler, SE.; Doyle, D.; One, D.; Schuller, E.; Willinger, R. COST 327: Motorcycle Safety Helmets. Luxembourg: Office for Official Publications of the European Communities; 2001.
12. Nahum, AM.; Melvin, JW. Accidental injury. Springer-Verlag; New York: 1993.
13. Yoganandan N, Pintar FA. Biomechanics of Temporo-parietal Skull Fracture. Clinical Biomechanics. 2004; 19:225–239. [PubMed: 15003337]
14. O’Riordain K, Thomas PM, Phillips JP, Gilchrist MD. Reconstruction of Real World Injury Accidents Resulting From Falls Using Multibody Dynamics. Clinical Biomechanics. 2003; 18:590–600. [PubMed: 12880706]
15. Fan X, Verpoest I, Vandepitte D. Finite Element Analysis of Out-of-Plane Compressive Properties of Thermoplastic Honeycomb. Journal of Sandwich Structures and Materials. 2006; 8:437–458.
16. Ferguson, J.; Lloyd, JD.; Schulz, B.; Castle, S.; Caccese, V. SBBIR Phase I Project Report No I R43 AG033936-0 1. Alba-Teclmic, LLC; Oct. 2009 Development of Headwear to Prevent Falls Related Injury in Elderly Persons; p. 119

Fig. 1.
Hexagonal cell structure of honeycomb material

Fig. 2.
Instron impact test schematic

Fig. 3.
Basic finite element model geometry

Fig. 4.
Finite element model

a) Peak acceleration and HIC

b) Peak force and Period

Fig. 5.
Response of unprotected drop with varying mass and impact energy

a) Deformation contour

b) with top hidden

Fig. 6.
Buckling deformation for the baseline model

a) no damping

b) with Rayleigh stiffness proportional damping.

Fig. 7.
Time history example for the baseline honeycomb model

Fig. 8.
Maximum acceleration and HIC_{15} vs. impact energy for baseline case

Fig. 9.
Maximum acceleration vs. honeycomb modulus at different input energy

Fig. 10.
Effect of honeycomb thickness for HY=100MPa

Fig. 11.
Effect of honeycomb wall thickness for HY=100MPa

Fig. 12.
Effect of honeycomb cell leg length a

Fig. 13.
Effective of spring stiffness on peak acceleration

Fig. 14. Energy level, spring stiffness and honeycomb depth required to achieve desired peak acceleration

Fig. 15.
Optimization curve for contact model with rigid impactor

Table 1

Value of parameters for the honeycomb model designations

Designation	a, mm	t _w , mm	d, mm	Solid ratio
M1	3.362	0.8	6.4	0.268
M1d	3.362	0.8	6.4	0.268
M2d	3.362	0.8	8.0	0.268
M3d	3.362	0.8	5.0	0.268
M4d	3.362	0.6	6.4	0.203
M5d	3.362	0.4	6.4	0.136
G2d	5.040	0.8	6.4	0.180
G3d	2.241	0.8	6.4	0.398

Table 2

Comparison of peak acceleration vs. input energy for various models

Energy J	Drop Height mm	Maximum Acceleration, g		
		Unprotected 6.35kg	HY 100MPa	HY 250MPa
4.4	70	246	54	84
12.5	200	499	80	127
20.2	325	666	100	150