Published in final edited form as:

J Biomed Mater Res A. 2009 June 15; 89(4): 841–853.

Fibroblasts regulate monocyte response to ECM-derived matrix: The effects on monocyte adhesion and the production of inflammatory, matrix remodeling, and growth factor proteins

Amy S. Chung¹ and Weiyuan John Kao^{1,2}

¹School of Pharmacy, Division of Pharmaceutical Sciences, University of Wisconsin-Madison, Wisconsin

²Department of Biomedical Engineering, College of Engineering, University of Wisconsin-Madison, Wisconsin

Abstract

Monocytes/macrophages and fibroblasts are recruited to the injury site and orchestrate the host response and tissue repair. We have previously shown that polyethylene glycol (PEG)-ylated arginine-glycine-aspartic acid (RGD) sequence grafted onto an extracellular matrix (ECM)-based semi-interpenetrating network (sIPN) enhances monocyte adhesion, and modulates subsequent gene expression and release of inflammatory and matrix remodeling factors. In this study, we investigate the direct influence of fibroblasts on monocyte response to this ECM mimic. Key wound-healing factors in inflammation, matrix remodeling, and regeneration were analyzed to gain insight into the interrelated role of regulation in fibroblast-monocyte interaction. Interleukin-1 α /–1 β (IL-1 /–1), interleukin-6 (IL-6), tumor necrosis factor- (TNF-), monocyte inflammatory protein-1 α /–1 β (MIP-1 /–1), transforming growth factor- α (TGF-), monocyte chemoattractant factor (MCP-1), matrix metalloproteinase-2/–9 (MMP-2/–9), vascular endothelial growth factor (VEGF), granulocyte-macrophage colony-stimulating factor (GM-CSF) were analyzed. Fibroblasts decreased monocyte adhesion onto the RGD-grafted sIPN while increasing monocyte GM-CSF on all surfaces over time except for on RGD and PHSRN-grafted sIPN at 96 h. Monocytes decreased initial fibroblast IL-1 and TGF- , but drastically increased fibroblast MMP-2 and GM-CSF. Monocyte IL-1 , TNF- , MIP-1 , MCP-1, MMP-9, and GM-CSF expression was increased over time in the presence of all sIPNs, and when the sIPNs were immobilized with ligands, a down-regulation of fibroblast IL-1 , MIP-1 , MCP-1 compared with unmodified sIPN was observed. When the ligand immobilized was RGD, monocyte TGF- , MIP-1 , and VEGF expression was increased while monocyte GM-CSF was decreased at selected time points. These results showed a dynamic monocyte response to selected ECM components in the presence of fibroblasts.

Keywords

monocytes/macrophages; fibroblast; interleukin-1; matrix metalloproteinase-2/-9; granulocyte-macrophage colony-stimulating factor; vascular endothelial growth factor

INTRODUCTION

During wound healing, a large number of monocytes are quickly recruited into the site of injury, and they play a crucial role in orchestrating the subsequent tissue repair.^{1–3} Monocyte/macrophage response to the extracellular matrix (ECM) components such as fibronectin, collagen, and gelatin is an active field of research.^{4–7} Some of these ECM proteins contain proline-histidine-serine-arginine-asparagine (PHSRN) and conserved motifs such as arginine-glycine-aspartic acid (RGD) that allow monocyte integrin-mediated cell attachment, focal contact formation, motility, and protein expression.^{8–11} RGD has been utilized extensively to modify biomaterials to promote integrin-mediated cell attachment and we have previously demonstrated that RGD grafted onto an ECM-based semi-interpenetrating network (sIPN) enhances cell adhesion and modulates signaling, and cytokine and gene expression.^{12–15} We have shown that adherent monocyte density was increased by RGD tethered onto a flexible polyethylene glycol (PEG) linker on the gelatin-based sIPN, and that subsequent protein and genetic regulation of IL-1 and MMP-2/–9 were increased in response to sIPNs.^{13,14} RGD-PEG-grafted sIPNs also enhanced cellularity and organized ECM reconstruction over time *in vivo* in dermal wound-healing models.¹⁶

In this study, we sought to investigate the influence of fibroblasts on monocyte response to this ECM mimic. Both fibroblasts and monocytes are present during the granulation stage of wound healing and they coordinate a highly controlled set of inflammatory, ECM production, and breakdown events during wound healing.^{17,18} However, there are few studies investigating the role of fibroblasts in directly regulating human monocyte response to ECM components.^{19–21} Key wound-healing factors in inflammation, matrix remodeling, and regeneration were analyzed to gain insight into the interrelated role of regulation in fibroblast–monocyte interaction.

METHODS AND MATERIALS

Ligand-PEG-grafted gelatin synthesis: PEG-diol modification to Bis-N-hydroxysuccinimide-PEG and Ligand-PEG grafting to gelatin

N-hydroxysuccinimide activated esters were prepared from PEGdiol (2k) as previously described.²² All starting materials were purchased from Aldrich unless otherwise specified. First, bis-t-butylacetate-PEG (Bis-tBuOAc-PEG) was prepared by activating PEG with sodium hydride and then by reacting it with t-butyl bromoacetate for 24 h. T-butyl bromoacetate was filtered and extracted to remove impurities and analyzed by ¹H NMR. Bis-tBuOAc-PEG was then reacted with 4N HCl in dioxane to yield bis-carboxylate-PEG (bis-COOH-PEG). Bis-COOH-PEG was converted to bis-N-hydroxysuccinimide-PEG (bis-NHS-PEG) by adding bis-COOH-PEG to an oxalyl chloride solution (2M in CH₂Cl₂, 15.6 mmol) then adding one drop of catalytic DMF slowly via syringe, under argon, where catalytic DMF refers to one drop of DMF in 1 mL of CH₂Cl₂. In THF cooled to –108C, N-hydroxysuccinimide (NHS) in THF was added (5.71 mmol), followed by pyridine, then stirred for 2 h at room temperature. The bis-NHS-PEG powder was filtered and precipitated in ether then dried. ¹H NMR analysis was carried out to confirm bis-NHS-PEG purity.¹⁶ NHS-mPEG was prepared as described above, but from monomethoxy polyethylene glycol (mPEG) rather than PEGdiol.

RGD and PHSRN for use in preparation of PEGy-lated peptides were prepared following standard solid phase peptide synthesis based on Fmoc resin cleavage and deprotection.^{23,24} Peptide purity was confirmed at >95% with reverse phase high performance liquid chromatography. RGD and PHSRN identity was analyzed with H NMR and MALDI mass spectrometry as described previously (University of Wisconsin Biotechnology Center, Madison, WI).¹⁶ Bis-NHS-PEG (0.43 mmol) was dissolved in 5 mL of DMF and GGG,

RGD, or PHSRN (0.52 mmol) was added, followed by a dropwise addition of *N,N*-diisopropylethylamine (DIPEA) (0.52 mmol). After 45 min, the peptide-PEG solution was poured into a 1% gelatin (0.008 mol gelatin, 0.21 mol lysine) in 1× PBS solution and adjusted to pH 8. For mPEG conjugation onto gelatin backbone, 1.5 g of NHS-mPEG was dissolved in 100 mL of 1× PBS. After 60 min, purification was carried out with a Millipore filter apparatus with a 30 kDa filter, rinsing with pH = 4 DI water. The product was lyophilized and characterized with the 2,4,6-trinitro-benzenesulphonic acid assay for lysyl group modification and with gel permeation chromatography for average molecular weight determination and conjugation.^{25,12} Lysyl modification averaged 70% for mPEG gelatin, 73% for GGG-PEG gelatin, 77% for RGD-PEG gelatin, and 79% for PHSRN-PEG gelatin ($n = 3$).

Preparation of semi-interpenetrating networks

Semi-interpenetrating networks (sIPNs) were prepared as described elsewhere.^{12,13} Briefly, mPEG-gelatin, GGG-PEG-gelatin, RGD-PEG-gelatin, PHSRN-PEG-gelatin, or unmodified gelatin was dissolved in ddH₂O (10% w/v) by heating at 60°C. The gelatin solution was added PEG diacrylate (PEGdA, $M_n \approx 575$ Da) to form a 4:6 gelatin:PEGdA weight ratio. About 20 μ L of 2,2-dimethoxy-2-phenyl-acetophenone (DMPA) initiator solution (0.02 g DMPA in 0.5 g PEGdA) was added to the gelatin/PEGdA mixture, vortexed, and 175 μ L was transferred to the polycarbonate transwell insert (3.0 μ m pore size, $d = 12$ mm, Corning Inc., Corning, NY) and polymerized directly in the insert via exposure to light emitting diode ($\lambda_{max} = 365$ nm at 10 cm) for 5 min. The resultant sIPNs were dipped into a 70% ethanol solution for 30 min for sterilization, rinsed three times with 1× PBS and transferred to 12-well plates to equilibrate for 3 days in 1× PBS all under 48°C. Density of peptide-PEG-grafted sIPN was previously analyzed on RGD-PEG-grafted sIPNs via ELISA using RGD directed antibody.²⁶ We found that accessible RGD concentration (μ mol/mL) on the unmodified sIPN surface was significantly ($p < 0.05$) lower compared with that of RGD-PEG-grafted sIPN.²⁷ sIPN containing transwells and polycarbonate transwells were equilibrated in RPMI 1640 (GIBCO, Calsbad, CA) at 37°C and 5% CO₂ for 2 h prior to monocyte seeding.

Monocyte/fibroblast monoculture and coculture

Neonatal human dermal fibroblasts (NHDF) (Lonza Group Ltd., Switzerland) between passages 4 through 7 were seeded in a 12-well TCPS plate (Corning Inc., Corning, CA) and cultured to a monolayer confluency (approximately >90%) in fibroblast growth media (FGM) plus 5% FBS as previously described.²⁸ Once fibroblasts reached confluency, the media was removed and replaced with RPMI 1640 containing 10% human serum for 3 days prior to the experiment. Effects of the media transition were optimized prior to the experiment and fibroblast confluency/cell density, morphology, and viability on TCPS were monitored at 48 and 168 h. Confluency was unaffected by RPMI with 10% human serum through 168 h and LIVE/DEAD assay (Invitrogen, Carlsbad, CA) confirmed >95% fibroblast viability was also maintained by this media, as observed with FGM supplemented with 5% FBS ($n = 3$). Morphological observations also revealed that the characteristic spindle shape (data not shown) was unaltered by RPMI supplemented with 10% human serum. This indicates that the culture medium employed in the coculture sets in this study did not adversely affect the behavior of fibroblasts.

Human peripheral blood monocytes were isolated from citrated whole blood of a healthy, medication-refrained adult volunteer using a density-gradient, nonadhesion method previously described in detail.^{14,29} Briefly, citrated blood (100 ~ 150 mL) was diluted 1:2 with PBS/5 mM EDTA (PBSE), layered onto Ficoll-Paque (GE Healthcare, Uppsala, Sweden), and centrifuged at 400g for 30 min (no brake). The resultant mononuclear cells

were serially washed three times with 50 volumes of PBSE by centrifugation at 350, 200, and 150g for 10 min each. Cells were resuspended in 2 ~ 3 mL of PBSE, layered onto two 10-mL columns of FBS, and centrifuged at 120g for 10 min. The same procedure was repeated, after which cells were resuspended in 3.5 mL of PBSE, added to 6.7 mL of Percoll (Sigma, St. Louis, MO), mixed, and centrifuged at 2000g for 25 min (no brake). The resultant topmost cell layer (1 mL) was washed twice with 50 volumes of cold RPMI 1640 medium resuspended in cold RPMI 1640, and seeded immediately.

Co-culture set up: Freshly isolated cells were seeded onto each surface on the transwell insert (i.e. polycarbonate transwell or ligand-PEG-grafted sIPN surface) at a concentration of 10^6 cells/mL in RPMI 1640 culture medium and 10% autologous serum at 37°C and 5% CO₂ and cultured up to 96 h. Once the monocytes were seeded onto the transwell insert with or without sIPN, it was immediately but gently placed into the well with a confluent layer of fibroblasts. Figure 1 outlines the monocyte and fibroblast coculture schematic in the presence of the sIPN.

Chamber A refers to the upper chamber where monocytes were seeded and chamber B refers to the bottom chamber where a confluent layer of fibroblasts were cultured. Monocultures were constructed in the same set up as cocultures, but with only monocytes in chamber A for monocyte monocultures and only fibroblasts in chamber B for fibroblast monocultures. While monocytes in monocultures were in direct contact with sIPNs or polycarbonate transwell, a confluent layer of fibroblasts on TCPS in chamber B in fibroblast monocultures were in the presence of, but were not in direct contact with the various surfaces. Supernatants were collected from both chamber A and B at all time points and all monocultures and cocultures.

In separate experiments, small molecule diffusion across the sIPN was also examined with fluorescein (332.31 g/mol, Sigma, St. Louis, MO) at 67 µg/mL in PBS where 0.5 mL of this solution was placed in chamber A and 1.5 mL of PBS without the dye molecule was placed in chamber B and absorbance was measured at 469 nm at 5, 30, 60, and 120 min, all under ambient temperature. Diffusion across chambers was observed as early as 5 min, and by 120 min both chambers had equilibrated with 16.4 µg/mL in chamber A and 13.4 µg/mL in chamber B. A portion of the fluorescein was entrapped within the sIPN thus absorbance readings in both chambers did not reflect the total concentration throughout 120 min. We also observed previously that time to maximum percent released of basic fibroblast growth factor out of the sIPN was 2 h.³⁰

Live/dead adherent monocyte assay, ELISA, and microsphere-based multiplex protein assay

At 2, 24, and 96 h, all surfaces were rinsed with D-PBS and stained with LIVE/DEAD (Invitrogen, Carlsbad, CA). Working dilutions of calcein-AM (2 µM) and ethidium homodimer-1 (4 µM) were made in D-PBS immediately before use. For each sample well in chamber A, a minimum of two different areas at 0.55 mm² each were imaged using an inverted microscope. Confluent fibroblasts in chamber B were not quantified but LIVE/DEAD assay was still carried out for verification of fibroblast viability. Supernatants were collected from both chamber A and B at 2, 24, and 96 h. With the supernatant collected at 2, 24, and 96 h, all proteins were analyzed with the microsphere-based multiplex protein assay (Linco Research, St. Charles, MO), except MMP-2 and MMP-9, where the ELISA (Raybiotech Inc., Norcross, GA) method was used. The ELISA and the microsphere-based multiplex protein assays were carried out according to manufacturers' instructions. The protein concentrations reported contain the concentrations in addition to the protein concentrations from the 10% autologous serum in the media.

Statistical Analysis

Cell adhesion and ELISA data were expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Adherent live cell density data and protein concentrations were analyzed by unpaired Student t-test where $p < 0.05$ was considered statistically significant.

RESULTS AND DISCUSSION

Fibroblasts decrease monocyte adhesion onto RGD-PEG-grafted sIPN

The presence of fibroblasts decreased initial monocyte adhesion on RGD-PEG-grafted sIPN. At 2 h, adherent monocyte density in monocyte monoculture and coculture was significantly higher on RGD-PEG-grafted sIPNs when compared with that on all other surfaces with the exception of unmodified sIPN in coculture (Table I). Furthermore, adherent monocyte density on RGD-PEG-grafted sIPN was approximately twofold less in coculture compared with that in monocyte monoculture at 2 h. On other surfaces, there were no significant differences in adherent monocyte density when comparing monocyte monoculture and coculture at 2 and 24 h. Our previous studies had shown that monocytes adhered at significantly -/GGG-PEG-grafted sIPN when compared with tissue culture polystyrene (TCPS) and PEG-only hydrogels.^{13,31} RGD-PEG-grafted sIPN mediated enhanced monocyte adhesion in a ligand-integrin dependent fashion and that sub-unit 1- and 3-containing integrins were critical in mediating this observation. Although enhanced monocyte adhesion on RGD-grafted surfaces is consistent with others' findings, fibroblasts inhibiting this enhanced monocyte adhesion is unexpected.

Fibroblast-monocyte protein regulation: Attenuated inflammatory and up-regulated growth and matrix remodeling factors

To gain insight into monocyte-fibroblast regulated proteins in the presence of the ECM-derived matrix as a communication conduit, we quantified several growth factors and inflammatory and remodeling proteins. We found that monocyte and fibroblast in coculture resulted in increased GM-CSF concentrations in chambers A and B at 24 and 96 h, except with RGD- and PHSRN-PEG-grafted sIPN at 96 h (Fig. 2). Under monoculture conditions, GM-CSF was expressed by both monocytes and fibroblasts; however, only low levels were expressed in our fibroblast monocultures. Under monocyte monocultures in the presence of the RGD- and PHSRN-grafted sIPN, a significant increase in GM-CSF concentration was observed from 2 to 24 h as observed with other surfaces, but by 96 h, levels were significantly decreased. It has been reported that the integrin $\alpha 5$ subunit mRNA is down-regulated by GM-CSF in a dose-dependent manner.³² In this study, we observed drastically increased GM-CSF levels from 2 to 24 h along with decreased monocyte adhesion on RGD-PEG-grafted sIPN at 2 and 96 h in coculture compared with monoculture. Hence, our results suggest that the decreased monocyte adhesion on RGD-PEG-grafted sIPN in the presence of fibroblasts may be a result of a monocyte-fibroblast regulation that has been indicated in wound healing and likely the down-regulation of monocyte integrin by the increased GM-CSF levels up until 24 h.

Inflammatory factors were also directed by the presence of fibroblasts. In monocyte monocultures, high IL-1 (Fig. 3) and TGF- (Fig. 4) concentrations were observed in chambers A and B at 2 h in the presence of polycarbonate, but the presence of fibro-blasts significantly decreased those concentrations in coculture. Monocytes also attenuated initial fibro-blast IL-1 and TGF- expression. For example, IL-1 concentrations in chambers A and B from fibro-blast monoculture were generally significantly higher at 2 h compared with that from coculture at 2 h, in the presence of all surfaces. Although IL-1 and TGF- were expressed more in monocytes/macrophages, our results indicate that significant expression was also observed in our fibroblast monocultures that was initially decreased in cocultures.

In addition to inflammatory and growth factors, we characterized matrix remodeling factors critical in the proliferation and remodeling phase of wound healing. Monocytes induced fibroblast expression of MMP-2 (Fig. 5). For example, MMP-2 levels from chamber B in fibroblast monocultures were generally consistent from 2 to 96 h. In monocyte monocultures, subtle increases in MMP-2 levels were observed from 2 to 96 h. However, in cocultures versus monocultures, MMP-2 concentrations from chamber B were drastically increased at 96 h to concentrations beyond the detection limit (>18,000 pg/mL). This high concentration was also observed in chamber A only on polycarbonate and sIPN containing unmodified gelatin at 96 h, indicating different protein transport property between the unmodified and ligand-grafted sIPNs. Although both fibroblasts and monocytes express MMP-2, our data indicate that the presence of both cell types enhanced fibroblast MMP-2 expression at 96 h especially with ligand-immobilized sIPN suggesting the synergistic interaction between fibroblasts and monocytes during the matrix remodeling process. Although MMP-2 possesses important implications in tissue remodeling, angio-genesis, and foreign body giant reaction, GM-CSF also plays an important role in these processes and a closely regulated relationship between growth factors and matrix metalloproteases exists.^{2,33,34} GM-CSF has been reported to induce MMP-2 expression and our data shows drastically increased GM-CSF levels at 24 h and MMP-2 concentrations at 96 h only in cocultures and not in monocultures.³⁵ This suggests a monocyte-fibroblast paracrine mediated MMP-2 induction by GM-CSF in coculture. Inflammatory proteins can also induce growth factors and matrix remodeling agents as these factors are also closely intertwined players in activation and regulation of the inflammatory phase that eventually progress through the proliferative and remodeling stage.³⁶ Our data suggest that though initial fibro-blast inflammatory factors could be attenuated, these inflammatory factors increased in concentration with time, and they could up-regulate growth and matrix remodeling factors.

ECM-derived matrix mediated monocyte-fibroblast protein regulation: Expression and transport are dependent on sIPN and ligand immobilization of the sIPN

Although culture condition (i.e. coculture versus monoculture) mediated IL-1 β , TGF- β , GM-CSF, and MMP-2 expression, the ECM-based sIPN predominantly mediated the expression of other monocyte inflammatory and remodeling proteins such as IL-1 β , TNF- α , MIP-1 α , and MMP-9. In both monocyte monoculture and coculture, the presence of sIPNs significantly elevated IL-1 β (Fig. 6), TNF- α (data not shown), and MIP-1 α (Fig. 7) concentrations from 2 to 24 h in chamber A when compared with the polycarbonate controls. MCP-1 concentrations in chamber A also increased in monocyte monocultures and cocultures in the presence of all sIPNs at 24 and 96 h when compared with the polycarbonate controls (data not shown). As inflammatory factors such as TNF- α and IL-1 β have been reported to stimulate MCP-1 levels in various cell types, the sIPN substrata's modulation of these inflammatory proteins may hold a critical role in activation of a cascade of events crucial to wound healing.^{37,38} Furthermore, MMP-9 levels at 96 h in chamber A were significantly elevated in the presence of sIPNs and not the polycarbonate controls in both cocultures and monocyte monocultures (Fig. 8). These results are consistent with others' findings that the ECM substratum can play a critical role in increasing MMP-9 levels over time.^{39,40} GM-CSF levels at 24 h were also increased in response to the ECM-derived matrix, but in cocultures, this increase was amplified by the presence of fibroblasts. Additionally, TNF- α and IL-1 β have been shown in literature to be common inducers of matrix remodeling and growth factors such as MMP-9 and GM-CSF.⁴¹⁻⁴³ The inflammatory proteins and the ECM-derived sIPN are likely to have a cooperative enhancement effect on GM-CSF and MMP-9 expression.

In addition to sIPN-mediated effects, ligand immobilization on the sIPNs led to varied protein expression and transport compared with unmodified sIPN. In the presence of unmodified sIPN, TGF- β concentrations in chambers A and B were generally significantly lower at 24 h and significantly higher at 2 and 24 h in monocyte and fibroblast monocultures, respectively, when compared with sIPN immobilized with ligand. IL-1 concentrations in chambers A and B at 24 h were significantly higher with unmodified sIPN when compared with ligand-grafted sIPN in monocyte and fibroblast monocultures. In fibroblast monoculture, IL-1 in chambers A and B were significantly higher with unmodified sIPNs versus ligand-grafted sIPN at 2 h as well, and MIP-1 (data not shown) and MIP-1 also showed higher concentrations at 2 h in the presence of unmodified sIPN compared with ligand-grafted sIPN. The increased inflammatory agents IL-1, MIP-1, and MIP-1 could be the result of the greater rate of gelatin dissolution from the unmodified sIPN versus the ligand-PEG-grafted sIPN that we have observed previously and in separate experiments (data not shown).⁴⁴ Taken together, the immobilization of the ligand-PEG on the sIPN appears to down-regulate certain key proinflammatory mediators such as IL-1, MIP-1, and MIP-1 in fibroblast monocultures. Additionally, the matrix also regulated the transport of these proteins, depending on ligand immobilization on the sIPN. For TNF- α (data not shown), we observed concentrations at 24 h in chamber B that were significantly higher in the presence of unmodified gelatin compared with all other ligand immobilized sIPN in monocyte monocultures, though concentrations in chamber A at 24 h did not differ in the presence of unmodified sIPN compared to other ligand immobilized sIPN. Similarly, MMP-2 concentrations in chamber B at 96 h were over the detection limit of 18000 pg/mL in the presence of all surfaces while, in chamber A at 96 h, only those in the presence of polycarbonate and unmodified sIPN reflected the concentrations over the detection limit. These results indicate a selective transport property for TNF- α and MMP-2 across the peptide-modified sIPN and that this selectivity is less observed in unmodified sIPN. Although sIPN with or without grafted peptides enhanced the expression of monocyte proinflammatory and matrix remodeling regulator, the effect of these proteins on an effector cell would be decreased by the inhibited transport of these proteins through the sIPN ECM mimics. These sIPNs are rather porous hydrogels and the mesh structure would restrict diffusive movement of a solute and the addition of polymer chains would cause an increase in diffusion path length.^{45,46} Furthermore, diffusive passage of proteins through the sIPNs as well as other hydrogel systems depends on the protein's molecular weight, hydrodynamic radius, and ionic interactions with other solutes, properties that remain incompletely understood.^{46,47}

ECM-derived matrix-mediated monocyte-fibroblast protein regulation: Expression is mediated by identity of peptide grafted on the sIPN

We have observed that ligand immobilized sIPN induced varied protein expression and transport from unmodified sIPN. In addition to these findings, we observed that the identity of grafted peptides also induced peptide-specific protein expression. We identified decreased GM-CSF levels in the presence of RGD and PHSRN-grafted sIPN as described above. We also measured elevated TGF- β concentrations at 24 h in cocultures in the presence of RGD and PHSRN-grafted sIPN compared with other ligand-grafted sIPN. Also in cocultures, we observed increased concentrations of MIP-1 at 96 h and VEGF (Fig. 9) at 24 h and in the presence of grafted RGD but not PHSRN and RGD and PHSRN, respectively, when compared with other sIPN. It has been reported that integrin $\alpha_3\beta_1$ mediates and activates various intracellular signaling pathways involved in proliferation and differentiation secondary to multiple growth factor receptors such as VEGF.⁴⁸ Furthermore, the presence of monocytes and sIPN-enhanced fibroblast matrix remodeling expression in terms of elevated GM-CSF and MMP-2. Postligation signaling and phenotypic expression modulated by RGD and PHSRN in monocyte and fibroblasts are unclear at the moment. However, these data

indicate divergent downstream effects of these ligands in monocytes and fibroblasts, perhaps in response to other stimuli as a part of signal proofreading and cooperative regulation. Recognition and signaling activities can be mediated solely by integrins (private functions), but integrins can also have public activities in which they interact physically with other plasma membrane receptors to elicit cellular responses to ligands that do not bind directly to integrins. In monocytes, this relationship has been established for several systems: (i) monocyte $\alpha 4 \beta 1$ integrin is activated through the G protein-coupled receptor binding of MCP-1 and MIP-1 chemokines; (ii) integrin ($\alpha v \beta 3$, $\alpha 5 \beta 1$, $\alpha v \beta 5$, $\beta 1$ superfamily) crosstalk with growth factor receptors (i.e., platelet derived growth factor, basic fibroblast growth factor, epithelial growth factor, VEGF) has been implicated in the cooperative regulation of 100–120 monocyte genes when adhered to fibronectin.^{49–52} For the latter, these cross-talks occur in several fashions including shared signaling molecules and coclustering of receptors in the formation of focal adhesion. Thus fibroblasts in coculture with monocytes can mediate physical and intermolecular monocyte interactions with the sIPN.

In this investigation, we have shown that fibroblasts decrease monocyte adhesion onto RGD-PEG-grafted sIPN while increasing monocyte GM-CSF except on RGD and PHSRN-grafted sIPNs at 96 h. The presence of monocytes decreased initial fibroblast IL-1 β , TGF- β , and VEGF, but increased MMP-2 and GM-CSF at later time points. Furthermore, the ECM-derived sIPNs led to increased monocyte IL-1 β , TNF- α , MIP-1 α , MCP-1, MMP-9, and GM-CSF expression. Ligand immobilization of the sIPNs led to a down-regulation of fibroblast IL-1 β , MIP-1 α , MIP-1 β compared with unmodified sIPN. When the ligand immobilized on the sIPN was RGD, increased TGF- β , MIP-1 α , and VEGF but decreased GM-CSF expression at selected time points was observed. Figure 10 summarizes the effects of a secondary cell type and of the sIPN substrata on monocyte and fibroblast protein expression. These results shed light into the dynamic monocyte adhesion, and inflammatory, matrix remodeling, and growth factor response to the ECM mimic in the presence of fibroblasts in wound healing.

Acknowledgments

Contract grant sponsor: NIH; contract grant numbers: R01 HL077825, R01 EB006613

Contract grant sponsor: NSF Predoctoral Fellowship; contract grant number: 2006043753

The authors thank Heather Waldeck for her guidance in the immunoassay and Dr. Qiang Gao for his assistance with media optimization.

References

1. Singer AJ, Clark RAF. Cutaneous wound healing. *New Eng J Med*. 1999; 341:738–746. [PubMed: 10471461]
2. Schaffer CJ, Nanney LB. Cell biology of wound healing. *Int Rev Cytol*. 1996; 169:151–181. [PubMed: 8843654]
3. Park JE, Barbul MD. Understanding the role of immune regulation in wound healing. *Am J Surg*. 2004; 187:11S–16S. [PubMed: 15147986]
4. Jenney CR, Anderson JM. Adsorbed serum proteins responsible for surface dependent human macrophage behavior. *J Biomed Mater Res*. 2000; 49:435–447. [PubMed: 10602077]
5. Garnotel R, Sabbah N, Jaisson S, Gillery P. Enhanced activation of and increased production of matrix metalloproteinase-9 by human blood monocytes upon adhering to carbamylated collagen. *FEBS Lett*. 2004; 563(1–3):13–16. [PubMed: 15063715]
6. Xia Z, Triffitt JT. A review on macrophage response to bio-materials. *Biomed Mater*. 2006; 1:R1–R9. [PubMed: 18458376]

7. Penc SF, Blumenstock FA, Kaplan JE. 70-kDa amino-terminal fibronectin fragment supports gelatin binding to macro-phages and decreases gelatinase activity. *J Leukoc Biol.* 1998; 64:351–357. [PubMed: 9738662]
8. Kao WJ, Lee D, Schense JC, Hubbell JA. Fibronectin modulates macrophage adhesion and FBGC formation: The role of RGD PHSRN, and PRRARV domains. *J Biomed Mater Res.* 2000; 55:79–88. [PubMed: 11426401]
9. Massia SP, Hubbell JA. An RGD spacing of 440 nm is sufficient for integrin $\alpha 3$ -mediated fibroblast spreading and 140 nm for focal contact and stress fiber formation. *J Cell Biol.* 1991; 114:1089–1100. [PubMed: 1714913]
10. Mann BK, West JL. Cell adhesion peptides alter smooth muscle cell adhesion, proliferation, migration, and matrix protein synthesis on modified surfaces and in polymer scaffolds. *J Biomed Mater Res.* 2002; 60:86–93. [PubMed: 11835163]
11. Cutler SM, Garcia AJ. Engineering cell adhesive surfaces that direct integrin $\alpha 5$ binding using a recombinant fragment of fibronectin. *Biomaterials.* 2003; 24:1759–1770. [PubMed: 12593958]
12. Phillips JM, Kao WJ. Macrophage adhesion on gelatin-based interpenetrating networks grafted with PEGylated RGD. 2005; 11(5/6):964–973.
13. Chung AS, Gao Q, Kao WJ. Either integrin subunit $\alpha 1$ or $\alpha 3$ is involved in mediating monocyte adhesion IL-1 protein and mRNA expression in response to surfaces functionalized with fibronectin-derived peptides. *J Biomater Sci Polym Ed.* 2007; 18:713–729. [PubMed: 17623553]
14. Chung AS, Gao Q, Kao WJ. Macrophage matrix metalloproteinase-2/-9 gene and protein expression following adhesion to ECM-derived multifunctional matrices via integrin complexation. *Biomaterials.* 2007; 28:285–298. [PubMed: 16979234]
15. Gao Q, Chung AS, Kao WJ. Monocytic U937 adhesion, tumor necrosis factor- α and interleukin-1 β expression in response to gelatin-based networks grafted with arginine-glycine-aspartic acid and proline-histidine-serine-arginine-asparagine oligopeptides. *Tissue Eng.* 2007; 13:179–185. [PubMed: 17518591]
16. Waldeck HM, Chung AS, Toth M, Williams K, Kao WJ. Interpenetrating networks containing gelatin modified with PEGylated RGD and soluble KFG: Synthesis characterization application in in vivo critical dermal wound. *J. Biomed Mater Res A.* 2007; 82:861–871. [PubMed: 17335014]
17. Weihrauch D, Arras M, Zimmermann R, Schaper J. Importance of monocytes/macrophages and fibroblasts for healing of micronecroses in porcine myocardium. *Mol Cell Biochem.* 1995; 147(1/2):13–19. [PubMed: 7494542]
18. Concannon MJ, Barrett BB, Adelstein EH, Thorton WH, Puckett CL. The inhibition of fibroblast proliferation by a novel monokine: An in vitro and in vivo study. *J Burn Care Rehabil.* 1993; 14(Part 1):141–147. [PubMed: 8501100]
19. Bonfield TL, Colton E, Anderson JM. Fibroblast stimulation by monocytes cultured on protein adsorbed biomedical polymers I Biomer and polydimethylsiloxane. *J Biomed Mater Res.* 1991; 25:165–175. [PubMed: 2055914]
20. Skold CM, Liu XD, Umino T, Zhu YK, Ertl RF, Romberger DJ, Rennard SI. Blood monocytes attenuate lung fibroblast contraction of three-dimensional collagen gels in coculture. *Am J Physiol Lung Cell Mol Physiol.* 2000; 279:L667–L674. [PubMed: 11000126]
21. Zhu Y, Liu XD, Skold CM, Wang H, Kohyama T, Wen FQ, Ertl RF, Rennard SI. Collaborative interactions between neutrophil elastase and metalloproteinases in extracellular matrix degradation in three-dimensional collagen gels. *Respir Res.* 2001; 2:300–305. [PubMed: 11686900]
22. Waldeck HM, Kao WJ. Extended interaction of $\beta 1$ integrin subunit-deficient cells (GD25) with surfaces modified with fibronectin-derived peptides: Culture optimization, adhesion and cytokine panel studies. *Acta Biomaterialia.* 2008; 4:1172–1186. [PubMed: 18514047]
23. Fields, GB. *Solid Phase Peptide Synthesis.* San Diego: Academic Press; 1997. p. 780
24. Chan, WC.; White, PD. *Fmoc Solid Phase Peptide Synthesis: A Practical Approach.* New York: Oxford University Press; 2000. p. 368
25. Einerson NJ, Stevens KR, Kao WJ. Synthesis and physiochemical analysis of gelatin-based hydrogels for drug carrier matrices. *Biomaterials.* 2002; 24:509–523. [PubMed: 12423606]

26. Benoit DS, Anseth KS. The effect on osteoblast function of colocalized RGD and PHSRN epitopes on PEG surfaces. *Bio-materials*. 2005; 26:5209–5220.
27. Chung AS, Waldeck HM, Schmidt DR, Kao WJ. Monocyte inflammatory and matrix remodeling response modulated by grafted ECM-derived ligand concentration. *J Biomed Mater Res A*. 2008 Dec 2. Epub ahead of print.
28. Witte RP, Kao WJ. Keratinocyte-fibroblast paracrine interaction: The effects of substrate and culture condition. *Biomaterials*. 2005; 26:3673–3682.
29. McNally AK, Anderson JM. Complement C3 participation in monocyte adhesion to different surfaces. *Proc Natl Acad Sci USA*. 1994; 91:10119. [PubMed: 7937848]
30. Burmania JA, Martinez-Diaz GJ, Kao WJ. Synthesis and physicochemical analysis of interpenetrating networks containing modified gelatin and poly(ethylene glycol) diacrylate. *J Biomed Mater Res A*. 2003; 67:224–234. [PubMed: 14517880]
31. Schmidt DR, Kao WJ. Monocyte activation in response to polyethylene glycol hydrogels grafted with RGD and PHSRN separated by interpositional spacers of various lengths. *J Biomed Mater Res A*. 2007; 83:617–625. [PubMed: 17503491]
32. Feng X, Teitelbaum SL, Quiroz ME, Towler DA, Ross FP. Cloning of the murine beta5 integrin subunit promoter: Identification of a novel sequence mediating granulocyte-macrophage colony stimulating factor-dependent repression of beta5 integrin gene transcription. *J Biol Chem*. 1999; 274:1366–1374. [PubMed: 9880508]
33. Jansen PL, Kever M, Rosch R, Krott E, Jansen M, Alfonso-Jaume A, Dooley S, Klinge U, Lovett DH, Mertens PR. Polymeric meshes induce zonal regulation of matrix metalloproteinase-2 gene expression by macrophages and fibroblasts. *FASEB J*. 2007; 21:1047–1057. [PubMed: 17215487]
34. Kuzuya M, Iguichi A. Role of matrix metalloproteinases in vascular remodeling. *J Atheroscler Thromb*. 2003; 10:275–282. [PubMed: 14718744]
35. Tomita T, Fujii M, Tokumaru Y, Kanke M, Yamashita T, Ishiguro R, Kanzaki J, Kameyama K, Otani Y. Granulocyte macrophage colony-stimulating factor upregulates matrix metalloproteinase-2 (MMP-2) and membrane type-1 MMP (MT1-MMP) in human head and neck cancer cells. *Cancer Lett*. 2000; 156:83–91. [PubMed: 10840163]
36. Boughton G II, Janis JE, Attinger CE. The basic science of wound healing. *Plast Reconstr Surg*. 2006; 117:12S–34S. [PubMed: 16799372]
37. Zickus C, Kunkel SL, Simpson K, Evanoff H, Glass M, Strieter RM, Lukacs NW. Differential regulation of C-C chemokines during fibroblasts-monocyte interactions: Adhesion vs inflammatory cytokine pathways. *Med Inflamm*. 1998; 7:269–274.
38. Ozaki K, Hanazawa S, Takeshita A, Chen Y, Watanabe A, Nishida K, Miyatay Y, Kitano S. Interleukin-1 and tumor necrosis factor-alpha stimulate synergistically the expression of monocyte chemoattractant protein-1 in fibroblastic cells derived from human periodontal ligament. *Oral Microbiol Immunol*. 1996; 11:109–114. [PubMed: 8941762]
39. Jacob SS, Sudhakaran PR. Molecular mechanism involved in matrix dependent upregulation of matrix metalloproteinases in monocyte/macrophage. *J Biochem Mol Biol Biophys*. 2002; 6:335–340. [PubMed: 12385969]
40. Sudhakaran PR, Radhika A, Jacob SS. Monocyte macrophage differentiation in vitro: Fibronectin-dependent upregulation of certain macrophage-specific activities. *Glycoconjugate J*. 2007; 24:49–55.
41. Marom B, Rahat MA, Lahat N, Weiss-Cerem L, Kinarty A, Bitterman H. Native and fragment fibronectin oppositely modulate monocyte secretion of MMP-9. *J Leukocyte Biol*. 2007; 81:1466–1476. [PubMed: 17327485]
42. Wilson SE, Lloyd SA. Epidermal growth factor and its receptor, basic fibroblast growth factor, transforming growth factor beta-1, and interleukin-1 alpha messenger RNA production in human corneal endothelial cells. *Invest Ophthalmol Vis Sci*. 1991; 32:2747–2756. [PubMed: 1716619]
43. Yokoo T, Kitamura M. Dual regulation of IL-1 beta-mediated matrix metalloproteinase-9 expression in mesangial cells by NF-kappa B and AP-1. *Am J Physiol*. 1996; 270(Part 2):F123–F130. [PubMed: 8769830]
44. Martinez-Diaz GJ, Nelson D, Crone WC, Kao WJ. Mechanical and chemical analysis of gelatin-based hydrogel degradation. *Macromol Chem Phys*. 2003; 204:1898–1908.

45. Burmania JA, Stevens KR, Kao WJ. Cell interaction with protein-loaded interpenetrating networks containing modified gelatin and poly(ethylene glycol) diacrylate. *Biomaterials*. 2003; 24:3921–3930. [PubMed: 12834587]
46. Amsden B. Solute diffusion within hydrogels: Mechanisms and models. *Macromolecules*. 1998; 31:8382–8395.
47. Erikson A, Andersen HN, Naess SN, Sikorski P, Davies CL. Physical and chemical modifications of collagen gels: Impact on diffusion. *Biopolymers*. 2007; 89:135–143. [PubMed: 17957715]
48. Soldi R, Mitola S, Strasly M, Defilippi P, Tarone G, Bussolino F. Role of alphavbeta3 integrin in the activation of vascular endothelial growth factor receptor-2. *EMBO J*. 1999; 18:882–892. [PubMed: 10022831]
49. Petty HR, Worth RG, Todd RF III. Interactions of integrins with their partner proteins in leukocyte membranes. *Immunol Res*. 2002; 25:75–95. [PubMed: 11868935]
50. Chan JR, Hyduk SJ, Cybulsky MI. Chemoattractants induce a rapid and transient upregulation of monocyte $\alpha 4$ integrin affinity for vascular cell adhesion molecule 1 which mediates arrest: An early step in the process of emigration. *J Exp Med*. 2001; 193:1149–1158. [PubMed: 11369786]
51. da Costa Martins PA, van Gils JM, Mol A, Hordijk PL, Zwa-ginga JJ. Platelet binding to monocytes increases adhesive properties of monocytes by up-regulating the expression and functionality of $\beta 1$ and $\beta 2$ integrins. *J Leuk Biol*. 2006; 79:499–507.
52. Newton RA, Thiel M, Hogg N. Signaling mechanisms and the activation of leukocyte integrins. *J Leukoc Biol*. 1997; 61:422–426. [PubMed: 9103228]

Figure 1.

Monocyte/fibroblast coculture setup with the sIPN schematic outlined. [Color figure can be viewed in the online issue, which is available at www.interscience.wiley.com.]

Figure 2.

GM-CSF concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: § from monocyte monoculture, * from fibroblast monoculture, $^{\#}$ from all other surfaces, t from polycarbonate transwell surface, u different from unmodified sIPN, m from methoxy-PEG-grafted sIPN, g from GGG-PEG-grafted sIPN, r from RGD-PEG-grafted sIPN, p from PHSRN-PEG-grafted sIPN.

Figure 3.

IL-1 concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: §from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, ‡from methoxy-PEG-grafted sIPN, §from GGG-PEG-grafted sIPN, ¶from RGD-PEG-grafted sIPN, ¶from PHSRN-PEG-grafted sIPN.

Figure 4. TGF- α concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: §from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, ‡different from unmodified sIPN, §from methoxy-PEG-grafted sIPN, ¶from GGG-PEG-grafted sIPN, †from RGD-PEG-grafted sIPN, ‡from PHSRN-PEG-grafted sIPN.

Figure 5. MMP-2 concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: §from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, udifferent from unmodified sIPN, mfrom methoxy-PEG grafted sIPN, sfrom GGG-PEG-grafted sIPN, rfrom RGD-PEG-grafted sIPN, ffrom PHSRN-PEG grafted sIPN. Over the detection limit of 18,000 pg/mL.

Figure 6.

IL-1 concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: \$from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, ‡different from unmodified sIPN, ¶from methoxy-PEG-grafted sIPN, §from GGG-PEG-grafted sIPN, †from RGD-PEG-grafted sIPN, ¶from PHSRN-PEG-grafted sIPN.

Figure 7.

MIP-1 β concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: §from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, ‡different from unmodified sIPN, §from methoxy-PEG-grafted sIPN, ¶from GGG-PEG-grafted sIPN, †from RGD-PEG-grafted sIPN, §from PHSRN-PEG-grafted sIPN.

Figure 8. MMP-9 concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: §from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, †from polycarbonate transwell surface, ‡different from unmodified sIPN, †from methoxy-PEG-grafted sIPN, §from GGG-PEG grafted sIPN, †from RGD-PEG-grafted sIPN, ‡from PHSRN-PEG-grafted sIPN.

Figure 9. VEGF concentrations (pg/mL) over time from various culture conditions and on various substrates. All values expressed as the mean of triplicate wells $\pm$ standard deviation ($n = 3$). Significantly different ($p < 0.05$) within time, surface, and chamber: [§]from monocyte monoculture, *from fibroblast monoculture, #from all other surfaces, ^tfrom polycarbonate transwell surface, ^udifferent from unmodified sIPN, ^mfrom methoxy-PEG-grafted sIPN, ^gfrom GGG-PEG-grafted sIPN, ^rfrom RGD-PEG-grafted sIPN, ^pfrom PHSRN-PEG-grafted sIPN.

Figure 10.

Monocyte response to the ECM-derived sIPNs (A) and monocyte response to RGD-PEG-grafted sIPN (B). Monocyte interaction with sIPN led to increased IL-1, TNF-, MIP-1, MCP-1, MMP-9, and GM-CSF concentrations over time. Elevated levels of monocyte GM-CSF as a result of interaction with the sIPN were amplified by the presence of fibroblasts. Monocytes attenuated fibroblast TGF-, IL-1, and VEGF at selected time points but drastically increased fibroblast GM-CSF and MMP-2 release. On RGD-PEG-grafted sIPN at selected time points, monocyte TGF-, MIP-1, and VEGF were increased, but GM-CSF was decreased.

TABLE I

Adherent Live Monocyte Density (cell/mm²) on Various Surfaces at 2, 24, and 96 h Under Monocyte Monoculture or Monocyte/Fibroblast Coculture Conditions

	Surface/Ligand-PEG-Grafted sIPN	Culture Time (h)		
		2	24	96
Monocyte Monoculture	Polycarbonate transwell	62 ± 25	27 ± 7 [*]	18 ± 5 [*]
	Unmodified gelatin	138 ± 15 ^t	72 ± 20 ^{g,p}	85 ± 31 ^{m,p}
	Methoxy-PEG	156 ± 74	125 ± 47	30 ± 5
	GGG-PEG	158 ± 38 ^t	142 ± 18	53 ± 21
	RGD-PEG	609 ± 90 ^{g,t}	296 ± 43 [†]	174 ± 27 ^{g,t}
	PHSRN-PEG	121 ± 35	126 ± 12	76 ± 22 ^g
Monocyte/fibroblast coculture	Polycarbonate transwell	39 ± 7 [*]	48 ± 20 [*]	27 ± 4
	Unmodified gelatin	225 ± 58 [#]	111 ± 31	73 ± 7 ^t
	Methoxy-PEG	92 ± 2	126 ± 14	54 ± 20
	GGG-PEG	95 ± 23	114 ± 11	30 ± 13 ^u
	RGD-PEG	273 ± 24 [†]	340 ± 48 [†]	99 ± 18 ^{t,m,g}
	PHSRN-PEG	116 ± 23	141 ± 35	24 ± 9

All values expressed as the mean of triplicate wells ± standard deviation ($n = 3$). Significantly different within time point and surface ($p < 0.05$):

^g Higher than those under coculture conditions. Significantly different within time point and culture condition ($p < 0.05$):

^{*} Lower than all surfaces,

[†] higher than all surfaces,

[#] higher than all surfaces except RGD-PEG-grafted sIPN,

[†] higher than all surfaces except unmodified gelatin sIPN,

^t higher than polycarbonate transwell surface,

^m lower than methoxy-PEG-grafted sIPN,

^g lower than GGG-PEG-grafted sIPN,

^p lower than PHSRN-PEG-grafted sIPN.