Biomechanical comparison of vertebral augmentation with silicone and PMMA cement and two filling grades

Tobias L. Schulte · Alexander Keiler · Felix Riechelmann · Tobias Lange · Werner Schmoelz

Received: 4 March 2013 / Revised: 7 June 2013 / Accepted: 8 July 2013 / Published online: 24 July 2013
© Springer-Verlag Berlin Heidelberg 2013

Abstract

Purpose Vertebral augmentation with PMMA is a widely applied treatment of vertebral osteoporotic compression fractures. Subsequent fractures are a common complication, possibly due to the relatively high stiffness of PMMA in comparison with bone. Silicone as an augmentation material has biomechanical properties closer to those of bone and might, therefore, be an alternative. The study aimed to investigate the biomechanical differences, especially stiffness, of vertebral bodies with two augmentation materials and two filling grades.

Methods Forty intact human osteoporotic vertebrae (T10–L5) were studied. Wedge fractures were produced in a standardized manner. For treatment, PMMA and silicone at two filling grades (16 and 35 % vertebral body fill) were assigned to four groups. Each specimen received 5,000 load cycles with a high load range of 20–65 % of fracture force, and stiffness was measured. Additional low-load stiffness measurements (100–500 N) were performed for intact and augmented vertebrae and after cyclic loading.

Results Low-load stiffness testing after cyclic loading normalized to intact vertebrae showed increased stiffness with 35 and 16 % PMMA (115 and 110 %) and reduced stiffness with 35 and 16 % silicone (87 and 82 %). After cyclic loading (high load range), the stiffness normalized to the untreated vertebrae was 361 and 304 % with 35 and 16 % PMMA, and 243 and 222 % with 35 and 16 %

silicone augmentation. For both high and low load ranges, the augmentation material had a significant effect on the stiffness of the augmented vertebra, while the filling grade did not significantly affect stiffness.

Conclusions This study for the first time directly compared the stiffness of silicone-augmented and PMMA-augmented vertebral bodies. Silicone may be a viable option in the treatment of osteoporotic fractures and it has the biomechanical potential to reduce the risk of secondary fractures.

Keywords Silicone · PMMA · Vertebral augmentation · Elastoplasty · Vertebroplasty · Osteoporosis · Compression fracture · Stiffness

Introduction

Vertebroplasty (VP) using polymethylmethacrylate (PMMA) cement is a widely used form of treatment for vertebral osteoporotic compression fractures. However, there is still a lack of consensus regarding the clinical long-term efficacy and superiority of this technique in comparison with conservative treatment [1–9]. Reported complications, possibly due to the addition of a material that is stiffer than the surrounding bone, include fractures of the augmented and adjacent vertebrae. New osteoporotic vertebral compression fractures, in the months after VP, are reported in 7–63 % of VP patients, up to 82 % of these occur at the adjacent levels, with adjacent fractures occurring sooner than nonadjacent fractures; rates of recurrent fracture of the augmented vertebra itself range up to 63 % in the literature [1, 10–26]. It is still under debate whether new vertebral fractures appear more often in patients who received cement augmentation than in

T. L. Schulte · T. Lange
Department of Orthopedics and Tumor Orthopedics,
Münster University Hospital, Münster, Germany

A. Keiler · F. Riechelmann · W. Schmoelz (✉)
Department of Trauma Surgery, Medical University Innsbruck,
Anichstr. 35, 6020 Innsbruck, Austria
e-mail: werner.schmoelz@uki.at

conservatively treated patients; some studies support this hypothesis [1, 6, 7, 27–29], while others question it [2, 3, 26, 30]. Reducing the augmentation volume [31], using low-modulus PMMA [32] and prophylactic augmentation of adjacent vertebrae [13, 25, 33] have been proposed as ways of minimizing the risk of subsequent fractures. In particular, a need for materials with less stiffness has been identified to prevent this adverse effect of VP [34].

VK100 (BONWRX, Phoenix, AZ, USA), a two-component injectable, self-curing elastomeric material (“silicone”), is a new alternative material available for vertebral augmentation. VK100 was engineered to be less stiff than PMMA and to have a stiffness in the same range as cancellous bone. It is hypothesized that an augmentation material with mechanical properties similar to those of cancellous bone may reduce the rates of adjacent fractures and vertebral sintering [32].

The aim of the present biomechanical in vitro cadaver study was to compare the stiffness of vertebrae augmented with VK100 and PMMA using two different filling grades.

Materials and methods

Forty human intact vertebrae (T10–L5, mean age 75.3 ± 13.9 years) were evenly distributed in four groups, each consisting of ten vertebrae with identical levels and comparable bone mineral density (BMD). To exclude vertebrae with previous fractures, a qCT was conducted (GE Lightspeed 16, GE Medical Systems, Waukesha, WI, USA), and trabecular BMD was measured. Mean trabecular BMD was $74.4 \pm 22.5 \text{ mg/cm}^3$, osteoporosis was, therefore, present [35].

To create fractures, the vertebral bodies were compressed by 30 % of their intact anterior height (loading rate 5 mm/min) using a servohydraulic biaxial material testing machine (858 Mini Bionix II; MTS, Eden Prairie, Minnesota, USA). The wedge fracture was created in a specially designed adjustable jig, allowing a standardized load application in the ventral third of the vertebral bodies for fracture creation and subsequent cyclic loading (Fig. 1) [36]. The ventral third of each vertebral body was determined using axial fluoroscopy images of each single vertebrae.

The intact vertebral body volume (excluding pedicles) was determined prior to fracture using the Archimedes principle. For fracture treatment, two different filling materials, PMMA (CementoFixx, Optimed, Ettlingen, Germany) and VK100 (BONWRX, Phoenix, AZ, USA), and two different filling grades (16 and 35 % of intact vertebral body volume filling) were assigned to the four groups. These filling grades resulted in an average augmentation volume of 5.4 ml for the 16 % filling groups and 11.8 ml for the 35 % augmentation groups. According to

Fig. 1 The test setup in the material testing machine, with adjustable load application via ball-and-socket joints and a hinge joint at the dorsal side used to provoke a vertebral wedge fracture and for cyclic loading

the literature, 16 % filling is required to restore the biomechanical properties and 35 % filling is equivalent to endplate-to-endplate filling [32, 37, 38]. An experienced senior spine surgeon performed a bipedicular VP in each vertebra under fluoroscopic guidance.

Each augmented specimen was subjected to 5,000 load cycles (0.5 Hz) using the same jig, load application point (ventral third), and material testing machine as for fracture creation. To standardize the cyclic load magnitude, each vertebral body was sinusoidally loaded between 20 and 65 % of the compressive force initially required to fracture the corresponding vertebra (high load range).

The stiffness of the vertebra being treated was calculated for cyclic loading and normalized to the corresponding stiffness of the intact vertebrae determined during fracture creation (high load range 20–65 % of fracture force). Additional low load magnitude stiffness measurements in the load range between 100 and 500 N (loading rate 50 N/s) were carried out for the intact vertebra, after augmentation and at the end of the cyclic loading (low load range). Height loss of the augmented vertebrae and the elastic per cycle motion in the course of cyclic loading were determined from the displacement of the load application point. For height loss measurements, the initial ten cycles were taken as preconditioning of the augmented specimens.

Statistical analysis was carried out using SPSS version 20 and included a one way ANOVA with repeated measurements of the tested conditions in the course of the experiment and a two way ANOVA with Bonferroni post-hoc test to evaluate the effect of the material and the filling grade. The level of significance was set to 0.05.

Results

Fracture loads of the four groups were comparable ($p = 0.67$): $3,667 \pm 1,062$ N (35 % PMMA), $3,409 \pm 683$ N (35 % VK100), $3,208 \pm 856$ N (16 % VK100) and $3,009 \pm 863$ N (16 % PMMA). Wedge type fractures with intact posterior walls could be created in all specimens.

Normalized to the intact vertebra the low-load stiffness tests (100–500 N) showed an initial stiffness reduction after augmentation (Fig. 2) for both filling materials and grades ($p < 0.05$). In comparison with the augmented stiffness, the low-load stiffness increased significantly ($p < 0.05$) after the cyclic loading period in all of the test groups. In comparison with the intact vertebra, the stiffness after cyclic loading increased in the 16 and 35 % PMMA augmented vertebra (110 and 115 %) and decreased in the 16 and 35 % VK100 augmented vertebra (82 and 87 %). When the materials for the two filling grades were pooled at the end of cyclic loading, significant differences in stiffness were noted between PMMA and VK100 ($p = 0.01$), whereas the difference between the filling grades (16 or 35 %) was not significantly independent of the filling material ($p = 0.591$).

Normalized to the intact vertebra, the high-load range stiffness (20–65 % of fracture load) at the end of the cyclic loading was 361 and 304 % for the 35 and 16 % PMMA

Fig. 2 Box plot of the stiffness normalized to the intact state for low load magnitude (100–500 N) for augmented and postcyclic states

Fig. 3 Box plot of the stiffness normalized to the intact state for high load magnitude (20–65 % of fracture load) after 10 (cyc_10), 100 (cyc_100), 1,000 (cyc_1000) and 5,000 (cyc_5000) load cycles

augmentation, and 243 and 222 % for the 35 and 16 % VK100 augmentation (Fig. 3). The stiffness increased in all of the test groups during cyclic loading ($p < 0.05$). At the end of cyclic loading, the VK100 groups showed a lower stiffness in high load ranges than the PMMA groups. When the two filling grades for the two materials were pooled, no significant differences in the stiffness between 16 and 35 % filling were found for the high load range at the end of cyclic loading ($p = 0.202$). Independent of the filling grade, the PMMA groups showed a significantly greater stiffness ($p = 0.001$) for the high load range than the VK100 groups.

During cyclic loading, the height loss at the load application point for the VK100 augmented groups was significantly higher than the PMMA-augmented groups ($p = 0.001$) with magnitudes of 3.0 and 2.7 mm for the 35 and 16 % VK100 groups and 1.2 and 1.1 mm for the 35 and 16 % PMMA groups after 5,000 load cycles (Fig. 4).

The elastic per cycle motion at the end of the cyclic loading was significantly higher than the PMMA-augmented groups than for the VK100-augmented groups ($p = 0.04$) with a magnitude of 0.26 mm for both VK100 and 0.22 mm for both PMMA groups (Fig. 5).

Discussion

Vertebroplasty, first developed to treat vertebral angioma [39] and first described in 1989 to treat vertebral osteoporotic fractures [40], is the current gold standard for surgical treatment of osteoporotic compression fractures. The development of kyphoplasty [41] modified the surgical technique, but the augmentation material—PMMA—remained the same.

Fig. 4 Displacement at the lower load point after 20 (cyc_20), 100 (cyc_100), 1,000 (cyc_1000) and 5,000 (cyc_5000) load cycles

Fig. 5 Per cycle elastic displacement after 10 (cyc_10), 100 (cyc_100), 1,000 (cyc_1000) and 5,000 (cyc_5000) load cycles

Placing a relatively stiff material such as PMMA in a fragile and soft osteoporotic vertebra carries a risk of interface failure at the cement–trabecular bone boundary and subsequent sintering of the cement within the augmented vertebra due to high interface stresses. Reducing the difference in stiffness between the augmentation material used and the surrounding bone reduces interface stresses and may reduce the risk of sintering. Aiming for endplate-to-endplate filling to prevent cement sintering in an augmented vertebral body may shift the fracture risk resulting from the increased stiffness further toward the adjacent segments.

Various reasons and risk factors for fractures that occur following VP have been discussed: increased stiffness in

the vertebra treated [34, 42], cement formation of a solid mass rather than interdigitation [43], changes in load transfer [44, 45], an altered loading direction [46], cement leakage into the disc (pro: [12, 14, 21, 47–49], contra: [50]), use of too much cement [15, 49], the degree of vertebral height restoration [12, 15] and persistent local kyphosis [20], deflection of the endplate and the intervertebral disc into adjacent vertebra [34], fracture shape [51], pre-existing fracture [12, 23], advanced patient age [23], ongoing osteoporosis [16, 20, 24], and low BMD [12, 16, 19, 21, 23], and a high number of VPs at baseline [16, 26]. In addition, patients with high parathyroid hormone concentrations, low body mass index, no use of back brace, no anti-osteoporosis therapy, history of metabolic disease, and use of drugs which influence bone metabolism tend to have a greater risk of recurrent fractures [16, 17, 47]. Studies on refractures of augmented vertebrae focused on the influence of vertebral height restoration, distribution patterns of cement in the augmented vertebra and intravertebral clefts [52], pre-operative osteonecrosis [18, 53], fracture shape, loading case and elastic modulus of fracture region and cement [51]. The initiation of fissures along the cement–bone interface due to uneven deformation of the vertebra is attributed to refractures claiming for a VP technique that ensures even deformation of the augmented vertebra [54].

Ahn et al. [47] described the “direct pillar effect (that is, the difference in strength caused by cement augmentation)” as being responsible for subsequent vertebral fractures.

The problem of potentially detrimental differences in stiffness between the augmentation material and the surrounding cancellous bone led to the innovative introduction of silicone as an augmentation material. Silicones have been used increasingly in the medical field since the 1960s with well-documented biocompatibility and biodegradability [55–57]. The innovative technique investigated in the present study—i.e., augmentation of a vertebral body with silicone—thus represents only a further application of a well-known material in a new field of medicine.

The idea to use augmentation materials with less stiffness than regular PMMA is not new. In an *in vitro* biomechanical study, Boger et al. [32] observed biomechanical advantages with a low-modulus PMMA in comparison with regular PMMA. Other types of cement in addition to PMMA have also been developed for augmentation. In comparison with PMMA, calcium phosphate cement, for example, leads to fewer adjacent fractures in biomechanical studies, although, the rate of recurrent fractures in the augmented vertebrae themselves is still very high [58]. The use of completely different augmentation materials, such as silicone, instead of cement to achieve better stiffness parameters is new, however.

The present study is the first to directly compare the biomechanical stiffness of PMMA-augmented and sili-cone-augmented vertebrae in an in vitro setting. The results show that fractured vertebrae undergoing VP have a significantly lower stiffness with VK100 in comparison with PMMA. Both materials have greater stiffness values with 35 % augmentation in comparison with 16 %. The difference was not significant, but was more pronounced with PMMA. However, the overall height loss during cyclic loading was significantly higher for VK100 augmented vertebrae than the PMMA augmented vertebrae. Further experiments to investigate this overall height loss of the VK augmented vertebrae are planned.

The question of the ideal amount of vertebral filling with augmentation material has been investigated for PMMA with controversial results. Liebschner et al. [37] found that only a small amount of bone cement (about 15 % of the vertebral body volume) was needed to restore stiffness to predamage levels, while greater filling can result in a substantial increase in stiffness well beyond the intact level. Molloy et al. [38] reported that restoration of strength required filling of approximately 16 % of the vertebral body volume and that restoration of stiffness required filling of approximately 29 % of the vertebral body volume.

Luo et al. [59] compared the PMMA augmentation of 3.5 cm³ (about 13 % of the vertebral body volume) and 7 cm³ (about 25 % of the vertebral body volume) and reported that a 13 % filling largely restored the distribution of compressive stress acting on the fractured and adjacent vertebral bodies. An additional 3.5 cm³ of PMMA had no further effect on these stress distributions, but was required to restore spinal stiffness and to normalize load sharing between the vertebral body and neural arch. Vertebral augmentation using too much PMMA has been discussed as one of the reasons for subsequent fractures [15, 49].

In typical everyday activities, loads acting on the spine are higher than those applied in the low load protocol. For greater load magnitudes, VK100 augmented vertebrae show stiffness results that are much closer to that of the intact vertebrae when compared to PMMA augmented vertebrae. Given that, it is desirable to achieve a stiffness close to the intact vertebra under all loading conditions of the spinal column, these results support the use of 16 % VK100 augmentation.

Further clinical and radiographic studies are now necessary to investigate the clinical and radiological results and to focus on correlations with these biomechanical findings. In particular, the rates of recurrent fracture of augmented vertebrae and of fractures in adjacent vertebrae require detailed investigation, in addition to possible side effects such as osteonecrosis, infection, and embolism.

Conflict of interest None.

References

1. Blasco J, Martinez-Ferrer A, Macho J, San Roman L, Pomes J, Carrasco J, Monegal A, Guanabens N, Peris P (2012) Effect of vertebroplasty on pain relief, quality of life, and the incidence of new vertebral fractures: a 12-month randomized follow-up, controlled trial. *J Bone Miner Res* 27(5):1159–1166
2. Buchbinder R, Osborne RH, Ebeling PR, Wark JD, Mitchell P, Wriedit C, Graves S, Staples MP, Murphy B (2009) A randomized trial of vertebroplasty for painful osteoporotic vertebral fractures. *N Engl J Med* 361(6):557–568
3. Farrokhi MR, Alibai E, Maghami Z (2011) Randomized controlled trial of percutaneous vertebroplasty versus optimal medical management for the relief of pain and disability in acute osteoporotic vertebral compression fractures. *J Neurosurg Spine* 14(5):561–569
4. Kallmes DF, Comstock BA, Heagerty PJ, Turner JA, Wilson DJ, Diamond TH, Edwards R, Gray LA, Stout L, Owen S, Hollingworth W, Ghdoke B, Annesley-Williams DJ, Ralston SH, Jarvik JG (2009) A randomized trial of vertebroplasty for osteoporotic spinal fractures. *N Engl J Med* 361(6):569–579
5. Longo UG, Loppini M, Denaro L, Brandi ML, Maffulli N, Denaro V (2010) The effectiveness and safety of vertebroplasty for osteoporotic vertebral compression fractures. A double blind, prospective, randomized, controlled study. *Clin Cases Miner Bone Metab* 7(2):109–113
6. Rousing R, Andersen MO, Jespersen SM, Thomsen K, Lauritsen J (2009) Percutaneous vertebroplasty compared to conservative treatment in patients with painful acute or subacute osteoporotic vertebral fractures: three-months follow-up in a clinical randomized study. *Spine (Phila Pa 1976)* 34(13):1349–1354
7. Rousing R, Hansen KL, Andersen MO, Jespersen SM, Thomsen K, Lauritsen JM (2010) Twelve-months follow-up in forty-nine patients with acute/semiacute osteoporotic vertebral fractures treated conservatively or with percutaneous vertebroplasty: a clinical randomized study. *Spine (Phila Pa 1976)* 35(5):478–482
8. Voormolen MH, Mali WP, Lohle PN, Fransen H, Lampmann LE, van der Graaf Y, Juttman JR, Janssens X, Verhaar HJ (2007) Percutaneous vertebroplasty compared with optimal pain medication treatment: short-term clinical outcome of patients with subacute or chronic painful osteoporotic vertebral compression fractures. The VERTOS study. *AJNR Am J Neuroradiol* 28(3): 555–560
9. Klazen CA, Lohle PN, de Vries J, Jansen FH, Tielbeek AV, Blonk MC, Venmans A, van Rooij WJ, Schoemaker MC, Juttman JR, Lo TH, Verhaar HJ, van der Graaf Y, van Everdingen KJ, Muller AF, Elgersma OE, Halkema DR, Fransen H, Janssens X, Buskens E, Mali WP (2010) Vertebroplasty versus conservative treatment in acute osteoporotic vertebral compression fractures (Vertos II): an open-label randomised trial. *Lancet* 376(9746):1085–1092
10. Grados F, Depriester C, Cayrolle G, Hardy N, Deramond H, Fardellone P (2000) Long-term observations of vertebral osteoporotic fractures treated by percutaneous vertebroplasty. *Rheumatology (Oxford)* 39(12):1410–1414
11. Hierholzer J, Fuchs H, Westphalen K, Baumann C, Slotosch C, Schulz R (2008) Incidence of symptomatic vertebral fractures in patients after percutaneous vertebroplasty. *Cardiovasc Intervent Radiol* 31(6):1178–1183
12. Kim MH, Lee AS, Min SH, Yoon SH (2011) Risk factors of new compression fractures in adjacent vertebrae after percutaneous vertebroplasty. *Asian Spine J* 5(3):180–187

13. Kobayashi N, Numaguchi Y, Fuwa S, Uemura A, Matsusako M, Okajima Y, Ishiyama M, Takahashi O (2009) Prophylactic vertebroplasty: cement injection into non-fractured vertebral bodies during percutaneous vertebroplasty. *Acad Radiol* 16(2):136–143
14. Komemushi A, Tanigawa N, Kariya S, Kojima H, Shomura Y, Komemushi S, Sawada S (2006) Percutaneous vertebroplasty for osteoporotic compression fracture: multivariate study of predictors of new vertebral body fracture. *Cardiovasc Intervent Radiol* 29(4):580–585
15. Li YA, Lin CL, Chang MC, Liu CL, Chen TH, Lai SC (2012) Subsequent vertebral fracture after vertebroplasty: incidence and analysis of risk factors. *Spine (Phila Pa 1976)* 37(3):179–183
16. Lin H, Bao LH, Zhu XF, Qian C, Chen X, Han ZB (2010) Analysis of recurrent fracture of a new vertebral body after percutaneous vertebroplasty in patients with osteoporosis. *Orthop Surg* 2(2):119–123
17. Lin WC, Cheng TT, Lee YC, Wang TN, Cheng YF, Lui CC, Yu CY (2008) New vertebral osteoporotic compression fractures after percutaneous vertebroplasty: retrospective analysis of risk factors. *J Vasc Interv Radiol* 19(2 Pt 1):225–231
18. Lin WC, Lee YC, Lee CH, Kuo YL, Cheng YF, Lui CC, Cheng TT (2008) Refractures in cemented vertebrae after percutaneous vertebroplasty: a retrospective analysis. *Eur Spine J* 17(4):592–599
19. Lu K, Liang CL, Hsieh CH, Tsai YD, Chen HJ, Liliang PC (2012) Risk factors of subsequent vertebral compression fractures after vertebroplasty. *Pain Med* 13(3):376–382
20. Movrin I, Vengust R, Komadina R (2010) Adjacent vertebral fractures after percutaneous vertebral augmentation of osteoporotic vertebral compression fracture: a comparison of balloon kyphoplasty and vertebroplasty. *Arch Orthop Trauma Surg* 130(9):1157–1166
21. Rho YJ, Choe WJ, Chun YI (2012) Risk factors predicting the new symptomatic vertebral compression fractures after percutaneous vertebroplasty or kyphoplasty. *Eur Spine J* 21(5):905–911
22. Trout AT, Kallmes DF, Kaufmann TJ (2006) New fractures after vertebroplasty: adjacent fractures occur significantly sooner. *AJNR Am J Neuroradiol* 27(1):217–223
23. Tseng YY, Yang TC, Tu PH, Lo YL, Yang ST (2009) Repeated and multiple new vertebral compression fractures after percutaneous transpedicular vertebroplasty. *Spine (Phila Pa 1976)* 34(18):1917–1922
24. Voormolen MH, Lohle PN, Juttman JR, van der Graaf Y, Fransen H, Lampmann LE (2006) The risk of new osteoporotic vertebral compression fractures in the year after percutaneous vertebroplasty. *J Vasc Interv Radiol* 17(1):71–76
25. Yen CH, Teng MM, Yuan WH, Sun YC, Chang CY (2012) Preventive vertebroplasty for adjacent vertebral bodies: a good solution to reduce adjacent vertebral fracture after percutaneous vertebroplasty. *AJNR Am J Neuroradiol* 33(5):826–832
26. Klazen CA, Venmans A, de Vries J, van Rooij WJ, Jansen FH, Blonk MC, Lohle PN, Juttman JR, Buskens E, van Everdingen KJ, Muller A, Fransen H, Elgersma OE, Mali WP, Verhaar HJ (2010) Percutaneous vertebroplasty is not a risk factor for new osteoporotic compression fractures: results from VERTOS II. *AJNR Am J Neuroradiol* 31(8):1447–1450
27. Mudano AS, Bian J, Cope JU, Curtis JR, Gross TP, Allison JJ, Kim Y, Briggs D, Melton ME, Xi J, Saag KG (2009) Vertebroplasty and kyphoplasty are associated with an increased risk of secondary vertebral compression fractures: a population-based cohort study. *Osteoporos Int* 20(5):819–826
28. Wang HK, Lu K, Liang CL, Weng HC, Wang KW, Tsai YD, Hsieh CH, Liliang PC (2010) Comparing clinical outcomes following percutaneous vertebroplasty with conservative therapy for acute osteoporotic vertebral compression fractures. *Pain Med* 11(11):1659–1665
29. Wardlaw D, Cummings SR, Van Meirhaeghe J, Bastian L, Tillman JB, Ransam J, Eastell R, Shabe P, Talmadge K, Boonen S (2009) Efficacy and safety of balloon kyphoplasty compared with non-surgical care for vertebral compression fracture (FREE): a randomised controlled trial. *Lancet* 373(9668):1016–1024
30. Chosa K, Naito A, Awai K (2011) Newly developed compression fractures after percutaneous vertebroplasty: comparison with conservative treatment. *Jpn J Radiol* 29(5):335–341
31. Baroud G, Heini P, Nemes J, Bohner M, Ferguson S, Steffen T (2003) Biomechanical explanation of adjacent fractures following vertebroplasty. *Radiology* 229(2):606–607 Author reply 607–608
32. Boger A, Heini P, Windolf M, Schneider E (2007) Adjacent vertebral failure after vertebroplasty: a biomechanical study of low-modulus PMMA cement. *Eur Spine J* 16(12):2118–2125
33. Chiang CK, Wang YH, Yang CY, Yang BD, Wang JL (2009) Prophylactic vertebroplasty may reduce the risk of adjacent intact vertebra from fatigue injury: an ex vivo biomechanical study. *Spine (Phila Pa 1976)* 34(4):356–364
34. Wilcox RK (2006) The biomechanical effect of vertebroplasty on the adjacent vertebral body: a finite element study. *Proc Inst Mech Eng H* 220(4):565–572
35. Pickhardt PJ, Lee LJ, del Rio AM, Lauder T, Bruce RJ, Summers RM, Pooler BD, Binkley N (2011) Simultaneous screening for osteoporosis at CT colonography: bone mineral density assessment using MDCT attenuation techniques compared with the DXA reference standard. *J Bone Miner Res* 26(9):2194–2203
36. Ruger M, Schmoelz W (2009) Vertebroplasty with high-viscosity polymethylmethacrylate cement facilitates vertebral body restoration in vitro. *Spine (Phila Pa 1976)* 34(24):2619–2625
37. Liebschner MA, Rosenberg WS, Keaveny TM (2001) Effects of bone cement volume and distribution on vertebral stiffness after vertebroplasty. *Spine (Phila Pa 1976)* 26(14):1547–1554
38. Molloy S, Mathis JM, Belkoff SM (2003) The effect of vertebral body percentage fill on mechanical behavior during percutaneous vertebroplasty. *Spine (Phila Pa 1976)* 28(14):1549–1554
39. Galibert P, Deramond H, Rosat P, Le Gars D (1987) Preliminary note on the treatment of vertebral angioma by percutaneous acrylic vertebroplasty. *Neurochirurgie* 33(2):166–168
40. Lapras C, Mottolese C, Deruty R, Lapras C Jr, Remond J, Duquesnel J (1989) Percutaneous injection of methyl-metacrylate in osteoporosis and severe vertebral osteolysis (Galibert's technic). *Ann Chir* 43(5):371–376
41. Lieberman IH, Dudeney S, Reinhardt MK, Bell G (2001) Initial outcome and efficacy of “kyphoplasty” in the treatment of painful osteoporotic vertebral compression fractures. *Spine (Phila Pa 1976)* 26(14):1631–1638
42. Laredo JD, Hamze B (2004) Complications of percutaneous vertebroplasty and their prevention. *Skeletal Radiol* 33(9):493–505
43. Han IH, Chin DK, Kuh SU, Kim KS, Jin BH, Yoon YS, Cho YE (2009) Magnetic resonance imaging findings of subsequent fractures after vertebroplasty. *Neurosurgery* 64(4):740–744 Discussion 744–745
44. Berlemann U, Ferguson SJ, Nolte LP, Heini PF (2002) Adjacent vertebral failure after vertebroplasty. A biomechanical investigation. *J Bone Joint Surg Br* 84(5):748–752
45. Polikeit A, Nolte LP, Ferguson SJ (2003) The effect of cement augmentation on the load transfer in an osteoporotic functional spinal unit: finite-element analysis. *Spine (Phila Pa 1976)* 28(10):991–996
46. Aquarius R, Homminga J, Verdonschot N, Tanck E (2011) The fracture risk of adjacent vertebrae is increased by the changed loading direction after a wedge fracture. *Spine (Phila Pa 1976)* 36(6):E408–E412
47. Ahn Y, Lee JH, Lee HY, Lee SH, Keem SH (2008) Predictive factors for subsequent vertebral fracture after percutaneous vertebroplasty. *J Neurosurg Spine* 9(2):129–136

48. Chen WJ, Kao YH, Yang SC, Yu SW, Tu YK, Chung KC (2010) Impact of cement leakage into disks on the development of adjacent vertebral compression fractures. *J Spinal Disord Tech* 23(1):35–39
49. Sun YC, Teng MM, Yuan WS, Luo CB, Chang FC, Lirng JF, Guo WY, Chang CY (2011) Risk of post-vertebroplasty fracture in adjacent vertebral bodies appears correlated with the morphologic extent of bone cement. *J Chin Med Assoc* 74(8): 357–362
50. Lee KA, Hong SJ, Lee S, Cha IH, Kim BH, Kang EY (2011) Analysis of adjacent fracture after percutaneous vertebroplasty: does intradiscal cement leakage really increase the risk of adjacent vertebral fracture? *Skeletal Radiol* 40(12):1537–1542
51. Rohlmann A, Boustani HN, Bergmann G, Zander T (2010) A probabilistic finite element analysis of the stresses in the augmented vertebral body after vertebroplasty. *Eur Spine J* 19(9): 1585–1595
52. Chen LH, Hsieh MK, Liao JC, Lai PL, Niu CC, Fu TS, Tsai TT, Chen WJ (2011) Repeated percutaneous vertebroplasty for refracture of cemented vertebrae. *Arch Orthop Trauma Surg* 131(7):927–933
53. Heo DH, Chin DK, Yoon YS, Kuh SU (2009) Recollapse of previous vertebral compression fracture after percutaneous vertebroplasty. *Osteoporos Int* 20(3):473–480
54. Wang JL, Chiang CK, Kuo YW, Chou WK, Yang BD (2012) Mechanism of fractures of adjacent and augmented vertebrae following simulated vertebroplasty. *J Biomech* 45(8):1372–1378
55. Colas A, Curtis J (2004) Silicone biomaterials: history and chemistry. In: Ratner BD, Hoffman AS, Schoen FJ, Lemons JE (eds) *Biomaterials science: an introduction to materials in medicine*, 2nd edn. Elsevier Academic Press, San Diego, pp 80–86
56. Colas A, Curtis J (2004) Medical applications of silicones. In: Ratner BD, Hoffman AS, Schoen FJ, Lemons JE (eds) *Biomaterials science: an introduction to materials in medicine*, 2nd edn. Elsevier Academic Press, San Diego, pp 697–707
57. Heide C (1999) Silicone rubber for medical device applications. *Medical device and diagnostic industry magazine*, Nov, pp 38–44
58. Nouda S, Tomita S, Kin A, Kawahara K, Kinoshita M (2009) Adjacent vertebral body fracture following vertebroplasty with polymethylmethacrylate or calcium phosphate cement: biomechanical evaluation of the cadaveric spine. *Spine (Phila Pa 1976)* 34(24):2613–2618
59. Luo J, Daines L, Charalambous A, Adams MA, Annesley-Williams DJ, Dolan P (2009) Vertebroplasty: only small cement volumes are required to normalize stress distributions on the vertebral bodies. *Spine (Phila Pa 1976)* 34(26):2865–2873