Published in final edited form as:

Langmuir. 2013 June 11; 29(23): 6983–6988. doi:10.1021/la4009174.

Polypeptoid Brushes by Surface-Initiated Polymerization of N-Substituted Glycine N-Carboxyanhydrides

Maximilian Schneider[†], Corinna Fetsch^{†,‡}, Ihsan Amin[†], Rainer Jordan^{†,*}, and Robert Luxenhofer^{†,‡,*}

[†]Professur für Makromolekulare Chemie, Department Chemie, TU Dresden, Zellescher Weg 19, 01069 Dresden, Germany

[‡]Functional Polymer Materials, Chair for Chemical Technology of Materials Synthesis, University Würzburg, Röntgenring 11, 97070 Würzburg, Germany

Abstract

Polypeptoid brushes were synthesized by surface-initiated polymerization of N-substituted glycine N-carboxyanhydrides (NNCAs) on self assembled amine monolayers. Using the presented grafting from approach, polypeptoid brush thicknesses of approx. 40 nm could be obtained as compared previously reported brush thicknesses of 4 nm. Moreover, hydrophilic, hydrophobic and amphiphilic polymer brushes were realized which are expected to have valuable applications as non-fouling surfaces and as model or reference systems for surface grafted polypeptides.

Keywords

sarcosine; N-carboxyanhydride; NCA; polypeptoid; polymer brush; surface-initiated polymerization

INTRODUCTION

In various fields, like biotechnology,¹ food processing² and biomedical/biomaterials science^{3–5} much attention is paid to protein adsorption and denaturation at solid surfaces. This property is critically influencing biocompatibility, non-biofouling coatings and selective attachment of specific proteins.^{4–7} A promising attempt features peptide-based self-assembled monolayers to prevent the attachment of proteins.⁸ The versatile peptide chemistry enables the creation of a manifold of coatings with desired and switchable functions and excellent biocompatibility.^{9,10} However, peptides are prone to degradation and tend to undergo secondary structure formation via intra- and intermolecular hydrogen bonds which influences biocompatibility.

Polypeptoids are a class of biomimetic polymers that resemble polypeptides to some extent.¹¹ They feature a poly(glycine) backbone, but in contrast to polypeptides, they are substituted at the amide nitrogen. Polypeptoids are either synthesized by nucleophilic living ring-opening polymerization (NuLROP) of N-substituted glycine N-carboxyanhydrides

*Corresponding Authors: rainer.jordan@tu-dresden.de; robert.luxenhofer@uni-wuerzburg.de.

Conflict of Interests

The authors declare no competing financial interest.

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

(NNCA) or by iterative sub-monomer solid phase synthesis (SSPS).¹¹ The simplest polypeptoid is poly(N-methylglycine) also known as polysarcosine (PSar). Due to this substitution secondary structure formation due to H-bonding is impossible. In combination with the excellent hydrophilicity and the electroneutrality, PSar meets all the requirements for the development of a protein repellent coating.⁴ Messersmith and co-workers¹²⁻¹⁷ prepared substrates with surface tethered hydrophilic polypeptoids, including PSar, and demonstrated the excellent non-fouling properties of the polypeptoids. They synthesized the polymer via SSPS and tethered the polymer onto the surfaces via a peptide anchor. Layer thickness was typically about 4 nm.¹³

For PSar, NuLROP was established already in 1949,^{18,19} while other N-substituted NCAs (NNCAs) have only been investigated recently.²⁰⁻²⁸ In stark contrast to the ring-opening polymerization (ROP) of NCAs, ROP of NNCAs is much less plagued by side reactions.²⁹ Surface grafted polypeptides have been of interest for researchers for a variety of applications³⁰⁻³⁹. Chang and Frank described the surface initiated polymerization of amino acid NCAs in solution and by means of chemical vapor deposition.^{30,32} On the other hand, Higashi and co-workers utilized prearranged surface-tethered helices to influence the growth of new polymer from the surface.⁴⁰ However, the preparation of polypeptide brushes from surfaces is apparently hampered by a number of factors, as is the polymerization of N-carboxyanhydrides in solution. Since polypeptoids are intriguing alternatives to polypeptides and NNCA polymerization has shown to be much more robust as compared to NCA polymerization¹¹, the surface-initiated ring-opening polymerization (SI-ROP) of NNCAs should be feasible. Comparison of the surface initiated polymerization of NCAs and NNCAs may eventually be helpful to better understand the mechanism and limitations of the method, as was successfully demonstrated for the polymerization in solution.²⁹ Thus, we investigated the SI-ROP of NNCAs on defined amino-functionalized surfaces, i.e. a self-assembled monolayer (SAM) of aminopropylsilane (APS) on silicon dioxide surfaces (Scheme 1). From our present work, it is apparent that there are similarities and differences between the SI-ROP of NCAs and NNCAs. While there appears to be a similar limitation in brush height, we were able to demonstrate the successful preparation of block copolypeptoids using SI-ROP, which has, to the best of our knowledge, not been demonstrated for SI ROP of NCAs. However, further work will be necessary to elucidate the underlying mechanistic differences.

Experimental Methods

Materials

All chemicals were purchased from Sigma-Aldrich (Steinheim, Germany) or Acros (Geel, Belgium) and used as received unless otherwise stated. Acetonitrile (ACN) (extra dry, Acroseal) was transferred and stored in a glove box. Benzonitrile (BN) and triethylamine (TEA) were refluxed over P₄O₁₀ and distilled under argon prior to use. Dichloromethane (DCM) was stored over CaCl₂. All organic solvents were tested regarding their water content using a C20 compact coulometer (Mettler-Toledo, Giessen, Germany) and showed a typically water content < 30 ppm. The monomers Sar-NCA and nBuGly-NCA were prepared according to a published procedure.²³ Only bidistilled water was used to treat the samples.

Pretreatment of substrates

Silicon wafer pieces (approx. 10 × 5 mm) with a 300 nm oxide layer were obtained as a generous gift from Wacker AG, Burghausen, Germany. Substrates were cleaned with "Piranha Solution" (H₂O₂:H₂SO₄, 1:3 v/v; 90°C; 30min; WARNING: Piranha solution

reacts violently with organic matter!), washed extensively with bidistilled water and dried with a stream of dry argon.

Preparation of self-assembled monolayers (SAMs)

Freshly cleaned substrates were immersed in a 5 % (v/v) aminopropyltrimethoxysilane (APTMS) solution in dry acetone and subjected to treatment with ultrasound for 30 min. After SAM formation, the samples were extensively rinsed with dry acetone and dried under argon atmosphere. Curing of the substrates took part overnight at room temperature. The quality of this SAM preparation method was confirmed by X-ray photoelectron spectroscopy (XPS) ($d = 0.72 \text{ nm}$) and water contact angle ($\Theta = 55 \pm 3^\circ$) measurements as published earlier.²⁴ All substrates were transferred to a glove box and rinsed with dry acetonitrile prior to use.

Polymerization procedures

The monomer solution was prepared in dried Schlenk-tubes in the glove box by dissolving 1 mmol monomer (115 mg of Sar-NCA, 157 mg of nBuGly-NCA) in 1 mL benzonitrile (BN). After complete dissolution of the monomer, the substrates were immersed and 0.1 mL triethylamine (TEA) was added to deprotonate any surface ammonium groups. The reaction solution was stirred under inert and dry atmosphere at r.t. in an open reaction vial (evolution of CO_2 !). The same procedure was performed for consecutive polymerization experiments. In this case, substrates were removed from the reaction mixture and rinsed thoroughly. Subsequently, the substrates were re-immersed in fresh monomer solution.

Characterization of substrates

The optical thickness of polymer layers were determined on a Sentech SE 800 spectral ellipsometer assuming a refractive index of 1.45 and applying the Cauchy model for fitting. The used parameters were in good agreement with the parameters used for protein layers⁴¹ and were identified by the group of Messersmith.^{15,16}

Static water contact angles were measured on a Krüss DSA10. The given contact angle presents the average of at least 5 measurements on different sample spots selected randomly.

AFM scans were recorded with a atomic force microscope Ntegra Aura (NT-MDT) with SMENA head in semi-contact mode. The used probes have a typically curvature radius of 6 nm, a resonant frequency of 47-150 kHz and a force constant of 0.35 – 6.10 N/m.

The surface roughness (arithmetic average of absolute values, R_a) was determined with the free data analysis software “Gwyddion” (<http://gwyddion.net/>) at several characteristic areas of the sample in the dimension of $5 \times 5 \mu\text{m}$. IR-spectra were recorded with a Nicolet 5700 (Thermo) IR spectrometer. The polymer powder was ground with potassium bromide, pressed into a clear disc and mounted in the optical path. The spectrum was recorded in transmission mode using a DTGS detector. The spectrum of the polymer brushes was recorded with a VariGATR (Harrick) grazing angle ATR accessory with Ge ATR crystal and a liquid nitrogen cooled MCT-detector.

XPS was performed on several freshly prepared APS monolayers to verify reproducibility of the SAM preparation. The spectra were recorded with an Omicron Multiprobe spectrometer using monochromatic aluminium K-alpha radiation. The spectra were calibrated by setting the Si-2p signal to 102.0 eV. Spectra were fitted by symmetric Voigt functions with Shirley background correction.

RESULTS AND DISCUSSION

Primary amino functions are the initiator of choice for the ROP of NCAs and NNCAs^{23,28,29} and it is expected that the grafting-from approach in combination with living polymerizations ensures a high grafting density of linear chains and thus, a better surface screening in combination with thicker layers for a given polymerization degree as compared to the grafting-onto approach. Moreover, the use of SAMs as thin 2D initiator systems offers the possibility of direct patterning at any length scale.⁴² APS-SAM modified silicon wafer pieces bearing a 300 nm silicon dioxide layer were immersed in a 1 M solution of NNCA in benzonitrile. In this solvent, high polymerization rates at room temperature have been observed.²³ The successful preparation of a homogeneous APS-SAM was confirmed by contact angle measurement (data not shown) and x-ray photoelectron spectroscopy (XPS). First, we investigated the increase of the layer thickness with the SI-ROP reaction time for Sar-NCA as the monomer (Figure 1). The initial growth rate was found to be 0.55 nm/h, but eventually a plateau at a brush thickness of about 40 nm is reached. In comparison, PSar brushes prepared by grafting-onto only gave approx. 4 nm thick layers.^{15,16} This increased brush thickness accessible through our approach could be particularly important for effective surface screening and long-term use of PSar brushes. The layer growth rate we observed was about one order of magnitude smaller as compared to the rates observed by Frank et al.,^{34,39} presumably due to our solution phase approach.

Moreover, Frank et al. and Schouten and co-workers found a similar limitation of the brush layer thickness for the SI-ROP of various unsubstituted NCAs.^{35,43-45} They attributed the layer thickness limitation to the formation of chemically or physically “dead” chain ends, which is commonly regarded as major limitation on controlling NCA polymerization, also in solution.²⁹ However, the mechanisms responsible for chemical inactivation of NCAs should not apply for NNCAs as these cannot deprotonate at the nitrogen atom, the attack at the 2-position of the ring leading to hydantoic acids termini is blocked⁴⁶, and the β -sheet or α -helix formation within the brush³⁴ can be ruled out due to the lack of inter- or intramolecular hydrogen bonding.¹¹ Thus, our results hint that other factors or mechanism may be responsible, potentially also in the case of SI-ROP of NCAs.

Another possibility for the limitation of brush height is the gelation of the monomer solution and therefore, reduced access of fresh monomer to the surface. Hence, we performed consecutive polymerization experiments by repeated addition of fresh SarNCA solution to surfaces (after removal of previous reaction medium). In solution, the living ring-opening polymerization of SarNCA allowed consecutive monomer addition for at least ten times.²⁷ Also for SI-ROP of Sar-NCA, we were able to restart the polymerization for several times and the resulting brush thickness after a given total polymerization time fits excellently to the brush heights obtained by a series of individual experiments and show the living character of the SI-ROP (Figure 1, arrows).²⁷ However, a similar limitation of the maximum layer thickness at approx. 40 nm was observed. Thus, gelation or increase in solution viscosity can be ruled out to be a significant factor regarding the limitation of the layer thickness. Interestingly, Shouten and co-workers found that in a first step, polymerization of γ -benzyl-L-glutamate-NCA yielded 20 nm thickness after 24 h, while in a second polymerization of the same monomer only 8 nm increase in layer thickness was observed.⁴⁴ In that work, the limitation was attributed to a formation of non-grafted, physisorbed material on top of the chemisorbed ones. However, why after washing a reduced growth rate is observed remained and remains unclear.

In our case, a layer thickness of 40 nm would correlate to a contour length of PSar with a degree of polymerization (DP) of 111. However, it should be noted that it is not assumed that the PSar is fully extended, so a larger DP is expected. The polymerization of Sar-NCA

has been used for decades to elucidate the polymerization mechanisms of NCAs. It has been well established that the common limitations of NCA polymerizations can be ruled out for NNCAs, yet on surfaces, a limitation of the brush height is clearly evident. Possible reasons for this are currently under investigation in our laboratories. One hypothesis is that the attack at the 2-position of the monomer is severely limited but cannot be ruled out entirely. However, since this appears to be no significant limitation in solution polymerization, we find it unlikely to be of major importance. More likely appears to be a mechanism which is specific the surface initiated polymerization (and the resulting high local chain density) that has yet to be discovered. The surface coverage was found to be very homogenous and the surface appeared to be very smooth with a mean surface roughness < 1 nm (Ra) (Figure 2). This stands in contrast to the observations for surfaces which were coated with different polypeptides (e.g. poly(γ -benzyl-L-glutamate, poly(β -benzyl-L-aspartate) and others) which were thinner and exhibited a higher surface roughness.³⁴ Although hypothetical, this may attributed to the formation of secondary structures in the case of polypeptides and their absence in the case of polypeptoids, respectively.

In Figure 3, transmission fourier-transform infrared spectra of bulk PSar prepared by solution polymerization and attenuated total reflectance fourier-transform infrared spectra of a PSar layer prepared by SI-ROP on APS-SAMs are compared. In both spectra, the typical absorption bands are present, confirming the successful preparation of surface tethered PSar by SI-ROP.

The smooth and homogeneous surface coverage is important for the use of tethered polypeptoids for non-fouling coatings as polymer brushes exhibit superior properties due to their effective substrate surface screening as well as the polymer brush repelling effect on strongly adhering proteins.^{24,47,48} As in both cases the tethering was performed by living SI-ROP from a defined SAM it can be concluded that the SI-ROP of NNCAs as described here, results in the formation of dense polymer brushes. Additionally, the chemical composition of the initiator layer (APS-SAM) and the PSar brush was verified by XPS (Figure 4). All expected signals of the monolayer and the SiO₂ signals of the substrate were observed. After polymerization, the Si signals are barely visible because of the screening by the thick polymer layer ($h = 30$ nm). A detailed scan of the PSar surface (Figure 4c) shows two different carbon peaks in a 2:1 ratio. These peaks can be assigned to the different carbon species (CH_2/CH_3 and $\text{C}=\text{O}$) of the polymer. The binding energy of the oxygen atom is consistent with a carbonyl group, as expected.

As depicted in Scheme 1, consecutive polymerization was also performed using two different monomers. Sar-NCA yields hydrophilic brushes while nBuGly-NCA is expected to result in hydrophobic brushes²³. By consecutive polymerization of the two monomers, amphiphilic polypeptoid brushes should be accessible, the orientation of the brush depending on the order of the monomers employed. Schouten and co-workers have previously prepared block copolypeptides using the same approach, but to the best of our knowledge, no brushes based on amphiphilic polymers were reported using this methodology.⁴³

First, hydrophobic P(nBuGly) brushes were prepared by SI ROP for 90 h with nBuGlyNCA. It is known that nBuGlyNCA has a much smaller polymerization rate as compared to Sar-NCA,²³ which is reflected here by smaller brush heights after the same polymerization time. Nevertheless, with a static water contact angle of $\Theta = 89^\circ$, the resulting brushes of 12 nm height exhibits a hydrophobic character (Figure 5). The same substrate was then reacted for 48 h with Sar-NCA to result in an amphiphilic brush (P(nBuGly-b-Sar)) of a total height of 21 nm and $\Theta < 20^\circ$. Apparently, the thin 9 nm PSar brush was sufficient to mask the underlying hydrophobic brush.

Accordingly, a hydrophilic PSar brush ($h = 28$ nm; $\Theta < 20^\circ$) could be converted to P(Sar-*b*-nBuGly) ($h = 42$ nm, $\Theta = 92^\circ$) showing remarkably hydrophobic properties and the same water contact angle as a P(nBuGly) homopolymer brush. This not only demonstrates the livingness of the SI-ROP of NNCAs that gives direct access to block copolymer brushes, but also demonstrates the formation of dense and homogeneous brushes since in the last case, the underlying hydrophilic PSar block layer does not reduce the static water contact angle. At this stage, we did not perform a systematic long-term study to investigate potential long-term restructuring, but the large contact angles remained unaffected by storage at ambient air humidity over several days.

A more systematic study on the long term brush restructuring, in dependence of the brush height and solvent challenges will be necessary and is currently under way in our laboratories. Moreover, we are currently investigating the reasons for the limitation in brush height in SI-ROP of NNCAs.

CONCLUSION

In summary, we report on the synthesis of polypeptoid brushes by means of surface-initiated polymerization of different NNCAs on self-assembled monolayers. Exemplarily, the SI-ROP of sarcosine-NCA and n-butylglycine-NCA was shown. Dense and homogeneous brush layer were readily obtained with brush layer thicknesses being 10 fold higher as reported by a grafting-onto approach. Hydrophilic (PSar), hydrophobic (P(nBuGly)) as well as amphiphilic polypeptoid brushes are accessible by consecutive SI-ROP. This also demonstrates the living character of the nucleophilic ring-opening polymerization since consecutive homo- and blockcopolymerization with a systematic layer thickness increase was observed. The chemical composition was verified by FTIR spectroscopy and XPS. As for NCAs, the SI-ROP of NNCAs was found to be limited in the maximal obtainable brush thickness. This straightforward method is suitable to prepare biomimetic non-fouling coatings that are expected to have improved and prolonged non-fouling properties.

Acknowledgments

This work was supported by the Fond der Chemischen Industrie, the Center for Regenerative Therapies Dresden (CRTD) and in part by United States National Institutes of Health (NIH) U01 grant CA151806 of the National Cancer Institute (NCI). We would like to thank Andreas Winter and Prof. Armin Gölzhäuser, Physics of Supramolecular Systems, Universität Bielefeld for XPS measurements.

REFERENCES

- (1). Ballet T, Boulange L, Brechet Y, Bruckert F, Weidenhaupt M. Protein conformational changes induced by adsorption onto material surfaces: an important issue for biomedical applications of material science. *B. Pol. Acad. Sci.-Tech.* 2010; 58:303–313.
- (2). Meyer B. Approaches to prevention, removal and killing of biofilms. *Int. Biodeter. Biodegr.* 2003; 51:249–253.
- (3). Faxälv L, Ekblad T, Liedberg B, Lindahl TL. Blood compatibility of photografted hydrogel coatings. *Acta Biomater.* 2010; 6:2599–2608. [PubMed: 20045090]
- (4). Ostuni E, Chapman RG, Holmlin RE, Takayama S, Whitesides GM. A Survey of Structure-Property Relationships of Surfaces that Resist the Adsorption of Protein. *Langmuir.* 2001; 17:5605–5620.
- (5). Zhou M, Liu H, Venkiteswaran A, Kilduff J, Anderson DG, Langer R, Belfort G. High throughput discovery of new fouling-resistant surfaces. *J. Mater. Chem.* 2010; 21:693–704.
- (6). Fischer M, Sperling C, Tengvall P, Werner C. The ability of surface characteristics of materials to trigger leukocyte tissue factor expression. *Biomaterials.* 2010; 31:2498–2507. [PubMed: 20035991]

- (7). Banerjee I, Pangule RC, Kane RS. Antifouling Coatings: Recent Developments in the Design of Surfaces That Prevent Fouling by Proteins, Bacteria, and Marine Organisms. *Adv. Mater.* 2011; 23:690–718. [PubMed: 20886559]
- (8). Chelmowski R, Köster SD, Kerstan A, Prekelt A, Grunwald C, Winkler T, Metzler Nolte N, Terfort A, Wöll C. Peptide-based SAMs that resist the adsorption of proteins. *J. Am. Chem. Soc.* 2008; 130:14952–14953. [PubMed: 18928285]
- (9). Lubell WD. Peptide Chemistry. *Org. Lett.* 2012; 14:4297–4302. [PubMed: 22954352]
- (10). Wilke P, Börner HG. Mussel Glue Derived Peptide Polymer Conjugates to Realize Enzyme Activated Antifouling Coatings. *ACS Macro Letters.* 2012; 1:871–875.
- (11). Luxenhofer R, Fetsch C, Grossmann A. Polypeptoids: A Perfect Match for Molecular Definition and Macromolecular Engineering? *J. Polym. Sci.: Part A: Polym. Chem.* 2013 DOI: 10.1002/pola.26687.
- (12). Statz AR, Meagher RJ, Barron AE, Messersmith PB. New peptidomimetic polymers for antifouling surfaces. *J. Am. Chem. Soc.* 2005; 127:7972–7973. [PubMed: 15926795]
- (13). Statz AR, Barron AE, Messersmith PB. Protein, cell and bacterial fouling resistance of polypeptoid-modified surfaces: effect of side-chain chemistry. *Soft Matter.* 2008; 4:131–139. [PubMed: 21472038]
- (14). Statz AR, Kuang J, Ren C, Barron AE, Szleifer I, Messersmith PB. Experimental and Theoretical Investigation of Chain Length and Surface Coverage on Fouling of Surface Grafted Polypeptoids. *Biointerphases.* 2009; 4:FA22–FA32. [PubMed: 20300542]
- (15). Lau KHA, Ren C, Sileika TS, Park SH, Szleifer I, Messersmith PB. Surface-Grafted Polysarcosine as a Peptoid Antifouling Polymer Brush. *Langmuir.* 2012; 28:16099–16107. [PubMed: 23101930]
- (16). Lau KHA, Ren C, Park SH, Szleifer I, Messersmith PB. An Experimental-Theoretical Analysis of Protein Adsorption on Peptidomimetic Polymer Brushes. *Langmuir.* 2012; 28:2288–2298. [PubMed: 22107438]
- (17). Brubaker CE, Messersmith PB. The Present and Future of Biologically-Inspired Adhesive Interfaces and Materials. *Langmuir.* 2012; 28:2200–2205. [PubMed: 22224862]
- (18). Waley SG, Watson J. The Kinetics of the Polymerization of Sarcosine Carbonic Anhydride. *P. Roy. Soc. Lond. A Mat.* 1949; 199:499–517.
- (19). Ballard DG, Bamford CH. Kinetics of the Formation of Polypeptides from N-Carboxy- α -amino-acid Anhydrides. *Nature.* 1953; 4365:907–908.
- (20). Guo L, Zhang D. Cyclic poly(α peptoid)s and their block copolymers from N-heterocyclic carbene-mediated ring-opening polymerizations of N-substituted N-carboxylanhydrides. *J. Am. Chem. Soc.* 2009; 131:18072–18074. [PubMed: 19950948]
- (21). Guo L, Li J, Brown Z, Ghale K, Zhang D. Synthesis and Characterization of Cyclic and Linear Helical Poly(α -peptoid)s by N-Heterocyclic Carbene-Mediated Ring-Opening Polymerizations of N-Substituted N-Carboxyanhydrides. *Biopolymers.* 2011; 96:596–603. [PubMed: 22180907]
- (22). Lahasky SH, Serem WK, Guo L, Garno JC, Zhang D. Synthesis and Characterization of Cyclic Brush Like Polymers by N-Heterocyclic Carbene-Mediated Zwitterionic Polymerization of N-Propargyl N-Carboxyanhydride and the Grafting-to Approach. *Macromolecules.* 2011; 44:9063–9074.
- (23). Fetsch C, Grossmann A, Holz L, Nawroth JF, Luxenhofer R. Polypeptoids from N-Substituted Glycine N-Carboxyanhydrides: Hydrophilic, Hydrophobic, and Amphiphilic Polymers with Poisson Distribution. *Macromolecules.* 2011; 44:6746–6758.
- (24). Zhang N, Pompe T, Amin I, Luxenhofer R, Werner C, Jordan R. Tailored polymer brushes of poly(2-oxazoline)s to control the protein adsorption and cell adhesion. *Macromol. Biosci.* 2012; 7:926–936. [PubMed: 22610725]
- (25). Robinson JW, Schlaad H. A versatile polypeptoid platform based on N-allyl glycine. *Chem. Commun.* 2012; 48:7835–7837.
- (26). Fetsch C, Luxenhofer R. Thermal properties of aliphatic polypeptides. *Polymers.* 2013; 5:112–127.

- (27). Fetsch C, Luxenhofer R. Highly Defined Polypeptoids via Multiple Chain Extension and Macroinitiators. *Macromol. Rapid. Commun.* 2012; 33:1708–1713. [PubMed: 22674859]
- (28). Gangloff N, Fetsch C, Luxenhofer R. Polypeptoids by Living Ring-opening Polymerization of N-Substituted N-Carboxyanhydrides from Solid Supports. *Macromol Rapid Commun.* 2013 DOI: 10.1002/marc.201300269.
- (29). Kricheldorf, HR. α -Aminoacid-N-Carboxyanhydrides and Related Materials. Springer; New York: 1987.
- (30). Chang YC, Frank CW. Grafting of poly (γ -benzyl-L-glutamate) on chemically modified silicon oxide surfaces. *Langmuir.* 1996; 12:5824–5829.
- (31). Chang Y-C, Frank CW. Surface polymerization of poly(γ -alkyl-L-glutamate) on solid substrates. *Makromolekulare Chemie Macromolecular Symposia.* 1997; 118:641–646.
- (32). Chang YC, Frank CW. Vapor deposition polymerization of α -amino acid N-carboxy anhydride on the silicon (100) native oxide surface. *Langmuir.* 1998; 14:326–334.
- (33). Jaworek T, Neher D, Wegner G, Wieringa RH, Schouten AJ. Electromechanical Properties of an Ultrathin Layer of Directionally Aligned Helical Polypeptides. *Science.* 1998; 279:57–60. [PubMed: 9417021]
- (34). Lee NH, Christensen LM, Frank CW. Morphology of Vapor-Deposited Poly(α -amino acid) Films. *Langmuir.* 2003; 19:3525–3530.
- (35). Lee NH, Frank CW. Surface-Initiated Vapor Polymerization of Various α -Amino Acids. *Langmuir.* 2003; 19:1295–1303.
- (36). Atmaja B, Cha JN, Frank CW. Adsorbed α -Helical Diblock Copolypeptides: Molecular Organization, Structural Properties, and Interactions. *Langmuir.* 2008; 25:865–872. [PubMed: 19177647]
- (37). Hardesty JO, Cascão-Pereira L, Kellis JT, Robertson CR, Frank CW. Enzymatic Proteolysis of a Surface-Bound α -Helical Polypeptide. *Langmuir.* 2008; 24:13944–13956. [PubMed: 19360953]
- (38). Wang J, Gibson MI, Barbey R, Xiao S-J, Klok H-A. Nonfouling Polypeptide Brushes via Surface-initiated Polymerization of N^E-oligo(ethylene glycol)succinate-L-lysine N-carboxyanhydride. *Macromol Rapid Commun.* 2009; 30:845–850. [PubMed: 21706667]
- (39). Zheng W, Frank CW. Surface-Initiated Vapor Deposition Polymerization of Poly(γ -benzyl-L-glutamate): Optimization and Mechanistic Studies. *Langmuir.* 2009; 26:3929–3941. [PubMed: 19961195]
- (40). Niwa M, Kuwagaki Y, Yamaguchi S, Higashi N. Effect of the helix macrodipole on surface-initiated N-carboxyanhydride polymerization on gold. *Angew. Chem. Int. Ed.* 2003; 42:1839–1841.
- (41). Vörös J. The density and refractive index of adsorbing protein layers. *Biophys. J.* 2004; 87:553–61. [PubMed: 15240488]
- (42). Chen T, Amin I, Jordan R. Patterned polymer brushes. *Chem. Soc. Rev.* 2012; 41:3280–3296. [PubMed: 22234473]
- (43). Wieringa RH, Siesling EA, Werkman PJ, Vorenkamp EJ, Schouten AJ. Surface grafting of poly (L-glutamates). 3 Block copolymerization. *Langmuir.* 2001; 17:6491–6495.
- (44). Wieringa RH, Siesling EA, Geurts PFM, Werkman PJ, Vorenkamp EJ, Erb V, Stamm M, Schouten AJ. Surface grafting of poly (L-glutamates). 1 Synthesis and characterization. *Langmuir.* 2001; 17:6477–6484.
- (45). Wieringa RH, Siesling EA, Werkman PJ, Angerman HJ, Vorenkamp EJ, Schouten AJ. Surface grafting of poly (L-glutamates). 2. Helix orientation. *Langmuir.* 2001; 17:6485–6490.
- (46). Kopple KD. Some Reactions of Amino Acid N-Carboxy Anhydrides. *J. Am. Chem. Soc.* 1957; 79:6442–6446.
- (47). Senaratne W, Andruzzi L, Ober CK. Self-Assembled Monolayers and Polymer Brushes in Biotechnology: Current Applications and Future Perspectives. *Biomacromolecules.* 2005; 6:2427–2448. [PubMed: 16153077]
- (48). Konradi R, Pidhatika B, Mühlebach A, Textor M. Poly-2-methyl-2-oxazoline: a peptide-like polymer for protein-repellent surfaces. *Langmuir.* 2008; 24:613–616. [PubMed: 18179272]

Figure 1.

Layer thickness vs. time as determined by ellipsometry (individual experiments) for surface initiated polymerization of sarcosine N-carboxyanhydride. The arrows connect data points obtained by consecutive polymerization of one sample using fresh monomer solution. The dotted dashed line indicates the fit of all data points using a Langmuir isotherm model.

Figure 2.

The AFM scans of a) PSar brushes after 48h of polymerization and b) PSar homoblock brushes after the third consecutive polymerization and a total polymerization time of 138h. The roughness analysis of representative areas showed for both samples a typical arithmetic average roughness of less than 1nm.

Figure 3. Comparison of the infrared spectra of polysarcosine obtained by solution polymerization and as a polymer brush.

Figure 4.

X-ray photoelectron spectra for a) APS SAM on Si/SiO₂, b) Same substrate after SI-ROP of Sar and detailed scans of PSar brush for c) carbon, d) oxygen e) nitrogen and f) silicon.

Figure 5. Amphiphilic polypeptoid brushes by consecutive SI-ROP of Sar-NCA and nBuGly-NCA. Brush layer height as determined by atomic force microscopy. Contact angles refer to static water contact angle (depicted are the actual photos of the sessile water drop).

Scheme 1.

Reaction scheme of the surface-initiated polymerization of N-substituted glycine N-carboxyanhydrides on amino-functionalized SAMs to yield hydrophilic or hydrophobic polypeptoid brushes. A consecutive surface-initiated polymerization with different monomers can yield amphiphilic polypeptoid brushes.