Hybridization gap and Fano resonance in SmB_6

Sahana Rößler^a, Tae-Hwan Jang^a, Dae-Jeong Kim^b, L. H. Tjeng^a, Zachary Fisk^{b,1}, Frank Steglich^a, and Steffen Wirth^{a,1}

^aMax-Planck-Institut für Chemische Physik fester Stoffe, 01187 Dresden, Germany; and ^bDepartment of Physics and Astronomy, University of California, Irvine, CA 92697

Contributed by Zachary Fisk, February 11, 2014 (sent for review November 26, 2013)

Hybridization between conduction electrons and the strongly interacting f -electrons in rare earth or actinide compounds may result in new states of matter. Depending on the exact location of the concomitant hybridization gap with respect to the Fermi energy, a heavy fermion or an insulating ground state ensues. To study this entanglement locally, we conducted scanning tunneling microscopy and spectroscopy (STS) measurements on the “Kondo insulator” SmB_6 . The vast majority of surface areas investigated were reconstructed, but infrequently, patches of varying sizes of nonreconstructed Sm- or B-terminated surfaces also were found. On the smallest patches, clear indications for the hybridization gap with logarithmic temperature dependence (as expected for a Kondo system) and for intermultiplet transitions were observed. On nonreconstructed surface areas large enough for coherent cotunneling, we were able to observe clear-cut Fano resonances. Our locally resolved STS indicated considerable finite conductance on all surfaces independent of their structure, not proving but leaving open the possibility of the existence of a topologically protected surface state.

Materials with strong electron correlations continue to draw enormous attention, not only because they may give rise to fundamentally new states of matter or new phenomena but also because of the hope for advanced technological applications. Heavy fermion (HF) materials, i.e., intermetallics of certain rare earths (REs), such as Ce, Sm, and Yb, are model systems to study strong electronic correlations (1). Here, the RE-derived localized $4f$ states are covalently mixed with the conduction-band states and, thus, acquire a finite lifetime. The associated decay rate in relation to the energy of the localized $4f$ state corresponds to the valency. In an Sm-based HF system, the valence lies between $3+$ ($4f^5$) and $2+$ ($4f^6$), which implies a considerable amount of charge fluctuations. This usually is referred to as intermediate valence (2). In addition to the abovementioned mixing of $4f$ states and the conduction band, which is well described within the framework of one-electron models, a many-body interaction is operating between the $4f$ and conduction electrons. This “Kondo effect” (3) eventually leads to a screening of the local moments as a result of particle-hole excitations that are manifested by a narrow Abrikosov–Suhl, or Kondo, resonance at E_F , the width of which is given by the single-ion Kondo temperature T_K .

Because of the periodic arrangement of REs in an HF intermetallic, the Kondo resonances form a weakly dispersive HF or “coherent $4f$ –” band, resulting in a heavy Fermi liquid state well below T_K . The band interaction between the renormalized $4f$ and the conduction band generates a so-called hybridization gap, which opens at around T_K . Under certain conditions, E_F may reside inside this gap, characterizing a so-called Kondo insulator (4).

SmB_6 is such a Kondo insulator, with a valence $\nu \sim 2.6$ (5), ν being slightly temperature dependent (6, 7). A sharp decrease in the density of states (DOS) at E_F is seen most dramatically in the rise of the resistance over more than three orders of magnitude below ~ 40 K (8, 9). Many other measurements, including far-infrared absorption (9) and NMR (10), are consistent with the opening of an activation gap of about 3 meV. The gradual opening of a hybridization gap of about 18 meV below ~ 100 K and signatures of interion correlations below ~ 30 K recently were

reported based on point-contact (11) and angle-resolved photoemission spectroscopy (ARPES) (12–14). However, the gap being caused by hybridization is discussed controversially. For instance, if the hybridization is altered by the application of pressure, a continuous change in the gap is expected (15, 16), although other experiments show a discontinuous change (17, 18). This is relevant because altered atomic distances at the surface (e.g., by valence changes at the surface) then also may result in a conducting surface layer. Moreover, the hybridization usually is discussed in relation to a gap of around 20 meV (11, 13, 19), whereas a thermal activation gap of around 3 meV is referred to in-gap states (9, 20, 21); the relation between the two is not clear.

Intriguingly, unlike in an insulator, the resistance of SmB_6 saturates below about 4 K (22). Recently, it was proposed (23, 24) that SmB_6 may be a strong 3D topological insulator in which the topologically nontrivial insulating state is produced by the hybridization between the conduction band and coherent $4f$ band. This proposal sparked a flurry of experimental attempts to demonstrate the existence of such topological surface states (25–29). However, ARPES could not unambiguously reveal (12–14, 21) the associated Dirac cones. Our focus, however, is not primarily on these topological properties of SmB_6 , yet our atomically resolved surface topographies provide valuable information for nonlocal types of measurements whereas the concomitant spectroscopy indicates a finite low-temperature surface conductance independent of the surface termination.

In an effort to study the DOS, tunneling (30, 31) and point contact spectroscopy (11, 20) were conducted, most of which indicated the opening of a gap of the order of 20 meV. However, as shown below, locally (atomically) resolved information on the DOS is required and may be obtained (32) by scanning tunneling microscopy (STM) on SmB_6 . For any surface-sensitive measurement, information on the surface structure is required to

Significance

Quantum entanglement may give rise to emerging phenomena and new states of matter. In the intermediate-valence material SmB_6 , this is realized via hybridization between localized $4f$ and conduction band states that, at sufficiently low temperatures, results in the screening of the $4f$ local moments by the conduction electrons and produces a so-called Kondo resonance in the density of states. The latter is examined by scanning tunneling spectroscopy down to temperatures well below the Kondo temperature. This atomically resolved spectroscopy allows one to distinguish between reconstructed and pristine surfaces and different surface terminations, all of which influence the spectroscopic results. These insights are vital for other, less local spectroscopic tools in the context of possible topologically protected surface states.

Author contributions: Z.F. and S.W. designed research; S.R. and T.-H.J. performed research; D.-J.K. and Z.F. contributed new reagents/analytic tools; S.R., D.-J.K., L.H.T., Z.F., F.S., and S.W. analyzed data; and S.R., L.H.T., F.S., and S.W. wrote the paper.

The authors declare no conflict of interest.

Freely available online through the PNAS open access option.

¹To whom correspondence may be addressed. E-mail: wirth@cpfs.mpg.de or zfisk@uci.edu.

This article contains supporting information online at www.pnas.org/lookup/suppl/doi:10.1073/pnas.1402643111/-DCSupplemental.

Fig. 2. Topography on small ($2 \times 2 \text{ nm}^2$) nonreconstructed surface areas of (A) Sm-termination ($V = 0.2 \text{ V}$, $I_{sp} = 0.6 \text{ nA}$) and (B) B-termination. Cyan circles in (A) indicate Sm atoms, the pink one encircles a B atom (compare Fig. 1). (C and D) Height scans along the white line (parallel to $\langle 110 \rangle$) indicated in A and the line parallel to $\langle 100 \rangle$ in B, respectively.

and (iii), can barely be disentangled (see also spectra at even higher temperature; Fig. S3 in *Supporting Information*). To investigate the hybridization gap further, we studied the T -dependence of its depth at $V = 0$ relative to the tunneling conductance at $|V| \geq 50 \text{ mV}$ (*Materials and Methods* and Fig. S4). The T -dependent closing-up of this partial gap for two different samples is presented in Fig. 3C. The experimental values for the normalized depth of this gap agrees well with results for the single-ion conductance within numerical renormalization group calculations (48) that predict a logarithmic decay, i.e., $\propto -\log(T/T_K)$, for T of order T_K (dashed line). Such a logarithmic T -dependence is a hallmark of Kondo physics and supports a scenario based on the Kondo effect (4, 49). The gap has decayed to half its zero-temperature depth (50) at $T_K \approx 39 \text{ K}$, in line with other estimates for the opening of the hybridization gap. Deviations from this logarithmic T -dependence due to departure from single-ion behavior, i.e., due to enhanced lattice effects of the Kondo ions, become apparent at $T \lesssim 15 \text{ K}$, in a regime in which possible in-gap states also appear [feature (v)].

Temperature-dependent dI/dV -curves obtained on a nonreconstructed B-terminated surface are presented in Fig. 3D. As expected, the hybridization gap exhibits behavior very similar to that on Sm-terminated surfaces. However, all other features appear to be shifted toward smaller absolute values of energy (or $|V|$). This highlights the necessity to involve spectroscopic techniques that allow discrimination between differently terminated surfaces when analyzing SmB_6 surfaces. However, the B-terminated surfaces also exhibit a finite conductance at $V = 0$, again compatible with an additional (surface) conductance channel.

Only very rarely did we succeed in locating larger patches of nonreconstructed areas that clearly exceed lateral dimensions of 10 nm^2 (so far, such patches were found on only two cleaved surfaces), as reported in ref. 51. Two such examples are shown in Fig. 4A and B. The height scans along the white lines in Fig. 4A and B, which are presented in Fig. 4C and D respectively, were conducted parallel to $\langle 100 \rangle$ directions and confirm the expected unit-cell spacing a between the corrugations. There are no discernible intermediate corrugations at any $\langle 110 \rangle$ direction in Fig. 4A. However, they are obvious in Fig. 4B: The height scan along the $[110]$ direction, blue lines marked 2 in Fig. 4B and D, exhibits corrugations spaced by about $a/\sqrt{2}$, as in Fig. 2A. Consequently, we attribute the surface of Fig. 4A to a B-terminated

one, whereas Fig. 4B represents an Sm-terminated surface. The latter surface exhibits dents of about 80 pm in depth (see blue line 2 in Fig. 4D), corresponding to the height difference between Sm and the topmost B atom on an Sm-terminated surface (compare *Supporting Information, Investigation of Step Edges*). This suggests that these dents are caused by missing Sm atoms, probably ripped out of the Sm surface layer while cleaving the sample. In contrast, on the B-terminated, nonreconstructed surface of Fig. 4A, there are only small height variations of some picometers, resulting in patches of a few lattice constants in extent.

Discussion

Conducting STS on such an extended nonreconstructed B surface provided dI/dV -curves such as the one shown in Fig. 4E for $T = 4.6 \text{ K}$. Clearly, such a tunneling conductance indicates a Fano resonance at energy E_0 that results from tunneling into two coupled channels (33), namely the conduction band and the $4f$ quasiparticle states (34, 36, 37). Likely, these nonreconstructed areas are large enough to establish coherence in the two tunneling channels; yet, it also is possible that the position in energy relative to E_F of these two channels or the electronic structure changes accordingly (52). The resulting tunneling conductance may be expressed as (53):

$$g(V) \propto \frac{(\epsilon + q)^2}{\epsilon^2 + 1}, \quad \epsilon = \frac{2(eV - E_0)}{\Gamma}. \quad [1]$$

Here, Γ describes the resonance width. The asymmetry parameter q is related to the ratio of probabilities for tunneling into the $4f$ states vs. into the conduction band as well as the particle-hole asymmetry of the conduction band (36). Eq. 1 was applied successfully to single-impurity (54, 55) as well as Kondo lattice systems (56, 57). Clearly, Eq. 1 also describes our low-temperature data excellently, even without considering details of the DOS (11). The corresponding fit (red line in Fig. 4E) yields $\Gamma = 16.5 \text{ mV}$, a value that agrees well with the width of the hybridization gap discussed above. As to be expected for a B-terminated surface, the value of $|q| = 0.77$ is smaller than unity, consistent with predominant tunneling into the conduction band. Note that the asymmetry shown here is consistent with other STM

Fig. 3. Tunneling spectroscopy on an Sm-terminated surface. (A) Spectroscopy at 4.6 K . Features marked by arrows are discussed in the text using corresponding labels. (B) Temperature-dependent STS on an Sm-terminated surface. dI/dV -curves for $T \geq 7 \text{ K}$ are offset for clarity. (C) Temperature dependence of the zero-bias dip measured on Sm-terminated surfaces of two different samples. The dashed line indicates a logarithmic T -dependence. (D) T -dependent STS on a B-terminated surface. All spectra are averaged over areas of some square nanometers. Parameters before opening the feedback loop for conducting spectroscopy: $V = 0.2 \text{ V}$, $I_{sp} = 0.6 \text{ nA}$.

Fig. 4. Comparison between larger, nonreconstructed B-terminated (Left) and Sm-terminated surfaces (Right). (A and B) Topographies on B-surfaces ($20 \times 20 \text{ nm}^2$) and Sm-surfaces ($17.2 \times 17.2 \text{ nm}^2$), respectively. (C and D) Height scans along the lines marked in A and B. White lines are parallel to $\langle 100 \rangle$ directions; blue line 2 in B and D is along $\langle 110 \rangle$ to enable comparison of distances between corrugations to Fig. 2A. (E and F) Tunneling spectroscopies (circles) at 4.6 K on B- and Sm-terminated surfaces, respectively. The lines are fits to the Fano formula; the obtained values of q are indicated.

measurements on a reconstructed surface (32) but opposite to results from point-contact spectroscopy (11).

An overall very similar behavior is observed for spectra obtained on an Sm-terminated surface (Fig. 4F), with the exception of two additional excitations at around 10 and 25 meV. If these two excitations are ignored, again, a good fit of Eq. 1 to the data is possible (line in Fig. 4F). The value $\Gamma = 16.4 \text{ meV}$ thus obtained agrees with that of the B-terminated surface, as expected for the hybridization. However, $|q| = 1.16$ indicates a more pronounced tunneling into the $4f$ quasiparticle states, which appears reasonable on an Sm-terminated surface. Both additional excitations also have been seen in earlier point-contact measurements in the tunneling regime (20). One may speculate that the excitation at 25 meV has its counterpart at -27 meV at smaller nonreconstructed Sm surfaces [feature (iv) above], with the respective features at opposite voltage signs masked by other, more pronounced excitations.

To allow comparison of the tunneling spectra on different surfaces, we also present $dI(V)/dV$ -curves obtained on reconstructed surfaces, both disordered (Fig. 5A) and ordered [i.e., with (2×1) reconstruction (Fig. 5B)]. These data were obtained at $T = 4.6 \text{ K}$. Part of a disordered, chain-like surface reconstruction is shown in Fig. 5A, Inset. Two exemplary spectra were taken on top of the chain-like features (speculated to be Sm; blue spectrum and position marked by a blue dot in the topography image) and between these features (speculated to be B terraces; red spectrum and position marked by a red dot). No significant difference is apparent. Moreover, the area-averaged conductance curve (black curve) does not reveal any apparent

feature; only a faint, broad hump might be visible at around -20 mV . This finding reinforces our focus on nonreconstructed surface areas above.

Tunneling conductance obtained within the ordered (2×1) reconstructed surface shown in Fig. 1A is presented in Fig. 5B. This $dI(V)/dV$ -curve is similar to other STS results (32) obtained on (2×1) reconstructed surfaces. Furthermore, it also bears resemblance to the spectra observed on larger nonreconstructed areas (compare Fig. 4E and F). The red dashed line again results from a fit to a Fano resonance (Eq. 1), yielding $|q| = 1.28$ and $\Gamma = 8.4 \text{ meV}$. Clearly, this fit is of inferior quality if compared with fits performed on $dI(V)/dV$ -curves from nonreconstructed surfaces, specifically on B-terminated surfaces.

We speculate that both surface reconstructions alter the electronic properties at the surface. In case of the disordered surface reconstruction, it may mask the bulk electronic properties. For the ordered (2×1) reconstruction, we observe a clear shift in the position of the peak in the $dI(V)/dV$ -curves to approximately -8 mV (Fig. 5B) [in contrast to -16 mV on both nonreconstructed surfaces: B-terminated (Fig. 4E) and Sm-terminated (Fig. 4F)]. Also, it may lead to the reduced value of Γ in the case of (2×1) reconstruction. There is, of course, the possibility that a description by a Fano resonance may become inappropriate in describing the spectroscopy on the reconstructed surface. Further, one may speculate that such altered electronic properties are one contribution for the need to describe point-contact spectra (11) by a more elaborate scenario going well beyond the simple Fano resonance Eq. 1 used here. This, again, supports our focus on nonreconstructed surfaces, for which a description by a simple Fano resonance works best.

All the investigated surfaces exhibit a finite conductance at $V = 0$. Consequently, our locally resolved measurements show that the surface reconstruction alone cannot account for the surface conductance (51). The robustness of the measured conductance at $V = 0$ is consistent with an additional conductance channel, possibly at the surface.

Fig. 5. Spectroscopy on differently reconstructed surfaces of SmB_6 at 4.6 K. (A) Disordered surface reconstruction as shown in Inset (area of $8 \times 3 \text{ nm}^2$). The blue $dI(V)/dV$ curve was taken on top of the chain-like features (likely Sm), the red one between those (positions marked by dots of matching color in the topography Inset). The black spectrum is an area-averaged curve with only very faint features. (B) Spectroscopy on the (2×1) reconstructed surface of Fig. 1A. The red dashed line is a fit assuming a Fano resonance.

In conclusion, we observed two different types of surfaces: predominantly reconstructed surfaces but occasionally also non-reconstructed ones. For the latter, Sm- as well as B-terminations were found, but larger areas (lateral extension well beyond 10 nm) were encountered only very rarely. STS on nonreconstructed surfaces indicated the formation of a hybridization gap with logarithmic T -dependence and $T_K \approx 40$ K, as well as intermultiplet transitions of Sm^{2+} ions. Spectra on larger nonreconstructed areas showed excellent formation of Fano resonances, establishing the underlying hybridization effect. We speculate that the size of the nonreconstructed surface area is important to establish quantum interference between the two tunneling channels and, hence, Fano resonance. All SmB_6 surfaces exhibited a finite conductance consistent with the existence of a robust surface conducting layer.

Materials and Methods

Single crystals of SmB_6 were grown by using the aluminum flux method. SmB_6 crystallizes in a CaB_6 structure type with space group $Pm\bar{3}m$ (221), lattice constant $a = 4.133$ Å. Reported here are results obtained from nine samples, cleaved in situ at $T \sim 20$ K approximately along one of the principal cubic crystallographic axes. STM was conducted in an ultra-high vacuum

system (Omicron Nanotechnology) at $p \lesssim 2 \times 10^{-9}$ Pa and with a base temperature of 4.6 K.

The tunneling conductance spectra $g(V) = dI(V)/dV$ exhibit a partially developed hybridization gap at sufficiently low temperature. Our estimate of its depth at zero bias was based on the procedure introduced in ref. 49. The good linearity of $g(V, T)$ for $|V| \geq 30$ mV and $T \geq 30$ K is shown in an exemplary way ($T = 50$ K) in Fig. S4. Based on this linearity, we estimate the zero-bias conductance without the effect of a hybridization gap, $g^{\text{lin}}(V=0, T)$, i.e., under the assumption of a fully suppressed gap, by linearly extrapolating the $g(V, T)$ data for $|V| > 30$ mV to $V=0$ (red dashed lines in Fig. S4). The relative gap depth—as shown in Fig. 3C—is then given by $[g^{\text{lin}}(V=0, T) - g(V=0, T)]/g^{\text{lin}}(V=0, T)$, which corresponds to the relative conductance difference between the blue (experimental) data and the red extrapolations at $V=0$ in Fig. S4. For temperatures $T < 30$ K, additional features were observed in $g(V, T)$, as discussed in the main text. Therefore, for the linear extrapolations only values $g(V, T)$ for $|V| > 50$ mV were considered.

ACKNOWLEDGMENTS. The authors are indebted to J. W. Allen, P. Coleman, A. Damascelli, C. Geibel, S. Kirchner, Q. Si, and P. Thalmeier for stimulating discussions. This work was supported by the Max Planck–POSTECH Center for Complex Phase Materials. Research at University of California, Irvine was supported by National Science Foundation Grant DMR-0801253.

- Grewe N, Steglich F (1991) *Handbook on the Physics and Chemistry of Rare Earths*, eds Gschneidner KA, Jr., Eyring L (Elsevier, Amsterdam), Vol 14, pp 343–474.
- Varma CM (1976) Mixed-valence compounds. *Rev Mod Phys* 48(2):219–238.
- Kondo J (1964) Resistance minimum in dilute magnetic alloys. *Prog Theor Phys* 32(1):37–49.
- Aeppli G, Fisk Z (1992) Kondo insulators. *Comments Cond Mat Phys* 16(3):155–165.
- Vainshtein EE, Blokhin SM, Paderno YuB (1965) X-ray spectral investigation of samarium hexaboride. *Sov Phys-Solid State* 6(10):2318–2320.
- Tarascon JM, et al. (1980) Temperature dependence of the samarium oxidation state in SmB_6 and $\text{Sm}_{1-x}\text{La}_x\text{B}_6$. *J Phys* 41(10):1141–1145.
- Mizumaki M, Tsutsui S, Iga F (2009) Temperature dependence of Sm valence in SmB_6 studied by X-ray absorption spectroscopy. *J Phys Conf Ser* 176:012034.
- Allen JW, Batlogg B, Wachter P (1979) Large low-temperature Hall effect and resistivity in mixed-valent SmB_6 . *Phys Rev B* 20(12):4807–4813.
- von Molnár S, et al. (1982) *Valence Instabilities*, eds Wachter P, Boppert H (North-Holland, Amsterdam), pp 389–395.
- Pena O, Lysak M, MacLaughlin DE, Fisk Z (1981) Nuclear spin relaxation, hybridization, and low-temperature $4f$ spin fluctuations in intermediate-valent SmB_6 . *Solid State Commun* 40(5):539–541.
- Zhang X, et al. (2013) Hybridization, correlation, and in-gap states in the Kondo insulator SmB_6 . *Phys Rev X* 3(1):011011.
- Xu N, et al. (2013) Surface and bulk electronic structure of the strongly correlated system SmB_6 and implications for a topological Kondo insulator. *Phys Rev B* 88(12):121102.
- Neupane M, et al. (2013) Surface electronic structure of the topological Kondo-insulator candidate correlated electron system SmB_6 . *Nat Commun* 4:2991.
- Frantzeskakis E, et al. (2013) Kondo hybridization and the origin of metallic states at the (001) surface of SmB_6 . *Phys Rev X* 3(4):041024.
- Moshchalkov VV, et al. (1985) SmB_6 at high pressures: The transition from insulating to the metallic Kondo lattice. *J Magn Magn Mater* 47-48:289–291.
- Gabáni S, et al. (2003) Pressure-induced Fermi-liquid behavior in the Kondo insulator SmB_6 : Possible transition through a quantum critical point. *Phys Rev B* 67(17):172406.
- Cooley JC, Aronson MC, Fisk Z, Canfield PC (1995) SmB_6 : Kondo insulator or exotic metal? *Phys Rev Lett* 74(9):1629–1632.
- Derr J, et al. (2008) From unconventional insulating behavior towards conventional magnetism in the intermediate-valence compound SmB_6 . *Phys Rev B* 77(19):193107.
- Gorshunov B, et al. (1999) Low-energy electrodynamics of SmB_6 . *Phys Rev B* 59(3):1808–1814.
- Flachbart K, et al. (2001) Energy gap of intermediate-valent SmB_6 studied by point-contact spectroscopy. *Phys Rev B* 64:085104.
- Miyazaki H, Hajiri T, Ito T, Kunii S, Kimura SI (2012) Momentum-dependent hybridization gap and dispersive in-gap state of the Kondo semiconductor SmB_6 . *Phys Rev B* 86(7):075105.
- Menth A, Buehler E, Geballe TH (1969) Magnetic and semiconducting properties of SmB_6 . *Phys Rev Lett* 22(7):295–297.
- Dzero M, Sun K, Galitski V, Coleman P (2010) Topological Kondo insulators. *Phys Rev Lett* 104(10):106408.
- Takimoto T (2011) SmB_6 : A promising candidate for a topological insulator. *J Phys Soc Jpn* 80(12):123710.
- Wolgast S, et al. (2013) Low-temperature surface conduction in the Kondo insulator SmB_6 . *Phys Rev B* 88(18):180405.
- Kim DJ, et al. (2013) Surface hall effect and nonlocal transport in SmB_6 : Evidence for surface conduction. *Sci Rep* 3:3150.
- Jiang J, et al. (2013) Observation of possible topological in-gap surface states in the Kondo insulator SmB_6 by photoemission. *Nat Commun* 4:3010.
- Kim D-J, Xia J, Fisk Z (2013) Topological surface state in the Kondo insulator samarium hexaboride. arXiv:1307.0448.
- Li G, et al. (2013) Quantum oscillations in Kondo insulator SmB_6 . arXiv:1306.5221.
- Güntherodt G, Thompson WA, Holtzberg F, Fisk Z (1982) Electron tunneling into intermediate-valence materials. *Phys Rev Lett* 49(14):1030–1033.
- Amsler B, et al. (1998) Electron-tunneling studies of the hexaboride materials SmB_6 , EuB_6 , CeB_6 , and SrB_6 . *Phys Rev B* 57(15):8747–8750.
- Yee MM, et al. (2013) Imaging the Kondo insulating gap on SmB_6 . arXiv:1308.1085.
- Fano U (1961) Effects of configuration interaction on intensities and phase shifts. *Phys Rev* 124(6):1866–1878.
- Maltseva M, Dzero M, Coleman P (2009) Electron cotunneling into a Kondo lattice. *Phys Rev Lett* 103(20):206402.
- Yang Y-F (2009) Fano effect in the point contact spectroscopy of heavy-electron materials. *Phys Rev B* 79(24):241107.
- Figgins J, Morr DK (2010) Differential conductance and quantum interference in Kondo systems. *Phys Rev Lett* 104(18):187202.
- Wölfle P, Dubi Y, Balatsky AV (2010) Tunneling into clean heavy fermion compounds: Origin of the Fano line shape. *Phys Rev Lett* 105(24):246401.
- Aono M, et al. (1979) LaB_6 and SmB_6 (001) surface studies by angle-resolved XPS, LEED, and ISS. *Surf Sci* 86:631–637.
- Noguera M (2000) Polar oxide surfaces. *J Phys Condens Matter* 12(31):R367–R410.
- Monnier R, Delley B (2001) Point defects, ferromagnetism, and transport in calcium hexaboride. *Phys Rev Lett* 87(15):157204.
- Alekseev PA, et al. (1993) Neutron scattering study of the intermediate-valent ground state in SmB_6 . *Europhys Lett* 23(5):347–353.
- Antonov VN, Harmon BN, Yaresko AN (2002) Electronic structure of mixed-valence semiconductors in the LSDA+U approximation: SmB_6 and YbB_{12} . *Phys Rev B* 66(16):165209.
- Alekseev PA, Lazukov VN, Mignot J-M, Sadikov IP (2000) Neutron scattering studies of intermediate-valence compounds. *Physica B* 281-282:34–41.
- Nyhus P, Cooper SL, Fisk Z, Sarrao JL (1995) Light scattering from gap excitations and bound states in SmB_6 . *Phys Rev B* 52(20):14308–14311.
- Gabáni S, et al. (2001) Properties of the in-gap states in SmB_6 . *Solid State Commun* 117(11):641–644.
- Nozawa S, et al. (2002) Ultrahigh-resolution and angle-resolved photoemission study of SmB_6 . *J Phys Chem Solids* 63(6-8):1223–1226.
- Caldwell T, et al. (2007) High-field suppression of in-gap states in the Kondo insulator SmB_6 . *Phys Rev B* 75(7):075106.
- Costi TA (2000) Kondo effect in a magnetic field and the magnetoresistivity of kondo alloys. *Phys Rev Lett* 85(7):1504–1507.
- Ernst S, et al. (2011) Emerging local Kondo screening and spatial coherence in the heavy-fermion metal YbRh_2Si_2 . *Nature* 474(7351):362–366.
- Goldhaber-Gordon D, et al. (1998) From the Kondo regime to the mixed-valence regime in a single-electron transistor. *Phys Rev Lett* 81(23):5225–5228.
- Zhu Z-H, et al. (2013) Polarity-driven surface metallicity in SmB_6 . *Phys Rev Lett* 111(21):216402.
- Pihl M, Gadzuk JW (2001) Nonequilibrium theory of scanning tunneling spectroscopy via adsorbate resonances: Nonmagnetic and Kondo impurities. *Phys Rev B* 63(8):085404.
- Schiller A, Hershfield S (2000) Theory of scanning tunneling spectroscopy of a magnetic adatom on a metallic surface. *Phys Rev B* 61(13):9036–9046.
- Madhavan V, Chen W, Jamneala T, Crommie MF, Wingreen NS (1998) Tunneling into a single magnetic atom: spectroscopic evidence of the kondo resonance. *Science* 280(5363):567–569.
- Li J, Schneider W-D, Berndt R, Delley B (1998) Kondo scattering observed at a single magnetic impurity. *Phys Rev Lett* 80(13):2893–2896.
- Schmidt AR, et al. (2010) Imaging the Fano lattice to ‘hidden order’ transition in URu(2)Si(2). *Nature* 465(7298):570–576.
- Aynajian P, et al. (2012) Visualizing heavy fermions emerging in a quantum critical Kondo lattice. *Nature* 486(7402):201–206.