Published in final edited form as:

RSC Adv. 2014 January 1; 4(21): 10586–10596. doi:10.1039/C3RA46149A.

Aqueous Ionic Liquids and Deep Eutectic Solvents for Cellulosic Biomass Pretreatment and Saccharification

Shuqian Xia^a, Gary A. Baker^b, Hao Li^a, Sudhir Ravula^b, and Hua Zhao^{*,c}

^a School of Chemical Engineering & Technology, Tianjin University, Tianjin 300072, China

^b Department of Chemistry, University of Missouri-Columbia, Columbia, MO 65211, USA

^c Department of Chemistry and Forensic Science, Savannah State University, Savannah, GA 31404, USA

Abstract

Ionic liquids (ILs) have proven effective solvents for pretreating lignocellulose, leading to the fast saccharification of cellulose and hemicellulose. However, the high current cost of most ILs remains a major barrier to commercializing this recent approach at a practical scale. As a strategic detour, aqueous solutions of ILs are also being explored as less costly alternatives to neat ILs for cellulose pretreatment. However, limited studies on a few select IL systems are known and there remains no systematic survey of various ILs, eluding an in-depth understanding of pretreatment mechanisms afforded by aqueous IL systems. As a step toward filling this gap, this study presents results for Avicel cellulose pretreatment by neat and aqueous solutions (1.0 and 2.0 M) of 20 different ILs and three deep eutectic solvents, correlating enzymatic hydrolysis rates of pretreated cellulose with various IL properties such as hydrogen-bond basicity, polarity, Hofmeister ranking, and hydrophobicity. The pretreatment efficiencies of neat ILs may be loosely correlated to the hydrogen-bond basicity of the constituent anion and IL polarity; however, the pretreatment efficacies for aqueous ILs are more complicated and cannot be simply related to any single IL property. Several aqueous IL systems have been identified as effective alternatives to neat ILs in lignocellulose pretreatment. In particular, this study reveals that aqueous solutions of 1-butyl-3-methylimidazolium methanesulfonate ([BMIM][MeSO₃]) are effective for pretreating switchgrass (*Panicum virgatum*), resulting in fast saccharification of both cellulose and hemicellulose. An integrated analysis afforded by X-ray diffraction, scanning electron microscopy, thermogravimetric analysis and cellulase adsorption isotherm of lignocellulose samples is further used to deliver a more complete view of the structural changes attending aqueous IL pretreatment.

Keywords

ionic liquid; cellulose; pretreatment; enzymatic hydrolysis; cellulosic ethanol

1 Introduction

Ionic liquids (ILs) are unconventional, essentially non-volatile ionic organic solvents with melting points generally below 100 °C. Some ILs are capable of dissolving cellulosic biomass and have thus become the subject of intensive study as alternative media for lignocellulose pretreatment toward bioethanol production.¹⁻³ Although IL pretreatment often

*Corresponding author: Department of Chemistry and Forensic Science Savannah State University Savannah, GA 31404, USA
huazhao98@gmail.com (or zhaoh@savannahstate.edu) Phone: 912-358-4448.

†In this case, 1 U corresponds to the liberation of 1.0 µg of glucose per minute at 35 °C.

leads to an accelerated saccharification of cellulosic biomass, this method has encountered several obstacles associated with ILs such as their high cost, energy intensive recycling, and environmental concerns over their toxicity and biodegradability.^{4, 5} It is worth noting that the high IL cost is at least in part due to the pervasive use of the currently expensive imidazolium cations in designing cellulose-dissolving ILs.

To address the high cost issue of ILs, a number of different approaches have been considered in addition to the recycling and reuse of ILs.⁶⁻⁸ The first approach entails the synthesis of some novel but less expensive ILs for cellulose dissolution. Along these lines of inquiry, our group has recently prepared relatively inexpensive and low-viscosity ether-functionalized alkylammonium and piperidinium ILs bearing acetate anions that are able to dissolve ~10 wt% cellulose.^{9, 10} Other groups have prepared cellulose-dissolving ILs containing amino acid-derived anions: (a) [EMIM][glycinate] reportedly afforded the complete dissolution of bamboo biomass¹¹; and (b) *N,N*-diethyl-*N*-(2-methoxyethyl)-*N*-methylammonium ILs containing amino acid anions like alaninate were able to dissolve 5–12 wt% cellulose at 100 °C.¹² King et al.¹³ prepared novel guanidine-based ‘distillable’ acid–base conjugate ILs for dissolving microcrystalline cellulose (up to 5–10 wt%) at 100 °C. Zhang et al.¹⁴ developed a new CO₂-triggered switchable system by mixing DMSO, non-ionic bases, and CO₂. This switchable solvent platform was able to dissolve up to 15 wt % microcrystalline cellulose and the regenerated cellulose displayed a reduced crystallinity and a fast hydrolysis rate.

A second strategy for improving the economics of IL-based cellulose pretreatment is substituting pure ILs with ionic or eutectic mixtures. For example, the Jérôme group¹⁵ claimed that inexpensive ionic mixtures of cholinium acetate with 5–15 wt% of tributylmethylammonium chloride could dissolve 2–6 wt% microcrystalline cellulose (i.e., Avicel PH 105) at 110 °C. Rinaldi¹⁶ reported that amide-related solvents (such as 1,3-dimethyl-2-imidazolidinone and DMSO) containing a small fraction of [EMIM][OAc] or [BMIM]Cl (at molar fractions below 0.3, for instance) could instantaneously dissolve 10 wt % cellulose at 100 °C. In another example, the Francisco group¹⁷ designed biorenewable deep eutectic solvents (DESs) based on betaine, choline, and amino acids coupled with lactic or malic acid for dissolving large amounts (up to 12 to 15 wt%) of lignin (despite the poor solubility of cellulose), and further demonstrated the utility of their DESs in the delignification of wheat straw.

A third approach used to minimize the cost associated with using ILs to treat cellulosic materials involves the addition of compatible organic co-solvents. Unlike solvents such as alcohols, the co-solvents selected for this application are those that do not precipitate cellulose from the IL solution, at least within the chosen solvent composition range. In recent work, the Heinze group¹⁸ systematically examined the impact of 18 solvents and three binary solvent mixtures on cellulose solutions in IL and indicated that ideal co-solvents (such as DMSO, DMF and dichloromethane) typically have solvatochromic polarity E_T^N values above 0.3, very low ‘acidity’ ($\alpha < 0.5$), and relatively high ‘basicity’ ($\beta \approx 0.4$). The use of these co-solvents not only forms homogeneous cellulose solutions in ILs, but also considerably reduces the cost and viscosity of the resulting IL-based system. Tian et al.¹⁹ examined the enzymatic digestibility of microcrystalline cellulose pretreated by organic electrolyte solutions (mixtures of 1-allyl-3-methylimidazolium chloride ([AMIM]Cl) with DMSO) and suggested that the hydrolysis yield and rate increased with the mole fraction of [AMIM]Cl in the mixture; after cellulose pretreatment by an organic electrolyte solution containing 0.7 mole fraction of [AMIM]Cl, they achieved 54.1% glucose yield, which was 7.2 times higher than that of untreated cellulose.

Yet a fourth approach entails pretreating cellulose with aqueous solutions of ILs (i.e., as opposed to neat ILs). For example, the Mazza group^{20, 21} achieved an optimum fermentable sugar recovery of 71.4% from wheat straw when using an aqueous solution of 49.5 wt% [EMIM][OAc] at 158 °C for 3.6 h. Brandt et al.²² obtained ca. 90% glucose yields from cellulosic biomass pretreated by aqueous solutions of 80 vol% [BMIM][MeSO₃], [BMIM][MeSO₄], or [BMIM][HSO₄] at 120 °C for 22 h, but observed lower saccharification yields after pretreatment with 80 vol% acetate-based ILs. The Zhang group²³ pretreated sugarcane bagasse at 130 °C for 30 min by aqueous [BMIM]Cl solution containing 1.2% HCl, leading to a glucan recovery of >90% and digestibility of 94–100% after 72 h of enzymatic hydrolysis; however, the acidic condition resulted in the loss of most xylan. Although these aqueous ILs appear promising alternatives to neat ILs for lignocellulose pretreatment, there currently exists no study screening a wide spectrum of ILs. In addition, although the cellulose dissolution capability of neat ILs is often associated with the hydrogen-bond basicity of their constituent anions,^{9, 24} it is not currently understood how aqueous ILs impact biomass pretreatment, as cellulose is insoluble in known aqueous IL systems.

Aiming at an in-depth understanding of cellulose pretreatment by aqueous ILs, we set out to determine and compare saccharification rates for cellulose pretreated with 20 different ILs and three cholinium-based DESs, neat and at 1.0 and 2.0 M concentrations in water. In order to better understand the pretreatment process, we also examined the cellulosic structure by X-ray diffraction (XRD), scanning electron microscopy (SEM), and thermogravimetric analysis (TGA), as well as attempting to correlate the enzymatic hydrolysis rate with the physical properties of the ILs. Finally, we also tested the saccharification efficiency for switchgrass pretreated with neat and aqueous ILs. The mechanistic insights offered by our systematic study bring into focus a clearer picture of what future role aqueous ILs might play in lignocellulose pretreatment and saccharification.

2 Experimental

2.1 Materials

A number of ILs were acquired from commercial sources, although several were prepared in house (see Table S1 in *Electronic Supporting Information (ESI)* for details). The following chemicals and enzymes were purchased from Sigma-Aldrich (St. Louis, MO): Avicel PH-101 cellulose (microcrystalline cellulose (MCC), particle size 50 µm, DP 225, produced by FMC Corp.), cellulase from *Trichoderma reesei* (product # 22173, Lot # 1086305, E.C. #3.2.1.4, slightly brown powder, 6.7 U/mg or 0.5 FPU/mg) and glucose (HK) assay kit. β-Glucosidase from sweet almonds was obtained from MP biomedical (product # 100348, Lot # R28034, 3811 U/mg[±]). Switchgrass was a kind gift from Dr. H. M. O'Neill (Oak Ridge National Laboratory); it was grown, harvested, dried, and then knife-milled to an average particle size of 0.5 mm. D-Xylose assay kit (Catalog # K-XYLOSE) was obtained from the Megazyme International Ireland Ltd. (Bray, Co. Wicklow, Ireland).

2.2 Pretreatment of Avicel PH-101 and switchgrass by IL solutions—Most attempts at IL pretreatment of cellulosic biomass can be subsumed under two broad categories: regeneration pretreatment and suspension pretreatment. Both avenues were involved in the course of the current work. (1) *Regeneration pretreatment*. When employing neat cellulose-dissolving ILs, 2.0 mL of an IL within a glass test tube was immersed in an oil bath held at 110 °C. Samples of cellulose were carefully added to the IL in 10 mg increments. After each addition step, a clear and visually homogeneous solution was awaited before proceeding to the next addition. The cellulose was incubated in the oil bath for 4 h at 110 °C. After cooling to room temperature, the cellulose was regenerated by the addition of distilled water followed by vigorous stirring for 30 min. The ensuing cellulose precipitates

were collected by vacuum filtration, followed by thorough washing and drying using distilled water followed by acetone. The pretreated cellulose was dried in air for 48 h before use in experiments. (2) *Suspension pretreatment*. In cases where IL solutions could not fully dissolve cellulose, 0.2 g of cellulose (or 0.1 g of switchgrass) was suspended in 2.0 mL of an IL (or its aqueous solution) and incubated in an oil bath at 110 °C for 4 h. After the solution was cooled to room temperature, distilled water was added into the solution with vigorous stirring for 30 min. The treated cellulose was collected, washed, and dried exactly as written for the regeneration pretreatment approach.

2.3 Enzymatic hydrolysis of cellulose and switchgrass—A suspension of 20 mg (untreated or pretreated) of Avicel PH-101 cellulose or switchgrass (2% wt/v loading) in 1.0 mL of citrate buffer solution (50 mM, pH 4.8) was incubated in a water bath at 50 °C under gentle stirring. The reaction was initiated by adding 3.0 mg (or 20 U) of *Trichoderma reesei* cellulase and 1.0 mg (or 3811 U) of β -glucosidase. An aliquot of 50 μ L of the reaction mixture was periodically withdrawn and diluted with citrate buffer. The glucose concentration was determined by the glucose HK assay method at 340 nm using a Shimadzu UV-Mini-1240 spectrophotometer.²⁵ The xylose concentration was determined by the D-xylose assay kit spectrophotometrically at 340 nm.²⁶ All experiments were run in duplicate.

2.4 XRD and SEM characterization—XRD patterns for untreated and IL-pretreated Avicel celluloses were analyzed at 25 °C by a D8-Focus X-ray diffraction system (Bruker AXS GmbH) using CuK α radiation ($\lambda = 1.542 \text{ \AA}$) generated at 40 kV and 40 mA. Samples were scanned over the angular range $2\theta = 6\text{--}45^\circ$, with a step size of 0.02° and a step time of 0.5 s. The morphologies of the cellulosic materials, with or without IL pretreatment, were examined by scanning electron microscopy (S-4800, Hitachi, Ltd, Japan) at a 3-kV accelerating voltage.

2.5 Thermogravimetric analysis—Thermogravimetric analysis (TGA) was performed with a TA Instruments TGA Q50 or TGA Q500 under a nitrogen atmosphere (40 mL min^{-1}) using Pt pans and scanning from 20 to 600 °C at a heating rate of $10 \text{ }^\circ\text{C min}^{-1}$. The decomposition temperature T_{dep} denotes the thermal onset of decomposition, signifying the occurrence of a 10% total mass loss during TGA scanning. T_{der} is another measure of decomposition temperature, which is defined as the maximum in the first-derivative envelope of the TGA scan.

2.6 Cellulase adsorption isotherm—A known amount of cellulase was dissolved in 1.0 mL citrate buffer (pH 4.8, 50 mM) at 4 °C. The cellulose powder (20 mg) was added into the enzyme solution. The suspension solution was stirred continuously at 4 °C. After 30 min, the suspension solution was centrifuged to settle the insoluble cellulose. Thirty microliters (30 μ L) of the supernatant were added into a curvet containing 1.5 mL of Bradford reagent. After mixing the solution at room temperature for 10 min, the protein concentration was determined by its absorbance at 595 nm (blank was 30 μ L citrate buffer in 1.5 mL Bradford reagent). A protein calibration curve was generated from standard solutions of bovine serum albumin (BSA). The amount of adsorbed protein on cellulose was calculated from subtracting the remaining protein in solution after 30 min from the initial protein content.

3 Results and discussion

3.1 Screening of ILs for cellulose pretreatment and the hydrolysis rate model

In this work, we chose Avicel PH-101 as our model cellulose because it represents a well-studied microcrystalline cellulose (MCC). We tested a wide variety of ionic solvent systems for cellulosic pretreatment, including 20 different ILs and three cholinium-based deep

eutectic solvents (see Table S1 in *ESI*) in Avicel cellulose pretreatment; the ionic solvents employed were either neat (anhydrous) or diluted in water to 1.0 or 2.0 M concentrations. Among those ILs examined, ones containing the chloride, acetate, or dimethylphosphate anion (viz., entries **1**, **5**, **13**, and **16–20** in Table 1) appeared most adequate for dissolving appreciable amounts of cellulose (typically, 5–10 wt%). We further carried out enzymatic hydrolysis on native Avicel PH-101 or cellulose pretreated with the 23 different ionic solvent systems (neat and as 1.0 and 2.0 M solutions in water; 69 total solvent systems); typical hydrolysis kinetics profiles are illustrated in Fig. S1 (*ESI*) using the example of [BMIM][OAc]. As shown in Fig. S1, the hydrolysis of cellulose regenerated from neat [BMIM][OAc] was much faster than cellulose pretreated by aqueous [BMIM][OAc] solutions.

To quantitatively compare the hydrolysis rates, a simple Michaelis–Menten model was used to evaluate the hydrolysis reaction rate. Although cellulase is a cocktail consisting of several major enzymes (such as endoglucanase, exoglucanase and β -glucosidases), many studies have suggested that the Michaelis–Menten equation (competitive or noncompetitive inhibition)^{27–29} or its modifications (such as kinetics with competitive inhibition and Langmuir adsorption)^{30, 31} could describe the kinetics of enzymatic hydrolysis of cellulose. Therefore, this study adopts the Michaelis–Menten equation (Eq. 1) to curve-fit our hydrolysis data.

$$\frac{d[S]}{dt} = -\frac{V_{\max}[S]}{K_m + [S]} \quad (1)$$

Here, $[S]$ is the concentration of substrate (i.e. cellulose) which can be estimated from the initial cellulose concentration (20 g/L) and time-dependent glucose concentration (determined by the glucose HK assay periodically); $V_{\max}$ represents the maximum hydrolysis rate; K_m is the substrate concentration at which the reaction rate is half of $V_{\max}$; $V_{\max}/K_m$ represents the reaction rate constant at a low substrate concentration. The Runge-Kutta algorithm (see *ESI*) was used in the curve fitting analysis with the Microsoft Excel GRG Nonlinear method to obtain the $V_{\max}$ and K_m values for each hydrolysis reaction in 5 h. The $V_{\max}/K_m$ values are compiled in Table 1. The R^2 values are in the range of 0.927–0.998 and most of them fall between 0.97–0.99, which suggests the simple Michaelis–Menten equation correlates the hydrolysis data quite well. The results for the ionic solvents shown in Table 1 are divided into three distinct categories: (i) ILs based on the [BMIM]⁺ cation with different anions, (ii) ILs based on the acetate (OAc[−]) anion paired with different cations, and (iii) deep eutectic solvents (DESs). As a benchmark, untreated Avicel showed a $V_{\max}/K_m$ value of 0.10 g L^{−1} h^{−1}, and this forms the basis for comparing how IL various pretreatments influence cellulose hydrolysis.

3.2 Impact of IL properties on cellulose pretreatment

At first, we noticed that Avicel samples regenerated from cellulose-dissolving ILs (i.e., **1**, **5**, **13**, **16–20**) displayed much higher hydrolysis rates ($V_{\max}/K_m$ ranging from 0.21 to 0.46 g L^{−1} h^{−1}) than untreated cellulose (0.10 g L^{−1} h^{−1}). As has been explained in earlier studies, cellulose regenerated from an IL is more accessible to cellulase action due to the reduction in crystallinity, a transition from cellulose I to cellulose II structure, as well as other factors.^{10, 32–34} In this study, we are interested in learning how different anions and cations within neat ILs, as well as aqueous IL solutions, influence cellulose accessibility and hydrolysis. In order to facilitate a general discussion of trends in the anion's influence on cellulose hydrolysis rates, we summarize our results for a series of [BMIM]⁺ ILs in Fig. 1. Broadly, for each ionic solvent condition (i.e., neat, 1.0 M (aq), and 2.0 M (aq)) we can

categorize the ILs into three groups: (i) those achieving hydrolysis rates for treated Avicel much faster than that observed for untreated Avicel, (ii) those reaching only slightly faster rates, and (iii) those showing a similar hydrolysis rate as the untreated cellulose.

When neat ILs were used in the pretreatment of cellulose, those with the “cellulose-dissolving” anions OAc^- , Me_2PO_4^- and Cl^- gave the fastest reaction rates ($V_{\text{max}}/K_{\text{m}} = 0.21\text{--}0.46 \text{ g L}^{-1} \text{ h}^{-1}$). ILs containing NO_3^- , SCN^- , Tf_2N^- , MeSO_4^- and Br^- anions yielded only moderately improved rates ($V_{\text{max}}/K_{\text{m}} = 0.12\text{--}0.13 \text{ g L}^{-1} \text{ h}^{-1}$) while Avicel treated with ILs containing the remaining anions (dca^- , CF_3COO^- , BF_4^- , MeSO_3^- , PF_6^- and OTf^-) showed about the same hydrolysis rates as the untreated cellulose. The high hydrogen-bond basicity of certain anions (as designated by a high Kamlet–Taft β parameter) has been credited with breaking up key inter- and intra-molecular hydrogen-bonds within cellulose, leading to biomass dissolution in favorable ILs.^{24, 35, 36} As illustrated in Fig. 2, a correlation between the observed Avicel hydrolysis rates and the Kamlet–Taft β value exists for cellulose treated with neat ILs. In general, a higher hydrogen-bond basicity coincides with a higher hydrolysis rate, although exceptions such as OTf^- and Tf_2N^- are apparent. In addition, we established a weak correction between the hydrolysis rate and the polarity of neat ILs (see Fig. 3): a lower IL polarity correlates to a faster hydrolysis. A likely explanation is that favorable cellulose solvation and dissolution require balanced van der Waals forces and hydrophobic interactions,³⁷ which is only partially reflected in the empirical polarity determined by Reichardt’s dye. Conversely, as shown in Figs. S2 and S3, the Hofmeister ranking of anions (as characterized by viscosity B -coefficients) and the hydrophobicity of ILs (as quantified by log P values) have no direct correlation with the hydrolysis rate of cellulose pretreated by neat ILs.

Water is known as an “anti-solvent” in cellulose dissolution because the addition of water rapidly precipitates out cellulose initially dissolved in an IL. Aqueous solutions of ILs (such as our 1.0 and 2.0 M solutions studies here) cannot dissolve cellulose. Consequently, the pretreatment of cellulose by aqueous ILs is referred to as “suspension pretreatment”. As shown in Table 1, for a 2.0 M concentration, ILs comprising the anions MeSO_3^- , SCN^- , Tf_2N^- , BF_4^- , Br^- and OAc^- gave the fastest hydrolysis with $V_{\text{max}}/K_{\text{m}}$ ranging from 0.13 to 0.16 $\text{g L}^{-1} \text{ h}^{-1}$. ILs based on Cl^- , Me_2PO_4^- , MeSO_4^- and NO_3^- led to moderate rate increases ($V_{\text{max}}/K_{\text{m}} = 0.11\text{--}0.12 \text{ g L}^{-1} \text{ h}^{-1}$) whilst the remaining ILs (CF_3COO^- , dca^- , PF_6^- , HSO_4^- and OTf^-) actually showed about the same (or slightly lower) hydrolysis rate as untreated Avicel.

When these same ILs are employed at a lower concentration of 1.0 M, their relative impact on cellulose hydrolysis differs from the case of 2.0 M. At 1.0 M, ILs with Cl^- , MeSO_3^- , OAc^- , SCN^- , PF_6^- and Tf_2N^- anions resulted in the fastest reactions ($V_{\text{max}}/K_{\text{m}} = 0.13\text{--}0.15 \text{ g L}^{-1} \text{ h}^{-1}$), those containing MeSO_4^- , NO_3^- , BF_4^- , Me_2PO_4^- , dca^- and Br^- gave modestly improved rates ($V_{\text{max}}/K_{\text{m}} = 0.11\text{--}0.12 \text{ g L}^{-1} \text{ h}^{-1}$), and others (CF_3COO^- , HSO_4^- , and OTf^-) caused no appreciable changes to the reaction rate. In contrast to the use of neat ILs for pretreatment, aqueous ILs show strikingly different effects on the Avicel hydrolysis rate and no clear or direct correction between the hydrolysis rate and simple physicochemical properties could be established, including hydrogen-bond basicity (Fig. 2), polarity (Fig. 3), Hofmeister classification (Fig. S2), or hydrophobicity (Fig. S3).

As highlighted in Table 1, pretreatment by several aqueous IL solutions proved effective for improving the hydrolysis rate of cellulose. These solutions included [BMIM]Cl (1.0 M: $V_{\text{max}}/K_{\text{m}} = 0.15 \text{ g L}^{-1} \text{ h}^{-1}$), [BMIM][OAc] (1.0 M: $V_{\text{max}}/K_{\text{m}} = 0.14 \text{ g L}^{-1} \text{ h}^{-1}$), [BMIM][MeSO₃] (1.0 M: $V_{\text{max}}/K_{\text{m}} = 0.14 \text{ g L}^{-1} \text{ h}^{-1}$; 2.0 M: $V_{\text{max}}/K_{\text{m}} = 0.16 \text{ g L}^{-1} \text{ h}^{-1}$), and [BMIM][SCN] (1.0 and 2.0 M: $V_{\text{max}}/K_{\text{m}} = 0.14 \text{ g L}^{-1} \text{ h}^{-1}$). An earlier study by Brandt et al.²² suggested that 80% (v/v) aqueous solutions of [BMIM][HSO₄], [BMIM][MeSO₃], and

[BMIM][MeSO₄] were effective for the delignification and improved digestibility of cellulose. These authors also indicated that no correlation exists between the pretreatment effectiveness and the hydrogen-bond basicity of the ILs. In our hands, neat [BMIM][HSO₄] caused considerable cellulose degradation at 110 °C, resulting in little recovered cellulose. For this reason, the highest level of [BMIM][HSO₄] used was 4.0 M, as noted in Table 1. In either case, [BMIM][HSO₄] proved ineffective in generating a rapid cellulose hydrolysis.

It emerges from the entries in Table 1 and Fig. 1 that pretreatment by several IL systems actually causes a slight reduction ($V_{\max}/K_m$ below 0.10 g L⁻¹ h⁻¹) in cellulose hydrolysis. One probable reason is that residual ILs in IL-treated cellulose might lead to cellulase inactivation. As shown in Table S1, the calculated cellulose recovery may actually exceed 100%, especially among regenerated celluloses. This is an indication that IL residues likely become embedded within cellulose chains and resist efforts to wash it away. In an earlier study, we were able to both detect residual ILs after the complete hydrolysis of cellulose and to confirm that the presence of ILs inactivated cellulases.³³

The cationic structure of the IL may also moderate the pretreatment efficiency. As suggested by the entries of Table 1, the hydrolysis rate of cellulose pretreated by [HMIM][OAc] (**17**) is slower than those pretreated by [EMIM][OAc] (**16**) and [BMIM][OAc] (**5**). There are two likely reasons for this: (1) Firstly, a longer alkyl chain leads to a larger molar volume, effectively lowering the anion concentration, which in turn minimizes the disruptive capability of the anion.⁹ (2) In addition, the residual IL lingering in the recovered cellulose (see Table S1) may prompt dissimilar degrees of cellulase deactivation. Notably, the three ILs prepared from cations bearing ether functionality (**18**, **19**, **20**) are capable of dissolving cellulose and enabling its fast enzymatic hydrolysis ($V_{\max}/K_m = 0.25\text{--}0.40$ g L⁻¹ h⁻¹) (Table 1). These ether-containing ILs developed previously in our group^{9, 10, 38} have the advantages of relatively low viscosity and low cost, potentially high biodegradability, and minimal cellulase inactivation, the latter due in part to the low anion concentration.

Cousins to the conventional IL, deep eutectic solvents (DESs, frequently choline based) are extensions of and alternatives to ILs and deliver several attractive properties such as low cost, low toxicity, high biodegradability and high enzyme compatibility.³⁹ For this reason, we examined three DESs (**21**, **22**, **23**) and their aqueous solutions in the pretreatment of Avicel cellulose (Table 1). Encouragingly, we found that some DESs are as effective as aqueous ILs in pretreating cellulose and improving its subsequent hydrolysis. Further, in aqueous solutions of choline chloride (or acetate) mixed with glycerol, we measured $V_{\max}/K_m$ values of 0.14 and 0.13 g L⁻¹ h⁻¹ in 1.0 M solutions of **22** and **23**, respectively. Remarkably, we also witnessed that a 1.0 M solution outperforms a 2.0 M solution, the latter frequently giving no advantage over untreated Avicel. Overall, these results suggest a largely untapped potential for aqueous DESs in the pretreatment of cellulose.

3.3 Cellulose structural characterization by XRD, SEM, TGA and adsorption isotherm

To better elucidate how ionic solvents perturb the cellulosic structure, we performed X-ray diffraction (XRD), scanning electron microscopy (SEM), and thermogravimetric analysis (TGA) analysis on untreated Avicel alongside several representative treated samples. As shown in Fig. 4a, XRD studies indicate that cellulose regenerated from [BMIM][OAc] has a much lower crystallinity (35%) than untreated Avicel (79%). In contrast, cellulose samples pretreated by aqueous [BMIM][OAc] (1.0 and 2.0 M) exhibit no such reduction in crystallinity. The changes in cellulose crystallinity correlate nicely with the enzymatic hydrolysis rate of cellulose (Table 1). Earlier studies^{10, 40} showed that cellulosic regeneration from an IL is often accompanied by a change in structure from cellulose I to cellulose II. Representative SEM images further corroborate that the morphology of untreated cellulose (Fig 5a) is more heterogeneous consisting of large particles, while the

regenerated cellulose (Fig 5b) appears to be more homogeneous and uniform; celluloses treated by aqueous [BMIM][OAc] (1.0 and 2.0 M) (Fig. 5c, d) seem to be in-between the heterogeneous and homogeneous morphologies. In the case of [BMIM][MeSO₃], however, Avicel cellulose pretreatment gave no reduction in crystallinity (Fig. 4b) for either neat IL or aqueous ILs. From these results, it should be clear that the cellulose structural changes and accessibility to cellulase cannot be solely predicted from the XRD crystallinity index.

The alteration in cellulose structure caused by pretreatment can also be reflected in the thermal stability of the resultant cellulose. Toward this, we conducted TGA experiments on cellulose samples prior to and following various pretreatment strategies. Two representative stability parameters are given in Table 2: (i) the decomposition temperature (T_{dcp}) denotes the thermal onset of decomposition at a 10% total mass loss; and (ii) T_{der} is the maximum displayed in the first-derivative of the TGA scan. We note that although T_{dcp} is most seen in the recent literature, we provide both indices for completeness. Untreated cellulose displays a fairly high T_{dcp} of 323 °C. Typically, cellulose pretreatment results in structural changes which reduce T_{dcp} .¹⁰ Thus, to an extent, the T_{dcp} value reflects the severity of structural changes occurring as a result of pretreatment. As indicated in Table 2, regenerated cellulose from [BMIM][OAc] has a much lower T_{dcp} (222 °C) than cellulose pretreated by aqueous [BMIM][OAc] solution (~300 °C). This accords with our earlier XRD and SEM results, as well as the observed hydrolysis rates. Namely, the process of dissolving cellulose in neat [BMIM][OAc] significantly modifies the cellulose crystallinity and makes the cellulose more susceptible to hydrolysis whereas aqueous [BMIM][OAc] has minimal impact on the cellulose structure. However, this analysis appears less applicable in the case of [BMIM][MeSO₃] pretreatment. Specifically, cellulose pretreated by neat [BMIM][MeSO₃] shows a significant reduction in thermal stability (T_{dcp} = 281 °C), however, $V_{\text{max}}/K_{\text{m}}$ is only 0.093 g L⁻¹ h⁻¹ in this case. Contrariwise, cellulose samples treated by aqueous [BMIM][MeSO₃] show essentially an identical T_{dcp} as untreated Avicel (Table 2 and Fig. S5). However, cellulose hydrolysis kinetics analysis clearly reveals a favorable boost upon pretreatment with aqueous [BMIM][MeSO₃] (1.0 M: $V_{\text{max}}/K_{\text{m}}$ = 0.14 g L⁻¹ h⁻¹; 2.0 M: $V_{\text{max}}/K_{\text{m}}$ = 0.16 g L⁻¹ h⁻¹). From this, we can conclude that XRD and TGA studies may not be able to reveal some subtle but important structural changes that occur during cellulose pretreatment with ILs and their aqueous solutions.

To probe such subtle structural changes, we carried out the cellulase adsorption isotherm of Avicel celluloses pretreated by various ionic solutions (Figs 6 and S7). The adsorption experiments were carried out at 4 °C to minimize the enzymatic hydrolysis of cellulose. The adsorption isotherm measures the cellulase-binding capability of cellulose, which further implies the porousness and accessibility of cellulose. As shown in Fig 6, celluloses pretreated by aqueous [BMIM][MeSO₃] (1.0 and 2.0 M) exhibit a higher enzyme-adsorption capacity than that treated by neat [BMIM][MeSO₃], suggesting the aqueous IL-pretreatment leads to a higher accessible surface area and more binding sites for cellulase. This explains the higher hydrolysis rates of celluloses pretreated by aqueous [BMIM][MeSO₃] than that by neat IL (Table 1). Fig 7S indicates no significant adsorption differences among cellulose samples pretreated by neat or aqueous choline chloride/glycerol (1:2). Although the exact mechanism of how aqueous ILs interact with cellulose chains is not clear, it is helpful to offer some insightful discussions. When neat or aqueous ILs are not capable of dissolving cellulose, these solvent molecules may not considerably disrupt the hydrogen-bonding network to make noticeable structure changes as detected by XRD and TGA. However, in aqueous ILs, hydrated ions may have better penetration/diffusion power than (non-cellulose dissolving) neat IL molecules to weakly disrupt the hydrogen-bonds, enable subtle morphology changes, and increase the cellulose accessibility and digestibility.

3.4 IL pretreatment of switchgrass

Switchgrass (*Panicum virgatum* L.) is known to be a viable source of lignocellulose for bioethanol production.⁴¹ Given its relevance to bioenergy, we initiated studies pretreating switchgrass with [BMIM][OAc], [BMIM][MeSO₃], and their aqueous solutions (Figs 7 and 8). As shown in Fig. 7 and Fig. 8, pretreatment by both neat [BMIM][OAc] (which partially dissolves the grass) and [BMIM][MeSO₃] significantly sped up the enzymatic hydrolysis of cellulose. In addition, pretreatment with neat [BMIM][OAc] improved the hydrolysis of hemicellulose. Aqueous [BMIM][OAc] solutions proved to be much less effective for pretreating switchgrass and gave low hydrolysis rates for both cellulose and hemicellulose. XRD patterns (Fig. 9a) confirm a substantially reduced crystallinity (23%) for switchgrass regenerated from neat [BMIM][OAc] (cf. 41% for untreated grass), and a lower, but still substantial, reduction in crystallinity following aqueous [BMIM][OAc] treatment (1.0 M: 27%; 2.0 M: 30%). The associated SEM images shown in Fig. 10 indicate that switchgrass samples pretreated by aqueous [BMIM][OAc] retain a heterogeneous morphology similar to the untreated grass, while the grass regenerated from neat [BMIM][OAc] appears to be more homogeneous.

Alternatively, aqueous [BMIM][MeSO₃] solutions proved surprisingly effective as pretreatment agents to produce high hydrolysis rates for both cellulose and hemicellulose. These observations are in agree with our above results demonstrating that aqueous [BMIM][MeSO₃] is a promising treatment medium for processing Avicel cellulose. However, as revealed in Fig. 9b, there is no perceptible reduction in crystallinity observed for switchgrass samples pretreated by either neat [BMIM][MeSO₃] or aqueous [BMIM][MeSO₃]. This observation supports the notion that, in spite of no evident change in crystallinity, certain pretreatments can lead to subtle changes that markedly impact the cellulose accessibility and digestibility.

4 Conclusions

In this research, we have systematically studied the hydrolysis rates of cellulose and switchgrass pretreated by neat ILs, DESs, and their aqueous solutions. The hydrolysis rate of cellulose treated by neat ILs can be correlated with the H-bond basicity of the constituent anions and the empirical IL polarity, however, the hydrolysis rates of cellulose pretreated by aqueous ILs cannot be simply related to any single property of ILs (e.g., H-bond basicity, polarity, Hofmeister ranking, hydrophobicity). We further examined the structural changes of cellulosic biomass upon pretreatment by IL solutions using XRD, SEM, TGA and adsorption isotherm characterizations. In the case of [BMIM][OAc], the hydrolysis rates for Avicel and switchgrass correspond to observable structural changes: particularly, a reduction in crystallinity, a homogeneous morphology, and a reduced thermal stability. However, in the case of [BMIM][MeSO₃], the hydrolysis rates of (ligno)cellulose can be related to neither the crystallinity nor the thermal stability of the cellulose; but a higher cellulase-adsorption trend was observed for celluloses pretreated by aqueous IL solutions than that by neat IL. Clearly, multifaceted or elusive structural changes must be implicated in this case. From this work, aqueous solutions of several ILs and DESs emerge as effective pretreatment agents for cellulose, including [BMIM][MeSO₃] (**7**), [CH₃(OCH₂CH₂)₃-Et-Pip][OAc] (**20**), [BMIM][OAc] (**5**), [EMIM][OAc] (**16**), [BMIM]Cl (**1**), [BMIM][SCN] (**9**), as well as choline chloride/glycerol (1:2) (**22**). In short, aqueous ILs and aqueous DESs represent promising and inexpensive alternative solvent systems for pretreating lignocellulose to attain rapid saccharification rates of both cellulose and hemicellulose. In this regard, we anticipate that our present results will embolden much-needed consideration and activity in this underexplored area.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The authors declare no potential sources of conflict of interest. HZ acknowledges supports by the Henry Dreyfus Teacher-Scholar Award, NIH MBRS-RISE grant (1R25GM096956), and NIH NIBIB contract award (HHSN268201200011C).

References

1. Mora-Pale M, Meli L, Doherty TV, Linhardt RJ, Dordick JS. *Biotechnol. Bioeng.* 2011; 108:1229–1245. [PubMed: 21337342]
2. Stark A. *Energy Environ. Sci.* 2011; 4:19–32.
3. Vancov T, Alston A-S, Brown T, McIntosh S. *Renewable Energy.* 2012; 45:1–6.
4. Tadesse H, Luque R. *Energy Environ. Sci.* 2011; 4:3913–3929.
5. Wang H, Gurau G, Rogers RD. *Chem. Soc. Rev.* 2012; 41:1519–1537. [PubMed: 22266483]
6. Lee SH, Doherty TV, Linhardt RJ, Dordick JS. *Biotechnol. Bioeng.* 2009; 102:1368–1376. [PubMed: 19090482]
7. Mukesh C, Mondal D, Sharma M, Prasad K. *Chem. Commun.* 2013; 49:6849–6851.
8. Mondal D, Sharma M, Mukesh C, Gupta V, Prasad K. *Chem. Commun.* 2013; 49:9606–9608.
9. Zhao H, Baker GA, Song Z, Olubajo O, Crittle T, Peters D. *Green Chem.* 2008; 10:696–705.
10. Tang S, Baker GA, Ravula S, Jones JE, Zhao H. *Green Chem.* 2012; 14:2922–2932.
11. Muhammad N, Man Z, Bustam MA, Abdul Mutalib MI, Wilfred CD, Rafiq S. *Appl. Biochem. Biotechnol.* 2011; 165:998–1009. [PubMed: 21720837]
12. Ohira K, Abe Y, Kawatsura M, Suzuki K, Mizuno M, Amano Y, Itoh T. *ChemSusChem.* 2012; 5:388–391. [PubMed: 22259151]
13. King AWT, Asikkala J, Mutikainen I, Järvi P, Kilpeläinen I. *Angew. Chem. Int. Ed.* 2011; 50:6301–6305.
14. Zhang Q, Oztekin NS, Barrault J, De Oliveira Vigier K, Jérôme F. *ChemSusChem.* 2013; 6:593–596. [PubMed: 23505138]
15. Zhang Q, Benoit M, De Oliveira Vigier K, Barrault J, Jérôme F. *Chem. – Eur. J.* 2012; 18:1043–1046. [PubMed: 22190146]
16. Rinaldi R. *Chem. Commun.* 2011; 47:511–513.
17. Francisco M, van den Bruinhorst A, Kroon MC. *Green Chem.* 2012; 14:2153–2157.
18. Gericke M, Liebert T, El Seoud OA, Heinze T. *Macromol. Mater. Eng.* 2011; 296:483–493.
19. Tian X, Fang Z, Jiang D, Sun X. *Biotechnol. Biofuels.* 2011; 4:53. [PubMed: 22099703]
20. Fu D, Mazza G. *Biores. Technol.* 2011; 102:7008–7011.
21. Fu D, Mazza G. *Biores. Technol.* 2011; 102:8003–8010.
22. Brandt A, Ray MJ, To TQ, Leak DJ, Murphy RJ, Welton T. *Green Chem.* 2011; 13:2489–2499.
23. Zhang Z, O'Hara IM, Doherty WOS. *Bioresour. Technol.* 2012; 120:149–156. [PubMed: 22789826]
24. Ohno H, Fukaya Y. *Chem. Lett.* 2009; 38:2–7.
25. Bondar RJL, Mead DC. *Clin. Chem.* 1974; 20:586–590. [PubMed: 4363766]
26. Zhao H, Baker GA, Cowins JV. *Biotechnol. Prog.* 2010; 26:127–133. [PubMed: 19918908]
27. Dwivedi CP, Ghose TK. *J. Ferment. Technol.* 1979; 57:15–24.
28. Caminal G, López-Santín J, Solá C. *Biotechnol. Bioeng.* 1985; 27:1282–1290. [PubMed: 18553816]
29. Ghose, TK.; Das, K. in *Advances in Biochemical Engineering I*. Ghose, TK.; Fiechter, A., editors. Springer-Verlag; New York: 1971. p. 55–76.
30. Huang AA. *Biotechnol. Bioeng.* 1975; 17:1421–1433. [PubMed: 1182273]

31. Fan LT, Lee YH. *Biotechnol. Bioeng.* 1983; 25:2707–2733. [PubMed: 18548602]
32. Dadi AP, Varanasi S, Schall CA. *Biotechnol. Bioeng.* 2006; 95:904–910. [PubMed: 16917949]
33. Zhao H, Jones CL, Baker GA, Xia S, Song Z, Olubajo O, Person VN. *J. Biotechnol.* 2009; 139:47–54. [PubMed: 18822323]
34. Singh S, Simmons BA, Vogel KP. *Biotechnol. Bioeng.* 2009; 104:68–75. [PubMed: 19489027]
35. Fukaya Y, Hayashi K, Wada M, Ohno H. *Green Chem.* 2008; 10:44–46.
36. Doherty TV, Mora-Pale M, Foley SE, Linhardt RJ, Dordick JS. *Green Chem.* 2010; 12:1967–1975.
37. Novoselov NP, Sashina ES, Petrenko VE, Zaborsky M. *Fibre Chem.* 2007; 39:153–158.
38. Tang S, Baker GA, Zhao H. *Chem. Soc. Rev.* 2012; 41:4030–4066. [PubMed: 22456483]
39. Zhao H, Baker GA. *J. Chem. Tech. Biotechnol.* 2013; 88:3–12.
40. Samayam IP, Hanson BL, Langan P, Schall CA. *Biomacromolecules.* 2011; 12:3091–3098. [PubMed: 21740062]
41. Keshwania DR, Cheng JJ. *Bioresour. Technol.* 2009; 100:1515–1523. [PubMed: 18976902]
42. Fukaya Y, Sugimoto A, Ohno H. *Biomacromolecules.* 2006; 7:3295–3297. [PubMed: 17154453]
43. Oehlke A, Hofmann K, Spange S. *New J. Chem.* 2006; 30:533–536.
44. Crowhurst L, Mawdsley PR, Perez-Arlandis JM, Salter PA, Welton T. *Phys. Chem. Chem. Phys.* 2003; 5:2790–2794.
45. Kaar JL, Jesionowski AM, Berberich JA, Moulton R, Russell AJ. *J. Am. Chem. Soc.* 2003; 125:4125–4131. [PubMed: 12670234]
46. Huddleston, JG.; Broker, GA.; Willauer, HD.; Rogers, RD. in *Ionic Liquids: Industrial Applications to Green Chemistry*. American Chemical Society. Rogers, RD.; Seddon, KR., editors. Washington, D. C.: 2002. p. 270-288.
47. Muldoon MJ, Gordon GM, Dunkin IR. *J. Chem. Soc., Perkin Trans. 2*; 2001:433–435.

Pure IL: **2.0 M IL:** **1.0 M IL:** **Fig. 1.**

Summary of anion effect on the hydrolysis rates of Avicel PH-101 pretreated by [BMIM]⁺ type ILs ($V_{\max}/K_m$ in the unit of $\text{g L}^{-1} \text{h}^{-1}$).

Fig. 2.

Effect of hydrogen-bond basicities of [BMIM]⁺-based ILs on $V_{\max}/K_m$ ($\text{g L}^{-1} \text{h}^{-1}$) of Avicel PH-101. [Data references for IL Kamlet–Taft β -values: OAc^- ²⁴, Cl^- ⁴², MeSO_4^- and SCN^- ⁴³, OTf^- , BF_4^- , Tf_2N^- , and PF_6^- ⁴⁴].

Fig. 3. Effect of polarity of [BMIM]⁺-based ILs on $V_{\max}/K_m$ ($\text{g L}^{-1} \text{h}^{-1}$) of Avicel PH-101. [Data references for E_T^N polarity values: OAc⁻, CF₃COO⁻, and NO₃⁻⁴⁵, Cl⁻⁴⁶, and Tf₂N⁻, PF₆⁻, OTf⁻, and BF₄⁻⁴⁷].

Fig. 4. XRD patterns for untreated Avicel PH-101 cellulose and Avicel pretreated by (a) [BMIM][OAc] or (b) [BMIM][MeSO₃]. Cellulose regenerated from neat [BMIM][OAc] was first fully dissolved and incubated at 110 °C for 4 h. Other samples were pretreated by suspension in neat [BMIM][MeSO₃] or aqueous solutions of IL at 110 °C for 4 h.

Fig. 5. SEM images illustrating the morphology of (a) untreated Avicel cellulose, (b) Avicel regenerated from [BMIM][OAc], (c) Avicel pretreated by 2.0 M [BMIM][OAc], and (d) Avicel pretreated by 1.0 M [BMIM][OAc].

Fig. 6. *T. reesei* cellulase adsorption isotherm (4 °C) of Avicel PH-101 pretreated by neat or aqueous [BMIM][MeSO₃].

Fig. 7.

Enzymatic hydrolysis of switchgrass pretreated by [BMIM][OAc]. (Conditions: 1.0 mL of citrate buffer (pH 4.8, 50 mM), 0.02 g of untreated or pretreated switchgrass (regenerated from [BMIM][OAc] or pretreated by aqueous [BMIM][OAc]), 3.0 mg of *Trichoderma reesei* cellulase and 1.0 mg of β -glucosidase under gentle agitation at 50 °C).

Fig. 8. Enzymatic hydrolysis of switchgrass pretreated by [BMIM][MeSO₃]. (Conditions: 1.0 mL of citrate buffer (pH 4.8, 50 mM), 0.02 g of switchgrass (untreated or pretreated by [BMIM][MeSO₃]), 3.0 mg of *Trichoderma reesei* cellulase, and 1.0 of mg β -glucosidase under gentle agitation at 50 °C).

Fig. 6. XRD patterns for untreated switchgrass and switchgrass pretreated by (a) [BMIM][OAc] and (b) [BMIM][MeSO₃]. *Note:* pure [BMIM][OAc] was used to partially dissolve and incubate the switchgrass at 110 °C for 4 h; in the other cases, samples were pretreated by suspension in solution at 110 °C for 4 h.

Fig. 10. SEM images illustrating the morphology of (a) untreated switchgrass, (b) switchgrass regenerated from [BMIM][OAc], (c) switchgrass pretreated by 2.0 M [BMIM][OAc], and (d) switchgrass pretreated by 1.0 M [BMIM][OAc].

Table 1Effect of pretreatment by ionic solvents on the hydrolysis rate of cellulose ^a

Ionic solvent		$V_{\max}/K_m$ (g L ⁻¹ h ⁻¹) and (R^2) ^b		
		Pure	2.0 M	1.0 M
None (untreated)		0.10 (0.984)		
Different anions				
1	[BMIM]Cl	0.22 ^c (0.972)	0.12 ^d (0.990)	0.15 (0.980)
2	[BMIM]Br	0.12 (0.989)	0.13 (0.991)	0.11 (0.993)
3	[BMIM][BF ₄]	0.11 (0.985)	0.13 (0.996)	0.12 (0.992)
4	[BMIM][CF ₃ COO]	0.11 (0.998)	0.10 (0.991)	0.10 (0.991)
5	[BMIM][OAc]	0.46 (0.980)	0.13 (0.976)	0.14 (0.971)
6	[BMIM][OTf]	0.065 (0.991)	0.078 (0.994)	0.083 (0.975)
7	[BMIM][MeSO ₃]	0.093 (0.988)	0.16 (0.985)	0.14 (0.985)
8	[BMIM][HSO ₄]	0.036 (0.978) (4.0 M)	0.081 (0.968)	0.090 (0.975)
9	[BMIM][SCN]	0.13 (0.980)	0.14 (0.996)	0.14 (0.989)
10	[BMIM][dca]	0.11 (0.989)	0.10 (0.987)	0.11 (0.995)
11	[BMIM][NO ₃]	0.13 (0.988)	0.11 (0.988)	0.12 (0.984)
12	[BMIM][MeSO ₄]	0.12 (0.995)	0.11 (0.994)	0.12 (0.993)
13	[BMIM][Me ₂ PO ₄]	0.42 (0.990)	0.12 (0.987)	0.12 (0.966)
14	[BMIM][PF ₆]	0.088 (0.977)	0.10 (0.976)	0.13 (0.989)
15	[BMIM][Tf ₂ N]	0.13 (0.983)	0.13 (0.960)	0.13 (0.982)
Different cations				
16	[EMIM][OAc]	0.44 (0.927)	0.14 (0.970)	0.12 (0.992)
5	[BMIM][OAc]	0.46 (0.980)	0.13 (0.976)	0.14 (0.971)
17	[HMIM][OAc]	0.21 (0.974)	0.13 (0.984)	0.13 (0.992)
18	[CH ₃ (OCH ₂ CH ₂) ₃ -Et-Im][OAc]	0.25 (0.995)	0.10 (0.981)	0.12 (0.990)
19	[CH ₃ (OCH ₂ CH ₂) ₂ -Et ₃ N][OAc]	0.34 (0.955)	0.13 (0.998)	0.13 (0.991)
20	[CH ₃ (OCH ₂ CH ₂) ₃ -Et-Pip][OAc]	0.40 (0.960)	0.10 (0.960)	0.15 (0.985)
Deep eutectic solvents (DES)				
21	Choline chloride/urea (1:2)	0.085 (0.998)	0.10 (0.988)	0.10 (0.967)
22	Choline chloride/glycerol (1:2)	0.13 (0.950)	0.11 (0.986)	0.14 (0.997)
23	Choline acetate/glycerol (1:1.5)	0.10 (0.982)	0.11 (0.987)	0.13 (0.970)

^aHydrolysis conditions: 1.0 mL citrate buffer (pH 4.8, 50 mM), 0.02 g untreated or pretreated Avicel PH-101, 3.0 mg *Trichoderma reesei* cellulase and 1.0 mg β-glucosidase under gentle agitation at 50 °C;

^bcalculated from hydrolysis data using the Michaelis–Menten equation (the number in parenthesis represents R^2);

^cUnderlined data indicate *regeneration pretreatment* and others are *suspension pretreatments*; bold $V_{\max}/K_m$ values indicate significantly high hydrolysis rates;

^d cellulose was partially dissolved in neat IL.

Table 2Thermogravimetric results of cellulosic samples ^a

Sample pretreatment	Early mass loss ^b	$T_{\text{der}}/^{\circ}\text{C}^c$	$T_{\text{dcp}}/^{\circ}\text{C}^d$	Transition shape ^e	Residual char ^f
Avicel, untreated	5.6%	345	323	S	1.1%
Avicel, neat [BMIM][OAc]	4.8%	280	222	M	24.8%
Avicel, 2.0 M [BMIM][OAc]	4.7%	370	300	S	8.7%
Avicel, 1.0 M [BMIM][OAc]	4.3%	370	301	S	3.0%
Avicel, neat [BMIM][MeSO ₃]	4.7%	323	281	S	6.9%
Avicel, 2.0 M [BMIM][MeSO ₃]	4.1%	355	325	S	6.6%
Avicel, 1.0 M [BMIM][MeSO ₃]	4.9%	351	323	S	4.6%
Switchgrass, untreated	5.2%	332	250	B	22.0%
Switchgrass, neat [BMIM][OAc]	10.9%	294	232	B	15.4%
Switchgrass, 2.0 M [BMIM][OAc]	8.0%	351	250	B	5.3%
Switchgrass, 1.0 M [BMIM][OAc]	3.6%	346	248	B	17.3% ^g

^aTGA scans were measured on a TA Instruments TGA Q50 under a nitrogen atmosphere using Pt pans with a heating rate of 10 °C min⁻¹. See footer graphic for a diagram illustrating the measurement of the various transitions and mass loss steps tabulated; * and † indicate the early mass loss step and the position for determination of residual char, respectively.

^bThe early mass loss at temperatures below 100 °C is attributed primarily to buoyancy effects and, for this reason, is disregarded in the estimation of T_{dcp} .

^c T_{der} is determined from the maximum in the first-derivative envelope of the TGA scan.

^d T_{dcp} is the decomposition temperature measured at the onset of decomposition (i.e., 10% mass loss following the initial plateau beyond the early mass loss).

^eThe main mass loss behavior is characterized on the basis of whether it occurs as a single, discrete step (S) or exhibits multi-step (M) thermal decomposition. (B) indicates a derivative thermogram which essentially occurs as a single step but with a slightly bimodal appearance, such as a pronounced shoulder.

^fThe amount of carbonaceous char is determined from the mass remaining at 600 °C; uncertainties are estimated to be on the order of ± 1 –2%.

^gIn contrast to the other samples, the residual char observed for this particular sample showed a large variability.