Published in final edited form as:

Hyperfine Interact. 2014 April 1; 226(1-3): 797–801. doi:10.1007/s10751-014-1065-0.

Mössbauer spectroscopy of europium-containing glasses: Optical activator study for x-ray image plates

C.E. Johnson,

University of Tennessee Space Institute, Tullahoma, TN 37388, USA

M. Vu,

University of Tennessee Space Institute, Tullahoma, TN 37388, USA

J.A. Johnson,

University of Tennessee Space Institute, Tullahoma, TN 37388, USA

D.E. Brown,

Northern Illinois University, DeKalb, IL 60115, USA

J.K.R. Weber,

Materials Development Inc., Arlington Heights, IL 60004, USA

C. Paßlick, and

Centre for Innovation Competence SiLi-nano, Martin Luther University of Halle-Wittenberg, Karl-Freiherr-von-Fritsch-Str. 3, 06120 Halle (Saale), Germany

S. Schweizer

Centre for Innovation Competence SiLi-nano, Martin Luther University of Halle-Wittenberg, Karl-Freiherr-von-Fritsch-Str. 3, 06120 Halle (Saale), Germany, and Fraunhofer Center for Silicon Photovoltaics, Walter-Hülse-Str. 1, 06120 Halle (Saale), Germany

Abstract

A fluorozirconate glass (ZBLAN) containing BaCl₂ nanocrystals doped with divalent Eu is a promising material for x-ray image plates for medical diagnosis. Since it is known that Eu²⁺ readily oxidizes to Eu³⁺, which reduces fluorescence efficiency of the image plates, ¹⁵¹Eu Mössbauer spectroscopy was used in this work to monitor the Eu oxidation state of the samples during degradation over time in the presence of ambient humidity. In addition, Mössbauer spectroscopic experiments show that the oxidation state has already changed during the glass melt: The sample made from 5 mol% EuCl₂ contained 78% EuCl₂ + 22% EuCl₃ deduced from the relative areas of the absorption lines. The sample made from 2.5 mol% EuCl₂ + 2.5 mol% EuCl₃ contained 37% EuCl₂ + 63% EuCl₃, i.e. 26% of the original EuCl₂ was oxidized to EuCl₃.

1 Introduction

Fluorochlorozirconate (FCZ) glass ceramics are being developed to detect x-rays for biomedical imaging. The materials are based on a standard ZBLAN formulation. ZBLAN (zirconium, barium, lanthanum, aluminum, and sodium) is a fluoride glass in its original form. These glasses however, under investigation for mammography image plates, are additionally doped with chlorine ions by total substitution of barium chloride for barium

fluoride and the addition of europium (II) chloride as an optical activator. Upon appropriate thermal annealing, barium chloride nanocrystals precipitate within the glass and take up the divalent europium. Upon x-ray irradiation, electron-hole pairs are created, which are stable until stimulated by a laser, at which time the electron-hole pairs recombine followed by a luminescence signal. This luminescence produces the image. It is critical to mammography image plates that the europium remains in the 2+ state inside the barium chloride nanocrystals. However, photoluminescence and x-ray excited luminescence measurements [1] have shown that there is always a significant amount of Eu^{3+} in the glass, which reduces the performance of the material as an image plate. Some of the trivalent europium comes from the source material, some from oxidation after removal from the inert atmosphere where the material is stored and some from redox reactions within the glass melt.

Ball et al. [2] showed that EuCl_2 can be produced by heating EuCl_3 above 300 °C in a vacuum. The reaction proceeds according to the equation $\text{EuCl}_3 \leftrightarrow \text{EuCl}_2 + \frac{1}{2}\text{Cl}_2$. The goal of this work is to investigate the oxidation of Eu^{2+} to Eu^{3+} in the raw material as a function of time using Mössbauer spectroscopy and also to investigate the redox reaction in the glass melt by the same technique. Deeper understandings of this issue will feedback to an improved synthesis of the modified ZBLAN glass plates. Previous Mössbauer studies of Eu-doped FCZ glass ceramics have been reported by Newman *et al* [3].

2 Experimental

The two modified ZBLAN glasses measured consist of $51\text{ZrF}_4\text{-}17\text{BaCl}_2\text{-}20\text{NaF}\text{-}3.5\text{LaF}_3\text{-}3\text{AlF}_3\text{-}0.5\text{InF}_3\text{-}X$ ($X = 5 \text{ mol\% EuCl}_2$ or $2.5 \text{ mol\% EuCl}_2$ plus $2.5 \text{ mol\% EuCl}_3$). They were made by heating the constituent chemicals in a platinum crucible in a furnace at 750 °C inside a glove box with an argon atmosphere. Then they were poured into a 200 °C hot brass mold and slowly cooled down to room temperature linearly over 4 hours. During these preparation steps oxygen and water vapor were continuously monitored and found to be < 0.1 ppm; this prevents oxidation of the melt. Plates of dimensions 5 mm × 5 mm were cut and ground to 0.2 mm thickness.

Mössbauer measurements were made on samples at room temperature using a spectrometer manufactured by SEE Co, Edina, Mn, USA. The ^{151}Eu Mössbauer spectra were measured using a $^{151}\text{SmF}_3$ source, which was accelerated through a $\pm 30 \text{ mm/s}$ range of velocities using a linear motor. The transmitted 21.7 keV γ -rays were detected with a Kr-filled proportional counter. The resulting spectra were fitted with a Mössbauer fitting program for the ^{151}Eu resonance.

3 Results and discussion

For the investigation of the raw materials, 99.9% cation purity EuCl_3 obtained from Aldridge Chemical Company was heated at 700 °C for 1 hour and the resulting spectrum is shown in Figure 1 (a). Initially, EuCl_2 is formed but is unstable; the subsequent decay, as a function of time after heating, is shown in Figures 1 (b) to (f). The spectra show the variation in Eu^{2+} and Eu^{3+} contributions. Analysis of the area under the Eu^{2+} and Eu^{3+} absorption curves yield that the amount of Eu^{2+} decreases and Eu^{3+} increases with time. The resulting product is identified as Eu_2O_3 from its isomer shift (see later). The Eu^{2+}

degradation can be described by $2\text{EuCl}_2 + 2\text{H}_2\text{O} + \frac{1}{2}\text{O}_2 \rightarrow \text{Eu}_2\text{O}_3 + 4\text{HCl}$. Figure 2 shows a fitted exponential decay curve; the Eu^{2+} has a half life of approximately 7 days.

The two glass samples were made with 5 mol% europium doping in order to provide sufficient Mössbauer signal to obtain spectra over a reasonable time scale. One sample was made with 5 mol% EuCl_2 , the other with 2.5 mol% EuCl_2 and 2.5 mol% EuCl_3 . The Mössbauer spectra are shown in Figures 3 (a) and (b). The absorption is small and difficult to observe, partly because of the small amount of europium and partly because the 21.7 keV γ -rays are strongly absorbed by the more abundant zirconium which has an L x-ray edge close by, thereby reducing the signal/noise ratio. The Eu^{2+} line is especially difficult to observe as it is broad (FWHM = 7.7 mm/s). Coey *et al.* [4] have observed such broadening in fluoride glasses and attributed it to a spread in isomer shifts due to the different Eu-F environments in a glass. It is more likely to be caused by slow electron spin relaxation rates which arise from the weak interactions between the paramagnetic Eu^{2+} ions due to their low concentration; such broadening has been observed in Eu^{2+} diluted (2 mol%) in CaF_2 [5]. This reduces the depth of the absorption relative to that of the narrower Eu^{3+} line (FWHM = 2.6 mm/s), and combined with the low Debye temperature adds to the difficulty of observing the spectrum at room temperature. The Mössbauer spectrum (Figure 3(a)) of the sample made from 5 mol% EuCl_2 showed that it also contained some EuCl_3 , the relative areas of the lines $\text{Eu}^{2+}:\text{Eu}^{3+}$ being 78:22. This supports conclusions from photoluminescence and x-ray excited luminescence. Similar results were found by Coey *et al.* [4] in Mössbauer spectra of $\text{ZrF}_4\text{-BaF}_2\text{-ThF}_4$ glasses. They made measurements at low temperatures and deduced the Debye temperatures of the two valence states to be 145 K (Eu^{2+}) and 261 K (Eu^{3+}). Using Coey's data the relative amount of Eu^{2+} to Eu^{3+} 92:8, i.e. the glass contained 4.6% Eu^{2+} and 0.4% Eu^{3+} .

In the sample made from 2.5 mol% EuCl_2 and 2.5 mol% EuCl_3 the areas of the spectra showed an Eu^{2+} to Eu^{3+} ratio of 37:63. Correcting for the different Debye-Waller factors the glass contained 3.25% Eu^{2+} and 1.75% Eu^{3+} , i.e. 30% of the original EuCl_3 was reduced to EuCl_2 .

The shift of the Eu^{3+} was close to 0 mm/s, so that unlike the result of heating EuCl_3 followed by oxidation in air (Figure 1(f)) the Eu^{2+} has oxidized to EuCl_3 . Presumably the oxygen and water vapor in the air does not penetrate the plates, whereas it can react extensively with powdered samples (Figure 2).

4 Conclusion

EuCl_2 in the raw oxidizes to Eu_2O_3 whereas EuCl_2 in the glass oxidizes to EuCl_3 . This is because there is a chlorine source in the glass. The interior of the plate is protected by the outer surface and inward diffusion of oxygen and moisture is slow. With a diffusion coefficient of 10^{-16} cm²/s at 25 °C for moisture/oxygen in the glass, internal oxidation would proceed at a rate of approximately 10 $\mu\text{m}/\text{year}$.

Acknowledgments

This publication was supported by Grant Number 1R01EB006145-01A2 from the National Institutes of Health to The University of Tennessee Space Institute. Its contents are solely the responsibility of the authors and do not necessarily represent the official views of the National Institutes of Health or the University of Tennessee, Space Institute. C. Paßlick and S. Schweizer would like to thank the German Federal Ministry for Education and Research (BMBF) for the financial support within the Centre for Innovation Competence SiLi-nano (Project No. 03Z2HN11). Financial support from the FhG Internal Programs under Grant No. Attract 692 034 is also acknowledged. We thank Dr N. Benczer-Koller for the loan of the ^{151}Sm source.

References

1. Johnson JA, Schweizer S, Henke B, Chen G, Woodford J, Newman PJ, MacFarlane DR. J. App. Phys. 2006; 100:034701.
2. Ball J, Jenden CM, Lyle SJ, Westall WA. J. Less Common Metals. 1983; 95:161.
3. Newman PJ, MacFarlane DR, Cashion J, Edgar A. J. Non-Cryst. Solids. 1999; 256&257:53.
4. Coey JMD, McEvoy A, Shafer MW. J. Non-Cryst. Solids. 1981; 43:387.
5. Selling J, Bielemeier B, Wortmann G, Johnson JA, Alp E, Chen T, Brown DE, Johnson CE, Schweizer S. Phys. Rev. B. 2008; 77:224442.

Figure 1.

Room temperature Mössbauer spectra of finely powdered EuCl_3 heated at 700 °C for 1 hour, (a) directly, (b) 2.9 days (c) 4.8 days (d) 6.9 days (e) 15.9 days, and (f) 19.9 days after the heat treatment.

Figure 2.

Percentage of Eu²⁺ in EuCl₃ heated over time. The data were fitted by $y(t) = 64.3 \cdot \exp(-t/7.0)$.

Figure 3. Mössbauer spectra of 0.2 mm thick plates of ZBLAN:Eu with (a) 5 mol% EuCl_2 and (b) 2.5 mol% EuCl_2 and 2.5 mol% EuCl_3 .