Simple battery armor to protect against gastrointestinal injury from accidental ingestion

Bryan Laulicht^{a,b,1}, Giovanni Traverso^{c,d,1}, Vikram Deshpande^e, Robert Langer^{b,d,2}, and Jeffrey M. Karp^{a,b,f,2}

^aDivision of Biomedical Engineering, Department of Medicine, Center for Regenerative Therapeutics, Brigham and Women's Hospital, Harvard Medical School, Boston, MA 02115; ^bHarvard-MIT Division of Health Sciences and Technology, Massachusetts Institute of Technology, Cambridge, MA 02139; ^cDivision of Gastroenterology, Massachusetts General Hospital, Harvard Medical School, Boston, MA 02114; ^dDepartment of Chemical Engineering and Koch Institute for Integrative Cancer Research, Massachusetts Institute of Technology, Cambridge, MA 02139; ^eDepartment of Pathology, Massachusetts General Hospital, Harvard Medical School, Boston, MA 02114; and ^fHarvard Stem Cell Institute, Cambridge, MA 02138

Contributed by Robert Langer, September 24, 2014 (sent for review August 22, 2014)

Inadvertent battery ingestion in children and the associated morbidity and mortality results in thousands of emergency room visits every year. Given the risk for serious electrochemical burns within hours of ingestion, the current standard of care for the treatment of batteries in the esophagus is emergent endoscopic removal. Safety standards now regulate locked battery compartments in toys, which have resulted in a modest reduction in inadvertent battery ingestion; specifically, 3,461 ingestions were reported in 2009, and 3,366 in 2013. Aside from legislation, minimal technological development has taken place at the level of the battery to limit injury. We have constructed a waterproof, pressure-sensitive coating, harnessing a commercially available quantum tunneling composite. Quantum tunneling composite coated (QTCC) batteries are nonconductive in the low-pressure gastrointestinal environment yet conduct within the higher pressure of standard battery housings. Importantly, this coating technology enables most battery-operated equipment to be powered without modification. If these new batteries are swallowed, they limit the external electrolytic currents responsible for tissue injury. We demonstrate in a large-animal model a significant decrease in tissue injury with QTCC batteries compared with uncoated control batteries. In summary, here we describe a facile approach to increasing the safety of batteries by minimizing the risk for electrochemical burn if the batteries are inadvertently ingested, without the need for modification of most battery-powered devices.

coin cell battery ingestion | battery-induced injury | ingestion of foreign bodies | button battery safety | esophageal injury

Battery ingestion in the pediatric population has been documented for decades and results in an estimated 5,000 emergency room visits per year (1). Of particular concern are button batteries, which can lodge in the esophagus and lead to serious complications, including death. The U.S. Consumer Product Safety Commission has analyzed data from 1997 to 2010 and estimated that 40,400 children younger than 13 years received treatment in hospital emergency departments for battery-related injuries, with 14 battery-related deaths in children from 7 mo to 3 y in age (1). Recent data from the National Capital Poison Center note that 3,366 reported battery ingestions occurred in 2013, with 2,277 occurring in the <6 y age group, and with 8% of these leading to adverse events, including major clinical complications, including death (2, 3). To help protect children from battery accidents, the Consumer Product Safety Improvement Act of 2008 was passed, which mandates toy safety standards (known as F963-11) and requires batteries to be inaccessible in all toys intended for children younger than 3 years. Unfortunately, additional legislation to further regulate the safety associated with button cell batteries (the Button Cell Battery Safety Act of 2011) introduced on June 9, 2011, in a previous session of Congress, was not enacted. This new legislation would have required warning labels and more secure battery compartments on a wide range of products, including watches, cameras, calculators, laptops, and smart phones. Although progress has been made to regulate safety by restricting battery access, improving the safety of batteries

themselves has not been addressed. In fact, newer, higher-voltage batteries such as the 3V lithium-ion batteries, particularly in the ≥20-mm format, which can also be modified using the described approach, are recognized as leading causes of complications if ingested (4).

Injuries and sequelae from inadvertent battery ingestion include vocal cord paralysis, esophageal strictures, esophageal perforation, tracheoesophageal fistula, and aortoesophageal fistula leading to death (1, 5–8). It has been recognized for more than 30 y that esophageal impaction is associated with the most severe morbidity (7). Battery-induced injuries are proposed to occur via three mechanisms: ischemic necrosis from direct pressure, leakage of caustic alkaline electrolytes, and the generation of an external electrolytic current generating hydroxide at the negative pole of the battery (1, 3, 8–10). It is this last mechanism that leads to significant tissue injury (3). Because the interval from ingestion to injury is only 2 h (11), current management guidelines recommend endoscopic evaluation for foreign body retrieval in all cases of battery ingestion (5, 12).

To mitigate injuries caused by battery ingestion, here we report the development of pressure-sensitive, waterproof quantum tunneling composite coated (QTCC) button batteries based on off-the-shelf components. A QTC was applied to the anode of conventional button batteries to impart pressure-sensitive conductive properties. QTCs consist of conductive metal microparticles suspended in an insulating polymer matrix. Nanoscale roughness on the microparticle surface enhances the electric field gradient, such that when the particles come into close proximity (less than 1–5 nm), electrons can tunnel through the

Significance

Accidental battery ingestion in children is a recognized source of significant morbidity and mortality. To mitigate the risks of accidental battery ingestion, legislation has been introduced to regulate the locking of battery compartments. Regulation of battery housings has translated into modest reductions in the number of battery ingestion cases reported. We report here the fabrication of waterproof, pressure-sensitive battery coatings that are nonconductive in the low-pressure gastrointestinal tract, yet conduct in higher-pressure standard battery housings. These safer batteries are expected to reduce complications from accidental battery ingestion.

Author contributions: B.L., G.T., R.L., and J.M.K. designed research; B.L., G.T., and V.D. performed research; B.L., G.T., and V.D. contributed new reagents/analytic tools; B.L., G.T., V.D., R.L., and J.M.K. analyzed data; and B.L., G.T., R.L., and J.M.K. wrote the paper.

Conflict of interest statement: A provisional patent application for the technologies described herein was filed by B.L., R.L., and J.M.K. on March 13, 2013.

¹B.L. and G.T. contributed equally to this work.

²To whom correspondence may be addressed. Email: jmkarp@partners.org or rlanger@mit.edu.

This article contains supporting information online at www.pnas.org/lookup/suppl/doi:10.1073/pnas.1418423111/-DCSupplemental.

given density of conductive microparticles. When the microparticles have higher average spacing at zero stress, greater axial compression is required to bring them into close enough proximity to achieve conduction. Because the QTCCs are affixed to the rigid battery housing, compression is restricted to the axial direction. Therefore, the required pressure for conduction is not diameter-dependent and can be applied to any diameter button battery without significant design modification. Moreover, given that conduction is directly proportional to coating thickness and particle density, significant tunability exists for triggering conduction. QTCCs impart weatherproofing of batteries, expanding the possible applications beyond accidental ingestion scenarios to include using batteries in high humidity or more corrosive environments that would otherwise affect the battery structure.

Results

QTCC Battery Design. Conventional button batteries have circular anodes and cylindrical cathodes separated by insulating ring gaskets (Fig. 1A). To construct a QTCC button battery, a conductive silver paste affixes a QTC disk to the anode (Fig. 1A). Water-impermeable silicone rubber seals the area between the QTC edge and the cathode, bridging the remainder of the anode and gasket to thereby waterproof the battery. To demonstrate that QTCC button batteries function within standard button battery enclosures, three stacked QTCC button batteries were shown to power a commercially available laser pointer (Fig. 1B). Importantly, the materials used to construct QTCC button batteries are inexpensive and readily scalable for mass production.

A high-magnification scanning electron micrograph of the QTC shows a conductive metal microparticle embedded in compressible, insulating silicone polymer (Fig. 1C). Nanoscale features are present on the surface of the metal microparticles, which facilitate quantum tunneling between microparticles because electric field density enhancement increases nonlinearly with decreasing radius of curvature (11, 12). Electron dispersive X-ray spectroscopy peaks for silicon (Si), carbon (C), and oxygen

(O) can be attributed to the poly(dimethyl siloxane) (PDMS), and the silver (Ag) peak to the metal microparticles (Fig. 1D).

Fig. 1E shows a schematic depiction of a QTC with nano-rough silver microparticles suspended in PDMS. When the compressive stress exceeds σ_c , the metal microparticles are in close enough proximity that electrons can tunnel and conduct current, transforming the QTC from an insulator to a conductor. This mechanism allows QTCs to be insulating below compressive stresses of the gastrointestinal tract and conductive above compressive stresses of battery housings, at which QTCC batteries achieve maximum voltage ($V_{\max}$), while remaining impermeable to water.

QTCC Battery Electromechanical Characterization. To quantify the σ_c at which QTCC button batteries achieve their $V_{\max}$, load and voltage were measured continuously between an insulated electrode and a ground electrode held in a water bath (Fig. 2A). Conventional and QTCC button batteries were tested in dry and simulated intestinal fluid (SIF) conditions. The insulated electrode is brought into contact with the battery by the mechanical testing apparatus, applying compressive stress while measuring voltage. Below σ_c , the QTC component of QTCC batteries remains an insulator. Above σ_c , the microparticles within the

Fig. 2. Mechanical and electrical properties comparison between conventional and QTCC button batteries. (A) Experimental setup used to test the threshold force beyond which QTCC button batteries will conduct in SIF. Compressive force and voltage are measured in real time. (B) Schematic diagram of a QTCC button battery compressed below and above the σ_c and when the circuit is completed, achieving $V_{\max}$. (C) A dry conventional button battery conducts at $V_{\max}$ with low applied stress, as highlighted by the dashed lines, showing the compressive stress at which the battery first achieves conduction (σ_c). (D) When immersed in SIF, a conventional button battery shows a ~20% reduction in conduction voltage because of the short-circuit current leaked via the conductive fluid connecting the anode and cathode as an alternate conduction pathway. (E) $V_{\max}$ is reached at ~58 N/cm² by a QTCC button battery in dry conditions. The $V_{\max}$ is equal to that of a conventional button battery. (F) Immersed in SIF, QTCC button batteries require similar levels of compressive stress to achieve conduction. In addition, the $V_{\max}$ achieved is indistinguishably different from that in the dry state because of the waterproof design of QTCC button batteries.

In addition, we have demonstrated that insulated electrodes, such as those used in the electromechanical characterization of the critical stress of conduction (σ_c), allow QTCC batteries to conduct at their full potential, even immersed in conductive fluid environments. Standard batteries under the same conditions will form electrolytic currents that have the potential to not only impart tissue damage but also cause the breakdown of the gasket separating the anode and cathode. Within hours after immersion, standard batteries begin to release their contents once the gaskets are compromised, whereas QTCC batteries show no signs of damage or current loss. Therefore, QTCC batteries also have the potential to function in aqueous and corrosive environments based solely on the QTC coating without requiring additional waterproof battery housings.

Further studies in animal models including evaluation of larger batteries and a broad range of batteries inclusive of the more recently developed 3V lithium batteries will be conducted to maximize translational potential. Furthermore, accidental impaction in orifices including the nose and ear will be evaluated in future studies. The platform we present has the capacity for extensive tunability to varying pressures, depending on the button battery-powered device requirements, by virtue of the QTC parameters. Implementation of safer button batteries should result in significant reductions in morbidity and mortality in the pediatric population in particular, as well as other vulnerable populations using button batteries, such as the elderly. Furthermore, by limiting moisture exposure, QTC coatings have the potential to lengthen the shelf life of batteries.

Materials and Methods

QTCC Button Battery Construction. To construct QTCC button batteries, 1-mm-thick sheets of QTCs (Zoflex) were punched with 6-mm-diameter biopsies (Integra Miltex) to form disks. QTC discs were affixed to the anodes of conventional button batteries often used in hearing aids (Rayovac 675, 11.6 mm diameter, 5.4 mm height, 1.4V), using conductive silver paste (McMaster-Carr). Sylgard 184 (Dow Corning) silicone (PDMS) prepolymer and cross-linking agent mixture was applied in the area surrounding the QTC disk, ensuring that the edges of the QTC, exposed anode surface, and gasket were completely covered. Once the PDMS cured, the applied coating imparted waterproofing and pressure-sensitive conduction properties.

QTCC Button Battery Functional Analysis. To verify the functioning of QTCC button batteries in a device commonly powered by conventional button batteries, a miniature laser pointer (LaserPointerPro.com) was powered with three QTCC button batteries. The only alteration to the battery housing was a viewing window that was milled to enable visualization of the QTCC button batteries in action. The normal functioning of the laser pointer indicates that QTCC button batteries could readily be used in place of conventional button batteries.

Morphological and Compositional Analysis. The QTC surface was analyzed on a Zeiss Ultra55 field emission scanning electron microscope (Carl Zeiss AG) equipped with energy-dispersive spectroscopic elemental analysis.

Electromechanical Testing. To quantify the compressive stress at which QTCC batteries achieve $V_{\max}$ compared with conventional button batteries in SIF and dry conditions, batteries were placed between an insulated electrode and a ground electrode. A mechanical tester (ADMET) was used to simultaneously measure applied compressive force and voltage. Digital recordings of the electromechanical test were obtained and analyzed to calculate the contact area between the insulated conductive probe and the batteries.

Simulated Intestinal Fluid Immersion Testing. To determine how conventional and QTCC batteries would differ in a simulated intestinal environment, conventional and QTCC button batteries were immersed in phosphate buffer saline as a model for SIF (phosphate-buffered saline at pH 7.4; Life Technologies). Small intestinal tissue from Yorkshire swine was procured within 20 min of animal death and stored at 4 °C. All tissue was obtained from Research 87, Inc. Samples were placed anode-down on the mucosal side of porcine intestinal tissue for 48 h to simulate exposure for the full duration of gastrointestinal transit. After immersion, voltage was measured as described earlier to quantify loss. Samples were placed anode-down on the mucosal side of porcine intestinal tissue for 2 h while being digitally recorded or photographed.

Statistics. For single comparisons, an unpaired Student *t* test was used. For multiple comparisons, analysis of variance was performed with the Tukey's honestly significant difference test at significance levels of 95%. Error bars in bar graphs represent the SD.

In Vivo Evaluation of QTCC Button Batteries. In vivo porcine studies were performed in two female Yorkshire pigs weighing 65 kg. After induction of anesthesia with intramuscular injection of Telazol (tiletamine/zolazepam) 5 mg/kg, xylazine 2 mg/kg, and atropine 0.04 mg/kg, the pigs were intubated and maintained on isoflurane 1–3% (vol/vol). An esophageal overtube (Guardus overtube 50 cm; US Endoscopy) with an inner diameter of 16.7 mm was placed to enable facile and rapid esophageal access, as well deployment of the batteries. Control (uncoated) and QTCC batteries were deployed individually in varying segments of the esophagus. A total of three control (uncoated) and three QTCC batteries were evaluated. Individual batteries were evaluated one at a time by deployment in the esophagus and monitoring every 30 min endoscopically to ensure these remained stationary, thereby approximating esophageal battery impaction. To ensure the batteries remained stationary within the esophagus and to enable targeted biopsy sampling, batteries were placed immediately distal to the overtube, whereby the distal end of the overtube served as both a fiducial and guide for the location of the batteries. After 2 h, the batteries were removed and the site of battery placement biopsied for histological evaluation. All procedures were conducted in accordance with protocols approved by the Massachusetts Institute of Technology Committee on Animal Care.

ACKNOWLEDGMENTS. We thank Janet Freilich for her thoughtful discussions and writing assistance. We thank Hao-Yu Lin for his technical assistance with electron microscopy, and Richard Gedney and Ross Barman for their technical assistance. We thank Pentax for providing the endoscopic equipment used for this research, and in particular, Mike Fina for facilitating access to the equipment. This work was funded in part by NIH Grants DE013023 and EB000244 (to R.L.), Grant GM086433 (to J.M.K.), and Grant T32 DK 7191-38 S1 (to G.T.).

- Centers for Disease Control and Prevention (CDC) (2012) Injuries from batteries among children aged <13 years—United States, 1995–2010. *MMWR Morb Mortal Wkly Rep* 61(34):661–666.
- National Capital Poison Center (2014) National Capital Poison Center. Available at www.poisson.org/battery/stats.asp. Accessed July 16, 2014.
- Litovitz T, Whitaker N, Clark L (2010) Preventing battery ingestions: An analysis of 8648 cases. *Pediatrics* 125(6):1178–1183.
- Soccorso G, et al. (2012) 20 mm lithium button battery causing an oesophageal perforation in a toddler: Lessons in diagnosis and treatment. *Arch Dis Child* 97(8):746–747.
- Kimball SJ, Park AH, Rollins MD, 2nd, Grimmer JF, Muntz H (2010) A review of esophageal disc battery ingestions and a protocol for management. *Arch Otolaryngol Head Neck Surg* 136(9):866–871.
- Patel SA, Hillel AD, Perkins J (2013) Battery ingestion leading to bilateral vocal cord paresis. *JAMA Otolaryngol Head Neck Surg* 139(3):304–306.
- Litovitz TL (1983) Button battery ingestions. A review of 56 cases. *JAMA* 249(18):2495–2500.
- Hamilton JM, Schraff SA, Notrica DM (2009) Severe injuries from coin cell battery ingestions: 2 case reports. *J Pediatr Surg* 44(3):644–647.
- Slamon NB, et al. (2008) An unusual case of button battery-induced traumatic tracheoesophageal fistula. *Pediatr Emerg Care* 24(5):313–316.
- Yoshikawa T, Asai S, Takekawa Y, Kida A, Ishikawa K (1997) Experimental investigation of battery-induced esophageal burn injury in rabbits. *Crit Care Med* 25(12):2039–2044.
- Walker AJ, Caldera F (2013) Corrosive esophageal injury by button battery. *Gastrointest Endosc* 78:654, and discussion 654–655.
- Ikenberry SO, et al.; ASGE Standards of Practice Committee (2011) Management of ingested foreign bodies and food impactions. *Gastrointest Endosc* 73(6):1085–1091.
- Stassi S, Canavese G (2012) Spiky nanostructured metal particles as filler of polymeric composites showing tunable electrical conductivity. *J Polym Sci, B, Polym Phys* 50:984–992.
- Stassi S, Cauda V, Canavese G, Manfredi D, Pirri CF (2012) Synthesis and Characterization of Gold Nanostars as Filler of Tunneling Conductive Polymer Composites. *Eur J Inorg Chem* 2012:2669–2673.
- Richter JE, et al. (1987) Esophageal manometry in 95 healthy adult volunteers. Variability of pressures with age and frequency of “abnormal” contractions. *Dig Dis Sci* 32(6):583–592.