Published in final edited form as:

Lab Chip. 2015 March 7; 15(5): 1329–1334. doi:10.1039/c4lc01294a.

Fracture Fabrication of a Multi-scale, Channel Device that Efficiently Captures and Linearizes DNA from Dilute Solutions

Byoung Choul Kim^{1,2,3}, Priyan Weerappuli, M.D.^{1,3}, Thouless^{4,5}, and Shuichi Takayama^{1,2,3,6}

¹Department of Biomedical Engineering, College of Engineering, University of Michigan, 2200 Bonisteel Blvd, Ann Arbor, MI 48109, USA

²Macromolecular Science and Engineering Center, College of Engineering, University of Michigan, 2300 Hayward St., Ann Arbor, MI 48109, USA

³Biointerfaces institute, University of Michigan, 2800 Plymouth Rd, Ann Arbor, MI 48109, USA

⁴Department of Mechanical Engineering, College of Engineering, University of Michigan, 2350 Hayward St., Ann Arbor, MI 48109, USA

⁵Department of Materials Science & Engineering, College of Engineering, University of Michigan, 2300 Hayward St., Ann Arbor, MI 48109, USA

⁶Division of Nano-Bio and Chemical Engineering WCU Project, UNIST, Ulsan, Republic of Korea

Abstract

This paper describes a simple technique for patterning channels on elastomeric substrates, at two distinct scales of depth, through the use of controlled fracture. Control of channel depth is achieved by the careful use of different layers of PDMS, where the thickness and material properties of each layer, and the position of layers relative to one another, dictate the depth of the channels formed. The system created in this work consists of a single ‘deep’ channel, whose width can be adjusted between the micron- and nano-scale by the controlled application or removal of a uniaxial strain, and an array of ‘shallow’ nano-scale channels oriented perpendicular to the ‘deep’ channel. The utility of this system is demonstrated through the successful capture and linearization of DNA from a dilute solution, by executing a two-step ‘concentrate-then-linearize’ procedure. When the ‘deep’ channel is in its open state, and a voltage is applied across the channel network, an overlapping electric double layer forms within the ‘shallow’ channel array. This overlapping electric double layer is used to prevent passage of DNA into the ‘shallow’ channels when the DNA molecules migrate into the junctional region by electrophoresis. Release of the applied strain then allows the ‘deep’ channel to return to its closed state, reducing the cross-sectional area of this channel from the micro- to the nano-scale. The resulting hydrodynamic flow and nano-confinement effects then combine to efficiently uncoil and trap the DNA in its linearized form. By adopting this strategy, we were able to overcome the entropic barriers associated with capturing and linearizing DNA derived from a dilute solution.

*takayama@umich.edu.

Introduction

Fabrication techniques capable of producing features at both the micro- and nano-scales, present novel opportunities for pursuing broad biological applications; including more efficient sample preparation, pre-processing, and analysis at both the cellular and molecular level.^{1–7} The fabrication of multi-scale features by conventional methods requires complex procedures, careful handling, and the use of specific materials and expensive equipment. Consequently, it is generally a much more difficult task than the fabrication of mono-scale features. In previous work, we have reported the use of controlled-fracture to fabricate channels at either the micro- or nano-scale by the use of multilayered structures, where channel depth is controlled by the properties and dimensions of the individual layers. Furthermore, we have also reported the capacity to produce uniform arrays of size-adjustable channels by judicious positioning of stress-shielding structures.⁸ Here, we combine these methodologies to develop a simple approach for creating multi-scale patterns using controlled fracture.

We report a technique which we have used successfully to produce orthogonally-oriented channels of differing scales using multi-layered assemblies comprised of poly(dimethylsiloxane) (PDMS) and its variant, hard-PDMS (h-PDMS). The resulting channel system consisted of a ‘deep’ single channel, whose cross-sectional area could be stably adjusted between the micro- and nano-scale by the application of sustained uniaxial strain; intersected by a ‘shallow’, fixed-width, nano-scale channel array. This unique system was used to conduct a nano-confinement-based single-DNA analysis, where the DNA image was derived from a dilute solution.

The introduction of DNA into nanochannels has traditionally been most efficient when the initial sample concentration is high, or when an external force is applied.^{9–11} This is the result of two fundamental challenges associated with capturing DNA from dilute solutions within a nanochannel geometry: the entropic cost of concentrating DNA molecules within a small volume, and the entropic cost associated with uncoiling DNA.^{11, 12} In this paper, our channel system was employed to overcome such challenges by sequentially exploiting (i) nanochannel-based electrophoretic migration to position single DNA molecules in a desired location, and (ii) tunable modulation of channel width to induce uncoiling of the DNA.

Materials and Methods

Criss-crossing ‘deep’/‘shallow’ channel fabrication

A carefully-planned sequence of material layering and strain application is used to create a four-layered structure with criss-crossing ‘deep’/‘shallow’ channels. The four-layers making up this structure are (i) PDMS (capping layer), (ii) silica-like h-PDMS (SL-h-PDMS), (iii) hPDMS, and (iv) PDMS (substrate layer). The thickness and modulus differences between these four layers determine which layer cracks are formed in, and the size of the resulting cracks. Strategically placed features molded into the structures using conventional micro-fabrication methods,¹³ serve the dual roles of controlling crack location and functioning as liquid reservoirs during operation of the device.

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Opposing pairs of micron-scale, sharp, V-notch reservoirs and blunt reservoirs were cast into an h-PDMS elastomer mixture as previously described,¹⁴ and spin-coated directly on a master-mold consisting of SU-8 (Microchem) features patterned upon a polished silicon wafer. The sharp and blunt reservoirs were aligned perpendicular to one another. This h-PDMS layer (target thickness: ~ 10 microns) was then incubated at 120°C for 120 s. Following incubation, a 10:1 mixture of PDMS monomer and a Sylgard 184 cross-linker (Dow Corning) was deposited above the h-PDMS layer to a target thickness of 5 mm, and cured overnight at 60°C. The cured h-PDMS/PDMS bilayer was then carefully peeled from the SU-8 mold, and loaded into a stretcher (S.T. Japan USA LLC, FL, USA). When a uniaxial strain of approximately 15% was applied in a direction perpendicular to the V-notch tips, a single crack was initiated at each tip. These propagated uni-directionally until a complete crack was formed between the tips. A thorough characterization of such crack formation, and its control, is presented in earlier work.^{8, 15} This ‘deep’ crack occurred at the micron-scale, corresponding to the thickness of the h-PDMS layer. The applied strain was then removed, and the h-PDMS layer was covered with tape (3M, Inc.). Four tape segments were cut and carefully applied to the h-PDMS layer under a stereoscope, such that only the rectangular region between the blunt reservoirs (measuring approximately 1.0×0.3 mm) remained uncovered. This region could then be selectively treated by plasma oxidation (200W, 600s), to create a thin silica-like surface (SL-h-PDMS). After removing the tape, a uniaxial strain of approximately 6% was applied in a direction perpendicular to the blunt-tip features to induce the formation of multiple ‘shallow’ cracks between the blunt micro-features that were positioned orthogonal to the original deep crack. This second set of the ‘shallow’ cracks occurred at the nano-scale, corresponding to the thickness of the SL-h-PDMS layer. The resulting SL-h-PDMS/h-PDMS/PDMS tri-layer was then bonded to a PDMS membrane (target thickness: 200 μ m) to convert these fractures, through sealing, into the single ‘deep’/multiple ‘shallow’ channel pattern.

Electrophoretic single DNA migration, capture, and elongation in hybrid micro-nanochannel structure

All reservoirs and channels were perfused with 0.1x TBE buffer immediately after plasma bonding. This ensures maximal retention of the plasma treatment-induced channel wall surface charge, and consequently, the hydrophilic state (and possibly vacuum-applied state of PDMS)¹⁶ necessary for preventing bubble formation when channel dimensions are modulated. Following perfusion, a low concentration λ -DNA solution (1 pg/ μ l, New England Biolabs, Inc), stained with YOYO-1 intercalating dye at a base-pair to dye ratio of 20:1, was loaded into one of the sharp-tip reservoirs in the four-layer assembly. A cathode was then positioned in the same reservoir, and a corresponding anode was positioned in one of the blunt tip reservoirs. An electric field (400V/cm) was then applied while the ‘deep’ channel was held in its open state by the sustained application of uniaxial strain. The presence of the electric field caused the λ -DNA molecule in the solution to migrate through the open ‘deep’ channel toward the intersecting ‘shallow’ channels. The inability of the DNA to enter the ‘shallow’ channels, however, resulted in single molecules being stranded at this junction. The stranded λ -DNA molecule was then linearized by the controlled release of the applied strain, which induced narrowing of the ‘deep’ channel to its closed state.

Results & Discussion

Size-controllable channel structures for concentration, trapping, and elongation of DNA

As described above, the device used in these experiments consisted of a single ‘deep’ channel connecting the two sharp-tip reservoirs, and an array of ‘shallow’ channels connecting the blunt-tip reservoirs (Figure 1a). Application of uniaxial strain in the direction perpendicular to the axis delineated by the sharp-tip reservoirs opened the normally-closed ‘deep’ channel (Figure 1b). Subsequent application of an electric field across the channel network then induced electrophoretic movement of DNA molecules to the junction between the ‘shallow’ channels and the open ‘deep’ channel (Figure 1c). After successfully positioning the molecule at this junction, the applied strain was released, to generate hydrodynamic forces that elongated and linearized the DNA as the ‘deep’ channel passively returned to its closed state (Figure 1d).

Fracture fabrication procedures to create the criss-crossing ‘deep’/‘shallow’ channel device

The differing inherent fracture characteristics of h-PDMS and SL-h-PDMS^{2, 9, 11–14} were exploited to generate intersecting cracks of differing scale. Summarizing previous work, the fracturing of films produced by the plasma oxidation of PDMS (referred to as silica-like PDMS (SL-PDMS)) result in the formation of nano-scale channels, owing to the thin and brittle nature of the SL-PDMS layer^{2, 17, 18}. Fracturing of h-PDMS deposited on a PDMS slab results in the formation of micro-scale channels, owing to the relatively thick and compliant nature of the h-PDMS film¹⁴. To construct the crisscrossing multi-scale ‘deep’/‘shallow’ channel device presented herein; we first formed a single, normally-closed ‘deep’ channel within an h-PDMS/PDMS bilayer structure using pre-patterned stress-shielding features and controlled fracture^{8, 14, 15}. Next, we speculated, and confirmed, that plasma treatment of h-PDMS creates a thin SL-h-PDMS layer that forms nano-scale cracks. By restricting the region of the h-PDMS surface exposed to plasma oxidation through use of a tape mask formed by carefully aligned tape segments relative to patterned features (Figure 2D), and by applying the cracking strain in a direction perpendicular to the direction used for formation of the ‘deep’ channel, an array of ‘shallow’ nano-scale channels was formed perpendicular to the original ‘normally-closed’ ‘deep’ channel. This ensured that any fluid communication between the ‘deep’ and ‘shallow’ channels occurred only at their points of intersection (Figure 2, and see Materials and Method section). In the resulting device, the multiple ‘shallow’ channels formed in the SL-h-PDMS layer remained slightly open at the nano-scale, even in the absence of an applied strain, owing to residual stresses resulting from the plasma oxidation^{19, 20}.

Electrophoretic DNA migration by ion concentration polarization (ICP)

The functional significance of the ‘shallow’ channel array within this system, is its capacity to facilitate pre-concentration of negatively charged DNA molecules by providing a structural environment capable of generating an exclusion-enrichment effect (EEE) induced by ion-concentration polarization (ICP).^{21–23} Here, the narrow width of the nano-scale ‘shallow’ channels produces overlapping electrical double layers (EDLs) within each channel that restrict the directionality of ion transfer upon application of an external electric

potential.^{21, 24, 25} Consequently, the negative surface charge on the SL-h-PDMS layer, combined with the presence of EDLs within the ‘shallow’ channels, prevent λ -DNA molecules from being able to enter these channels after they have been drawn along the ‘deep’ channel (in its open state) from the cathodic sharp-tip reservoir (Figure 3A). The use of cathodic side enrichment, which is often less efficient than the anodic side, is because of higher precision and ease with which we could capture single DNA molecules at the desired ‘shallow’/‘deep’ channel junction region.

Single DNA capturing and linearization in the ‘deep’ channel

Based upon a theoretical understanding of electrophoretic DNA migration within the criss-crossing channel device, we performed single-molecule DNA capturing and linearization using a very low concentration λ -DNA solution (1 pg/ μ l). Following sample loading, the ‘deep’ channel extending between the sharp-tip reservoirs was opened, and an electric field (approximately 400V/cm) was applied to localize a single DNA molecule at the ‘deep’/‘shallow’ channel junction. The ‘deep’ channel could be expanded to a cross-sectional area of approximately 70 μ m² in its open state (under 10% strain), and reduced to approximately 1220 nm² in the absence of an applied strain (Figure 3B). This cross-sectional size-adjustability of the ‘deep’ channel enabled easy loading of λ -DNA into the strain-widened channel under an applied electric field and, also, circumvented the entropic costs associated with λ -DNA uncoiling, by coupling this process with the reduction in channel width initiated by the slow release of the previously-applied strain. By doing so, DNA linearization was performed passively by simply exploiting the hydrodynamic forces and nano-confinement effects produced during the narrowing of the ‘deep’ channel to its normally-closed nano-scale dimensions (Figure 3C). Here, the position of the junctional area between the ‘deep’ channel and the ‘shallow’ channels relative to the positions of the sharp-tip reservoirs was critical for achieving successful DNA linearization, and preventing the loss of DNA during channel narrowing. As depicted in Figure 3A, the junctional area was centered about the midline of the ‘deep’ channel. Consequently, λ -DNA drawn to this junction, were also positioned at the midline of the open ‘deep’ channel under the applied electric field. This positioning ensured that the λ -DNA molecule remained trapped as the surrounding fluid was evacuated from the channel during ‘deep’ channel narrowing. If the λ -DNA molecule had been inappropriately positioned at an off-centered position, it could easily be flushed out of the channel by this flow. The calculated local concentration of the single λ -DNA molecule achieved following channel narrowing was approximately 145 ng/ μ l, which is nearly 145,000x higher relative to the initial stock solution (See Supplementary Discussion). The calculated degree of linearization of the trapped DNA ($n = 39$) in the closed ‘deep’ channel was $52 \pm 20\%$ relative to the contour length of λ -DNA considering intercalating dye effects (expected full length of λ -DNA under the dye concentration used is approximately 17.5 μ m) (Figure 3D). These results suggest that the entropic challenge to un-coiling DNA has also been overcome. Compared to previous work reporting $> 90\%$ elongation relative to DNA contour length,^{2, 26} the degree of DNA linearization achieved within the criss-crossing ‘deep’/‘shallow’ channel device presented is relatively low, and characterized by considerable variability owing to rare events including partial channel collapse or DNA adsorption to the channel wall. These deficits, however, may be addressed by additional mechanical compression of the ‘deep’ channel to achieve a

narrower cross-sectional area in its closed-state, by surface passivation of the ‘deep’ channel sufficient to prevent DNA adsorption, and by the application of an electric field following closing of the ‘deep’ channel.

Conclusions

We have developed a simple method to fabricate criss-crossing ‘deep’/‘shallow’ channels in multilayered soft materials by a fracture-based technique. Careful control of the thickness and properties of each layer provided the capacity to pattern differentially-sized fractures. Stress-shielding features and applied strain (both magnitude and direction) were then used to generate a hybrid micro/nanochannel system. To our knowledge, this is the first reported approach to develop multi-scaled channel structures in such a robust, yet simple, manner. This paper expands the capabilities of fracture-based micro/nanofabrication. Importantly, this fabrication technique was applied to create a unique and useful fluidic platform capable, in itself, of overcoming inherent entropic barriers to efficiently pre-concentrate and linearize single DNA molecules isolated from a sample with low initial concentration. These barriers, the entropic costs of concentrating and uncoiling DNA, are overcome by exploiting the exclusion-enrichment effect and ion-concentration polarization, to produce efficient electrophoretic pre-concentration. The use of hydrodynamic shear, generated by the controlled release of an applied strain, then uncoiled these DNA molecules within the size-adjustable channels. In addition to the successful manipulation of DNA that has been reported here, criss-crossing arrangements of channels have demonstrated their utility in a variety of applications including the handling of worms^{27, 28} or bacteria,²⁹ oocyte cryopreservation³⁰, and single cell analysis.³¹ Owing to the versatility of the fracture-based fabrication method for the fabrication of channels in producing differing micro- and nano-scale channels, we believe this fabrication method and device will prove to have broader applications beyond the specific example presented here.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

This work was supported by a grant from the US National Institute of Health (HG004653-03), a Rare Cells Seed Grant from the Biointerfaces Institute, University of Michigan, and the Wayne State University Interdisciplinary Biomedical Sciences Competitive Research Fellowship (to PW).

References

1. Diana SFL, Streng E, Pan Junhan, Karpusenka Alena, Riehn Robert. *Lab on a Chip*. 2009; 9:2772–2774. [PubMed: 19967112]
2. Matsuoka T, Kim BC, Huang J, Douville NJ, Thouless M, Takayama S. *Nano letters*. 2012
3. Matsuoka T, Kim BC, Moraes C, Han M, Takayama S. *Biomicrofluidics*. 2013; 7:041301.
4. Aguilar CA, Craighead HG. *Nature Nanotechnology*. 2013; 8:709–718.
5. Cao H, Tegenfeldt JO, Austin RH, Chou SY. *Applied Physics Letters*. 2002; 81:3058–3060.
6. Persson F, Tegenfeldt JO. *Chemical Society Reviews*. 2010; 39:985–999. [PubMed: 20179820]
7. Lam ET, Hastie A, Lin C, Ehrlich D, Das SK, Austin MD, Deshpande P, Cao H, Nagarajan N, Xiao M. *Nature Biotechnology*. 2012; 30:771–776.

8. Kim BC, Matsuoka T, Moraes C, Huang J, Thouless M, Takayama S. Scientific reports. 2013; 3:3027. [PubMed: 24149668]
9. Reisner W, Pedersen JN, Austin RH. Reports on Progress in Physics. 2012; 75:106601. [PubMed: 22975868]
10. Han J, Craighead H. Science. 2000; 288:1026–1029. [PubMed: 10807568]
11. Cabodi M, Turner SW, Craighead HG. Analytical chemistry. 2002; 74:5169–5174. [PubMed: 12403567]
12. Mannion J, Reccius C, Cross J, Craighead H. Biophysical journal. 2006; 90:4538–4545. [PubMed: 16732056]
13. Xia Y, Whitesides GM. Annual review of materials science. 1998; 28:153–184.
14. Kim BC, Moraes C, Huang J, Matsuoka T, Thouless M, Takayama S. Small. 2014
15. Huang J, Kim BC, Takayama S, Thouless M. Journal of Materials Science. 2014; 49:255–268.
16. Monahan J, Gewirth AA, Nuzzo RG. Analytical chemistry. 2001; 73:3193–3197. [PubMed: 11467573]
17. Mills KL, Huh D, Takayama S, Thouless MD. Lab Chip. 2010; 10:1627–1630. [PubMed: 20517560]
18. Huh D, Mills K, Zhu X, Burns MA, Thouless M, Takayama S. Nature materials. 2007; 6:424–428. [PubMed: 17486084]
19. Thouless MD, Li Z, Douville N, Takayama S. Journal of the Mechanics and Physics of Solids. 2011
20. Douville NJ, Li Z, Takayama S, Thouless MD. Soft Matter. 2011; 7:6493–6500.
21. Kim SJ, Song YA, Han J. Chemical Society Reviews. 2010; 39:912–922. [PubMed: 20179814]
22. Kim H, Kim J, Kim EG, Heinz AJ, Kwon S, Chun H. Biomicrofluidics. 2010; 4:043014.
23. Wu ZY, Li CY, Guo XL, Li B, Zhang DW, Xu Y, Fang F. Lab Chip. 2012; 12:3408–3412. [PubMed: 22785610]
24. Chantiwas R, Park S, Soper SA, Kim BC, Takayama S, Sunkara V, Hwang H, Cho YK. Chemical Society Reviews. 2011; 40:3677–3702. [PubMed: 21442106]
25. Sparreboom W, Van Den Berg A, Eijkel J. Nature Nanotechnology. 2009; 4:713–720.
26. Tang J, Doyle PS. Applied Physics Letters. 2007:90.
27. Chronis N, Zimmer M, Bargmann CI. Nature methods. 2007; 4:727–731. [PubMed: 17704783]
28. Rohde CB, Zeng F, Gonzalez-Rubio R, Angel M, Yanik MF. Proceedings of the National Academy of Sciences. 2007; 104:13891–13895.
29. Tandogan N, Abadian PN, Epstein S, Aoi Y, Goluch ED. PloS one. 2014; 9:e101429. [PubMed: 24978477]
30. Lai DJ, Smith D, GW, Smith GD, Takayama S. Human Reproduction. 2015; 30:37–45. [PubMed: 25355589]
31. Di Carlo D, Aghdam N, Lee LP. Analytical chemistry. 2006; 78:4925–4930. [PubMed: 16841912]

Figure 1.

Schematic of DNA migration and squeezing system. (A) A single 'deep' channel and multiple perpendicularly-oriented 'shallow' channels. Each fracture-formed structure originates, and terminates, within a reservoir so that 'shallow' channels effectively connect the blunt-tip reservoirs, while the 'deep' channel connects the sharp-tip reservoirs. A photograph of the device is provided for reference (*Right*). In its operation, (B) the 'deep' channel is transitioned from a closed to an open-state through the application of a uniaxial strain along an axis perpendicular to the 'deep' channel itself. When in its open state, (C) DNA introduced via one of the sharp-tip reservoirs will migrate and become localized at the juncture between the 'deep' channel and its intersecting 'shallow' channels through exclusion-enrichment effect. (D) The subsequent release of the previously-applied uniaxial strain then allows the 'deep' channel to return to its closed-state, and in doing so, generates hydrodynamic flow within the channel sufficient to linearize the trapped DNA molecule.

Figure 2.

A diagram of the stepwise fabrication process used for the fabrication of the described crisscrossing channel system. (A) Two pairs of symmetrical micro-features were first cast within the h-PDMS/PDMS bilayer assembly from a pre-patterned SU-8 mold. (B) A single crack was then formed in the h-PDMS layer. This crack extended between the mirrored V-notch tips by the controlled application of uniaxial strain, and was capable of being (C) 'healed' (closed and bonded through van der Waals forces) upon release of the applied strain. (D) The two-layer assembly was then covered by a tape mask so that only the surface region between the blunt-tip features (measuring approximately 1.0×0.3 mm) was exposed. This enabled the (E) selective plasma-treatment of this region, producing a SL-h-PDMS nano-layer on the surface of the h-PDMS layer. (F) Multiple nano-cracks were then

produced in the SL-h-PDMS layer when the assembly was subjected to a second uniaxial strain applied in a direction perpendicular to that of the previously applied strain. The resulting cracks were then sealed by plasma bonding the cracked-surface to a PDMS membrane, forming (G) a single ‘deep’ channel in the h-PDMS layer and multiple orthogonally-oriented ‘shallow’ channels in the SL-h-PDMS layer.

Figure 3.

Application of the 'deep'/'shallow' channel system for capturing and elongating single DNA molecules. (A) A schematic illustrating the ion concentration polarization and DNA migration generated within the 'deep'/'shallow' channel junction under an applied electric field. (B) Changes in the cross-sectional dimensions of the 'deep' channel in response to a sustained applied strain. (C) An illustration of the multiple steps involved in DNA concentration, trapping, and linearization in the 'deep' channel. As the 'deep' channel narrows, a hydrodynamic squeezing flow is generated. The coincident application of a hydrodynamic squeezing flow and nano-confinement induce and maintain DNA elongation. The yellow dashed-line represents the 'shallow' nano-scale channel region. Scale bar is 5 μm . (D) A plot of the frequency distribution of the lengths of elongated λ -DNA in the closed 'deep' channel.