Published in final edited form as:

Curr Cardiol Rep. 2011 April ; 13(2): 113–120. doi:10.1007/s11886-010-0161-2.

The Heterogeneous Biomechanics and Mechanobiology of the Mitral Valve: Implications for Tissue Engineering

K. Jane Grande-Allen, Ph.D.¹ and Jun Liao, Ph.D.²

¹Department of Bioengineering, Rice University, Houston, TX

²Department of Biological Engineering, Mississippi State University, Mississippi State, MS

Abstract

There are very compelling reasons to develop a tissue engineered mitral valve, but this endeavor has not received the same attention as tissue engineering strategies for the semilunar valves. Challenges in regenerating a mitral valve include recapitulating the complex heterogeneity in terms of anatomy (differently sized leaflets, numerous chordae), extracellular matrix composition, biomechanical behavior, valvular interstitial cell and endothelial cell phenotypes, and interior vasculature and innervation. It will also be essential to restore the functional relationships between the native mitral valve and left ventricle. A growing amount of information relevant to tissue engineering a mitral valve has been recently collected through investigations of cell mechanobiology and collagen organization. It is hoped that the development of tissue engineered mitral valves can build on knowledge derived from engineering semilunar valves, but the mitral valve will presents its own unique challenges as investigators move towards a first generation prototype.

Keywords

valvular interstitial cells; extracellular matrix; collagen; material behavior; mechanobiology; biomechanics; glycosaminoglycans; mitral regurgitation; congenital heart disease; valvular endothelial cells; tissue engineering; leaflets; chordae tendineae; smooth muscle alpha-actin; elastic modulus

Introduction

Although the drive to generate tissue engineered heart valves has been primarily focused on the semilunar valves (aortic and pulmonary), there are compelling reasons to develop tissue engineered atrioventricular valves (mitral and tricuspid). The incidence of myxomatous mitral valve disease in industrialized nations such as the USA is estimated at 1–2% [1,2]. Approximately 41,000 hospitalizations per year are due to surgical corrections of mitral

Correspondence to: K. Jane Grande-Allen.

Author addresses:

K. Jane Grande-Allen, Ph.D., Department of Bioengineering, Rice University, 6100 Main St., MS 142, Houston, TX 77005, Phone: 713-348-3704, Fax: 713-348-5877, grande@rice.edu

Jun Liao, Ph.D., Department of Biological Engineering, Mississippi State University, 130 Creelman Street, Mississippi State, MS 39762, Phone: 662-325-5987, Fax: 662-325-3853, jliao@abe.msstate.edu

valve regurgitation (MR) in the USA [1], yet this number represents only 44% of persons with severe MR who would benefit from surgical correction [2]. In addition, the initial durability of these repairs has been impressive, but there is an increasing recognition of the occurrence of late return of significant MR.[2] Furthermore, congenital heart defects in the USA occur in 9 in 1000 live births [1], the majority of which are associated with abnormal valves. There are very few options for treating congenital valve defects, such as valve repair or replacement with a tiny mechanical or bioprosthetic valve, but these corrections are only palliative and do not preclude the need for re-operation on the valve later in the patient's life. The prognosis for children with congenital valve disease as well as adults with mitral valve disease would be profoundly improved by the development of a living tissue engineered mitral valve (TEMV).

The essential function of the mitral valve (MV) is opening to allow blood flow from the left atrium to left ventricle and closing to prevent retrograde flow. This function is coordinated by the complicated structure and mechanical behavior of the MV, which in turn depend upon the inherent heterogeneity in extracellular matrix and cell phenotype within these diverse anatomic structures. This review will address the different scales of tissue and cell mechanobiology found within the MV and explain how these present challenging design goals for a TEMV.

Anatomy

The MV consists of 2 primary leaflets and numerous chordae tendineae (Fig. 1a). The anterior leaflet (AL) of the MV begins as a distal continuation of the sub-aortic curtain below the left and noncoronary leaflets of the aortic valve. The posterior leaflet (PL) is attached to the lateral wall of the left ventricle just below the left atrium. Hence, the annulus (leaflet attachment region) is muscular for the PL and fibrous for the AL. Both leaflets extend into the mitral orifice, with the AL covering the majority of the orifice and the PL wrapping around the free edge of the AL to provide a sealed closure. The upper ends of the chordae tendineae attach either underneath the leaflet (basal, strut) or at the leaflet free edge (marginal), and the lower ends insert in the papillary muscles. Normal valve function involves coordinated motion of the leaflets and chordae as guided by blood flow, ventricular and atrial pressures, and contraction of the ventricle, papillary muscles, and annulus. The various components of the MV also play essential roles in ventricular function; the AL serves as a dynamic portion of the left ventricular outflow tract and helps to direct flow during ventricular ejection of blood through the aortic valve [2]. Additionally, it was recognized more than a decade ago that chordal tension makes critical contributions to ventricular health [2]. It will be important for a TEMV to recapitulate this fundamentally intertwined integration of MV and ventricular function.

Microstructure and Extracellular Matrix

The MV leaflets have a layered microstructure that is readily distinguishable using multi-color histological stains and that can be examined to understand the mechanical behavior of the entire tissue. From top to bottom, the primary layers are the atrialis, spongiosa, and fibrosa. The fibrosa is a thick, heavily collagenous layer on the ventricular surface, the

atrialis is a thin, predominantly elastic layer on the atrial surface, and the inner “spongiosa” layer contains proteoglycans and the glycosaminoglycan hyaluronan (Fig. 1b). These layers do not exclusively contain only one type of ECM; the atrialis and spongiosa both contain loosely organized collagen [3], the spongiosa also contains a network of elastic fibers [4], and the fibrosa and atrialis also contain certain types of proteoglycans [4]. The total leaflet thickness and fibrosa layer thickness in AL are greater than those of the PL [3]. Furthermore, the relative thicknesses of these layers varies within each leaflet from its attachment edge to its free edge [3]. This variation in layer thicknesses is particularly evident in the AL, where the proximal third of the leaflet is marked by a very thick fibrosa, rich in highly aligned collagen and small leucine-rich proteoglycans, with only minor presence of the other layers. This region of the leaflet is also notable by an absence of underlying chordal insertions, and has been frequently denoted as the leaflet “clear zone.” The distal two-thirds of the AL, in contrast, do have chordal insertions and the corresponding name for this region is “rough zone.” The PL has chordal insertions underneath its entire surface and hence lacks a clear zone. The rough zones (AL middle and free edge, PL) have much more substantial spongiosa layers and hence are rich in hydrated proteoglycans and glycosaminoglycans such as hyaluronan [4].

Collagen fibers within the MV leaflets show a primary alignment along the circumferential direction of leaflets, which is largely responsible for the observed anisotropy in leaflet mechanical behavior (described below) [3,5,6]. These collagen fibers are highly crimped with a wavy form that is readily observable using a polarized light microscope (Fig. 1c). The crimped collagen fiber structure allows the leaflet tissue to undergo substantial deformation under even low levels of stress, a behavior that promotes the coaptation of the two leaflets in the closed valve. The cross-linked state of the collagen in atrioventricular valves is different from that of semilunar valves; hydrothermal isometric tension data indicates that the atrioventricular valve collagen has fewer overall crosslinks, which would allow more rapid remodeling than in the aortic and pulmonary valves [7].

Chordae tendineae primarily contain collagen that is highly aligned along the chordal length. Chordal collagen fibril diameters range from 40–70 nm [8] and adjacent collagen fibrils interact via small leucine-rich PGs to assemble into parallel fiber bundles with a wavy crimp pattern (period 10–20 μm , crimp angle 20–40°) [8]. Liao et al. recently showed that chordal collagen fibers are arranged in a skew-registered configuration and undulate in three dimensions, which better suits a rounded columnar structure than would a planar arrangement [9]. As with the MV leaflets, the highly crimped nature of the chordal collagen fibers permits an initial tissue deformation under very low loading. Another important ultrastructural feature of chordal collagen is that the fibril size and packing pattern vary with chordal type [8,9]. For example, marginal chordae have a smaller average fibril diameter, a higher fibril density, and a narrow fibril size distribution. In contrast, the basal and strut chordae exhibit a larger average fibril diameter, a lower fibril density, and a wider fibril size distribution.

Over the last several years there has been increasing attention paid to the vascular networks and innervations of the MV tissues. Pediatric and young adult valves have a well-defined vascular network in their leaflets [10] and chordae [11] although the vasculature is much

less in the valves of older adults [12]. These vessels are believed to supply nutrients to cells within diffusion-limited regions of these young valve tissues; their absence in older valves may be associated with the quiescent state of the older valvular interstitial cells (VICs). Furthermore, heart valves have a well defined network of nerve fibers that work together with the VICs to contract the valve tissue (recently reviewed by Borin et al. [13]). Both the vascular and innervation aspects of living valves represent challenges to be addressed in developing tissue engineered atrioventricular valves, particularly for the pediatric population.

Leaflet Mechanics

Numerous studies have characterized the nonlinear anisotropic mechanical behavior of the mitral valve leaflets [5,6,14–16]. The stress-strain curves of both leaflets can be described by three major regions: a relatively long, low slope “toe” region at the beginning, a nonlinear transition region following, and then a second linear region with a high slope (large tensile modulus) that functionally locks up further deformation. This long toe region is due to uncrimping of the collagen fibers, whereas the transitional region is due to collagen fiber recruitment, and the linear high slope region represents the behavior of the recruited, uncrimped collagen. Biaxial testing data also shows that the behavior of leaflets in the circumferential and radial directions is coupled, implying that collagen fibers are interacting at the microstructural level [6]. Both the anterior and posterior leaflets are stiffer and less extensible in the circumferential direction than in the radial direction. Additionally, leaflet stiffness in both directions is significantly increased with advancing age [16]. Furthermore, the PL tends to exhibit greater extensibility and lower tensile stiffness; one proposed explanation for this difference between leaflets is that the PL has more chordal attachments that provide additional mechanical support and therefore it does not require such high strength [6]. Numerous *in vivo* and *in vitro* studies have reported that there is also heterogeneity of mechanical behavior throughout individual leaflets [17,18]; for example, the clear zone of the AL has a circumferential tensile elastic modulus that is 30–200% higher than in the rough zone [14,16]. This distinction between the clear zone and rough zone stiffness was confirmed in an interesting study of mitral AL heterogeneity using scanning acoustic microscopy [19]; this same study also found that the speed of sound was higher (and hence the stiffness was greater) in the collagenous fibrosa layer than in the other layers of the mitral AL.

Viscoelasticity of connective tissues is commonly measured by stress relaxation, creep, and strain rate dependence tests. A recent study by Grashow et al. showed that the stress-strain responses of MV ALs were remarkably independent of a wide range of strain rates, including physiological strain rates [5]. The MV leaflets did show a small degree of hysteresis (approximately 12%) but that also did not vary with strain rate; this innate low level of hysteresis likely reduces energy dissipation during the cyclic opening and closing of the MV. Similar to other collagenous tissues, MV leaflets do exhibit significant stress relaxation [16,20]; although interestingly they exhibit negligible creep when subjected to a constant physiological level load over a 3-hour period [20]. This combination of stress relaxation, creep, and strain rate results appears to be unique in the soft tissue literature [20]. Liao et al. examined the molecular mechanism underlying this asymmetric viscoelasticity

and found that the microstructural processes differ between creep and stress relaxation [15]. When the leaflet samples were subjected to constant stress the collagen fibrils maintained a constant strain, but when subjected to constant strain the collagen fibril strain decreased over time, suggesting that some type of fibril-level “locking” mechanism exists to allow for stress release under constant strain conditions, but not under constant stress [15]. The above studies show that MV leaflets cannot be treated as classical viscoelastic materials. Rather, MV leaflets appear intrinsically designed at the fibril level to minimize creep and hysteresis, and behave more as “quasi-elastic” biological materials in a manner that favors valvular function [5,15,20]. Indeed, MV leaflets do not exhibit creep under full systolic loading *in vivo* [18]. Whether engineered tissue constructs are able to imitate this unique “quasi-elastic” behavior might be an important factor that affects the long-term durability of an engineered MV leaflet.

Chordal Mechanics

The marginal, basal, and strut chordae attach to the MV leaflets in different ways and correspondingly perform distinct mechanical roles in the opening and closing of the MV [21]. The strut chordae are the two thickest chordae, the basal chordae are thinner than strut chordae, and the marginal chordae are the thinnest [8]. Lomholt et al. reported that the strut and basal chordae bear higher systolic tension than do the marginal chordae [21]. From a functional perspective, marginal chordae (also known as primary chordae) are more involved in MV competence, whereas the strut and basal chordae (also known as secondary chordae) participate more in the governing the geometry and function of the left ventricle [22].

Many years ago, it was observed that chordae tendineae had an apparently paradoxical size-dependent mechanical behavior in that thinner chordae (i.e., marginal) were less extensible and more stiff than thick chordae (i.e., basal and strut) [14,23]. Further investigation by Liao et al. confirmed the trend of increasing extensibility with an increase in cross-sectional area, in the order of marginal, basal, and strut chordae [8], and additionally demonstrated the mechanism for this pattern by analysis of crimp periodicity. Thicker chordae had smaller crimp periods than thinner chordae ($11.3 \pm 1.4 \mu\text{m}$ vs. $14.8 \pm 3.0 \mu\text{m}$), and thus their collagen was more highly crimped (both had similar crimp amplitudes). Thicker chordae could therefore undergo greater strain before the collagen was uncrimped (i.e., greater extensibility). Chordal mechanics are also affected by the size and packing pattern of collagen fibrils, as shown by transmission electron microscopy (TEM). Even though the area percentage of collagen fibrils in thinner and thicker chordae is equal, the tensile modulus of thinner chordae is greater than that of thicker chordae [8]. TEM also shows that thinner chordae have lower average fibril diameter than thicker chordae but greater average fibril density. Therefore, the greater modulus of thinner chordae can possibly be explained by the greater number of interfibrillar interactions via small leucine-rich proteoglycans in these chordae; this explanation is supported both by quantitative measurements of glycosaminoglycan content and by the shear-lag theory of interfibrillar proteoglycans [8,24].

The chordal insertion zone represents another unique structural and mechanical aspect of the MV. Padala et al. reported a heterogeneous stretch distribution in the strut chordal insertion

region due to the complex collagen architecture spanning into the leaflet [25]. The strut chordal insertion region is also believed to stretch and bear load during both systolic and diastolic phases [25]. This important interface between chordae and leaflet might represent a challenge for MV tissue engineering in terms of structural continuity and material strength (comparable to the challenge of recreating the bone-tendon interface).

Cells

Valvular interstitial cells (VICs) have a well-recognized range of phenotypic characteristics. Although originally the phenotypic description of VICs had a primary emphasis upon their nearly uniform expression of fibroblast characteristics and less common but notable expression of smooth muscle features, over the last few years these phenotypic definitions have become more tailored. Recently, Gotlieb et al., summarized their phenotypes as quiescent, activated, progenitor, and osteoblastic (in the case of aortic VICs). The activated VICs, in particular, express smooth muscle α -actin (SM α A) and are responsible for repair and remodeling of the valve tissues; indeed, Stephens et al. reported that activated VICs located deep within the leaflet interior were always co-localized with regions of active collagen synthesis and/or degrading enzymes [26]. Furthermore, VICs within the mitral valve have been shown to be functionally coupled with collagen fibers via α 2 β 1 integrins connections to the actin cytoskeleton, and KCl-stimulated isometric force generation by the mitral VICs *in situ* can be blocked either by blocking the α 2 β 1 integrins with antibodies or blocking actin polymerization via cytochalasin [27].

Although VICs from the aortic valve have been characterized to a much greater extent than those from the mitral valve, mitral VICs have been shown to demonstrate some unique features. Merryman et al. reported that aortic and mitral VICs demonstrated comparable cell membrane stiffness, expression of SM α A, and expression of a molecular chaperone involved in collagen synthesis [28]. Additionally, both aortic and mitral VICs demonstrate a heterogeneous phenotype *in vitro* and *in vivo* [29–31]. However, mitral and aortic VICs respond differentially to cytokine stimulation: specifically, treatment with transforming growth factor- β (TGF- β) reduced proliferation by aortic VICs [32] but increased mitral VIC proliferation [33]. Similarly, actively migrating mitral VICs in an *in vitro* scratch wound model upregulate fibroblast growth factor-2 (FGF-2) and fibroblast growth factor receptor 1 [34] as well as greater expression of TGF- β and SM α A and phosphorylation of Smad2/3 [33]. This process appears to be different from aortic VICs in which FGF-2 inhibits TGF- β -mediated upregulation of SM α A expression [35].

The diverse anatomy and microstructural composition of the mitral valve is also reflected in the cell phenotype within these regions. Blevins et al. reported that VICs isolated from distinct anatomic regions of porcine MVs (specifically the AL clear zone, PL, and chordae) show heterogeneity in ECM synthesis, adhesion to substrates, and phenotype [31]. For example, PL cells grew faster than chordal cells, but demonstrated less SM α A, vimentin, and internal complexity, suggesting that the PL cells were less differentiated than the chordal cells [31]. These cells reside within a leaflet rich in GAGs and PGs and experience more compressive loading than do the cells within the chordae and AL clear zone [31]. When PL cells were divided into subpopulations by differential adhesion, the two

differentially adhesive cell groups did not demonstrate differential production of distinct GAG classes. This result was different from the results of the same method applied to VICs from the other 2 regions, in which the cells demonstrating stronger adhesion synthesized more sulfated GAGs. VICs from the AL clear zone exhibited the fastest metabolism but slowest growth, and also secreted less collagen into the culture medium but more 4-sulfated GAGs than other cells. This heterogeneity of phenotypic behavior of VICs across the valve structure is also shown by the valve remodeling in animal models of MR. In a sheep model of MR induced by tachycardia-induced cardiomyopathy, VICs from the middle regions of the mitral leaflets showed significant changes in activation and expression of matrix remodeling enzymes, whereas those VICs located more proximally to the annulus were less affected [36].

The differential adhesion result noted above [31], together with other studies [37–39] have led to the speculation that the mitral chordal cells are initially more responsive to their mechanical environment than the mitral leaflet cells. Gupta et al. have reported that both PL VICs and chordal VICs are influenced by stretch, in that the presence and magnitude of stretch applied to VICs cultured within a 3D collagen gel influences the retention of GAGs and PGs within the gel as well as the secretion of these ECM components into the culture medium [37–39]. Interestingly, chordal VICs subjected to constant stretch synthesized fewer GAGs than did PL VICs under the same culture conditions [38], which reflects the abundance of GAGs within actual chordal vs. leaflet tissue [4]. Two other studies found that chordal VICs responded to changes in applied stretch by altering their ECM synthesis in a more rapid manner [39] and were more affected by stretch magnitude [37] than were PL VICs. However, over time the PL VICs did show the ability to change the type of ECM produced in response to altered stretching conditions [39], indicating that despite their phenotypic heterogeneities, mitral VICs are all mechanosensitive. This latter point was recently demonstrated *in vivo* in a sheep model of ventricular dysfunction, mitral regurgitation, and abnormal mitral valve stresses caused by papillary muscle displacement and hence leaflet tethering [40]. Within 60 days, an endothelial-mesenchymal transdifferentiation response by the valve cells resulted in active remodeling, growth, and thickening of the chordae and MV leaflets. Overall, these studies make it evident that improving our understanding of MV biology and active adaptive mechanisms will greatly benefit the development of a TEMV.

Valvular endothelial cells (VECs) are also garnering attention, although the mitral VECs have not been investigated to the same extent as have aortic VECs. In recent studies by Flanagan et al., VECs were found to synthesize the basement membrane components laminin and type IV collagen, but not type I collagen and chondroitin sulfate [41]. VECs were also found to synthesize endothelial nitric oxide synthase (NOS) both *in vivo* and *in vitro*, in contrast with VICs, for which only a minority of cells expressed neuronal NOS *in vitro* [41]. These same authors found that growing mitral VECs on collagen-chondroitin sulfate scaffolds promoted a more *in vivo* like phenotype than did culture on collagen-only scaffolds [42]. It is also likely that mitral VECs will demonstrate a regionally-specific (leaflets, chordae) and/or side-specific (atrial, ventricular) phenotype much like that of aortic VECs [43]. Overall, these characterizations of the *in vitro* and *in vivo* phenotypes of

various MV cell populations can provide vital information for a MVTE, particularly for determining the ideal cell sources and effective scaffold designs to direct cell differentiation and function.

Towards a Tissue Engineered Mitral Valve

Thus far, only a handful of publications describe actual efforts to generate a tissue engineered mitral valve tissue. In an early stage effort to create a TEMV, Shi and Vesely focused on fabricating a simple tendinous structure that mimicked chordae tendineae. These constructs were generated by mixing smooth muscle cells with soluble collagen and allowing the cells to contract the collagen gel in response to tension induced by anchors in the culture dish [44]. Over several weeks this method produced a highly compact collagen construct with well-aligned dense, crimped collagen fibrils, an elastic fiber sheath around the collagen core, and nonlinear stress-strain behavior resembling tendinous tissues [44]. The material strength of these constructs was improved by applying bioreactor-controlled mechanical stimuli and by optimizing the shape and material employed in the construct anchors [45]. This approach was then extended to demonstrate more complex branching structures using either direct fabrication or culture-driven fusion of 2 single constructs [46].

Other publications demonstrate an active movement towards technology development to make TEMV endeavors possible. For example, investigators have developed sterile bioreactors that could be used for culturing tissue engineered or organ cultured mitral valves [37,39,47]. A new bioreactor system described by Lieber et al. is particularly interesting because it was designed for the culture of murine hearts at various ages (perinatal through adults) [48]. Although many of these culture systems are being currently used to investigate the biology and pathology of MV tissues and cells, these research efforts are nonetheless useful in developing design goals for a TEMV. Another promising direction for gaining insight into the development of TEMVs is to investigate the signaling pathways involved in embryonic development of the valves [49]. As noted above, it is also important to determine how valvular cells will respond to a TEHV scaffold; for example, valve cells can vary their phenotypes when they are cultured on substrates of different stiffness. Stephens et al. recently reported that mitral VICs show age-dependent and valve region-dependent levels of expression of SMAA, prolyl-4-hydroxylase, and heat shock protein 47 when cultured atop polyethylene glycol diacrylate hydrogels of different stiffnesses [50].

Conclusions

The MV demonstrates heterogeneity and the capacity for rapid cell-driven remodeling, both of which impose challenges and opportunities for developing a TEMV. These mechanical and structural heterogeneities mandate a careful design in order to match the structural and functional roles of the target MV components, and to maintain their relationships with other cardiac structures. A disruption of the native structural and mechanical balance of the MV might cause unfavorable remodeling in the leaflet or chordal tissues. On the other hand, the capability of MV tissues or engineered components to adapt could indicate a self-adjusting mechanism, in which positive adaptation would favor proper MV function.

Although the development of TEMVs is in its infancy compared to other engineered tissues, this time lag offers the opportunity to reflect upon the successes and failures of tissue engineered aortic valves. For example, are the polymer mesh scaffolds and acellular approaches that are so widely investigated for tissue engineered aortic valves appropriate for TEMVs? Are newer scaffold approaches such as electrospinning, smart biofunctional materials, or small intestinal submucosa feasible options? What cell source should be used in a TEMV, and how will the TEMV be assembled in order to recapitulate the diverse cell phenotypes found across the native MV? How should vasculature and innervation be addressed? Finally, how will the TEMV be implanted in a manner that maintains or restores the essential functions of the MV and its integral relationship with the left ventricle? These and other questions are certain to be addressed as investigators move towards a first generation prototype of a tissue engineered mitral valve.

Abbreviations

AL	anterior leaflet
ECM	extracellular matrix
FGF-2	fibroblast growth factor-2
MR	mitral regurgitation
MV	mitral valve
NOS	nitric oxide synthase
PL	posterior leaflet
SMαA	smooth muscle alpha-actin
TEM	transmission electron microscope
TEMV	tissue engineered mitral valve
TGF-β	transforming growth factor- β
VEC	valvular endothelial cell
VIC	valvular interstitial cell

References

1. Lloyd-Jones D, Adams RJ, Brown TM, et al. Heart disease and stroke statistics--2010 update: A report from the American Heart Association. *Circulation*. 2010; 121:e46–e215. [PubMed: 20019324]
2. Fedak PW, McCarthy PM, Bonow RO. Evolving concepts and technologies in mitral valve repair. *Circulation*. 2008; 117:963–974. [PubMed: 18285577]
3. Kunzelman KS, Cochran RP, Murphree SS, et al. Differential collagen distribution in the mitral valve and its influence on biomechanical behaviour. *J Heart Valve Dis*. 1993; 2:236–244. [PubMed: 8261162]
4. Stephens EH, Chu CK, Grande-Allen KJ. Valve proteoglycan content and glycosaminoglycan fine structure are unique to microstructure, mechanical load and age: Relevance to an age-specific tissue-engineered heart valve. *Acta Biomater*. 2008; 4:1148–1160. [PubMed: 18448399]

5. Grashow JS, Yoganathan AP, Sacks MS. Biaxial stress-stretch behavior of the mitral valve anterior leaflet at physiologic strain rates. *Ann Biomed Eng.* 2006; 34:315–325. [PubMed: 16450193]
6. May-Newman K, Yin FC. Biaxial mechanical behavior of excised porcine mitral valve leaflets. *Am J Physiol.* 1995; 269:H1319–1327. [PubMed: 7485564]
7. Aldous IG, Veres SP, Jahangir A, Lee JM. Differences in collagen cross-linking between the four valves of the bovine heart: A possible role in adaptation to mechanical fatigue. *Am J Physiol Heart Circ Physiol.* 2009; 296:H1898–1906. This work finds considerable differences in collagen crosslinking between the semilunar and atrioventricular valves, which may have implications for the fundamental distinctions between aortic valve disease (calcific) and mitral valve disease (myxomatous). [PubMed: 19329765]
8. Liao J, Vesely I. A structural basis for the size-related mechanical properties of mitral valve chordae tendineae. *J Biomech.* 2003; 36:1125–1133. [PubMed: 12831738]
9. Liao J, Priddy LB, Wang B, et al. Ultrastructure of porcine mitral valve chordae tendineae. *J Heart Valve Dis.* 2009; 18:292–299. [PubMed: 19557986]
10. Swanson JC, Davis LR, Arata K, et al. Characterization of mitral valve anterior leaflet perfusion patterns. *J Heart Valve Dis.* 2009; 18:488–495. This study is the first *in vivo* demonstration of perfusion of the blood vessels within the mitral valve leaflets and chordae. [PubMed: 20099688]
11. Ritchie J, Warnock JN, Yoganathan AP. Structural characterization of the chordae tendineae in native porcine mitral valves. *Ann Thorac Surg.* 2005; 80:189–197. [PubMed: 15975365]
12. Duran CM, Gunning AJ. The vascularization of the heart valves: A comparative study. *Cardiovasc Res.* 1968; 2:290–296. [PubMed: 5670736]
13. Borin C, Vanhercke D, Weyns A. Innervation of the atrioventricular and semi-lunar heart valves: A review. *Acta Cardiol.* 2006; 61:463–469. [PubMed: 16970058]
14. Kunzelman KS, Cochran RP. Stress/strain characteristics of porcine mitral valve tissue: Parallel versus perpendicular collagen orientation. *J Card Surg.* 1992; 7:71–78. [PubMed: 1554980]
15. Liao J, Yang L, Grashow J, Sacks MS. The relation between collagen fibril kinematics and mechanical properties in the mitral valve anterior leaflet. *J Biomech Eng.* 2007; 129:78–87. [PubMed: 17227101]
16. Stephens EH, de Jonge N, McNeill MP, et al. Age-related changes in material behavior of porcine mitral and aortic valves and correlation to matrix composition. *Tissue Eng Part A.* 2010; 16:867–878. [PubMed: 19814589]
17. Chen L, McCulloch AD, May-Newman K. Nonhomogeneous deformation in the anterior leaflet of the mitral valve. *Ann Biomed Eng.* 2004; 32:1599–1606. [PubMed: 15675673]
18. Sacks MS, Enomoto Y, Graybill JR, et al. In-vivo dynamic deformation of the mitral valve anterior leaflet. *Ann Thorac Surg.* 2006; 82:1369–1377. [PubMed: 16996935]
19. Jensen AS, Baandrup U, Hasenkam JM, et al. Distribution of the microelastic properties within the human anterior mitral leaflet. *Ultrasound Med Biol.* 2006; 32:1943–1948. [PubMed: 17169706]
20. Grashow JS, Sacks MS, Liao J, Yoganathan AP. Planar biaxial creep and stress relaxation of the mitral valve anterior leaflet. *Ann Biomed Eng.* 2006; 34:1509–1518. [PubMed: 17016761]
21. Obadia JF, Casali C, Chassignolle JF, Janier M. Mitral subvalvular apparatus: Different functions of primary and secondary chordae. *Circulation.* 1997; 96:3124–3128. [PubMed: 9386184]
22. Lomholt M, Nielsen SL, Hansen SB, et al. Differential tension between secondary and primary mitral chordae in an acute in-vivo porcine model. *J Heart Valve Dis.* 2002; 11:337–345. [PubMed: 12056724]
23. Lim KO, Boughner DR. Morphology and relationship to extensibility curves of human mitral valve chordae tendineae. *Circ Res.* 1976; 39:580–585. [PubMed: 963842]
24. Liao J, Vesely I. Skewness angle of interfibrillar proteoglycans increases with applied load on mitral valve chordae tendineae. *J Biomech.* 2007; 40:390–398. [PubMed: 16483580]
25. Padala M, Sacks MS, Liou SW, et al. Mechanics of the mitral valve strut chordae insertion region. *J Biomech Eng.* 2010; 132:081004. [PubMed: 20670053]
26. Stephens EH, Grande-Allen KJ. Age-related changes in collagen synthesis and turnover in porcine heart valves. *J Heart Valve Dis.* 2007; 16:672–682. [PubMed: 18095519]

27. Stephens EH, Durst CA, Swanson JC, et al. Functional coupling of valvular interstitial cells and collagen in the mitral leaflet. *Cell Mol Bioeng.* 2010; 3:428–437.
28. Merryman WD, Youn I, Lukoff HD, et al. Correlation between heart valve interstitial cell stiffness and transvalvular pressure: Implications for collagen biosynthesis. *Am J Physiol Heart Circ Physiol.* 2006; 290:H224–231. [PubMed: 16126816]
29. Rabkin E, Aikawa M, Stone JR, et al. Activated interstitial myofibroblasts express catabolic enzymes and mediate matrix remodeling in myxomatous heart valves. *Circulation.* 2001; 104:2525–2532. [PubMed: 11714645]
30. Taylor PM, Batten P, Brand NJ, et al. The cardiac valve interstitial cell. *Int J Biochem Cell Biol.* 2003; 35:113–118. [PubMed: 12479860]
31. Blevins TL, Peterson SB, Lee EL, et al. Mitral valvular interstitial cells demonstrate regional, adhesional, and synthetic heterogeneity. *Cells Tissues Organs.* 2008; 187:113–122. [PubMed: 17851228]
32. Walker GA, Masters KS, Shah DN, et al. Valvular myofibroblast activation by transforming growth factor-beta: Implications for pathological extracellular matrix remodeling in heart valve disease. *Circ Res.* 2004; 95:253–260. [PubMed: 15217906]
33. Liu AC, Gotlieb AI. Transforming growth factor-beta regulates in vitro heart valve repair by activated valve interstitial cells. *Am J Pathol.* 2008; 173:1275–1285. [PubMed: 18832581]
34. Gotlieb AI, Rosenthal A, Kazemian P. Fibroblast growth factor 2 regulation of mitral valve interstitial cell repair in vitro. *J Thorac Cardiovasc Surg.* 2002; 124:591–597. [PubMed: 12202876]
35. Cushing MC, Mariner PD, Liao JT, et al. Fibroblast growth factor represses smad-mediated myofibroblast activation in aortic valvular interstitial cells. *Faseb J.* 2008; 22:1769–1777. [PubMed: 18218921]
36. Stephens EH, Timek TA, Daughters GT, et al. Significant changes in mitral valve leaflet matrix composition and turnover with tachycardia-induced cardiomyopathy. *Circulation.* 2009; 120:S112–119. [PubMed: 19752355]
37. Gupta V, Tseng H, Lawrence BD, Grande-Allen KJ. Effect of cyclic mechanical strain on glycosaminoglycan and proteoglycan synthesis by heart valve cells. *Acta Biomater.* 2009; 5:531–540. [PubMed: 19004676]
38. Gupta V, Werdenberg JA, Blevins TL, Grande-Allen KJ. Synthesis of glycosaminoglycans in differently loaded regions of collagen gels seeded with valvular interstitial cells. *Tissue Eng.* 2007; 13:41–49. [PubMed: 17518580]
39. Gupta V, Werdenberg JA, Lawrence BD, et al. Reversible secretion of glycosaminoglycans and proteoglycans by cyclically stretched valvular cells in 3d culture. *Ann Biomed Eng.* 2008; 36:1092–1103. [PubMed: 18425579]
40. Dal-Bianco JP, Aikawa E, Bischoff J, et al. Active adaptation of the tethered mitral valve: Insights into a compensatory mechanism for functional mitral regurgitation. *Circulation.* 2009; 120:334–342. This investigation builds on previous studies of mitral valve remodeling in functional mitral regurgitation by demonstrating that the valvular cells undergo a reactivation of embryonic remodeling pathways. [PubMed: 19597052]
41. Flanagan TC, Black A, O'Brien M, et al. Reference models for mitral valve tissue engineering based on valve cell phenotype and extracellular matrix analysis. *Cells Tissues Organs.* 2006; 183:12–23. [PubMed: 16974091]
42. Flanagan TC, Wilkins B, Black A, et al. A collagen-glycosaminoglycan co-culture model for heart valve tissue engineering applications. *Biomaterials.* 2006; 27:2233–2246. [PubMed: 16313955]
43. Simmons CA, Grant GR, Manduchi E, Davies PF. Spatial heterogeneity of endothelial phenotypes correlates with side-specific vulnerability to calcification in normal porcine aortic valves. *Circ Res.* 2005; 96:792–799. [PubMed: 15761200]
44. Shi Y, Vesely I. Characterization of statically loaded tissue-engineered mitral valve chordae tendineae. *J Biomed Mater Res A.* 2004; 69:26–39. [PubMed: 14999748]
45. Vesely I, Shi Y, Dobkin D, et al. Progress in developing a composite tissue-engineered aortic valve. *Conf Proc IEEE Eng Med Biol Soc.* 2005; 7:7129–7130. [PubMed: 17281919]

46. Shi Y, Rittman L, Vesely I. Novel geometries for tissue-engineered tendonous collagen constructs. *Tissue Eng.* 2006; 12:2601–2609. [PubMed: 16995793]
47. Gheewala N, Grande-Allen KJ. Design and mechanical evaluation of a physiological mitral valve organ culture system. *Cardiovasc Eng Technol.* 2010; 1:123–131.
48. Lieber SC, Kruithof BP, Aubry N, et al. Design of a miniature tissue culture system to culture mouse heart valves. *Ann Biomed Eng.* 2010; 38:674–682. This new bioreactor device will allow the in vitro culture of a mouse heart. Using this system, scientists can leverage the enormous range of knockout and transgenic mouse models of cardiovascular and other diseases to understand the impact of these genes on the biology and pathology of heart valves and other cardiac tissues. [PubMed: 20099034]
49. Chiu YN, Norris RA, Mahler G, et al. Transforming growth factor beta, bone morphogenetic protein, and vascular endothelial growth factor mediate phenotype maturation and tissue remodeling by embryonic valve progenitor cells: Relevance for heart valve tissue engineering. *Tissue Eng Part A.* 2010; 16:3375–3383. This work exemplifies the innovative combination of developmental biology and bioengineering strategies to understand the remodeling principles that are desired in the regeneration of replacement tissues. These approaches can also be used to investigate pathological remodeling of heart valves, since it is believed that some valve disease mechanisms may invoke regression to embryonic phenotypes. [PubMed: 20629541]
50. Stephens EH, Durst CA, West JL, Grande-Allen KJ. Mitral valvular interstitial cell responses to substrate stiffness depend on age and anatomic region. *Acta Biomater.* 2011; 7:75–82. [PubMed: 20624493]

Fig. 1.

a, Photograph of a mitral valve cut open and viewed from the ventricular side to demonstrate the anterior and posterior leaflets and the chordae tendineae. **b,** Layered mitral valve microstructure shown in a radially oriented cross-section stained with Movat pentachrome, which colors elastic fibers black, hydrated proteoglycans and glycosaminoglycans blue, and collagen yellow. F = fibrosa; S = spongiosa; A = atrialis. **c,** Polarized light micrographs of mitral valve leaflet cross-section (in the “clear zone”) showing crimped nature of collagen in the fibrosa. The ventricularis is a thin layer of elastic fibers and loose collagen on the outflow surface of the mitral valve leaflet.