Published in final edited form as:

Biomaterials. 2015 November ; 69: 110–120. doi:10.1016/j.biomaterials.2015.07.064.

Enabling Non-invasive Assessment of an Engineered Endothelium on ePTFE Vascular Grafts without Increasing Oxidative Stress

Bin Jiang, Ph.D.^{1,2}, Louisiane Perrin, B.S.¹, Dina Kats, B.S.³, Thomas Meade, Ph.D.⁴, and Guillermo Ameer, Sc.D.^{1,2,*}

¹ Biomedical Engineering Department, Northwestern University, Evanston, IL, 60201

² Department of Surgery, Northwestern University Feinberg School of Medicine, Chicago, IL, 60611.

³ Interdisciplinary Biological Sciences (IBiS) Program, Northwestern University, Evanston, IL, 60201

⁴ Department of Chemistry, Northwestern University, Evanston, IL 60201

Abstract

Magnetic resonance imaging (MRI) in combination with contrast enhancement is a potentially powerful tool to non-invasively monitor cell distribution in tissue engineering and regenerative medicine. The most commonly used contrast agent for cell labeling is super paramagnetic iron oxide nanoparticles (SPIONs). However, uptake of SPIONs triggers the production of reactive oxygen species (ROS) in cells often leading to a pro-inflammatory phenotype. The objective of this study was to develop a labeling system to non-invasively visualize an engineered endothelium in vascular grafts without creating excessive oxidative stress. Specifically, we investigated: (1) chitosan-coated SPIONs (CSPIONs) as an antioxidant contrast agent for contrast enhancement, and (2) poly(1,8-octamethylene citrate) (POC) as an antioxidant interface to support cell adhesion and function of labeled cells on the vascular graft. While SPION-labeled endothelial cells (ECs) experienced elevated ROS formation and altered cell morphology, CSPION-labeled ECs cultured on POC-coated surfaces mitigated SPION-induced ROS formation and maintained EC morphology, phenotype, viability and functions. A monolayer of labeled ECs exhibited sufficient contrast with T₂-weighed MR imaging. CSPION labeling of endothelial cells in combination with coating the graft wall with POC allows non-invasive monitoring of an engineered endothelium on ePTFE grafts without increasing oxidative stress.

*Corresponding author: Guillermo A. Ameer, Sc.D., 2145 Sheridan Road, Tech B382, Evanston, IL 60208-3107, Tel: +1-847-467-2992, Fax: +1-847- 491-4928, g-ameer@northwestern.edu.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Keywords

Super paramagnetic iron oxide nanoparticles (SPIONs); Endothelial cells (ECs); Reactive oxygen species (ROS); Chitosan; poly (1,8-octanediol-co-citric acid) (POC); Magnetic resonance imaging (MRI)

1. Introduction

An intact endothelium plays a variety of critical roles in proper vascular functions, including selective barrier and filtration, thrombosis prevention, and inflammation mediation.[1] In vascular tissue engineering, endothelial cells (ECs) are often seeded onto the lumen of a tubular scaffold to recreate the endothelium of a normal blood vessel.[2] For these strategies to work, it is important to monitor the presence and distribution of seeded ECs in tissue-engineered blood vessels both before and after surgical implantation to ensure an intact endothelium formation within a vascular graft. Therefore, a non-invasive method to monitor ECs would be a very useful tool for translational research.

Magnetic resonance imaging (MRI) in combination with contrast agents has been used to track live cells both *in vitro* and *in vivo*. [3] Super paramagnetic iron oxide nanoparticles (SPIONs) of different sizes and surface chemistry have been widely used as MRI contrast agents for cell labeling because they produce regions of low intensity (dark areas) in MRI images.[4] Although SPIONs have been used to label a wide variety of cell types, recent studies have found some adverse effects on cell functions.[5, 6] Potential toxicity arises from the leaching of iron ions and the production of excess reactive oxygen species (ROS), leading to the oxidation of lipids and proteins. [5] In particular, SPIONs have been reported to cause problems when used on vascular cells.[7-9] For example, several different types of SPIONs were found to impair endothelial integrity, inhibit nitric oxide production, change EC morphology and mechanics, and induce cell apoptosis and autophagy. [7-9]

To address this problem, we investigate the use of antioxidant polymers to modify both the nanoparticle's surface and the substrate used for EC attachment. We chose chitosan as an antioxidant coating for the SPIONs and poly (1,8 octamethylene citrate) (POC) as an antioxidant coating for the graft surface. Chitosan is a naturally-derived linear polysaccharide that exhibits positive charge, antimicrobial, and antioxidant properties.[10, 11] Chitosan has been used in a wide range of biomedical applications, such as scaffolds for tissue engineering, drug delivery systems, and wound dressings.[12] Although others have used chitosan to coat nanoparticles, the ability of chitosan to reduce SPION-mediated ROS has not been investigated. [13, 14] POC is a citric acid-based biodegradable elastomer that has been used to facilitate EC adhesion on vascular grafts, improve graft hemocompatibility, and provide antioxidant characteristics to the lumen of vascular grafts, potentially reducing neointimal hyperplasia.[15-19] Therefore, we hypothesized that the use of both chitosan and POC would counteract oxidative stress in the EC.

In this study, we aim to assess whether chitosan-coated SPIONs (CSPIONs) are a suitable labeling agent to image a single layer of ECs cultured on POC-coated surfaces using MRI. We report the effect of CSPION labeling on ROS production, EC viability, morphology,

phenotype, and functions and for the first time show that CSPION labeling produces enough contrast to allow the imaging of an EC monolayer without altering cell viability or functions.

2. Materials and Methods

2.1 Nanoparticle preparation and characterization

2.1.1 Particle synthesis—All chemicals were obtained from Sigma-Aldrich unless specified otherwise. SPIONs coated with low molecular weight chitosan were synthesized following a protocol previously described by Tsai et al.[14] Briefly, Iron chlorides (Fe^{3+} , 37 mM and Fe^{2+} , 22.5 mM) were co-dissolved with low molecular weight chitosan (50~190 kDa, 2 mg/mL) in acetic acid solution (0.5% v/v). The solution was reacted with ammonium hydroxide (25 wt%) under sonication at 50 °C to co-precipitate the iron oxide nanoparticles with a chitosan coating. After washing with water, the particles were re-suspended in water, with mannitol and lactic acid added as stabilizers, and pH adjusted to 3.0. As a control group, SPIONs were synthesized by following the synthesis procedure for CSPIONs but omitting the addition of chitosan.

2.1.2 Particle characterization—The iron concentration in the CSPION stock suspension was determined with inductively coupled plasma mass spectrometry (ICP-MS) after dissolving the particles in 70% nitric acid.[20] The size and charge distribution of CSPIONs were determined with dynamic light scattering (DLS) using NanoBrook Omni Particle Sizer and Zeta Potential Analyzer (Brookhaven Instruments Corporation, Holtsville, NY). The particles were suspended in DI water or Endothelial Growth Medium 2 (EGM-2, Lonza, Walkersville, MD) at 20 $\mu\text{g/mL}$ prior to measurement. The particles were imaged with transmission electron microscopy (TEM) using JEOL JEM-2100 FasTEM (JEOL Ltd, Tokyo, Japan). To measure the particle T_2 relaxivity (R_2), several concentrations of CSPIONs were firstly analyzed with Bruker Minispec mq60 NMR analyzer (Bruker Corporation, Billerica, MA) to obtain T_2 values, and then compared with ICP-MS for corresponding iron concentration in each sample. R_2 was calculated as the slope of linear regression when plotting T_2^{-1} (s^{-1}) vs. Iron concentration (mM).

2.2 POC synthesis and coating on cell culture surfaces

POC prepolymer was synthesized using equal molar amounts of citric acid and 1,8-octanediol as described previously. [17] The prepolymer was firstly dissolved in absolute ethanol at 10 wt% and added to tissue culture multi-well plates (Corning®, Lowell, MA) at 10 mg/cm^2 , or perfused through 5 mm diameter ePTFE vascular grafts (Vascutek, Somerset, NJ) using a syringe pump set at 1 mL/min flow rate. After ethanol evaporation, the plates or grafts with POC prepolymer were post-polymerized at 80°C for 4 days. POC-coated plates or grafts were sterilized with a gas sterilizer overnight and then incubated in sterile PBS at 37 °C for 3 days to remove non-crosslinked low molecular weight POC prepolymer. POC-coated surfaces were used for all cell culture experiments unless specified otherwise.

2.3 Cell cultures

2.3.1 EC labeling with the nanoparticles—Human umbilical vein endothelial cells (HUVECs, Lonza) from passage 3 to passage 8 were cultured in endothelial growth

medium-2 (EGM-2, Lonza) using standard tissue culture practice. HUVECs were seeded onto POC-coated multiwell plates at 10,000 cells/cm² and incubated overnight with various concentrations of CSPIONs or SPIONs in EGM-2. The cell culture medium was changed every 2 to 3 days for up to 1 month.

2.3.2 Cell iron uptake—Particle distribution in cells with varying CSPIONs or SPIONs concentration (0 to 5 mM) was determined via Prussian blue staining for iron. Briefly, the cells were fixed with paraformaldehyde 24 hours after particle labeling, washed with PBS, and incubated in 5% potassium ferrocyanide with 10% hydrochloric acid. Any iron present in the cells reacts with the ferrocyanide and results in the formation of the bright blue pigment Prussian blue. Phase contrast microscopy (Nikon TE2000U, Japan) was then used to image the stained cells with a 10× objective. To quantitatively analyze iron concentration in cells, CSPION- or SPION-labeled HUVECs seeded in 12-well plates (n=4) were firstly trypsinized and counted for cell number. The trypsinized cells were lysed with TES lysis buffer in combination with HCl and HNO₃ (100 µl/well) to dissolve the particles by incubating at 65°C overnight. The iron concentration was then determined colorimetrically using UV spectrometer at 700 nm after adding equal volume of 5% potassium ferrocyanide. [21] Iron chloride (FeCl₃*6H₂O) was used for preparing standard solutions. The results were normalized with cell number as picomol (pmol) of iron per cell.

2.3.3 Cell morphology—Cell morphology with CSPION/SPION labeling was evaluated with Alexa Fluor® 488 Phalloidin (Life Technologies, Carlsbad, CA) staining for filamentous actin, following the manufacturer's protocol. The cells were counter stained with Hoechst dye to visualize cell nuclei. Fluorescence microscopy (20× objective, Nikon TE2000U, Japan) was used to image the Phalloidin and Hoechst staining with a blue and UV filter, respectively.

2.3.4 ROS formation—ROS formation within cells was assessed using cell-permeable 2', 7'-dichlorodihydrofluorescein diacetate (DCF-DA) (Life Technologies, Carlsbad, CA) following the manufacturer's instructions. HUVECs were seeded at 10,000 cells/cm² onto 48-well plates without or with a 10 wt% POC in ethanol coating and labeled with 0 mM, 0.25 mM and 0.5 mM CSPIONs or SPIONs. After washing twice with PBS, half of the cells from each group were treated with 0.03% H₂O₂ in EGM-2 for 30 minutes to create a high oxidative stress condition, while the other half was kept in regular cell culture medium (EGM-2). DCF-DA (1 µM in PBS) was added to each well for 60 minutes before reading with a fluorescence spectrometer (Ex 495 nm, Em 520 nm). Cells without DCF-DA labeling were used to assess baseline autofluorescence.

2.3.5 Cytotoxicity—The effect of CSPION uptake on cell viability was accessed via MTT assay (Sigma-Aldrich, St. Louis, MO) using the manufacturer's protocol. The assay was performed at 1 day, 1 week and 1 month after CSPION labeling to assess the short term and long term cytotoxicity.

2.3.6 Inflammatory status—EC inflammatory status was determined using a cell-based ELISA for ICAM-1, VCAM-1 and E-selectin.[22] Briefly, HUVECs were seeded onto POC-coated 96-well plates and labeled with 0 mM, 0.25 mM or 0.5 mM CSPIONs in

EGM-2 (n=4). At 1 day, 1 week and 1 month after CSPION labeling, the cells were fixed with 4% formaldehyde and quantified for the expression of ICAM-1, VCAM-1 and E-selectin using commercially available ELISA kits (ScienCell™ Research Laboratories, Carlsbad, CA).

2.3.7 EC phenotype—EC phenotype was determined by probing for the cell surface marker CD31 (PECAM) as well as acetylated low-density lipoprotein (Ac-LDL) uptake using flow cytometry analysis. For CD31 analysis, HUVECs labeled with 0 mM, 0.25 mM or 0.5 mM CSPIONs were harvested (200,000 cells per group), washed with 0.2% BSA/PBS and coated with 5% FBS on ice. For each group, half of the cells were stained with FITC-conjugated PECAM antibody (1:200 dilution, Sigma-Aldrich, St Louis, MO), while the other half were stained with FITC-IgG isotype control (1:200 dilution, Sigma-Aldrich, St Louis, MO). The cells were washed twice with 0.2% BSA/PBS buffer prior to flow cytometry. For Ac-LDL uptake, 100,000 cells exposed to varying amounts of CSPION were incubated with 10 µg/mL Alexa Fluor® 488 Conjugated Ac-LDL (Life Technologies, Carlsbad, CA) for 1 hour, after which the cells were harvested and washed with 0.2% BSA/PBS. The same number of cells without Ac-LDL labeling from each group served as a negative control.

2.3.8 Nitric oxide production—Nitric oxide formation within cells was assessed using cell-permeable 4,5-Diaminofluorescein-Diacetate (DAF2-DA) (Life Technologies, Carlsbad, CA). Briefly, 100,000 HUVECs labeled with varying amounts of CSPION were incubated with 10 µM DAF2-DA in PBS for 30 min, after which the cells were harvested and washed with 0.2% BSA/PBS. Cells without DAF2-DA from each group served as a negative control.

2.3.9 Flow cytometry—All flow cytometry was performed at Northwestern University Flow Cytometry Core (Evanston, IL) on a BD LSR II flow cytometer (BD Biosciences, San Jose, CA) using 488nm excitation wavelength. For each sample, data from a minimum number of 10,000 cells were obtained. The data were exported as FCS files and analyzed with FlowJo (Ashland, OR). Three independent replicates were performed for each experiment (n=3). The same gating was used for all samples to analyze the percentage of positive cells in the stained group (CD31+, Ac-LDL+ or DAF2-DA+).

2.3.10 Clotting kinetics—Re-calcified whole blood clotting time assay was used to assess the thrombogenicity of CSPIONs.[15] Anti-coagulated pig whole blood was obtained from a local abattoir (Chicago, IL). HUVECs were seeded into POC-coated 12-well plates and allowed to grow to confluency. CSPIONs concentrations of 0 mM, 0.25 mM and 0.5 mM were used to label the cells (n=3). Cells were rinsed with PBS and 100 µl whole blood containing 0.1M CaCl₂ were added to each well. At each time point (0, 5, 10, 20 and 30 min), 3 mL of milli-Q water were added to each well. After 5 min incubation to allow free hemoglobin to diffuse from non-coagulated blood, the concentration of hemoglobin was measured via spectrophotometry at 540 nm. The data were converted to percent clotting by normalizing to the maximum absorbance reading (0 % clotted) and the minimum absorbance reading (100 % clotted).

2.4 Magnetic contrast assessment

All MRI images were acquired at the Center for Advanced Molecular Imaging (CAMI), Northwestern University (Evanston, IL). T₂-weighed images of CSPIONs and of CSPION-labeled HUVECs were acquired using a 7T Bruker PharmaScan MRI system (Billerica, MA). The following samples were prepared for imaging.

2.4.1 CSPION suspension—CSPIONs were diluted with PBS at 0 mM, 0.25 mM, and 0.5 mM and filled in 15 mL conical tubes. The solutions were sonicated for 5 minutes at room temperature to eliminate any air bubbles that might cause false positive during imaging. All tubes were imaged at the same time using the same setting to allow direct comparison within the same images.

2.4.2 HUVEC aggregates—HUVECs labeled with 0 mM, 0.25 mM, or 0.5 mM CSPIONs were trypsinized and seeded into a 96-well round-bottom low-attachment plate with 10,000 cells/well. Cell aggregates formed overnight and were harvested, washed with PBS and embedded in 1% agarose gel.

2.4.3 ePTFE grafts—HUVECs labeled with 0 mM, 0.25 mM, or 0.5 mM CSPIONs were seeded into the lumen of POC-coated ePTFE grafts (2-4 cm long, 5mm in diameter) with 10,000 cells/cm² seeding density. Cells were labeled prior to seeding to reduce non-specific binding between CSPIONs and the surfaces. ePTFE grafts with 0% and 10% POC coating with no cells were also imaged as control grafts. All samples were embedded in 1% agarose gel before imaging.

2.4.4 Post-imaging processing—All MR images were exported as DICOM images from the 7T system, and processed with ImageJ software (NIH, Bethesda, MD). For cell-seeded ePTFE grafts, 3D volume rendering was performed by stacking 8 of the 2D scans to and illustrate the various 3D planes.

2.5 Statistical Analysis

All data were expressed as mean± standard deviation. Data were analyzed using one-way ANOVA with a Tukey-Kramer post test using SigmaStat (San Jose, CA). For all comparisons, p<0.05 was considered statistically significant.

3. Results

3.1 Particle characterization

In this study, CSPIONs were synthesized using an *in situ* coating method with low molecular weight chitosan as described previously.[14] As a control, SPIONs without chitosan coating were synthesized using the same protocol without chitosan. The CSPION product is a black nanoparticle-water suspension, which remained stable for more than a year under acidic condition (pH 3.0), in the presence of mannitol and lactic acid as stabilizers. On the other hand, SPIONs without chitosan coating suspended in the same solution as CSPIONs resulted in phase separation of black precipitation at the bottom layer and clear solution at the top layer.

CSPIONs were spherical in shape based on TEM imaging (Figure 1.A). Although the individual particle size appeared to be smaller than 20 nm, they formed aggregates with a z-average diameter of 172.6 ± 3.2 nm (PDI 0.344 ± 0.053) in water measured by DLS. (Table 1) SPIONs without chitosan coating resulted in particles with z-average diameter of 596.5 ± 47.7 nm (PDI 0.281 ± 0.112), due to aggregates formation in the absence of the chitosan, which works as a surfactant. To take into account the protein corona effect [23], the particles were also incubated in endothelial cell growth medium EGM-2, containing 2% FBS. Both CSPIONs and SPIONs in EGM-2 formed larger aggregates approximately twice the diameter of particles in water, with z-average diameter of 368.5 ± 78.45 nm (PDI 0.291 ± 0.019) and 1015.1 ± 126.0 nm (PDI 0.303 ± 0.035) for CSPIONs and SPIONs, respectively.

CSPIONs exhibited a positive charge in water (zeta potential 49.1 ± 1.2 mV, Table 1), which was higher than that of SPIONs (17.6 ± 5.0 mV) in water due to chitosan coating. However in EGM-2, both CSPIONs and SPIONs exhibited negative surface charges (-6.8 ± 0.2 mV and -8.3 ± 0.9 mV for CSPION and SPION, respectively), possibly due to the effects of pH (7.4) and corona effect of albumin [23]. T_2 relaxivity (R_2) value of CSPIONs was measured to be 158.1 ± 6.7 mM⁻¹ s⁻¹, which is comparable to or higher than that of most commercially available SPIONs (e.g. Feridex $R_2=128$ mM⁻¹ s⁻¹[24]). T_2 MRI phantom images showed reduced T_2 relaxation (dark images) with increasing CSPION concentration in PBS. (Figure 1. B)

3.2 Cell iron uptake

Prussian blue staining demonstrated the CSPIONs (Figure 2, A, C, E) and SPIONs (Figure 2, B, D, F) distribution in HUVECs at varying loading concentration (0.25 mM, 0.5 mM and 1 mM). Increased iron particle density was observed with increasing CSPION and SPION loading concentration. Cell iron concentration analysis showed increased iron concentration per cell with increasing CSPION and SPION loading concentration up to 1 mM, with no significant difference in cell iron concentration between CSPION and SPION labeling (Figure 2.G). CSPIONs that were internalized in cells remained in cells for up to 1 month in culture (Supplemental Figure 1), suggesting the feasibility of long-term non-invasive imaging.

At higher loading concentrations, cell iron uptake plateaued at 1 mM for CSPION, and at 2.5 mM for SPION. (SPIONs 14.6 ± 4.8 pmol/cell vs CSPIONs 4.2 ± 2.5 pmol/cell at 2.5 mM loading concentration, Supplemental Figure 2. A) Viable cell numbers quantified during iron uptake assay revealed significant lower percentage of viable cells with SPION loading concentration 1 mM, while no significant difference with CSPION labeling (Supplemental Figure 2. B).

Cell morphology was evaluated at 0 mM, 0.25 mM, 0.5 mM and 1 mM CSPION or SPION loading concentrations. Phalloidin/Hoechst staining showed no obvious alteration with CSPION labeling (Figure 3, A, C, E, G). However, SPION labeling (Figure 3, B, D, F, H) induced an elongated morphology at high concentration (0.5 mM, Figure 3, F, H), similar to observations made by Buyukhatipoglu et al.[8]

3.3 ROS production in the cell

At the nanoparticle loading concentrations studied, SPION- and CSPION- labeled HUVECs had similar cellular iron concentrations (Figure 2. G) and therefore ROS levels were compared. HUVECs with SPION labeling on tissue culture plastic (TCP) surfaces showed significant increase of ROS formation with increasing SPION labeling concentration, regardless of the exogenous oxidative stress conditions (with or without H₂O₂). (Figure 4.A) The presence of 0.03% H₂O₂ caused 4.9 to 8.8-fold increase in cell ROS formation compared to normal (0% H₂O₂). SPION labeled HUVECs that were seeded on POC-coated surfaces still showed increased ROS formation with 0.5 mM SPION loading concentration but not 0.25 mM (Figure 4. B). The presence of exogenous H₂O₂ still caused 3.3 to 5.8- fold increase in cell ROS formation compared to normal culture condition. The overall ROS for SPION labeled cells on POC surfaces was 75% lower than cells cultured on TCP.

CSPION labeling of HUVECs on TCP, did not increase ROS under low oxidative stress condition (0% H₂O₂). (Figure 4.C) Under high oxidative stress condition (0.03% H₂O₂), increased ROS formation was observed with increasing CSPION labeling concentration. There was a 4.9 to 6.8-fold increase in ROS formation induced by exogenous hydrogen peroxide. HUVECs labeled with CSPIONs that were seeded on POC-coated surfaces showed no increase in ROS formation under low oxidative stress conditions (0% H₂O₂) (Figure 4.D) and under high oxidative stress conditions (0.03% H₂O₂), the increase was only 1.2 to 1.9-fold relative to baseline (0% H₂O₂) and 85% lower relative to cells cultured on TCP.

Overall, the chitosan coating of the iron oxide nanoparticles successfully attenuated cell ROS formation under normal oxidative stress condition (0% H₂O₂). (Figure 4. C, D) Although CSPIONs can induce a dose dependent increase in ROS in cells under high oxidative stress condition (0.03% H₂O₂), the effect was significantly mitigated with the presence of the POC. CSPION labeled cells cultured on POC-coated surfaces had a 35% decrease in cell ROS levels compared to cells cultured on TCP with 0% H₂O₂ and an 85% decrease in ROS for cells exposed to 0.03% H₂O₂. The combination of CSPIONs and POC scavenge ROS, potentially counteracting the cytotoxic adverse effects caused by iron oxide.

3.4 Effects of nanoparticle labeling on EC viability, differentiation, function, and inflammatory status

CSPION labeling did not affect cell viability. (Figure 5.A) VCAM-1 (Figure 5.B), ICAM-1 (Figure 5.C) and E-Selectin (Figure 5.C) expression were increased when using the 0.5 mM CSPION concentration; however, the effect was short lived as this increase was not observed in cells that were cultured for 30 days. CD31 expression, Ac-LDL uptake, and nitric oxide production, assessed 24 hours after CSPION labeling, were not affected by CSPION labeling as values were comparable to those of non-labeled HUVECs (Figure 6, A-J). Also, clotting kinetics, assessed 24 hours after CSPION labeling, were not affected by CSPION labeling (Figure 6.K, n=3), indicating no additional pro-thrombogenic effect due to the CSPIONs.

3.5 Magnetic contrast assessment

HUVEC spheroids (10,000 cells/spheroid) labeled with various concentrations of CSPIONs were imaged using T_2 relaxation time. (Supplemental Figure 3) A direct correlation was observed between increased CSPIONs labeling and degree of visualization of the cell spheroids. All samples had the same number of spheroids embedded in the same plane; therefore, only HUVECs labeled with the 0.5 mM CSPIONs were seeded onto ePTFE grafts.

Prior to cell seeding, bare ePTFE grafts were imaged for the baseline level of T_2 contrast of the material itself. (Figure 7) Due to the highly hydrophobic nature and highly porous structure of ePTFE, the graft wall trapped air when embedded in 1 % agarose hydrogel. T_2 images showed completely dark contrast of the ePTFE walls (Figure 7. A, C), which is problematic for cell visualization given that CSPION-labeled cells would also exhibit a dark contrast under T_2 . However, after application of the POC coating (10% polymer solution), the ePTFE grafts became hydrophilic, allowing water to permeate throughout the porous wall and as a result brightening the T_2 image of the graft. (Figure 7. B, D) Therefore, 10 % POC coating was used for all cell-seeded ePTFE grafts.

HUVECs seeded on POC-ePTFE grafts were imaged at different depths (z-direction) and stacked for 3D volume rendering using ImageJ. POC-ePTFE grafts can be easily detected in T_2 images, regardless of cell seeding or CSPION labeling. (Figure 8, A-D, yellow boxes) However, for grafts that had HUVECs without CSPION labeling, the graft wall appeared as a light gray color (Figure 8.A and C). CSPION-labeled HUVECs showed up as a dark shadow on ePTFE grafts, and were visible from both outside (Figure 8. B) and at the cross-section of the graft (Figure 8. D), suggesting sufficient contrast for visualizing seeded ECs. H&E staining confirmed the presence of a HUVEC monolayer on the grafts (Figure 8. E, F).

4. Discussion

Endothelium is in direct contact with blood flow and its integrity is critical to the blood vessel's function. [25] Seeding ECs onto biological [26, 27] or synthetic [28, 29] vascular scaffolds is an intriguing strategy to reduce thrombosis and potentially improve graft patency. One of the challenges for this approach is the facile monitoring of EC coverage before and after implantation in the patient. Traditionally, researchers have relied mostly on histology and/or scanning electron microscopy to assess EC coverage on the graft. However, these methods are destructive and a very costly proposition to enabling widespread application.

To date, there is no reliable non-invasive method to clinically assess the presence, distribution, or function of ECs that are seeded within a vascular graft. The work described is a first step toward the goal of non-destructive assessment of an engineered endothelium within a vascular graft. Non-invasive assessment of endothelialized grafts could potentially be conducted at the following graft production stages: (1) immediately after cell seeding to ensure sufficient cell coverage; (2) after shear stress conditioning *in vitro* prior to implantation to monitor cell detachment; and (3) post-implantation *in vivo* to confirm the presence of the seeded ECs.

MRI in combination with contrast agents has been implemented as a powerful tool for non-invasive cell tracking in animal studies [30] as well as in clinical trials [31]. Based on different contrast mechanisms such as T_1 and T_2 relaxation times, contrast agents can be divided into T_1 (e.g. Gd (III) based) and T_2 (e. g. Iron based) agents. Gadolinium (Gd (III))-based T_1 contrast agents are the most commonly used complexes for MRI contrast enhancement clinically [32], and have been used for tracking various cell types such as human skin fibroblasts [33] and tumor cells [34]. However, when used on healthy ECs, cell viability is impaired significantly even at low Gd (III) concentration according to our preliminary studies (data not shown). Iron-based T_2 contrast agents such as SPIONs, are not as popular clinically but have been more commonly used for cell tracking purposes. Unlike Gd (III), iron is a naturally occurring metal present in the human body, which theoretically makes it less toxic to most cell types, although ROS-mediated toxicity has become a concern.[6]

When SPIONs are used to label HUVECs, increase in cell ROS (Figure 4. A), alteration in cell morphology (Figure 3. F, H), and decrease in cell viability (Supplemental Figure 2. B) have been observed by us and others[5, 7]. Although the SPIONs and CSPIONs used in our study vary in particle size as well as surface charge in water, cellular iron concentration was used to enable comparisons among the various cellular responses to labeling. Hence, the observed difference in ROS production in CSPION- vs. SPION- labeled HUVECs is likely due to the oxidative nature of the particles. Coating SPIONs with antioxidant chitosan and impregnating the vascular grafts with POC successfully inhibited the production of ROS. (Figure 4) Moreover, CSPIONs have high relaxivity ($R_2 = 158.1 \pm 6.7 \text{ mM}^{-1} \text{ s}^{-1}$), which means a low labeling concentration (0.5 mM) is needed to achieve a clinically acceptable degree of contrast enhancement.

Surface engineering of SPIONs with several biomaterials, such as Silicon dioxide (SiO_2) [20], poly (ethylene glycol) (PEG),[35] dextran, chitosan and gelatin, has been used to stabilize nanoparticles, improve particle biocompatibility and/or allow a targeted delivery with particle localization to a specific area.[4] When used as a coating material for SPIONs, chitosan has been shown by others to enhance long-term retention of particles in cells, [36] a phenomenon also observed by us. It is noteworthy that chitosan itself is a thrombogenic biomaterial, which accelerates blood coagulation when exposed to blood. [37] Therefore, it is important to ensure that CSPIONs are internalized by ECs rather than adhering to the cell surface. When exposed to re-calcified whole blood, CSPION-labeled HUVECs did not alter clotting kinetics in comparison to non-labeled HUVECs (Figure 6.K). Chitosan coating resulted in higher positive surface charge for CSPION in water ($49.1 \pm 1.2 \text{ mV}$ CSPION vs. $17.6 \pm 5.0 \text{ mV}$ SPION in water). However, the positive charge did not maintain when incubated in EGM-2, which contains 2% FBS ($-6.8 \pm 0.2 \text{ mV}$ CSPION vs. $-8.3 \pm 0.9 \text{ mV}$ SPION in EGM-2), possibly due to the albumin interaction with nanoparticles.

POC is a biocompatible, biodegradable elastomer that has been previously described by our group as a modifying agent for both synthetic vascular grafts [38] and decellularized vascular grafts [39]. In addition to POC's capacity to improve EC adhesion and provide antioxidant properties, herein we show that POC modification of the graft is an important requirement to allow imaging of cells on ePTFE grafts through T_2 imaging.

Most researchers use MRI in combination with contrast agents to monitor cell aggregates rather than a cell monolayer or individual cells. For example, Juan et al used chitosan-coated SPIONs to label mouse islets and imaged them for up to 5 weeks after implanting them in the animal.[40] Thu et al. used iron oxide-labeled therapeutic neural stem cells to visualize the cells in a brain tumor model.[41] It is more challenging to use MRI to visualize a single layer of cells, due to the limited spatial resolution of MRI, which is in the order of hundreds of microns, and the cytotoxicity issues observed by us and others. While better and more powerful scanners are being developed, higher resolution images typically require much longer scan time, which could be problematic *in vivo*. [42]

Other imaging modalities have also been used to monitor live cells in tissue engineering and regenerative medicine applications. For example, optical imaging techniques such as fluorescence imaging [43] and bioluminescence imaging [44] have been used to track cells following implantation. Although optical imaging techniques can provide high spatial resolution for individual cells and even subcellular features, they are often limited in regards to the volumes/depths that can be imaged and are mostly used for subcutaneous cell tracking.[42, 45] Nuclear imaging techniques, such as Positron Emission Tomography (PET) and Single Positron Emission Computed Tomography (SPECT), have been implemented to track live cells with specific radio-tracers after being implanted *in vivo*. [46] While those techniques can provide functional information for implanted cells by detecting their metabolic activity, they typically do not provide any structural or anatomical data.[42] The future of non-invasive cell tracking will most likely combine multiple imaging modalities that can provide not only high spatial resolution and imaging depth capabilities, but also functional information on cell performance.

5. Conclusion

In this study, we describe a method to visualize a tissue-engineered endothelium on ePTFE grafts with T_2 contrast enhancement, which allows non-invasive cell monitoring with MR imaging. The EC-seeded graft is modified with antioxidant nanoparticles (CSPIONs used for labeling) and an antioxidant polymer coating (POC), which together counteract ROS formation from the iron oxide nanoparticles. The combination of CSPION labeling and POC coating is not only critical in ROS scavenging and EC functions, but also essential to the successful visualization of EC-seeded ePTFE grafts with T_2 contrast enhancement. We demonstrated that a hydrophilic POC coating of the ePTFE allows water infiltration within the porous walls and reduces imaging artifacts caused by trapped air. Our findings enable the safe and non-invasive monitoring of EC distribution before and after surgical implantation of vascular graft.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgment

This work is funded by the National Institute of Health (5R01EB017129-02), American Heart Association (AHA) Midwest Affiliate Postdoctoral Fellowship, and the Chicago Biomedical Consortium (CBC) Postdoctoral Award.

The authors would like to thank Kevin G. Baler, Ph.D. and Jisheng Xiao, Ph.D. for assistance in DLS and TEM, Andy Hung, Ph.D. for assistance in T_2 relaxivity measurement and Emily A. Waters, Ph.D. for assistance in MR imaging.

References

1. Michiels C. Endothelial cell functions. *Journal of cellular physiology*. 2003; 196:430–43. [PubMed: 12891700]
2. Nerem RM, Seliktar D. Vascular tissue engineering. *Annual review of biomedical engineering*. 2001; 3:225–43.
3. Berry CC, Curtis AS. Functionalisation of magnetic nanoparticles for applications in biomedicine. *Journal of physics D: Applied physics*. 2003; 36:R198.
4. Gupta AK, Gupta M. Synthesis and surface engineering of iron oxide nanoparticles for biomedical applications. *Biomaterials*. 2005; 26:3995–4021. [PubMed: 15626447]
5. Liu G, Gao J, Ai H, Chen X. Applications and Potential Toxicity of Magnetic Iron Oxide Nanoparticles. *Small*. 2013; 9:1533–45. [PubMed: 23019129]
6. Singh N, Jenkins GJS, Asadi R, Doak SH. Potential toxicity of superparamagnetic iron oxide nanoparticles (SPION). *Nano Reviews*. 2010; 1 10.3402/nano.v1i0.5358.
7. Astanina K, Simon Y, Cavelius C, Petry S, Kraegeloh A, Kierner AK. Superparamagnetic iron oxide nanoparticles impair endothelial integrity and inhibit nitric oxide production. *Acta Biomaterialia*. 2014; 10:4896–911. [PubMed: 25123083]
8. Buyukhatipoglu K, Clyne AM. Superparamagnetic iron oxide nanoparticles change endothelial cell morphology and mechanics via reactive oxygen species formation. *Journal of Biomedical Materials Research Part A*. 2011; 96A:186–95. [PubMed: 21105167]
9. Yang FY, Yu MX, Zhou Q, Chen WL, Gao P, Huang Z. Effects of iron oxide nanoparticle labeling on human endothelial cells. *Cell transplantation*. 2012; 21:1805–20. [PubMed: 22776829]
10. Wan A, Xu Q, Sun Y, Li H. Antioxidant Activity of High Molecular Weight Chitosan and N,O-Quaternized Chitosans. *Journal of Agricultural and Food Chemistry*. 2013; 61:6921–8. [PubMed: 23706102]
11. Yen M-T, Yang J-H, Mau J-L. Antioxidant properties of chitosan from crab shells. *Carbohydrate Polymers*. 2008; 74:840–4.
12. Dash M, Chiellini F, Ottenbrite RM, Chiellini E. Chitosan—A versatile semi-synthetic polymer in biomedical applications. *Progress in Polymer Science*. 2011; 36:981–1014.
13. Arami, H.; Stephen, Z.; Veis, H.; Zhang, M. Chitosan-Coated Iron Oxide Nanoparticles for Molecular Imaging and Drug Delivery. In: Jayakumar, R.; Prabakaran, M.; Muzzarelli, RAA., editors. *Chitosan for Biomaterials I*. Springer; Berlin Heidelberg: 2011. p. 163–84.
14. Tsai Z-T, Wang J-F, Kuo H-Y, Shen C-R, Wang J-J, Yen T-C. In situ preparation of high relaxivity iron oxide nanoparticles by coating with chitosan: A potential MRI contrast agent useful for cell tracking. *Journal of Magnetism and Magnetic Materials*. 2010; 322:208–13.
15. Allen J, Khan S, Serrano MC, Ameer G. Characterization of porcine circulating progenitor cells: toward a functional endothelium. *Tissue engineering Part A*. 2008; 14:183–94. [PubMed: 18333816]
16. Motlagh D, Allen J, Hoshi R, Yang J, Lui K, Ameer G. Hemocompatibility evaluation of poly(diols) in vitro for vascular tissue engineering. *Journal of Biomedical Materials Research Part A*. 2007; 82A:907–16. [PubMed: 17335023]
17. van Lith R, Gregory EK, Yang J, Kibbe MR, Ameer GA. Engineering biodegradable polyester elastomers with antioxidant properties to attenuate oxidative stress in tissues. *Biomaterials*. 2014; 35:8113–22. [PubMed: 24976244]
18. Yang J, Motlagh D, Allen JB, Webb AR, Kibbe MR, Aalami O, et al. Modulating Expanded Polytetrafluoroethylene Vascular Graft Host Response via Citric Acid-Based Biodegradable Elastomers. *Advanced Materials*. 2006; 18:1493–8.
19. Yang J, Webb AR, Ameer GA. Novel Citric Acid-Based Biodegradable Elastomers for Tissue Engineering. *Advanced Materials*. 2004; 16:511–6.

20. Schultz-Sikma EA, Joshi HM, Ma Q, Macrenaris KW, Eckermann AL, Dravid VP, et al. Probing the Chemical Stability of Mixed Ferrites: Implications for MR Contrast Agent Design. *Chemistry of materials : a publication of the American Chemical Society*. 2011; 23:2657–64. [PubMed: 21603070]
21. Rad AM, Arbab AS, Iskander ASM, Jiang Q, Soltanian-Zadeh H. Quantification of superparamagnetic iron oxide (SPIO)-labeled cells using MRI. *Journal of Magnetic Resonance Imaging*. 2007; 26:366–74. [PubMed: 17623892]
22. Lapidos KA, Sprague SM, Ameer GA. Impact of serum source and inflammatory cytokines on the isolation of endothelial colony-forming cells from peripheral blood. *Journal of tissue engineering and regenerative medicine*. 2014; 8:747–56. [PubMed: 22888041]
23. Monopoli MP, Åberg C, Salvati A, Dawson KA. Biomolecular coronas provide the biological identity of nanosized materials. *Nature nanotechnology*. 2012; 7:779–86.
24. Taylor R, Huber D, Monson T, Ali A-M, Bisoffi M, Sillerud L. Multifunctional iron platinum stealth immunomicelles: targeted detection of human prostate cancer cells using both fluorescence and magnetic resonance imaging. *J Nanopart Res*. 2011; 13:4717–29. [PubMed: 22121333]
25. Giannotta M, Trani M, Dejana E. VE-cadherin and endothelial adherens junctions: active guardians of vascular integrity. *Developmental cell*. 2013; 26:441–54. [PubMed: 24044891]
26. Teebken O, Bader A, Steinhoff G, Haverich A. Tissue engineering of vascular grafts: human cell seeding of decellularised porcine matrix. *European Journal of Vascular and Endovascular Surgery*. 2000; 19:381–6. [PubMed: 10801371]
27. Zhou M, Liu Z, Liu C, Jiang X, Wei Z, Qiao W, et al. Tissue engineering of small diameter vascular grafts by endothelial progenitor cells seeding heparin-coated decellularized scaffolds. *Journal of Biomedical Materials Research Part B: Applied Biomaterials*. 2012; 100:111–20.
28. Ott MJ, Ballermann BJ. Shear stress-conditioned, endothelial cell-seeded vascular grafts: improved cell adherence in response to in vitro shear stress. *Surgery*. 1995; 117:334–9. [PubMed: 7878541]
29. Zilla P, Fasol R, Deutsch M, Fischlein T, Minar E, Hammerle A, et al. Endothelial cell seeding of polytetrafluoroethylene vascular grafts in humans: a preliminary report. *Journal of vascular surgery*. 1987; 6:535–41. [PubMed: 3320387]
30. Rogers WJ, Meyer CH, Kramer CM. Technology insight: in vivo cell tracking by use of MRI. *Nature Clinical Practice Cardiovascular Medicine*. 2006; 3:554–62.
31. Bulte JW. In vivo MRI cell tracking: clinical studies. *AJR American journal of roentgenology*. 2009; 193:314. [PubMed: 19620426]
32. Hung AH, Holbrook RJ, Rotz MW, Glasscock CJ, Mansukhani ND, MacRenaris KW, et al. Graphene oxide enhances cellular delivery of hydrophilic small molecules by co-incubation. *ACS nano*. 2014; 8:10168–77. [PubMed: 25226566]
33. Varani J, DaSilva M, Warner RL, Deming MOB, Barron AG, Johnson KJ, et al. Effects of gadolinium-based magnetic resonance imaging contrast agents on human skin in organ culture and human skin fibroblasts. *Investigative radiology*. 2009; 44:74–81. [PubMed: 19077912]
34. Vuu K, Xie J, McDonald MA, Bernardo M, Hunter F, Zhang Y, et al. Gadolinium-rhodamine nanoparticles for cell labeling and tracking via magnetic resonance and optical imaging. *Bioconjugate chemistry*. 2005; 16:995–9. [PubMed: 16029042]
35. Lin, WB.; Hyeon, T.; Lanza, GM.; Zhang, MQ.; Meade, TJ. Magnetic Nanoparticles for Early Detection of Cancer by Magnetic Resonance Imaging. Vol. 34. *Mrs Bull*; 2009. p. 441-8.
36. Bakhru SH, Altioik E, Highley C, Delubac D, Suhan J, Hitchens TK, et al. Enhanced cellular uptake and long-term retention of chitosan-modified iron-oxide nanoparticles for MRI-based cell tracking. *International journal of nanomedicine*. 2012; 7:4613. [PubMed: 22942643]
37. Balan V, Verestiuc L. Strategies to improve chitosan hemocompatibility: A review. *European Polymer Journal*. 2014; 53:171–88.
38. Hoshi RA, Van Lith R, Jen MC, Allen JB, Lapidos KA, Ameer G. The blood and vascular cell compatibility of heparin-modified ePTFE vascular grafts. *Biomaterials*. 2013; 34:30–41. [PubMed: 23069711]
39. Jiang B, Akgun B, Lam RC, Ameer GA, Wertheim JA. A Polymer-Extracellular Matrix Composite with Improved Thromboresistance and Recellularization Properties. *Acta Biomaterialia*. 2015

40. Juang J-H, Shen C-R, Wang J-J, Kuo C-H, Chien Y-W, Kuo H-Y, et al. Magnetic resonance imaging of mouse islet grafts labeled with novel chitosan-coated superparamagnetic iron oxide nanoparticles. *PloS one*. 2013; 8:e62626. [PubMed: 23658638]
41. Thu MS, Najbauer J, Kendall SE, Harutyunyan I, Sangalang N, Gutova M, et al. Iron labeling and pre-clinical MRI visualization of therapeutic human neural stem cells in a murine glioma model. *PloS one*. 2009; 4:e7218. [PubMed: 19787043]
42. Appel AA, Anastasio MA, Larson JC, Brey EM. Imaging challenges in biomaterials and tissue engineering. *Biomaterials*. 2013; 34:6615–30. [PubMed: 23768903]
43. Hadjantonakis A-K, Papaioannou VE. Dynamic in vivo imaging and cell tracking using a histone fluorescent protein fusion in mice. *BMC biotechnology*. 2004; 4:33. [PubMed: 15619330]
44. Wang X, Rosol M, Ge S, Peterson D, McNamara G, Pollack H, et al. Dynamic tracking of human hematopoietic stem cell engraftment using in vivo bioluminescence imaging. *Blood*. 2003; 102:3478–82. [PubMed: 12946998]
45. Sutton EJ, Henning TD, Pichler BJ, Bremer C, Daldrup-Link HE. Cell tracking with optical imaging. *European radiology*. 2008; 18:2021–32. [PubMed: 18506449]
46. Acton P, Zhou R. Imaging reporter genes for cell tracking with PET and SPECT. *QJ Nucl Med Mol Imaging*. 2005; 49:349–60.

Figure 1.
TEM (A) and T₂ MR (B) images of CSPION suspension in PBS. Scale bar=100 nm.

Figure 2. Prussian blue staining (A-F) and cell iron concentration (G) of CSPION- (A, C, E) and SPION- (B, D, F) labeled HUVECs. All experiments were performed at 24 hours after nanoparticle loading.

Figure 3. Phalloidin (green) and Hoechst (blue) staining of CSPION- (A, C, E, G) and SPION-(B, D, F, H) labeled HUVECs at 0 mM (A, B), 0.25 mM (C, D) and 0.5 mM (E, F) iron concentration 24 hours after nanoparticle loading. Elongated cell morphology was observed with higher SPION concentration (F, H), while CSPION labeled cells maintained cobble stone morphology. Scale bar=100 μ m.

Figure 4. ROS formation within SPION- (A, B) and CSPION- (C, D) labeled HUVECs on TCP (A, C) and POC (10 wt%) coated surface (B, D) in the absence and presence of hydrogen peroxide-induced oxidative stress. All experiments were performed at 24 hours after nanoparticle loading. * indicates $p < 0.05$ ($n=4$).

Figure 5. Cell viability (A) and inflammatory status evaluation, including VCAM-1 (B), ICAM-1 (C), and E-Selectin expression (D) at 1 day, 1 week and 1 month after CSPION labeling. * indicates statistical significance ($p < 0.05$). (n=4)

Figure 6.

Flow cytometry analysis (A-I) of CD31 expression (A-C), Ac-LDL uptake (D-F), and nitric oxide production (G-I) for HUVEC labeled with 0 mM (A, D, G), 0.25 mM (B, E, H) and 0.5 mM (C, F, I) CSPIONs. The percentages of positive population (black histogram) are shown comparing to negative control (white histogram). No significant difference was found in the flow cytometry evaluation of HUVECs with varying CSPION labeling concentration (J, n=3). No significant difference was found in re-calcified whole blood clotting kinetics on

HUVECs with varying CSPION labeling concentration (K, n=3). All experiments were performed at 24 hours after nanoparticle loading.

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Figure 7.

T₂ images of ePTFE vascular graft with 0% (A, C) and 10% (B, D) POC coating at cross-sections. No cells were seeded. Field of view 2 cm × 2 cm.

Figure 8.

Three dimensional volume rendering (A-D) and H&E (E, F) staining images of HUVEC-seeded POC-ePTFE grafts with 0 mM (A, C, E) and 0.5 mM (B, D, F) CSPIONs. H&E staining images (E, F) confirmed monolayer of cells present on the lumen side of both grafts. Yellow boxes in 3D images (A-D) indicate ePTFE grafts, while black arrows in H&E images (E, F) indicate EC monolayers. All experiments were performed at 24 hours after nanoparticle loading. Scale bar=200 μ m.

Table 1

CSPION and SPION characterization

128.3 ± 30.2 [23]	CSPION	SPION
	172.6 (PDI 0.344)	549.4 (PDI 0.271)
Particle diameter in EGM-2 (nm)	368.5 (PDI 0.291)	1015.1 (PDI 0.303)
Zeta potential in water (mV)	49.1 ± 1.2	17.6 ± 5.0
Zeta potential in EGM-2 (mV)	−6.8 ± 0.2	−8.3 ± 0.9
T ₂ Relaxivity (R ₂ , mM ^{−1} s ^{−1})	158.1 ± 6.7	