Anal Chem. 2013 May 7; 85(9): 4307–4310. doi:10.1021/ac4003479.

Near-edge X-ray absorption fine structure (NEXAFS) spectroscopy, as a technique, offers detailed information about the bonding environment of molecules at a surface. However, because it is a synchrotron based method, beam-time is limited and users must typically prioritize and narrowly define the scopes of experiments. In this study, we demonstrate a novel method that opens up the possibility of the use of large area NEXAFS imaging to pursue combinatorial studies. To explore the capabilities of the NIST full field NEXAFS microscope available at the National Synchrotron Light Source as a high throughput imaging instrument, we collected NEXAFS images from a sample array consisting of 144 different elements with a periodic sequence of different surface modifications. NEXAFS images collected from this model system illustrate how hyperspectral NEXAFS data can be used for parallel analysis of large numbers of samples either directly from the overall image or by extracting spectra from regions of interest.

Combinatorial approaches have been very successful at identifying novel solutions to problems across a wide range of fields. New chemical agents for photoresist systems,¹ catalysts,² thin film function-property relationships,³ and even engineered peptides that bind to specific metal alloys have been identified with these approaches.⁴ Yet, combinatorial studies rely upon the ability to quickly examine libraries of different materials and experimental conditions. In this context, hyper- and multispectral imaging methods can provide a means to simultaneously evaluate large numbers of samples or gradients from mixtures of different materials.

*Corresponding Author: dfischer@nist.gov (D.A.F.); weidner@mpip-mainz.mpg.de (T.W.).

Notes

The authors declare no competing financial interest.

One probe of surface chemistry is near-edge X-ray absorption fine structure (NEXAFS) spectroscopy.⁵ By probing the resonant photoexcitation of atomic core level electrons into unoccupied molecular orbitals, NEXAFS provides valuable information about the chemical state, orientation, and structure of surface species. A variety of surface analytical techniques, including imaging X-ray photoelectron spectroscopy (XPS),⁶ hyperspectral IR imaging,⁷ time-of-flight secondary ion mass spectrometry (ToF-SIMS) imaging,⁸ fluorescence,⁹ and thermographic imaging¹⁰ have been used to screen the performances and chemical properties of large matrixes and gradients of samples. The current limitation for the application of NEXAFS spectroscopy in combinatorial studies is due to the fact that the technique requires tunable X-rays only available at synchrotron sources, where beam access is typically limited. As a result, parallel screening large numbers of samples ($\gg 100$) for combinatorial experiments would require prohibitively extended data acquisition times.¹¹

A newly developed NEXAFS microscope available at the NIST U7a beamline at the National Synchrotron Light Source (NSLS) adapts NEXAFS spectroscopy, by magnetically guiding the emitted electrons onto a detector that forms a two-dimensional NEXAFS image over a $13 \times 18 \text{ mm}^2$ region while providing a spatial resolution of $50 \mu\text{m}$ at all relevant X-ray incidence angles.¹² Unlike other photoelectron emission microscopy (PEEM) techniques, this new NEXAFS imaging microscope can handle insulators, conductors, and nonplanar samples without charging effects.¹² For the full field imaging NEXAFS microscope, all photoelectrons leaving the sample surface must move along the magnetic field lines toward the partial electron yield grid in front of the channel plate electron detector. Charging is mitigated by the reflection (rejection) back to the sample of low energy photo electrons; these electrons may even collide with the grid before reflection producing a supply of additional electrons for charge compensation. This large field of view, combined with the ability to analyze a range of sample types, enables the user to rapidly screen the surface properties of a large array of samples. In this study, we demonstrate how this microscope, through the use of multiplexed orientational and structural analysis by imaging NEXAFS (MOSAIX), enables the characterization of large sets of samples required for combinatorial studies in a realistic time frame (hours versus days).

RESULTS AND DISCUSSION

In the past, NEXAFS spectroscopy has been very successful at probing the orientation and chemical integrity of thiol based self-assembled monolayers (SAMs).^{5,13–21} In this study, we created an array of well-characterized SAMs as a model system to benchmark the high throughput analysis provided by this new NEXAFS microscope. This system was built upon a periodic sequence of different SAMs, on $1 \times 1 \text{ mm}^2$ gold substrates, which were physically arranged into a $12 \times 12 \text{ mm}^2$ sample array (Figure 1). This array consisted of a periodic sequence of substrates modified by terphenylthiol (TPT), aminoundecanthiol (AUT), dodecanethiol (DoDT), mercaptoundecanol (MUD), and mercaptoundecanoic acid (MUDA) precursors. This created a pattern where identical SAMs travel diagonally down the entire array (Figure 1).

Once assembled, MOSAIX image stacks of the array were collected at both the carbon and nitrogen K-edges. The resulting $13 \times 18 \text{ mm}^2$ images, where each pixel (stack) contains an

entire NEXAFS spectrum, thereby, enable us to map specific features within the spectrum. Pre- and post-edge normalized MOSAIX images, collected at an X-ray incidence angle of 30°, can be found in Figure 2. Stepping through and mapping the relative intensities of different spectral regions at the C K-edge provides a detailed examination of the molecular environment across the array. The pre-edge π^* resonance shown in Figure 2 is representative of aromatic C=C bonds and, as expected, the TPT samples show the highest signal intensity stemming from the monolayer's terphenyl backbone.²² Moving to higher photon energies and mapping the π^* resonance related to C=O bonds (289 eV) the areas of high signal intensity shift from the TPT regions to the MUDA regions.^{5,18,21} By just imposing a pre-edge normalization, the surface concentrations of these different species can be assessed by the intensity at the post-edge and are highlighted in panel C of Figure 2. Moving onto the N K-edge (panel D), as expected, we observe a strong electron yield from the AUT regions of the sample.¹⁹ Since the N K-edge data was pre-edge normalized, the nitrogen-free areas exhibit electron yield related to background photoelectrons from the Au and C edges.

As mentioned above, each pixel of this image stack contains a spectrum; therefore, we can export spectra from a region of interest or export spectra along a line that transverses the sample. Figure 3 demonstrates how we can hyperspectrally image across the array. The result is a surface plot where spectral features rise and fall as we traverse across different regions of the sample. Moving across the sample, within the AUT regions, we observe resonances at 288 and 293 eV related to R*/C-H σ^* and C-C σ^* , respectively.^{13-15,19} The region just below, the MUDA monolayer, is dominated by a π^* resonance related to C=O bonds. This resonance then disappears as we move to the TPT region and is replaced by a large peak π^* peak related to C=C bonds.^{5,13,22} Spectra from the DoDT portion of the array contain a sharp σ^* (C-H) feature at 288 eV and a broad resonance at 293 eV (C-C σ^*).¹³ Moving down to the MUD region the C-C σ^* resonance is again present but we also unexpectedly also observe the π^* resonance related to C=O bonds (289 eV).

As with NEXAFS spectroscopy, the orientation and ordering of molecular bonds can be determined by simply following the change in the X-ray resonance line absorption as we rotate the sample and vary the incident angle of the X-rays (the electric field polarization on the sample). Figure 4 presents NEXAFS images collected at X-ray incidence angles of 30°, 50°, and 70°. Ordering of specific bonds at the array surface was then assessed by comparing spectra collected at these different incident angles. Difference spectra (70°-30°), extracted from TPT regions and presented in Figure 4, show a large positive dichroism at the C=C π^* resonance. Spectra from the other regions (AUT, DoDT, MUD, and MUDA) exhibit a weak but discernible positive dichroism for the R*/C-H σ^* molecular orbitals indicating that the alkane chains within these monolayers are somewhat ordered.¹³⁻¹⁵

In conclusion, the large field of view provided by the NEXAFS microscope and the size of our samples enabled us to probe the surface chemistry of 144 samples in roughly the same amount of time typically required to collect spectra from a single surface. In addition, the throughput could be increased by just moving to smaller and smaller array features (<1 mm²), that is until the size of the features reaches the spatial resolution dictated by the microscope. Adopting this strategy of imaging a large array of small features now provides a

novel method of expanding the use of NEXAFS spectroscopy for combinatorial experiments.

EXPERIMENTAL METHODS

Sample Preparation

All surfaces were built upon $1 \times 1 \text{ mm}^2$ silicon substrates (Microelectronics Inc., San Jose, CA) that were cleaned by sequential sonication in deionized water, dichloromethylene, acetone, and methanol. In a high vacuum electron beam evaporator (pressure $<1 \times 10^{-6}$ Torr), the Si substrates were then coated with a thin adhesion layer of titanium (10 nm) followed by high purity gold (99.99%, 80 nm). Each set of SAMs was assembled by submerging the respective gold surfaces in 0.1 mM thiol-ethanol (Sigma Aldrich) solution for 16 h. The TPT monomer was predissolved in a few drops of tetrahydrofuran. These small substrates were then placed in a ceramic funnel filter cone and then repeatedly rinsed with 200 proof ethanol (Decon Laboratories, King of Prussia, PA). Once rinsed, the individual $1 \times 1 \text{ mm}$ samples were arranged onto a $12 \times 12 \text{ mm}$ strip of copper tape and then stored under nitrogen until analysis.

Near-Edge X-ray Absorption Fine Structure (NEXAFS) Microscopy

NEXAFS spectra were collected at the National Synchrotron Light Source (NSLS) beamline U7A at Brookhaven National Laboratory using a parallel processing imaging system.¹² A soft X-ray beam, with energy scanned around the carbon K-edge (270–340 eV; resolution $\sim 0.1 \text{ eV}$; flux $\sim 5 \times 10^{10}$ photons/s (0.1% BW)), was rastered across an $18 \times 13 \text{ mm}^2$ area on the sample. A large area rapid imaging analytical tool (LARIAT, Synchrotron Research Inc.) was used to measure partial electron yield. Step size for the carbon K-edge scans was 0.1 eV with a two second dwell time. Therefore, the time required for the entire scan is less than 24 min. The emitted photoelectrons were guided to an electron yield detector by a full field imaging parallel magnetic field. This produced a series of two-dimensional NEXAFS images with a $50 \mu\text{m}$ spatial resolution.¹² To eliminate the effect of incident beam intensity fluctuations and absorption features in the beamline optics, the PEY signals were normalized by the photo yield of a clean gold mesh located upstream along the path of the incident X-ray beam. Unless mentioned in the text, all images were pre- and post-edge normalized.

Acknowledgments

The authors thank David G. Castner for support of this work and Lara J. Gamble for collaboration at the synchrotron. T.W. thanks the Deutsche Forschungsgemeinschaft (DFG) for financial support (WE4478/2-1). J.E.B. thanks the National Science Foundation for a research fellowship (NSF grant #1202620). This work was performed at the NSLS, Brookhaven National Laboratory, which is supported by the U.S. Department of Energy, Division of Materials Science and Division of Chemical Sciences. This work is also a part of the research program of the Max-Planck Society. Certain commercial names are mentioned in this manuscript for the purpose of example and do not represent an endorsement by the National Institute of Standards and Technology.

References

1. Bauer WAC, Neuber C, Ober CK, Schmidt HW. Adv Mater. 2011; 23:5404. [PubMed: 22009688]
2. Tompos A, Margitfalvi JL, Hegedus M, Szegedi A, Fierro JLG, Rojas S. Comb Chem High T Scr. 2007; 10:71.
3. Kafizas A, Parkin IP. Chem Soc Rev. 2012; 41:738. [PubMed: 21938290]

4. Tamerler C, Khatayevich D, Gungormus M, Kacar T, Oren EE, Hnilova M, Sarikaya M. *Pept Sci*. 2010; 94:78.
5. Stöhr, J. *NEXAFS Spectroscopy*. Springer-Verlag; Berlin: 1992.
6. Eglin M, Rossi A, Spencer N. *Tribol Lett*. 2003; 15:199.
7. Oguchi H, Hattrick-Simpers J, Takeuchi I, Heilweil EJ, Bendersky LA. *Rev Sci Instrum*. 2009; 80:073707. [PubMed: 19655956]
8. Roberson SV, Fahey AJ, Sehgal A, Karim A. *Appl Surf Sci*. 2002; 200:150.
9. Vendrell M, Zhai D, Er JC, Chang YT. *Chem Rev*. 2012; 112:4391. [PubMed: 22616565]
10. Huxtable S, Cahill DG, Fauconnier V, White JO, Zhao JC. *Nat Mater*. 2004; 3:298. [PubMed: 15064757]
11. Fischer DA, Efimenko K, Bhat RR, Sambasivan S, Genzer J. *Macromol Rapid Commun*. 2004; 25:141.
12. Konicek AR, Jaye C, Hamilton MA, Sawyer WG, Fischer DA, Carpick RW. *Tribol Lett*. 2011; 44:99.
13. Outka DA, Stohr J, Rabe JP, Swalen JD. *J Chem Phys*. 1988; 88:4076.
14. Väterlein P, Fink R. *J Chem Phys*. 1998; 108:3313.
15. Weiss K, Bagus PS, Wöll C. *J Chem Phys*. 1999; 111:6834.
16. Frey S, Stadler V, Heister K, Eck W, Zharnikov M, Grunze M, Zeysing B, Terfort A. *Langmuir*. 2001; 17:2408.
17. Willey TM, Vance AL, van Buuren T, Bostedt C, Nelson AJ, Terminello LJ, Fadley CS. *Langmuir*. 2004; 20:2746. [PubMed: 15835147]
18. Cabarcos OM, Shaporenko A, Weidner T, Uppili S, Dake LS, Zharnikov M, Allara DL. *J Phys Chem C*. 2008; 112:10842.
19. Baio JE, Weidner T, Brison J, Graham DJ, Gamble LJ, Castner DG. *J Electron Spectrosc Relat Phenom*. 2009; 172:2.
20. Dietrich PM, Graf N, Gross T, Lippitz A, Krakert S, Schüpbach B, Terfort A, Unger WES. *Surf Interface Anal*. 2010; 42:1184.
21. Ballav N, Schupbach B, Dethloff O, Feulner P, Terfort A, Zharnikov M. *J Am Chem Soc*. 2007; 129:15416. [PubMed: 18041835]
22. Himmel HJ, Terfort A, Wöll C. *J Am Chem Soc*. 1998; 120:12069.

Figure 1.

Diagram of the array and sample map. The array consists of 144 SAMs on gold with a size of $1 \times 1 \text{ mm}^2$. This array consisted of a periodic sequence of substrates modified by terphenylthiol (TPT), aminoundecanethiol (AUT), dodecanthiol (DoDT), mercaptoundecanol (MUD), and mercaptoundecanoic acid (MUDA) precursors. This resulted in a pattern where identical SAMs travel diagonally down the entire array.

Figure 2.

MOSAIX images of the array of AUT, MUDA, TPT, DoDT, and MUD SAMs on gold. The images highlight the C K-edge at the (A) $\pi^*(\text{C}=\text{C})$ and (B) $\pi^*(\text{C}=\text{O})$ resonances, (C) the post-edge intensity of the pre-edge normalized data, and (D) the N K-edge data. All square features are 1×1 mm in size.

Figure 3. Surface plot extracted from a region of interest within the array. Inset: A map of the region of interest.

Figure 4.

MOSAIX images of the array collected at 30°, 50°, and 70° X-ray incidence angles. Images presented here map the relative intensities of all features at the C K-edge. Spectra presented below the images were extracted for the individual samples and are shown for the respective angles.