Published in final edited form as:

J Mater Chem A Mater Energy Sustain. 2015 November 7; 3(41): 20819–20826. doi:10.1039/C5TA04923G.

Optimised room temperature, water-based synthesis of CPO-27-M metal-organic frameworks with high space-time yields †

L. Garzón-Tovar^a, A. Carné-Sánchez^a, C. Carbonell^a, I. Imaz^{a,*}, and D. Maspoch^{a,b,*}

^aICN2 (ICN-CSIC), Institut Català de Nanociència i Nanotecnologia, Esfera UAB 08193 Bellaterra, Spain

^bInstitució Catalana de Recerca i Estudis Avançats (ICREA), 08100 Barcelona, Spain

Abstract

The exceptional porosity of Metal-Organic Frameworks (MOFs) could be harnessed for countless practical applications. However, one of the challenges currently precluding the industrial exploitation of these materials is a lack of green methods for their synthesis. Since green synthetic methods obviate the use of organic solvents, they are expected to reduce the production costs, safety hazards and environmental impact typically associated with MOF fabrication. Herein we describe the stepwise optimisation of reaction parameters (pH, reagent concentrations and reaction time) for the room temperature, water-based synthesis of several members of the CPO-27/MOF-74-M series of MOFs, including ones made from Mg(II), Ni(II), Co(II) and Zn(II) ions. Using this method, we built MOFs with excellent BET surface areas and unprecedented Space-Time Yields (STYs). Employing this approach, we have synthesised CPO-27-M MOFs with record BET surface areas, including 1279 m² g⁻¹ (CPO-27-Zn), 1351 m² g⁻¹ (CPO-27-Ni), 1572 m² g⁻¹ (CPO-27-Co), and 1603 m² g⁻¹ (CPO-27-Mg). We anticipate that our method could be applied to produce CPO-27-Ni, -Mg, -Co and -Zn with STYs of 44 Kg m⁻³ day⁻¹, 191 Kg m⁻³ day⁻¹, 1462 Kg m⁻³ day⁻¹ and a record 18720 Kg m⁻³ day⁻¹, respectively.

Introduction

Metal-Organic Frameworks (MOFs) are an emerging class of porous materials comprising metal components and organic ligands. They are characterised by extremely large surface areas (S_{BET}) and high structural/compositional flexibility that confer them with potential for myriad applications, including gas sorption and separation, catalysis, sensing, and biomedicine, among many others.^{1–7} Seeking to exploit this exceptional porosity, researchers have developed several methods for the industrial-scale fabrication of MOFs, including the classical solvothermal synthesis,⁸ mechano-synthesis,⁹ electrochemistry,¹⁰ continuous flow techniques,^{11, 12} and spray-drying.¹³ These methods are continuously being optimised in the hopes of finally enabling widespread use of MOFs in practical applications.

inhar.imaz@icn.cat; daniel.maspoch@icn.cat.

Optimisation of industrial MOF fabrication methods not only addresses the production rates, but also the related costs, safety hazards and environmental impact. One measure that can simultaneously provide savings while improving safety and environmental friendliness is to use water as the only solvent. Along these lines, the company BASF has developed a water-based synthesis of aluminium fumarate (Basolite A520®) at the tonne scale, achieving the extremely high Space-Time Yield (STY) of $3600 \text{ Kg m}^{-3} \text{ day}^{-1}$.¹⁴ In fact, this breakthrough in the green synthesis of MOFs was awarded the Pierre Potier Prize.

Herein, we report another example of the green synthesis of MOFs: a room temperature, water-based synthesis of several members of the isostructural CPO-27-M (also known as *MOF-74*) family of the general structure $M_2(\text{dhtp})$, where dhtp = 2,5-dioxido-1,4-benzenedicarboxylate and $M = \text{Mg(II)}, \text{Co(II)}, \text{Ni(II)}$ and Zn(II)] family at room temperature in terms of their production rates (STYs up to $18500 \text{ Kg m}^{-3} \text{ day}^{-1}$) while maintaining their excellent sorption capabilities.

Isostructural CPO-27-M MOFs are undoubtedly among the most widely studied MOFs, as they are highly porous ($S_{\text{BET}} = 1039\text{--}1542 \text{ m}^2 \text{ g}^{-1}$) and stable and show hexagonal channels that can exhibit open metal sites and that can be easily functionalised with various groups.^{15, 16} Given these advantages, CPO-27-M MOFs are excellent candidates for catalysis,¹⁷ storage and delivery of biologically relevant gases,¹⁸ and separation and/or adsorption of gases (H_2 , CO, CH_4 , ammonia, etc.).^{19–27} For instance, CPO-27-Mg has been widely reported to be among the best porous materials for CO_2 adsorption and separation due to its high selectivity, facile regeneration and high CO_2 dynamic-adsorption capacities.^{28–33}

To date, the most common CPO-27-M syntheses involve solvothermal reactions of a solution containing the corresponding metal salt and dhtp in organic solvents (e.g. DMF) or mixtures of organic solvents and water.^{34–37} However, very recent reports have shown that totally water-based routes for the synthesis of CPO-27-M are possible and that, despite the low aqueous solubility of dhtp, such methods can be efficient. Quadrelli *et al.* first reported the synthesis of CPO-27-Ni ($S_{\text{BET}} = 1233 \text{ m}^2 \text{ g}^{-1}$) with an STY of $680 \text{ kg m}^{-3} \text{ day}^{-1}$. They mixed an aqueous solution of Ni(II) acetate with an aqueous suspension of dhtp, and then heated the resulting mixture at reflux for 1 h.³⁸ Their success stems from the use of Ni(II) acetate because metal acetates in the MOF syntheses can be used as both the metal source and the base (acetate ion).³⁹ Thus, the basic character of the acetate ion promotes deprotonation of the dhtp and therefore, its dissolution in water and subsequent reaction with Ni(II) ions. More recently, Sánchez-Sánchez *et al.* adapted this method to synthesise CPO-27-Zn ($S_{\text{BET}} = 1039 \text{ m}^2 \text{ g}^{-1}$; reaction time = 20 h) at room temperature, without the need for any heating, by introducing a minimum amount of NaOH.⁴⁰ However, to date, there have not been any reports demonstrating whether this route to CPO-27-Zn could afford similar or even higher STYs compared to that achieved in the hydrothermal synthesis of CPO-27-Ni, or whether it could be generalised to encompass CPO-27-M built up from metal ions other than Zn(II).

Seeking to further develop the aforementioned room-temperature, water-based chemistry, we have developed similar methods for several members of the CPO-27-M series, including ones made from Mg(II), Ni(II), Co(II), Cu(II) and Zn(II) ions. We optimised each method

stepwise, by carefully studying the influence of reaction parameters on the purity and quality of the synthesised CPO-27-M and on the corresponding reaction yields. Specifically, we evaluated the pH, the reagent concentrations (of the metal acetate/nitrate [hereafter designed as Met] and of the dthp), and the reaction time. We have proven that, except in the case of CPO-27-Cu, fine-tuning of these parameters for each CPO-27-M affords high-quality product (in terms of S_{BET}) with high STYs.

Experimental

Reagents

Nickel acetate tetrahydrate, cobalt acetate tetrahydrate, magnesium nitrate hexahydrate, zinc acetate dehydrate, copper acetate hydrate, 2,5-dihydroxyterephthalic acid (dthp) and sodium hydroxide were purchased from Sigma Aldrich. Methanol was obtained from Fisher Chemical. All the reagents were used without further purification. Deionised water, obtained with a Milli-Q® system (18.2 MΩ·cm), was used in all reactions.

General protocol for the synthesis and activation of CPO- 27-M

Our protocol for the synthesis of CPO-27-M MOFs began with the addition of an aqueous solution of metal salt (Met) to an aqueous solution of dthp and NaOH. The resulting reaction mixture, which contained the precursors Met (at the concentration C_1) and dthp (at the concentration C_2), was stirred at room temperature for a certain period of time (t). In all cases, the volume was 10 mL and the molar ratio (Met/dthp) was 2. After the time t , each resulting solid was collected by centrifugation, washed three times with water and methanol, dried at 70 °C overnight and weighed.

The prepared solids were characterised by XRPD, activated using a protocol recently described by Yaghi *et al.*,⁴¹ and their respective S_{BET} values were measured. The activation protocol started with the immersion of the synthesised CPO-27-M in methanol for 6 days (12 days for CPO-27-Mg), during which the solvent was exchanged once daily. Then, each CPO-27-M was exposed to five consecutive heating ramps under vacuum [from room temperature to 80 °C; from 80 °C to 100 °C; from 100 °C to 150 °C; from 150 °C to 200 °C, and from 200 °C to 250 °C (265 °C for CPO-27-Zn) at a constant rate of 4 °C min⁻¹, with the temperature held at 1 h at the end of each ramp; except for at 250 °C (265 °C for CPO-27-Zn), at which all samples were held for 12 h.

Gram-scale synthesis of CPO-27-Zn

In a typical synthesis, an aqueous solution of $\text{Zn}(\text{CH}_3\text{COO})_2 \cdot 2\text{H}_2\text{O}$ was rapidly added to an aqueous solution of dthp and NaOH in a D15/CN10-F2 pilot-plant stirrer (DISPERMAT) equipped with a 1-L reactor. The volume of the reaction mixture was 500 mL; the molar ratio (Met/dthp/NaOH/H₂O), 2:1:4:304; $C_1 = 0.365 \text{ mol L}^{-1}$; and $C_2 = 0.183 \text{ mol L}^{-1}$. This reaction mixture was stirred for 5 min at room temperature. The resulting solid was collected by centrifugation, washed three times with deionised water and methanol, and finally, dried at 70 °C overnight (weight: 32.5 g; yield: 97%).

Characterisation

X-ray powder diffraction (XRPD) patterns were collected on an X'Pert PRO MPDP analytical diffractometer (Panalytical) at 45 kV, 40 mA using CuK α radiation ($\lambda = 1.5419$ Å). Nitrogen adsorption and desorption measurements were done at 77K using an Autosorb-IQ-AG analyser (Quantachrome Instruments). Field-Emission Scanning Electron Microscopy (FE-SEM) images were collected on a FEI Magellan 400L scanning electron microscope at an acceleration voltage of 1.0–2.0 Kv, using aluminium as support. Transmission electron microscopy (TEM) images were obtained with a FEI Tecnai G² F20.

Results and discussion

Space-Time Yield (STY)

Space-Time Yield is an industrial parameter that refers to the quantity of a product (Kg) produced per unit volume (m³) per unit time (day). Widely used in the field of catalysis,⁴² it has been employed by BASF to assess a given reaction/method for MOF production. Initial STY values reported by BASF include 60 Kg m⁻³ day⁻¹ for the solvothermal synthesis of Basolite A100 (or MIL-53-Al), and 100 Kg m⁻³ day⁻¹ and 225 Kg m⁻³ day⁻¹ for the electrochemical synthesis of Basolite Z1200 (or ZIF-8) and Basolite C300 (or HKUST-1),⁴³ respectively.

Since the initial work of BASF, increasingly higher STYs have been reported for MOF synthesis. Interestingly, very competitive STYs have begun to be reported for water-based green syntheses of most iconic MOFs. Illustrative examples include a hydrothermal (T = 60 °C) synthesis of Basolite A520

(STY: 3600 Kg m⁻³ day⁻¹) and a microwave (T = 130 °C) synthesis of Al fumarate (STY: 15200 Kg m⁻³ day⁻¹), reported by BASF and Maurin, Serre *et al.*, respectively^{51, 52}. Impressive STYs have also been reported for the synthesis of HKUST-1 at room temperature (2035 Kg m⁻³ day⁻¹),⁵³ the hydrothermal (T = 160 °C) synthesis of MIL-100-Fe (1700 Kg m⁻³ day⁻¹ for),⁵⁴ the continuous flow hydrothermal (T = 250 °C) synthesis of MIL-53-Al (1300 Kg m⁻³ day⁻¹ for),¹² and the hydrothermal (T = 100 °C) synthesis of CPO-27-Ni (680 Kg m⁻³ day⁻¹).³⁸

Quality of a synthesised MOF

One parameter that is suitable for analysing the quality of a synthesised MOF is the surface area⁵⁵, which is generally reported as either the *BET surface area* (S_{BET}) or, less commonly, the *Langmuir surface area*. However, it is important to highlight here that S_{BET} is not a direct experimental value: it must be calculated from the N₂ isotherm performed at 77 K according to the BET model. This fact, when considered together with the (variable) quality of the synthesised MOF and the activation method used, mean that the S_{BET} values reported for a particular MOF can vary widely. A clear example of a MOF for which various S_{BET} values have been reported is our target, CPO-27-M (Table 1). Another reason for the differences among reported S_{BET} values for a particular MOF is the pressure range selected for calculating the value. In order to enable comparison of different S_{BET} values for a given MOF, even when the MOF has been synthesised by different methodologies, the use of two

criteria has recently been suggested:^{55–57} *firstly*, the straight line fitted to the BET plot must have a positive intercept; and *secondly*, the pressure range should be chosen such that $v_{\text{ads}}(1-P/P_0)$ always increases with P/P_0 . Accordingly, in the study reported here, we chose the pressure range based on these criteria.

As stated above, a second parameter that must be taken into account when comparing S_{BET} values is the activation process, which can also vary for a particular MOF. For instance, CPO-27-M has been activated by various methods (see Table 1). For consistency in the study reported here, we activated all the CPO-27-M samples using the general activation method described by Yaghi *et al.*⁵⁸

Optimisation of the room temperature water-based synthesis of CPO-27-M: STY versus quality

To increase the STY in a given MOF reaction, two parameters must be optimised: the *quantity of pure MOF produced per unit volume*, which must be maximised (mainly by balancing the maximum reaction yield and reagent concentrations); and the *reaction time*, which must be minimised. To optimise both parameters in our targeted syntheses of CPO-27-M, we followed a rational protocol comprising four steps. Firstly, we defined the maximum concentrations of Met (C_1) and dthp (C_2) that could be used. We found that the limiting concentration in the reaction mixture was $C_2 = 0.183 \text{ mol L}^{-1}$, which corresponds to the maximum amount of dthp that could be dissolved at room temperature under normal stirring conditions in 1 L of water in the presence of NaOH. By fixing the stoichiometry of metal ion and dthp in CPO-27-M (the total molar ratio of Met/dthp; to 2:1), C_1 and the total molar ratio Met/dthp/ H_2O were then automatically defined to be 0.365 mol L^{-1} and 2:1:304, respectively. Secondly, we optimised the molar ratio of NaOH (hereafter designated as x) for the total molar ratio Met/dthp/ $\text{H}_2\text{O} = 2:1:304$. For this, we studied the effect of the pH on the purity of the resulting CPO-27-M and on the reaction yields for a randomly selected reaction time of 24 h. At this point, we analysed the quality of the different CPO-27-M products synthesised at the optimum x by measuring their S_{BET} . We considered CPO-27-M samples that showed S_{BET} values greater than 90% of the highest reported S_{BET} values (Table 1) to be of sufficiently high quality. Thirdly, those with lower S_{BET} values were optimised for quality, by decreasing C_1 and C_2 . Finally, once we had determined the ideal C_1 , C_2 and total molar ratio Met/dthp/NaOH (2:1:4) that afforded the maximum quantity of each CPO-27-M per volume unit with acceptable quality, we determined the lowest reaction time for each CPO-27-M, in order to achieve the highest STY.

Influence of the pH

We systematically studied a series of reactions that varied by total molar ratio (2:1: x :304, where $x = 2, 3, 4, 5$ and 6), in order to determine the optimum x in terms of purity and reaction yield. In the case of CPO-27-Zn, we found that an unidentified crystalline phase was formed at $x = 6$ (pH = 9.10); that a mixture of this amorphous phase and CPO-27-Zn was obtained at $x = 5$ (pH = 8.43); that pure CPO-27-Zn was synthesised at $x = 4$ (pH = 7.20), in a yield of 98%; and that a mixture of CPO-27-Zn and a second crystalline phase was obtained at $x = 2$ (pH = 6.27) and at $x = 3$ (pH = 6.86) (Figure 1a). These results are in concordance with those observed by Sánchez-Sánchez *et al.*⁴⁰ At $x = 2$ and $x = 3$, we

identified the second crystalline phase as $[\text{Zn}(\text{H}_2\text{O})_2(\text{dhtp})]_m$,⁵⁹ in which only the two carboxylate groups—and not the two hydroxyl groups—of dhtp are deprotonated and coordinate to Zn(II) ions (Figure S1†). Interestingly, this coordination is quite different to that observed in CPO-27-Zn, in which the two hydroxyl groups of dhtp are also deprotonated and coordinate to Zn(II) ions. Therefore, we reasoned that a minimum amount of NaOH is required to synthesise pure CPO-27-Zn, and that the optimum amount should be $x = 4$, in order to fully deprotonate the carboxylate and hydroxyl groups of dhtp for their subsequent coordination to Zn(II) ions. To further prove this assumption, we also ran the reaction at $x = 3.25$, $x = 3.5$ and $x = 3.75$. Albeit pure CPO-27-Zn samples were produced, the reaction yields were lower (yields: 86%, 93% and 95%, respectively) compared to that obtained at $x = 4$ (yield: 98%).

We then extended the aforementioned systematic study to the other metal ions. Importantly, we found that $x = 4$ was also optimal for the water-based synthesis of CPO-27-Ni, CPO-27-Co and CPO-27-Mg at room temperature. However, the final products of the reactions in which x was altered, varied slightly depending on the metal ion. In the case of CPO-27-Ni, a second crystalline phase mixed with CPO-27-Ni was observed at $x = 2$ (pH = 5.92) (Figure 1b). From $x = 3$ to $x = 5$, pure CPO-27-Ni samples were synthesised in yields of 62% ($x = 3$; pH = 6.77), 93% ($x = 4$; pH = 7.84) and 72% ($x = 5$; pH = 8.99). However, unidentified amorphous solid was formed at $x = 6$ (pH = 12.10). For CPO-27-Co, pure samples were synthesised in yields of 13% ($x = 2$; pH = 5.64), 55% ($x = 3$; pH = 5.96) and 98% ($x = 4$; pH = 8.03) (Figure 1c). At $x = 5$ (pH = 10.04) and $x = 6$ (pH = 11.05), the precipitation of amorphous solids was observed. Finally, in the case of CPO-27-Mg, no precipitation occurred at $x = 2$ (pH = 4.61), whereas pure CPO-27-Mg samples were synthesised in yields of 48% ($x = 3$; pH = 8.08) and 91% ($x = 4$; pH = 9.18) (Figure 1d). As with the cobalt MOF, amorphous solids were obtained at $x = 5$ (pH = 10.36) and $x = 6$ (pH = 11.95). Notice here that when the pH values are higher than 10, amorphous and unknown phases are formed in all cases. This observation is in concordance with the fact that these metal ions are not present as solvated ions above this pH, according to their Pourbaix diagrams.⁶⁰

Interestingly, we observed completely different behaviour for the reaction of dhtp with Cu(II) ions at the different x than that which we had observed for the other metals. We did not observe formation of CPO-27-Cu in any of the reactions, but we did observe an unknown phase that did not correspond to any reported phase resulting from the association of dhtp and Cu(II) ions (Figure S2†). A potential explanation for such differences could be the trend of Cu(II) ions to form $\text{Cu}(\text{OH})_2$ phases, even at pH < 7. Indeed, by comparing the Pourbaix diagrams of the different metal ions at a concentration of $\sim 0.3 \text{ mol L}^{-1}$, one can observe that Ni(II), Zn(II), Mg(II) and Co(II) ions are stable as solvated ions until pH = 7, whereas Cu(II) ions show a higher tendency to form $\text{Cu}(\text{OH})_2$ at this pH.⁶⁰

We then determined the S_{BET} values of the different CPO-27-M synthesised at the optimum NaOH concentration ($x = 4$), finding values of $900 \text{ m}^2 \text{ g}^{-1}$ (CPO-27-Zn), $650 \text{ m}^2 \text{ g}^{-1}$ (CPO-27-Ni), $1310 \text{ m}^2 \text{ g}^{-1}$ (CPO-27-Co) and $1020 \text{ m}^2 \text{ g}^{-1}$ (CPO-27-Mg). Based on these values, we determined that the CPO-27-Zn and CPO-27-Co were of sufficiently good quality and that their S_{BET} respective values fell above the 90 % of the maximum reported S_{BET} (Table 1).

Effect of the concentrations of the reagents

Having determined that the CPO-27-Ni and CPO-27-Mg products did not pass our quality threshold, we sought to find the maximum concentration of reagents that would provide good quality S_{BET} in their respective syntheses. To this end, we decreased C_1 and C_2 . Thus, we systematically varied C_1 and C_2 (maintaining the molar ratio Met/dhtp/NaOH = 2:1:4; $C_1 = 0.273 \text{ mol L}^{-1}$, 0.182 mol L^{-1} , 0.137 mol L^{-1} , 0.091 mol L^{-1} and 0.069 mol L^{-1}) used in the synthesis of CPO-27-Ni and of CPO-27-Mg. Under the studied conditions, the highest C_1 and C_2 values that provided CPO-27-Ni (yield = 76%) with a good S_{BET} ($1350 \text{ m}^2 \text{ g}^{-1}$) were $C_1 = 0.069 \text{ mol L}^{-1}$ and $C_2 = 0.0345 \text{ mol L}^{-1}$. Note here that lower reagent concentrations led to a CPO-27-Ni that exhibited greater crystallinity and an enhanced S_{BET} (Table S1 and Figure S3†). In the case of CPO-27-Mg, the optimal C_1 and C_2 were 0.273 mol L^{-1} and 0.137 mol L^{-1} , respectively. Under these conditions, CPO-27-Mg, obtained in good yield (96%), exhibited an S_{BET} of $1337 \text{ m}^2 \text{ g}^{-1}$ (Table S1 and Figure S4†). However, in this case the use of lower reagent concentrations produced CPO-27-Mg of lesser crystallinity. We compared these results to those for CPO-27-Ni, and tentatively attributed the difference to the need for a critical concentration of dhtp to break the highly stable $[\text{Mg}(\text{H}_2\text{O})_x]$ complexes in water and form the MOF.

Influence of the reaction time

Once we had determined the highest C_1 and C_2 , we finally evaluated the minimum reaction time that enables synthesis of each CPO-27-M (Table S2†). For this, we performed a series of reactions decreasing the reaction times from 24 h to 5 min. For each reaction, we determined the yield and we characterised the resulting solids by XRPD and BET analysis. For all samples that passed our quality S_{BET} control threshold, we calculated the STY, taking into account the precursor concentrations, the yield and the reaction time (Table 2).

The minimum reaction times for CPO-27-Ni and -Mg were found to be 6 h and 4 h, respectively (Figures S5,6†). At these times, the synthesised CPO-27-Ni showed a S_{BET} of $1220 \text{ m}^2 \text{ g}^{-1}$ (yield = 92%), whereas CPO-27-Mg showed a S_{BET} of $1376 \text{ m}^2 \text{ g}^{-1}$ (yield = 81%) (Figure S9†). Taking into account these values, the STYs of these processes were $44 \text{ Kg m}^{-3} \text{ day}^{-1}$ for CPO-27-Ni and $191 \text{ Kg m}^{-3} \text{ day}^{-1}$ for CPO-27-Mg. Figure 2a,b shows representative Scanning Electron Microscopy (SEM) images for both materials, revealing the formation of CPO-27-Ni nanoparticles (mean size = $44 \pm 7 \text{ nm}$) and hexagonal rod-like crystals of CPO-27-Mg (length = $1.1 \pm 0.2 \mu\text{m}$; width = $0.7 \pm 0.1 \mu\text{m}$). In the case of CPO-27-Co (Figure S7†), the minimum reaction time was 1 h, which provided nanoparticles (mean size = $24 \pm 5 \text{ nm}$) in 90% yield and with an S_{BET} of $962 \text{ m}^2 \text{ g}^{-1}$ (Figures 2c and S9†). The resulting STY of this reaction was $1462 \text{ Kg m}^{-3} \text{ day}^{-1}$. Notice here that in the case of CPO-27-Ni and -Co nanoparticles, the use of a centrifugation step instead of a conventional filtration step may be required for collecting them. This limiting step should also be considered in a realistic industrial production using this room temperature water-based synthesis.

However, the most surprising result that we found was for CPO-27-Zn (Figure S8†), which we were able to synthesise in only 5 min, in an excellent yield of 92% and with an S_{BET} of $1154 \text{ m}^2 \text{ g}^{-1}$ (Figure S9†). Under these conditions, the STY of the process was as high as

17986 Kg m⁻³ day⁻¹. Importantly, we also proved that this 5 min water-based synthesis of CPO-27-Zn is reproducible and can be synthesized at least to the gram scale (Figure 2d,e). To scale up the reaction, we used the same conditions described above, except that we used larger quantities of each reagent (40.1 g Zn(Ac)₂; 18.1 g dhtp; 14.6 g NaOH; and 0.5 L H₂O) and a 1-L reactor. After only 5 min of reaction, 32.5 g (97% yield) of pure CPO-27-Zn (S_{BET} = 1076 m² g⁻¹) was collected (Figure S10†). Based on these experimental conditions, the STY of this gram-scale process was 18720 kg m⁻³ day⁻¹. Figure 2d,f shows SEM images for CPO-27-Zn synthesised at the milligram and gram scale, revealing the formation of hexagonal rod-like crystals in both cases. The length of CPO-27-Zn crystals synthesised at the gram scale (length = 9.3 ± 1.3 μm; width = 1.3 ± 0.3 μm) was slightly larger than those synthesised at the milligram scale (length = 5.5 ± 0.5 μm; width = 1.5 ± 0.6 μm). This difference is probably due to the sensitivity of the nucleation, and the crystal growth of CPO-27-Zn, to experimental factors such as the stirring homogeneity and rate.

Finally, the differences in the synthesis reaction rates of CPO-27-M materials [Zn(II) > Co (II) > Mg (II) > Ni (II)] may be explained as a result of the inertness or lability of the metal ions in the ligand exchange process. According with the water exchange rate constants of the complexes [M(H₂O)_x]²⁺, the lability of the metal ions follows the order of Zn(II) > Co (II) > Mg (II) > Ni (II).⁶¹ As a consequence, the reaction rate between a highly labile [Zn(H₂O)_x]²⁺ with a deprotonated ligand should be faster than the less labile [Co(H₂O)_x]²⁺. In fact, these results are consistent with previous studies reported for the synthesis of CPO-27 materials under different reaction conditions, also showing that ligand exchange kinetics depends of the lability of the metals ions, being the determining step in the reaction between the deprotonated dhtp and the metal ions.^{62, 63}

Optimisation of the room temperature water-based synthesis of CPO-27-M in terms of BET surface area

Given that the conditions that provide an optimal STY do not generally deliver the best quality MOF, we further evaluated the maximum achievable S_{BET} values for each CPO-27-M synthesised through the aforementioned reaction. By systematically modifying the same parameters (mainly, the precursor concentrations and the reaction time; Table 2), we ultimately observed that the S_{BET} values for CPO-27-Ni and CPO-27-Co increased with decreasing reagent concentrations and increasing reaction times. The best S_{BET} values were 1351 m² g⁻¹ for CPO-27-Ni (reaction time = 24 h; C_1 = 0.069 mol L⁻¹; yield = 76%; STY = 9 Kg m⁻³ day⁻¹) and 1572 m² g⁻¹ for CPO-27-Co (reaction time = 24 h; C_1 = 0.045 mol L⁻¹; yield = 93%; STY = 16 Kg m⁻³ day⁻¹). On the contrary, the S_{BET} values for CPO-27-Zn and CPO-27-Mg increased with increasing precursor concentrations and decreasing reaction times. The maximum S_{BET} values were found to be 1279 m² g⁻¹ for CPO-27-Zn (reaction time = 10 min; C_1 = 0.364 mol L⁻¹; yield = 98%; STY = 9501 Kg m⁻³ day⁻¹) and 1603 m² g⁻¹ for CPO-27-Mg (reaction time = 6 h; C_1 = 0.182 mol L⁻¹; yield = 94%; STY = 98 Kg m⁻³ day⁻¹) (Figure S11†). Interestingly, all these synthesised CPO-27-M crystals showed similar morphologies and sizes in comparison to those obtained for the highest STYs (Figure S12†).

Conclusions

We have reported the stepwise optimisation of the room temperature, water-based synthesis of several members of the CPO-27/MOF-74-M series of MOFs, including ones made from Mg(II), Ni(II), Co(II) and Zn(II) ions. We evaluated the main reaction parameters affecting this method and found that by fine-tuning the pH, reagent concentrations and reaction time for each case, we were able to fabricate CPO-27-M with excellent BET surface areas (up to 1603 m² g⁻¹) and unprecedented STYs (as high as 18720 Kg m⁻³ day⁻¹). The development of such green syntheses, which obviate the use of costly and harmful organic solvents yet enable the efficient fabrication of high quality MOFs, should ultimately facilitate the industrial exploitation of these materials.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgements

This work was supported by the Spanish MINECO (project PN MAT2012-30994) and the EC (project FP7 ERC-Co 615954). I.I. acknowledges the Spanish MINECO for a Ramón y Cajal grant. ICN2 acknowledges support of the Spanish MINECO through the Severo Ochoa Centres of Excellence Program (Grant SEV-2013-0295).

References

- [1]. Special issue on metal-organic framework materials. Chem Soc Rev. 2009;1201.
- [2]. Special issue on metal-organic framework materials. Chem Soc Rev. 43:5403.
- [3]. Furukawa H, Ko N, Go YB, Aratani N, Choi SB, Choi E, Yazaydin AÖ, Snurr RQ, O’Keeffe M, Kim J, Yaghi OM. Science. 2010; 329:424–428. [PubMed: 20595583]
- [4]. Horcajada P, Gref R, Baati T, Allan PK, Maurin G, Couvreur P, Ferey G, Morris RE, Serre C. Chem Rev. 2012; 112:1232–1268. [PubMed: 22168547]
- [5]. Allendorf MD, Stavila V. CrystEngComm. 2015; 17:229–246.
- [6]. Carné A, Carbonell C, Imaz I, Maspoch D. Chem Soc Rev. 2011; 40:291–305. [PubMed: 21107481]
- [7]. Stock N, Biswas S. Chem Rev. 2012; 112:933–969. [PubMed: 22098087]
- [8]. Mueller U, Schubert M, Teich F, Puetter H, Schierle-Arndt K, Pastre J. J Mater Chem. 2006; 16:626–636.
- [9]. James SL, Adams CJ, Bolm C, Braga D, Collier P, Friscic T, Grepioni F, Harris KD, Hyett G, Jones W, Krebs A, et al. Chem Soc Rev. 2012; 41:413–447. [PubMed: 21892512]
- [10]. Martinez Joaristi A, Juan-Alcañiz J, Serra-Crespo P, Kapteijn F, Gascon J. Cryst Growth Des. 2012; 12:3489–3498.
- [11]. Rubio-Martinez M, Batten MP, Polyzos A, Carey K-C, Mardel JI, Lim K-S, Hill MR. Sci Rep. 2014; 4
- [12]. Bayliss PA, Ibarra IA, Perez E, Yang S, Tang CC, Poliakoff M, Schroder M. Green Chem. 2014; 16:3796–3802.
- [13]. Carné-Sánchez A, Imaz I, Cano-Sarabia M, Maspoch D. Nat Chem. 2013; 5:203–211. [PubMed: 23422562]
- [14]. Gaab M, Trukhan N, Maurer S, Gummaraju R, Müller U. Microporous Mesoporous Mater. 2012; 157:131–136.
- [15]. Rosi NL, Kim J, Eddaoudi M, Chen B, O’Keeffe M, Yaghi OM. J Am Chem Soc. 2005; 127:1504–1518. [PubMed: 15686384]
- [16]. Dietzel PDC, Morita Y, Blom R, Fjellvåg H. Angew Chem Int Ed. 2005; 44:6354–6358.

- [17]. Valvekens P, Vandichel M, Waroquier M, Van Speybroeck V, De Vos D. *J Catal.* 2014; 317:1–10.
- [18]. Allan PK, Wheatley PS, Aldous D, Mohideen MI, Tang C, Hriljac JA, Megson IL, Chapman KW, De Weireld G, Vaesen S, Morris RE. *Dalton Trans.* 2012; 41:4060–4066. [PubMed: 22378060]
- [19]. McDonald TM, Mason JA, Kong X, Bloch ED, Gygi D, Dani A, Crocella V, Giordanino F, Odoh SO, Drisdell WS, Vlasisavljevič B, et al. *Nature.* 2015; 519:303–308. [PubMed: 25762144]
- [20]. Zhou W, Wu H, Yildirim T. *J Am Chem Soc.* 2008; 130:15268–15269. [PubMed: 18950163]
- [21]. Bao Z, Alnemrat S, Yu L, Vasiliev I, Ren Q, Lu X, Deng S. *Langmuir.* 2011; 27:13554–13562. [PubMed: 21942644]
- [22]. Grant Glover T, Peterson GW, Schindler BJ, Britt D, Yaghi O. *Chem Eng Sci.* 2011; 66:163–170.
- [23]. Wang N, Mundstock A, Liu Y, Huang A, Caro J. *Chem Eng Sci.* 2015; 124:27–36.
- [24]. Li L, Yang J, Li J, Chen Y, Li J. *Microporous Mesoporous Mater.* 2014; 198:236–246.
- [25]. Rosnes MH, Opitz M, Frontzek M, Lohstroh W, Embs JP, Georgiev PA, Dietzel PDC. *J Mater Chem A.* 2015; 3:4827–4839.
- [26]. Peng Y, Krungleviciute V, Eryazici I, Hupp JT, Farha OK, Yildirim T. *J Am Chem Soc.* 2013; 135:11887–11894. [PubMed: 23841800]
- [27]. Wu H, Zhou W, Yildirim T. *J Am Chem Soc.* 2009; 131:4995–5000. [PubMed: 19275154]
- [28]. Lee K, Howe JD, Lin L-C, Smit B, Neaton JB. *Chem Mater.* 2014
- [29]. Kong X, Scott E, Ding W, Mason JA, Long JR, Reimer JA. *J Am Chem Soc.* 2012; 134:14341–14344. [PubMed: 22908934]
- [30]. Britt D, Furukawa H, Wang B, Glover TG, Yaghi OM. *PNAS.* 2009; 106:20637–20640. [PubMed: 19948967]
- [31]. Caskey SR, Wong-Foy AG, Matzger AJ. *J Am Chem Soc.* 2008; 130:10870–10871. [PubMed: 18661979]
- [32]. Mason JA, McDonald TM, Bae TH, Bachman JE, Sumida K, Dutton JJ, Kaye SS, Long JR. *J Am Chem Soc.* 2015; 137:4787–4803. [PubMed: 25844924]
- [33]. Remy T, Peter SA, Van der Perre S, Valvekens P, De Vos DE, Baron GV, Denayer JFM. *The Journal of Physical Chemistry C.* 2013; 117:9301–9310.
- [34]. Guasch J, Dietzel PDC, Collier P, Acerbi N. *Microporous Mesoporous Mater.* 2015; 203:238–244.
- [35]. Dietzel PDC, Besikiotis V, Blom R. *J Mater Chem.* 2009; 19:7362–7362.
- [36]. Dietzel PDC, Morita Y, Blom R, Fjellvåg H. *Angew Chem Int Ed.* 2005; 44:6354–6358.
- [37]. Ruyra À, Yazdi A, Espín J, Carné-Sánchez A, Roher N, Lorenzo J, Imaz I, Maspoch D. *Chem Eur J.* 2015; 21:2508–2518. [PubMed: 25504892]
- [38]. Cadot S, Veyre L, Luneau D, Farrusseng D, Alessandra Quadrelli E. *J Mater Chem A.* 2014; 2:17757–17763.
- [39]. Tranchemontagne DJ, Hunt JR, Yaghi OM. *Tetrahedron.* 2008; 64:8553–8557.
- [40]. Sanchez-Sanchez M, Getachew N, Diaz K, Diaz-Garcia M, Chebude Y, Diaz I. *Green Chem.* 2015
- [41]. Wang LJ, Deng H, Furukawa H, Gándara F, Cordova KE, Peri D, Yaghi OM. *Inorg Chem.* 2014; 53:5881–5883. [PubMed: 24878113]
- [42]. Weissmehl, K.; Arpe, H-J. *Industrial Organic Chemistry.* Wiley-VCH Verlag GmbH; 2007. p. 424-438.
- [43]. Czaja AU, Trukhan N, Muller U. *Chem Soc Rev.* 2009; 38:1284–1293. [PubMed: 19384438]
- [44]. Perry JJ, Teich-McGoldrick SL, Meek ST, Greathouse JA, Haranczyk M, Allendorf MD. *The Journal of Physical Chemistry C.* 2014; 118:11685–11698.
- [45]. Díaz-García M, Mayoral Á, Díaz I, Sánchez-Sánchez M. *Cryst Growth Des.* 2014; 14:2479–2487.
- [46]. Ruano D, Díaz-García M, Alfayate A, Sánchez-Sánchez M. *ChemCatChem.* 2015; 7:674–681.
- [47]. Wu X, Bao Z, Yuan B, Wang J, Sun Y, Luo H, Deng S. *Microporous Mesoporous Mater.* 2013; 180:114–122.
- [48]. Lee D-J, Li Q, Kim H, Lee K. *Microporous Mesoporous Mater.* 2012; 163:169–177.
- [49]. Cho H-Y, Yang D-A, Kim J, Jeong S-Y, Ahn W-S. *Catal Today.* 2012; 185:35–40.

- [50]. Dietzel PDC, Blom R, Fjellvåg H. Eur J Inorg Chem. 2008; 2008:3624–3632.
- [51]. Leung, E.; Müller, U.; Trukhan, N.; Mattenheimer, H.; Cox, G.; Blei, S. Patentanmeldung 10183283.01. 2010.
- [52]. Alvarez E, Guillou N, Martineau C, Bueken B, Van de Voorde B, Le Guillouzer C, Fabry P, Nouar F, Taulelle F, de Vos D, Chang J-S, et al. Angew Chem Int Ed. 2015 n/a-n/a.
- [53]. Huo J, Brightwell M, El Hankari S, Garai A, Bradshaw D. J Mater Chem A. 2013; 1:15220–15223.
- [54]. Seo Y-K, Yoon JW, Lee JS, Lee UH, Hwang YK, Jun C-H, Horcajada P, Serre C, Chang J-S. Microporous Mesoporous Mater. 2012; 157:137–145.
- [55]. Düren T, Millange F, Férey G, Walton KS, Snurr RQ. J Phys Chem C. 2007; 111:15350–15356.
- [56]. Rouquerol, J.; Rouquerol, F.; Llewellyn, P.; Maurin, G.; Sing, KSW. Adsorption by Powders and Porous Solids: Principles, Methodology and Applications. Elsevier Science; 2013.
- [57]. Llewellyn, P.; Reinoso, FR.; Rouquerol, J.; Seaton, N. Characterization of Porous Solids VII: Proceedings of the 7th International Symposium on the Characterization of Porous Solids (COPS-VII), Aix-en-Provence; France. 26-28 May 2005; Elsevier Science; 2006.
- [58]. Wang LJ, Deng H, Furukawa H, Gándara F, Cordova KE, Peri D, Yaghi OM. Inorg Chem. 2014; 53:5881–5883. [PubMed: 24878113]
- [59]. Ghermani NE, Morgant G, d' Angelo J, Desmaële D, Fraisse B, Bonhomme F, Dichi E, Sgahier M. Polyhedron. 2007; 26:2880–2884.
- [60]. Wulfsberg, G. Principles of Descriptive Inorganic Chemistry. University Science Books; 1991.
- [61]. Housecroft, CE.; Sharpe, AG. Inorganic Chemistry. Pearson Prentice Hall; 2012.
- [62]. El Osta R, Feyand M, Stock N, Millange F, Walton RI. Powder Diffr. 2013; 28:S256–S275.
- [63]. Haque E, Jhung SH. Chem Eng J. 2011; 173:866–872.

Figure 1.

XRPD diffractograms of the collected powder at different NaOH equivalents (Red: $x = 2$, Blue: $x = 3$, Pink: $x = 4$, Green: $x = 5$, orange: $x = 6$) for: a) CPO-27-Zn, b) CPO-27-Ni, c) CPO-27-Co and d) CPO-27-Mg, as compared to the simulated powder pattern for CPO-27 (black).

Figure 2.

Scanning Electron Microscope images of a) CPO-27-Ni, b) CPO-27-Mg, c) CPO-27- Co, d) CPO-27- Zn (mg-scale) and f) CPO-27- Zn (gram-scale) synthesized with the highest STYs. e) Pilot plant stirrer used in the scale-up synthesis of CPO-27- Zn. Scale bars: 1 μm (a, b, c) and 5 μm (d, f).

Table 1Summary of activation methods and S_{BET} values reported for CPO-27-M

CPO-27-M	Activation method	S_{BET} ($\text{m}^2 \text{g}^{-1}$)	References
Zn	at a constant rate of 5°C min^{-1} from 25°C to 270°C , and then held at 270°C for 16 h	816	31
	at a constant rate of 2°C min^{-1} from 25°C to 225°C , and then held at 265°C for 16 h	973	44
	10 h at 150°C , and then 10 h at 265°C	496	22
	18 h at 350°C	867	45
	16 h at 100°C	948	46
	72 h at 100°C	885	27
	Not reported	1039	40
Ni	at a constant rate of 5°C min^{-1} from 25°C to 250°C , and then held at 250°C for 5 h.	1070	31
	at a constant rate of 2°C min^{-1} from 25°C to 225°C , and then held at 265°C for 16 h	1199	44
	5 h at 250°C	599	22
	18 h at 350°C	402	45
	16 h at 100°C	514	46
	19 h at 200°C , and then 1 h at 110°C	1218	35
	20 h at 150°C	1233	38
	12 h at 250°C	1252	47
	6 h at 250°C	1350	26
	72 h at 100°C	1027	27
	Not reported	1018	24
	Not reported	1318	48
Co	at a constant rate of 5°C min^{-1} from 25°C to 250°C , and then held at 250°C for 5 h.	1080	31
	at a constant rate of 2°C min^{-1} from 25°C to 225°C , and then held at 265°C for 16 h	1292	44
	24 h at 250°C	835	22
	18 h at 350°C	521	45
	16 h at 100°C	693	46
	5 h at 250°C	1327	49
	72 h at 100°C	1056	27
	Not reported	1089	24
Mg	at a constant rate of 5°C min^{-1} from 25°C to 250°C , and then held at 250°C for 5 h.	1495	31
	at a constant rate of 2°C min^{-1} from 25°C to 225°C , and then held at 265°C for 16 h	1530	44
	6 h at 250°C	1206	22
	18 h at 350°C	1007	45
	48 h at 240°C , and then 1 h at 110°C .	1542	35
	Not reported	1415	24
	72 h at 100°C	1332	27
	12 h at 250°C	1416	47
	24 h at 250°C	1249	33

CPO-27-M	Activation method	S_{BET} (m ² g ⁻¹)	References
	16 h at 250 °C	877	50

Table 2

Comparison of the synthetic details, yield and S_{BET} values of CPO-27-M synthesised with the highest STY values and the highest S_{BET} values.

CPO-27-M	C_1 (mol L ⁻¹)	C_2 (mol L ⁻¹)	Yield (%)	Time (h)	S_{BET} (m ² g ⁻¹)	V_p (cm ³ g ⁻¹) ^a	STY (kg m ⁻³ day ⁻¹)
Zn (mg scale)	0.364	0.182	92	0.08	1154	0.44	17986
Zn (g scale)	0.365	0.182	97	0.08	1076	0.40	18720
Zn	0.364	0.182	98	0.17	1279	0.47	9501
Co	0.364	0.182	90	1	962	0.39	1462
Co	0.045	0.023	93	24	1572	0.57	16
Mg	0.273	0.137	81	4	1376	0.52	191
Mg	0.182	0.091	94	6	1603	0.60	98
Ni	0.069	0.035	92	6	1220	0.48	44
Ni	0.069	0.036	76	24	1351	0.53	9

^aPore volume was calculated at $P/P_0 = 0.15$ (N₂, 77 K) using the Quantachrome ASiQWin software