Published in final edited form as:

Nanotechnology. 2016 April 1; 27(13): 13LT02. doi:10.1088/0957-4484/27/13/13LT02.

Label-free capture of breast cancer cells spiked in buffy coats using carbon nanotube antibody micro-arrays

Farhad Khosravi¹, Patrick Trainor^{2,3}, Shesh N Rai^{2,3}, Goetz Kloecker⁴, Eric Wickstrom⁵, and Balaji Panchapakesan¹

Balaji Panchapakesan: bpanchapakesan@wpi.edu

¹Department of Mechanical Engineering, Small Systems Laboratory, Worcester Polytechnic Institute, Worcester, MA 01532, USA

²Department of Biostatistics, Biostatistics Shared Facility, James Graham Brown Cancer Center, University of Louisville, Louisville, KY 40292, USA

³Department of Bioinformatics and Biostatistics, University of Louisville, Louisville, KY 40292, USA

⁴Hematology and Oncology, James Graham Brown Cancer Center, University of Louisville, Louisville, KY 40292, USA

⁵Department of Biochemistry and Molecular Biology, Kimmel Cancer Center, Thomas Jefferson University, Philadelphia, PA 19130, USA

Abstract

We demonstrate the rapid and label-free capture of breast cancer cells spiked in buffy coats using nanotube-antibody micro-arrays. Single wall carbon nanotube arrays were manufactured using photo-lithography, metal deposition, and etching techniques. Anti-epithelial cell adhesion molecule (EpCAM) antibodies were functionalized to the surface of the nanotube devices using 1-pyrene-butanoic acid succinimidyl ester functionalization method. Following functionalization, plain buffy coat and MCF7 cell spiked buffy coats were adsorbed on to the nanotube device and electrical signatures were recorded for differences in interaction between samples. A statistical classifier for the ‘liquid biopsy’ was developed to create a predictive model based on dynamic time warping to classify device electrical signals that corresponded to plain (control) or spiked buffy coats (case). In training test, the device electrical signals originating from buffy versus spiked buffy samples were classified with ~100% sensitivity, ~91% specificity and ~96% accuracy. In the blinded test, the signals were classified with ~91% sensitivity, ~82% specificity and ~86% accuracy. A heatmap was generated to visually capture the relationship between electrical signatures and the sample condition. Confocal microscopic analysis of devices that were classified as spiked buffy coats based on their electrical signatures confirmed the presence of cancer cells, their attachment to the device and overexpression of EpCAM receptors. The cell numbers were counted to be ~1—17 cells per 5 μ l per device suggesting single cell sensitivity in spiked buffy coats that is scalable to higher volumes using the micro-arrays.

Keywords

carbon nanotube; micro-arrays; cancer cells; buffy coats; fine needle aspirates; circulating tumor cells

1. Introduction

Commercially available nucleic acid microarrays allow sensitive identification of thousands of DNA sequences simultaneously [1–5]. However, they cannot capture many changes in cellular response and function in many cases which are carried out by proteins. The cellular proteomic profiles, which is directly relevant for disease detection, label-free high-throughput diagnostics has, however, remained a challenge and sample handling to get a complete proteomic profile is also challenging and enormous in some cases [6].

Techniques that have been developed for protein analysis include: flow cytometry [7], fluorescent reporting of antigen– antibody binding [8], time-of-flight mass spectroscopy [9], electrophoretic separation [10], label-free detection of changes in surface mechanical properties due to antigen–antibody binding using micro-cantilevers [11], change in electronic properties using silicon nanowires [12] and carbon nanotubes due to biomarker interaction [13]. The cellular proteomic analysis that is important for auto-immune diseases, label-free devices are rare [14]. Some of these devices have focused on understanding how device properties change on cellular attachment or detachment after growth on the substrates and the drug interaction [15].

Recent progress in area of isolation of rare cells has used different techniques namely immunomagnetic methods [16], microfluidic chips [17, 18] laser scanning cytometry [19], and nano-Velcro array [20] to name a few and has created the need for capturing and molecular profiling of cells based on their biomarkers for targeted therapy. While these above mentioned devices have used large volumes of blood (~7.5 ml) to isolate circulating cancer cells using microfluidic devices, magnetic devices for fine needle aspirates (1 μ l) has also been reported to capture and analyze single cells [21], thereby showing the importance of capturing cells and profiling their biomarkers in small and large volume samples. Current technologies namely ELISA or Western blots for measuring protein concentrations are painstakingly slow and need skilled personnel for accurate results. Therefore, devices that can capture single cancer cells in highly complex medium such as blood/buffy coats in rapid, low cost and high throughput fashion with the capability to profile them for their biomarker can result in significant clinical impact.

In this study we present capture of breast cancer cells spiked in buffy coats using carbon nanotube micro-arrays functionalized with anti-epithelial cell adhesion molecule (EpCAM) antibodies and their stratification based on their electrical signatures using classifier based on dynamic time warping (DTW). EpCAM, is a mesenchymal marker that is overexpressed in all epithelial cancer cells [22, 23]. EpCAM is overexpressed in carcinomas and also is upregulated in metastases thereby making it a highly valuable diagnostic marker [24]. A multiplexed micro-array of nanotube sensors functionalized with anti-EpCAM antibodies enables measurement of electrical signatures of specific and non-specific interactions as

characteristic spikes in conductance versus time data. These signatures are then analyzed using DTW technique to develop heatmap with integrated dendrogram to enable classification of the electrical signatures and relate it to their sample condition (MCF7 spiked buffy or plain buffy), for the ease of reference, we call cases and controls. The experiments demonstrated 'spikes' in electrical device signatures in cell cultures and cancer cells spiked in buffy coats with natural partitioning between plain buffy coats and spiked buffy coats using nanotube-antibody arrays. To predict classification between cases and controls, the training set data indicated ~100% sensitivity, ~90% specificity, and ~96% accuracy in classifying devices that corresponded to un-spiked and spiked buffy coats based on their electrical signatures. A blinded test to classify case and control samples revealed ~91% sensitivity, ~90% specificity, and ~86% accuracy. Staining of captured cells on the device based on electrical signatures using confocal microscopy revealed the overexpression of EpCAM with each device capable of capturing anywhere from 1 to 17 cells per device suggesting single cell sensitivity. Our demonstration of the combination of multiplexed micro-arrays, sensitive nanotube elements and statistical data mining enables a new line of thought in developing devices for isolation of cells based on their mesenchymal biomarker profiles both in fine needle aspirates and for large volume samples in isolation and analysis of circulating tumor cells.

2. Methods

2.1. CNT-network formation

The first step in the process is assembling the nanotube network. Iso-semiconducting single wall carbon nanotubes were purchased from Nanointegris LLC. The manufacturer specified diameter was in the range of 1.2 nm to 1.7 nm and length was in the range of 300 nm to 5m. Nanotubes were suspended in surfactant solution at 1 mg/100ml as received. 100 μ l, 200 μ l and 400 μ l of the stock solution was then mixed with 85 ml of DI water and 15 ml of 1% w/v sodium dodecyl sulfate (Sigma-Aldrich, Cat. No. 436143), for a final concentration of 1, 2 and 4 μ g/100 ml.

2.2. Vacuum filtration

The 100 ml solutions each were vacuum filtered over a cellulose membrane, 0.05 μ m pore size (Millipore, No. VMWP09025). Three CNT film networks were generated at three different concentrations. The vacuum filtration method self-regulates the deposition rate of nanotubes on the membrane to produce an evenly distributed conductive network. The CNT film network was then pressed onto a dry oxidized (300 nm thickness) 4" silicon wafer for 30 min. Next the wafer was transferred to an acetone vapor bath that dissolved the overlaying filter membrane.

2.3. Clean room processing

Patterning of the nanotube film and electrode and insulating layer fabrication were done by photolithography in the cleanroom. The S1813 photoresist was used to mask the nanotube film areas needed for the sensor elements. Exposed nanotubes were etched away in a March reactive ion etcher for 90 s at 200 W power and 10% O₂. The S1813 photoresist was also used to mask the electrode pattern. Electrodes, 15 nm Ni and a 90 nm Au layers, were

deposited by sputtering in a Leskar PVD 75 system, 300 W DC power. Lift-off process was conducted in an acetone bath to remove the excess Ni/Au layers. Lastly, the sensors were covered with SU8–2005, a 5 μm thick photopolymer layer. A window over each of the nanotube sensor elements was developed, but the electrodes remain insulated beneath the SU8.

2.4. Raman spectroscopy

Raman analysis was done at an excitation wavelength of ~ 532 nm using a XploRA Raman spectrometer (Horiba Scientific). The laser beam is focused onto the surface of the CNT film on top of a Si wafer substrate through a $50\times$ objective lens. This measurement was repeated six times at different locations of the sample. The RBM (172 cm^{-1}), Si (518 cm^{-1}), D (1340 cm^{-1}), G (1590 cm^{-1}), and 2D (2673 cm^{-1}) peaks were identified throughout the sample.

2.5. Device functionalization

Finished carbon nanotube sensors were functionalized with anti-EpCAM by a pyrene linker molecule. The pyrene rings of 1-pyrenebutanoic acid, succinimidyl ester (PASE AnaSpec #81238) adsorb onto carbon nanotube sidewalls by π -stacking. The ester on the other end of the molecule provided an attachment point for antibodies. PASE (AnaSpec, Cat. No. 81238) was dissolved in methanol at 1 mM. Devices were incubated in the PASE solution for 2 h at room temperature, and then rinsed with methanol and then DI water. Devices were then incubated in Anti-EpCAM (EMD Bioscience, Cat. No. OP187) or anti-IgG (EMD Millipore, Cat. No. 411550), $20\text{ }\mu\text{g ml}^{-1}$ in 1X PBS, for 2 h at room temperature. After incubation, devices were rinsed in DI water 3X. Tween20 was used to block unfunctionalized nanotube sidewalls to minimize non-specific interactions. Devices were incubated with 0.5% Tween20 for 2 h at room temperature. After incubation, devices were washed with water, then incubated in 5 μl droplets of PBS overnight in a humid chamber at $4\text{ }^{\circ}\text{C}$ before testing.

2.6. Hg^{2+} and NH_4^{+} ion experimentation

HgCl_2 (Sigma-Aldrich, Cat. No. 215465) in DI water was prepared to create Hg^{2+} ions with concentrations ranging from 30 pM to 13 μM . Similarly, NH_4OH (Sigma-Aldrich, Cat. No. 338818) in DI water was prepared with concentrations ranging from 300 nM to 1.5 mM. Array of un-functionalized bare devices were prepared with initial 5 μl droplet of DI water suspended on top. 100 mV source drain bias and 0 V gate voltage applied by reference Ag/AgCl electrode. Device current was monitored as ion concentrations were increased on the devices every 180 s. In addition voltage-sweep readings were taken after addition of each ion concentration.

2.7. Cell culture and preparation

The breast adenocarcinoma cell line, MCF7, MCF10 A and SKBR3 (ATCC, Cat. No. HTB-22; CRL-10317; HTB-30), was cultured under conditions as recommended by the supplier. MCF10 A is non-tumorigenic cells that are EpCAM negative and MCF7 and SKBR3 are EpCAM positive cell lines. Cells were grown for 3–4 days to reach $\sim 80\%$ confluence. The cells were then detached using Accutase solution (Sigma, Cat. No. A6964), centrifuged and resuspended in 1X PBS at $10\text{ }000\text{ cells }\mu\text{l}^{-1}$. This solution was used to spike

the healthy buffy coat sample (James Graham Brown Cancer Center, Study No. C020-01) at 1:1 ratio for a final MCF7 concentration of 10 000 cells μl^{-1} .

2.8. Confocal microscopy

After experimental data had been collected, the devices were saved and taken for staining and confocal imaging. The devices were first rinsed with PBS to remove excess cells and buffy coat fragments and then incubated with 4% paraformaldehyde (Santa Cruz Biotechnology Inc., Cat. No. sc-281692). After initial preparation device were stained with anti-EpCAM (EMD Bioscience, Cat. No. OP187) primary antibody, anti-mouse IgG-TR (Santa Cruz Biotechnology Inc., Cat. No. sc-2781) Texas Red conjugated secondary antibody, and DAPI (Molecular Probes, Cat. No. D1306) according to the standard confocal staining protocol. A coverslip was placed on top of each device and sealed before imaging. Confocal laser scanning microscopy images were obtained on a Nikon Eclipse T. with coverslip corrected objective focused at 600 $\times$.

2.9. Antibody functionalization studies using gold nanoparticles

Similar to device functionalization process, devices were prepared and functionalized. Instead of using anti-EpCAM, an antibody conjugated gold NPs (Nanopartz, Cat. No. C11–15-TX-50) were used to functionalize with the PASE linker molecule. The NPs were diluted 1:250 in 1XPBS and incubated on top of the device for 2 h. Finally, devices were rinsed with water 3X and samples were taken to SEM for imaging.

2.10. Device testing

The testing platform was set up on Signatone probe station. Agilent 4156C Semiconductor Parameter Analyzer equipped with a custom LabVIEW interface was used for monitoring the sensors and data collection. 100 mV bias was applied and the source–drain current, I_{SD} , was recorded for the duration of the test. The accuracy of the semiconductor parameter analyzer is 1 fA. The entire probe station assembly is placed on an optical table that is vibration isolated using air on all four legs. A metal box covers the entire assembly to avoid electromagnetic interference. The probes are connected to the parameter analyzer using a triaxial cable that is EM shielded. Throughout the testing the devices were maintained inside a humidified chamber to prevent evaporation of the sample droplet. The testing protocol started with a hydrated device, and a 5 μl droplet of 1X PBS, which was placed immediately after functionalization and left overnight. The bias was applied, and the sensor was monitored for the initial 3 min, then 5 μl droplets of the sample solution, 1X PBS or buffy coat suspension, was pipetted directly into the standing 5 μl droplets. Devices were monitored for 360 s after each addition of a new sample solution. The total duration of one test varied from 540 to 1980 s. To compare results among devices, I_{SD} data were normalized to obtain the G/G_0 values for conductance. The sensor element was also imaged on an optical microscope to confirm the presence of cancer cells. The spiked buffy coat samples consisted of 10 000 MCF7 cells μl^{-1} for these experiments. Such concentration was chosen to cover consistently the active sensor element surface with 1–30 cells at the sensor window for assessing cell capture per device.

2.11. Statistical classifier

Statistical classification was done using DTW package in R. The sensitivity, specificity, and misclassification rate were then computed, considering Spiked Buffy to be a positive test and Buffy to be a negative test. Sensitivity is defined as TP/P , where TP denotes the number of positive test outcomes, and P denotes the number of true positives. Specificity is defined as TN/N , where TN denotes the number of negative test outcomes, and N denotes the number of true negatives.

3. Results

Figure 1 presents the schematic of the sensing technique. Biomolecular reactions are driven thermodynamically by the reduction in free energy of the system. For specific interactions, the reduction in free energy should be higher than nonspecific interactions as presented in equation (1) [25]. It is this thermodynamic advantage of specific interactions that is the hall mark of living systems which enables a high degree of control in biological processes. Otherwise, non-specific interactions would prevail resulting in loss of cellular specificity and directionality in function [25]. One can use a spectrum of energy domains to transduce the change in the free energy of the specific interactions into mechanics, electricity, thermal or magnetism [25]. While label-free sensors have been developed for measuring ultra-low protein concentrations as mentioned before, the measurement of specific versus non-specific binding events in cells as electrical spikes in a fast manner and the ability to stratify them rapidly are rare. If such cellular arrays that are fast, label-free and one that can detect specific versus non-specific interactions at the level of single cells and relate the electrical signatures to their biological condition using advanced classifiers developed, could revolutionize the disease paradigm for isolation and analysis of rare cells

$$\Delta G_{\text{specific}} \gg \Delta G_{\text{non-specific}} \quad (1)$$

Since the reduction in free energy is universal for specific and non-specific pairs, we hypothesize that this should be true for detection of specific versus non-specific interactions in cells. Extracellular overexpressed receptors namely EpCAM interacts with their corresponding anti-EPCAM antibodies on the nanotube surface. The cooperative specific interaction of thousands of extracellular receptors with specific antibodies on nanotube surface creates spikes in the normalized electrical conductance versus time [26]. Non-specific samples such as plain buffy coats also create such spikes in the electrical conductance versus time data with differences in their slopes. The philosophy behind this work is whether such spikes in the signals could carry meaningful information about the sample condition/interaction that could be indicator of disease status.

3.1. Fabrication of nanotube sensor arrays

Figure 2(a) presents the wafer scale image of the 60 element array of nanotube network sensors. The sensor arrays were developed using a combination of vacuum filtration of carbon nanotube network (suppl. figure S1) film onto oxide coated wafers followed by multiple photo-lithography and reactive ion etching as presented in schematic (suppl. figure

S2). Vacuum filtration is one of the most preferred methods of making macroscopic and transparent networks of randomly oriented/highly aligned carbon nanotubes thin films and transistor devices. The film can be formed by using stock solutions of known concentrations. Vacuum filtration of SWNT suspension creates a concentration gradient due to the fluid velocity across the membrane [27]. With appropriate bulk solution concentration and fluid velocity, one can form either isotropic or highly oriented nanotube films [27]. While vacuum filtration has been used, in general, to make randomly oriented bucky papers, recent work by our group has demonstrated the isotropic-nematic transition of semiconducting nanotube films at ultra-low concentrations than what was thought to be achievable [27]. These semiconducting nanotube films are finding applications as thin-film transistors with high mobility and ON/OFF ratio's [27], nanotube liquid crystal elastomer based light-driven actuators [28] and as chemical and biological sensors as presented here. Our films were very low concentrations (1–4 μg) and most of our films were isotropic with the 2–4 μg samples partially transitioning into the nematic domains [27] and also mostly single layers laying on the substrate as shown in the scanning electron microscope (SEM) image of figure 2(b).

Figure 2(c) presents the Raman spectroscopic micrograph of the nanotube network suggesting a very large G band (1590 cm^{-1}), small D band (1340 cm^{-1}) and large 2D band (2673 cm^{-1}). This suggests very low amorphous carbon content. Further, we also measured the I_G/I_D ratio for several networks measured $I_G/I_D \sim 30$ suggesting a low density of defects and suitable for high-quality sensing applications. The Iso-semiconducting nanotubes had iodine as specified by the manufacturer (5% by mass using neutron activation analysis) in the form of iodixanol. This was observed in the shift in radial RBM mode $\omega_r = 174\text{ cm}^{-1}$ suggesting iodine doped nanotubes due to poly iodide ions or I_3^- and I_5^- in the RBM mode at the same excitation wavelength [29]. The iodine also decreased the tangential mode to 1590 cm^{-1} in these samples as compared to pristine nanotube samples (1593 cm^{-1}) in line with past reports [30]. Figure 2(d) shows an array of devices and compares them to a penny with the source, drain, reference Ag/AgCl electrode and sample droplet all in one set-up.

Following fabrication, the devices were investigated for their electrical resistance change with annealing. Figure 3(a) presents the SEM image of the devices made from for different nanotube film concentrations. Films of three different concentrations were made, and devices were fabricated and tested for their electrical properties before and after annealing. It is observed that as the concentration increased so did the network density. At the film concentration of $\sim 1\text{ }\mu\text{g}$, the nanotube contacts were not established at some points, and this is reflected in their high electrical resistance. For samples with higher concentrations, $4\text{ }\mu\text{g}$, uniform network density was observed. We, therefore, used $4\text{ }\mu\text{g}$ films with more directional nanotubes for our studies with optimized electrical properties. The film electrical resistance before and after annealing was measured as presented in figure 3(b). Annealing at $250\text{ }^\circ\text{C}$ decreased the resistance of the devices. It was observed that the decrease in electrical resistance of the device with annealing was directly related to the concentration of the nanotube films. Devices made with $1\text{ }\mu\text{g}$ films registered a larger decrease in electrical resistance of $\sim 95\%$, compared to devices with larger film concentrations ($\sim 57\%$ and $\sim 47\%$ decrease in resistance for $2\text{ }\mu\text{g}$ and $4\text{ }\mu\text{g}$ respectively). The electrical resistivity (ρ) was measured to be in the range of $50\text{ k}\Omega\text{ m}$ for the low concentration $1\text{ }\mu\text{g}$ film to $180\text{ }\Omega\text{ m}$ for the devices made from $4\text{ }\mu\text{g}$ film ($R \sim 10^6 - 10^8\text{ }\Omega$, $l = 100\text{ }\mu\text{m}$ and $W = 80\text{ }\mu\text{m}$). The large

decrease in electrical resistance suggests healing and refining the nanotube network structure to enable stable electrical pathways associated with the device. Figure 3(c) presents the distribution of nanotube device resistance versus number of counts for 58 devices suggesting narrow distribution of network resistance in the $10^6 - 10^7 \Omega$ range and quite repeatable and suitable for further sensing applications. A linear sheet conductance with nanotube film mass suggests samples above the percolation threshold [27]. The table 1 presents the summary of the 4 point probe (1 mm probe spacing) measurements for the sheet resistance before and after annealing and final device resistance. While the low concentrations (1 and 2 μg) yielded highly rarefied nanotubes and much higher decrease in electrical resistance as suggested with annealing, it was difficult to always get a resistance reading due to lack of connection between all the nanotubes in low concentration nanotube devices. Therefore, we optimized our devices for 4 μg nanotube films to provide stable network connectivity and stability were used for all the studies henceforth presented.

3.2. Understanding semiconducting nanotube network for chemical sensing

Understanding the network structure and how they behave reproducibly is highly important in assessing complex biochemical reactions. Towards this, series of experiments were conducted in Hg^{2+} and NH_4^+ ions to understand the change in electrical characteristics of the bare nanotube devices. HgCl_2 in DI water was prepared to create Hg^{2+} ions with concentrations ranging from 30 pM to 13 μM . Similarly, NH_4OH in DI water was prepared with concentrations ranging from 300 nM to 1.5 mM. Figure 4(a) presents the real time monitoring of both NH_4^+ and Hg^{2+} ions with each spike is a measure of increasing concentration from 300 nM to 1.3 mM for NH_4^+ ions and 30 pM to 13 μM for Hg^{2+} ions respectively. Surprisingly, we found that both Hg^{2+} and NH_4^+ ions increased the conductance of the nanotube network as the concentration of ions increased. It is seen that for some intermediate concentrations, the amplitude of the spike decrease suggesting saturation of the sensor but they are also seen to recover as the amplitudes increase with time at higher concentrations. This is clearly observed in Hg^{2+} ion sensing. In past Hg^{2+} has been shown to increase the conductance of nanotube device [31], while NH_4^+ ions decreased the conductance of the device [32]. The increase in conductance with concentration for both Hg^{2+} and NH_4^+ ion are as a result of doping. Typical electron-acceptor dopants such as I_2 , and Br_2 are expected to transfer electrons from the carbon π states in the tubes to the dopant molecules, creating an increase in hole carriers in the SWNTs [30]. This can increase the conductivity due to charging when positively charged molecules such as NH_4^+ and Hg^{2+} interact with the nanotube thereby increasing the current of the p-type nanotube. The shift in the RBM and G mode of the Raman spectrum presented (figure 2(c)) also agrees with the presence of iodine as dopant in these nanotubes. An interesting result is that our doped nanotube devices did take the level of detection of both Hg^{2+} and NH_4^+ ions to ~30 pM and ~300 nM respectively, which is significantly higher in sensitivity compared to past reports on pristine nanotubes where the limits of detection has been shown to be ~10 nM for Hg^{2+} [33]. Voltage sweeps as presented in figure 4(b) shows a shift in threshold voltage towards more negative V_g suggesting p-type behavior. The real time Hg^{2+} and NH_4^+ chemical sensing therefore correlates well with the voltage sweeps. Figure 4(c) presents the change in I_{ds} versus V_g for different concentrations of Hg^{2+} and NH_4^+ ions. As the concentration increases, so does the current suggesting an increase in hole carrier density for

both types of ions. A G/G_0 versus $\log [A]$ is presented in figure 4(d) suggesting a Langmuir-adsorption isotherm with a linear response centered around $[A] = 1/K$. The higher (G/G_0) for our doped nanotubes (y -axis) presented here in the Langmuir adsorption isotherm compared to past networks of mixed metallic and semiconducting nanotube [31] also suggests the increased sensitivity of the iodine doped semiconducting nanotube sensors and lower limits of detection. The mechanism of sensing ions for both NH_4^+ and Hg^{2+} is therefore due to an increase in carrier density of iodine doped nanotubes. The same increase in conductance for the same type of charge also suggests similar mechanism and predictable sensor response of the doped nanotubes sensor devices. One application of these iodine doped nanotube networks with 30 pM sensitivity for Hg^{2+} could be in screening drinking water (Hg^{2+} ions set by most governmental EPA is ~ 10 nM [33]).

3.3. Antibody functionalization

In exploring the use of such multiplexed nanotube devices for measuring differential cellular response, understanding the functionalization of antibodies that are specific to the receptors, their coverage on the surface and their eventual interaction with the cellular receptors producing an electrical signal must be understood in depth.

The prepared SWNT sensors were functionalized with anti-EpCAM antibodies through a pyrene linker molecule. The pyrene rings of the 1-pyrenebutanoic acid, succinimidyl ester (PASE) adsorb on to the sidewalls of the SWNT through π stacking and produce a stable nanotube-PASE composite. The ester on the other end of the PASE provides the attachment to the antibodies as presented in figure 5(a) schematic. Antibody conjugated gold nanoparticles (15 nm) were targeted to the PASE functionalized nanotubes and imaged in a SEM to assess their binding to nanotube. The antibody conjugated nanoparticles were observed to be arranged on the nanotube side wall as presented in figure 5(b). A negative control experiment was conducted by targeting antibody conjugated gold nanoparticles to bare nanotube surface without PASE functionalization to the nanotube surface. The results in figure 5(c) conclusively suggest that antibody functionalized nanoparticles attached to the nanotube side wall by binding to PASE while no functionalization accrued between bare nanotubes and antibody conjugated nanoparticles without the presence of the PASE linker molecule. Overall the PASE conjugation provided a stable platform for all sensing in cell cultures and buffy coats.

We also investigated two other functionalization methods namely: (a) streptavidin–biotin conjugation chemistry and (b) Au-amine-polymer-conjugation chemistry (suppl. figure S3) and compared with antibody–PASE functionalization (figure 5(d)). It was found that the antibody–PASE functionalization gave the most promising results with ~ 76 particles per μm^2 , followed by streptavidin–biotin conjugation chemistry of ~ 71 particles per μm^2 , followed by Au-amine-polymer functionalization of ~ 21 particles per μm^2 . Non-specific controls yielded about ~ 1 – 6 particles per μm^2 . Standard deviation of the particle count by each method was plotted suggesting high degree of control and reproducibility of the functionalization and attachment of antibody to the PASE molecule. The devices presented here had channel length of $100\ \mu\text{m}$ and width of $80\ \mu\text{m}$. For a $4\ \mu\text{g}$ network distributed uniformly and assuming 1 antibody site per particle, this would translate into 608 000 sites

for antibody binding to PASE for the entire device. Similarly, for the streptavidin–biotin chemistry, this would translate into 568 000 binding sites and for the amine-polymer-Au nanoparticle functionalization protocol, this would translate into 168 000 binding sites. For non-specific controls this would translate into 8000–48 000 binding sites. Typically, a cancer cell surface has 250 000 receptors overexpressed all over the surface compared to normal cells which has less than 10 000. With 608 000 sites, this is a ratio 2.4 antibody available per receptor for interaction.

3.4. Testing in cell cultures

Testing in different cell lines yielded highly intriguing results on the measurement of normalized electrical conductance G/G_0 over various cell lines. In these experiments several cell lines namely normal breast cell line (MCF10A), breast cancer cell lines (SKBR3, MCF7) were used. Anti-EpCAM antibodies were used as specific controls while anti-IgG antibody was used as non-specific controls. Both SKBR3 and MCF7 overexpress EpCAM while MCF10A normal cells do not. A representative micrograph of the testing protocol is presented (suppl. figure S4). Surprisingly, two differential signals were generated between positive and negative controls. The positive controls such as targeting EpCAM on SKBR3 (figure 6(a)) and MCF7 (figure 6(b)) produced characteristic spikes in the electrical signatures with positive slopes that stabilized after few seconds. It is also noted that the stabilized conductance levels even after 60 s are higher than initial value before the sample addition suggesting an irreversible change in the electrical signature or forward reaction kinetics for the formation of the antibody-receptor complex. Similarly, the negative controls namely targeting EpCAM in MCF10A (figure 6(c)) and targeting IgG in all the cells (figure 6(d)) and even phosphate-buffered saline (PBS) produced similar spikes with negative slopes and stabilized after several seconds. It is also noted that the final conductance after cell addition was higher than the initial conductance value and stabilized at that value. In determining the statistical significance, the average slope of ~ 0.5 s following the inflection point was calculated for each signal. Both data sets were determined to be random and of equal variance. A final p value of $0.0011 < 0.05$ was calculated showing a statistically significant difference between all positive and negative controls as presented in table 2. It should be noted that the positive controls consisted of two different cell lines MCF7 and SKBR3 targeted for EpCAM mentioned as G1 and G2 respectively in table 2. Similarly the negative control consisted of EpCAM-MCF10A, and IgG-(MCF7, MCF10A, SKBR3) mentioned as G3 and G4. The p values in the table 2 suggest that there is a significant statistical difference between specific and non-specific electrical signatures. It is also observed that within the same group, the p values do not reflect a significant difference suggesting natural partitioning of specific and non-specific signals. This suggests that the nanotube sensor is capable of differentiating between two different cell populations which are similar except for their surface markers. The similar results over wide ranging cell lines and antibodies suggest specific interactions gave rise to characteristic spikes in electrical signatures due to their cooperative binding of antibodies to their receptors. The ability to distinguish between cancerous and non-cancerous cell populations based on their surface markers with statistical significance in fast manner as presented here is thus a significant accomplishment for any nanotube thin film sensor.

3.5. Testing in buffy coats and development of a statistical classifier for liquid biopsy

If nanotube thin film sensors were to be used for any diagnostic/prognostic value in the clinic, testing in more complex medium such as buffy coats/blood would be necessary. The ability to capture cancer cells and analyze their biomarkers in complex medium both in large and small volumes can have profound translational impact. Biosensors that produce electrical signals or other time series data present a unique challenge for researchers attempting to use such sensors to classify biological samples. The analysis of such data is complicated by undesirable variation in the time domain between samples of the same class in addition to variability in the characteristic patterns that may be shared between samples of the same class. Further, use of such complex medium such as buffy coats with white blood cells and other proteins makes it highly complicated and cannot be simply differentiated based on simple time domain electrical signatures. Currently, there exists no statistical classifiers for 'liquid biopsy' samples for both small and large volumes of samples.

We used ANOVA balanced design to reduce any systematic variability. Factors in ANOVA design includes medium (Bare, Igg EpCAM) and three types of samples (PBS: control1, Buffy: control 2 and Spiked Buffy: case) with fixed number of replicates. With the same design two data sets were generated for training set and then for test set. As summarized in Cambon *et al* [34, 35], there are different approaches to classification of higher dimensional data sets based on biosensor signals. In the recent past, group classification of cervical cancer versus control samples were done based on differential scanning calorimetry thermograms. The excess specific heat capacity versus temperature were measured from both cervical cancer sample and control samples. These were then classified using a parametric classifier with 96.7% classification rate. Compared to the newly developed parametric method, the I-RELIEF method that is commonly used to classify higher dimensional data sets only showed a classification rate of 73.3% [36]. Here, we use DTW for classification as the biosensor signals and patterning techniques are quite different.

To demonstrate the ability of the devices to discriminate between buffy and spiked buffy signals, we used a training-test approach to building a k -nearest neighbor (k -nn) classifier using DTW [37–42]. To evaluate if devices could differentiate between MCF7 positive samples and MCF7 negative samples, both were tested utilizing the devices. The negative samples consisted of a buffy coat sample from the biorepository without the presence of breast cancer cells. The positive samples consisted of the same buffy coat sample that was spiked with MCF7 breast cancer cells ($10\,000\,\mu\text{l}^{-1}$) as a proof of concept. The drain current from the nanotube devices was recorded continuously throughout each experiment. A representative figure of the testing protocol is presented (suppl. figure S4). The resulting data consisted of time series with characteristic 'spikes' occurring after the application of the sample as shown in figure 7 for the training set.

3.6. Construction of the classifier

A set of training signals from the devices was used for selecting the optimal tuning parameters for the classifier. An independent set of mixed signals was then classified using the classifier. Sensitivity, specificity, and the misclassification rate of the classifier on the test set were then used to evaluate performance.

To describe the construction of the classifier, we first introduce some notation. We represent a device signal as a time series, $\mathbf{y} = \{y_t, t \in T\}$ where T is a finite set that indexes time. To indicate that the signal is the i th replicate from the j th group (buffy versus spiked buffy) we use the notation $\mathbf{y}_{ij}$. Before a classifier could be constructed, the raw signals were processed so that the signals had comparable a sampling rate, length, and intensity. The signals $\mathbf{y}_{ij}$ were first averaged so that each signal had the same sampling rate of one sample per second. The signal was then truncated by removing series values between the first value and five seconds after signal most extreme peak—resulting in a new t_0 for each signal. Experimental variation in the timing of the replicate drops contacting the device resulted in non-uniform length time indices. For length standardization, the signals were then truncated at 253 s. The final processing step was mean and variance standardization so that each signal had mean 0 and variance 1.

To compare signals and develop a classifier, a measure of signal similarity is needed. The technique employed to develop a similarity measure in this analysis is known as DTW [37–42].

DTW is a method of aligning two-time series so that a traditional distance metric (such as the Euclidean metric) can be used as a measure of similarity. To measure the similarity between two signals $\mathbf{y}_1$ and $\mathbf{y}_2$, we compute two matrices $\mathbf{D} \in \mathbb{R}^{m \times n}$ and $\mathbf{\Gamma} \in \mathbb{R}^{(m+1) \times (n+1)}$. The first matrix $\mathbf{D}$ has entries representing the pairwise distances between points in the series, that is:

$$\delta(t, t') = d(\mathbf{y}_{1,t}, \mathbf{y}_{2,t'}),$$

where d is a distance metric. For this analysis we chose to use the Euclidean distance metric. Once this distance matrix was defined, we determined the elements of $\mathbf{\Gamma}$ using a recurrence relation that weights steps through a cumulative distance matrix. Two formulations for this matrix were considered using the following recursions:

$$\gamma_1(i, j) = \min\{\delta(i, j) + \gamma_1(i-1, j), \delta(i, j) + \gamma_1(i-1, j-1), \delta(i, j) + \gamma_1(i, j-1)\},$$

$$\gamma_2(i, j) = \min\{\delta(i, j) + \gamma_2(i-1, j), 2 \times \delta(i, j) + \gamma_2(i-1, j-1), \delta(i, j) + \gamma_2(i, j-1)\}.$$

Once the cumulative distance matrix $\mathbf{\Gamma}$ has been defined, we seek a warping curve that aligns the time indices for each time series:

$$\phi(k) = (\phi_s(k), \phi'_s(k)), k \in \{1, \dots, K\}, \phi(k) \in \{1, \dots, m\} \times \{1, \dots, n\}.$$

This warping curve was chosen such that once $\mathbf{y}_1$ and $\mathbf{y}_2$ are aligned, the cumulative distance between the series is minimized. To find such a curve, we find the lowest scoring path through the cumulative distance matrix $\mathbf{\Gamma}$ subject to the following constraints:

$$1. \quad \phi(1) = (1, 1),$$

2. $\phi(T) = (m, n)$,
3. $(\phi(k) - \phi(k-1)) \in \{(1, 1), (1, 0), (0, 1)\} \forall k > 1$.

Constraint (1) and (2) ensure that the beginning and the end of the signals $\mathbf{y}_1$ and $\mathbf{y}_2$ are aligned. Constraint (3) ensures uniform length of step sizes and that the warping curve is monotonic increasing. An illustration of the alignment process for a pair of qualitatively similar and qualitatively different signals are presented (suppl. figures S5 and S6) respectively. Once a warping path has been defined, the DTW distance between two signals (not a formal distance metric) is given by:

$$d_{\text{DTW}}(\mathbf{y}_1, \mathbf{y}_2) = \sum_{k=1}^T \Delta(\phi(k)).$$

For each step pattern, a dissimilarity matrix using DTW distance as the dissimilarity measure was constructed for the signals using the DTW package in R [43].

A training-test approach was used to develop a k -nn classifier [40] from the DTW distance dissimilarity matrices. The training set consisted of ten buffy signals and 28 spiked buffy signals. Ten-fold cross-validation [40] was employed using 10 000 bootstrapped samples from the training set to determine which step pattern (symmetric 1 versus symmetric 2) and a number of nearest neighbors yielded the lowest misclassification rate (suppl. figure S7). The misclassification rate is defined as:

$$\text{Err} = \sum_{i=1}^N I(Y_i \neq \hat{Y}_i),$$

where Y_i denotes the true class of the signal $\mathbf{y}_i$ and $\hat{Y}_i$ denotes the k -nn classifier predicted class the for $\mathbf{y}_i$.

Once the optimal step pattern and classifier design had been selected, the classifier was evaluated on the 22 signals of the test set. The study personnel who conducted the classification on this test set were blinded to the true class (buffy versus spiked buffy) of the signals.

3.7. Training set classification

A training validation test set approach was used to construct DTW distance based probabilistic modeling of surrounding observations (such as κ th- nearest neighbors). The training data consisted of plain PBS (not shown), ten buffy coat samples (figure 7(a) and 17 spiked buffy coats as presented in figure 7(b). A κ -fold cross-validation parameter selection was conducted using 10-fold cross validation on 10 000 bootstrapped samples from the training set of 27 signals for which the class (buffy versus spiked buffy) was known. The tuning parameters selected were those that minimized the mean and variance of the misclassification rate. The test set misclassification rate, classifier sensitivity, and classifier specificity were then used as criteria to measure the success of the devices in discriminating between positive and negative samples. The statistical table for training set is presented in table 3. A positive predictor value (PPV) = 94% and negative predictor value (NPV) = 100%

with accuracy = 96.3% was obtained for training set. One data was misclassified and was false positive or type I error. No false negatives were observed in training set.

3.8. Blinded test classification

Figures 8(a) and (b) present the composite plot of the normalized electrical signal for the blinded test. Based on the training set, the tuning parameters were selected, 22 test signals presented in figures 8(a) and (b) (*of class unknown to the personnel constructing the classifier*) were classified using the training signals as reference signals. Table 4 presents the corresponding classification table for the blind test. A PPV = 83%, NPV = 90% and accuracy = 86% was observed. A misclassification rate of ~14% was observed in these blind testing. Three samples over 22 samples were misclassified. Two samples that were misclassified were false positive or type I error and one sample that was misclassified was false negative or type II error. This suggests the classifier is capable of differentiating electrical signals between samples that were plain buffy coat or buffy coat with cancer cells which is the first accomplishment for any nanotube biosensor device.

3.9. Heatmap

Figure 9 is the heat map of the between signal DTW distances for the signals used in the k -fold cross-validation tuning parameter selection and as reference signals for the classifier. Ten-fold cross-validation on the bootstrap samples resulted in a final DTW distance based on κ -nn classifier utilizing a symmetric two step pattern and three nearest neighbors. In the margins of this figure a dendrogram of the complete-linkage agglomerative hierarchical clustering of the same is shown [40]. This demonstrates that on the training data, DTW distance as a dissimilarity measure, naturally partitions the sample data into two distinct clusters (with one misclassification) according to sample class. The statistical classifier partitions the buffy versus spiked buffy coats suggesting specific interactions are quite unique in their electrical signatures compared to non-specific interactions and establishes a relationship between electrical conductance data with biological and possibly proteomic features (presence or absence of cancer cells in buffy coats versus presence or absence of mesenchymal marker EpCAM).

3.10. Cell capture with single cell sensitivity and confocal microscopy

The devices that gave positive signatures were then further processed to assess the ability to capture spiked MCF7 cells from buffy coats. Figure 10 are the images from 22 processed samples from the blind test with both buffy and spiked buffy coats. Each image was taken of the device immediately after taking the electrical signature measurement. For easier presentation, the spiked buffy coats are presented in figure 10(a), the plain buffy coats are presented in figure 10(b) and table 5 consisting of number of cells captured on the device in figures 10(a) and (b). The cells could be counted after imaging in a Nikon Eclipse optical microscope in the buffy coat using imaging software. The images show the ability to capture 1–20 cells per device and their positive/negative electrical signatures assessed from the classifier. Our buffy coat was mainly proteins and denatured hematologic cells, we were able to identify the MCF7 cells which were quite distinct as these were spiked cells. The single cells captured in the plain buffy coat are believed to be one or two hematologic or white blood cells that were bound to the device.

Six devices were removed and also imaged using confocal microscopy as presented in figure 11 (only 4 shown). The samples were washed three times to assess binding and stained for DAPI and EpCAM. A cover slip was placed on the device and imaged using confocal microscope. The images from devices as presented suggest single cell sensitivity as well as positive for EpCAM overexpression. The results suggest that the samples were bound to the nanotube device through cooperative binding of the receptors to the antibodies. Again, anywhere ~1–17 cells were observed in line with optical microscopy observations.

4. Discussion and outlook

The ability of to distinguish samples that have cancer cells from samples that have no cancer cells in a medium such as blood/buffy coats in rapid manner for both large and small volumes can have significant implications in the clinic. The semiconducting nanotube arrays presented here is a promising technology with potential advantages in a clinical setting due to its simplicity. The technology requires minimal sample preparation, can perform assays in turbid/obscure media, can be adapted to profile different targets namely proteins, and cells, and has the capability for high-throughput operation (60–240 sensor arrays). For the first time, we have merged the nanotube sensor data with predictive statistical classifiers for liquid biopsy, an important step towards clinical translation with high sensitivity and specificity for a digital device. Our past work has also shown the detection of $\sim 1 \text{ ng ml}^{-1}$ based on similar devices that were functionalized with anti-EPCAM antibodies using the same PASE functionalization protocol [44]. Our results on cell cultures and buffy coats thus suggest similarity in patterns that could potentially arise only from specific antibodies interacting with their corresponding EpCAM receptors. The ~91% sensitivity, ~82% specificity and ~86% accuracy in the blind classification test give us great confidence in development of this technology further for future clinical applications. One advantage is that our work shows the feasibility of classifying samples based on the device electrical signatures in short time frames (within few minutes), an important advantage in the clinic and considering that cells removed from their native microenvironment rapidly change their phenotype. Once classified, devices that gave positive electrical signals can then be sent to a laboratory for further validation such as qPCR. With its capability for fast and sensitive cell capture, the nanotube arrays has the potential to become a useful tool for early screening of cancer cells from a drop of blood and also studies related to multiplexed drug screening and intracellular signaling. Although our study was focused on being able to classify signals from buffy coats that had cancer cells from the buffy coats that had no cancer cells based on nanotube micro-arrays functionalized with anti-EpCAM antibodies, the nanotube-assay can be expanded to interrogate other complex cancer signatures and receptors namely Her2 and EGFR two important markers involved in metastases. Anti-Her2 and anti-EGFR antibodies functionalized to the nanotube devices could potentially be useful in isolation of cells based on those markers. The system itself can be further improved through larger arrays, automated sample handling and development of statistical classifier for blood samples and the use of custom-aptamer technology for high specificity which are the focus of our future work. Therefore, the potential for these devices are high both for fine needle aspirates and circulating tumor cell capture and analysis and worth pursuing given the simplicity of the system.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

Funding for this work was provided by the National Cancer Institute through grant R15CA156322 and 7 R15CA156322-02, NSF CMMI 1463869, NSF DMR 1410678; and NSF ECCS 1463987 for B.P. The authors would like to thank Dr Micheal Timko's laboratory for Raman Spectroscopy. Dr S N Rai is supported by Wendell Cherry Chair in Clinical Trial Research and generous support from Dr D M Miller, Director, James Graham Brown Cancer Center, University of Louisville.

FK and BP designed the experiments and wrote the manuscript. FK designed and fabricated the devices inside a clean room and tested the devices for their electrical signatures in buffy and spiked buffy coats. SNR and PT designed and built the statistical classifier. PT and FK worked on classification of signals. SNR and PT classified the blind signals that were unknown to them during blind test. EW assisted with experimental concepts and discussions. GK assisted with experimental discussions and buffy coats from the biorepository.

References

- Shulze A, Downward J. Navigating gene expression using microarrays-a technology review. *Nat. Cell Biol.* 2001; 3:E190–E195. [PubMed: 11483980]
- Dmitriev AA, et al. Genetic and epigenetic analysis of non-small cell lung cancer with NotI-microarrays. *Epigenetics.* 2012; 7:502–513. [PubMed: 22491060]
- Flach J, Dicker F, Schnittger S, Schindela S, Kohlmann A, Haferlach T, Kern W, Haferlach C. An accumulation of cytogenetic and molecular genetic events characterizes the progression from MDS to secondary AML: an analysis of 38 paired samples analyzed by cytogenetics, molecular mutation analysis and SNP microarray profiling. *Leukemia.* 2011; 25:713–718. [PubMed: 21233836]
- Lashkari DA, DeRisi JL, McCusker JH, Namath AF, Gentile C, Hwang SY, Brown PO, Davis RW. Yeast microarrays for genome wide parallel genetic and gene expression analysis. *Proc. Natl Acad. Sci. USA.* 1997; 94:13057–13062. [PubMed: 9371799]
- Weidenhammer EM, Kahl BF, Wang L, Wang L, Duhon M, Jackson JA, Slater M, Xu X. Multiplexed, targeted gene expression profiling and genetic analysis on electronic microarrays. *Clin. Chem.* 2002; 48:1873–1882. [PubMed: 12406971]
- Florens L, et al. A proteomic view of the plasmodium falciparum life cycle. *Nature.* 2002; 419:520–526. [PubMed: 12368866]
- Fulwyler M. Electronic separation of biological cells by volume. *Science.* 1965; 150:910–911. [PubMed: 5891056]
- Whelan JP, Kusterbeck AW, Wemhoff GA, Bredehorst R, Ligler FS. Continuous-flow immunosensor for detection of explosives. *Anal. Chem.* 1993; 65:3561–3565.
- Davies H, Lomas L, Austen B. Profiling of amyloid beta peptide variants using SELDI ProteinChip (R) arrays. *Biotechniques.* 1999; 27:1258–1261. [PubMed: 10631507]
- Heegaard NHH, Kennedy RT. Identification, quantitation, and characterization of biomolecules by capillary electrophoretic analysis of binding interactions. *Electrophoresis.* 1999; 20:3122–3133. [PubMed: 10596820]
- Wu GH, Datar RH, Hansen KM, Thundat T, Cote RJ, Majumdar A. Bioassay of prostate-specific antigen (PSA) using microcantilevers. *Nat. Biotechnol.* 2001; 19:856–860. [PubMed: 11533645]
- Zheng GF, Patolsky F, Cui Y, Wang WU, Lieber CM. Multiplexed electrical detection of cancer markers with nanowire sensor arrays. *Nat. Biotechnol.* 2005; 23:1294–1301. [PubMed: 16170313]
- Okuno J, Maehashi K, Kerman K, Takamura Y, Matsumoto K, Tamiya E. Label-free immunosensor for prostate-specific antigen based on single-walled carbon nanotube array-modified microelectrodes. *Biosens. Bioelectron.* 2007; 22:2377–2381. [PubMed: 17110096]
- Shao N, Wickstrom E, Panchapakesan B. Nanotube-antibody biosensor arrays for the detection of circulating breast cancer cells. *Nanotechnology.* 2008; 19:465101. [PubMed: 21836232]

15. Lin P, Yan F, Yu JJ, Chan HLW, Yang M. The application of organic electrochemical transistors in cell-based biosensors. *Adv. Mater.* 2010; 22:3655. [PubMed: 20661950]
16. Cristofanilli M, et al. Circulating tumor cells, disease progression, and survival in metastatic breast cancer. *New England J. Med.* 2004; 351:781–791. [PubMed: 15317891]
17. Nagrath S, et al. Isolation of rare circulating tumour cells in cancer patients by microchip technology. *Nature.* 2007; 450:1235–U1210. [PubMed: 18097410]
18. Stott SJJ, et al. Isolation of circulating tumor cells using a microvortex-generating herringbone-chip. *Proc. Natl Acad. Sci. USA.* 2010; 107:18392–18397. [PubMed: 20930119]
19. Pachmann K, Heiss P, Demel U, Tilz G. Detection and quantification of small numbers of circulating tumour cells in peripheral blood using laser scanning cytometer (LSC (R)). *Clin. Chem. Lab. Med.* 2001; 39:811–817. [PubMed: 11601678]
20. Lu YT, et al. NanoVelcro Chip for CTC enumeration in prostate cancer patients. *Methods.* 2013; 64:144–152. [PubMed: 23816790]
21. Lee H, Yoon TJ, Figueiredo JL, Swirski FK, Weissleder R. Rapid detection and profiling of cancer cells in fine-needle aspirates. *Proc. Natl Acad. Sci. USA.* 2009; 106:12459–12464. [PubMed: 19620715]
22. Munz M, Baeuerle PA, Gires O. The emerging role of EpCAM in cancer and stem cell signaling. *Cancer Res.* 2009; 69:5627–5629. [PubMed: 19584271]
23. Balzar M, Winter MJ, de Boer CJ, Litvinov SV. The biology of the 17-1A antigen (Ep-CAM). *J. Mol. Med.-Jmm.* 1999; 77:699–712.
24. van der Gun BTF, Melchers LJ, Ruiters MHJ, de Leij LFMH, McLaughlin PMJ, Rots MG. EpCAM in carcinogenesis: the good, the bad or the ugly. *Carcinogenesis.* 2010; 31:1913–1921. [PubMed: 20837599]
25. Majumdar A. Bioassays based on molecular nanomechanics. *Dis. Markers.* 2002; 18:167–174. [PubMed: 12590170]
26. King BC, Clark M, Burkhead T, Sethu P, Rai S, Kloecker G, Panchapakesan B. Electrical detection of specific versus non-specific binding events in breast cancer cells. *Biosensing Nanomedicine V.* 2012; 8460
27. King B, Panchapakesan B. Vacuum filtration based formation of liquid crystal films of semiconducting carbon nanotubes and high performance transistor devices. *Nanotechnology.* 2014; 25:175201. [PubMed: 24721979]
28. Fan XM, King BC, Loomis J, Campo EM, Hegseth J, Cohn RW, Terentjev E, Panchapakesan B. Nanotube liquid crystal elastomers: photomechanical response and flexible energy conversion of layered polymer composites. *Nanotechnology.* 2014; 25:355501. [PubMed: 25116197]
29. Cambedouzou J, Sauvajol JL, Rahmani A, Flahaut E, Peigney A, Laurent C. Raman spectroscopy of iodine-doped double-walled carbon nanotubes. *Phys. Rev. B.* 2004; 69:235422.
30. Rao AM, Eklund PC, Bandow S, Thess A, Smalley RE. Evidence for charge transfer in doped carbon nanotube bundles from Raman scattering. *Nature.* 1997; 388:257–259.
31. Lee BY, Sung MG, Lee J, Baik KY, Kwon YK, Lee MS, Hong S. Universal parameters for carbon nanotube network-based sensors: can nanotube sensors be reproducible? *ACS Nano.* 2011; 5:4373–4379. [PubMed: 21615164]
32. Bradley K, Gabriel JCP, Briman M, Star A, Gruner G. Charge transfer from ammonia physisorbed on nanotubes. *Phys. Rev. Lett.* 2003; 91:218301. [PubMed: 14683342]
33. Kim TH, Lee J, Hong S. Highly selective environmental nanosensors based on anomalous response of carbon nanotube conductance to mercury ions. *J. Phys. Chem. C.* 2009; 113:19393–19396.
34. Cambon AC, Baumgartner KB, Brock GN, Cooper NGF, Wu D, Rai SN. Classification of clinical outcomes using high-throughput informatics: II. Non-parametric method reviews. *J. Model Assist. Stat. Appl.* 2015; 10:89–107.
35. Cambon AC, Baumgartner KB, Brock GN, Cooper NGF, Wu D, Rai SN. Classification of clinical outcomes using high-throughput informatics: I. Non-parametric method reviews. *J. Model Assist. Stat. Appl.* 2015; 10:3–23.
36. Rai SN, Pan J, Cambon A, Chaires JB, Garbett NC. Group classification based on high-dimensional data: application to differential scanning calorimetry plasma thermogram analysis of cervical cancer and control samples *Open Access. Med. Stat.* 2013; 3:1–9.

37. Müller, M. Information Retrieval for Music and Motion. Vol. 2. Berlin: Springer; 2007.
38. Rabiner, LR.; Juang, B-H. Fundamentals of Speech Recognition. Vol. 14. Englewood Cliffs, NJ: Prentice Hall; 1993.
39. Sakoe H, Chiba S. Dynamic programming algorithm optimization for spoken word recognition IEEE. Trans. Acoust. Speech Signal Process. 1978; 26:43–49.
40. Hastie, T.; Tibshirani, R.; Friedman, J.; Hastie, T.; Friedman, J.; Tibshirani, R. The Elements of Statistical Learning. Vol. 2. Berlin: Springer; 2009.
41. Fu T-C. A review on time series data mining. Eng. Appl. Artif. Intell. 2011; 24:164–181.
42. Berndt, DJ.; Clifford, J. Finding patterns in time series: a dynamic programming approach Advances in Knowledge Discovery and Data Mining. Menlo Park, CA: AAAI; 1996.
43. Giorgino T. Computing and visualizing dynamic time warping alignments in R: the dtw package. J. Stat. Softw. 2009; 31:1–24.
44. Khosravi F, King B, Panchapakesan B, Rai S, Kloecker G, Wickstrom E. Nanotube devices for digital profiling of cancer biomarkers and circulating tumor cells 2013 IEEE 7th. Int. Conf. on Nano/Molecular Medicine and Engineering (Nanomed). 2013:107–112.

Figure 1. Schematic of sensing mechanism. Cooperative binding of anti-EPCAM antibodies to their corresponding receptors in cells on top of nanotube biosensors creates 'spikes' in electrical conductance.

Figure 2.

Device characterization. (a) Optical image of the wafer with 60 devices manufactured using photolithography, metal deposition and etching; (b) scanning electron micrograph of carbon nanotubes; (c) Raman spectrum of semiconducting carbon nanotubes showing a large G band, small D band and 2D band. The $I_G/I_D \sim 30$ was observed in these nanotubes; (d) Test set up showing six devices on a chip and compares it to a penny. The source, drain and reference electrodes are observed.

Figure 3.

Electrical characteristics of nanotube devices. (a) SEM image of the actual device fabricated from 4, 2, and 1 μg of carbon nanotube film and their corresponding high magnification; (b) film resistance before and after annealing at 250 $^{\circ}\text{C}$; (c) histogram suggesting high degree of control in device resistance over 58 devices.

Figure 4.

Understanding semiconducting nanotube network. (a) Real time response of device to concentrations of NH_4^+ , 300 nM to 1.3 mM, and Hg^{2+} , 30 pM to 13 μM , ions; (b) voltage sweep before and after exposure to NH_4^+ and Hg^{2+} ions; (c) concentration sensitivity of voltage sweep for NH_4^+ and Hg^{2+} ions; (d) normalized signal conductance versus concentration of Hg^{2+} ions suggesting Langmuir-adsorption isotherm. The inset shows the percentage sensitivity versus concentration for Hg^{2+} . Similar results were seen for NH_4^+ ions suggesting same sensing mechanism.

Figure 5. Functionalization of antibodies. (a) Schematic of the PASE functionalization protocol; (b) SEM image of positive control suggesting high degree of antibody functionalization; (c) SEM image of negative control suggesting no functionalization; (d) comparison of different functionalization protocols including PASE–antibody, streptavidin–biotin and amine-polymer-NP conjugation.

Figure 6.

Testing in cell cultures. (a) Normalized device conductance of anti-EpCAM functionalized device with SKBR3 cancer cells; (b) normalized device conductance of anti-EpCAM functionalized device with MCF7 cancer cells; (c) normalized device conductance of anti-EpCAM functionalized device with MCF10 A normal cells; (d) representative graph of normalized device conductance of anti-IgG functionalized device with SKBR3, MCF7 and MCF10A cells.

Figure 7.

Merge of sensor arrays with statistical classifiers in training set: Normalized conductance versus time data from the arrays grouped into two categories. (a) Plain buffy coat; (b) buffy coat spiked with MCF7 cells.

Figure 8.

Merge of sensor arrays with statistical classifiers in blinded set: Normalized conductance versus time data from the arrays grouped into two categories. (a) Plain buffy coat; (b) buffy coat spiked with MCF7 cells.

Figure 9.

Heat map. Summary of the relationship between electrical signatures and the cellular-proteomic features namely overexpression of EpCAM in spiked buffy coats versus buffy coats. The statistical classifier naturally partitions the buffy versus spiked buffy coats suggests specific interactions are quite unique in their electrical signatures compared to non-specific interactions and establishes a relationship between electrical conductance data with proteomic features.

Figure 10.

Cell capture using nanotube devices based on optical microscopy. (a) Optical microscopy of spiked cells in buffy coats using nanotube devices; (b) optical microscopy of plain buffy coats.

Figure 11. Cell capture using nanotube devices using confocal microscope. Representative confocal images from six devices imaged shown) of captured cells in spiked buffy coats ranging from 1 to 17 cells per 5 µl sample.

Table 1

Film resistance summary.

CNT film concentration	4 μg	2 μg	1 μg
Sheet resistance before annealing ($\Omega \text{ sq}^{-1}$)	4.16E + 06	3.30E + 07	5.82E + 08
Sheet resistance after annealing ($\Omega \text{ sq}^{-1}$)	2.25E + 06	1.41E + 07	2.40E + 07
CNT film resistance after annealing (Ω)	2.81E + 06	1.76E + 07	3.00E + 07
% Drop in film resistance after annealing	45.92%	57.38%	95.88%

Table 2

Statistical comparison between specific and control signals in cell cultures.

	Specific		Non-specific	
	G1: EpCAM-SKBR3	G2: EpCAM-MCF7	G3: EpCAM-MCF10A	G4: IgG-(SKBR3, MCF7, MCF10A)
	0.0249	0.0498	-0.0471	-0.1761
Calculated slopes	0.1205	0.0296	-0.0279	-0.0432
	0.0414	0.0943	-0.0258	-0.1197
Average	0.0623	0.0579	-0.0336	-0.1130
Std. deviation	0.0417	0.0270	0.0095	0.0544
<i>p</i> value	G1 versus G2 :		0.9072	
	G1 versus G3 :		0.0340	
	G1 versus G4 :		0.0225	
	G2 versus G3 :		0.0107	
	G2 versus G4 :		0.0164	
	G3 versus G4 :		0.1120	
Final <i>p</i> value	Specific versus non-specific		0.0011	

Table 3

Training classification of biosensor signals based on dynamic time warping (DTW).

		Condition training		
		Condition Positive	Condition Negative	
Test outcome	Test outcome positive	True positive = 17	False positive = 1 (Type I error)	PPV = 94%
	Test outcome negative	False negative = 0 (Type II error)	True Negative = 9	NPV = 100%
		Sensitivity = 100%	Specificity = 90%	Accuracy = 96.3%

Table 4

Blinded set classification of biosensor signals based on dynamic time warping (DTW).

		Blinded Test		
		Condition Positive	Condition Negative	
Test outcome	Test outcome positive	True positive = 10	False positive = 2 (Type I error)	PPV = 83%
	Test outcome negative	False negative = 1 (Type II error)	True negative = 9	NPV = 90%
		Sensitivity = 91%	Specificity = 90%	Accuracy = 86%

Table 5

Captured cells on each device for both case and controls using optical microscope.

Device No	<u>Spiked</u>		Number of cells
	(+)	(-)	
1	✓		25
2	✓		22
3	✓		3
4	✓		14
5	✓		6
6	✓		9
7	✓		6
8	✓		19
9	✓		4
10	✓		19
11		x	0
12		x	0
13		x	1
14		x	0
15		x	0
16		x	1
17		x	0
18		x	0
19		x	2
20		x	2