Published in final edited form as:

J Am Chem Soc. 2016 September 28; 138(38): 12655–12663. doi:10.1021/jacs.6b08069.

Self-Sorting and Co-Assembly of Fluorinated, Hydrogenated, and Hybrid Janus Dendrimers into Dendrimersomes

Qi Xiao[†], Jack D. Rubien[†], Zhichun Wang[‡], Ellen H. Reed[‡], Daniel A. Hammer^{‡,§}, Dipankar Sahoo^{†,||}, Paul A. Heiney^{||}, Srujana S. Yadavalli[⊥], Mark Goulian[⊥], Samantha E. Wilner[†], Tobias Baumgart[†], Sergei A. Vinogradov[¶], Michael L. Klein[#], and Virgil Percec^{†,*}

[†]Department of Chemistry, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6323, United States

[‡]Department of Bioengineering, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6321, United States

[§]Department of Chemical and Biomolecular Engineering, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6391, United States

^{||}Department of Physics and Astronomy, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6396, United States

[⊥]Department of Biology, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6313, United States

[¶]Department of Biochemistry and Biophysics, Perelman School of Medicine, University of Pennsylvania, Philadelphia, Pennsylvania 19104-6059, United States

[#]Institute of Computational Molecular Science, Temple University, Philadelphia, Pennsylvania 19122, United States

Abstract

The modular synthesis of a library containing seven self-assembling amphiphilic Janus dendrimers is reported. Three of these molecules contain environmentally friendly chiral-racemic fluorinated dendrons in their hydrophobic part (**R_F**), one contains achiral hydrogenated dendrons (**R_H**), while one denoted hybrid Janus dendrimer, contains a combination of chiral-racemic fluorinated and achiral hydrogenated dendrons (**R_{HF}**) in its hydrophobic part. Two Janus dendrimers contain either chiral-racemic fluorinated dendrons and a green fluorescent dye conjugated to its hydrophilic part (**R_F-NBD**) or achiral hydrogenated and a red fluorescent dye in its hydrophilic part (**R_H-RhB**). These **R_F**, **R_H**, and **R_{HF}** Janus dendrimers self-assembled into unilamellar or onion-like soft vesicular dendrimersomes (DSs), with similar thicknesses to biological membranes by simple injection from ethanol solution into water or buffer. Since **R_F** and **R_H** dendrons are not miscible, **R_F-NBD** and **R_H-RhB** were employed to investigate by fluorescence microscopy the self-sorting

Corresponding Author: percec@sas.upenn.edu.

Notes: The authors declare no competing financial interest.

ASSOCIATED CONTENT

Supporting Information: Synthetic procedures with complete structural and self-assembly analysis, sample preparation, experimental protocol, and movies. This material is available free of charge via the Internet at <http://pubs.acs.org>.

and co-assembly of R_F and R_H as well as of phospholipids into hybrid DSs mediated by the hybrid hydrogenated-fluorinated R_{HF} Janus dendrimer. The hybrid R_{HF} Janus dendrimer co-assembled with both R_H and R_F . Three-component hybrid DSs containing R_H , R_F , and R_{HF} were formed when the proportion of R_{HF} was higher than 40%. With low concentration of R_{HF} and in its absence, R_H and R_F self-sorted into individual R_H or R_F DSs. Phospholipids were also co-assembled with hybrid R_{HF} Janus dendrimers. The simple synthesis and self-assembly of DSs and hybrid DSs, their similar thickness with biological membranes and their imaging by fluorescence and ^{19}F -MRI make them important tools for synthetic biology.

Graphical Abstract

INTRODUCTION

Synthetic lipids¹ such as phospholipids and glycolipids self-assemble into vesicles that mimic biological membranes. The amphiphilic structure of the lipids contains a hydrophilic head and hydrophobic tails. Lipophilic groups such as alkyl chains and fluorophilic groups such as fluorocarbon fragments have been successfully incorporated into lipids as their hydrophobic tails^{1b} and therefore form hydrogenated and fluorinated vesicles with different stabilities and permeabilities.² The immiscibility of hydrogenated and fluorinated components induced the phase separation of these domains.^{2h} Fluorinated amphiphiles have been employed for biomedical applications including for drug and gene delivery.^{2d,e} Fluorinated components including fluoropolymer nanoparticles also present potential functions such as ^{19}F magnetic resonance imaging (MRI) agents.³ This requires stable and biocompatible fluorinated vesicles, which can be synthesized and self-assembled by simple methods. The miscibility of hybrid structures with both hydrogenated and fluorinated chains have been preliminarily investigated in phospholipids and glycolipids.⁴ However, very little is known about their assemblies.

Amphiphilic Janus dendrimers⁵ containing both hydrophobic (hydrogenated lipophilic chains) and hydrophilic dendrons self-assemble into nanoscale vesicular dendrimerosomes (DSs) by simple injection of their solution in a water miscible organic solvent into water and buffer and into micrometer-scale giant DSs by film hydration. The sizes of DSs can be predicted from the thickness of their bilayer in the bulk state and from the concentration of the Janus dendrimer.^{5b} It is expected that hydrogenated chains can be replaced with

fluorinated chains leading to a new family of fluorinated vesicles named fluorinated DSs that will follow the same self-assembly principles as hydrogenated DSs.

Hybrid vesicles co-assembled from lipids and either block copolymers⁶ or Janus dendrimers^{5c} provided a platform for the incorporation of biological cell membrane components into polymersomes and DSs.^{5c} Polymersomes⁷ generate bilayers with a thickness of 8–50 nm and therefore are not compatible with biological membranes that have a thickness of ~4 nm,^{6c} while DSs overcame this biocompatibility issue.^{5c} Hence the design and synthesis of stable and biocompatible fluorinated DSs and of their hybrid structures with biological membranes including phospholipids and glycolipids became achievable.

Here we report the design and synthesis of a library containing hydrogenated, environmentally friendly chiral-racemic fluorinated and hybrid hydrogenated-fluorinated amphiphilic Janus dendrimers. Fluorinated and hydrogenated Janus dendrimers conjugated in their hydrophilic part with complementary fluorescent dyes were also elaborated. This library allowed for the first time to investigate the self-sorting and the co-assembly of fluorinated, hydrogenated and hybrid hydrogenated-fluorinated Janus dendrimers into fluorinated, hydrogenated and hybrid hydrogenated-fluorinated DSs as well as hybrid vesicles co-assembled from phospholipids and fluorinated Janus dendrimers.

RESULTS AND DISCUSSION

Design and Modular Synthesis of Amphiphilic Janus Dendrimers with Fluorinated, Hydrogenated, and Hybrid Fluorinated-Hydrogenated Chains

The chiral-racemic fluorinated dendrons employed in this study provide access to less ordered structures than those resulting from achiral hydrogenated or perfluorinated dendrons.^{8,9} Perfluoropropyl vinyl ether (PPVE) used in their synthesis is an environmentally tolerable fluorinated component that has been incorporated into chiral-racemic fluorinated dendrons in one step reaction performed under very mild reaction conditions (Scheme 1).⁹

With a catalytic amount of potassium *tert*-butoxide (*t*-BuOK) as base in anhydrous dimethylformamide, PPVE chains were introduced as side groups to benzyl (3,5)-, (3,4)-, and (3,4,5)-hydroxyl benzoates (Scheme 1). Previous studies have demonstrated that linear perfluorooctyl alkyl groups enhance the stability of vesicles² and of other supramolecular assemblies.⁸ However all linear perfluorooctyl based compounds degrade to the toxic and biopersistent perfluorooctanoic acid that was prohibited by the Environmental Protection Agency.⁹ The chiral-racemic fluorinated PPVE based dendrons employed in this study are prepared in one step, are soluble in ethanol rather than Freon-113 as the perfluorooctyl groups are, and degrade to environmental friendly natural hydroxybenzoic acids and perfluoropropyl chains that are nontoxic and nonbiopersistent.⁹

Subsequent hydrogenation with palladium on carbon in a solvent mixture of dichloromethane and methanol gave the respective fluorinated (R_F) –COOH containing first generation dendrons (3,5)PPVE-G1 (**3**), (3,4)PPVE-G1 (**6**), and (3,4,5)PPVE-G1 (**9**) (Scheme S1). These R_F dendrons were conjugated to form half of a Janus dendrimer *via*

esterification with half protected pentaerythritol (PE) as the core and 3,4,5-tris(methyl triethylene glycol)benzoic acid [(3,4,5)-3EO-G1-(OCH₃)₃] (**10**) as the hydrophilic fragments, which has been previously developed for the modular synthesis of amphiphilic Janus dendrimers that formed stable but soft DSs with narrow size distribution (Scheme 1).⁵ A stepwise esterification strategy (Scheme 1) was employed for the synthesis of a hybrid Janus dendrimer containing both (3,5)PPVE-G1 (**3**) (R_F) and 3,5-bis(dodecyloxy)benzoic acid [(3,5)12G1] (**14**) (R_H) fragments. This hybrid compound was denoted as hybrid R_{HF} Janus dendrimer.

In order to elucidate the self-assembly and co-assembly/self-sorting of R_F, R_H, and hybrid R_{HF} Janus dendrimers as individual and as a multi-component system and to investigate their miscibility/immiscibility, two Janus dendrimers with R_F or R_H chains, and with different dyes attached to their hydrophilic parts, were designed and synthesized (Scheme 2, and Scheme S4–5).

A Janus dendrimer with R_H chains was labeled with a rhodamine B (RhB) red fluorescent dye, and a Janus dendrimer with R_F chains was labeled with a 7-nitrobenzofurazan (NBD) green fluorescent dye. These azido triethylene glycol conjugated dyes were conjugated with the alkyne groups from the tris(hydroxymethyl)aminomethane (Tris) core *via* copper-catalyzed click chemistry¹⁰ which was previously developed for the synthesis of carbohydrates (glycan) conjugated Janus glycodendrimers.¹¹

The molecular structures of three R_F Janus dendrimers (3,5)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃, (3,4)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃, and (3,4,5)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃, one hybrid R_{HF} Janus dendrimers [(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃^{5a–5c} together with a R_H Janus dendrimer (3,5)12G1-PE-(3,4,5)-3EO-G1-(OCH₃)₃ are presented in Scheme 3a, in which magenta denotes R_F chains, green denotes R_H chains, and blue denotes hydrophilic parts. The fluorescent R_F Janus dendrimer with NBD label (3,5)PPVEG1-Tris-(3,4,5)-3EO-G1-(OCH₃)₃-NBD and R_H Janus dendrimer with RhB label (3,5)12G1-Tris-(3,4,5)-3EO-G1-(OCH₃)₃-RhB were presented in Scheme 3b, with abbreviations as **R_F-NBD** and **R_H-RhB**.

The structures of the newly synthesized R_F and R_{HF} Janus dendrimers were confirmed by NMR, in particular a ¹H NMR chemical shift at 6.0–6.2 ppm, with a hydrogen–fluorine coupling ²J_(HF) = 53 Hz (Figure 1c). The five different fluorine atoms in the PPVE chain were observed by ¹⁹F NMR as five groups of signals, from *F*-CF₂ at the lowest field to *F*-C(O)H at the highest field (Figure 1a).

Self-Assembly of Amphiphilic Janus Dendrimers with Fluorinated, Hydrogenated, and Hybrid Chains into Nanoscale Unilamellar or Onion-Like DSs

Nanoscale DSs of R_F, hybrid R_{HF} and of R_H Janus dendrimers were prepared by injection of their ethanol solution into water. Monodisperse peaks with narrow polydispersity (PDI) obtained from dynamic light scattering (DLS) analysis (Scheme 3a, Figure S1) indicated the formation of nanoscale assemblies. R_F, R_{HF} and R_H Janus dendrimers shared a similar trend of increasing the size of their assemblies with increasing concentration of the Janus dendrimer (Figure S1).^{5b} The vesicular morphologies of the assemblies were characterized

by cryogenic-transmission electron microscopy (Cryo-TEM) (Figure 2a). **(3,4)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃** and **(3,4,5)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃** self-assembled into unilamellar DSs with single bilayers, while **(3,5)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃** and **[(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃** formed multilamellar DSs.¹² In samples of hybrid **R_{HF}** Janus dendrimer **[(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃**, well-defined onion-like vesicles were observed, with numbers of bilayers from 2 to 11 (Figure 2b). The unilamellar vesicular assemblies from **R_H** Janus dendrimers was reported before.^{7a} The thickness of the bilayers of DSs was calculated from cryo-TEM data (Figure 3).^{8a,13} Cryo-TEM together with molecular modeling (Figure S2), demonstrated that **R_F** Janus dendrimers with (3,5)- and (3,4)-substituted PPVE chains and the hybrid **R_{HF}** Janus dendrimer showed interdigitation of their fluorinated fragments, with a membrane thickness in the range of 4.5 to 5 nm. These values are comparable to those of the biological phospholipid-derived membranes (~4 nm) and thinner than that of the interdigitated **R_H** Janus dendrimer (6.1 nm).^{5a} This is due to the shorter PPVE chain compared to the dodecyl alkyl chain and/or the perfluorooctyl-based linear chains of the same length in the dendrons.^{8a} In contrast, the (3,4,5)-substituted derivative showed a thicker bilayer (6.3 nm) indicative of no interdigitation. These results are consistent with the structures reported in a previous report on **R_H** based Janus dendrimers.^{5b}

A representative ¹⁹F NMR spectrum of the DSs self-assembled from hybrid **R_{HF}** Janus dendrimers exhibited a clear fluorine signal (Figure 1b) and suggests potential applications of these or related fluorinated DSs as ¹⁹F MRI imaging agents capable of being loaded with drugs, proteins, nucleic acids, or even with other imaging agents to generate hybrid imaging tools.^{5f}

The non-crystallization nature of **R_F** chains of these Janus dendrimers was also confirmed by a combination of differential scanning calorimetry (DSC) (Figure S3) and X-ray diffraction (XRD) (Figure S4) experiments. Below the phase transition temperature at -60 °C, all **R_F** and hybrid **R_{HF}** Janus dendrimers present a glassy phase. The **R_H** Janus dendrimer exhibited a 2D hexagonal columnar phase as previously reported.^{5b} These non-crystallizable **R_F** chains help their self-assembly into soft vesicles.

Self-Sorting and Co-assembly of Janus Dendrimers with **R_F**, **R_F**, and Hybrid **R_{HF}** chains

In order to be analyzable by fluorescence microscopy, giant DSs (diameter > 1 μm) in phosphate-buffered saline (PBS) from **R_F**, **R_H**, and hybrid **R_{HF}** Janus dendrimers were prepared by film hydration on a Teflon sheet (Figure 4),⁵ *via* co-assembly with 1% of the dye-labeled Janus dendrimers **R_H-RhB** with red fluorescence, and **R_F-NBD** with green fluorescence. **(3,5)PPVEG1-PE-(3,4,5)-3EO-G1-(OCH₃)₃** was selected as the fluorinated **R_F** molecule based on its structural similarity with the **R_H** and hybrid **R_{HF}** Janus dendrimers (Scheme 3). Due to the expected immiscibility between **R_H** and **R_F**, the **R_H** Janus dendrimer preferentially co-assemble with **R_H-RhB** (Figure 4a), while the **R_F** Janus dendrimer co-assemble with **R_F-NBD** (Figure 4e), leading to bright red or green fluorescence along the boundary of the vesicles. By contrast, since **R_F** and **R_H** are not miscible and therefore attempts to co-assemble **R_F** with **R_H-RhB** (Figure 4b) and **R_H** with **R_F-NBD** (Figure 4d)

produced vesicles that exhibit much weaker fluorescence. This miscibility problem was alleviated with the help of **R_{HF}** which enabled both dye-labeled Janus dendrimers **R_H-RhB** (Figure 4c) and **R_F-NBD** (Figure 4f) to be incorporated into the giant DSs formed from **R_{HF}** Janus dendrimers, resulting in intense red or green fluorescence (Figure 4c and 4f). A representative confocal scanning laser tomograph (Movie S1) of a giant DS formed from **R_F** Janus dendrimer and a reconstructed 3D projection (Movie S2) demonstrate their self-assembly into vesicular structures.

When both **R_H-RhB** and **R_F-NBD** were co-assembled with **R_{HF}** Janus dendrimers, their giant DSs showed an expected decrease in green emission (Figure 5) (significant *p*-value < 0.001) due to intermolecular fluorescent resonance energy transfer (FRET)¹⁴ from the green dye to the red dye over a short distance (1–10 nm). This FRET experiment indicates that immiscible **R_H-RhB** and **R_F-NBD** Janus dendrimers mix well in giant DSs with the help of **R_{HF}** Janus dendrimers without phase separation.

The phase diagram of the three-component assemblies generated from **R_H**, **R_F**, and hybrid **R_{HF}** Janus dendrimers was investigated by confocal microscopy performed on giant DSs (Figure 6). The ratio of **R_H** and **R_F** was maintained 1:1. The proportion of **R_{HF}** could be decreased to 50% and subsequently to 40% without phase isolation between the **R_H** and **R_F** components (Figure 6a–6c).

At 34% of the **R_{HF}** component, the red and green colors from the dyes started to separate into a core-shell structure (Figure 6d). Without **R_{HF}** in the mixture (0% of **R_{HF}**), **R_F** and **R_H** self-assembled into individual green and red giant vesicles, indicating the self-sorting of **R_F** and **R_H** into incompatible perfluorinated and perhydrogenated incompatible DSs (Figure 6e). Self-sorting¹⁵ of immiscible fluorinated and hydrogenated components during their attempts to co-assemble was previously demonstrated with a hydrogenated-fluorinated peptide system.^{15a} Here we demonstrate and visualize self-sorting of vesicular DSs self-assembled from individual **R_F** and **R_H** Janus dendrimers.

Co-assembly of Janus Dendrimers with Phospholipid

Finally, for potential biomedical applications of these **R_F** and **R_{HF}** DSs, the co-assembly of **R_H**, **R_F** and **R_{HF}** Janus dendrimers with phospholipids was conducted by using a phospholipid labeled with the red dye, Texas Red (TR), denoted phospholipid **TR-DHPE**, where DHPE = 1,2-dihexadecanoyl-*sn*-glycero-3-phosphoethanolamine (Figure 7a).

Confocal images demonstrated that **TR-DHPE** could be incorporated into vesicles generated from **R_{HF}** derived Janus dendrimers (Figure 7e, Movie S3) even more efficiently than in vesicles assembled from **R_H** Janus dendrimers (Figure 7b, 7f) with higher intensity of fluorescence emission. As expected, giant DSs from **R_F** Janus dendrimer showed quite weak fluorescence (Figure 7c, 7d, 7f). These co-assembly experiments are consistent with the previous co-assembly with dye-labeled Janus dendrimers and reveal that different fluorinated vesicles, miscible or immiscible with the biological membrane, can be used for different purposes. For example, DSs from **R_F** Janus dendrimers can be used for remote lipophilic and hydrophilic drug loading due to low diffusion within biological membranes. In contrast, DSs from **R_{HF}** Janus dendrimers may co-assemble with multiple components

from biological membranes, including glycolipids, glycoproteins, and transmembrane proteins, to build biocompatible hybrids for immunology and targeted delivery. It is expected that these fluorinated components may co-assemble with bacterial and human cell membranes as demonstrated recently with **R_H** Janus dendrimers.^{5c} Therefore the building block reported here provide an important new toolbox for the area of synthetic biology.

CONCLUSIONS

A library containing achiral hydrogenated (**R_H**), chiral-racemic fluorinated (**R_F**), hybrid hydrogenated-fluorinated (**R_{HF}**), hydrogenated conjugated in the hydrophilic part with a red fluorescent dye (**R_H-RhB**) and a fluorinated conjugated in the hydrophilic part with a green fluorescent dye (**R_F-NBD**) is reported. These **R_H**, **R_F** and **R_{HF}** Janus dendrimers are soluble in ethanol and self-assemble into nanometer size unilamellar and multilamellar onion-like DSs by injection of their ethanol solution into water or buffer and by hydration into micrometer size DSs. The thickness of these narrow size distribution DSs is similar to that of biological membranes. Self-assembly and co-assembly of these Janus dendrimers were monitored by fluorescence microscopy to reveal self-sorting and self-assembly of the immiscible **R_H** and **R_F** Janus dendrimers into hydrogenated and fluorinated DSs. Co-assembly of **R_H** with **R_F** and **R_{HF}** as a function of composition provided hybrid hydrogenated-fluorinated DSs when a high concentration (> 40%) of **R_{HF}** was employed, and self-sorting into individual **R_H** or **R_F** DSs when low proportions of the **R_{HF}** component were used. The simple synthesis and self-assembly, the similar thickness to biological membranes and the imaging capabilities *via* fluorescence and ¹⁹F MRI of these DSs make these building blocks and assemblies interesting tools for supramolecular science, medicine and synthetic biology,¹⁶ including hybrid hydrogenated-fluorinated cell-like assemblies.^{5c}

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

Financial support from the National Science Foundation (grants DMR-1066116 and DMR-1120901), the P. Roy Vagelos Chair at the University of Pennsylvania, and the Humboldt Foundation (all to VP), National Science Foundation (grant DMR-1120901 to DAH, PAH, MG, and MLK) is gratefully acknowledged.

References

- (a) Kunitake T, Okahata Y. *J Am Chem Soc.* 1977; 99:3860.(b) Ringsdorf H, Schlarb B, Venzmer J. *Angew Chem Int Ed Engl.* 1988; 27:113–158.(c) Thomas JL, Tirrell DA. *Acc Chem Res.* 1992; 25:336–342.(d) Kunitake T. *Angew Chem Int Ed Engl.* 1992; 31:709–726.
- (a) Ishikawa Y, Kuwahara H, Kunitake T. *Chem Lett.* 1989; 10:1737–1740.(b) Sakata K, Kunitake T. *Thin Solid Films.* 1992; 210:26–28.(c) Kuwahara H, Hamada M, Ishikawa Y, Kunitake T. *J Am Chem Soc.* 1993; 115:3002.(d) Krafft M. *Adv Drug Deliv Rev.* 2001; 47:209–228. [PubMed: 11311993] (e) Vierling P, Santaella C, Greiner J. *J Fluor Chem.* 2001; 107:337–354.(f) Schutt EG, Klein DH, Mattrey RM, Riess JG. *Angew Chem Int Ed.* 2003; 42:3218–3235.(g) Schmutz M, Michels B, Marie P, Krafft MP. *Langmuir.* 2003; 19:4889–4894.(h) Krafft MP, Riess JG. *Chem Rev.* 2009; 109:1714–1792. [PubMed: 19296687] (i) Riess JG. *Curr Opin Colloid Interface Sci.* 2009; 14:294–304.(j) Homma T, Harano K, Isobe H, Nakamura E. *Angew Chem Int Ed.* 2010; 49:1665–1668.(k) Homma T, Harano K, Isobe H, Nakamura E. *J Am Chem Soc.* 2011; 133:6364–6370.

- [PubMed: 21456527] (l) Schwieger C, Achilles A, Scholz S, Rüger J, Bacia K, Saalwaechter K, Kressler J, Blume A. *Soft Matter*. 2014; 10:6147–6160. [PubMed: 24942348] (m) Harano K, Takenaga S, Okada S, Niimi Y, Yoshikai N, Isobe H, Suenaga K, Kataura H, Koshino M, Nakamura E. *J Am Chem Soc*. 2014; 136:466–473. [PubMed: 24341551] (n) Krafft MP. *J Fluor Chem*. 2015; 177:19–28. (o) Krafft MP, Riess JG. *Curr Opin Colloid Interface Sci*. 2015; 20:192–212.
3. (a) Du W, Nystrom AM, Zhang L, Powell KT, Li Y, Cheng C, Wickline SA, Wooley KL. *Biomacromolecules*. 2008; 9:2826–2833. [PubMed: 18795785] (b) Ruiz-Cabello J, Barnett BP, Bottomley PA, Bulte JWM. *NMR Biomed*. 2011; 24:114–129. [PubMed: 20842758] (c) Rolfe BE, Blakey I, Squires O, Peng H, Boase NRB, Alexander C, Parsons PG, Boyle GM, Whittaker AK, Thurecht KJ. *J Am Chem Soc*. 2014; 136:2413–2419. [PubMed: 24437730] (d) Wang K, Peng H, Thurecht KJ, Puttick S, Whittaker AK. *Polym Chem*. 2014; 5:1760–1771. (e) Wang K, Peng H, Thurecht KJ, Puttick S, Whittaker AK. *Biomacromolecules*. 2015; 16:2827–2839. [PubMed: 26218187]
 4. (a) Guillod F, Greiner J, Riess JG. *Biochim Biophys Acta*. 1996; 1282:283–292. [PubMed: 8703984] (b) Trabelsi S, Zhang S, Lee TR, Schwartz DK. *Phys Rev Lett*. 2008; 100:037802. [PubMed: 18233038]
 5. For selected examples of dendrimersomes, see: Percec V, Wilson DA, Leowanawat P, Wilson CJ, Hughes AD, Kaucher MS, Hammer DA, Levine DH, Kim AJ, Bates FS, Davis KP, Lodge TP, Klein ML, DeVane RH, Aqad E, Rosen BM, Argintaru AO, Sienkowska MJ, Rissanen K, Nummelin S, Ropponen J. *Science*. 2010; 328:1009–1014. [PubMed: 20489021] Peterca M, Percec V, Leowanawat P, Bertin A. *J Am Chem Soc*. 2011; 133:20507–20520. [PubMed: 22066981] Xiao Q, Yadavalli SS, Zhang S, Sherman SE, Fiorin E, da Silva L, Wilson DA, Hammer DA, André S, Gabius H-J, Klein ML, Goulian M, Percec V. *Proc Natl Acad Sci USA*. 2016; 113:E1134–E1141. [PubMed: 26884210] Filippi M, Martinelli J, Mulas G, Ferraretto M, Teirlinck E, Botta M, Tei L, Terreno E. *Chem Commun*. 2014; 50:3453–3456. Nazemi A, Gillies ER. *Chem Commun*. 2014; 50:11122–11125. Filippi M, Remotti D, Botta M, Terreno E, Tei L. *Chem Commun*. 2015; 51:17455–17458. Filippi M, Patrucco D, Martinelli J, Botta M, Castro-Hartmann P, Tei L, Terreno E. *Nanoscale*. 2015; 7:12943–12954. [PubMed: 26167654]
 6. (a) Ruysschaert T, Sonnen AFP, Haefele T, Meier W, Winterhalter M, Fournier D. *J Am Chem Soc*. 2005; 127:6242–6247. [PubMed: 15853329] (b) Le Meins JF, Schatz C, Lecommandoux S, Sandre O. *Mater Today*. 2013; 16:397–402. (c) Schulz M, Binder WH. *Macromol Rapid Commun*. 2015; 36:2031–2041. [PubMed: 26457675]
 7. Discher BM, Won Y-Y, Ege DS, Lee JC-M, Bates FS, Discher DE, Hammer DA. *Science*. 1999; 284:1143–1146. [PubMed: 10325219]
 8. For examples of semifluorinated linear alkyl compounds in self-assembly and their complex synthesis, see: Percec V, Schlueter D, Kwon YK, Blackwell J, Moeller M, Slangen PJ. *Macromolecules*. 1995; 28:8807–8818. Johansson G, Percec V, Ungar G, Smith K. *Chem Mater*. 1997; 9:164–175. Percec V, Johansson G, Ungar G, Zhou J. *J Am Chem Soc*. 1996; 118:9855–9866. Percec V, Glodde M, Bera TK, Miura Y, Shiyanovskaya I, Singer KD, Balagurusamy VSK, Heiney PA, Schnell I, Rapp A, Spiess HW, Hudson SD, Duan H. *Nature*. 2002; 419:384–387. [PubMed: 12352988]
 9. For environmentally friendly chiral-racemic semifluorinated compounds in self-assembly, see: Wu Y-C, Leowanawat P, Sun H-J, Partridge BE, Peterca M, Graf R, Spiess HW, Zeng X, Ungar G, Hsu C-S, Heiney PA, Percec V. *J Am Chem Soc*. 2015; 137:807–819. [PubMed: 25549011]
 10. (a) Kolb HC, Finn MG, Sharpless KB. *Angew Chem, Int Ed*. 2001; 40:2004–2021. (b) Rostovtsev VV, Green LG, Fokin VV, Sharpless KB. *Angew Chem, Int Ed*. 2002; 41:2596–2599.
 11. (a) Percec V, Leowanawat P, Sun HJ, Kulikov O, Nusbaum CD, Tran TM, Bertin A, Wilson DA, Peterca M, Zhang S, Kamat NP, Vargo K, Moock D, Johnston ED, Hammer DA, Pochan DJ, Chen Y, Chabre YM, Shiao TC, Bergeron-Brele M, André S, Roy R, Gabius HJ, Heiney PA. *J Am Chem Soc*. 2013; 135:9055–9077. [PubMed: 23692629] (b) Zhang S, Xiao Q, Sherman SE, Muncan A, Ramos Vicente ADM, Wang Z, Hammer DA, Williams D, Chen Y, Pochan DJ, Vértessy S, André S, Klein ML, Gabius H-J, Percec V. *J Am Chem Soc*. 2015; 137:13334–13344. [PubMed: 26421463]
 12. (a) Zhang S, Sun HJ, Hughes AD, Moussodia RO, Bertin A, Chen Y, Pochan DJ, Heiney PA, Klein ML, Percec V. *Proc Natl Acad Sci USA*. 2014; 111:9058–9063. [PubMed: 24927561] (b) Xiao Q, Zhang S, Wang Z, Sherman SE, Moussodia RO, Peterca M, Muncan A, Williams DR, Hammer

- DA, Vértesy S, André S, Gabius HJ, Klein ML, Percec V. *Proc Natl Acad Sci USA*. 2016; 113:1162–1167. [PubMed: 26787853]
13. Davis KP, Lodge TP, Bates FS. *Macromolecules*. 2008; 41:8289–8291.
14. Wu PG, Brand L. *Anal Biochem*. 1994; 218:1–13. [PubMed: 8053542]
15. (a) Bilgiçer B, Xing X, Kumar K. *J Am Chem Soc*. 2001; 123:11815–11816. [PubMed: 11716746] (b) Safont-Sempere MM, Fernández G, Würthner F. *Chem Rev*. 2011; 111:5784–5814. [PubMed: 21846150]
16. (a) Guo X, Szoka FC. *Acc Chem Res*. 2003; 36:335–341. [PubMed: 12755643] (b) Lee CC, MacKay JA, Fréchet MJ, Szoka FC. *Nat Biotechnol*. 2005; 23:1517–1526. [PubMed: 16333296] (c) Farokhzad OC, Langer R. *ACS Nano*. 2009; 3:16–20. [PubMed: 19206243] (d) Menjoge AR, Kannan RM, Tomalia DA. *Drug Discov Today*. 2010; 15:171–185. [PubMed: 20116448] (e) Deming TJ. *WIREs Nanomed Nanobiotechnol*. 2014; 6:283–297. (f) Wei T, Chen C, Liu J, Liu C, Posocco P, Liu X, Cheng Q, Huo S, Liang Z, Fermeglia M, Priol S, Liang XJ, Rocchi P, Peng L. *Proc Natl Acad Sci USA*. 2015; 112:2978–2983. [PubMed: 25713374] (g) Thota BNS, Urner LH, Haag R. *Chem Rev*. 2016; 116:2079–2102. [PubMed: 26669418]

Figure 1.

Excerpt of (a–b) ^{19}F NMR spectra (470 MHz) (a) R_{HF} Janus dendrimer [(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃ in $CDCl_3$, and (b) self-assembled dendrimersomes prepared by injection of an ethanol solution of R_{HF} Janus dendrimer [(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃ into D_2O . (c) Excerpt of 1H NMR spectrum ($CDCl_3$, 500 MHz) of R_{HF} Janus dendrimer [(3,5)12G1+(3,5)PPVEG1]-PE-(3,4,5)-3EO-G1-(OCH₃)₃.

Figure 2.

(a) Cryo-TEM images of DSs assembled by $0.5 \text{ mg}\cdot\text{mL}^{-1}$ (final concentration) of R_F and R_HF Janus dendrimers. (b) Selected cryo-TEM images of onion-like DSs self-assembled from $0.5 \text{ mg}\cdot\text{mL}^{-1}$ $[(3,5)12\text{G1}+(3,5)\text{PPVEG1}]\text{-PE-(3,4,5)-3EO-G1-(OCH}_3)_3$ with hybrid R_HF chains and their 3D intensity-plotting images with different numbers of bilayers and diameters. Scale bar = 100 nm.

Figure 3. Molecular models of the bilayer thickness with and without interdigitation of fluorinated or hydrogenated chains calculated from cryo-TEM images.

Figure 4.

Representative microscopy images of giant unilamellar vesicles assembled from R_H , R_F and hybrid R_{HF} Janus dendrimers with an additional 1% (wt/wt) $R_H\text{-RhB}$, or $R_F\text{-NBD}$.

Exposure time for fluorescence = 5 ms. Phase-contrast images and fluorescence images under red fluorescence channel or green fluorescence channel were taken by successive exposures on the same vesicle. Images in the same fluorescence channel were normalized to have the same values for the darkest and brightest pixels.

Figure 5.

(a) Representative microscopy images of giant unilamellar vesicles assembled from hybrid R_{HF} Janus dendrimer with an additional 1% (wt/wt) $R_H\text{-RhB}$, and 1% (wt/wt) $R_F\text{-NBD}$. Exposure time for fluorescence = 5 ms. Phase-contrast images and fluorescence images under red fluorescence channel and green fluorescence channel were taken by successive exposures on the same vesicle. Images in the same fluorescence channel were normalized to have the same values for the darkest and brightest pixels. (b) Relative fluorescence intensity of giant vesicles in Figure 4c, 4f, and 5a, respectively. Green and red columns represent green and red fluorescence intensities of vesicles generated from hybrid R_{HF} Janus dendrimer with additional $R_H\text{-RhB}$ or $R_F\text{-NBD}$ (left two columns), and of vesicles obtained from hybrid R_{HF} Janus dendrimer with both $R_H\text{-RhB}$ and $R_F\text{-NBD}$ (right two columns). Relative intensity was calculated from the brightness histogram analysis by dividing the maximum value of each vesicle by the background. Error bars indicate standard error (SEM) of the mean based on data derived from five vesicles. *** denotes p -value < 0.001.

Figure 6.

Representative confocal fluorescent microscopy images of giant vesicles assembled from mixtures of R_H , R_F and hybrid R_{HF} Janus dendrimers with proportions (in wt%) of (a) $R_H = 0\%$, $R_F = 0\%$, $R_{HF} = 100\%$; (b) $R_H = 25\%$, $R_F = 25\%$, $R_{HF} = 50\%$; (c) $R_H = 30\%$, $R_F = 30\%$, $R_{HF} = 40\%$; (d) $R_H = 33\%$, $R_F = 33\%$, $R_{HF} = 34\%$; (e) $R_H = 50\%$, $R_F = 50\%$, $R_{HF} = 0\%$. All mixtures contain an additional 1% (wt/wt) of R_H -RhB and 1% (wt/wt) R_F -NBD. Red and green fluorescent images were merged into one to demonstrate their co-assembly or self-sorting.

Figure 7.

(a) Chemical structure of Texas Red (TR)-labeled phospholipid TR-DHPE, DHPE = 1,2-dihexadecanoyl-*sn*-glycero-3-phosphoethanolamine. (b–e) Representative confocal fluorescent microscopy images of giant unilamellar vesicles assembled from (b) R_H , (c,d) R_F and (e) hybrid R_{HF} Janus dendrimers with 1% (wt/wt) of Texas Red (TR)-labeled phospholipid TR-DHPE, DHPE = 1,2-dihexadecanoyl-*sn*-glycero-3-phosphoethanolamine. Images (c) and (d) show the same area, but the intensity has been multiplied by 5-fold in (d) to better display vesicle formation. (f) Fluorescence intensity of giant vesicles. Error bars indicate standard error (SEM) of the mean based on data derived from 25 vesicles of each sample. *** denotes p -value < 0.001.

Scheme 1. Synthesis of R_F Janus Dendrimers and Hybrid R_{HF} Janus Dendrimer with Both R_F and R_H Chains.^a

^aReagents and conditions: (i) *t*-BuOK (cat.), DMF, 0 °C for 2 h, then 23 °C for 24 h; (ii) H₂, Pd/C, DCM, methanol, 23 °C, 12 h; (iii) 4-(Dimethylamino)pyridinium 4-toluenesulfonate, DCC, DCM, 23 °C, 12 h.

Scheme 2. Synthesis of NBD Conjugated Janus Dendrimer with R_F Chains and Rhodamine B Labeled Janus Dendrimer with R_H Chains.^a

^aReagents and conditions: (i) CuSO₄·5H₂O, sodium ascorbate, THF, water, 23 °C, 24 h.

Scheme 3. The Library Containing (a) Three Janus dendrimers with R_F , One Hybrid with R_{HF} , and One with R_H chains.^a (b) Green Fluorescent Probe (NBD) Labeled Janus Dendrimer with R_F Chains and Red Fluorescent Probe (RhB) Labeled Janus Dendrimer with R_H Chains

^aDiameters (D_{DLS}) and polydispersities (in between parentheses) indicated were obtained by DLS and refer to dendrimersomes obtained by injection of their ethanol solution into water (final concentration: 0.5 mg·mL⁻¹).