Published in final edited form as:

Langmuir. 2017 July 18; 33(28): 7028–7035. doi:10.1021/acs.langmuir.7b01431.

Antifouling Stripes Prepared from Clickable Zwitterionic Copolymers

Pornpen Sae-ung¹, Kristopher W. Kolewe², Ying Bai³, Eric W. Rice², Jessica D. Schiffman^{2,*}, Todd Emrick³, and Voravee P. Hoven^{4,5,*}

¹Program in Macromolecular Science, Faculty of Science, Chulalongkorn University, Phayathai Road, Pathumwan, Bangkok 10330, Thailand ²Department of Chemical Engineering, University of Massachusetts, Amherst, MA 01003, USA ³Department of Polymer Science and Engineering, Conte Center for Polymer Research, University of Massachusetts, Amherst, MA 01003, USA ⁴Department of Chemistry, Faculty of Science, Chulalongkorn University, Phayathai Road, Pathumwan, Bangkok 10330, Thailand ⁵Center of Excellence in Materials and Bio-interfaces, Chulalongkorn University, Phayathai Road, Pathumwan, Bangkok 10330, Thailand

Abstract

In this study, we have fabricated robust patterned surfaces that contain biocompatible and antifouling stripes, which cause microorganisms to consolidate into bare silicon spaces. Copolymers of methacryloyloxyethyl phosphorylcholine (MPC) and a methacrylate-substituted dihydrolipoic acid (DHLLA) were spin-coated onto silicon substrates. The MPC units contributed biocompatibility and antifouling properties, while the DHLLA units enabled crosslinking and the formation of robust thin films. Photolithography enabled the formation of 200 μm wide poly(MPC-DHLLA) striped patterns that were characterized using atomic force microscopy (AFM), X-ray photoelectron spectroscopy (XPS) and rhodamine 6G staining. Regardless of the spacing between the poly(MPC-DHLLA) stripes (10, 50, or 100 μm) *Escherichia coli* (*E. coli*) rapidly adhered to the bare silicon gaps that lacked the copolymer, confirming the antifouling nature of MPC. Overall, this work provides a surface modification strategy to generate alternating bio-fouling and non-fouling surface structures that are potentially applicable for researchers studying cell biology, drug screening, and biosensor technology.

Graphical Abstract

*Corresponding Author: Tel: +66-2218-7627. Fax: +66-2218-7598. vipavee.p@chula.ac.th. Tel: +1-413-545-6143. schiffman@ecs.umass.edu.

Supporting Information. ¹H NMR spectrum of HEMA-LA monomer, optical images of patterned surfaces, and XPS spectra of patterned surface on poly(MPC-DHLLA) area. This material is available free of charge via the Internet at <http://pubs.acs.org>.

Keywords

antifouling; patterning; poly(2-methacryloyloxyethyl phosphorylcholine); dihydrolipoic acid; photolithography; surface coating

INTRODUCTION

Micropatterning of biomolecules, such as cells, proteins, and bacteria on substrates is critically important for fundamental studies in cell biology, drug screening, biosensor technology, and tissue engineering.^{1–6} Cell micropatterning can be achieved with fouling resistant materials that enable selective cell adhesion while limiting the non-specific adsorption of biomolecules.^{7–15} Currently, poly(ethylene glycol) (PEG) is the most widely-used antifouling polymer for grafting and lithographical patterning.^{10–14} However, the polyether structure and terminal hydroxyl groups of PEG leads to oxidative degradation in the presence of oxygen.¹⁶ Ultralow fouling polymer zwitterions are a promising alternative to PEG-based materials due to their excellent stability in aqueous media as well as in aqueous salt solutions.^{17–20} In aqueous environments, zwitterionic polymers readily hydrogen bond with water to form a robust surface hydration layer that limits the adsorption of biomolecules thus delaying the onset of biofouling.²¹ One such polymer zwitterion is poly(2-methacryloyloxyethyl phosphorylcholine) (PMPC); it is currently used commercially in contact lenses, and holds promise as a fouling resistant platform for surface patterning.

Some initial protein and cell manipulation studies have utilized PMPC-patterned surfaces on inorganic substrates using silane coupling chemistry.^{22–25} An additional report by Enomoto *et al.*²⁶ offered more flexibility with respect to applications by coating a surface using random copolymers of methyl methacrylate (MMA) and 2,2-dimethoxy-1,2-di(4-methacryloyloxy)phenylethane-1-one (DMAB) without relying on surface-grafting. By using a photomask to obtain selective UV-irradiated sites, PMPC patterns on (MMA/DMAB) films were generated via photoinduced polymerization. Kuroda *et al.*²⁷ synthesized diblock copolymers containing a PMPC block and random copolymer block of 3-(tris(trimethylsiloxy)silyl)propyl methacrylate (TSM) and 2-cinnamoyl ethyl acrylate (CEA). A thin film of this diblock copolymer was formed on PDMS substrates using physical adsorption of TSM units and photo-crosslinking of CEA units. By applying a photomask, only the area that was exposed to UV light was selectively crosslinked to improve the robustness of the surface coating and PMPC patterns on PDMS was obtained. Although

antifouling PMPC patterns have been generated without covalent surface grafting, these methods still required multiple steps of polymer synthesis or silane-containing comonomer. Thus, a simple and universal coating approach capable of generating antifouling patterns on any biomedically-relevant surfaces remains a challenge.

By taking advantage of the biocompatibility and biofouling resistance of PMPC, we developed a straightforward method for crosslinking and patterning PMPC on silicon (Si) substrates that limited the deposition of microorganisms only to PMPC-free zones. Copolymers prepared from MPC and the methacrylate of dihydrolipoic acid (DHLLA) (poly(MPC-DHLLA)) were synthesized so that the thiol groups of DHLLA could offer crosslinkable units by thiol-ene reactions in the presence of multifunctional alkenes. Antifouling PMPC stripes 200 μm wide were separated by 10, 50, and 100 μm bare silicon voids generated using a photolithographic procedure. Here, we demonstrate that PMPC-patterns reject the adhesion of *Escherichia coli* (*E. coli*), thus micropatterning the bacteria in the negative space.

EXPERIMENTAL SECTION

Materials

2-Hydroxyethyl methacrylate (HEMA), 4-(dimethylamino)pyridine (DMAP), ($\pm$)- α -lipoic acid (LA), 2-methacryloyloxyethyl phosphorylcholine (MPC), 4,4'-azobis(4-cyanovaleric acid) (ACVA), 4-cyano-4-(thiobenzoylthio)pentanoic acid (CPD), sodium borohydride, 2,2-dimethoxy-2-phenylacetophenone (DMPA) and 1,3,5-triallyl-1,3,5-triazine-2,4,6(1*H*,3*H*,5*H*)-trione were purchased from Sigma-Aldrich (St. Louis, MO, USA). 2,2,2-Trifluoroethanol (TFE) (99+%) was obtained from Alfa Aesar (Haverhill, MA, USA). Spectra/Por®7 dialysis membrane (3.5 kDa MWCO, pretreated RC tubing) was purchased from VWR Scientific (Radnor, PA, USA). *N*-(3-(dimethylamino)propyl)-*N*-ethylcarbodiimide hydrochloride (EDC) was purchased from TCI Chemical (Portland, OR, USA). Negative lift-off photoresist, NR9-1000PY, and resist developer, RD6, were obtained from Futurrex, Inc. (Franklin, NJ, USA). Quartz photomask (101.6 mm) was bought from Benchmark Technologies, Inc. (Lynnfield, MA, USA). Silicon (Si) wafer (diameter = 100 mm and thickness = 500 μm) were purchased from University Wafer, Inc. (South Boston, MA, USA). Purified MPC was prepared by mixing MPC with anhydrous diethyl ether and filtering the solution to remove inhibitor; purified MPC was stored at 4 °C. All other materials were used as received without additional purification.

Synthesis of poly(MPC-DHLLA)

A monomer based on HEMA conjugated with lipoic acid (HEMA-LA) was synthesized according to previously reported procedure²⁸ with slight modifications. Briefly, lipoic acid (8.00 g, 38.8 mmol) was dissolved in 100 mL of anhydrous dichloromethane in a dry round-bottom flask. To this stirring solution, EDC (11.20 g, 58.2 mmol) and HEMA (4.69 mL, 38.8 mmol) were added. DMAP (0.47 g, 3.88 mmol) was then added as a solid. The reaction mixture was stirred under nitrogen at room temperature and atmospheric pressure for 24 h. After the reaction was complete, the mixture was washed with 100 mL of 1 M HCl (3 times), 100 mL of saturated NaHCO₃ (4 times), and 100 mL of saturated NaCl (3 times).

The organic layer was dried with MgSO_4 , filtered, and concentrated by rotary evaporation to obtain HEMA-LA monomer as a yellow oil (7.7 g, 62.4% yield). The final product was stored at -80°C .

Copolymers of MPC and HEMA-LA (poly(MPC-LA)) at varied compositions were prepared by reversible addition-fragmentation chain transfer (RAFT) polymerization using a modified version of a previously described method.^{28, 29} Briefly, solid CPD (8.4 mg, 0.03 mmol) and ACVA (2.8 mg, 0.01 mmol) were added to MPC monomer (620 mg, 2.1 mmol) followed by TFE (2 mL) in a 20 mL vial equipped with magnetic bar and septum. The mixture was placed in an ice bath, and then HEMA-LA monomer (286.2 mg, 0.9 mmol) was slowly added via syringe. The reaction mixture was degassed using dry nitrogen gas for 30 min then stirred at 70°C for 6 h. The polymerization was quenched by rapidly cooling the solution in liquid nitrogen and opening to air. To remove the remaining monomer and the excess reagents, the polymer was precipitated in diethyl ether. To synthesize poly(MPC-DHLA), poly(MPC-LA) was re-dissolved in 15 mL of degassed water and stirred in an ice bath. Sodium borohydride (4 mole equivalent with respect to HEMA-LA) was added as a solid under nitrogen atmosphere, and the reaction mixture was stirred in an ice bath for 2 h. The pH was adjusted to a value of ~ 3.0 using 1.0 M HCl. The polymer was purified at 4°C via dialysis (MWCO 3,500 Da membrane) against methanol for 24 h and reverse osmosis (RO) water for another 48 h before being lyophilized to obtain white powder as a product. The reaction conditions above were used to prepare poly(MPC-DHLA) with 30% DHLA composition. To prepare poly(MPC-DHLA) with 10, 15, and 20% DHLA composition, MPC = 2.70, 2.55, and 2.40 mmol and HEMA-LA = 0.30, 0.45, and 0.60 mmol, respectively, were used.

Copolymer Characterization

Proton nuclear magnetic resonance (^1H NMR) spectra was obtained using a Bruker 500 spectrometer operating at 300 MHz. Molecular weights of the synthesized poly(MPC-DHLA) were analyzed using gel permeation chromatography (GPC) in trifluoroethanol (TFE) with 20 mM sodium trifluoroacetate at 40°C using an Agilent 1200 system equipped with an isocratic pump operated at 1 mL/min, a degasser, an autosampler, a Polymer Standards Service (PSS) PFG guard column (8 mm $\times$ 50 mm), 3 PSS PFG analytical linear M columns (8 mm $\times$ 300 mm, particle size 7 μm), and a refractive index detector. PMMA standards (1.5–250 kDa) were used to generate a calibration curve.

Preparation of poly(MPC-DHLA) Patterned Surfaces

To prepare patterns, a poly(MPC-DHLA) film was first spin-coated onto a silicon (Si) wafer then patterned using photolithography. Si wafers that were cut into squares (1.2 $\times$ 1.2 cm) were cleaned by sequential sonication in acetone, isopropanol, SparkleenTM 1 detergent (FisherbrandTM), RO water, acetone, and isopropanol for 15 min each followed by oxygen plasma treatment (Harrick expanded plasma cleaner) for 20 min. The cleaned Si wafers were spin-coated using a Specialty Coating SystemsTM Spincoat G3P-8 (Amherst, NH, USA) at 3,000 rpm for 90 sec with a poly(MPC-DHLA) solution (5 mg/mL in ethanol) containing 1,3,5-triallyl-1,3,5-triazine-2,4,6(1*H*,3*H*,5*H*)-trione (10 mole equivalent with $-\text{SH}$ group) and 2,2-dimethoxy-2-phenyl-acetophenone as radical initiator (1 mole equivalent with $-\text{SH}$

group). The poly(MPC-DHLA)-thin film was then crosslinked via a thiol-ene click reaction between the thiol groups in DHLA and 1,3,5-triallyl-1,3,5-triazine-2,4,6(1*H*,3*H*,5*H*)-trione by irradiation with UV light (CL-100 ultraviolet crosslinker at 365 nm and power of 100 mJ/cm²) for 4 h to obtain a stable poly(MPC-DHLA) thin film. Crosslinked poly(MPC-DHLA) thin films were cleaned through sequential washes of methanol, acetone, toluene, acetone, and isopropanol then dried under nitrogen gas.

The photolithography process used for surface patterning was slightly modified from our previous work.³⁰ Negative lift-off photoresist NR9-1000PY (~ 1 mL) was spin-coated on top of the poly(MPC-DHLA) thin film at 3,000 rpm for 30 sec then placed in a Fisher Scientific Isotemp™ Oven at 150 °C for 1 min. A photomask was then applied to the photoresist-coated poly(MPC-DHLA) thin film before 15 sec of UV exposure at 365 nm in vacuum contact mode (Suss MicroTec MA6 Mask Aligner, 12 mW/cm²). Following UV exposure, samples were heated at 100 °C for 1 min, treated with RD6 developer for 10 sec, rinsed with deionized water for 2 min, and dried with nitrogen gas. To obtain the final poly(MPC-DHLA) pattern, the unmasked area was etched away by exposure to oxygen plasma (STS Vision 320 Reactive Ion Etch system) at 40 W for 6 min, and the remaining photoresist was removed with acetone and isopropanol and dried with nitrogen gas. Modification of the photomask dimensions produced 200 µm wide copolymer stripes separated by 10, 50, and 100 µm bare Si stripes.

Characterization of Poly(MPC-DHLA) Thin Films and Patterned Surfaces

Film thickness was measured by using a Gaertner LSE stokes ellipsometer (632.8 nm He Ne Laser at a fixed incidence angle of 70°) with the Gartner Ellipsometry Program (GEMP) software. The refractive index (*n*) of the organic layer and the silica layer were assumed to be 1.529³¹ and 1.46, respectively. Ellipsometry was used to monitor the stability of poly(MPC-DHLA) thin films that were fabricated using different comonomer compositions. Thin film thickness was measured before and after being immersed in 10 mM phosphate-buffered saline (PBS) solution (pH value of 7.4) for 48 h.³² The generation of poly(MPC-DHLA) stripe-patterned surfaces was confirmed using fluorescence microscopy by rhodamine 6G staining that specifically absorbs to MPC.³³ The poly(MPC-DHLA) pattern on a Si substrate was immersed in rhodamine 6G aqueous solution (200 ppm) for 30 sec, washed two times with RO water for 30 sec, and dried with nitrogen gas. Optical and fluorescence micrographs were acquired using an Olympus BX51 fluorescence microscope (Center Valley, PA, USA) with a 100W mercury lamp. Tapping-mode atomic force microscopy (AFM, Digital Instrument Dimension 3100) was used under ambient conditions with Si cantilevers (MikroMasch, CA, USA) and Scanning Probe Image Processor (SPIP) software. X-ray photoelectron spectra (XPS) were acquired using a Physical Electronics Quantum 2000 Microprobe instrument with a monochromatic Al 50-W X-ray source under ultrahigh vacuum. The take-off angle and spot area were fixed at 45° and 10 µm, respectively.

Characterization of Bacterial Adhesion

Selective bacterial adhesion on poly(MPC-DHLA) patterned surfaces was evaluated using a modified adhesion protocol and the model organism *E. coli* K12 MG1655 (DSMZ, Leibniz-

Institut, Germany).³⁴ Patterned surfaces and controls were placed at the base of 6-well plates (Fisher Scientific) to which 5 mL of M9 media with 100 µg/mL ampicillin were inoculated to a working bacterial concentration of 1×10^8 cells/mL. No forces or flow was applied during incubation. Following 2 h growth at 37 °C, the surfaces were washed 3 times using PBS then imaged immediately using a Zeiss Microscope Axio Imager A2M (Thornwood, NY, USA). Imaging was performed at 20x and 50x magnification by analyzing 10–15 randomly acquired images over at least 3 parallel replicates. Direct cell counting was performed using *ImageJ*[®] 1.45 software (National Institutes of Health, Bethesda, MD, USA) to distinguish the location of bacterial adhesion across the patterned substrate. Raw cell counts were normalized by the total area of poly(MPC-DHLA) stripes present in each micrograph, as will be discussed more in the results and discussion section.

RESULTS AND DISCUSSION

Synthesis and Characterization of Poly(MPC-DHLA)

2-Hydroxyethyl methacrylate conjugated with lipoic acid (HEMA-LA) was successfully synthesized by carbodiimide coupling of HEMA monomer with lipoic acid at a yield of 60%.^{28, 29} ¹H NMR (Figure S1 in Supporting Information) confirmed the formation of HEMA-LA. Storage in dichloromethane at –80 °C proved effective at preserving the structure and preventing unwanted disulfide formation and/or gelation. Random poly(MPC-LA) copolymers were next prepared by RAFT polymerization in trifluoroethanol (TFE) using 4,4-azobis(4-cyanovaleric acid) (ACVA), 4-cyano-4-(thiobenzoylthio)pentanoic acid (CPD) as the radical initiator and chain transfer agent (CTA), respectively, as shown in Scheme 1. TFE was particularly chosen as the solvent because it has been found in our previous work that it can function as an excellent solvent for polymer zwitterion and is extremely useful in polymerization chemistry.³⁵ One challenge with zwitterion-containing copolymers is finding a solvent that can accommodate both the zwitterionic and non-zwitterionic monomers. TFE is very well suitable for this. A CTA to initiator ratio of three was employed and a degree of polymerization (DP) of 100 was targeted. Poly(MPC-LA) copolymers having a variety of copolymer compositions were obtained as orange-colored solids in isolated yields of ~50–90%.

Figure 1 shows representative ¹H NMR spectra of the copolymers before and after disulfide reduction to afford the free thiols. In the crude polymer product, monomer conversion was calculated by integrating the intensity of the methyl proton resonances of the polymer backbone (0.7–1.2 ppm) and the sum of the intensities these methyl resonances and the vinyl protons of residual monomer (5.65 ppm and 6.15 ppm). All of the copolymerizations reached 60–85% conversion in 6 h. ¹H NMR spectroscopy was also used for compositional analysis by comparing the relative peak ratios of HEMA-LA protons ($H_{j'+e'}$ at 2.3–2.6 ppm) and polymer backbone protons. As shown in Table 1, the percent HEMA-LA incorporated into the copolymers corresponded closely to the feed ratio employed in the polymerization, indicating a high level of control of the RAFT polymerization technique when using these monomers. Unimodal molecular weight distributions revealed by gel permeation chromatography (GPC) (Figure 1) combined with low polydispersity index (PDI) values (Table 1) further confirmed a well-controlled polymerization.

The synthesized poly(MPC-LA) was reduced with sodium borohydride to convert the disulfides to dithiols, and cleave the aromatic chain-end, which resulted in the poly(MPC-DHLA) copolymer as a white solid. After reduction, resonances from DHLA ($H_{1'}$ at 3.0 ppm and $H_{1''}$ at 2.7 ppm) were observed (Figure 1b), indicating a successful reductive ring-opening of the lipoic acid pendent group. The DHLA compositions in poly(MPC-LA) closely resembled the HEMA-LA compositions in the poly(MPC-DHLA) and the GPC-estimated molecular weights were nearly identical and remained unimodal after 45 days of storage (Figure 1e). Like all thiol-rich polymers, gelation would be anticipated upon storage. We found that the molecular weight and PDI values of poly(MPC-DHLA) were stable for up to 6 weeks when the polymer was stored under nitrogen gas at 4 °C.

Characteristics of Poly(MPC-DHLA) Patterned Surfaces

As shown in Scheme 2, poly(MPC-DHLA) containing variable DHLA contents were spin-coated onto silicon (Si) wafers from ethanol with 1,3,5-triallyl-1,3,5-triazine-2,4,6(1*H*,3*H*,5*H*)-trione (10 mol equivalent with –SH group) and 2,2-dimethoxy-2-phenyl-acetophenone (DMPA) (1 mol equivalent with –SH group). Next, the poly(MPC-DHLA)-thin film was crosslinked via a thiol-ene click reaction using UV light exposure at 365 nm for 4 h. Ellipsometry was used to monitor the stability of poly(MPC-DHLA) thin films that were fabricated using different monomer compositions. Thin film thickness before and after being immersed in 10 mM PBS solution (pH value of 7.4) for 48 h was compared, Table 2.³² Thin films with an increasing DHLA content exhibited a higher stability in the PBS solution. The copolymer with 15% DHLA composition was not stable as evidenced by the 58.4% reduction in the film thickness. Raising the DHLA content to 28% was certainly enough to provide active sites for crosslinking, thus yielding thin film with reasonable stability. Thin films fabricated using the copolymer with 28% DHLA experienced a 6.6% loss in film thickness and a 19% increase in surface roughness, as evaluated by atomic force microscopy (AFM). These changes suggest that there was a certain extent of surface erosion upon submerging the samples in the 10 mM PBS solution. The thin film stability was further improved by increasing the DHLA composition from 28% to 42%. To obtain durable films without sacrificing antifouling characteristic that originates from the MPC, poly(MPC-DHLA) patterns containing 18 and 28% DHLA were chosen for further bacterial adhesion tests.

Poly(MPC-DHLA) patterned surfaces were successfully prepared following the process illustrated in Scheme 2 from copolymers containing 18 and 28% DHLA. Photolithography provided control over the formation of copolymer stripes separated by pristine regions of Si. Patterning was first performed using a photomask that produced 100 μ m wide copolymer stripes separated by 10 μ m bare Si stripes. The alternating 100 μ m stripes of 28% DHLA separated by 10 μ m stripes of Si are distinguishable through optical microscopy, Figure 2(a). The specific interaction of rhodamine 6G with MPC, enabled clear visualization of the copolymer stripes through fluorescence microscopy, Figure 2(b). All stripes and bare regions were fabricated to be wider than the diameter of a typical *E. coli* cell (~2.0 μ m long and 0.5 μ m in diameter). For further bacterial adhesion studies, the photomask dimensions were altered to afford 200 μ m wide copolymer stripes separated by bare Si stripes that were 10,

50, and 100 μm wide. Optical images of other patterned dimensions are available in Figure S2 in Supporting Information.

AFM measurements, Figure 2(c) indicate that the poly(MPC-DHLA) patterns had an average height of ~ 17 nm with a root mean square (rms) value of 6.78 nm, which was in good agreement with the ~ 20 nm height determined by ellipsometry. The spacing between the poly(MPC-DHLA) stripes was ~ 10.0 μm , which was consistent with the dimension of the photomask. The sharp boundary between the copolymer film and the line gap (uncoated region) reflected effectiveness of etching where O_2 plasma treatment removed the unshielded, crosslinked poly(MPC-DHLA) from the substrate (Scheme 2, **Step IV**). The highest surfaces in the AFM scans are likely polymer aggregates that form due to microphase separation between the polar poly(MPC) and crosslinked poly(DHLA), while rhodamine 6G staining (Figure 2(b)) confirmed that the aggregates containing MPC in the structure. In addition, the presence of the poly(MPC-DHLA) stripes was also verified by x-ray photoelectron spectroscopy (XPS), of which atomic spectra are shown in Figure S3 in Supporting Information. The characteristic $\text{P}_{2\text{p}}$ and $\text{N}_{1\text{s}}$ peaks appearing at 132 and 401 eV, respectively, indicate phosphorylcholine (PC) groups. The XPS atomic compositions shown in Table 3 coincide well with the theoretical ratio calculated from the copolymer repeat.

Bacterial Adhesion as a Function of DHLA Content

To evaluate the effect that copolymer composition has on bacterial adhesion, substrates were patterned with poly(MPC-DHLA) with either an 18 or 28 mol% DHLA content. These copolymers were chosen to maximize the MPC content of the copolymer while maintaining sufficient stability during exposure to biological media. Consistent 200 μm wide stripes of poly(MPC-DHLA) separated by 10 μm negative regions (bare Si) were tested and compared to bare Si controls (no stripes). We wanted to directly compare the effect that polymer composition has on bacterial adhesion. Therefore, experiments were conducted with polymer area and Si spacing held constant. Figure 3 shows the relative amount of *E. coli* that adhered on the polymer stripes versus the Si spaces for two different copolymer compositions. While 1300 ± 100 *E. coli* cells/ mm^2 attached to Si controls (no stripes, data not shown), over the total area of the patterned samples (18 and 28% DHLA polymer stripes plus Si stripes) there were only 56 ± 23 and 150 ± 43 *E. coli* cells/ mm^2 , respectively. The surfaces patterned with 28% DHLA exhibited the expected trend; fewer *E. coli* (13 ± 6 cells/ mm^2) adhered to the copolymer stripes, than to the bare Si stripes, 2200 ± 200 cells/ mm^2 . Additionally, the number of microbes was lower on the 28% DHLA copolymer stripes than on the 18% DHLA copolymer stripes, which had 41 ± 18 cells/ mm^2 . However, an unexpected result occurred on stripes patterned using 18% DHLA copolymer. Sixty four percent more bacteria adhered to the 18% copolymer region than to the Si spacing. As all other variables were held constant, we attribute this difference to the chemistry of the copolymer region, and specifically to the decreased stability of the 18% DHLA copolymer reducing the antifouling activity of the surface. Therefore, we conducted further bacterial adhesion tests using the 28% DHLA copolymer.

Bacterial Adhesion as a Function of Stripe Spacing

To investigate the bacterial adhesion dependence on stripe geometry, the bare Si gap between poly(MPC-DHLA) stripes was systematically varied to be 10, 50, and 100 μm wide. The copolymer stripes had a fixed width of 200 μm and featured 28% DHLA copolymer. As we increased the width of Si stripes, the proportional ratio of copolymer to bare Si changed. Thus, raw cell counts per fluorescence micrograph were normalized by the total area occupied by bare Si (number of stripes times the area per Si stripe). Representative fluorescent micrographs demonstrate the preferential adhesion of *E. coli* to bare Si regions independent of the spacing between copolymer stripes, Figure 4. Interestingly, the number of adhered *E. coli* per area on the Si spaces was independent of the line spacing, 2200 ± 200 , 2000 ± 290 , and 2400 ± 140 cells/ mm^2 for 10, 50, and 100 μm Si spacing respectively. Comparatively, there was little-to-no bacterial attachment on the striped copolymer regions. The number of *E. coli* cells that adhered to the copolymer region was at most 30 cells/ mm^2 regardless of the size of Si spacing. The above results highly suggest that the antifouling stripes fabricated from poly(MPC-DHLA) may hold potential to confine biomolecules, such as cells, proteins, and bacteria on substrates into localized areas for further testing and analysis.

CONCLUSIONS

Here, stable and antifouling striped surfaces were prepared using photolithography on crosslinked poly(MPC-DHLA) thin films prepared by spin-coating. MPC plays a critical role in this case, due to its biocompatibility and nonspecific biofouling resistance, while crosslinking and subsequent film stability, can be induced via thiol-ene click reaction of the dithiol units available in DHLA. Photolithography using a negative lift-off photoresist yielded well-defined 200 μm poly(MPC-DHLA) stripes with controllable spacing as verified via fluorescent micrographs after rhodamine 6G staining, as well as with AFM and XPS analysis. The bacterial adhesion tests confirmed that the strong antifouling behavior of poly(MPC-DHLA) stripes caused the *E. coli* to adhere only on the bare Si stripes in consolidated areas. The ability to accumulate the bacteria in confined areas was independent of the width of the line gaps. We anticipate that this newly developed antifouling pattern can be used for biomolecule patterning applications and microbial behavior studies.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

P.S. acknowledges receipt of an academic scholarship from Chulalongkorn University Dutsadiphat Scholarship for her PhD study. K.W.K. was supported by the National Research Service Award T32 GM008515 from the National Institutes of Health. J.D.S. acknowledges the support of the National Science Foundation (NSF CBET-1719747). Thanks to Rachel Letteri, John Nicholson, and Jacob Hirsch for assistance with AFM, lithography, and XPS, respectively.

References

1. Chen CS, Mrksich M, Huang S, Whitesides GM, Ingber DE. Geometric Control of Cell Life and Death. *Science*. 1997; 276:1425–1428. [PubMed: 9162012]
2. Folch A, Toner M. Microengineering of Cellular Interactions. *Annu Rev Biomed Eng*. 2000; 2:227–256. [PubMed: 11701512]
3. Khetani SR, Bhatia SN. Microscale Culture of Human Liver Cells for Drug Development. *Nat Biotechnol*. 2008; 26:120–126. [PubMed: 18026090]
4. Lee JY, Jones C, Zern MA, Revzin A. Analysis of Local Tissue-Specific Gene Expression in Cellular Micropatterns. *Anal Chem*. 2006; 78:8305–8312. [PubMed: 17165820]
5. Jiang XY, Bruzewicz DA, Wong AP, Piel M, Whitesides GM. Directing Cell Migration with Asymmetric Micropatterns. *Proc Nat Acad Sci US A*. 2005; 102:975–978.
6. Kapur R, Giuliano KA, Campana M, Adams T, Olson K, Jung D, Mrksich M, Vasudevan C, Taylor DL. Streamlining the Drug Discovery Process by Integrating Miniaturization, High Throughput Screening, High Content Screening, and Automation on the CellChip (TM) System. *Biomed Microdevices*. 1999; 2:99–109.
7. Kitano H, Suzuki H, Kondo T, Sasaki K, Iwanaga S, Nakamura M, Ohno K, Saruwatari Y. Image Printing on the Surface of Anti-Biofouling Zwitterionic Polymer Brushes by Ion Beam Irradiation. *Macromol Biosci*. 2011; 11:557–564. [PubMed: 21243650]
8. Cho WK, Kong B, Park HJ, Kim J, Chegal W, Choi JS, Choi IS. Long-Term Stability of Cell Micropatterns on Poly((3-(methacryloylamino)propyl)-dimethyl(3-sulfopropyl)ammonium hydroxide)-Patterned Silicon Oxide Surfaces. *Biomaterials*. 2010; 31:9565–9574. [PubMed: 21056465]
9. Kamada T, Yamazawa Y, Nakaji-Hirabayashi T, Kitano H, Usui Y, Hiroi Y, Kishioka T. Patterning of Photocleavable Zwitterionic Polymer Brush Fabricated on Silicon Wafer. *Colloids Surf B Biointerfaces*. 2014; 123:878–886. [PubMed: 25466462]
10. Suh KY, Seong J, Khademhosseini A, Laibinis PE, Langer R. A Simple Soft Lithographic Route to Fabrication of Poly(ethylene glycol) Microstructures for Protein and Cell Patterning. *Biomaterials*. 2004; 25:557–563. [PubMed: 14585705]
11. Herbert CB, McLernon TL, Hypolite CL, Adams DN, Pikus L, Huang CC, Fields GB, Letourneau PC, Distefano MD, Hu WS. Micropatterning Gradients and Controlling Surface Densities of Photoactivatable Biomolecules on Self-Assembled Monolayers of Oligo(ethylene glycol) Alkanethiolates. *Chem Biol*. 1997; 4:731–737. [PubMed: 9375251]
12. Hahn MS, Taite LJ, Moon JJ, Rowland MC, Ruffino KA, West JL. Photolithographic Patterning of Polyethylene Glycol Hydrogels. *Biomaterials*. 2006; 27:2519–2524. [PubMed: 16375965]
13. Azioune A, Carpi N, Fink J, Chehimi MM, Cuvelier D, Piel M. Robust Method for High-Throughput Surface Patterning of Deformable Substrates. *Langmuir*. 2011; 27:7349–7352. [PubMed: 21604678]
14. Rodriguez-Emmenegger C, Preuss CM, Yameen B, Pop-Georgievski O, Bachmann M, Mueller JO, Bruns M, Goldmann AS, Bastmeyer M, Barner-Kowollik C. Controlled Cell Adhesion on Poly(dopamine) Interfaces Photopatterned with Non-Fouling Brushes. *Adv Mater*. 2013; 25:6123–6127. [PubMed: 23999835]
15. Li Y, Giesbers M, Gerth M, Zuilhof H. Generic Top-Functionalization of Patterned Antifouling Zwitterionic Polymers on Indium Tin Oxide. *Langmuir*. 2012; 28:12509–12517. [PubMed: 22888834]
16. Gullapalli RP, Mazzitelli CL. Polyethylene Glycols in Oral and Parenteral Formulations-A Critical Review. *Int J Pharm*. 2015; 496:219–239. [PubMed: 26581774]
17. Iwasaki Y, Ishihara K. Cell Membrane-Inspired Phospholipid Polymers for Developing Medical Devices with Excellent Biointerfaces. *Sci Tech Adv Mater*. 2016; 13:064101.
18. Schlenoff JB. Zwitteration: Coating Surfaces with Zwitterionic Functionality to Reduce Nonspecific Adsorption. *Langmuir*. 2014; 30:9625–9636. [PubMed: 24754399]
19. Estephan ZG, Schlenoff PS, Schlenoff JB. Zwitteration as an Alternative to PEGylation. *Langmuir*. 2011; 27:6794–6800. [PubMed: 21528934]

20. Kobayashi M, Ishihara K, Takahara A. Neutron Reflectivity Study of the Swollen Structure of Polyzwitterion and Polyelectrolyte Brushes in Aqueous Solution. *J Biomater Sci Polym Ed.* 2014; 25:1673–1686. [PubMed: 25178564]
21. Ishihara K, Nomura H, Mihara T, Kurita K, Iwasaki Y, Nakabayashi N. Why Do Phospholipid Polymers Reduce Protein Adsorption? *J Biomed Mater Res.* 1998; 39:323–330. [PubMed: 9457564]
22. Jang K, Sato K, Tanaka Y, Xu Y, Sato M, Nakajima T, Mawatari K, Konno T, Ishihara K, Kitamori T. An Efficient Surface Modification Using 2-Methacryloyloxyethyl Phosphorylcholine to Control Cell Attachment via Photochemical Reaction in a Microchannel. *Lab Chip.* 2010; 10:1937–1945. [PubMed: 20498909]
23. Iwata R, Suk-In P, Hoven VP, Takahara A, Akiyoshi K, Iwasaki Y. Control of Nanobiointerfaces Generated from Well-Defined Biomimetic Polymer Brushes for Protein and Cell Manipulations. *Biomacromolecules.* 2004; 5:2308–2314. [PubMed: 15530046]
24. Kuribayashi K, Tsuda Y, Nakamura H, Takeuchi S. Micro-Patterning of Phosphorylcholine-Based Polymers in a Microfluidic Channel. *Sens Actuators B-Chem.* 2010; 149:177–183.
25. Jang K, Sato K, Mawatari K, Konno T, Ishihara K, Kitamori T. Surface Modification by 2-Methacryloyloxyethyl Phosphorylcholine Coupled to a Photolabile Linker for Cell Micropatterning. *Biomaterials.* 2009; 30:1413–1420. [PubMed: 19081624]
26. Enomoto R, Sato M, Fujii S, Hirai T, Takahara A, Ishihara K, Yusa S-i. Surface Patterned Graft Copolymerization of Hydrophilic Monomers onto Hydrophobic Polymer Film upon UV Irradiation. *J Polym Sci A Polym Chem.* 2014; 52:2822–2829.
27. Kuroda K, Miyoshi H, Fujii S, Hirai T, Takahara A, Nakao A, Iwasaki Y, Morigaki K, Ishihara K, Yusa S-i. Poly(dimethylsiloxane) (PDMS) Surface Patterning by Biocompatible Photo-Crosslinking Block Copolymers. *RSC Adv.* 2015; 5:46686–46693.
28. Chen X, Lawrence J, Parelkar S, Emrick T. Novel Zwitterionic Copolymers with Dihydrolipoic Acid: Synthesis and Preparation of Nonfouling Nanorods. *Macromolecules.* 2013; 46:119–127.
29. McRae Page S, Martorella M, Parelkar S, Kosif I, Emrick T. Disulfide Cross-Linked Phosphorylcholine Micelles for Triggered Release of Camptothecin. *Mol Pharm.* 2013; 10:2684–2692. [PubMed: 23742055]
30. Sangsuwan A, Narupai B, Sae-ung P, Rodtamai S, Rodthongkum N, Hoven VP. Patterned Poly(acrylic acid) Brushes Containing Gold Nanoparticles for Peptide Detection by Surface-Assisted Laser Desorption/Ionization Mass Spectrometry. *Anal Chem.* 2015; 87:10738–10746. [PubMed: 26434604]
31. Zhang Y, Panneerselvam K, Ogaki R, Hosta-Rigau L, van der Westen R, Jensen BE, Teo BM, Zhu M, Stadler B. Assembly of Poly(dopamine)/Poly(N-isopropylacrylamide) Mixed Films and Their Temperature-Dependent Interaction with Proteins, Liposomes, and Cells. *Langmuir.* 2013; 29:10213–10222. [PubMed: 23902279]
32. Chang CC, Kolewe KW, Li Y, Kosif I, Freeman BD, Carter KR, Schiffman JD, Emrick T. Underwater Superoleophobic Surfaces Prepared from Polymer Zwitterion/Dopamine Composite Coatings. *Adv Mater Interfaces.* 2016; 3:1500521. [PubMed: 27774375]
33. Wang JH, Bartlett JD, Dunn AC, Small S, Willis SL, Driver MJ, Lewis AL. The Use of Rhodamine 6G and Fluorescence Microscopy in the Evaluation of Phospholipid-Based Polymeric Biomaterials. *J Microsc.* 2005; 217:216–224. [PubMed: 15725125]
34. Kolewe KW, Peyton SR, Schiffman JD. Fewer Bacteria Adhere to Softer Hydrogels. *ACS Appl Mater Interfaces.* 2015; 7:19562–19569. [PubMed: 26291308]
35. Chang CC, Letteri R, Hayward RC, Emrick T. Functional Sulfobetaine Polymers: Synthesis and Salt-Responsive Stabilization of Oil-in-Water Droplets. *Macromolecules.* 2015; 48:7843–7850.

Figure 1. ^1H NMR spectra of (a) purified poly(MPC-LA) and (b) purified poly(MPC-DHLA), as well as GPC traces of (c) purified poly(MPC-LA), (d) purified poly(MPC-DHLA), and (e) purified poly(MPC-DHLA) after storage for 45 days.

Figure 2. (a) Optical, (b) fluorescent, and (c) atomic force micrograph (AFM) images of 100 μm poly(MPC-DHLA) (28% DHLA) stripes separated by 10 μm Si stripes. Fluorescence micrograph was acquired using a rhodamine 6G stain.

Figure 3.
E. coli attached to poly(MPC-DHLA) surfaces patterned with 18 and 28% DHLA copolymer. Poly(MPC-DHLA) stripes were 200 μm wide separated by 10 μm Si stripes.

Figure 4.

Representative fluorescence micrographs of *E. coli* attached to (a) 10 μm , (b) 50 μm , and (c) 100 μm Si stripes separated by 200 μm wide poly(MPC-DHLA) (28% DHLA) stripes, as well as a (d) Si control (no stripes). (e) Total cell count quantified the number of attached *E. coli* cells per area of the poly(MPC-DHLA) (28% DHLA) patterned surfaces.

Scheme 1.

Preparation of poly(MPC-DHLA) by RAFT copolymerization.

Scheme 2.

Stepwise method for preparing a poly(MPC-DHLA) patterned surface using photolithography. After Step V, 200 μm poly(MPC-DHLA) stripes separated by 10, 50, or 100 μm bare Si stripes were formed.

Table 1

Molecular weight, PDI, conversion, and composition of HEMA-LA and DHLA in poly(MPC-LA) and poly(MPC-DHLA), respectively.

HEMA-LA in Feed (mol%)	Before Disulfide Reduction				After Disulfide Reduction			
	Conversion (%) ^a	<i>M_n</i> (kDa) ^b	PDI ^b	HEMA-LA Composition (mol%) ^a	<i>M_n</i> (kDa) ^b	PDI ^b	DHLA Composition (mol%) ^a	
10.0	84.0	31.6	1.1	15.6	33.1	1.1	15.0	
15.0	83.6	36.9	1.1	17.3	37.4	1.1	18.0	
20.0	63.0	30.1	1.1	26.7	31.6	1.2	28.0	
30.0	66.0	28.0	1.2	39.0	28.0	1.2	42.0	

^a Determined by ¹H NMR spectroscopy in CD₃OD;

^b Estimated by GPC.

Table 2

Poly(MPC-DHLA) thin film thickness before and after stability testing.

DHLA in Copolymer (mol%)	Poly(MPC-DHLA) Thin Film Thickness (nm)		Change in Thin Film Thickness (%)
	Initial	After 48 h Immersion in PBS	
15	8.9 ± 0.2	3.7 ± 0.3	58
18	21.7 ± 0.6	13.5 ± 1.5	38
28	19.8 ± 0.7	18.5 ± 0.8	6.6
42	22.1 ± 0.1	21.5 ± 0.2	2.7

Table 3

Summary of the elemental analysis of the high resolution XPS that provides composition analysis of poly(MPC-DHLA) (28% DHLA) stripes.

Elements	Atomic Percentage (%)	
	Calculated	XPS
C _{1s}	64.1	65.3
O _{1s}	27.0	26.6
N _{1s}	5.8	5.2
P _{2p}	3.1	2.9