Published in final edited form as:

Adv Mater. 2017 July ; 29(28): . doi:10.1002/adma.201604789.

Enhancing Photodynamic Therapy Through Resonance-Energy-Transfer Constructed Near InfraRed Photosensitized Nanoparticles

Ling Huang,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Dr. Zhanjun Li,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Dr. Yang Zhao,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States; Department of Radiology, the Second Hospital of Tianjin Medical University, Tianjin, 300211 China

Jinyi Yang,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Yucheng Yang,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Aarushi Iris Pendharkar,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Dr. Yuanwei Zhang,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Sharon Kelmar,

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Prof. Liyong Chen,

State Key Laboratory of Fine Chemicals, School of Chemical Engineering, Dalian University of Technology, E-208 West Campus, 2 Ling-Gong Road, Dalian, 116024, P. R. China

Prof. Wenting Wu,

Correspondence to: Gang Han.

Supporting Information: Supporting Information is available online from the Wiley Online Library or from the author.

State Key Laboratory of Heavy Oil Processing, School of Chemical Engineering, China University of Petroleum Qingdao, 266580 China

Prof. Jianzhang Zhao, and

State Key Laboratory of Fine Chemicals, School of Chemical Engineering, Dalian University of Technology, E-208 West Campus, 2 Ling-Gong Road, Dalian, 116024, P. R. China

Prof. Gang Han

Department of Biochemistry and Molecular Pharmacology, University of Massachusetts Medical School, Worcester, MA 01605, United States

Graphical abstract

Resonance energy transfer constructed NIR-absorbing BODIPY-based photosensitized dyad (RET-BDP) nanoparticles are developed. These nanoparticles enable targeted photodynamic therapy upon application of low-power NIR LED light irradiation. This work provides a new concept for the design of biocompatible nanoparticles with significantly improved NIR sensitivity, which is key to PDT development.

Keywords

bodipy; near infrared; nanoparticles; resonance energy transfer; photodynamic therapy

Photodynamic therapy (PDT) has great potential for cancer treatment. However, the limited photon absorption and concomitant low singlet-oxygen generation of photosensitizers (PS) in the near infrared (NIR) region are major hurdles that have hindered further development of applications of PDT. Here, a resonance-energy-transfer (RET) mechanism is used to boost NIR photon utility by constructing a dyad photosensitizer that enhances singlet-oxygen generation *in vivo* and NIR-light absorption ability of a single chromophore PS. In this study, the energy-donor moiety (distyryl-BODIPY) is connected to a photosensitizer (i.e., diiodo-distyryl-BODIPY) to form a dyad molecule (**RET-BDP**) by click chemistry. As a result, **RET-BDP** shows significantly enhanced absorption and singlet-oxygen efficiency relative to that of the acceptor moiety of the photosensitizer alone in the NIR region. **RET-BDP** can be further encapsulated within biodegradable copolymer pluronic F-127-folic acid (F-127-FA) to form water-soluble and tumor-targeting nanoparticles. Importantly, with an exceptionally low-power NIR LED light irradiation (10 mW cm^{-2}), these nanoparticles show superior tumor-targeted therapeutic PDT effects against cancer cells both *in vitro* and *in vivo* relative to unmodified photosensitizers. This research provides a new approach to

expand the options for designing NIR-absorbing photosensitizers for future clinical cancer treatments.

Photodynamic therapy (PDT) is an important, emerging tumor-therapy method. Relative to chemotherapy drugs, which induce systemic toxicity, or ionizing radiation therapy, which damages neighboring normal tissues, PDT sensitizers are significantly less toxic to biological systems.^[1] In general, PDT processes involve three basic elements: a photosensitizer, molecular oxygen, and light. Initially, tumor-localizing photosensitizers (PSs) are activated by illuminating the tumor by using a specific wavelength of light. The excited PSs then transfer their energy to surrounding oxygen molecules, which gives rise to cytotoxic reactive oxygen species (ROS), such as singlet oxygen ($^1\text{O}_2$); this process can result in tumor ablation.^[1]

For photosensitizers, factors such as absorption intensity and singlet-oxygen-generation efficiency in the NIR region are essential in the design of successful PDT molecules.^[1-2] These key factors are particularly important with regard to the treatment of tumors that are deep in tissue.^[1-2] Although conventional single chromophore-based photosensitizers like porphyrin derivatives (i.e. PpIX, chlorin e6),^[3] methyl blue,^[4] Rose Bengal,^[3] Merocyanine 540,^[3c] and certain heavy metal complexes (i.e. $\text{Ru}(\text{bpy})_3$)^[5] possess therapeutic capabilities for cancer, their absorption intensities and singlet oxygen generation efficiencies in the NIR region are suboptimal (Table S1). To improve NIR-mediated PDT of existing photosensitizers, lanthanide-doped up-converting nanoparticles (UCNPs) were developed as *in vivo* phototransducers that are excited by NIR light and emit in the visible spectrum, which overlaps with the activation wavelengths of existing photosensitizers.^[6] However, the levels of toxicity and mechanisms of body clearance of the rare earth elements (i.e. Yb, Er/Tm) used in UCNPs are unclear *in vivo* and the quantum efficiency of UCNPs and consequent PDT outcomes are still suboptimal and relative high power intensity ($>300\text{mW}/\text{cm}^2$) of the laser excitation sources are typically required (Table S2).^[7] Thus, new molecular design to develop photosensitizers that can intensify absorption and amplify singlet-oxygen quantum yields in the NIR region is urgently needed for PDT.^[1-2]

To extend NIR photosensitizer options with improved singlet-oxygen-generation efficiency and enhanced absorption of PSs in the NIR window, here we provide a new molecular design method to develop an NIR-absorbing dyad photosensitizer based on resonance energy transfer (RET) for *in vivo* PDT. We envision that relative to conventional photosensitizers (Table S1), our dyad PS has unique advantages, such as increased absorption intensity, which can maximize the use of absorbed photons, and significantly improved efficiency in concomitant singlet oxygen generation. These features will greatly improve the efficiency of PDT and thus reduce the dosage of PS molecules and lower the power of the excitation light required (Table S3).^[1] More specifically, BODIPY-based PSs possess excellent photophysical properties, such as intense absorption ($\epsilon > 80000\text{cm}^{-1}\text{ M}^{-1}$), long triplet-state lifetime, high singlet-oxygen quantum yield and excellent photostability.^[8] Although RET photosensitizers have been reported in a few papers^[8i], their absorption ability was limited to the visible region alone, which unfortunately has a fairly shallow tissue penetration depth. However, deeper tissue penetration is key to their development towards clinical translation. As a result, prior to our work, RET photosensitizers for use in deep tissue *in vivo* PDT

studies has been quite challenging. To our best knowledge, none of deep-tissue studies have been published in this regard.^[8b,8g] In this study, we construct a dual-chromophore PS dyad (**RET-BDP**) that combines the distinctive absorption bands of distyryl-BODIPY moiety **B-1** (the donor and fluorophore) and diiodo-distyryl-BODIPY moiety **B-2** (the acceptor and PS).^[8] In **RET-BDP**, diiodo-distyryl-BODIPY **B-2** is the optimized energy acceptor owing to its high singlet oxygen quantum yield and long absorption wavelength.^[8d, 9] Such conjugation shows markedly increased singlet-oxygen-generation efficiency upon treating with a broadband NIR LED excitation source (600–800 nm). Relative to photosensitizer **B-2** alone, **RET-BDP** is superior and has 1.9-fold improved singlet-oxygen generation. In addition, **RET-BDP** presented broader, stronger absorption spectra and a 1.6-fold improved singlet oxygen generation relative to widely used photosensitizer of Chlorin e6. After being encapsulated by F-127-FA, the resultant folic acid conjugated nanomicelles (**RET-BDP-TNM**) demonstrate excellent chemical and physical stability under physiological conditions. Their singlet-oxygen quantum yield was determined to be high (58% at 645 nm and 62% at 670 nm) and they have excellent NIR emission in PBS that peaks at 725 nm ($\Phi_F = 1.0\%$). More importantly, **RET-BDP-TNM** is a more efficient cancer therapy *in vitro* and *in vivo* under low-power LED light irradiation than mono-chromophore photosensitizer **B-2-TNM** (Scheme 1). To the best of our knowledge, this is the first time it has been demonstrated that broad absorption of a photosensitizer in the NIR region is better than a general photosensitizer for *in vivo* PDT. This study provides a new method to design highly efficient NIR BODIPY-based photosensitizers that enhance *in vivo* PDT.

To start, we studied the steady photophysical properties of **RET-BDP**, **B-1**, and **B-2** (see Figure 1 and Table S4). UV–Vis absorption spectra of **B-1**, **B-2**, and **RET-BDP** were measured in toluene. As shown in Figure 1a, energy donor distyryl-BODIPY **B-1** has an absorption peak at 645 nm, whereas energy acceptor diiodo-distyryl-BODIPY **B-2** has an absorption peak at 670 nm. Because these absorption bands significantly overlap, **RET-BDP** itself demonstrates an enhanced absorption band peak at ≈ 645 nm. The fluorescence emission spectra of these compounds in toluene were investigated (Figure 1b). Energy donor distyryl-BODIPY **B-1** has a strong emission at 670 nm ($\Phi_F = 52\%$). Upon coupling, the emission of the donor moiety is almost completely quenched in **RET-BDP**, which clearly suggests efficient energy transfer has occurred.^[11] However, **B-2** and **RET-BDP** give rise to emissions at 692 nm upon excitation with 610-nm light. To further verify energy transfer from donor distyryl-BODIPY moiety **B-1** to acceptor diiodo-distyryl-BODIPY moiety **B-2** in **RET-BDP**, the fluorescence excitation spectra of **RET-BDP** was measured.^[11a-c] In Figure S1, the fluorescence excitation and the UV–Vis absorption spectra of **RET-BDP** are analyzed: the two spectra agree well and overlay at 645 and 670 nm. We further validated that energy transfer had taken place by measuring the fluorescence lifetime of **B-1** and **RET-BDP** at 670 nm. **RET-BDP** presented a shorter fluorescence lifetime (2.50 ns) than **B-1** (7.35 ns), which directly suggests a highly efficient RET effect from distyryl-BODIPY moiety **B-1** to diiodo-distyryl-BODIPY moiety **B-2** (Figure S2).^[10] We calculated the overlapping integral for RET process in **RET-BDP** in accordance with a reported method^[11g-i] and the energy transfer efficiency is up to 99.9%.^[11g-i] (see SI) These results show that intramolecular energy transfer from the donor to the acceptor is efficient.^[10-11]

The singlet-oxygen-generation capability of **RET-BDP** was tested with 1,3-diphenylisobenzofuran (DPBF) as the $^1\text{O}_2$ scavenger. (Scheme S2)^[11a-c]. **RET-BDP** was 1.9-fold faster in singlet-oxygen generation than **B-2** upon exposure to NIR (Figure S3). Relative to conventionally used methyl blue (MB) and Chlorin e6 photosensitizers,^[3-4] **RET-BDP** shows a marked enhancement (2.8-fold and 1.6 fold) in singlet-oxygen generation (Figure S3 and Figure S6). Monochromatic light at 645 nm from a Horiba spectrometer was used as the excitation source in this study. As a result of a lack of intersystem crossing (ISC), **B-1** alone did not generate measurable singlet oxygen (Figure S4). In contrast, **RET-BDP** showed significantly higher singlet-oxygen generation efficiency than photosensitizer **B-2** alone (Figure S4). To verify the chemical coupling effect of RET, **B-1** (5 μM) and **B-2** (5 μM) were mixed as a control experiment to make a solution for analysis with **RET-BDP** (5 μM). We found that because of the lack of RET effect, the mixture of **B-1** and **B-2** without chemical coupling had much poorer singlet-oxygen generation than **RET-BDP** (Figure S5). These results suggest that **RET-BDP**'s singlet-oxygen-generation capability is indeed enhanced by RET construction.

To render **RET-BDP** water soluble and able to target tumors, a biodegradable folic acid conjugated pluronic F-127-FA amphiphilic polymer was prepared to encapsulate **RET-BDP**. The entrapment loading efficiency of **RET-BDP** in the polymer was determined to be 79% by UV-V is absorption.^[6c,12] As shown in Figure S7a, nanomicelle **RET-BDP-TNM** is small (12 ± 3.0 nm) as measured by TEM. In addition, as shown in Figure S7b, we tried to measure the morphology of **RET-BDP-TNM** on a mica sheet surface by atomic force microscopy (AFM), which gave a size distribution of 14.7 ± 3.2 nm. The micelle's hydrodynamic diameter was determined to be 31 ± 4.2 nm by using dynamic light scattering (DLS; Figure 2a). It is worth noting that the size of our nanoparticles is smaller than typically reported photosensitizer-loaded PDT nanoparticles.^[13] The hydrodynamic size of **RET-BDP-TNM** remained almost constant for 60 days (Figure S8) and it is also stable in 10% phosphate-buffered saline (FBS) solutions. After 200 hours, the fluorescence of **RET-BDP-TNM** remains nearly unchanged (Figure S8). These results suggest that **RET-BDP-TNM** is remarkably stable under physiological conditions. As controls, **B-1** and **B-2** were also encapsulated by pluronic F-127-FA polymer to give **B1-TNM** and **B2-TNM**, respectively, and the size of the resulting micelles was measured (Figure S9).

The photophysical properties of nanoparticles **RET-BDP-TNM** were then studied in PBS. As shown in Figure 2b, **RET-BDP-TNM** gives rise to a strong and broad absorption band from 600–750 nm. Fluorescence emission was observed at 725 nm in PBS ($\Phi_f = 1.0\%$) (Figure S10). The NIR fluorescence of **RET-BDP-TNM** is beneficial to track and evaluate **RET-BDP-TNM** distribution *in vivo*.^[13] The photostability of **RET-BDP-TNM** was tested by UV-V is absorption spectroscopy. No obvious photobleaching of **RET-BDP-TNM** was observed after exposure to 600–800 nm LED light (10 mW cm^{-2}) for 60 min (Figure S11), which suggests that the photostability of **RET-BDP-TNM** satisfies the requirements for photodynamic therapy processes. In addition, the photodecomposition quantum yield was estimated to be 2.32 % by using a reported method.^[14a] The singlet-oxygen generation of **RET-BDP-TNM** was measured with DPBF as the singlet-oxygen scavenger in a mixed solution (PBS/THF, 4:1 v/v). **RET-BDP-TNM** showed fast singlet-oxygen generation when

irradiated with 600–800 nm LED light (Figure 2c). With monochromatic light at 645 nm from a Horiba spectrometer as the excitation source, the singlet-oxygen-generation rate of **RET-BDP-TNM** was quantified to be a 1.8-fold improvement relative to that of **B2-TNM** alone (Figure S12).

Then **RET-BDP-TNM** was tested for PDT *in vitro*. The phototoxicity of **B1-TNM**, **B2-TNM**, and **RET-BDP-TNM** was measured by 3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide (MTT) assays in HeLa cells. When exposed to 600–800 nm LED light (10 mW cm^{-2}), cell death was not obvious with **B1-TNM** (Figure S13), whereas **B2-TNM** and **RET-BDP-TNM** resulted in high tumor cell cytotoxicity. **RET-BDP-TNM** and **B2-TNM** had negligible cell toxicity in the dark. In addition, the PDT effect of **RET-BDP-TNM** was superior to **B2-TNM** (Figure 3a-c). The PDT effect of **RET-BDP-TNM** was also tested against other cancer cells, such as 4T1 (breast cancer cells) and KP7B (lung cancer cells). The half lethal dose (IC_{50}) of **RET-BDP-TNM**, **RET-BDP-TNM**, and **B2-TNM** for HeLa, KP7B, and 4T1 cell lines were calculated.^[14b] As shown in Table S5, **RET-BDP-TNM** presented lower IC_{50} values with HeLa cells ($14.8 \pm 1.3 \text{ }\mu\text{g/mL}$), 4T1 cells ($15.2 \pm 0.9 \text{ }\mu\text{g/mL}$), and KP7B ($18.9 \pm 1.5 \text{ }\mu\text{g/mL}$) than **B2-TNM**. To further observe cancer inhibition by **RET-BDP-TNM** a propidium iodide (PI) assay was performed.^[14c-d] As shown in Figure 3 upper left, strong red fluorescent emission was observed in HeLa cells' nucleus after irradiation with light (600–800 nm), which suggests that cell death occurred. This result is consistent with the MTT assay results. Sodium azide is a well-known singlet oxygen quencher.^[2b,13d] Cells viability will be increased in the presence of sodium azide as a result of quenching of singlet oxygen, so that fluorescence of propidium iodide (PI) is weak (Figure 3d upper right). In the absence of light, **RET-BDP-TNM** does not induce the cells death because light is essential to PDT, so the fluorescence of PI is very weak (Figure 3d lower right and left). The mechanism of **RET-BDP-TNM**-induced cell death was investigated by using 2', 7'-dichlorofluorescein diacetate (DCFH-DA) assays.^[15] After incubating HeLa cells with **RET-BDP-TNM** for 1 h weak green fluorescence was observed in the dark. However, in the presence of **RET-BDP-TNM** and light irradiation a bright green emission was clearly observed (Figure 3e upper left). In addition, only weak green fluorescence was observed in the presence of sodium azide (Figure 3e upper right).^[2b, 13d] In the absence of light singlet oxygen is not generated in the cells, so we cannot observe green fluorescence of DCF in the cells (Figure 3e lower left and right). In addition, we measured cell viability in the presence of NaN_3 by means of MTT assay, in which the killing effects of **RET-BDP-TNM** reduced relative to tests in the absence of NaN_3 (Figure S14). Overall, these results clearly reveal that **RET-BDP-TNM** generates singlet oxygen efficiently, which leads to cancer-cell apoptosis.

Tumor targeting is an important feature of PDT. Therefore, we also prepared folic-acid-free nanomicelles (**RET-BDP-TNM**) as a control experiment and analyzed the cells' uptake of **RET-BDP-TNM** and **RET-BDP-TNM**. **RET-BDP-TNM** was taken up by HeLa cells to a greater extent than **RET-BDP-TNM** (Figure S15a and S15b) because more folic acid receptors are known to express on cancer cell membranes.^[16] **RET-BDP-TNM** was more efficient at inhibiting HeLa cells than **RET-BDP-TNM** (Figure S16). We also evaluated the killing effects of **RET-BDP-TNM** on normal cells (green go cells~normal epithelial cells)

and cancer cells (HeLa cells). **RET-BDP-TNM** inhibited cancer cells more efficiently than normal epithelial cells (Figure S15c). These results demonstrate that **RET-BDP-TNM** targets cancer cells more specifically.

To understand the tumor-targeting and biodistribution properties of **RET-BDP-TNM** in living mice, NIR fluorescence imaging of **RET-BDP-TNM** was applied *in vivo*. This feature may be beneficial for the development of NIR-imaging-guided cancer therapies.^[13] **RET-BDP-TNM** was intravenously injected into BALB/c mice with 4T1 breast tumors. After 8 h, we found significant fluorescence enhancement at the tumor site; the fluorescence intensity reached a maximum after 24 h. **RET-BDP-TNM** showed higher fluorescence intensity than **RET-BDP-TNM** because the folic acid ligand contributed to the accumulation of **RET-BDP-TNM** at the tumor site. After 96 h, the fluorescence of **RET-BDP-TNM** disappeared, which suggests that **RET-BDP-TNM** may be excreted by macrophage cells^[17] (Figure 4). The distribution of **RET-BDP-TNM** in 4T1 tumor-bearing mice was also measured in different organs over time (24, 48, and 96 h) by *ex vivo* fluorescence imaging. The major organs and tumors were dissected, and fluorescence spectra were acquired for further analysis (Figure S17). After 24 h after 4T1-bearing mice were injected; we observed stronger fluorescence in the liver than in other organs. After 48 h, fluorescence in the tumor increased, whereas the fluorescence intensity decreased in the liver. After 96 h, fluorescence disappeared from both the liver and the tumor.

To verify the phototoxicity of **RET-BDP-TNM** *in vivo*, we injected **RET-BDP-TNM** intravenously into 4T1 tumor-bearing mice. A low-power LED was used as the excitation source to activate **RET-BDP-TNM** for *in vivo* PDT. The phototoxicity of **RET-BDP-TNM** to the tumor was assessed by monitoring the relative volumes of the tumors.^[18] The treatment efficacy, in terms of tumor-cell death, was also evaluated by hematoxylin and eosin (H&E) staining of tissue sections. Six groups of tumor-bearing mice were subjected to different treatments by intravenous injection (see Experimental Section in the Supporting Information). After 24 h, as **RET-BDP-TNM** accumulation at the tumor sites reached its maximum, selected groups were irradiated with NIR LED light (10 mW cm⁻²). As shown in Figure 5, no tumor growth inhibition or tumor tissue necrosis was observed in group 1. Groups 2 and 3 also showed no tumor growth inhibition or tumor tissue necrosis, which indicates that **RET-BDP-TNM** has negligible toxicity in the dark and a low-power excitation source does not result in a noticeable photothermal effect. In marked contrast, tumor growth in group 6 was significantly suppressed, and the tumor tissue showed obvious necrosis, which indicates that **RET-BDP-TNM** can be effectively activated by LED irradiation to produce strong tumor phototoxicity. Group 4 showed no significant therapeutic effect in tumor tissues because of the lack of the targeting moiety, folic acid. Group 5 showed weaker tumor inhibition than group 6 because **RET-BDP-TNM** exhibits broader, stronger absorption and more efficient singlet-oxygen generation than **B2-TNM** in the NIR window. To the best of our knowledge, this is the first time that PDT has been realized *in vivo* by using a photosensitizer based on a RET mechanism.

To study the potential toxicity and side effects of **RET-BDP-TNM**, we measured the mice's body-weight loss and analyzed H&E stained slices of their major organs, which included heart, liver, spleen, lung, and kidney. Mice treated with **RET-BDP-TNM** did not show any

weight loss (Figure S18). After 10 days, both the PDT-treated mice and the untreated, age-matched, healthy mice were sacrificed. No noticeable signs of organ damage were observed in the H&E-stained organ slices, which suggests that **RET-BDP-TNM** is safe for *in vivo* PDT application (Figure S19).

In summary, nano-photosensitizer **RET-BDP-TNM** was successfully constructed. It operates based on a RET mechanism and significantly enhances photon unitization in the NIR window and singlet-oxygen generation. Ultra-small organic **RET-BDP-TNM** demonstrates excellent photostability, enhanced singlet-oxygen generation, low toxicity in the dark, and the ability to target tumors with great specificity. Moreover, **RET-BDP-TNM** can be activated by low-power NIR LED sources, which leads to efficient tumor inhibition *in vivo*. This work introduces a new strategy to design and extend the molecular options of efficient NIR photosensitizers for clinical anticancer practice.

Experimental Section

Detailed experimental materials and methods can be found in the Supporting Information.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

This research was supported by a grant from the China Scholarship Council (CSC) to L. H. This research was supported by the National Institutes of Health (grant number R01MH103133) and the Human Frontier Science Program (grant number RGY-0090/2014) to G.H.

References

1. a) Dolmans DEJGJ, Fukumura D, Jain K. *Nat Rev Cancer*. 2003; 3:380. [PubMed: 12724736] b) Lovell JF, Liu TWB, Chen J, Zheng G. *Chem Rev*. 2010; 110:2839. [PubMed: 20104890] c) Lucky SS, Soo KC, Zhang Y. *Chem Rev*. 2015; 115:1990. [PubMed: 25602130] d) Cheng L, Wang C, Feng L, Yang K, Liu Z. *Chem Rev*. 2014; 114:10869. [PubMed: 25260098] e) Liang C, Xu L, Song G, Liu Z. *Chem Soc Rev*. 2016; 45:6250. [PubMed: 27333329]
2. a) Ge JC, Lan MH, Zhou BJ, Liu WM, Guo L, Wang H, Jia QY, Niu GL, Huang X, Zhou HY, Meng XM, Wang PF, Lee CS, Zhang WJ, Han XD. *Nat Commun*. 2014; 5:4596. [PubMed: 25105845] b) Mitsunaga M, Ogawa M, Kosaka N, Rosenblum LT, Choyke PL, Kobayashi H. *Nat Med*. 2011; 17:1685. [PubMed: 22057348]
3. a) Ethirajan M, Chen YH, Joshi P, Pandey RK. *Chem Soc Rev*. 2011; 40:340. [PubMed: 20694259] b) Allison RR, Downie GH, Cuenca R, Hu XH, Childs CJ, Sibata CH. *Photodiagnosis Photodyn Ther*. 2004; 1:27. [PubMed: 25048062] c) Redmond RW, Gamlin JN. *Photochem Photobiol*. 1999; 70:391. [PubMed: 10546544]
4. a) Chen YJ, Zheng W, Li YQ, Zhong JY, Ji JG, Shen PP. *Cancer Sci*. 2008; 99:2019. [PubMed: 19016762] b) Chen H, Tian J, He W, Guo Z. *J Am Chem Soc*. 2015; 137:1539. [PubMed: 25574812] c) Lim EJ, Oak CH, Heo J, Kim YH. *Oncol Rep*. 2013; 30:856. [PubMed: 23708127] d) Tardivo JP, Giglio AD, Oliveira CS, Gabrielli DS, Junqueira HC, Tada DB, Severino D, Turchiello RF, Baptista MS. *Photodiagnosis Photodyn Ther*. 2005; 2:175. [PubMed: 25048768] e) Orth K, Beck G, Genze F, Rück A. *J Photochem Photobiol B*. 2000; 57:186. [PubMed: 11154085] f) Teichert MC, Jones JW, Usacheva MN, Biel MA. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod*. 2002; 93:155. [PubMed: 11862203] g) He X, Wu X, Wang K, Shi B, Hai L. *Biomaterials*. 2009; 30:5601. [PubMed: 19595455]

5. a) Lincoln R, Kohler L, Monro S, Yin HM, Stephenson M, Zong RF, Chouai A, Dorsey C, Hennigar R, Thummel RP, McFarland SA. *J Am Chem Soc.* 2013; 135:17161. [PubMed: 24127659] b) Huang L, Zhao J, Guo S, Zhang C, Ma J. *J Org Chem.* 2013; 78:5627. [PubMed: 23668289]
6. a) Wang M, Chen Z, Zheng W, Zhu H, Lu S, Ma E, Tu D, Zhou S, Huang M, Chen X. *Nanoscale.* 2014; 6:8274. [PubMed: 24933297] b) Ai X, Ho CJH, Aw J, Attia ABE, Mu J, Wang Y, Wang X, Wang Y, Liu X, Chen H, Gao M, Chen X, Yeow EKL, Liu G, Olivo M, Xing B. *Nat Commun.* 2016; 7:10432. [PubMed: 26786559] c) Idris NM, Gnanasammandhan MK, Zhang J, Ho PC, Mahendran R, Zhang Y. *Nat Med.* 2012; 18:1580. [PubMed: 22983397]
7. a) Sun Y, Feng W, Yang P, Huang C, Li F. *Chem Soc Rev.* 2015; 44:1509. [PubMed: 25113504] b) Gnach A, Lipinski T, Bednarkiewicz A, Rybka J, Capobianco JA. *Chem Soc Rev.* 2015; 44:1561. [PubMed: 25176037]
8. a) Kamkaew A, Lim SH, Lee HB, Kiew LV, Chung LY, Burgess K. *Chem Soc Rev.* 2013; 42:77. [PubMed: 23014776] b) Zhao J, Xu K, Yang W, Wang Z, Zhong F. *Chem Soc Rev.* 2015; 44:8904. [PubMed: 26465741] c) Kamkaew A, Burgess K. *J Med Chem.* 2013; 56:7608. [PubMed: 24063347] d) He H, Lo PC, Yeung SL, Fong WP, Ng DKP. *J Med Chem.* 2011; 54:3097. [PubMed: 21417218] e) Loudet A, Burgess K. *Chem Rev.* 2007; 107:4891. [PubMed: 17924696] f) Lu H, Mack J, Yang Y, Shen Z. *Chem Soc Rev.* 2014; 43:4778. [PubMed: 24733589] g) Zhao J, Wu W, Sun J, Guo S. *Chem Soc Rev.* 2013; 42:5323. [PubMed: 23450221] h) Ulrich G, Ziessele R, Harriman A. *Angew Chem Int Ed.* 2008; 47:1184. i) Cui X, Zhang CS, Xu KJ, Zhao JZ. *J Mater Chem C.* 2015; 3:8735.
9. a) Ke MR, Yeung SL, Ng DKP, Fong WP, Lo PC. *J Med Chem.* 2012; 55:5446. [PubMed: 22646131] b) Atilgan S, Ekmekci Z, Dogan AL, Guc D, Akkaya EU. *Chem Commun.* 2006:4398. c) Awuah SG, You Y, Adv RSC. 2012; 2:11169. d) Zhao J, Huang L, Cui X, Li S, Wu H. *J Mater Chem B.* 2015; 3:9194.
10. a) Lu S, Tu D, Hu P, Xu J, Li R, Wang M, Chen Z, Huang M, Chen X. *Angew Chem Int Ed.* 2015; 54:7915. b) Idris NM, Jayakumar MKG, Bansal A, Zhang Y. *Chem Soc Rev.* 2015; 44:1449. [PubMed: 24969662]
11. a) Guo S, Ma LH, Zhao JZ, Kucukoz B, Karatay A, Hayvali M, Yaglioglu HG, Elmali A. *Chem Sci.* 2014; 5:489. b) Huang L, Cui XN, Therrien B, Zhao JZ. *Chem Eur J.* 2013; 19:17472. [PubMed: 24318269] c) Zhang CS, Zhao JZ, Wu S, Wang ZL, Wu WH, Ma J, Guo S, Huang L. *J Am Chem Soc.* 2013; 135:10566. [PubMed: 23790008] d) Bozdemir OA, Erbas-Cakmak S, Ekiz OO, Dana A, Akkaya EU. *Angew Chem Int Ed.* 2011; 50:10907. e) Ziessele R, Ulrich G, Haefele A, Harriman A. *J Am Chem Soc.* 2013; 135:11330. [PubMed: 23863135] f) Zhang X, Xiao Y, Qian X. *Angew Chem Int Ed.* 2008; 47:8025. g) Zhang X, Xiao Y, Qian X. *Org Lett.* 2008; 10:29. [PubMed: 18069840] h) Zhang X, Xiao Y, He L, Zhang Y. *J Org Chem.* 2014; 79:6315. [PubMed: 24921157] i) Berberan-Santos MN, Choppinet P, Fedorov A, Jullien L, Valeur B. *J Am Chem Soc.* 2000; 122:11876.
12. Papadimitriou S, Bikiaris D. *J Control Release.* 2009; 138:177. [PubMed: 19446585]
13. a) Tian J, Ding L, Ju H, Yang YC, Li XL, Shen Z, Zhu Z, Yu JS, Yang CJ. *Angew Chem Int Ed.* 2014; 53:9544. b) Park YI, Lee KT, Suh YD, Hyeon T. *Chem Soc Rev.* 2015; 44:1302. [PubMed: 25042637] c) Yang D, Ma P, Hou Z, Cheng Z, Li C, Lin J. *Chem Soc Rev.* 2015; 44:1416. [PubMed: 24988288] d) Tian J, Ding L, Xu HJ, Shen Z, Ju H, Jia L, Bao L, Yu JS. *J Am Chem Soc.* 2013; 135:18850. [PubMed: 24294991] e) Tian J, Zhou J, Shen Z, Ding L, Yu JS, Ju H. *Chem Sci.* 2015; 6:5969. [PubMed: 28791094]
14. a) Bezares-Cruz J, Jafvert CT, Hua I. *Environ Sci Technol.* 2004; 38:4149. [PubMed: 15352454] b) Lau JTF, Lo PC, Jiang XJ, Wang Q, Ng DKP. *J Med Chem.* 2014; 57:4088. [PubMed: 24793456] c) Nescerecka A, Hammes F, Juhna T. *Journal of Microbiological Methods.* 2016; 131:172. [PubMed: 27810378] d) Niu J, Li C, Wu H, Feng X, Su Q, Li S, Zhang L, Yew DTW, Cho EYP, Sha O. *Acta Histochemica.* 2015; 117:182. [PubMed: 25596876]
15. a) Cui X, Zhao J, Lou Z, Li S, Wu H, Han KI. *J Org Chem.* 2015; 80:568. [PubMed: 25436874] b) Li S, Chang K, Sun K, Tang Y, Cui N, Wang Y, Qin W, Xu H, Wu C. *ACS Appl Mater Interfaces.* 2016; 8:3624. [PubMed: 26492203] c) Yuan Y, Liu B. *ACS Appl Mater Interfaces.* 2014; 6:14903. [PubMed: 25075548] d) Punjabi A, Wu X, Tokatli-Apollon A, El-Rifai M, Lee H, Zhang Y, Wang C, Liu Z, Chan EM, Duan G, Han G. *ACS Nano.* 2014; 8:10621. [PubMed: 25291544] e) Cakmak Y, Kolemen S, Duman S, Dede Y, Dolen Y, Kilic B, Kostereli Z, Yildirim LT, Dogan AL, Guc D, Akkaya EU. *Angew Chem Int Ed.* 2011; 50:11937. f) Koppenol WH. *Nature.* 262:420. g)

Kalyanaramana B, Darley-Usmarb V, Daviesc KJA, Dennerye PA, Formanc HJ, Grishamg MB, Mannh GE, Moorei K, Roberts LJ, Ischiropoulouse H. Free Radic Biol Med. 2012; 52:1. [PubMed: 22027063]

16. a) Roger E, Kalscheuer S, Kirtane A, Guru BR, Grill AE, Whittum-Hudson J, Panyam J. Mol Pharmaceutics. 2012; 9:2103. b) van Dongen MA, Silpe JE, Dougherty CA, Kanduluru AK, Choi SK, Orr BG, Low PS, Holl MMB. Mol Pharmaceutics. 2014; 11:1696. c) Lu J, Zhao W, Huang Y, Liu H, Marquez R, Gibbs RB, Li J, Venkataramanan R, Xu L, Li S, Li S. Mol Pharmaceutics. 2014; 11:4164.
17. Zhang JF, Liang YC, Lin XD, Zhu XY, Yan L, Li SL, Yang X, Zhu GY, Rogach AL, Yu PKN, Shi P, Tu LC, Chang CC, Zhang XH, Chen XF, Zhang WJ, Lee CS. ACS Nano. 2015; 9:9741. [PubMed: 26390118]
18. a) Wang C, Sun X, Cheng L, Yin S, Yang G, Li Y, Liu Z. Adv Mater. 2014; 26:4794. [PubMed: 24838472] b) Wang S, Huang P, Nie L, Xing R, Liu D, Wang Z, Lin J, Chen S, Niu G, Lu G, Chen X. Adv Mater. 2013; 25:3055. [PubMed: 23404693]

Figure 1.

a) UV–Vis absorption spectra of compounds **B-1**, **B-2**, and **RET-BDP** in toluene; b) emission spectra of compounds **B-1**, **B-2**, and **RET-BDP**, $\lambda_{ex} = 610$ nm, $c = 10$ μ M in toluene at 20 °C.

Figure 2.

a) Dynamic light scattering of **RET-BDP-TNM** in deionized water; b) UV–V is absorption spectrum of **RET-BDP-TNM** nanomicelles; c) plot of change in optical density of DPBF at 415 nm against irradiation time, with **RET-BDP-TNM** as the photosensitizer, in PBS with 10% THF, excitation range is 600–800 nm, and power intensity is 10 mW cm^{-2} .

Figure 3. Different cancer cell lines' (HeLa, KP7B, and 4T1) viability after treatment with different concentrations of **RET-BDP-TNM** and **B2-TNM** with or without irradiation, as measured by MTT assay: a) HeLa cells; b) KP7B cells; and c) 4T1 cells. Red columns: without PSs and NIR; green columns: only NIR; blue columns: **B2-TNM** and NIR; cyan columns: **RET-BDP-TNM** and NIR. NIR 600–800 nm, 10 mW cm^{-2}). d) Confocal fluorescence microscopy observed with **RET-BDP-TNM**-mediated (10 $\mu\text{g mL}^{-1}$) PDT with PI staining for dead cells, $\lambda_{\text{ex}} = 514$ nm, capture wavelength 580–620 nm; e) DCFH-DA verified singlet-oxygen generation in **RET-BDP-TNM**-mediated PDT (10 $\mu\text{g mL}^{-1}$), $\lambda_{\text{ex}} = 476$ nm, capture wavelength 485–520 nm, scale bar represents 30 μm .

Figure 4. Specific targeted NIR-fluorescence tumor imaging *in vivo*. a) Time-dependent *in vivo* NIR fluorescence images of 4T1 tumor-bearing mice after intravenous injection of $50 \mu\text{g mL}^{-1}$, $150 \mu\text{L}$: **RET-BDP-TNM** as the positive group and **RET-BDP-NNM** as the negative group. b) Normalized fluorescence intensity of **RET-BDP-TNM** and **RET-BDP-NNM** in 4T1 tumors at 8, 24, 48, and 96 h. Data are mean $\pm$ s.e.m ($n = 3$ mice).

Figure 5.
a) Tumor-growth inhibition by **RET-BDP-TNM**-mediated PDT in 4T1 tumors; PDT was performed 24 h after **RET-BDP-TNM** injection ($50 \mu\text{g mL}^{-1}$, $150 \mu\text{L}$). Values are means $\pm$ s.e.m. ($n = 4$ mice per group); b) digital photos of tumors for the four groups of mice. c) H&E staining of tumor-tissue sections from different treatment groups after 10 days of treatment, scale bar represents $50 \mu\text{m}$.

Scheme 1.

Schematic illustration of RET-photosensitizer-mediated PDT (RET-BDP-TNM; TNM = targeted nanomicelle) and the molecular structure of **RET-BDP**.