Published in final edited form as:

Dalton Trans. 2017 October 10; 46(39): 13562–13581. doi:10.1039/c7dt02317k.

Shortwave infrared luminescent Pt-nanowires: mechanistic study of emission in solution and solid state

Carl Cheadle¹, Jessica Ratcliff¹, Mikhail Berezin^{2,*}, Vadim Pal'shin³, Victor N. Nemykin⁴, and Nikolay N. Gerasimchuk^{1,*}

¹Department of Chemistry, Temple Hall 431, Missouri State University, Springfield, MO 65897, USA

²Department of Radiology, Washington University School of Medicine, St. Louis, MO 63110, USA

³J. Bennett Johnston Sr., Center for Advanced Microstructures & Devices, Louisiana State University, 6980 Jefferson Hwy, Baton Rouge, LA 70806, USA

⁴Department of Chemistry and Biochemistry, University of Minnesota-Duluth, 1039 University Drive, Duluth, MN 55812, USA

Abstract

Several complexes of “PtL₂” composition containing two cyanoxime anions – 2-oximino-2-cyano-N-piperidineacetamide (PiPCO[−]) and 2-oximino-2-cyano-N-morpholylacetamide (MCO[−]) have been obtained and characterized both in solutions and in solid state. Complexes exist as two distinct polymorphs: monomeric yellow complexes, and dark-green [PtL₂]_n 1D polymers, while for the MCO[−] anion a red, solvent containing dimeric [Pt(MCO)₂xDMSO]₂ complex also has been isolated. The interconversion of polymorphs was investigated. The monomeric PtL₂ units are arranged into the anisotropic extended solid [PtL₂]_n polymers with the help of Pt—Pt metallophilic interactions. Crystal structures of monomeric PtL₂ (L= PiPCO[−], MCO[−]) and red dimeric [Pt(MCO)₂xDMSO]₂ complexes were determined and revealed the cis-arrangement of cyanoxime anions. The Pt-Pt distance in the “head-to-tail” red dimer was found to be 3.133 Å. The structure of polymeric [Pt(PiPCO)₂]_n compound was elucidated using the EXAFS method and evidenced the formation of the Pt-wire with ~3.15 Å intermetallic separations. The EPR spectra of both 1D polymers at variable temperatures indicate the absence of Pt(III) species. Both pure dark-green [PtL₂]_n polymers showed considerable room temperature electrical conductivity of 20–30 S/cm, which evidences the formation of mixed valence Pt(II)/Pt(IV) system. We discovered that these 1D polymeric [PtL₂]_n complexes show an intense NIR fluorescence beyond 1000 nm, while yellow monomeric PtL₂ complexes are not emissive at all. The room temperature excitation spectra of 1D polymeric [PtL₂]_n complexes demonstrated their strong emission beyond 1000 nm regardless of the used excitation wavelength between 350 and 800 nm, which is typical of systems with delocalized charge carriers. For the first time the formation of mixed valence “metal wire”

*To whom correspondence should be addressed. NNGerasimchuk@MissouriState.edu and berezinm@mir.wustl.edu.

Electronic Supporting Information (ESI). This extensive section of the paper was compiled into several categories by the subject for better readers' navigation through pages of important and useful supporting materials. CIF files for all presented herein structures were deposited at CCDC under the following numbers: Pt(MCO)₂ – 1451036, Pt(PiPCO)₂ – 1451037, and [Pt(MCO)₂(DMSO)]₂ – 1451035. Both CIFs and checkCIF reports for discussed crystal structures are available from the ESI section. This material is available free of charge via the Internet at the journal website.

assembled by metallophilic interactions is directly linked both with an intense fluorescence in the NIR region of spectrum and the electrical conductivity. The effect of concentration of $[\text{PtL}_2]_n$ complexes dispersed in the dielectric salt matrix on the photoluminescence wavelength and intensity was investigated. Both polymers show a remarkably high for this region of spectrum quantum yield reaching ~2%. Variable temperature emission of polymeric $[\text{PtL}_2]_n$ in the -190 - $+60^\circ\text{C}$ range was studied as well.

TOC image

1. Introduction

There is unfading interest in one-dimensional (later 1D) “metal wires” bearing a variety of organic and inorganic ligands and transition metals.^{1,2} Many of these numerous coordination polymers are held together via metallophilic interactions and also represent mixed valence systems.³ Their classification and properties were outlined in the pioneering work of Robin and Day,^{4,5} Allen and Hush,^{6,7} Fackler,⁸ and summarized by Terril and Murray.⁹ In mixed valence complexes a low energy barrier between two different oxidation states provides the condition for electron transitions (hopping)⁹ induced by light or temperature. Solids that exhibit substantial conductivity represent systems with delocalized bonding^{3–5} (type III), commonly have an intense color (or metallic shine), and charge-transfer bands in the visible or near infrared (NIR) region.¹⁰ The prime interest in these systems has been driven by the fact that the major obstacle for a further decrease in the size of miniature electronic devices is heat dissipation, since conventional semiconductors require efficient cooling due to poor conductance and significant heat generation. Therefore, mixed valence compounds were extensively studied with the aim of potential application in molecular electronics due to their high electric conductance at ambient conditions. The mixed valence complexes with a two electrons transfer often possess polymeric 1D columnar structures.^{11–14} These electrons are thought to have coherence similar to that in the Cooper pair, with Pt-based systems being studied the most.^{10, 15–17} Historically there are two major types of conducting mixed valence Pt-based compounds known: MX complexes in which there are 50:50 mixture of Pt(II)/Pt(IV) centers^{18, 19} and KCP - classic cyano-platinates^{20, 21} such as $\text{K}_2[\text{Pt}(\text{CN})_4]\text{Br}_{0.3}$, Krogman’s salt (or partially-oxidized-cyano-platinates, later POCP)¹⁰ (*Electronic Supporting Information, ESI 1*). Other platinum-based 1D solids include mixed valence polymeric oxalates,^{22, 23} benzoquinon dioximes,^{24–26} and, more recently,

dimethylglyoximates, and its analogs.^{27–30} Blue Pt-pyrimidines and amidates,³¹ dimeric- and trimeric complexes with similar ligands were studied as well.^{32–35} A limited success in the development of a molecular electric conductor based on the KCP and MX systems is attributed to the poor ligands design of these 1D metal-organic networks, insufficient control of the crystal architecture, and limited electronic tunability of the obtained systems. Thus, the MX and KCP complexes contain homogeneous donor atoms sets: either [PtN₄], or [PtN₄X₂] (X=Cl, Br, I in MX solids), or [PtC₄] (in KCP solids), or [PtO₄] (in Pt-blue oxalates) in the metal center environment. The abovementioned Pt- α -dioximates also have a [PtN₄] square-planar environment.^{24, 26} The most important disadvantage of these systems from a chemical standpoint is their low solubility, which precluded their application as thin films conductors deposited on dielectric surfaces.

With the exception of several Pt(II) compounds obtained earlier for *in vitro* cytotoxicity testing,^{36–38} complexes of platinum with monoximes have never been systematically studied.

On the other hand, mixed valence complexes of the Type II and Type III^{5, 8} have been known to have low energy transitions in the red part of the electromagnetic spectrum including the NIR region. In the last decade work in the NIR technology opened a variety of new ways in industrial, scientific, military and medical applications with new optical devices,^{39, 40, 92} imaging techniques^{41, 42} contrast agents,^{43, 44} and sensors.^{45, 46} As a result of advances of new technology, a diverse set of photoluminescent compounds, emitting in the NIR region from small molecules to nanoparticles and larger aggregates, has emerged. The great majority of these materials, however, emit up to 850 nm while the number of NIR emitters with an emission beyond 900 nm is very limited. To the best of our knowledge no studies of emissive properties in that NIR region of mixed valence Pt-complexes have been carried out.

Recently we have discovered six dark-green powdery Pt-cyanoximates that demonstrate temperature dependent strong emission beyond 900 nm in the NIR region.^{48,47}

Thus, our interest in mixed valence oximes-based coordination polymers of platinum is two-fold: 1) several Pt-cyanoximates have demonstrated significant *in vitro* cytotoxicity against human cancer cells at the level of cisplatin;^{36, 38} 2) we recently discovered that one of those new Pt complexes with N,N'-diethylamino-2-oximino-2-cyanoacetamide (DECO)⁴⁸ self-assemble in solutions into 1D, intensely colored mixed valence species that are semiconductors at ambient conditions in solid state. Therefore, these complexes can be viewed as suitable candidates for *theranostic* applications because they combine an imaging/diagnostic possibility and therapeutic potential as well. Now we extended our investigations on other two members of this family of Pt complexes.⁹³ In this paper we report the preparation, thorough characterization in solid state and solutions three soluble in organic solvents Pt-cyanoximates that contain anionic MCO[−] and PiPCO[−] ligands (Scheme 1). It should be noted that earlier we presented synthesis and data of considerable biological activity of yellow monomeric Pt(MCO)₂ and Pt(PiPCO)₂ complexes.^{36–38} Their polymorphism and photophysical characteristics were unknown at that time.

2. Experimental Section

General Considerations

The common chemicals and solvents were all reagent grade (ALDRICH) and used without further purification. The TLC for ligands' identification were carried out on silica-coated glass plates (Merck) with a 256 nm fluorescent indicator. Elemental analyses on C, H, N content were performed at the Atlantic Microlab (Norcross, GA). Melting points were measured on a Digimelt apparatus without correction.

Cyclic Voltammetry (CV) and Differential Pulse Voltammetry (DPV) studies

Electrochemical measurements were conducted using a CHI-620C electrochemical analyzer utilizing the three-electrode scheme. Unless it is mentioned, platinum working, platinum auxiliary and Ag/AgCl pseudo-reference electrodes were employed in a 0.1 M solution of TBAP in DMSO for electrochemical experiments. In all cases, the redox potentials are referenced to the FcH/FcH^+ couple using ferrocene as an internal standard.

Dynamic Light Scattering

Particles size measurements during the course of the preparation of 1D polymeric complexes and for colloidal systems of $[\text{PtL}_2]_n$ ($\text{L}=\text{MCO}$, PiPCO) were carried out in organic solvents (spectral grade DMF, acetonitrile, DMSO), and in micelles with the help of Nano-Brook Omni apparatus from Brookhaven Inc. For these studies D_2O was used to eliminate possible absorbance of the NIR light with H_2O .

Micelles Preparation

The micelles originated after mixing of fine powders of dark-green $[\text{PtL}_2]_n$ ($\text{L}=\text{MCO}$, PiPCO) complexes with sodium decanoate, $\text{C}_9\text{H}_{19}\text{COONa}$ (later – C10) solution and sodium dodecyl-sulfate, $\text{C}_{10}\text{H}_{21}\text{SO}_3\text{Na}$ (later – SDS) solutions with the help of Branson 1510 ultrasound bath for 5 minutes. All procedures were carried out at $+25^\circ\text{C}$. The amount of water used was 5 mL, and the amount of detergent used was ~20 mg. Micelles were let stay in a dark for a week and clear green solutions were pipetted for studies from small amount of fine sediments at the bottom of the vial.

Pellets preparation

The KBr tablets for photophysical measurements were pressed as 13 mm disks from the thoroughly homogenized within 1-minute mixture of the IR-spectroscopy grade KBr and the studied complexes in a stainless steel ball mill. Typical amounts of ingredients were 10 mg of the PtL_2 complexes and 190 mg of dry KBr. The Carver hydraulic press at 23°C and pressure of 9 metric tons (~6000 psi) was used to make those pellets.

Synthesis

The preparation of the two cyanoximes HPiPCO and HMCO was accomplished as previously described.³⁶ Both organic ligands represent white powders soluble in alcohols, CH_3CN , acetone and sparingly soluble in water. Pure HPiPCO has m.p.= 151°C , $R_f = 0.31$ ($\text{EtOAc}/\text{hexane} = 1:1$), while HMCO has m.p.= 162°C , and $R_f = 0.38$ in $\text{EtOAc}/\text{hexane} =$

2:1. The preparation of Pt-cyanoximates was carried out according to the two step method depicted in Scheme 2 using a slightly modified previously published procedure.⁴⁹ Syntheses were repeated five times with averaged yields of dark-green polymeric $[\text{PtL}_2]_n$ complexes ($\text{L} = \text{PiPCO}$, MCO) to be 71% and 65% respectively.

The typical preparation is reported for only one compound – $[\text{Pt}(\text{PiPCO})_2]_n$ while the time course of the reactions was photo-documented as shown in ESI 2–4. Thus, 0.2283 g (1.26 mM) of microcrystalline HPiPCO were placed in a beaker with 5 mL distilled water, and then 0.087 g (0.63 mM) of solid K_2CO_3 were added at once upon stirring. The reaction mixture immediately turned bright yellow and the white powder of HPiPCO dissolved with the formation of the K^+PiPCO^- solution and evolution of CO_2 . The solution was heated at first to ensure the complete solubilization of the salt in water, and then was filtered through a glass-wool plug. The 0.2615 g (0.063 mM) of K_2PtCl_6 in 3 mL of water was added dropwise within 5 min to the above clear yellow solution of the K^+PiPCO^- under stirring. The reaction mixture began to change the color and became turbid, and after ~1 hour a very fine dark-green precipitate became visible. It was left overnight at room temperature in the dark, followed by filtration and two times washing of the precipitate with 5 mL of water. The $[\text{Pt}(\text{PiPCO})_2]_n$ was dried in a vacuum desiccator under $\text{H}_2\text{SO}_4(\text{c})$ giving 0.2458 g of the complex (71%). A very similar procedure was used for the preparation of $[\text{Pt}(\text{MCO})_2]_n$ with the amounts of reagents as: 0.2503 g (1.36 mM) of HMCO , 0.0944 g (0.68 mM) of K_2CO_3 , and 0.2836 g (0.68 mM) K_2PtCl_6 ; the yield of the dark-green solid was 65 % (0.2483 g). For $\text{C}_{16}\text{H}_{20}\text{N}_6\text{O}_4\text{Pt} - \text{Pt}(\text{PiPCO})_2$ – calculated (found), %: C – 34.60 (33.67), H – 3.63 (3.66), N – 15.13 (14.66). For $\text{C}_{14}\text{H}_{16}\text{N}_6\text{O}_6\text{Pt} - \text{Pt}(\text{MCO})_2$ – calculated (found), %: C – 30.06 (29.38), H – 2.88 (2.97), N – 15.02 (14.40). Both complexes have a very similar solubility in organic solvents (ESI 5, 6) and are thermally stable to ~170°C (ESI 7,8).

The preparation of the red dimer – $[\text{Pt}(\text{MCO})_2 \times (\text{DMSO})]_2$ – was carried out from dark-green $[\text{Pt}(\text{MCO})_2]_n$, 0.242 mg, upon dissolution in pure DMSO (1 mL) at ~45°C. The initial green solution slowly became yellow and after an overnight slow cooling in a thermostat, the fine red needles of the dimer were collected on a filter paper. The complex is not very stable and, after a day, red needles become yellow (a monomeric complex with no solvent in the lattice). All the operations and handling of this complex must be expeditious. Its' identity was confirmed by the X-ray analysis.

The synthesis of the yellow monomeric $\text{Pt}(\text{PiPCO})_2$ and $\text{Pt}(\text{MCO})_2$ was carried out from the dark-green polymeric complexes in pure DMSO/DMF = 1:1 mixture. After the compounds' dissolution the color of the mixture turned to yellow, and after several weeks in the dark in a vacuum desiccator, a small amount of nice yellow needles of both complexes were collected on a filter paper and dried. The analytical data for monomeric $\text{Pt}(\text{PiPCO})_2$ and $\text{Pt}(\text{MCO})_2$ correspond to their formulas satisfactory and the identity of these complexes was additionally confirmed by the X-ray analysis. Thus, for the yellow $\text{Pt}(\text{MCO})_2$, $\text{C}_{14}\text{H}_{16}\text{N}_6\text{O}_6\text{Pt}$, calculated (found), %: C – 30.06 (29.71), H – 2.88 (2.93), N – 15.02 (14.82). Similarly, for yellow $\text{Pt}(\text{PiPCO})_2$, $\text{C}_{16}\text{H}_{20}\text{N}_6\text{O}_4\text{Pt}$, calculated (found), %: C – 34.60 (34.72), H – 3.63 (3.80), N – 15.13 (15.04). This complex is slightly hygroscopic.

Safety note: Although we have not encountered any problems during many years of laboratory work and handling, special care should be taken during work with platinum compounds because of their toxicity typical of heavy metals and especially cytotoxicity. Many platinum sources are water-soluble compounds and that emphasizes the absolute necessity for wearing protective gloves at all times when working with them.

Spectroscopic studies

IR-spectroscopy—The IR-spectra of all compounds reported herein were recorded in KBr disks at room temperature using the Bruker R70 FT-IR-Raman spectrophotometer. The spectra were acquired with 64 repetitions at the resolution of 4 cm^{-1} .

Mass-spectrometry—The high-resolution electro-spray ionization mass spectra were recorded using a Bruker MicroTOF-III system for samples of 1D polymeric $[\text{PtL}_2]_n$ complexes (L = PiPCO, MCO) quickly after their mixing with CH_3CN at ambient conditions. The actual mass spectra and their analysis are presented in ESI 9–16.

UV-visible spectra—The electronic spectra of the compounds were recorded at room temperature using the HP 8354 diode array UV-visible spectrophotometer operating in the range of 200 – 1100 nm. The absorbance spectra from samples were measured in solutions and in fine suspensions squeezed between $1\times 4\text{ cm}$ quartz plates.

Emission spectra—The photoluminescence (further PL) of the solid metal complexes was investigated using the following experimental setup based on the Horiba model spectrofluorimeter using the CCD liquid nitrogen-cooled InGaAs diode array camera Symphony (Horiba) sensitive in the 600–1600 nm range and various integration times not exceeding 5 seconds. In the emission and excitation experiments both slits (emission and excitation) were kept constant at a width of 10 nm. The excitation was conducted with a Xe-lamp using a double grating ($2\times 1200\text{ gm/mm}$ @ 500 mm) monochromator. A long band pass 830 nm Schott RG 830 filter was placed in front of the spectrograph iHR-820 with grating 100 gm/mm @ 800 mm. The system was calibrated with special glass standard (Nd doped) with well-known peaks positions used for laser wavelength checking in the system before every set of measurements (ESI 21). A custom-built anodized aluminum vacuum pumped cryostat filled with liquid N₂ was used for the variable temperature experiments in the $-195/+70^\circ\text{C}$ range (ESI 17). Prior to each cryogenic experiment, the emission from the empty cryostat itself (cold finger insert, clear adhesive tape, cardboard, windows, etc.) and KBr pellet was carefully examined to avoid artifacts associated with possible emissive contamination (ESI 20–21). The J-Kem Scientific digital thermometer with a T-type thermocouple was used to monitor temperature. The 3D excitation-emission scans of the tablets (KBr matrix with 5% of metal complexes) were recorded with the simultaneous measurement of the light intensity (R) and correcting the emission by the lamp light intensity (T1). The absolute emission quantum yield of tablets with polymeric Pt-cyanoximates was measured using a large 150 mm (6 inch) integrating sphere, using a fiber optic bundle with high transmission in NIR. The tablet was placed at the bottom-loading circular shallow drawer in the sphere.

All glassware cuvettes and hardware parts that were in contact with either KBr pellets, or the powders of the studied metal complexes were washed using DMF warmed to ~65°C followed by DI water to avoid contamination and exclude the misinterpretation of the results of the photoluminescence measurements related to it. All synthesized complexes are well soluble in DMF.

NIR imaging—Images of pure solid powders of $[\text{PtL}_2]_n$ ($\text{L}=\text{MCO}$, PiPCO) and KBr pellets containing different concentrations of both complexes (0.1, 0.5, 1 and 5 weight %) were obtained with the help of the Ninox image camera and Nikkor lens 1:28, long pass 800 nm filter. Photographs were taken with illumination (excitation) with 735 nm bright LED from Thorlabs. The exposition time was set in all the experiments at 0.5 s and -15°C sensor temperature.

Electron Paramagnetic Resonance (EPR)—Spectra were recorded on the Bruker EMXplus X-band EPR spectrometer with a dual mode cavity and Oxford cryostat system at $+20$ and -193°C using the field sweep from 200 to 4000 G. The field was calibrated using the DFPG, while sensitivity of instrument was checked using a standard of solid solution of $\text{Al}_2(\text{SO}_4)_3$ containing 1% of Cr^{3+} centers as co-crystallized $\text{Cr}_2(\text{SO}_4)_3$. The spectra were recorded as a sum of five repetitions with time constant for each set at 160 ms. Some of the spectra are presented in ESI 22.

Structural Studies

EXAFS data—A sample of polymeric $[\text{Pt}(\text{PiPCO})_2]_n$ in ~250 mg quantity was investigated at Louisiana State University at J.B. Johnston Sr. Center for Advanced Microstructures and Devices (CAMD). Data fitting and calculations were carried out using the FEFF8.4 software package.

X-ray Crystallography—The crystal structures were determined for the yellow monomeric $\text{Pt}(\text{MCO})_2$ and $\text{Pt}(\text{PiPCO})_2$, and red $[\text{Pt}(\text{MCO})_2 \times (\text{DMSO})]_2$ dimer. Suitable single crystals of the first two complexes were grown by a slow ether vapors diffusion method in CH_3CN solutions, while red needles of the dimer were obtained overnight from a concentrated $\text{Pt}(\text{MCO})_2$ solution in DMSO. All attempts to grow suitable crystals of the dark-green polymeric $[\text{PtL}_2]_n$ complexes ($\text{L} = \text{PiPCO}^-$, MCO^-) were unsuccessful (ESI 23). The crystals of all yellow monomeric $\text{Pt}(\text{PiPCO})_2$ were very thin and small and even at 120 s per exposure value of $R(\text{int})$ was high: 0.24. Nevertheless, it was possible successfully to solve and refine structure of this complex. Crystals of the red $[\text{Pt}(\text{MCO})_2(\text{DMSO})]_2$ dimer were too small to study using Mo-radiation and were sent to synchrotron facility at the University of California-Berkeley to be studied as part of SCrALS (Service Crystallography at Advanced Light Source) program. Crystallographic data were collected at Beamline 11.3.1 at the Advanced Light Source (ALS), Lawrence Berkeley National Laboratory. All the crystals were placed on plastic MiTeGen holders attached to the copper-pin positioned on the goniometer head of the Bruker APEX-2 diffractometer, equipped with a SMART CCD area detector. The intensity data were collected at room and low temperatures in order to examine the possibility for temperature-dependent polymorphism that has been recently observed in other Pt-cyanoximates,⁵⁰ but was not observed in presented in this work

complexes. Only low temperature data is presented in this work. Data collection was done in ω scan mode using the Mo tube ($K\alpha$ radiation; $\lambda = 0.71073 \text{ \AA}$) with a highly oriented graphite monochromator. Intensities were integrated from 4 series of 364 exposures, each covering 0.5° in ω at 20 – 90 seconds of acquisition time, with the total data set being a sphere. The space group determination was done with the aid of XPREP software. The absorption correction was performed by a crystals face indexing procedure with a help of a videomicroscope followed by numerical input into the SADABS program that was included in the Bruker AXS software package. All structures were solved by direct methods and refined by least squares on weighted F^2 values for all reflections using the SHELXTL program. In all structures H-atoms were placed in calculated positions in accordance with the hybridization state of a hosting carbon atom and were refined isotropically. No apparent problems or complications were encountered during the structures' solutions and refinement. The crystal data for $\text{Pt}(\text{MCO})_2$, $\text{Pt}(\text{PiPCO})_2$, and $[\text{Pt}(\text{MCO})_2(\text{DMSO})]_2$ are summarized in Table 1, with selected bond lengths and valence angles presented in Table 2. The details of the crystal packing for these three complexes are presented in ESI 24–32. A representative drawing of the crystal structures and packing diagrams was done using the ORTEP and Mercury software packages. Reported structures have been deposited at CCDC at the following numbers: $\text{Pt}(\text{MCO})_2$ – 1451036, $\text{Pt}(\text{PiPCO})_2$ – 1451037, and $[\text{Pt}(\text{MCO})_2(\text{DMSO})]_2$ – 1451035, with PLATON checkCIF reports without A- and B-type alerts.

Electron Microscopy—Scanning Electron Microscopy (SEM) analysis for powders of dark-green $[\text{PtL}_2]_n$ complexes ($L = \text{PiPCO}$, MCO) was carried out on the JEOL JSM-6320F Field Emission apparatus operated at 5kV. Actual photographs are presented in ESI 34–38.

Solid State Electrical Conductivity—Measurements for the fine powders of dark-green $[\text{PtL}_2]_n$ complexes ($L = \text{PiPCO}$, MCO) were carried out using the Dimension 3100 SPM+C-AFM module with a platinum-iridium (PtIr) coated cantilever with a spring constant of 0.25 N/m (SCM-PIC by Veeco). The contact area was 19.5 nm^2 ; the scanning rate was set to 1Hz, while the sample bias voltage was 50 mV. The complexes' film thickness was 264 nm for $[\text{Pt}(\text{MCO})_2]_n$ and 216 nm for $[\text{Pt}(\text{PiPCO})_2]_n$. The obtained AFM images and specific details of these experiments can be found in ESI 40–42.

3. Results and Discussion

Synthesis

The protonated cyanoximes HPiPCO and HMCO are poorly water soluble and don't react in a reasonable time frame (days) with the K_2PtCl_4 that was used as Pt-source. Thus, at first aqueous solutions containing PiPCO^- and MCO^- anions, which are much better nucleophiles, have to be prepared (Scheme 2; ESI 2,43,45). An addition of stoichiometric amounts of K_2PtCl_4 leads to solid $[\text{PtL}_2]_n$ complexes ($L = \text{PiPCO}^-$ and MCO^- anions) as unusual dark-green precipitates within several hours. At first, monomeric PtL_2 complexes are formed, and quickly dimerize and polymerize into poor water soluble $[\text{PtL}_2]_n$ nano-size aggregates that form opaque colloid systems (ESI 47). A very fine dark-green solid eventually precipitated after the particles reached $\sim 1 \text{ }\mu\text{m}$ size (Scheme 2). It was not possible

to stop the reaction at the stage of the formation of the monomer or dimer and isolate these species in the direct reaction. The monomers of PtL_2 , however, can be obtained from a dry solid polymeric $[\text{PtL}_2]_n$ which forms upon reactions with an excess of donor solvent such as DMSO or DMF at elevated ($\sim 50^\circ\text{C}$) temperatures. Therefore, a yellow monomer and dark-green polymer represent true $\text{Pt}(\text{MCO})_2$ and $\text{Pt}(\text{PiPCO})_2$ polymorphs since they have the same chemical composition. The course of the reactions of the $[\text{PtL}_2]_n$ complexes ($\text{L} = \text{PiPCO}, \text{MCO}$) formation was monitored using the dynamic light-scattering techniques as shown Figure 1 and in the ESI 47, 48. A rather linear graph of the increase of the particles' size with time evidences an addition of the monomers to both ends of the growing polymer chain that is associated with the "Ostwald ripening".⁵¹ The red colored dimeric $[\text{Pt}(\text{MCO})_2 \times \text{DMSO}]_2$ was isolated upon careful dissolution of dark-green $[\text{Pt}(\text{MCO})_2]_n$ in a small amount of DMSO at room temperature. The dimeric complex technically is not the polymorph of $[\text{Pt}(\text{MCO})_2]$ because of the presence of the solvent molecule in the structure, albeit not coordinated to the metal center. Nevertheless, for a better description of the structures and properties of the synthesized complexes in the $\text{Pt}^{2+} - \text{MCO}^-$ system the red $[\text{Pt}(\text{MCO})_2 \times \text{DMSO}]_2$ complex is included as a logical intermediate species between the $\text{Pt}(\text{MCO})_2$ monomer and the $[\text{Pt}(\text{MCO})_2]_n$ polymer (Figure 2).

In order to examine the role of atmospheric oxygen in the synthesis of the self-assembled dark-green polymeric $[\text{PtL}_2]_n$ complexes ($\text{L} = \text{PiPCO}, \text{MCO}$), we performed an anaerobic preparation of $[\text{Pt}(\text{PiPCO})_2]_n$ in situ using a specialty quartz cuvette (ESI 49). Thus, in the separate compartments of this 1 cm path graded-seals cell we kept an aqueous solution of K^+PiPCO^- and solid $\text{K}_2[\text{PtCl}_4]$, which after several freeze-thaw cycles were combined under protective Ar atmosphere. The miniature magnetic stirbar allowed for a quick mixing of ingredients and the course of the reaction was monitored with the help of the UV-visible spectrophotometer (ESI 49). After ~ 10 min the reaction mixture slowly changed color to green, and within an hour, a very fine dark-green precipitate was observed at a similar time as for the reaction carried out at ambient conditions. The carefully filtered and dried powdery sample of $[\text{Pt}(\text{PiPCO})_2]_n$ obtained in anaerobic preparation also moderately conducts electricity similarly (yet to a lesser extent) to its aerobically-made analog. Therefore, for the formation of the mixed valence polymeric $[\text{Pt}(\text{PiPCO})_2]_n$, it is not necessary to have the presence of oxygen from the air. The cyanoxime can act as an oxidizer and partially oxidize $\text{Pt}(\text{II})$ to $\text{Pt}(\text{IV})$ since this class of organic molecules has an intermediate position between nitro- and amino-compounds (ESI 50). For example, the nitrosodicyanomethanide $\text{ONC}(\text{CN})_2^-$ anion was successfully oxidized to the nitrodicyanomethanide $\text{ON}_2\text{C}(\text{CN})_2^-$,⁵² and reduced to respective amine. Most likely, both O_2 from the air and the mild oxidizing power of the cyanoxime facilitate the formation of small amounts of $\text{Pt}(\text{IV})$ centers in aerobically made $[\text{Pt}(\text{PiPCO})_2]_n$. Another plausible explanation for the anaerobic formation of $\text{Pt}(\text{IV})$ species could be minor disproportionation reaction: $2 \text{Pt}(\text{II}) \rightarrow \text{Pt}(0) + \text{Pt}(\text{IV})$. Reduced platinum(0) species being in solutions do not contaminate the main precipitate of polymeric complexes as evident from their SEM studies (see discussion below in Solid State Studies section). Finally, Pt compounds are known to be catalytically active and may cause partial chemical transformation of cyanoximes to moieties able to generate $\text{Pt}(\text{IV})$ species. A variety of such reactions involving $\text{Pt}(\text{II})$ and oximes have been reported previously by Kukushkin⁹⁴ and Pombeiro.⁹⁵ In any case, the formation of

“poker chip” stacks has a thermodynamic drive to lose electrons from some number of Pt-atoms: when the hole is formed on the $6dz^2$ orbital then it creates favorable conditions for the electrons “hopping” from neighboring metal centers to share their filled $6dz^2$ orbitals, providing the delocalization of charge through larger groups of metal atoms in a “Pt-wire”. However, a detailed investigation of the role of oxidizers, disproportionation, as well as establishing of the reactions’ stoichiometry and the product(s) of redox transformations was out of the scope of this paper, but surely will be addressed in our future publications on that subject.

Solutions Studies

Mass-spectrometric measurements—Synthesized dark-green polymeric $[\text{PtL}_2]_n$ complexes display interesting behavior upon treatment with different solvents: they either keep the color, or change it to yellow (ESI 5, 6), which evidences the formation of monomeric PtL_2 species ($\text{L} = \text{PiPCO}$, MCO). The quick dissolution of $[\text{PtL}_2]_n$ in CH_3CN resulted in the formation of a solution that quickly changed color to a light salad-green, which was subjected to mass-spectrometric measurements with the data presented in ESI 9–16. It is apparent that the oligomers – up to tetramers – can be reliably detected, which directly supports the polymeric structure of the starting dark-green solids. The calculated and found masses of the observed fragments fit very well. Such extended aggregation, and certainly the formation of coordination polymers can be explained through the realization of the mixed valence $\text{Pt(II)}\text{—Pt(IV)}$ species in which electrons/holes are moving along the “metal wire” vector.

Aggregation/disaggregation studies: In dry CH_2Cl_2 , DMF, $\text{N,N}'$ -dimethylacetamide (DMAA), CH_3CN and some other solvents, both complexes dissolve with the formation of clear green solutions (ESI 5,6), which within minutes become opalescent due to the spontaneous aggregation of these complexes in these solvents to form extended “poker chip” structures. The aggregation leads to a clearly observable Tyndall effect both at ambient day light and in the dark (ESI 47). The investigation of the aggregation of the complexes during synthesis was carried out using the dynamic light scattering (DLS) method and revealed the formation of particles of ~ 900 nm in size during ~ 9.5 hours from the starting K(MCO) and K(PiPCO) and $\text{K}_2[\text{PtCl}_4]$ (Figure 1; Scheme 1). The rate of the linear particles growth of polymeric $[\text{Pt(MCO)}_2]_n$ and $[\text{Pt(PiPCO)}_2]_n$ was found to be in the range of $30.7 - 40.4$ nm/min for both compounds in aqueous solutions. Since the X-ray structures of the dimeric $[\text{Pt(MCO)}_2]_2$ complex (in its DMSO solvate), and the EXAFS studies of the $[\text{Pt(PiPCO)}_2]_n$ complex generated quite a reasonable Pt—Pt separation within $\sim 3.13 - 3.15$ Å, it was possible to assess how many molecules self-assemble into the stack per unit of time. Thus, the growth of the 1D column of $[\text{PtL}_2]_n$ ($\text{L} = \text{MCO}$, PiPCO) can be estimated between 97 and 130 molecules per minute.

However, the synthesized polymeric $[\text{Pt(MCO)}_2]_n$ and $[\text{Pt(PiPCO)}_2]_n$ in strong donor solvents such as DMSO, Py, HMPA and picolines become yellow (ESI 48). Similarly, the green aggregated solutions of the studied Pt-cyanoximates quickly become yellow upon the addition of a drop or two of these solvents (ESI 51, 52). Clearly, strong donor solvents disrupt the 1D structure in stacks held by metallophilic interactions and lead to the formation

of monomeric complexes. Thus, the “blue” CT band above 700 nm quickly disappears from the UV-visible spectra of complexes upon the addition of DMSO or Py (ESI 51, 52). At the same time the addition of sterically hindered strong bases such as 2,6-dimethylpyridine and 2,4,6-trimethylpyridine to solutions of both $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes in DMF, as expected, does not lead to the color change and their disaggregation. It is important to mention that yellow solutions of monomeric $\text{Pt}(\text{MCO})_2$ and $\text{Pt}(\text{PiPCO})_2$ upon drying generate the dark-green polymeric complexes again, which implies the reversibility of the aggregation disaggregation processes as depicted in Scheme 3. Also, in some cases it was possible to observe on the walls of vials and beakers the minor presence of red microcrystals of a dimeric species.

Dark-green $[\text{PtL}_2]_n$ ($\text{L} = \text{MCO}$, PiPCO) can be easily solubilized in aqueous solutions via micelles formation with the help of $\text{C}_9\text{H}_{19}\text{COONa}$ (C10) and $\text{C}_{10}\text{H}_{21}\text{SO}_3\text{Na}$ (SDS) (ESI, 53, 54). The results of DLS measurements indicated surprising formation of a single-size micelles particles in the above solutions (ESI 55). Thus, the average $[\text{Pt}(\text{MCO})_2]_n$ micelles size was determined to be 323 nm, and with a Pt—Pt bond = 3.15 Å (according to EXAFS data) there are ~ 920 units in the stack. For $[\text{Pt}(\text{PiPCO})_2]_n$ micelles the average particles size was found to be 214 nm, which transforms to ~ 680 units in the stack. Micelles, however, contain more than one stack cross-aligned in such way that a spherical particle is formed. This arrangement leads to rather significant Pt content in the micelle which was confirmed by analyzing total metal amount using the ICP method.

Electrochemical measurements: Redox properties of yellow solutions of the monomeric platinum complexes $\text{Pt}(\text{MCO})_2$ and $\text{Pt}(\text{PiPCO})_2$ along with the redox properties of the corresponding ligands were investigated using CV and DPV techniques and depicted in ESI 56–58. In general, all redox processes both in ligands and platinum complexes were found to be irreversible. The reduction potentials in all systems are close to each other and thus were assigned as the ligand-centered processes. The irreversible oxidation process in platinum complexes was observed at significantly lower potential as compared to the oxidation process observed in the corresponding ligands.

UV-visible spectra

Ligands: Both HMCO and HPiPCO cyanoximes are colorless compounds but gain a yellow color upon deprotonation. The UV-visible spectra of cyanoxime anions MCO^- and PiPCO^- (as Na^+ , K^+ or alkylammonium salts) contain three bands: two for $\pi - \pi^*$ transitions in the area of 200 – 300 nm and one low intensity $n \rightarrow \pi^*$ transition ($\epsilon \sim 80\text{--}100$) which, depending on a solvent, is typically observed around 420 nm. The latter band is responsible for the yellow color of cyanoxime anions.^{53–56} That band also demonstrates a pronounced solvatochromism: of 86 nm for the MCO^- anion (4857 cm^{-1} , 56.5 kJ/mol, or 601 meV), and 87 nm (4996 cm^{-1} , 59.8 kJ/mol, or 619 meV) for the PiPCO^- between UV-visible spectra in water and DMSO respectively (ESI 44–46).

Metal complexes: We found that the complexes $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ slowly dissolve in organic solvents and can form solutions of two different colors: green and yellow depending on the solvent. The green color is a combination of yellow (from $n \rightarrow \pi^*$

transition in the anion) and blue color originated as the result of a charge-transfer band between the Pt centers and cyanoximes in a stack.^{47, 48} Polar donor solvents tend to quickly discolor green solutions into yellow which indicates disaggregation of coordination polymers into yellow monomeric units Pt(MCO)₂ and Pt(PiPCO)₂ (ESI 48, 52, 53). Crystal structures of those have been determined (Figure 3 and discussion below).

There is a difference in the peaks position between [Pt(MCO)₂]_n and [Pt(PiPCO)₂]_n in solutions with even more of a red shift of λ_{max} to 810 and 841 nm respectively as opposed to solid samples (see discussion below). The origin of a further bathochromic shift of the blue bands is not clearly understood at the moment, but it could well be due to free “annealing” and reaching the most favorable equilibrated structures in the aggregated colloid solutions of 1D coordination polymers as opposed to solid samples. Moreover, we also observed rather significant solvent sensitive changes in the λ_{max} of the CT band in UV-visible spectra of the studied complexes in a series of organic solvents (ESI 59,60). For [Pt(MCO)₂]_n the largest variance in λ_{max} was observed for ethanol (765 nm) and DEAA (809 nm), giving a 45 nm difference that corresponds to an 8.69 kJ/mol energy change (ESI 59). The polymeric dark-green [Pt(PiPCO)₂]_n had a λ_{max} in formamide at 775 nm, while in ethyl acetate it is at 843 nm, which amounts to 74 nm, or to a 13.66 kJ/mol energy change (ESI 60).

Thus, the UV-visible spectroscopic studies of the solutions of dark-green 1D polymeric [Pt(MCO)₂]_n and [Pt(PiPCO)₂]_n in a large group of organic solvents allowed us to establish certain trends between Kosover’s specific solvation energy,⁵⁷ solvent donor number and λ_{max} of the Pt—Pt CT band in spectra (ESI 61).

Other known dark-colored Pt-based coordination polymers are the Magnus’ Green Salt (MGS), green Becton’s Salt and purple Milton’s Salt briefly described below. Those, however, have insufficient solubility in common solvents and were poorly studied in general.

Chemical oxidation studies in solutions: Known Pt-based 1D solids, such as KCP-type M₂[Pt(CN)₄] (M = Na, K, Rb, Cs), were successfully converted into partially oxidized (POCP) mixed valence compounds in which up to 30% of Pt-centers could become Pt(IV). These copper-like shiny crystalline complexes represent classic 1D solids that exhibit a strong optical anisotropy and conduct electricity at the level of metals. The oxidation of Pt(II) can be achieved either by electrochemical methods, or by using chemical oxidizers such as Ag⁺, bromine or H₂O₂, the standard half-reaction potentials^{58, 59} of which are shown below.

The data of the solid state electrical conductivity measurements of our polymeric $[\text{PtL}_2]_n$ ($\text{L} = \text{MCO}^-$, PiPCO^- anions) complexes evidenced already evidenced the formation of a mixed valence species (see ESI 41,42, and text below). Nevertheless, we were interested in the possibility of the further chemical oxidation of the metal center of our Pt-cyanoximates in solutions to learn whether or not these compounds followed trends similar to classic POCP complexes.

Pt(MCO)₂: In order to prove the formation of mixed valence aggregated Pt-cyanoximates, we carried out the partial oxidation of the Pt(II) in solutions using oxidizers such as Ag^+ and elemental bromine. For the oxidation of Pt(II) centers in a solid state, we used a 30% solution of H_2O_2 . Thus, in a separate experiment, the stepwise addition of 1 and 2 equivalents of the AgPF_6 solution to a green aggregated solution of $[\text{Pt}(\text{MCO})_2]_n$ in DMF resulted in an increase of the intensity of the “blue” CT- band that is associated with the “poker chip” stacking of complexes and the formation of a mixed valence species (ESI 62-A). Similarly, an addition of 0.2 equivalents of Br_2 solution in dry DMF to a green aggregated solution of $[\text{Pt}(\text{PiPCO})_2]_n$ also produced a significant bathochromic shift of the “blue” band in the UV-visible spectra (ESI 62-B). Therefore, both treatments evidenced the further oxidation of the Pt(II) centers to Pt(IV), in aggregated stacks and a more extensive formation of mixed valence species. Despite the good qualitative trend, we were not able, unfortunately, to isolate reproducibly and characterize products of performed chemical oxidation of green $[\text{PtL}_2]_n$ ($\text{L} = \text{MCO}^-$, PiPCO^- anions) in solutions. A similar situation is known for the KCP solids where generated mixed valence POCP complexes frequently have a variable, non-consistent composition that depends on “sample’s history” and the methods of their preparation.⁸⁷

Pt(PiPCO)₂: A sample of $[\text{Pt}(\text{PiPCO})_2]_n$ also was oxidized with Br_2 in dimethyl formamide (DMF). Thus, 47.3 mg (0.076 mmol) of dark-green $[\text{Pt}(\text{PiPCO})_2]_n$ was mixed with 4.0 mL of DMF and placed under a N_2 atmosphere. Then 0.590 mL (0.023 mmol) of a 0.039 M Br_2 solution (in DMF) was added to the $[\text{Pt}(\text{PiPCO})_2]_n$ mixture and closed overnight under an argon atmosphere for 24 hours. Upon opening the reaction vessel, it was heated to 35°C for one hour with the inert gas purging to remove an excess of Br_2 . A dark green solid was observed under a yellow solution. After drying under high vacuum, 25.6 mg of an olive-drab solid was recovered. The material had a slight metallic, copper-like sheen.

The further oxidation of dark-green $[\text{Pt}(\text{PiPCO})_2]_n$ also was carried out by titration with AgPF_6 in DMF. Thus, 1.5 mL aliquots of $7.75 \cdot 10^{-4}$ M of the Pt-complex solution (in DMF) were mixed with 23 μL aliquots of $2.65 \cdot 10^{-2}$ M AgPF_6 solutions (in DMF as well) and monitored by UV-Visible spectroscopy. An increase in the intensity of the Pt—Pt CT band at ~800 nm was observed similarly to that for the $[\text{Pt}(\text{MCO})_2]_n$ complex above.

Chemical oxidation in solid state: Bromine vapors were used to further oxidize and, therefore, introduce the Pt(IV) centers solid $[\text{Pt}(\text{MCO})_2]_n$, which was embedded into the KBr pellet (5% by weight, for the photoluminescence experiments; see the NIR spectroscopy discussion below) to the mixed valence species. The photographs of the initial dark-green pellet and one after exposure to Br_2 (copper-like shine) are presented in ESI 63. Hydrogen peroxide, 30% by weight, was also successfully used to further generate mixed valence Pt-cyanoximates complexes that were incorporated into the KBr pellets at 5% concentrations (see NIR experiments section). One drop of 10 μL of H_2O_2 applied on the surface of the pellet provided a significant NIR emission intensity increase. Therefore, the low energy photoluminescence of $[\text{PtL}_2]_n$ is directly associated with the formation of a mixed valence system.

Finally, the Pt-cyanoximates reported in this work resemble the previously studied Pt-based 1D solids^{5, 21} in the sense of their ability to form mixed valence complexes. However, contrary to classic compounds such as MGS, Krogman's salt and its derivatives, our $[\text{PtL}_2]_n$ ($\text{L} = \text{MCO}^-$, PiPCO^- anions) complexes: 1) exhibit a significant photoluminescence beyond 1000 nm, and 2) are soluble in organic solvents.

Solid State Studies—It is well known that the vast majority of Werner-type Pt(II) complexes with a variety of inorganic and organic ligands are colorless or have pale-yellow/off-white colors. There are only three intensely colored complexes: the Magnus' Green Salt (MGS)^{60, 61} of “ $\text{Pt}(\text{NH}_3)_2\text{Cl}_2$ ” composition, purple Millon's Salt $[\text{Cu}(\text{NH}_3)_4] [\text{PtCl}_4]$, and green Becton's Salt $[\text{Pt}(\text{NH}_3)_4] [\text{CuCl}_4]$.⁶² All have 1D polymeric stacked “poker-chips” type structures with alternating cationic $[\text{Pt}(\text{NH}_3)_4]^{2+}$, $[\text{Cu}(\text{NH}_3)_4]^{2+}$ and anionic $[\text{PtCl}_4]^{2-}$, $[\text{CuCl}_4]^{2-}$ units respectively. Accordingly, these are considered as Pt—Pt and alternating Cu—Pt wires with intermetallic distances less than 3.4 Å. A very unusual and intense color of the obtained presented here Pt(II) cyanoximates indicates that they have similar structures and properties of anisotropic 1D solids.²¹

Structural studies: The crystal structures of both ligands – HMCO and HPiPCO – have been determined in the past.^{36, 63} These compounds were found to have two polymorphs: the HMCO crystallizes in two different orthorhombic polymorphs in a $\text{P}2_12_12_1$ space group, while HPiPCO can crystallize in either monoclinic⁶³ $\text{P}2_1/\text{c}$, or orthorhombic³⁶ $\text{P}2_12_12_1$ space groups. The crystal structures of three Pt-cyanoximates were determined using the X-ray crystallography and the structure of one 1D-polymeric complex was elucidated by the EXAFS method. It should be mentioned that the structure of $\text{Pt}(\text{PiPCO})_2$ was determined earlier at 293 K, but we re-grew suitable single crystals and re-determined the structure more accurately at low temperature (100 K) because of the recently observed polymorphism in other Pt-cyanoximates.⁵⁰

X-ray structures of yellow monomeric $\text{Pt}(\text{PiPCO})_2$ and $\text{Pt}(\text{MCO})_2$: The formation of yellow monomeric cis-complexes of the PtL_2 composition ($\text{L} = \text{PiPCO}$, MCO) as products of the breakdown of dark-green polymeric $[\text{PtL}_2]_n$ has been confirmed (Figure 3). Cyanoxime anions in both complexes adopt *cis-anti* configuration^{36, 64} and are in the *nitroso* form as evident from much shorter N-O as C-N bonds in the C-N-O fragment (Table 2). The Pt(II) centers have a planar $[\text{PtN}_2\text{O}_2]$ environment with two shorter by ~ 0.06 Å cis-Pt-N

bonds as compared to two cis-Pt-O bonds. Both anionic PiPCO^- and MCO^- cyanoximes form five-membered che-late rings with metal centers. The metal-cyanoxime core in both complexes is virtually planar, but have dihedral angles $22\text{--}28^\circ$ between the PtN_2O_2 five atoms plane and piperidine and morpho-line cycles (both in the chair form) attached to the amide groups (ESI 24, 26). The details of the crystal packing for both yellow monomeric $\text{Pt}(\text{PiPCO})_2$, and $\text{Pt}(\text{MCO})_2$ polymorphs are presented in ESI 25, 27.

X-ray structure of red $[\text{Pt}(\text{MCO})_2 \times \text{DMSO}]_2$ dimer: The structure of a red dimeric complex $[\text{Pt}(\text{MCO})_2 \times \text{DMSO}]_2$ was found to consist of the dimeric head-to-tail $[\text{Pt}(\text{MCO})_2]_2 \times \text{DMSO}$ moiety associated with the Pt(2) atom (Figure 4), as well as slipped π -stacked columns of the $[\text{Pt}(\text{MCO})_2] \times \text{DMSO}$ complex with head-to-head oriented units associated with the Pt(1) atom (ESI 28,31,32). Two cyanoxime anions in both Pt(1) and Pt(2) centers form cis-complexes with planar $[\text{PtN}_2\text{O}_2]$ geometry with chelating ligands forming five-membered metallocycles (Figure 4; ESI 29). The closest metal-metal distance in the dimeric part of the molecule was found to be $3.1335(5) \text{ \AA}$ (Table 2).

The geometry of the cyanoxime anion in the dimer is very similar to that of the monomeric complex. The crystal packing of the dimeric $[\text{Pt}(\text{MCO})_2]_2 \times \text{DMSO}$ moiety is described as a column of dimers extended along the *a*-direction (ESI 30). Selected bonds and angles for the non-dimeric part of the structure at the Pt(1) center are present in ESI 33. The crystal packing for this part of the complex represents slipped zig-zag stacks that also form a columnar structure, but with long distances between the metal centers (ESI 31,32). Molecules of the DMSO are trapped in the structure and occupy channels along the *a*-direction (ESI 28,31). That feature explains the instability of the dried red complex when it loses the solvent and changes to the yellow monomeric $\text{Pt}(\text{MCO})_2$. The solvent, associated with the dimeric part in the structure, formed interesting short electrostatic contacts between one of DMSO methyl-groups and the oxygen atoms of the nitro-so-groups of two cyanoximes: $\text{O8} \cdots \text{H2C1}$ and $\text{O7} \cdots \text{H2C1}$ equal to 2.520 and $2.547 \text{ \AA}$ respectively.

EXAFS structure for 1D $[\text{Pt}(\text{PiPCO})_2]_n$: In order to elucidate the structure of these new types of compounds we used the EXAFS method at the Pt-K edge which allowed for the determination of the length of chemical bonds around the heavy atom. The results of the EXAFS studies are shown in ESI 38,39 and demonstrate a very good fit (within 1 – 7 % values) between calculated and experimentally determined parameters of bond length and intera-tomic distances. The model used for the fit had a bidentate cyanoxime anion binding Pt, with the formation of a five-membered chelate ring in a fashion similar to that found in $\text{Pd}(\text{II})^{36}$ and $\text{Ni}(\text{II})^{65}$ cyanoximates. Determined by the EXAFS method and data fitting Pt-N and Pt-O bonds are slightly shorter than those experimentally observed in yellow monomeric $\text{Pt}(\text{PiPCO})_2$ and $\text{Pt}(\text{MCO})_2$ (Table 2), which may suggest a rather tighter binding of the equatorial cyanoxime anion to the metal center in the dark-green 1D polymer. Established by the EXAFS intermetallic Pt—Pt separations is $3.15 \pm 0.1 \text{ \AA}$ (ESI 39) which is in a very good agreement with the commonly observed distances in established 1D Pt-based mixed valence electric conductors,^{10,13} as well as for the dimeric red $[\text{Pt}(\text{MCO})_2 \times \text{DMSO}]_2$ complex discussed above. The determination of the Pt—Pt distance was the prime goal of

using the EXAFS method since dark-green Pt-cyanoximates we could not crystallize for suitable for single crystal analysis specimen (ESI 23).

Known literature examples of complexes of platinum-based complexes with a variety of α -dioximes are presented in Table 4 which contains both polymeric, monomeric complexes and mixed valence systems as well. There is almost exclusively $[\text{PtN}_4]$ coordination environment around the central atom in displayed there complexes, whereas in our case we have a mixed donor atoms $[\text{N}_2\text{O}_2]$ surrounding of the central atom.

Scanning Electron Microscopy: Samples of dark-green fine powders of $[\text{Pt}(\text{PiPCO})_2]_n$ and $[\text{Pt}(\text{MCO})_2]_n$ polymers were studied at different magnification powers and the results are summarized in ESI 34–37. The compounds represent fibrous, pure and homogeneous single phase materials without any observable phases of foreign impurities.

Electrical Conductivity: The solid state conductivity measurements of the dark-green $[\text{Pt}(\text{PiPCO})_2]_n$ and $[\text{Pt}(\text{MCO})_2]_n$ polymers were determined to be at the upper level of semiconductors with values of 22.2 and 33.3 S/cm respectively (ESI 40–42). This is direct evidence for the formation of a mixed valence species with free charge carriers moving along the Pt-Pt vector in these 1D solids.

Thermal stability: Synthesized dark-green $[\text{Pt}(\text{PiPCO})_2]_n$ and $[\text{Pt}(\text{MCO})_2]_n$ polymers are thermally stable up to 172 and 200°C respectively (ESI 7,8). The final products of their decomposition are PtO (at 1180°C) for $[\text{Pt}(\text{PiPCO})_2]_n$ – 40.88% calculated (43.60% found), and Pt metal (at 980°C) for $[\text{Pt}(\text{MCO})_2]_n$ – 35.12 calculated (35.12% found).

Spectroscopic data

EPR spectra: Recorded at room and 80 K spectra from fine dark-green powders of $[\text{PtL}_2]_n$ complexes ($\text{L} = \text{PiPCO}^-$, MCO^-) demonstrated an absence of the signals of Pt^{3+} centers which have EPR observable d^7 electronic configuration³¹ (ESI 22). Therefore, the mixed valence species in the studied complexes belong to Pt(II)—Pt(IV) pairs with d^8 – d^6 electronic configurations. The same situation was well documented for classic mixed valence MX and KCP/POCP 1D solids (ESI 1) in the past.^{5, 10, 13, 66}

UV-visible spectra: Solid samples of 1D polymeric Pt-cyanoximates appeared as fine dark green powders (Figure 2; ESI 64). Thus, fine suspensions of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ contain intense bands at ca 746 and 795 nm respectively (Figure 5). The presence of these “blue bands” was conveniently used during the work and handling of these complexes as an indication of the formation or the presence of the stacks of coordination polymers. The effect of aggregation in solution, or the formation of 1D-polymer in solid state leads to a significant red shift of absorbance bands (and emission respectively) as was proposed by Miskowski⁸⁹ and more concisely presented by Li et al.⁹⁰ In our case in visible range a band at ~430 nm in yellow monomeric PtL_2 complexes shifts to ~550 in a dimer, and then to ~750 nm in 1D polymer. The latter is assigned to be $d\sigma^* \rightarrow \sigma(\pi^*)$ MMLCT.⁹⁰ Finally, based on the studies carried out,⁴⁸ the wavelength of 770 nm was selected as an excitation energy for recording the emission spectra of the solid 1D polymeric $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ which are presented below.

NIR spectroscopy: The most interesting property of those two dark-green $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes was a strong emission in the NIR region beyond 1000 nm. The importance of this part of the electromagnetic spectrum for biomedical research is outlined in ESI 65–68 and is associated with the fact of tissue transparency between 1030 and 1100 nm. A combination of imaging potential with the established cytotoxicity of several Pt-cyanoximates^{36–38} opens the possibility for their theranostic applications. Recently we reported the chemistry and photoluminescence properties of the first mixed valence Pt-cyanoximate.⁴⁸ Two other complexes presented in this work widen the series of newly discovered NIR emitters that could be useful for biomedical research.

The presence of absorption bands beyond 700 nm associated with aggregation via metallophilic interactions observable in the UV-visible spectra of dark-green $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ prompted us to investigate the photoluminescence of these compounds in the NIR range. To avoid the observed interconversion between the monomeric $\leftrightarrow$ dimeric $\leftrightarrow$ polymeric species in the solution (Scheme 3), we investigated the emission in the solid state. The solids were incorporated in the KBr matrix at 5% amounts to minimize the uncertainties associated with the powder density and particle size and enhance the reproducibility of the results. Such a technique is commonly used in FTIR measurements,⁵⁷ but was originally also proposed for the absorption spectra in the past.⁴⁸ Also, we prepared KBr pellets with 1%, 0.5% 0.1% by weight amounts of dark-green $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes to investigate the effect of the concentration on the emission properties of polymers. Finally, we studied pure powdery samples of Pt-cyanoximate polymers to compare their emission with solid solutions in KBr pellets. The details of the pellets preparation as well as used of pure dark-green $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ compounds and experimental setup can be found in ESI 18,19. The pellets had a long shelf-life stability (more than two years) if stored in a vacuum desiccator at room temperature. Crystalline IR-spectroscopy grade KBr was used to check any possible background emission stemming from the salt, or the instrument (ESI 20–22). We recently investigated the NIR emissive properties, or lack thereof, for control compounds, such as known model 1D Pt compounds with a known Pt—Pt distance – Magnus' Green Salt (MGS) and Krogman's Salt (partially oxidized tetracyano-platinate, POCP).⁴⁸

All pellets were excited at 770 nm with emission measured in the range of 800–1600 nm. The NIR photoluminescence spectra of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes (5% in KBr) are shown in Figure 5-B. The shape of the emission profile indicates a multicomponent emission for both complexes, and a satisfactory deconvolution of spectroscopic envelopes required only two Gaussian-type lines (ESI 71,72). Two components, however, have significantly different parameters: lines intensity, peaks area and energy. This observation is somewhat similar to our recent finding for the NIR photoemission of another dark-green 1D polymer $[\text{Pt}(\text{DECO})_2]_n$ (DECO[−] is anion of 2-cyano-2-oximino-N,N'-dimethylacetamid) which has almost symmetric emission profile at ~1060 nm,⁴⁸ but nevertheless fit for two Gaussian-type lines, but of a greatly different areas of 95:5. No vibronic progression is observable for the photoluminescence of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes. The emission-excitation scans for the KBr pellet with a 5% content of both complexes are shown in Figures 6 and ESI 86 and evidenced that the position and intensity of the emission signal

remains around ~1050 nm and is practically independent on the excitation wavelength. This is typical of systems with delocalized charge carriers such as mixed valence species, as well as quantum dots and quantum wells. In systems without charge delocalization excitation spectra have well-separated emission maximums, for example for Nd-doped glass used for the instrument calibration (ESI 21).

As expected, there is a pronounced concentration dependence of photoluminescence of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ polymers in KBr pellets: 1) the intensity of the emission undergoes the bathochromic shift upon the complex's concentration increase (Figure 7-A), 2) the absolute quantum yield also increased significantly upon complexes' dilution in the KBr matrix. The latter values are tabulated and plotted in ESI 77,78. The data can be reasonably well fit using the mono-exponential decay function ESI 79. The intensities of the photoluminescence and values of quantum yield versus concentration are in line with self-absorption of photons in more concentrated samples,^{67, 68} while the red-shift of energy of the emission at higher concentrations is indicative of coupled oscillators where the total energy of the system decreases with the increase of their number.^{69, 70} The PtL_2 ($\text{L} = \text{MCO}^-$, PiPCO^- anions) units connected via metallophilic interactions are forming a long-range "metal wire" that provides such coupling. Moreover, the presence of mixed valency also contributed to the coupling since it provides more tight binding of PtL_2 subunits in a stack via an extended charge delocalization component with shared between them electrons.

The life time's measurements were carried out for the 5% $[\text{PtL}_2]_n$ in the KBr pellets and turned out to be in the nanoseconds range: $T_1 = 3.37 \cdot 10^{-9}$ and $T_2 = 1.26 \cdot 10^{-8}$ sec (average time = $4.79 \cdot 10^{-9}$ sec) for $[\text{Pt}(\text{PiPCO})_2]_n$, and $T_1 = 2.73 \cdot 10^{-9}$ and $T_2 = 6.21 \cdot 10^{-9}$ sec (average time = $3.45 \cdot 10^{-9}$ sec) for $[\text{Pt}(\text{MCO})_2]_n$ (ESI 83, 84). The values suggest the fluorescence nature of the observed photoemission for both polymers. We predict, however, that the life times will increase when such measurements will be carried out for the solutions of these complexes and aggregates in micelles, which we plan to conduct in the nearest future.

Control complexes such as well-known MGS and KCP, POCP embedded into salt pellets (5% in KBr) do not exhibit any NIR luminescence irrespective of the excitation wavelengths. Also, it should be noted that the yellow monomeric PtL_2 ($\text{L} = \text{MCO}$, PiPCO) complexes did not show any photoluminescence at all regardless of the wavelength of excitation. Therefore, the observed emission in the NIR region beyond 1000 nm is a collective property of self-assembled mixed valence 1D polymeric Pt-cyanoximates.

Variable temperature studies of photoemission were conducted for both synthesized polymeric Pt-cyanoximate complexes and are shown in Figures 8-A and 9-A. Deconvolution of the photoemission signals is shown in ESI 71, 72, while processed data of the lines' widths, intensities and areas at different temperatures are summarized in ESI 73–76. There is rather pronounced batho-chromic shift in the energy of the photoemission for both components with the temperature decrease. Thus, for the $[\text{Pt}(\text{MCO})_2]_n$ complex the energy that corresponds to the red-shift of 41 nm is 4.49 kJ/mol, or 46 meV (375 cm^{-1}) (Figure 8-A), while for the $[\text{Pt}(\text{PiPCO})_2]_n$ complex these values at the bathochromic shift of 48 nm are 3.97 kJ/mol, or 41 meV (332 cm^{-1}) (Figure 9-A). Both these values are typical for quantum

dots and wells, which are semiconductors with free-moving charge carriers, and are also consistent with the delocalization of electrons along the 1D chain in compounds with metallophilic interactions.^{20, 24, 71}

The same trend again was observed for the peaks intensity: the higher the temperature – the more intense the photoemission lines are (ESI 73-A, 75-A). We reported similar behavior for the first representative of this new class of the NIR emitters – another mixed valence dark-green 1D polymer [Pt(DECO)₂]_n (DECO = 2-cyano-2-oximino-N,N'-dimethylacet-amid).⁴⁸ We explain the simultaneous increase in the emission intensity with temperature by analogy with the documented behavior of quantum wells (single quantum wells GaAsSb/AlGaAs) and quantum dots (multi-core and multi-shell CdSe/CdS/ZnS/ZnSe) with delocalized carriers typical for semiconductors. Both demonstrate similar temperature-induced changes in the emission energies and intensity profiles. Subsequently, excitons with a temperature increase gain sufficient thermal energy to overcome small potential barriers in the local potential minimum, become mobile, and transferred to higher energy states of the band until reaching the edge of the conduction band.^{72, 73} Therefore, the emission energy undergoes a blue shift with the temperature increase. We propose that at reached in our experiments low temperatures excitons mostly localize in a mixed valence aggregate which is small in size, or perhaps even in the mixed valence dimer. Also, the fact of the thermal lattice contraction caused by cooling results in shorter Pt—Pt distance in stacks which leads to the red shift.⁷⁴ Increase of the temperature creates delocalized excitons that can now reach higher energy states and, due to electron hopping, spread on a larger distance, increasing the probability of emission from a larger number of mixed valence centers along the Pt—Pt wire.

The metal-metal distance is increased with temperature as well. In general, increasing with temperature hopping of pairs of electrons between sites leads to a greater degree of delocalization in both ground and excited states.⁷⁵ At last, these results also can be explained in terms of the increase of the distance traveled by electrons along the 1D Pt—Pt chain (e-delocalization) with the rising temperature, which requires higher energy. Lower temperatures tend to localize such motion to a smaller distance. Similar blue-shift behavior was reported for a series of In-As quantum dots⁷⁶ and wells⁷² and Cd-halcogenide^{77, 78} where even values of the PL temperature shifts were reported to be in the same range of 30–60 meV.

It is interesting to note in context of our observation of emission beyond 900 nm in [PtL₂]_n that the oxidation of Pt(II) to Pt(III) in several As-Pt and phosphite-Pt dimers also leads to a significant red shift the emission.⁹¹

The plots of the emission intensity of the signal from the temperature showed considerable linear parts for both studied 1D polymeric Pt-cyanoximates (Figures 8-B, 9-B; Table 5). These are ~98° in length for [Pt(MCO)₂]_n (between –108° and +10°C), and ~140° in length for [Pt(PiPCO)₂]_n (between –80 and +60°C) (ESI 69, 70). The slope for the [Pt(PiPCO)₂]_n is about twice as steep as that for the linear part of [Pt(MCO)₂]_n, but both are significantly smaller than the linear part of the recently published [Pt(DECO)₂]_n.⁴⁸ Such long linear parts of the PL intensity of this new class of 1D polymeric Pt-cyanoximates can be used for nonelectrical, optical thermometers working in the NIR region.

Practicality of mixed valence “Pt-wires”

Micelles formation: Also, we performed solubilization of solid polymeric $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes into aqueous solutions with the help of an ultrasound and detergents such as sodium decanoate and sodium dodecylsulfate. Both complexes form dark-green micelles solutions (ESI 53, 54), which after filtration were examined by the DLS method. It was a surprise to see that $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ form homogeneous, single particle size colloidal solutions, which turned out to be stable within a month. Thus, the first complex forms micelles with an average size of 322.5 nm and, using the Pt—Pt bond = 3.15 Å in the polymer (determined by the EXAFS method), there are ~920 units in the stack. A similar evaluation for averaged single-size particles of 214.1 nm for $[\text{Pt}(\text{PiPCO})_2]_n$ micelles resulted in ~680 units in the stack. Data of elevated total Pt content determination in micelles of both complexes evidenced that the latter contain clearly more than one stack. Micelles of both polymeric $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes display photoluminescence at almost the same wavelength beyond 1000 nm as solid samples. These complexes have shown pronounced cytotoxicity,^{36–38} which makes them interesting for application as theranostic agents. Thus, recently we found that the $[\text{Pt}(\text{MCO})_2]_n$ complex being mixed with the anticancer drug Ganetespib and formulated in micelles with the Fe(III)-containing polymer of nanoparticles size significantly enhances the cytotoxicity of the drug.⁷⁹

NIR imaging: With the use of a special Ninox camera sensitive in the NIR region we were able to record actual images of both pure powders of polymeric $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ complexes as well as their 5 by weight % solid solutions in KBr (Figure 10). The KBr pellet with 5% of Krogman’s salt (partially oxidized KCP) was used as a non-luminescent control (Figure 10 C, D). Both type of samples – powders and pellets – were photographed at ambient conditions using white light (Figure 10 A, C). Images in the NIR region were recorded using 735 nm excitation with a bright LED source with 0.5 s exposure time and long-path 800 nm filter that blocks all light with wavelengths less than 800 nm. Good quality images of studied samples emitting in the NIR region beyond 1000 nm (shown in Figure 10 B,D) were recorded for the coordination polymers for the first time ever. Photographs of four un-illuminated four KBr pellets under excitation with 735 nm LED light, with different concentrations (0.1%, 0.5%, 1% and 5%) of $[\text{Pt}(\text{MCO})_2]_n$, are shown in ESI 85. Then the image of the same pellets being illuminated at the above wavelength shows them being clearly visible and brightly colored. In addition, the Petri dish with water was placed over two pellets to show that the NIR emission from the complex is not obstructed by water. This is important for future experiments with cell cultures and biological tissue directed at the theranostic applications of these NIR emitters.

Conclusions

- The reaction between the K^+ salts of the two N-substituted-acetamide cyanoxime anions PiPCO^- and MCO^- with K_2PtCl_4 led to the formation of complexes of PtL_2 composition which exist as at least two *polymorphs*: monomeric yellow complexes, and dark-green $[\text{PtL}_2]_n$ 1D polymers in which individual PtL_2 units are held together via Pt—Pt metallophilic interactions.

- Cyanoxime ligands used in these preparations are *inexpensive compounds* that are easily produced in one step from commercially available precursors that form Pt-complexes in a good yield. This is contrary to much more difficult to obtain and purify other known heterocyclic ligands and organometallic Pt-complexes that are typically used in these studies. Yet, presented in this work polymeric $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ compounds outperform in the NIR emission wavelengths all previously reported “Pt-wires”.
- Current work opens a new page in studies of mixed donor 1D solids with $[\text{PtN}_2\text{O}_2]$ inner coordination sphere with by far more interesting chemical and physical properties such as better solubility in common solvents, photoluminescence and solid state semiconductivity.
- The obtained solid $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ 1D polymers represent “metal wire” since they demonstrate a relatively high electrical conductivity (20–30 S/cm = semiconductors) which is typical for a *mixed valence species*. There is a small amount of Pt(IV) species in these complexes, sufficient for the facilitation of electron hopping between Pt(II) and Pt(IV) centers. Tetravalent platinum could be partially generated either aerobically by oxygen from the air, or via oxidation of the metal with the cyanoxime, or via disproportionation of the initial Pt(II) species to Pt(0) and Pt(IV) complexes, or due to catalytically generated products of further chemical modifications of cyanoximes that lead to partial generation of Pt(IV) species.
- Being dissolved in solvents that do not disrupt the metallophilic interactions in stacks these complexes *spontaneously aggregate* to form opaque colloidal systems with single-size particles that contain ~920 (for $[\text{Pt}(\text{MCO})_2]_n$) and ~680 (for and $[\text{Pt}(\text{PiPCO})_2]_n$) units per stack.
- The same 1D polymeric complexes also show a rather *intense NIR fluorescence* beyond 1000 nm. At the same time, yellow monomeric PtL_2 are not emissive, which evidences the importance of the aggregation and the metallophilic interaction for the fluorescence.
- The chemical oxidation of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ in solutions and solid state increases the intensity of the MMLCT band in the visible region of the spectrum and increases the NIR emission intensity.
- The photoluminescence of both 1D polymeric Pt-cyanoximates in an ionic salt matrix (KBr) increases with the concentration of the complex decrease, and with quantum yields being in the range between 0.2 and 2%.
- The photoluminescence of 1D polymers at 5% concentrations in KBr at variable temperatures showed a very pronounced bathochromic shift of the emission λ_{max} and an intensity decrease with lowering temperature similarly to some semiconductors-based confined quantum dots and wells. Our work with polymeric dark-green Pt-cyanoximates at variable temperatures represents the *first observations* of this kind of emission behavior in these mixed valence “metal wires”.

- *Images* of pure solid powders of $[\text{Pt}(\text{MCO})_2]_n$ and $[\text{Pt}(\text{PiPCO})_2]_n$ samples as well as in dilute KBr matrices emitting in the NIR region beyond 1000 nm *were recorded for the first time.*
- The demonstrated photoluminescence of the studied 1D complexes combined with the established compounds' cytotoxicity makes them interesting candidates for theranostic applications.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

NG is very grateful to the following individuals for their help during work on this project: Dr. Dan Zhou from the University of Missouri – St. Louis for the recording of SEM images; Prof. Dennis Tallman from North Dakota State University for his help with the electrical conductivity measurements of powdery Pt-cyanoximates samples using the AFM method; Dr. Allen Oliver (Notre Dame University) and Dr. Jeannette Krause (University of Cincinnati) for data collection on the synchrotron source at UC-Berkeley, where the Advanced Light Source is supported by the U.S. Department of Energy, Office of Energy Sciences Materials Sciences Division, under contract DE-AC02-05CH11231. Ng is also grateful to Prof. Vlad Kolesnichenko from Xavier University of Louisiana for his initial help with the assessment of particles size in Pt-cyanoximates systems; Prof. Vivi-an Yam from Hong-Kong University for her help with the initial measurements of photoemission of two Pt-cyanoximates in solutions; Dr. Jim Matheis from Horiba for the determination of the NIR emission lifetimes for both Pt-cyanoximates in a solid state, Ms. Hanna Roda for her kind help with the solutions' electrochemical measurements, and Ms. Alexandra Corbett for invaluable technical assistance during the manuscript preparation. We also acknowledge MSU Graduate College for partial financial support of this work throughout several years, the financial support from the NCI/NIH (R21CA149814), and NSF (1355466). We also thank the Washington University Optical Spectroscopy Core facility (NIH 1S10RR031621-01) for spectroscopy measurements. We are grateful to Dr. Justin Douglas from the University of Kansas for recording the EPR spectra of solid samples (support for the EPR instrumentation was provided by the NSF Chemical Instrumentation Grant # 0946883).

References

1. Doerr LH. *Comm Inorg Chem.* 2008; 29:93.
2. Berry, J. *Extended metal atoms chains.* 3. Springer Science and Business Media, Inc; 2005.
3. Peter Day NSH, Robin J, Clark H. *Philosophical Transactions of the Royal Society, A.* 2008; 366:5.
4. Robin MB, Day P. *Adv Inorg Chem Radiochem.* 1967; 10:247.
5. Day, P. *Mixed-valence Compounds.* Vol. 58. Reidel; Dordrecht: 1980. p. 3
6. Allen GC, Hush NS. Intervalence-transfer absorption. I. Qualitative evidence for intervalence-transfer absorption in inorganic systems in solution and in the solid state. 1967; 8
7. Hush NS. Intervalence-transfer absorption. Part 2. Theoretical considerations and spectroscopic data. 1967; 8
8. Fackler, JP. *Mixed Valence Compounds.* John Wiley & Sons; England: 2006.
9. Terril, RH., Murray, RW. *Electron hopping transport in electrochemically active, molecular mixed valent materials.* Blackwell Science; Hoboken, NJ, USA: 1997.
10. Krogmann K. *Ang Chem Int Ed (in English).* 1969; 8:35.
11. Kojima N, Fukuhara F, Kitagawa H, Takahashi H, Mōri N. *Syn Metals.* 1997; 86:2175.
12. Bret J-M, Castan P, Laurent J-P. *Inorg Chim Acta.* 1981; 51:103.
13. Miller JS, Epstein AJ. *Progr Inorg Chemistry series.* 1976; 20:1.
14. Tancret N, Obbade S, Bettahar N, Abraham F. *J Solid State Chem.* 1996; 124:309.
15. Kimura N, Ishimaru Si, Ikeda R, Yamashita M. *J Chem Soc, Faraday Transactions.* 1998; 94:3659.
16. De Sadeleer CM, Hanot VP, Robert TD. *Trans Met Chem.* 1994; 19:585.
17. Keller, HJ. *Extended Linear Chain Compounds.* Miller, JS., editor. Vol. 1. Plenum Press; New York: 1983. p. 357

18. Scott B, Bracewell BL, Johnson SR, Swanson BI, Bardeau JF, Bulou A, Hennion B. *Chem Mater.* 1996; 8:321.
19. Brozik JA, Scott BL, Swanson BI. *J Phys Chem, B.* 1999; 103:10566.
20. Stevens GC. *Platinum Met Rev.* 1979; 23:23.
21. Jack, M., Williams, AJS., Underhill, Allan E., Carneiro, Kim. The Synthesis, Structure, Electrical Conduction Properties, and Theory of Divalent, Tetravalent, and One-Dimensional Partially Oxidized Tetracyanoplatinate Complexes. In: Miller, JS., editor. *Extended Linear Chain Compounds.* Springer US: Plenum Press; NY: 1982. p. 73
22. Allan, E., Underhill, DMW., Williams, Jack M., Carneiro, Kim. Linear Chain Bis(oxalato)platinate Salts. In: Miller, J., editor. *Extended Linear Chain Compounds.* Springer US: Plenum Press; NY: 1982. p. 119
23. Underhill AE, Watkins DM, Jacobsen CS. *Solid State Comm.* 1980; 36:477.
24. Mégnamisi-Béloméé M. *J Solid State Chem.* 1979; 27:389.
25. Brill JW, Mégnamisi-Béloméé M, Novotny M. *J Chem Phys.* 1978; 68:585.
26. Yamaguchi T, Nishimura N, Shirakura K-i, Ito T. *Bull Chem Soc Japan.* 2000; 73:775.
27. Kanakubo M, Yamamoto K, Honda K, Ushijima H, Kamata T, Mizukami F, Ohta T. *Analytical Sciences.* 1999; 15:107.
28. Endres H, K HJ, van de Sand H, Dong V. *Z Naturforsch.* 1978; 33:843.
29. Ferraris G, Viterbo D. *Acta Cryst B.* 1969; 25:2066.
30. Brianso JL, Md M. *Afinidad.* 1982; 39:271.
31. Matsumoto K, Sakai K. *Advances in Inorg Chem, series.* 1999; 49:375.
32. Abe T, Moriyama H, Matsumoto K. *Inorg Chem.* 1991; 30:4198.
33. Sakai K, Matsumoto K. *J Am Chem Soc.* 1989; 111:3074.
34. O'Halloran TV, Mascharak PK, Williams ID, Roberts MM, Lippard SJ. *Inorg Chem.* 1987; 26:1261.
35. Lippert B, Schoellhorn H, Thewalt U. *Inorg Chem.* 1987; 26:1736.
36. Eddings D, Barnes C, Gerasimchuk N, Durham P, Domasevich K. *Inorg Chem.* 2004; 43:3894. [PubMed: 15206870]
37. Gerasimchuk N, Goeden L, Durham P, Barnes C, Cannon JF, Silchenko S, Hidalgo I. *Inorg Chim Acta.* 2008; 361:1983.
38. Ratcliff J, Durham P, Keck M, Mokhir A, Gerasimchuk N. *Inorg Chim Acta.* 2012; 385:11.
39. Liu Y, Bauer AQ, Akers WJ, Sudlow G, Liang K, Shen D, Berezin MY, Culver JP, Achilefu S. *Surgery.* 2011; 149:689. [PubMed: 21496565]
40. Troyan SL, Kianzad V, Gibbs-Strauss SL, Gioux S, Matsui A, Oketokoun R, Ngo L, Khamene A, Azar F, Frangioni JV. *Ann Surg Oncol.* 2009; 16:2943. [PubMed: 19582506]
41. Zhegalova NG, Gonzales G, Berezin MY. *Org Biomol Chem.* 2013; 11:8228. [PubMed: 24166035]
42. Salo D, Zhang H, Kim DM, Berezin MY. *J Biomed Opt.* 2014; 19:086008. [PubMed: 25104414]
43. Schaafsma BE, Mieog JS, Hutteman M, van der Vorst JR, Kuppen PJ, Lowik CW, Frangioni JV, van de Velde CJ, Vahrmeijer AL. *J Surg Oncol.* 2011; 104:323. [PubMed: 21495033]
44. Barone PW, Baik S, Heller DA, Strano MS. *Nat Mater.* 2005; 4:86. [PubMed: 15592477]
45. Knight MW, Sobhani H, Nordlander P, Halas NJ. *Science.* 2011; 332:702. [PubMed: 21551059]
46. Qian G, Zhong Z, Luo M, Yu D, Zhang Z, Wang ZY, Ma D. *Adv Mater.* 2009; 21:111.
47. Gerasimchuk, N., Berezin, M., Klaus, DR. In 1D coordination polymers based on Pt(II) cyanoximates as new class of NIR emitters beyond 900 nm; 49th Midwest Regional Meeting of the American Chemical Society; Columbia, MO, USA. November 15–16, 2014; Columbia, MO, USA: 2014. 2014; pp Oral presentation, #308
48. Klaus DR, Keene M, Silchenko S, Berezin M, Gerasimchuk N. *Inorg Chem.* 2015; 54:1890. [PubMed: 25615022]
49. Ratcliff J, Kuduk-Jaworska J, Chojnacki H, Nemykin V, Gerasimchuk N. *Inorg Chim Acta.* 2012; 385:1.
50. Mann A, Gerasimchuk N, Silchenko S. *Inorg Chim Acta.* 2016; 440:118.

51. Ostwald W. Zeits für Physik Chemie. 1897; 22:289.
52. Matschiner H, Kohler H, Matuschke R. Zeit anorg Allg Chem. 1971; 380:267.
53. Mokhir AA, Domasevich KV, Kent Dalley N, Kou X, Gerasimchuk NN, Gerasimchuk OA. Inorg Chim Acta. 1999; 284:85.
54. Marcano D, Gerasimchuk N, Nemykin V, Silchenko S. Cryst Growth & Design. 2012; 12:2877.
55. Gerasimchuk N, Esaulenko AN, Dalley KN, Moore C. Dalton Trans. 2010; 39:749. [PubMed: 20066220]
56. Köhler H, Lux G. Inorg Nuc Chem Lett. 1968; 4:133.
57. Gordon, A., Ford, R. The Chemist's Companion: A Handbook of Practical Data, Techniques, and References. John Wiley & Sons; New York, London, Sydney, Totonto: 1972.
58. Dean, JA. Lange's Handbook of Chemistry. Mc Graw-Hill; 1999.
59. CRC Handbook of Chemistry and Physics. 96th. Taylor & Francis Ltd; 2015. p. 2677
60. Anex BG. J Chem Phys. 1967; 46:1090.
61. Miller JR. J Chem Soc (Resumed). 1965; 44:713.
62. Morosin B, Fallon P, Valentine JS. Acta Cryst B. 1975; 31:2220.
63. Riddles CN, Whited M, Lotlikar SR, Still K, Patrauchan M, Silchenko S, Gerasimchuk N. Inorg Chim Acta. 2014; 412:94.
64. Mokhir AA, Domasevich KV, Kent Dalley N, Kou X, Gerasimchuk NN, Gerasimchuk OA. Inorg Chim Acta. 1999; 284:85.
65. Gerasimchuk N, Dalley NK. J Coord Chem. 2004; 57:1431.
66. Endres H, K HJ, van de Sand H, Dong Vu. Z Naturforsch. 1978; 33b:843.
67. Zhang X-F, Xi Q, Zhao J. J Mat Chem. 2010; 20:6726.
68. Gerasimchuk NN, Mokhir AA, Rodgers KR. Inorg Chem. 1998; 37:5641. [PubMed: 11670713]
69. Zhou, L. Mathematics course FICI 1039. University de Los Andes; 2012. n-coupled oscillator; p. 1
70. Martin RB. Chem Rev. 1996; 96:3043. [PubMed: 11848852]
71. Thomas TW, Underhill AE. Chem Soc Rev. 1972; 1:99.
72. Lourenco SAD, I FL, Duarte JL, Laureto E, Aquino VM, Harmand JC. Braz J Phys. 2007; 37:1212.
73. Jing P, Zheng J, Ikezawa M, Liu X, Lv S, Kong X, Zhao J, Masumoto Y. J Phys Chem, C. 2009; 113:13545.
74. Kent Mann, CD., Exstrom, Christopher, Jansen, Daron, Pomije, Marie. Vaporochromic platinum complexes and salts. US patent 5,766,952. 1998.
75. Buschmann WE, McGrane SD, Shreve AP. J Phys Chem, A. 2003; 107:8198.
76. Park HJ, Kim JH, Ryu HH, Jeon M, Leem JY, Kim JS, Kim JS, Son JS, Lee DY. J Korean Phys Soc. 2007; 51:1383.
77. Chi TTK, Liem NQ, Nam MH, Thanh DX. J Korean Phys Soc. 2008; 52:1510.
78. Bel Haj Mohamed N, Haouari M, Zaaboub Z, Nafoutti M, Hassen F, Maaref H, Ben Ouada H. J Nanopart Res. 2014; 16:2242. [PubMed: 24563613]
79. Kallu, JBT., Sulthana, S., Heckert, B., Gerasimchuk, N., Santra, S. Oral presentation, #183 In Hsp90 inhibitor carrying magnetic nanotheranostics for the treatment of non-small-cell lung cancer; 50th Midwest Regional ACS meeting; St. Joseph, Missouri, USA. October 21–24, 2015; St. Joseph, Missouri, USA: 2015. p. #183oral presentation
80. Sakhawat Hussain M, Salinas BEV, Schlemper EO. Acta Cryst B. 1979; 35:628.
81. Stork JR, Olmstead MM, Fettingner JC, Balch AL. Inorg Chem. 2006; 45:849. [PubMed: 16411723]
82. Aullón G, Alvarez S. Eur J Chem. 1997; 3:655.
83. Yamaguchi T, Nishimura N, Ito T. J Am Chem Soc. 1993; 115:1612.
84. Baxter LAM, Heath GA, Raptis RG, Willis AC. J Am Chem Soc. 1992; 114:6944.
85. Endres H. Acta Cryst C. 1985; 41:1047.
86. Endres H, Gelb L-B. Z Naturforsch. 1986; 41:137.
87. Miskowski VM, Houlding VH. Inorg Chem. 1989; 28:1529.

88. Seong Jin, Koh, Ehrlich, G. Phys Rev B. 2000; 62:R10645(R).
89. Miskowski VM, Houlding VH. Inorg Chem. 1991; 30:4446.
90. Li K, So Mi Tong G, Wan Q, Cheng G, Tong W-Y, Ang W-H, Kwong W-L, Che C-M. Chem Science. 2016; 7:1653.
91. Bennett MA, Bhargava SK, Cheng C-CE, Lam WH, Lee TK-M, Priver SH, Wagler J, Willis AC, Yam VW-W. J Am Chem Soc. 2010; 132(20):7094. [PubMed: 20433140]
92. Ly KT, Chen-Cheng R-W, Lin H-W, Shiau Y-J, Liu S-H, Chou P-T, Tsao C-S, Huang Y-C, Chi Y. Nature Photonics. 2017; 11:63.
93. Gerasimchuk, N., Berezin, M. A new strategy for the NIR emitters beyond 900 nm: preparation of self-assembled luminescent 1D Pt-cyanoximates; Abstract of Papers, 250th ACS National Meeting; Boston, MA. Aug 16–20. 2015 INOR-595; oral presentation
94. (a) Kukushkin, VYu, Belsky, VK., Tudela, D. Inorg Chem. 1996; 35(2):510. [PubMed: 11666238] (b) Bolotin D, Demakova MYu, Novikov AS, Avdontceva MS, Kuznetsov ML, Bokach NA, Kukushkin VYu. Inorg Chem. 2015; 54(8):4039. [PubMed: 25822628] (c) Mikhaleva AI, Zaitsev AB, Trofimov BA. Russ Chem Rev. 2006; 75(9)
95. (a) Kuznetsova ML, Bokach NA, Kukushkin VYu, Pakkanen T, Wagnera G, Pombeiro AJL. J Chem Soc Dalton Trans. 2000; 24:4683–4693.(b) Kukushkin, VYu, Tudela, D., Pombeiro, AKL. Coord Chem Rev. 1996; 156:333.

Synopsis

Yellow monomeric complexes of platinum with two cyanoxime ligands, 2-cyano-2-oximino-N-piperidinoacetamide, $\text{Pt}(\text{PiPCO})_2$, and 2-cyano-2-oximino-N-morpholinoacetamide, $\text{Pt}(\text{MCO})_2$, self-assemble into polymeric dark-green $[\text{PtL}_2]_n$ 1D stacks held by metallophilic interactions. Formed polymers exhibit significant electrical conductivity which evidences presence of mobile charge carriers and indicates the formation of mixed valence species. These polymers demonstrate unique optical characteristics showing broad absorption at ~400–850 nm and intense near-infrared luminescence within 1000–1100 nm in solid state.

Figure 1. Time profile of the formation of emerald-green opalescent colloidal solution of $[\text{Pt}(\text{PiPCO})_2]_n$ after its dissolution in dry N,N' -dimethylacetamide, DMAA. An arrow indicates appearance of visible precipitate particles, while red line shows their linear size growth consistent with “Oswald ripening” in extended chain systems.

Figure 2.

Three polymorphs in Pt-MCO system. The 1D coordination polymer is the only one major bulk product of the reaction, while other forms can be isolated after its treatment with donor solvents which disrupt Pt—Pt interactions.

Figure 4.

The ASU in the structure of a red-dimer $[\text{Pt}(\text{MCO})_2 \times 2\text{DMSO}]_2$ showing two crystallographically different molecules (A). The Pt2-based monomer has symmetry related (*i*) second part bound in a “head-to-tail” fashion (B) with a short connection between two Pt-centers at 3.133 Å (C, side view) shown in space-filling mode and H-atoms omitted for clarity.

Figure 5.

A – Solid-state UV-visible spectra of dark-green 1D polymeric $[\text{Pt}(\text{PiPCO})_2]_n$ (blue) and $[\text{Pt}(\text{MCO})_2]_n$ (red) recorded as fine suspensions in silicon oil; dotted line shows the excitation wavelength for recording emission spectra. **B** – emission spectra of these compounds embedded in KBr pellet at weigh 5% concentration.

Figure 6.

The excitation spectra of dark-green 1D polymeric $[\text{Pt}(\text{MCO})_2]_n$ at 5% in KBr pellet: top – 3D view; bottom – 2D map showing continuous emission at any excitation wavelength from 300 to 800 nm.

Figure 7. The concentration dependence on the emission intensity and its wavelength in KBr pellets with $[\text{Pt}(\text{PiPCO})_2]_n$ (A), and on the absolute quantum yield for both studied 1D polymeric Pt-cyanoximates (B).

Figure 8. Variable temperature photoluminescence of 1D dark-green polymeric $[\text{Pt}(\text{MCO})_2]_n$ embedded into KBr matrix at 5% concentration (A), and s-shaped response of emission intensity on temperature change (B). A “linear part” can be approximated as indicated by arrows.

Figure 9. Variable temperature photoluminescence of 1D dark-green polymeric $[\text{Pt}(\text{PiPCO})_2]_n$ embedded into KBr matrix at 5% concentration (**A**), and large range of linear response (indicated by arrows) of emission intensity on temperature change (**B**).

Figure 10.

Images of pure powders of dark-green 1D-polymeric Pt-cyanoximates (on double-sided transparent adhesive tape attached to black cardboard) recorded with the help of Ninox image camera. Left panel corresponds to $[\text{Pt}(\text{MCO})_2]_n$, right to $[\text{Pt}(\text{PiPCO})_2]_n$. **A** – “as is” images recorded at ambient conditions; **B** – same panels recorded using 735 nm excitation with LED source; **C** – KBr pellets with 5% embedded compounds; left – partially oxidized KCP (Krogman’s salt) and right – $[\text{Pt}(\text{PiPCO})_2]_n$; **D** – same pellets photographed using 735 nm excitation with LED source with 0.5 s exposure time and long-path 800 nm filter.

Scheme 1.

Scheme 2.

Scheme 3.

Table 1

Crystal and refinement data for studied Pt-cyanoximates: Pt(PiPCO)₂, Pt(MCO)₂ and its dimeric DMSO solvate.

	Pt(MCO) ₂ , <i>monomer</i>	[Pt(MCO) ₂ (DMSO)] ₂ , <i>dimer</i>	Pt(PiPCO) ₂ , <i>monomer</i>
Empirical formula	C ₁₄ H ₁₆ N ₆ O ₆ Pt	C ₁₆ H ₂₂ N ₆ O ₇ PtS	C ₁₆ H ₂₀ N ₆ O ₄ Pt
F.W, g/mol	559.42 g/mol	637.54	555.47
Color	yellow	red	yellow
Crystal size, mm	0.077 × 0.152 × 0.226	0.010 × 0.010 × 0.170	0.071 × 0.079 × 0.194
Temperature, K	120(2)	150(2)	100(2)
Crystal system	Triclinic	Triclinic	Orthorhombic
Space group, #	P-1, #2	P-1, #2	P b c a, #61
Unit cell, Å, °	a = 6.6507(5) b = 8.7986(7) c = 15.4740(12) α = 94.2700(10) β = 96.0640(10) γ = 106.4490(10)	a = 6.8051(9) b = 13.6157(17) c = 24.278(3) α = 76.5560(10) β = 89.595(2) γ = 75.966(2)	a = 6.6743(10) b = 17.455(3) c = 30.557(5) α = 90 γ = 90 γ = 90
Unit cell volume, Å ³	858.38(12)	2119.7(5)	3559.9(10)
Z	2	4	8
Density (calc.) Mg/m ³	2.164 g/cm ³	1.998	2.073
Absorp. coeff., mm ⁻¹	8.221	11.730	7.920
F(000)	536	1240	2144
Θ range, °	1.33 to 25.00°	2.55 to 33.58°	2.33 to 27.18°
Index ranges	-7<h<=7 -10<=k<=10 -18<=l<=18	-8<=h<=8 -16<=k<=16 -29<=l<=29	-8<=h<=8 -22<=k<=22 -39<=l<=39
Structures solution		<i>Direct</i>	
Reflections collected	8966	18231	41767
Independent reflections	3014 [R(int)=0.0282]	8171 [R(int) = 0.0579]	3958 [R(int) = 0.2445]
Completeness to Θ, (%)	25.00° (99.8)	33.58° (94.5)	27.18 (98.7)
Absorption correction	multi-scan	multi-scan	multi-scan
T _{max} and T _{min}	1.0000 and 0.7794	0.8170 and 0.7110	0.7455 and 0.5492
Refinement method		<i>Full-matrix least-squares on F²</i>	
Data/restraints/parameters	3014/0/244	8171/0/563	3958/36/245
Goodness-of-fit on F ²	1.043	1.010	0.980
Final R indices [I>2σ(I)]	R1 = 0.0193, wR2 = 0.0352	R1 = 0.0451 wR2 = 0.1366	R1 = 0.0538, wR2 = 0.1076
R indices (all data)	R1 = 0.0217 wR2 = 0.0359	R1 = 0.0480 wR2 = 0.1391	wR1 = 0.1267 wR2 = 0.1385
Largest peak/hole, e.Å ⁻³	0.737 and -1.368	1.153 and -1.546	1.845 and -2.153
Extinction coefficient	n/a	n/a	0.0023(2)

	Pt(MCO)₂, monomer	[Pt(MCO)₂(DMSO)]₂, dimer	Pt(PiPCO)₂, monomer
Structures volume, Å ³ (%):	565.7 (65.3)	1379.9 (65.1)	2309.3 (64.9)

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Table 2

Selected bond distances (Å) and angles (°) in the structure of monomeric yellow Pt-cyanoximates.

Pt(PiPCO)₂

Bonds		Angles	
Pt(1)-O(2)	2.005(8)	N(1)-C(1)-C(3)	114.1(10)
Pt(1)-O(4)	2.000(8)	C(1)-C(3)-O(2)	115.7(10)
Pt(1)-N(1)	1.984(10)	N(4)-C(9)-C(11)	112.2(10)
Pt(1)-N(4)	1.939(10)	C(9)-C(11)-O(4)	115.5(10)
O(2)-C(3)	1.271(13)	O(2)-Pt(1)-N(1)	79.6(4)
O(4)-C(11)	1.305(14)	O(2)-Pt(1)-O(4)	95.3(3)
N(1)-O(1)	1.270(13)	N(1)-Pt(1)-N(4)	104.1(4)
N(4)-O(3)	1.257(11)		
N(1)-C(1)	1.307(16)		
N(4)-C(9)	1.382(14)		
C(1)-C(2)	1.454(17)		
C(9)-C(10)	1.429(17)		
C(2)-N(2)	1.130(16)		
C(10)-N(5)	1.154(15)		

Pt(MCO)₂

Pt(1)-O(3)	2.027(2)	O(3)-C(3)-C(1)	116.7(3)
Pt(1)-O(6)	2.019(2)	C(3)-C(1)-N(1)	114.1(3)
Pt(1)-N(1)	1.957(3)	O(6)-C(10)-C(8)	116.0(3)
Pt(1)-N(4)	1.962(3)	O(10)-C(8)-N(4)	113.9(3)
N(1)-O(1)	1.246(3)	O(3)-Pt(1)-N(1)	81.25(11)
N(4)-O(4)	1.257(3)	O(3)-Pt(1)-O(6)	95.89(9)
N(1)-C(1)	1.361(4)	N(1)-Pt(1)-N(4)	102.51(12)
N(4)-C(8)	1.355(4)		
C(1)-C(2)	1.428(5)		
C(8)-C(9)	1.427(5)		
C(1)-C(3)	1.453(5)		
C(8)-C(10)	1.455(5)		

Table 3

Selected bond distances (Å) and angles (°) in the structure of the dimeric part of red $[\text{Pt}(\text{MCO})_2\cdot\text{DMSO}]_2$, at Pt(2) center.

Bonds		Angles	
Pt(2)-O(8)	2.025(4)	N(10)-Pt(2)-N(7)	104.1(2)
Pt(2)-O(11)	2.016(4)	N(7)-Pt(2)-O(11)	174.83(18)
Pt(2)-N(7)	1.981(5)	N(7)-Pt(2)-O(8)	80.57(19)
Pt(2)-N(10)	1.979(5)	N(10)-Pt(2)-O(11)	81.03(18)
N(7)-O(7)	1.249(6)	N(10)-Pt(2)-O(8)	175.03(16)
N(10)-O(10)	1.236(6)	O(11)-Pt(2)-O(8)	94.26(17)
N(7)-C(15)	1.348(8)	O(7)-N(7)-C(15)	120.6(5)
C(15)-C(16)	1.444(8)	N(7)-C(15)-C(16)	117.5(5)
C(16)-N(8)	1.140(8)	N(7)-C(15)-C(17)	114.7(5)
C(15)-C(17)	1.446(8)	C(16)-C(15)-C(17)	127.4(6)
C(17)-N(9)	1.331(8)	O(8)-C(17)-N(9)	117.3(5)
C(17)-O(8)	1.285(7)	O(8)-C(17)-C(15)	116.7(5)
C(22)-N(10)	1.354(7)	N(9)-C(17)-C(15)	126.0(5)
C(22)-C(23)	1.445(8)	N(10)-C(22)-C(24)	114.7(5)
C(22)-C(24)	1.451(7)	N(10)-C(22)-C(23)	117.9(5)
C(23)-C(11)	1.132(8)	N(12)-C(24)-C(22)	125.6(5)
C(24)-O(11)	1.297(7)	O(11)-C(24)-N(12)	117.9(5)
C(24)-N(12)	1.332(7)	O(11)-C(24)-C(22)	116.4(5)

Table 4

Literature data for crystal structures of different Pt-oximates and Pt-oxalates.

Complex	oxime ligand	color	Pt—Pt, Å	Space gr.	Comments	CCDC refcode, refs.
Pt(GLY) ₂	1,2-glyoxaldioxime	brown-viol	3.506	P2 ₁ /n	columnar 1D structure overlaid stacks extended along <i>a</i> direction	GLYOPT [2]
Pt(DMG) ₂	1,2-dimethylglyoxime	blue	3.257	Ibam	columnar structure overlaid stacks extended along <i>c</i> direction; <i>ID wire</i>	PTNGLO01 [3]
Pt(DMG) ₂ L ₂	1,2-dimethylglyoxime (dicarb = dicarbene)		7.053	P2 ₁ /c	layered structure with a large off-set of units to each other	HESWES [4]
Pt ₃ (DMG) ₃ (OAc) ₄	1,2-dimethylglyoxime (+ CH ₂ Cl ₂ solvent)		2.516, 2.603 2.522	P-1	isolated tri-Pt triangular motif with 2 bridging and 2 monodentate acetates; <i>mixed valence system</i>	MEMLEV [5]
Pt ₈ (DMG) ₇ (OAc) ₆	1,2-dimethylglyoxime (+ CH ₂ Cl ₂ solvent)		2.529 2.549 2.678	P-1	octa-Pt assembly comprised of two tetramers connected via bridging DMG ligand; 6 chelating DMG ligands, and 5 bidentate OAc and 1 monodentate OAc groups; <i>mixed valence system</i>	MEMLUL [5]
Pt(DEG) ₂	1,2-diethylglyoxime	dark-brown	3.555	C ₂ /c	slipped columnar structure extended along <i>c</i> direction	KACPAF [6]
Pt(DPG) ₂	1,2-diphenylglyoxime	orange/black	3.260	P4/ncc	columnar structure with stacks extended along <i>c</i> ; <i>ID wire</i>	PGLXPT [7]
Pt(DCG) ₂	1,2-dichloroglyoxime		3.176	Iba2	columnar structure with stacks extended along <i>a</i> ; <i>ID wire</i>	BOHWOK [8]
Pt(BQD) ₂	1,2-benzoquinone dioxime	blue	3.173	Ibam	columnar structure with stacks extended along <i>c</i> ; <i>ID wire</i>	BQDXPT [9]
Pt ₃ (DMG) ₃ (OAc) ₄ Pt ₃ (NIOX) ₃ (OAc) ₄	1,2-dimethylglyoxime, 1,2-cyclohexyldioxime	red-brown	2.259 2.542	P-1	isolated tri-Pt triangular cluster with 2 bridging and 2 monodentate acetate groups; <i>mixed valence system</i>	WAGPUP [10]
Pt(COG) ₂ Cl ₂	1,2-cyclooctylglyoxime (Cl ⁻ bound to the metal)		2.696	P2 ₁ /n	discrete Pt(III) dimers	PALTOL [11]
Pt(DAG) ₂ I H ₂ O	1,2-diaminoglyoxime (I ⁻ and H ₂ O as well)	red	3.242	P-1	slipped columnar structure with stacks along <i>a</i> direction; <i>mixed valence system</i>	DAXWAK [12]
Pt(DAG) ₂ Pt(Ox) ₂	1,2-diaminoglyoxime (mixed-ligands complex)		3.660	P2 ₁ /n	slipped columnar structure with tilted alternating stacks along <i>b</i> direction	DOGCAD [13]

Table 5

Comparison of photophysical properties of studied thus far dark-green 1D polymeric Pt-cyanoximates embedded into KBr matrix at 5 weight % concentration. All data collected at 770 nm excitation wavelength.

Complex	Cyanoxime	λ_{max} emissions	Variable temperature measurements				Refs.
			λ , nm/cm ⁻¹ /meV	Effect of VT on signals	Linear T range, °	QY, %	
[Pt(DECO) ₂] _n		one band; 1043 nm (+67°C) 1097 nm (−175°C)	54/472/58	hypsochromic shift with temperature increase; intensity decrease with temperature decrease	~115	0.51	[⁴⁸]
[Pt(PiPCO) ₂] _n		two overlapping bands* centered at 1052 nm (at +61 °C) centered at 1090 nm (at −192°C)	48/332/41	- same as above -	~140	0.91 tl	this work
[Pt(MCO) ₂] _n		two overlapping bands** centered at 1025 nm (at +70°C) centered at 1066 nm (at −196°C)	41/375/47	- same as above -	~98	0.21 t	his work

* details can be seen in ESI 83 ;

** and in ESI 82