Published in final edited form as:

Acta Biomater. 2017 May ; 54: 45–57. doi:10.1016/j.actbio.2017.02.045.

Shape Memory Polymers with Enhanced Visibility for Magnetic Resonance- and X-Ray Imaging Modalities

AC Weems, JM Szafron, AD Easley, S Herting, J Smolen, and DJ Maitland

Department of Biomedical Engineering, 5045 Emerging Technologies Building, 3120 TAMU Texas A&M University, College Station, TX, USA 77843-3120

Abstract

Currently, monitoring of minimally invasive medical devices is performed using fluoroscopy. The risks associated with fluoroscopy, including increased risk of cancer, make this method especially unsuitable for pediatric device delivery and follow-up procedures. A more suitable method is magnetic resonance (MR) imaging, which makes use of harmless magnetic fields rather than ionizing radiation when imaging the patient; this method is safer for both the patient and the performing technicians. Unfortunately, there is a lack of research available on bulk polymeric materials to enhance MR-visibility for use in medical devices. Here we show the incorporation of both physical and chemical modifying agents for the enhancement of both MR and X-ray visibility. Through the incorporation of these additives, we are able to control shape recovery of the polymer without sacrificing the thermal transition temperatures or the mechanical properties. For long-term implantation, these MR-visible materials do not have altered degradation profiles, and the release of additives is well below significant thresholds for daily dosages of MR-visible compounds. We anticipate our materials to be a starting point for safer, MR-visible medical devices incorporating polymeric components.

Graphical Abstract

Corresponding author: Duncan J Maitland, djmaitland@tamu.edu, Phone: 979-458-3471, Fax: 979-845-4450.

Disclosure

Shape Memory Medical, Inc. holds the license of medical applications of shape memory polymer foams discussed in this work. The authors disclose the DJ Maitland is a founder, board member, and shareholder of SMM. Furthermore, AC Weems holds stock options with SMM.

Publisher's Disclaimer: This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Keywords

Shape memory polymer; magnetic resonance imaging; x-ray imaging; cytocompatibility

1. Introduction

X-ray fluoroscopy is the most common method for monitoring implanted medical devices. While x-ray fluoroscopy does allow for real-time monitoring of device placement, there are associated risks for technicians, patients requiring multiple images, and especially pediatric patients, due to the ionizing radiation used. Magnetic resonance (MR) imaging offers an alternative technique for device monitoring during minimally invasive delivery and follow-up procedures. [1–4] Herein we present the development of a shape memory polymer (SMP) porous scaffold that can be visualized via MR-imaging, as well as possible imaging via X-ray fluoroscopy for dual imaging modality procedures.

Nearly 25% of the population is born with some type of congenital heart defect, and while most are not significant enough to require intervention, those that do are typically treated using a metallic device that is delivered via catheter and monitored post-operatively with x-ray fluoroscopy.[4–6] If left untreated, these defects may result in ischemic stroke, migraine, or decompression sickness, and in pediatric cases they may result in sudden death upon intense cardiac loading.[2, 6–8] Pediatric medical devices would be safer if visible under an alternative imaging modality.[2] As mentioned previously, the delivery and post-operative monitoring of the devices is performed almost solely via fluoroscopy.[2, 4–7] There is significant concern among researchers that continued exposure to ionized radiation is particularly harmful to pediatric patients.[8] The use of MR imaging as an alternative for pediatric applications provides a safer method of visualizing both the procedure and post-operative images for both the patient and the technicians.[1–4]

MR-visible polymers have been of interest in biomaterials, and a large body of work exists on such materials.[1,2,9] However, there appears to be a lack of bulk materials that are visible under MR-imaging. Most articles discussing the incorporation of MR-visible moieties are on topics including microspheres, liposomal structures, and other nano- or micro-scale devices. Devices that do incorporate MR-visibility either do so passively, such as embolic coils that will induce an artifact due to the metallic structure, or actively, and require radio-frequency modifications.[1,2,9] While passive modifications to materials are the easiest to manufacture, there is limited work for polymers on the scale necessary for tissue scaffolds and medical devices.

The use of porous SMPs for occlusion applications was first introduced by Metcalfe *et al* and was further pursued by Sokolowski and others.[10–14] Thermoplastic SMPs were used for these studies; limitations of these polymer systems include synthesis or degradation by-products being carcinogenic aromatic diamines, a lack of strain fixity over long time periods despite the cold hibernated elastic memory (CHEM) principle, and high stress recoveries with low strain recoveries.[10–15] Due to these limitations, a series of thermoset, aliphatic SMPs were developed by Wilson *et al*, which display low-stress–high-strain recoveries and do not possess aromatic monomers.[15] These SMPs were synthesized with the intent of

enhancing strain recovery and reducing stress recovery while maintaining the high biocompatibility of polyurethanes without the risk of carcinogenic byproducts.[15]

While these materials are superior for minimally invasive devices compared with traditional polyurethanes, polymers are limited when using MR imaging. One method of enhancing MR-visibility is through the inclusion of gadolinium; gadolinium has been conjugated to several polymers, typically for use in nanoparticles, with promising cytocompatibility results.[16–23] Many of these systems are multifunctional and can be used with fluorescence imaging, positron emission tomography (PET) imaging, or x-ray imaging. [16,21–23] Variations in the form of the additives range from complexed metals to the incorporation of gadolinium into carbon nanotubes.[19–24] Unfortunately, many of these polymer systems are synthesized from degradable polymers, which may result in the release of MR-visible compounds at a dangerous rate.[16,23–24]

Iron particles have also found use in MR imaging. Polymer systems, both coatings and bulk modifications, have successfully incorporated iron-based agents.[24–28] These particles can be metabolized by the liver, rather than the kidneys, which would be a limiting factor for alternative contrast agents such as iodine.[29–30]

For translating a device into the clinic, however, there are limitations in establishing a technology without physicians being able to implement it. While moving to devices that are imaged without radiation is ideal, this paradigm shift is not likely to be an achievable goal in the foreseeable future due to current widespread use and clinician familiarity with x-ray techniques for medical device delivery (most devices incorporate non-polymer marker bands for visualization rather than attempting to rely on the polymer to be visible). By developing a material that is multimodal for imaging, device delivery will most likely still be performed using x-ray techniques, but follow-up analysis of the devices or biomaterials (including healing, migration, etc.) can be performed using MRI, thus reducing the overall radiation dose that the patient will experience over their lifetime.

Here we present a method for enhancing the MR-visibility of SMPs through the use of iron nanoparticles or gadolinium chelates (Gd) incorporated into the polymer backbone. The resulting scaffold is highly porous with tunable thermal and mechanical properties. The incorporation of Gd compared with Fe allows for tunable shape recovery profiles, although this does not alter the total recoverable strain or volume. Both methods enhance x-ray density and MR-visibility without significantly altering the degradation rates, and more importantly, without a significant amount of Fe or Gd released into the blood stream over a one-month period. Our methodology will allow for the development of minimally invasive medical devices for use in endovascular applications such as aneurysm occlusion or peripheral occlusion devices.

2. Methods and Materials

2.1 Materials

N,N,N',N'-tetrakis(2-hydroxypropyl)ethylenediamine (HPED, 99%, Sigma Aldrich), triethanolamine (TEA, 98%, Alfa Aesar) and 2,2,4-trimethyl hexamethylene diisocyanate

(TMHDI, TCI America, a mixture of 2,2,4 and 2,4,4 monomers) were used as monomers. Iron oxide (Fe₂O₃) nanoparticles (Fe nps, 80 nm) were obtained from US Nanomaterials Research. Diethylenetriaminepentaacetic acid gadolinium (III) dihydrogen salt dehydrate (Gd, 97%, Sigma Aldrich) was purchased used without further modification. Fe particles were added from 0.5% (wt) to 10.0% (1.0, 2.0, 3.0, 4.0, 5.0 %); Gd was added from 0.25% to 1.0% (wt) by 0.25% increments.

2.2 Synthesis

A traditional two-step polyurethane foaming process was used for synthesis and is briefly described.[31–32] TEA, HPED and TMHDI were reacted to form a prepolymer prior to foaming. The isocyanate index of this prepolymer (NCO/OH ratio) was approximately 2.5; the prepolymer was cured at 50°C for 36 hours to increase viscosity and network formation prior to foaming. The prepolymer was then added to an alcohol premix, consisting of the remaining alcohols, surfactants, catalysts and blowing agents, followed by high speed shear mixing and curing for 20 minutes at 90°C. The Fe nps and/or Gd were added to the alcohol premix (mass %, Gd: 0.1%, 0.25%, 0.5%, 0.75%, 1.0%; Fe: 0.5%, 1.0%, 2.0%, 3.0%, 4.0%, 5.0%, 10.0%) during the second step of the foaming process and were dispersed/dissolved using high speed shear mixing.

Non-porous polymer samples were synthesized using a single-step process. Stoichiometric amounts of HPED and TEA (60:40 ratio) were added to TMHDI and mixed until all monomers were completely dissolved. Samples were cast onto silicone trays and degassed for 90 seconds before being cured overnight in a pressure chamber at 60 PSI. Samples were then removed and cured for an additional 12 hours at 120°C.

Samples were cleaned using a multi-step process, with alternating reverse osmosis (RO) water and isopropyl alcohol (IPA) solutions under sonication at 50°C. After cleaning, SMPs were removed and air dried for 1 hour, followed by drying in a vacuum oven at 50°C (30 in. Hg).

2.3 Fourier transform infrared spectroscopy characterization

Attenuated total reflectance Fourier transform infrared spectroscopy (ATR-FTIR) was used to determine any spectroscopic changes to the bulk material, although no significant changes were expected. ATR-FTIR spectra were taken using a Bruker ALPHA infrared spectrometer (Bruker, Billerica, MA) using 32 scans per spectra for both the background and the samples. Spectra data was collected in absorption mode with a resolution of 4 cm⁻¹.

2.4 Scanning electron microscopy

SMP foam cell structure was examined axially and transversely (based on the foaming axis) using scanning electron microscopy (SEM). Samples were cut from the bulk, mounted onto a stage, and sputter coated with gold using a Cressington Sputter Coater (Ted Pella, Inc., Redding, CA) for 60 seconds at 20 mA. Examination was performed using a Jeol NeoScope JCM-5000 SEM (Nikon Instruments Inc., Melville, NY) at 11X magnification and 15 kV under high vacuum (n=3).

2.5 Thermal analysis

Differential scanning calorimetry (DSC) was performed using a Q-200 DSC (TA Instruments, Inc., New Castle, DE) from -40°C to 120°C for dry samples, and -40°C to 80°C for wet samples, both at a rate of $10^{\circ}\text{C}/\text{min}$. [31] Dynamic mechanical analysis (DMA) was performed using a Q800 TA DMA (TA Instruments, New Castle, DE) were equilibrated at 20°C for 15 minutes and then ramped to 120°C at a rate of $2^{\circ}\text{C}/\text{min}$ for dry samples, and wet samples were equilibrated at 25°C and then ramped at a rate of $1^{\circ}\text{C}/\text{min}$ to 70°C . [31] Thermogravimetric analysis (TGA) using the TA Q50-0408 (TA Instruments, New Castle, DE) was performed on samples (12.5 mg $\pm$ 2.5mg) by heating from room temperature to 500°C at $20^{\circ}\text{C}/\text{min}$. [31] Specific heating cycles are discussed in greater detail in Supplemental Materials.

2.6 Mechanical testing

Uniaxial tensile testing was performed on ASTM D638 samples using an Insight 30 Material Tester (MTS Systems Corp, Eden Prairie, MN). The extension rate was set to 5 mm/min at room temperature, and twelve samples were tested for each species. Elastic modulus, strain to failure, ultimate tensile strength, and toughness were examined for unloaded foams and the highest contrast agent-loaded samples.

2.7 Shape recovery

The volume recovery profiles were determined by expanding crimped samples ($n=3$) in a heated water bath, using a previously reported protocol.[31, 33–34] The samples were cut to 6 mm in diameter and 1 cm in length. The samples were then threaded over wire radially compressed to the smallest possible diameter (approximately 1 mm) using a ST 150-42 stent crimper (Machine Solutions, Flagstaff, AZ). The samples were heated to 100°C , compressed using the stent crimper, held isothermally for 15 minutes, and then cooled to room temperature. An image was taken before and after radial crimping. Once the samples were shape set, they were stored in a dry container for 24 hours to ensure complete shape set of the foam and to allow for any relaxation to occur. After this relaxation period, an expansion test was performed using a RO water bath heated to 37°C . The samples were submerged in the water bath, and images were taken at set time points for 30 minutes. After 30 minutes, the samples were removed from the water bath. Volume expansion was calculated using Equation 1, and volume recovery was calculated using Equation 2.[31,33–34]

$$\text{Volume expansion} = \left(\frac{\text{Recovered diameter}}{\text{Compressed diameter}} \right)^2 \quad \text{Equation 1}$$

$$\text{Volume recovery} = \left(\frac{\text{Recovered diameter}}{\text{Original diameter}} \right)^2 \cdot 100\% \quad \text{Equation 2}$$

2.8 Magnetic Resonance (MR) Imaging

SMP solid and porous samples were placed on a polycarbonate (PC) sheet, along with a nylon rod standard. Solid samples with thicknesses ranging from 2 mm to 10 mm in 2 mm increments were examined for 2% and 5% Fe additives and for 0.5% and 1% Gd. Unmodified SMP solid samples were also examined. SMP porous samples were examined using the same techniques. Both expanded and compressed SMPs were examined (6 mm diameter expanded, 0.75 mm diameter compressed). 3 cm of both compressed and expanded SMPs were strung along a nylon monofilament line and attached to the PC sheet for analysis. A 3 T MR imager (Siemens Medical Solutions USA, Inc., Malvern, PA, USA) was used for analysis, taking 2 mm slices. Spin echo and gradient echo imaging sequences were used to obtain T1 and T2 weighted scans, images were exported as DICOM images, and ImageJ (NIH, Bethesda, MD) was used for processing.[20,25,29]

2.9 X-ray Imaging

Foam samples of 6 mm in diameter and 3 cm long were compressed along nylon monofilament line and stretched in a custom frame. A GDC coil and a custom platinum coil were used as standards and placed in the frame. Solid samples were also examined (control sample, 2.0 % Fe, 5.0 % Fe, 0.5% Gd, 1.0 % Gd) blocks were cut into samples with thicknesses ranging from 2 mm to 10 mm in increments of 2 mm. A nylon tube (10 mm out diameter, 0.5 mm inner diameter, 1.0 cm length) was placed next to the samples as a reference standard. All samples were epoxied to a polycarbonate sheet.

X-ray images were acquired on a Bruker In-Vivo Xtreme multimodal preclinical imaging system (Bruker BioSpin Corp.) outfitted with a 4 MP back-thinned, back-illuminated 4MP CCD detector. X-rays were collected with an exposure time of 1.0 s, where the f-stop = 1.40, FOV = 153.0 mm, vertical and horizontal resolution = 377 ppi, and X-ray energy = 45 KVP. Images were edited using Bruker molecular imaging software.[31] The background was subtracted using an illumination correction reference obtained under the same conditions. To quantify the radio-opacity for each material, a length of 0.48 cm was selected along each material in the X-ray image as the region of interest (SI Figure 1–2). 68 samples of X-ray density (X.D.) were taken within the region of interest utilizing Bruker Molecular Imaging Software. From these measurements, a mean and standard deviation of the X.D. were calculated, and an intensity per thickness was calculated from the mean.

2.10 Degradation and extraction (ICP)

SMP foams were cut into cubes (1.5 cm sides), cleaned, and dried at 50°C for 3 days. Samples were then weighed individually and placed into labeled vials containing 3% H₂O₂ solution. Sacrificial samples were weighed at 7, 14, 21, and 28 days after cleaning and drying. The degraded samples were then incubated at 37°C in deionized (DI) water for 14 days. Samples were then immersed in 3% hydrogen peroxide (H₂O₂) solution for 30 days; sacrificial samples (n=7) were processed for mass loss every seven days. SEM images were taken of degraded samples at 30 days and compared with original samples. Samples were tested for extractable metals every seven days via extractions in DI water; solutions were tested after two weeks of immersion.

Inductively coupled plasma mass spectrometry (ICP-MS) was used to characterize the concentration of metal removed from the bulk material during incubation, as a characterization of incorporation into the backbone as well as a metric of potential toxicity. Metal concentration was determined by comparison of known concentration standards of gadolinium and iron.[20]

2.11 Cytocompatibility

Control, 1% Gd, and 5% Fe films were cut into 6 mm diameter discs using a biopsy punch. The discs were cleaned and dried then submerged in 70% ethanol for 1 hour. They were then rinsed twice with fresh dication-free phosphate buffered saline and submerged in cell culture media in 24-well plates in a humidified incubator at 37°C with 5% CO₂ for 1 hour. Cell culture media consisted of DMEM, 10% fetal bovine serum, 1% penicillin/streptomycin solution, and 0.1% fungizone. GFP-expressing 3T3 mouse fibroblasts were pipetted directly onto the surface of each disc and into tissue culture polystyrene well controls (TCPS) at 10,000 cells/cm². Discs were incubated in the cell solutions overnight to allow cell adhesion, and then they were moved to new wells with fresh media. 24 and 72 hours after seeding, images of the cells were acquired using a fluorescent microscope (Nikon Eclipse TE2000-S), and then a resazurin solution was added to the cell culture media to afford a final concentration of 5%. Cells were incubated with resazurin for 3 hours, and the increase in fluorescence at 590 nm (560 nm excitation wavelength) relative to a blank (5% resazurin in media without cells) was measured using a plate reader (Tecan Infinite M200 Pro) to quantify metabolic activity.

2.12 Statistical Analysis

Statistical comparisons between study groups was performed in Matlab 2015b using a built-in function for a two-sample t-test, *ttest2*. Specific groups of interest were compared to the control and to each other. Significance was determined for groups with a p-value less than 0.05 (5% error). Error bars displayed on all charts were calculated as standard deviations of the data sets, and sample sizes are noted in the figures where relevant. For X-ray density, data collection is discussed in greater depth elsewhere, but the presented values are averaged from approximately 200 samples, with standard deviation calculated for each sample. [32] MR imaging is the collection approximately 200 measurements per composition, each taken from 6 slices (images).

3. Results

3.1 Materials Characterization

Spectroscopic analysis (SI Figures 2–4) demonstrated slight changes indicative of incorporation of the Gd or Fe into the SMP. The typical urethane peak at 1689 cm⁻¹ was present, with slight increases (5% or less for 5.0% Fe and 1.0% Gd SMPs) in the peak intensity with additives included. The urea peak at 1650 cm⁻¹ displayed greater increases with the additives, as expected due to the carboxylic acid reactive end groups of the Gd chelate and the surface functional groups of the Fe particles.

Figure 1A and 1B displays average pore sizes of MR-visible SMPs (Fe-loaded samples in Fig 1A, Gd-loaded samples in Fig 1B), as well as the pore isotropicity (Fig 1C). Isotropicity is the ratio of the average axial diameter to the average transverse diameter. With increased loading, either Fe nps or Gd, there is a decrease in the pore sizes and an increase in isotropicity overall, although with higher Fe loading isotropicity begins to increase. As demonstrated using SEM, the control SMP pores did not have distinct regions of collapse, but with increased loading of Fe nps, greater incidences of pore collapse and strut coalescence were found (Figure 1D–1F). This is distinctly visible in 10.0% Fe (SI Fig 1I). For this reason, it was not included in further testing, apart from a control for x-ray imaging. This trend was not as prevalent with the Gd series of SMPs.

3.2 Mechanical Testing

Mechanical testing of the SMPs indicates that both the Gd and Fe SMPs had statistically improved elastic moduli compared to the control SMPs (Figure 2A). It was also found that while increased loading of Gd reduced the modulus statistically significant, the increased loading of the Fe (up to 5.0%) was not. The strain to failure (Figure 2B) of the SMPs was not affected by Gd loading, but at 2.0% Fe it had statistically improved, and with 5.0% Fe loading it was significantly decreased. There were no significant statistical differences in ultimate tensile strength or toughness for the samples (Figure 2C–2D), despite greater tensile strength for the Gd-containing SMPs.

Thermomechanical examination of the materials revealed higher T_g for dry Gd doped ($\sim 85^\circ\text{C}$) samples and lower T_g for Fe SMPs ($\sim 80^\circ\text{C}$) when compared with controls ($\sim 83.5^\circ\text{C}$ for control) (SI Figure 6). The normalized storage moduli curves support this trend, with higher loading of Fe resulting in the shortest time to relaxation and Gd resulting in the longest time to relaxation. Immersion DMA experiments confirmed this trend and demonstrated a wet T_g occurring around 57°C for plasticized SMPs (SI Table 1).

3.3 Shape Recovery

All of the MR-visible SMPs possess shape memory, determined from volumetric recovery experiments, although only the general trends are presented (Figure 3). While the Fe SMPs' recovery kinetics are not significantly different with the control samples, the Gd series displays a slower recovery behavior. As the concentration of gadolinium chelate increases, the rate of shape recovery decreases. This behavior is most likely due to the relationship between the increasing T_g and increasing chelate concentration. Strain fixity was found to be approximately 100% for all examined compositions, as was strain recovery.

These materials all display complete strain recovery when examined using volume expansion, but this requires a water bath of 50°C to achieve. At 37°C , no significant recovery will occur with this formulation, which is expected due to the measured T_g s. Tuning of the T_g , and thus the shape recovery, is achievable through alteration of the alcohol ratios and diisocyanate species used during synthesis, allowing for control of kinetics for specific applications and device needs.

3.4 MR Imaging

MR imaging revealed that all SMPs were statistically improved in both MR modalities compared with nylon rod control (Figure 4A–4B). In T1 weighted scans, 1.0% Gd and 5.0% Fe were statistically enhanced compared with the other compositions and controls (Figure 4C). For SMPs imaged using T2 weighting, low loadings of Gd were not significantly improved while all of the Fe series were enhanced (Figure 4D). Additionally, the control SMP (no additive) was superior to the nylon control, and 5.0% Fe had statistically significant intensity compared with the 1.0% Gd SMPs.

3.5 X-ray Imaging

Mean x-ray density comparisons for compressed and expanded SMPs indicated that the presence of Fe results in sufficient enhancement for visualization at several loading densities, while even the highest loading, compressed state of Gd would most likely only be barely visible (Figure 5). From this imaging, it appears that all of the examined porous SMPs possessed x-ray density greater than the background (the SMPs could be visualized) in both the expanded and crimped forms. However, only the 1.0% Gd and Fe SMPs with loadings of 3.0% or greater were statistically superior to the control porous SMP (no additive), which is supported by the intensity per area determination (Table 1).

For the nylon rod, the high x-ray density is partially attributable to the density of the polymer, but primarily this is due to the rod being a solid material compared with the highly porous structures of the SMPs. The non-porous SMP samples also displayed higher mean x-ray density, as expected (SI Figure 7), as did the 10.0% Fe SMP (SI Figure 8). Further comparison of materials using diameter yielded an approximate intensity per length value. The GDC and Pt coils possessed the greatest intensities per length (1.24 and 2.45, respectively) due to their compositions; while the SMPs are not as significantly visible as these coils, the higher loadings of Fe and 1.0% Gd are still significantly improved to the controls.

3.6 Degradation Characterization

Degradation characterization appeared to reveal that 1.0% Gd and 1.0% Fe had greater mass loss compared with other compositions (Figure 6F). This degradation was not found to be statistically significant, however. Release of additives using ICP revealed that Fe levels were consistently low, never exceeding 30 ppb (Figure 6A–E). The doses of MR contrast agents never exceed 7 µg/day (1% Gd SMP for loaded Gd), with the removal of excess, poorly reacted chelate exception of week 1 of 1% Gd. The extremely high dosage (182.9 µg/day) is a cumulative total dosage that exceeds what is found in the entire examined material and appears to be a contaminant issue. All other examined time points and species do not exceed 7µg/day for Gd, and for Fe they are less than 0.5µg/day, as determined from concentrations of metal in the degradation solution (SI Figure 9). The change in pore morphology as it relates to bulk behavior was examined using SEM (Figure 7, SI Figure 10–14). The SMPs revealed collapsing pores and overall erosion of the struts, with ruptured pores found as well.

3.7 Cytocompatibility

Figure 8 shows images of GFP-expressing 3T3s on each surface after 24 and 72 hours. Cell adhesion appears denser on control discs, Gd discs, and Fe discs than the TCPS control group, indicating good cell adhesion on the materials. Statistical increases in cell density are also observed for all groups between 24 and 72 hours, suggesting that cell proliferation is supported by all surfaces tested. Additionally, no differences were found between the SMP compositions.

4. Discussion

We have demonstrated the synthesis of MR-visible SMPs that can be processed into highly porous materials suitable for tissue scaffolds or minimally invasive medical devices. Spectroscopic analysis did not indicate significant changes in either Fe SMPs or Gd SMPs, due to the lack of chemical crosslinks and the low concentrations, respectively. SEM analysis indicates that the pore size variation decreased with increased loading (isotropicity increases with increasing additives), although this eventually results in the collapsing of polymer struts and pores during synthesis, as found in the 10.0% Fe SMPs. While 10.0% Fe would be ideal for imaging (and was found to possess the highest x-ray density of the examined materials), it possessed reduced mechanical properties, most likely linked with the collapsed macrostructure, and was not utilized further. Such collapse would limit the usefulness for medical devices or tissue scaffolds, as it could reduce cellular infiltration or result in the generation of embolic particulates during placement. Thermal analysis indicates that while there are slight alterations in the T_g due to the additive used, the differences amount to less than 1°C above or below the no additive control. This would not be a significant concern for translation of these materials into scaffolds or devices. The T_g could be lowered through the use of alternative diisocyanates, increased incorporation of TEA, or by reducing the crosslink density. This would allow for tuning the T_g (and therefore the shape recovery) around body temperature or another designated transition temperature.[34]

Variation in mechanical properties could be attributed to pore size, as well as the material heterogeneity.[34] The role of pore size was minimized through the selection of dogbone samples with similar sizes prior to testing, but due to the heterogeneity of pores, pores with sizes not falling within the standard deviation may result in stress concentration regions that alter overall properties.[34] It is known that with sufficient loading of particles, mechanical properties of polymers will be altered; in foams, this has been found to occur at weight percents around 5%, although this greatly depends on the additive and dispersion methods. [34] For example, strain at break was improved with low concentrations (2.0% Fe) of Fe nps, before decreasing at higher concentrations, indicating that the dispersion of the nps throughout the matrix may reach a critical loading near this concentration. Examination of this is beyond the scope of this study but would be useful in future work.

Rate of shape recovery was found to vary with the concentration of Gd used, while the concentration for Fe nps loading did not significantly vary the shape recovery kinetics. This can be attributed to both the diffusion into the bulk of the material, with pore size of the samples altering the rate of water inflow, and plasticization of the urethane and urea bonds. It also could be due to changes in the overall rigidity of the polyurethane structure with the

inclusion of the Gd complex, with increasing Gd chelate increasing the regional rigidity of the bonds; the physical addition of Fe nps would not alter the rigidity of the molecules, thus not altering the shape recovery kinetics. Further work is needed to examine this.

MR- and X-ray visibility of the SMPs increased with increasing concentration of additives, with both 5.0% Fe and 1.0% Gd displaying the most significant enhancement compared to the no additive control. Fe nps, compared with Gd, displayed an overall enhancement for both T1 and T2 weighted scans, although with sufficient Gd an enhancement was achieved for both weighting sequences as well. Higher loading of Fe also resulted in significant improvement of X-ray visibility. Previous studies have determined that visualization with microparticle SMP systems was possible with sufficient loadings (% loading by volume) below 10% of tungsten, barium sulfate, and zirconium oxide.[31, 35] These experiments were conducted using the same x-ray excitation conditions, allowing for comparison between not only the industry standard endovascular occlusion coils (GDC coil) but also between the microparticle and nanoparticle SMPs. GDC coils had a mean x-ray intensity of 0.62, and Pt coils (a second standard metallic coil) had a density of 0.49. While these coils possess significant intensities for their diameters (greater than 1 and 2 per mm, respectively), the crimped 4.0% Fe SMP, 5.0% Fe SMP, and 1.0% Gd SMPs would also be visible under x-ray imaging, with the added benefit of MR-imaging. None of the SMPs would be distinctly visible when expanded without further modification.

Degradation analysis indicated that the inclusion of additives did not significantly alter mass loss of the SMPs. While the majority of the Gd released from the SMPs was below 7 $\mu\text{g/day}$, the high level found to be released at week 1 was determined to be associated with experimental error. The experimental value exceeded the amount of Gd present in the sample initially. Argon oxide has the same mass as iron, which would be partially subtracted out of the samples during analysis, reducing the measured concentration.

The toxicity of gadolinium contrast agents in patients is a concern for long-term implantable devices. Previous studies have examined toxicity in patients with compromised renal function and have determined that free gadolinium released from chelating agents does not cause any clinical deleterious effect.[36] While some studies raise the concern of nephrogenic systemic fibrosis (NSF) as a possible outcome of long-term gadolinium exposure, only 400 cases worldwide were reported between 2000 and 2007.[37,38] While cyclic agents could further improve the stability and reduce risk of high Gd percentage formulations, the dose of Gd associated with the polymer is low enough to be considered safe.[39–41] Furthermore, the structure of the Gd used for these studies requires multiple radicals prior to chain scission and will be in competition with the TEA or HPED for oxidation. The gadolinium chelate contains three tertiary amines that have a fourth bond with the gadolinium atom. A study of the reaction of these chelates with hydroxy radicals indicates rapid oxidation; however, the degradation products do not lead to toxic effects.[42] Despite this, literature does suggest that the transition to macrocyclic structures and more stable chelates has removed NSF as a risk to most patients, including those with severe renal failure.[43]

Fe nps have been approved for clinical applications.[44] Polymeric coatings, such as poly(vinyl alcohol), have been demonstrated to improve biocompatibility, along with increasing the particle hydrodynamic size. For such examinations, concentrations as high as 800 mM were not found to cause toxicity.[45] Heart and lung cells were found to tolerate particles with varied surface chemistries at higher concentrations relative to brain cells.[46] For the Fe SMPs, degradation will most likely occur as the amine linkages. The particles will not be liberated with a free surface. Rather, these Fe nanoparticles will be modified with varied lengths of carbamate linkages, with end groups of amines and aldehydes/carboxylic acids. This is due to the reaction of the surface hydroxyl groups, carboxylic acids, and aldehyde groups with the isocyanate during SMP synthesis (Figure 8).[47–50] One of the notable features of Fe nps toxicity is that coated particles display reduced toxicity compared with uncoated (unmodified) particles.[48–50] Figure 9 displays the idealized incorporation of the Fe nps into the SMP bulk, which further examines the behavior of the particles upon degradation of the surrounding polymer network. With the amine linkage undergoing oxidative fragmentation, the surface of the Fe nps will be coated with polyurethanes of at least 250 Da (at the farthest oxidation step), and during early oxidation, it will be much greater in size. This will reduce long-term toxicity risk and relates to the improved cellular compatibility demonstrated with these materials.

The 30-day time period for degradation was selected in order to examine differences in the degradation and release kinetics based upon unpublished data from *in vivo* experiments of the control SMP (no additives). In porcine aneurysm *in vivo* studies with the control SMP compositions, endothelialization of the aneurysm space occurs 30 days after implantation. [35] We are able to model release rates, exposure, and mass loss based upon the material degradation in 3% H₂O₂, with the initial 30 days sufficient to determine differences between material mass loss rates. [32, 51–52] From this, and the analysis of release of metals from the SMP, we are able to extrapolate levels of metal release over the material life, with levels below cytotoxicity thresholds of concern. Comparison of these degradation rates to those of the control materials indicates that the release rates of metals will not exceed an upper threshold of 10.0 µg/day for Gd and 1.0 µg/day for Fe. According to literature, most injections of Gd are between 0.25 and 0.5 mmol/mL, although the lowest presented risk threshold was 0.07 mmol/kg body weight, or 10.99 mg/kg body weight. [43] For the presented materials, the daily exposure dose as a result of degradation would be 0.14 µg/kg body weight/day, well below the levels of currently utilized methods. For the Fe nps, it has been proposed that both the polymer coatings on the surface as well as the nature of the oxide particles themselves make them non-toxic. [44–50, 53] Injections of 2.6 mg/kg body weight have been used in imaging studies of tumors in humans without adverse effects, levels that are nearly two orders of magnitude greater than those released by the presented SMPs. [53] Further examination of the cytotoxicity and greater analysis of the degrading SMPs is the subject of an upcoming publication.

While the presented degradation studies were only conducted for 30 days, further study is necessary to assess toxicity risks over the entire life of the material. Additional cytocompatibility testing of degraded samples and model compounds could be used to validate these conclusions further, providing greater certainty of their compatibility. However, based upon the currently available literature on the toxicity of these contrast

agents, it appears that there is minimal risk from the addition of Fe nps or Gd. [36–50] In terms of literature analysis, toxic risk analysis as indicated by the material testing standard ISO 10993–17 specifies that if references are not found to a specific compound that similar compounds may be used for calculating acceptable exposure thresholds as long as an appropriate uncertainty factor is utilized or acknowledged. [53] While this factor is dependent upon the analysis and is not compound specific, for structures such as mono-cyclic gadolinium chelates that have well studied *in vivo* behaviors and are currently in use in medical devices this factor is low (1 to 2x change in the threshold level). [53] Further work is necessary to confirm this, as well as for FDA approval for clinical translation of a device, but the presented results indicate that these methods are promising methods of enhancing MR-visibility without inducing significant risk to patients.

5. Conclusions

We demonstrated the enhancement of MR-visibility in polyurethane SMPs through the inclusion of Fe nps and Gd chelates. These materials could be incorporated into a number of configurations as either a tissue scaffold material or for intravascular medical devices. Their enhanced visibility could allow for delivery and long-term monitoring of polymeric implants without the need for harmful ionizing radiation. The enhancement of x-ray density was achieved more noticeably with the Fe series, and both MR-visible compositions lacked altered shape recovery properties in the examined additive concentration ranges. These materials displayed excellent cytocompatibility, supporting cell adhesion and showing no reduction in proliferation based on MR-visible species. Long term, the materials do not result in concerning levels of metals released, which is most noticeable for the Gd series, and a toxicological assessment of the degradation products compared with literature indicates that these materials are promising as implantable tissue scaffolds and intravascular devices. Comparison of Gd and Fe SMPs in terms of absolute performance using the presented results indicates that the Fe series as the obvious choice for further study and potential translation, as the presented properties are similar (thermal, shape recovery, cytocompatibility) or enhanced (x-ray visibility, MR-visibility, elastic modulus and strain to failure). However, some applications may require greater time to shape recovery, indicating that combinations of Gd with Fe may find use in device applications. An ideal composition is in fact entirely dependent on the desired application, which would indicate that a variety of properties are necessary to be tuned in order to achieve material compositions that meet the needs of several device designs. This, coupled with the performance results as well as initial biocompatibility, reveals the promise of the SMPs as biomaterials with multiple imaging modalities and that the presented technique of increasing MR-visibility in these SMPs warrants further examination.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The authors would like to thank the NASA H Jenkins Fellowship for funding, the Laboratory for Synthetic-Biologic Interactions for equipment use and time, and the Texas Institute for Preclinical Studies (TIPS) for equipment, time,

and expertise. The authors are grateful to Lauren Harrell for review of the manuscript and Rachel Johnson for her work with MRI imaging experiments. This research did not receive any specific grant from funding agencies in the public, commercial, or not-for-profit sectors.

References

1. Rogers T, Lederman RJ. Interventional CMR: Clinical applications and future directions. *Curr Cardiol Rep.* 2015; 17(5):31.doi: 10.1007/s11886-015-0580-1 [PubMed: 25894793]
2. Lederman RJ. Cardiovascular interventional MRI. *Circulation.* 2005; 112(19):3009.doi: 10.1161/CIRCULATIONAHA.104.531368 [PubMed: 16275886]
3. Tzifa A, Kromback GA, Kramer N, Kruger S, Schutte A, von Walter M, Schaeffter T, Qureshi S, Krasemann T, Rosenthal E, Schwartz CA, Varma G, Buhl A, Kohlmeier A, Bucker A, Gunther RW, Razavi R. Magnetic resonance-guided cardiac interventions using magnetic resonance-compatible devices: a preclinical study and first-in-man congenital interventions. *Circ Cardiovas Interv.* 2010; 3:585.doi: 10.1161/CIRCINTERVENTIONS.110.957209
4. Buecker A, Spuentrup E, Grabitz R, Freudenthal F, Muehler EG, Schaeffter T, van Vaals JJ, Gunther RW. Magnetic resonance-guided placement of atrial septal closure device in animal model of patent foramen ovale. *Circulation.* 2002; 106:511.doi: 10.1161/01.CIR.0000023624.88708.62 [PubMed: 12135954]
5. Fisher DC, Fisher EA, Budd JH, Rosen SE, Goldman ME. The incidence of patent foramen ovale in 1000 consecutive patients: a contrast transesophageal echocardiography study. *Chest.* 1995; 107:1504. [PubMed: 7781337]
6. Di Tullio MR, Jin Z, Russo C, Elkind MS, Rundek T, DeCarli C, Wright CB, Homma S, Sacco RL. Patent foramen ovale, subclinical cerebrovascular disease, and ischemic stroke in a population-based cohort. *Cardiology.* 2013; 62(1):35.doi: 10.1016/j.jacc.2013.03.064
7. Agnetti A, Carano N, Sani E, Tchana B, Allegri V, Bernasconi S, Squarcia U. Cryptogenic stroke in children: possible role of patent foramen ovale. *Neuropediatrics.* 2006; 37:53.doi: 10.1055/s-2006-923026 [PubMed: 16541369]
8. Rodan L, McCrindle BW, Manlhiot C, MacGregor DL, Askalan R, Moharir M, deVeber G. Stroke recurrence in children with congenital heart disease. *Ann Neurol.* 2012; 72(1):103–111. DOI: 10.1002/ana.23574 [PubMed: 22829272]
9. Nazarian S, Koldaivelu A, Zviman MM, Meininger GR, Kato R, Susil RC, Roguin A, Dickfeld TL, Ashikaga H, Calkins H, Berger RD, Bluemke DA, Lardo AC, Halperin HR. Feasibility of real-time magnetic resonance imaging for catheter guidance in electrophysiology studies. *Circulation.* 2008; 118(3):223.doi: 10.1161/CIRCULATIONAHA.107.42452 [PubMed: 18574048]
10. Metcalfe A, Desfaits AC, Salazkin I, Yahia L, Sokolowski WM, Raymond J. Cold hibernated elastic memory foams for endovascular interventions. *Biomaterials.* 2003; 24(3):491. [PubMed: 12423604]
11. Sokolowski W, Metcalfe A, Hayashi S, Yahia L, Raymond J. Medical applications of shape memory polymers. *Biomed Mater.* 2007; 2(1)doi: 10.1088/1748-6041/2/1/S04
12. Zhang D, George LJ, Petersen KM, Jimenez-Vergara AC, Hahn MS, Grunlan MA. A bioactive “self-fitting” shape memory polymer scaffold with potential to treat maxillo-facial bone defects. *Acta Biomater.* 2014; 10(11):4597.doi: 10.1016/j.actbio.2014.07.020 [PubMed: 25063999]
13. Sharifi S, van Kooten TG, Kranenburg JC, Meij BP, Behl M, Lendlein A, Grijpma DW. An annulus fibrosus closure device based on a biodegradable shape-memory polymer network. *Biomater.* 2013; 34(33):8105–8113. DOI: 10.1016/j.biomaterials.2013.07.061
14. Tseng L, Mather PT, Henderson JH. Shape-memory-actuated change in scaffold fiber alignment directs stem cell morphology. *Acta Biomater.* 2013; 9(11):8790.doi: 10.1016/j.actbio.2013.06.043 [PubMed: 23851156]
15. Wilson TS, Bearinger JP, Herberg JL, Marion JE, Wright WJ, Evans CL, Maitland DJ. Shape memory polymers based on uniform aliphatic urethane networks. *J Appl Polym Sci.* 2007; 106(1): 540.doi: 10.1002/app.26503

16. Liu J, Ding D, Geng L, Liu B. PEGylated conjugated polyelectrolytes containing 2,1,3-benzoxadiazole units for targeted cell imaging. *Polym Chem.* 2012; 3:1567.doi: 10.1039/C2PY20113E
17. Zhy D, Liu F, Ma L, Liu D, Wang Z. Nanoparticle-based systems for T1-weighted magnetic resonance imaging contrast agents. *Int J Mol Sci.* 2013; 14(5):10591.doi: 10.3390/ijms120510591 [PubMed: 23698781]
18. Howes P, Green M, Bowers A, Parker D, Varma G, Kallumadil M, Hughes M, Warley A, Brain A, Botnar R. Magnetic conjugated polymer nanoparticles as bimodal imaging agents. *J Am Chem Soc.* 2010; 132(28):9833.doi: 10.1021/ja1031634 [PubMed: 20572665]
19. Reynolds CH, Annan N, Beshah K, Huber JH, Shaber SH, Lenkinski RE, Wortman JA. Gadolinium-loaded nanoparticles: new contrast agents for magnetic resonance imaging. *J Am Chem Soc.* 2000; 122:8940.doi: 10.1021/ja001426g
20. Jiang B, Perrin L, Kats D, Meade T, Ameer G. Enabling non-invasive assessment of an engineered endothelium on ePTFE vascular grafts without increasing oxidative stress. *Biomater.* 2015; 69:110–120. DOI: 10.1016/j.biomaterials.2015.07.064
21. Kaittanis C, Shaffer TM, Bolaender A, Appelbaum Z, Appelbaum J, Chiosis G, Grimm J. Multifunctional MRI/PET nanobeacons derived from the in situ self-assembly of translational polymers and clinical cargo through coalescent intermolecular forces. *Nano Lett.* 2015; 15(12): 8032.doi: 10.1021/acs.nanolett.5b03370 [PubMed: 26540670]
22. Sowers MA, McCombs JR, Wang Y, Paletta JT, Morton SW, Dreaden EC, Boska MD, Ottaviani MF, Hammond PT, Rajca A, Johnson JA. Redox-responsive branched-bottlebrush polymers for in vivo MRI and fluorescence imaging. *Nat Comm.* 2014; 5:5460.doi: 10.1038/ncoms6460
23. Letouzey V, Huberlant S, Cornille A, Blanquer S, Guillaume O, Lemaire L, Garric X, de Tayrac R. Tolerance and long-term MRI imaging of gadolinium-modified meshes used in soft organ repair. *PLOS One.* 2015; 10(3)doi: 10.1371/journal.pone.0120218
24. van der Zande M, Sitharaman B, Walboomers XF, Tran L, Ananta JS, Veltien A, Wilson LJ, Alava JI, Heerschap A, Mikos AG, Jansen JA. In vivo magnetic resonance imaging of the distribution pattern of gadonanotubes released from a degrading poly(lactic-co-glycolic acid)scaffold. *Tiss Eng C Mater.* 2011; 17(1):19.doi: 10.1089/ten.tec.2010.0089
25. Wang X, Niu D, Wu Q, Su T, Liu X, Zhang S, Wang Q. Iron oxide/manganese oxide co-loaded hybrid nanogels as pH-responsive magnetic resonance contrast agents. *Biomater.* 2015; 53:349–357. DOI: 10.1016/j.biomaterials.2015.02.101
26. Mohr R, Kratz K, Weigel T, Lucka-Gabor M, Moneke M, Lendlein A. Initiation of shape-memory effect by inductive heating of magnetic nanoparticles in thermoplastic polymers. *PNAS.* 2011; 103(10):3540.doi: 10.1073/pnas.0600079103
27. Lee DE, Koo H, Sun IC, Ryu JH, Kim K, Kwon IC. Multifunctional nanoparticles for multimodal imaging and theragnosis. *Chem Soc Rev.* 2012; 41:2656.doi: 10.1039/C2CS15261D [PubMed: 22189429]
28. Barrow M, Taylor A, Murray P, Rosseinsky MJ, Adams DJ. Design considerations for the synthesis of polymer coated iron oxide nanoparticles for stem cell labelling and tracking using MRI. *Chem Soc Rev.* 2015; 44:6733.doi: 10.1039/C5CS00331H [PubMed: 26169237]
29. Riegler J, Liew A, Hynes SO, Ortega D, O'Brien T, Day RM, Richards T, Sharif F, Pankhurst QA, Lythgoe MF. Superparamagnetic iron oxide nanoparticle targeting of MSCs in vascular injury. *Biomater.* 2013; 34(8):1987–1994. DOI: 10.1016/j.biomaterials.2012.11.040
30. Duirk SE, Lindell C, Cornelison CC, Kormos J, Ternes TA, Attene-Ramos M, Osio J, Wagner ED, Plewa MJ, Richardson SD. Formation of toxic iodinated disinfection by-products from compounds used in medical imaging. *Environ Sci Technol.* 2011; 45(16):6845.doi: 10.1021/es200983f [PubMed: 21761849]
31. Weems AC, Raymond JE, Wacker KT, Gustafson TP, Keller B, Wooley KL, Maitland DJ. Examination of radio-opacity enhancing additives in shape memory polyurethane foams. *J Appl Polym Sci.* 2015; 132(23)doi: 10.1002/app.42054
32. Weems AC, Wacker KT, Carrow JK, Boyle AJ, Maitland DJ. Degradation of thermoset shape memory polyurethanes for vascular occlusion applications. Submitted.

33. Singhal P, Small W, Cosgriff-Hernandez E, Maitland DJ, Wilson TS. Low density biodegradable shape memory polyurethane foams for embolic biomedical applications. *Acta Biomater.* 2014; 10(1):67.doi: 10.1016/j.actbio.2013.09.027 [PubMed: 24090987]
34. Weems AC, Boyle AJ, Maitland DJ. Two-year performance study of porous, thermoset, shape memory polyurethanes intended for vascular medical devices. *Smart Mater Struct.* 2017; 26(3)doi: 10.1088/1361-665X
35. Rodriguez JN, Yu Y, Miller MW, Wilson TS, Hartman J, Clubb FJ, Gentry B, Maitland DJ. Opacification of shape memory polymer foam designed for treatment of intracranial aneurysms. *Ann Biomed Eng.* 2012; 40(4):883.doi: 10.1007/s10439-011-0468-1 [PubMed: 22101759]
36. Arsenault TM, King BF, Marsh JW, Goodman JA, Weaver AL, Wood CP, Ehman RL. Systemic gadolinium toxicity in patients with renal insufficiency and renal failure: retrospective analysis of an initial experience. *Mayo Clin Proc.* 1996; 71(12):1150. [PubMed: 8945485]
37. Thakral C, Alhariri J, Abraham JL. Long-term retention of gadolinium in tissues from nephrogenic systemic fibrosis patient after multiple gadolinium-enhanced MRI scans: case report and implications. *Cont Med Molecul Imag.* 2007; 2:199.
38. Grobner T. Gadolinium a specific trigger for the development of nephrogenic fibrosing dermopathy and nephrogenic systemic fibrosis. *Nephrol Dial Transplant.* 2006; 21:1104.doi: 10.1093/ndt/gfk062
39. Perazella MA. Current status of gadolinium toxicity in patients with kidney disease. *Clin J Am Soc Nephrol.* 2009; 4:461.doi: 10.2215/CJN.06011108 [PubMed: 19201920]
40. Bartolini ME, Pekar J, Chettle DR, McNeill F, Scott A, Sykes J, Prato FS, Moran GR. An investigation of the toxicity of gadolinium based MRI contrast agents using neutron activation analysis. *Mag Reson Imag.* 2003; 21:541.doi: 10.1016/S0730-725X(03)00081-X
41. Sam AD, Morsach MD, Collins J, Song G, Chen R, Pereles FS. Safety of gadolinium contrast angiography in patients with chronic renal insufficiency. *J Vas Surg.* 2003; 38:313.
42. Cyris M, Knolle W, Richard J, Dopp E, von Sonntag C, Schmidt TC. Reaction of gadolinium chelates with ozone and hydroxyl radicals. *ACS Environ Sci Tech.* 2013; 47:9942.doi: 10.1021/es402219u
43. Ramalho J, Semelka RC, Ramalho M, Nunes RH, AlObaidy M, Castillo M. Gadolinium based contrast agent accumulation and toxicity: an update. *Amer J Neuroradio.* 2015; doi: 10.3174/ajnr.A4615
44. Gould P. Nanomagnetism shows *in vivo* potential. *Nanotoday.* 2006; 1(4):34.doi: 10.1016/S1748-0132(06)70115-3
45. Mahmoudi M, Simchi A, Milani AS, Stoeve P. Cell toxicity of superparamagnetic iron oxide nanoparticles. *J Coll Interf Sci.* 2009; 336(2):510.doi: 10.1016/j.jcis.2009.04.046
46. Mahmoudi M, Lauren S, Shokrogozar MA, Hosseinkhani M. Toxicity evaluations of superparamagnetic iron oxide nanoparticles: cell viabilities versus physicochemical properties of nanoparticles. *ACSNano.* 2011; 5(9):7263.doi: 10.1021/nn2021088
47. Turcheniuk K, Tarasevych AV, Kukhar VP, Boukherroub R, Szunerits S. Recent advances in surface chemistry strategies for the fabrication of functional iron oxide based magnetic nanoparticles. *Nanoscale.* 2013; 5:10729.doi: 10.1039/c3nr04131j [PubMed: 24091568]
48. Misra A, Petryk AA, Strawbridge RR, Hoopes PJ. Macroscopic and microscopic biodistribution of intravenously administered iron oxide nanoparticles. *Energy based Treatment of Tissue and Assessment VIII, Proc of SPIE.* 2015; :9326.doi: 10.1117/12.2082989
49. Volkovova K, Handy RD, Staruchova M, Tulinska J, Kebis A, Pribojova J, Ulicna O, Kucharska J, Dusinska M. Health effects of selected nanoparticles in vivo: liver function and hepatotoxicity following intravenous injection of titanium dioxide and Na-oleate-coated iron oxide nanoparticles in rodents. *Nanotox.* 2015; 9(51):95.doi: 10.3109/17435390.2013.815285
50. Chen R, Ling D, Zhao L, Wang S, Liu Y, Bai R, Baik S, Zhao Y, Chen C, Hyeon T. Parallel comparative studies on mouse toxicity of oxide nanoparticle and gadolinium based T1 MRI contrast agents. *ACSNano.* 2015; 9(12):12425.doi: 10.1021/acsnano.5b05783
51. Association for the Advancement of Medical Instrumentation. Biological evaluation of medical devices-Part 13: Identification and quantification of degradation products from polymeric medical devices. Arlington, VA, USA: 2003. ANSI/AAMI/ISO 10993-17.

52. Christenson EM, Dadsetan M, Wiggins M, Anderson JM, Hiltner A. Poly(carbonate urethane) and poly(ether urethane) biodegradation: In vivo studies. *J Biomed Mater Res A*. 2004; 69A:407–416. DOI: 10.1002/jbm.a.30002
53. Association for the Advancement of Medical Instrumentation. Biological evaluation of medical devices-Part 17: Methods for the establishment of allowable limits for leachable substances. Arlington, VA, USA: 2003. ANSI/AAMI/ISO 10993-17.

Author Manuscript

Author Manuscript

Author Manuscript

Author Manuscript

Statement of Significance

Shape memory polymers (SMPs) are polymeric materials with unique shape recovery abilities that are being considered for use in biomedical and medical device applications. This paper presents a methodology for the development of MR and X-ray visible SMPs using either a chemically loaded or physical loaded method during polymer synthesis. Such knowledge is imperative for the development and clinical application of SMPs for biomedical devices, specifically for minimally-invasive vascular occlusion treatments, and while there are studies pertaining to the visibility of polymeric particles, little work has been performed on the utility of biomaterials intended for medical devices and the impact of how adding multiple functionalities, such as imaging, may impact material safety and degradation.

Figure 1. Pore diameter comparisons of MR-visible SMPs, displaying pore sizes of Fe (A) and Gd (B) containing SMPs. The relative isotropicity of the pores is displayed in panel C. SEMs of MR-visible SMPs are displayed; (D) no additive, (E) 1.0% Gd, (F) 5.0% Fe.

Figure 2. Mechanical properties of MR-visible SMPs, displaying elastic moduli (A), strain at break (B), ultimate tensile strength (C), and toughness (D) of selected formulations. (n=8) * indicates statistical difference compared with the control SMPs (p< 0.05).

Figure 3.
Shape recovery of SMPs at 50°C examined over 30 minutes. (n=3)

Figure 4. MR-imaging characterization of SMPs using both T1 (A, C) and T2 (B, D) weighted imaging. Actual diameter of sample is represented in C as a dotted red line. * indicates statistical difference compared with the control SMPs ($p < 0.05$).

Figure 5.

X-ray density of MRI-visible SMPs; (A) Iron oxide-doped SMP in crimped state, (B) Iron oxide-doped SMP in expanded state, (C) Gadolinium chelate-doped SMP in crimped state, (D) Gadolinium chelate-doped SMP in expanded state. (E) The x-ray image of the expanded and crimped SMPs along with the control nylon rod; an example of the regions of interest is denoted by a white box. * indicates statistical difference compared with the control SMPs ($p < 0.05$).

Figure 6.

An approximation of dose per day of MR contrast agents determined from ICP analysis of metals extracted from degraded SMPs. (A) No Additive SMP, (B) 0.5% Gd SMP, (C) 1.0% Gd SMP, (D) 1.0% Fe SMP, (E) 5.0% Fe SMP. Gravimetric changes of the bulk material (F) and the change in gel fraction were also examined (insert, F) over the same four-week period. (n=7)

Figure 7. SEM images of original (A–C) and degraded SMPs at four weeks (D–F), displaying the difference between the control (A, D), 5.0% Fe (B, E), and 1.0% Gd (C,F) SMPs.

Figure 8.

10x images acquired of GFP-expressing 3T3s on control discs (A, E), 1% Gd discs (B,F), 5% Fe discs (C,G), and TCPS wells (D,H) 24 (A–D) and 72 (E–H) hours after seeding (J). Increases in relative fluorescence units (RFU) per cm² after 3-hour incubation with 5% resazurin solution for GFP-expressing 3T3s 24 and 72 hours after seeding on control discs (Ctrl), 1% Gd discs, 5% Fe discs, or TCPS wells. * indicates statistical difference compared with the control SMPs (p < 0.05).

Figure 9.

An idealized schematic illustration presenting the initial surface hydroxyl groups of the Fe nps, the integration of the nps into the urethane network via reaction of the isocyanates with surface hydroxyls, and the degradation and subsequent dissolution of the particle with urethane linkages and primary amine or aldehyde endgroups due to network oxidation. Yellow denotes hydroxyl groups, blue denotes urethane linkages, green is tertiary amine linkages, and red indicates primary amine or aldehyde endgroups.

Table 1

Mean X-ray density of select MR-visible SMP compositions in expanded and crimped states.

Species	Mean X-ray Density	Intensity/mm
Nylon Control	1.46 ± 0.05	0.15
No Additive (crimped)	0.52 ± 0.03	0.55
No Additive (expanded)	0.40 ± 0.04	0.06
0.5% Gd (crimped)	0.52 ± 0.1	0.58
0.5% Gd (expanded)	0.39 ± 0.06	0.07
1.0% Gd (crimped)	0.52 ± 0.01	0.58
1.0% Gd (expanded)	0.40 ± 0.05	0.07
0.5% Fe (crimped)	0.53 ± 0.02	0.58
0.5% Fe (expanded)	0.40 ± 0.03	0.07
2% Fe (crimped)	0.53 ± 0.03	0.53
2% Fe (expanded)	0.40 ± 0.02	0.07
5.0% Fe (crimped)	0.61 ± 0.02	0.68
5.0% Fe (expanded)	0.43 ± 0.02	0.09
GDC Coil	0.62 ± 0.03	1.24
Pt Coil	0.49 ± 0.05	2.45