Published in final edited form as:

Nat Phys. 2018 August ; 14(8): 837–841. doi:10.1038/s41567-018-0134-8.

Pressure tuning of light-induced superconductivity in K_3C_{60}

A. Cantaluppi^{#1,2}, M. Buzzi^{#1}, G. Jotzu¹, D. Nicoletti^{1,2}, M. Mitrano¹, D. Pontiroli³, M. Riccò³, A. Perucchi⁴, P. Di Pietro⁴, and A. Cavalleri^{1,2,5,*}

¹Max Planck Institute for the Structure and Dynamics of Matter, Hamburg, Germany

²The Hamburg Centre for Ultrafast Imaging, Hamburg, Germany

³Dipartimento di Scienze Matematiche, Fisiche e Informatiche, Università degli Studi di Parma, Parma, Italy

⁴INSTM UdR Trieste-ST and Elettra–Sincrotrone Trieste, Trieste, Italy

⁵Department of Physics, Oxford University, Clarendon Laboratory, Oxford UK

These authors contributed equally to this work.

Abstract

Optical excitation at terahertz frequencies has emerged as an effective means to dynamically manipulate complex materials. In the molecular solid K_3C_{60} , short mid-infrared pulses transform the high-temperature metal into a non-equilibrium state with the optical properties of a superconductor. Here we tune this effect with hydrostatic pressure and find that the superconducting-like features gradually disappear at around 0.3 GPa. Reduction with pressure underscores the similarity with the equilibrium superconducting phase of K_3C_{60} , in which a larger electronic bandwidth induced by pressure is also detrimental for pairing. Crucially, our observation excludes alternative interpretations based on a high-mobility metallic phase. The pressure dependence also suggests that transient, incipient superconductivity occurs far above the 150 K hypothesised previously, and rather extends all the way to room temperature.

Resonant optical excitation of infrared-active phonon modes can drive the crystal lattice of solids nonlinearly¹, excite other orders coherently², switch lattice polarization³, drive insulator-to-metal⁴ or magnetic transitions⁵, and even induce transient superconductivity above equilibrium T_c ^{6,7}. In the potassium-doped fulleride K_3C_{60} , a superconductor at temperatures below $T_c = 20$ K, excitation of local molecular vibrations was shown to induce superconducting-like optical properties in the high temperature metal ($T > T_c$)⁸. Key

Users may view, print, copy, and download text and data-mine the content in such documents, for the purposes of academic research, subject always to the full Conditions of use:http://www.nature.com/authors/editorial_policies/license.html#terms

* andrea.cavalleri@mpsd.mpg.de.

Author contributions

A. Cav. conceived the project together with M.M. and A. Can. The time-resolved THz setup was built by A. Can. and M.B., who both performed the pump–probe measurements and analysed the data with support of G.J. and D.N. The equilibrium optical properties were measured by A. Can. and M.M., with support of A.P. and P.D.P., and were then analysed by A. Can. and M.B. The samples were grown and characterized by D.P. and M.R. The manuscript was written by A. Can., M.B., D.N., and A. Cav., with input from all co-authors.

Data Availability

The datasets generated and analysed during the current study are available from the corresponding author on reasonable request.

features of this state are a ~ 12 -meV-wide gap in the resistive optical conductivity $\sigma_1(\omega)$, twice as large as the equilibrium 6-meV-wide superconducting gap, and a divergent low-frequency imaginary conductivity $\sigma_2(\omega)$, indicative of large carrier mobility. This state was found to extend to at least 100 K, hence up to temperature scales far in excess of equilibrium T_c (20 K). For $T > 100$ K, a partially gapped state was reported. In this higher temperature regime, the light-induced state can be interpreted either as a high mobility metal “en route” to a transient superconducting state, or as an incipient superconductor, which is only partially coherent.

Many theoretical mechanisms have been invoked to explain these observations, ranging from a dynamical reduction of the electronic bandwidth⁹, to the parametric amplification of the pairing instability¹⁰ and to electron attraction¹¹ in vibrationally excited molecular sites^{12,13}. Recent experiments in bilayer graphene are consistent with some of these suggestions^{9,10}, as the optical excitation of a similar vibrational mode as that driven in K_3C_{60} appears to increase the electron phonon interaction¹⁴. Finally, recent theoretical work has raised the possibility that photo-stimulation may involve optical excitation and cooling of above-gap thermal quasi-particles into a super-excitonic state with high electronic heat capacity¹⁵.

The face-centred cubic structure of doped fullerenes A_3C_{60} is shown in Fig. 1a. Three electrons are donated by the alkali atoms to each C_{60} molecule, which then form three narrow, half-filled bands near the Fermi level. Figure 1c shows how the equilibrium superconducting transition appears in the steady-state optical properties of K_3C_{60} , measured above and below the critical temperature $T_c = 20$ K. When cooling metallic K_3C_{60} (red curves) below T_c , one observes large changes in the optical properties: a saturation of the low-frequency reflectivity to $R = 1$, a 6 meV gap in the real part of the optical conductivity $\sigma_1(\omega)$, and a $1/\omega$ divergence in the imaginary part $\sigma_2(\omega)$ ^{16,8} (blue curves).

As superconductivity in K_3C_{60} emerges from a combination of Jahn-Teller intramolecular distortions and electronic correlations^{17,18,19}, it is natural to explore the response of the material to direct excitation of optically accessible vibrational modes. In Fig. 1d we report the optical properties of polycrystalline powders of K_3C_{60} , 1 ps after the excitation tuned to “on ball” infrared active modes of T_{1u} symmetry at 170 meV energy (7.3 μm wavelength), whose atomic distortion is displayed in Fig. 1b. At this frequency, strongly correlated metallic carriers are also excited, as the radiation is also resonant with a broad absorption peak extending from ~ 40 to 200 meV²⁰, whose precise origin is still unclear¹⁵. A broadband probe pulse was used to detect the light-induced changes in the optical reflectivity and complex optical conductivity between 1.6 and 7 THz (6.5 – 29 meV) using THz-time-domain-spectroscopy. Starting from the unperturbed metallic state at 100 K (red curves), we observed an increase in the reflectivity, which saturates to $R = 1$ for all probe photon energies below ~ 12 meV, a gapped $\sigma_1(\omega)$ and a divergent $\sigma_2(\omega)$. These data confirm the results of Ref. 8, but were recorded with an improved apparatus, involving higher pump fluence and a broader probe bandwidth (see Supplementary Information S3).

In this paper, we study how the features reported in Fig. 1d change with the application of hydrostatic pressure. At equilibrium, the application of pressure reduces the superconducting

transition temperature T_c , because of the increase in the electronic bandwidth when the intermolecular spacing is reduced^{21,22}. As shown in Fig. 2, the size of the optical gap ($2\gamma_0$) and the critical temperature^{23,24} decay linearly already at relatively modest pressures. Due to the low bulk modulus (28 GPa²⁴), a pressure of 3 GPa reduces the superconducting gap to less than half of the ambient-pressure value, as the electronic bandwidth increases by $\sim 25\%$ ²⁵.

Figure 3 displays snapshots of the measured optical reflectivity $R(\omega)$ at the sample-diamond interface, along with complex conductivity spectra, $\sigma_1(\omega)$ and $\sigma_2(\omega)$, for different values of static pressure. The exact pressure was measured with calibrated ruby fluorescence (see Supplementary Information S3). In each panel, the red and blue curves trace the optical properties of the equilibrium metal and those of the non-equilibrium state induced by photo-excitation, respectively. For pressures up to 0.17 GPa (Fig. 3a-c) the transient optical response of K_3C_{60} is similar to that observed at ambient pressure, with a reflectivity approaching $R=1$, a gapped $\sigma_1(\omega)$ and a divergent $\sigma_2(\omega)$ toward low frequencies. However, some spectral weight is also found in $\sigma_1(\omega)$ at low energies, indicative of reduced coherence.

As the applied pressure increases, a stronger suppression of the light-induced changes in both the reflectivity and complex optical conductivity is observed (Fig. 3d-e). Above 0.3 GPa the enhancement in the reflectivity is clearly less pronounced, and a progressively broader Drude peak appears at low frequency in the $\sigma_1(\omega)$ spectrum.

The reduction in light-induced coherence observed as a function of pressure is clearly not compatible with what expected for a light-induced metallic state, as a lattice compression in a metal is typically associated with larger electronic bandwidth, smaller effective mass and larger mobility. This is for example evident when analysing the equilibrium metallic properties in the red curves of Fig. 3 (see also Supplementary Information S2), where one observes larger plasma frequencies ω_p with increasing pressure.

In Fig. 4a-c we report the fractional spectral weight loss for frequencies inside the gapped region of the spectrum, obtained by integrating $\sigma_1(\omega)$ between 6.5 and 12.9 meV for different pressures and base temperatures of 100 K, 200 K and 300 K (see Supplementary Information S9 for full data sets at 200 and 300 K). Shaded blue areas indicate the pressure-temperature ranges where the light-induced state is gapped. Overall, the light-induced gap fills already at moderate pressure values, becoming even smaller for increasing temperature. For $P \gtrsim 0.3$ GPa, the pressure dependence of the light-induced effects is strongly reduced.

Fits to the optical properties of Fig. 3 make the qualitative analysis above quantitatively significant (see Supplementary Information S10). By fitting the transient optical response of K_3C_{60} , we extrapolated the value of the low frequency optical conductivity $\sigma_0 = \lim_{\omega \rightarrow 0} \sigma_1(\omega)$. To compare both superconducting-like and metallic-like states in a consistent fashion, we used a Drude-Lorentz fit for the entire regime, in which σ_0 was allowed to float from finite (metal) to infinite values (perfect conductor), and a single lorentzian was used to capture the mid-infrared absorption band extending from 40 to 200 meV.

The results of this analysis are summarised in Fig. 5a-c, where we report the pressure dependence of σ_0 for three temperatures (100 K, 200 K, and 300 K). The red squares

describe the pressure dependence for the optical properties of the equilibrium metal, while the blue diamonds that of the photoexcited state. As shown in these plots, the equilibrium metallic conductivity increases with applied pressure. On the contrary, two pressure regimes are found for the light-induced state, one in which σ_0 *decreases* for small pressures ($d\sigma_0/dP < 0$, blue shaded area) and one where it eventually *increases* slightly for higher pressures ($d\sigma_0/dP > 0$, yellow shaded area). Several indications can be extracted from these data.

First, as mentioned above, from the optical properties alone reported in Ref. 8, one could not uniquely differentiate a superconductor from a perfect conductor, as optics only identifies the density of charge carriers and the scattering rate. The hydrostatic pressure dependence reported here adds crucial information. At low pressures, the photoexcited state has clear superconducting-like pressure dependence ($d\sigma_0/dP < 0$), whereas for higher pressures the response is clearly metal-like ($d\sigma_0/dP > 0$). Furthermore, at the high pressures σ_0 of the photo-excited state follows the same slope as that of the equilibrium metal.

In this context the results reported for high temperatures ($T = 200$ K and $T = 300$ K) are surprising. In that temperature range, a high mobility metallic state was proposed to interpret the data of Ref. 8. However, this interpretation was also not unique, as a superconducting-like state with progressively lower coherence could also have explained the data. Figure 5 suggests that in the low pressure regime the $d\sigma_0/dP < 0$ behaviour is retained all the way to 300 K, hinting that some incipient features of transient superconductivity may already be present up to room temperature.

These observations also provide guidance for a microscopic explanation of our results. Indeed, as summarised in Fig. 6, one finds a very strong dependence of the light-induced optical conductivity on pressure, and for the higher-pressure ranges (smaller lattice constants) the metallic phase (yellow) is stabilised. Our data sets an important benchmark for theories of photo-induced superconductivity^{9,10,11,15,27,28}, which should reproduce the observed pressure dependence. Figure 6 also indicates a clear path for future research in the broader context of A_3C_{60} superconductivity, showing on the right-hand side the region of the phase diagram still to be accessed (panel b), with the interesting perspective of optimizing light-induced superconductivity further, for even larger lattice spacing.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgments

The research leading to these results received funding from the European Research Council under the European Union's Seventh Framework Programme (FP7/2007-2013)/ERC Grant Agreement no. 319286 (QMAC). We acknowledge support from the Deutsche Forschungsgemeinschaft via the excellence cluster "The Hamburg Centre for Ultrafast Imaging - Structure, Dynamics and Control of Matter at the Atomic Scale" and the priority program SFB925. M. Buzzi acknowledges financial support from the Swiss National Science Foundation through an Early Postdoc Mobility Grant (P2BSP2_165352).

References

1. Först M, et al. Nonlinear phononics as an ultrafast route to lattice control. *Nat Phys.* 2011; 7:854–856.
2. Nova TF, et al. An effective magnetic field from optically driven phonons. *Nat Phys.* 2017; 13:132–136.
3. Mankowsky R, von Hoegen A, Först M, Cavalleri A. Ultrafast Reversal of the Ferroelectric Polarization. *Phys Rev Lett.* 2017; 118:197601. [PubMed: 28548509]
4. Rini M, et al. Control of the electronic phase of a manganite by mode-selective vibrational excitation. *Nature.* 2007; 449:72–74. [PubMed: 17805291]
5. Först M, et al. Driving magnetic order in a manganite by ultrafast lattice excitation. *Phys Rev B.* 2011; 84:241104(R).
6. Hu W, et al. Optically enhanced coherent transport in $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$ by ultrafast redistribution of interlayer coupling. *Nat Mater.* 2014; 13:705–711. [PubMed: 24813422]
7. Mankowsky R, et al. Nonlinear lattice dynamics as a basis for enhanced superconductivity in $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$. *Nature.* 2014; 516:71–73. [PubMed: 25471882]
8. Mitrano M, et al. Possible light-induced superconductivity in K_3C_{60} at high temperature. *Nature.* 2016; 530:461–464. [PubMed: 26855424]
9. Coulthard JR, Clark SR, Al-Assam S, Cavalleri A, Jaksch D. Enhancement of superexchange pairing in the periodically driven Hubbard model. *Phys Rev B.* 2017; 96:85104.
10. Knap M, Babadi M, Refael G, Martin I, Demler E. Dynamical Cooper pairing in nonequilibrium electron-phonon systems. *Phys Rev B.* 2016; 94:214504.
11. Kennes DM, Wilner EY, Reichman DR, Millis AJ. Transient superconductivity from electronic squeezing of optically pumped phonons. *Nat Phys.* 2017; 13:479–483.
12. Kaiser S, et al. Optical properties of a vibrationally modulated solid state Mott insulator. *Sci Rep.* 2014; 4:3823. [PubMed: 24448171]
13. Singla R, et al. THz-Frequency Modulation of the Hubbard U in an Organic Mott Insulator. *Phys Rev Lett.* 2015; 115:187401. [PubMed: 26565494]
14. Pomarico E, et al. Enhanced electron-phonon coupling in graphene with periodically distorted lattice. *Phys Rev B.* 2017; 95:24304.
15. Nava A, Giannetti C, Georges A, Tosatti E, Fabrizio M. Cooling quasiparticles in A_3C_{60} fullerenes by excitonic mid-infrared absorption. *Nat Phys.* 2018; 14:154–159.
16. Degiorgi L, Briceno G, Fuhrer MS, Zettl A, Wachter P. Optical measurements of the superconducting gap in single-crystal K_3C_{60} and Rb_3C_{60} . *Nature.* 1994; 369:541–543.
17. Nomura Y, Sakai S, Capone M, Arita R. Unified understanding of superconductivity and Mott transition in alkali-doped fullerenes from first principles. *Sci Adv.* 2015; 1:e1500568. [PubMed: 26601242]
18. Capone M, Fabrizio M, Castellani C, Tosatti E. Strongly correlated superconductivity. *Science.* 2002; 296:2364–2366. [PubMed: 12089436]
19. Gunnarsson O. Superconductivity in fullerenes. *Rev Mod Phys.* 1997; 69:575–606.
20. Degiorgi L, et al. Optical properties of the alkali-metal-doped superconducting fullerenes: K_3C_{60} and Rb_3C_{60} . *Phys Rev B.* 1994; 49:7012–7025.
21. Lorenz B, Chu CW. High Pressure Effects on Superconductivity. *Frontiers in Superconducting Materials.* Springer-Verlag; 2004. 459–497.
22. Schilling JS. High-Pressure Effects. *Handbook of High-Temperature Superconductivity.* Springer; New York: 2006. 427–462.
23. Potočnik A, et al. Size and symmetry of the superconducting gap in the f.c.c. Cs_3C_{60} polymorph close to the metal-Mott insulator boundary. *Sci Rep.* 2015; 4:4265.
24. Zhou O, et al. Compressibility of M_3C_{60} Fullerene Superconductors: Relation Between T_c and Lattice Parameter. *Science.* 1992; 255:833–835. [PubMed: 17756430]
25. Oshiyama A, Saito S. Linear dependence of superconducting transition temperature on Fermi-level density-of-states in alkali-doped C_{60} . *Solid State Commun.* 1992; 82:41–45.

26. Ihara Y, et al. Spin dynamics at the Mott transition and in the metallic state of the Cs_3C_{60} superconducting phases. *EPL*. 2011; 94:37007.
27. Kim M, et al. Enhancing superconductivity in A_3C_{60} fullerenes. *Phys Rev B*. 2016; 94:155152.
28. Mazza G, Georges A. Nonequilibrium superconductivity in driven alkali-doped fullerenes. *Phys Rev B*. 2017; 96:1–10.
29. Stephens PW, et al. Structure of single-phase superconducting K_3C_{60} . *Nature*. 1991; 351:632–634.
30. Sporn G, et al. Pressure Dependence of Superconductivity in Single-Phase K_3C_{60} . *Science*. 1991; 252:1829–31. [PubMed: 17753258]

Figure 1. Structure, equilibrium phase transition, and transient light-induced phase of K_3C_{60} .

a. The f.c.c. crystal structure of K_3C_{60} (Ref. 29). The C_{60} molecules are represented by the green bonds connecting all the C atoms. The grey spheres are the K atoms, acting as spacers between neighbouring buckyballs. The equilibrium lattice constant is 14.26 Å at room temperature. **b.** C_{60} molecular distortion (blue) along the $T_{1u}(4)$ vibrational mode coordinates. The equilibrium structure is shown in red. **c.** Reflectivity (sample-diamond interface), real and imaginary optical conductivity - $R(\omega)$, $\sigma_1(\omega)$ and $\sigma_2(\omega)$ - across the equilibrium superconducting transition in K_3C_{60} . The red curves are measured at 25 K, in

the metallic phase. The blue curves refer to the equilibrium superconductor (10 K). **d.** Reflectivity (sample-diamond interface), real and imaginary optical conductivity - $R(\omega)$, $\sigma_1(\omega)$ and $\sigma_2(\omega)$ - of K_3C_{60} at equilibrium (red) and 1 ps after photo-excitation (blue) at $T = 100$ K. The light-blue curves show the data reported in Ref. 8, measured with a fluence of 1 mJ/cm^2 , while those in dark blue were measured with a broader probe spectrum and a higher pump fluence (3 mJ/cm^2).

a. **b.**

Figure 2. Equilibrium pressure dependence of superconducting K_3C_{60} .

a. Schematic representation of a diamond anvil cell (DAC) acting on the K_3C_{60} crystal structure. By applying external pressure, the inter-molecular distances get reduced. **b.** Superconducting transition temperature and calculated optical gap ($2\Delta_0/k_B T = 3.5223$), plotted as a function of lattice parameter and external pressure. Data adapted from Refs. 24, 30.

Figure 3. Pressure dependence of the transient optical properties of K_3C_{60} at $T = 100$ K. Reflectivity (sample-diamond interface) and complex optical conductivity of K_3C_{60} measured at equilibrium (red) and 1 ps after photoexcitation (blue) at $T = 100$ K, for different external hydrostatic pressures. All data were taken with the same pump fluence of 3 mJ/cm^2 .

Figure 4. Scaling of the $\sigma_1(\omega)$ gap with external pressure.

Photo-induced reduction in $\sigma_1(\omega)$ spectral weight, integrated between 6.5 and 12.9 meV, normalised by the equilibrium value (integrated in the same range). The blue shaded areas identify the regions in which a photo-induced conductivity gapping is measured. All data were taken with the same pump fluence (3 mJ/cm²). Vertical error bars represent uncertainties determined from different sets of measurements and horizontal error bars show the calibration uncertainty of the ruby fluorescence measurements used to determine the pressure (see Supplementary Information S3).

Figure 5. Pressure dependence of the extrapolated conductivity.

Blue diamonds are extrapolated zero-frequency conductivities extracted from Drude-Lorentz fits of the transient optical spectra, as a function of pressure and for three different temperatures: 100 K (a), 200 K (b), and 300 K (c). Red squares are the corresponding zero-frequency conductivities determined at equilibrium. The blue areas identify the regions in which σ_0 is suppressed by pressure ($d\sigma_0/dP < 0$) while those in yellow indicate the regime in which $d\sigma_0/dP > 0$. All data were taken with the same pump fluence (3 mJ/cm^2). The insets show a close-up of the low-pressure region. Vertical error bars reflect the fit uncertainty and horizontal error bars show the calibration uncertainty of the ruby fluorescence measurements used to determine the pressure (see Supplementary Information S3).

Figure 6. Out-of-equilibrium phase diagram of f.c.c. K_3C_{60} .

a. K_3C_{60} phase diagram (T vs room-temperature lattice constant and pressure). Green filled circles indicate the superconducting transition temperature (T_c) measured for different lattice parameters²⁴ at equilibrium. The light-blue filled area defines the equilibrium superconducting phase (SC). The dark blue shading stands for the Light-Induced Superconductor (**LI-SC**), which evolves into a High-Mobility Metal (**HMM**) under the application of pressure (red area). **b.** Extension of the f.c.c. A_3C_{60} phase diagram for larger lattice constants. PI, PM, and SC refer to the equilibrium paramagnetic insulating, paramagnetic metallic, and superconducting phase, respectively. Based on Ref. 17,31,32.