Published in final edited form as:

J Phys Chem Lett. 2018 August 16; 9(16): 4802–4807. doi:10.1021/acs.jpcllett.8b01738.

Aggregation and Solubility of a Model Conjugated Donor-Acceptor Polymer

Daniel R. Reid[†], Nicholas E. Jackson^{†,¶}, Alexander J. Bourque[‡], Chad R. Snyder[‡], Ronald L. Jones[‡], and Juan J. de Pablo[†]

[†]Institute for Molecular Engineering, University of Chicago, Chicago, IL

[‡]National Institute of Standards and Technology (NIST), Gaithersburg, MD

[¶]Institute for Molecular Engineering, Argonne National Laboratory, Lemont, IL

Abstract

In conjugated polymers, solution-phase structure and aggregation exert a strong influence on device morphology and performance, making understanding solubility crucial for rational design. Using atomistic molecular dynamics (MD) and free energy sampling algorithms, we examine the aggregation and solubility of the polymer PTB7, studying how side-chain structure can be modified to control aggregation. We demonstrate that free energy sampling can be used to effectively screen polymer solubility in a variety of solvents, but that solubility parameters derived from MD are not predictive. We then study the aggregation of variants of PTB7 including those with linear (octyl), branched (2-ethylhexyl), and cleaved (methyl) side-chains, in a selection of explicit solvents and additives. Energetic analysis demonstrates that while side-chains do disrupt polymer backbone stacking, solvent exclusion is a critical factor controlling polymer solubility.

Graphical Abstract

In thin-film organic semiconductors, specifically bulk-heterojunction organic photovoltaic (OPV) cells,^{1,2} the film morphology is exceedingly complex.³ The inability to control morphologies of organic semiconductors (OSC) is perceived as a limiting step in the successful commercialization of these materials.⁴ While some OSC exhibit glass transition temperatures (T_g) below room temperature,⁵ many have T_g 's significantly above 298 K^{6–8} and exist in kinetically trapped, glassy morphologies. As solution-deposition is the most common processing route for many OSC, solution-phase conformations may be kinetically trapped into the deposited film morphology.

Evidence has emerged indicating that solution-phase polymer conformations influence the morphologies of thin-films,^{9–19} with increases in OSC performance obtained via solution-deposition at high temperatures²⁰ or in poor solvents.^{21–23} These results are supported by fundamental studies demonstrating solution-phase aggregation of conjugated polymers even in solvents considered “good” in the traditional Flory definition.²⁴ Indeed, even for short oligomeric chains, optical studies have revealed the occurrence of single-chain folding in oligomers above a critical molecular mass;^{25,26} in test systems, the enthalpic contributions to similar processes have been quantified.²⁷ Side-chain engineering has proven a powerful avenue for manipulating solubilities of conjugated polymers, with branched alkylic side-chains often improving solubility relative to that of chemically equivalent linear side-chains.²⁸

Molecular modeling is used here to shed light on the solution-phase conformations of conjugated polymers. While experimental methods can be applied to assess general aggregation trends,^{29–31} molecular simulations can reveal the atomistic structure of aggregates that give rise to complex optoelectronic phenomena. We emphasize that in recent studies, atomistic^{32–37} and coarse-grained^{38–40} simulations have broached the topic of solution-phase conformations of conjugated polymers. However, an understanding of the thermodynamic contributions to conjugated polymer solubility is still lacking.

In this letter we examine the conformations and solubilities of the polymer PTB7 in explicit solvents, and determine the mechanisms by which side-chain structure influences thermodynamics. To assess solubility, we determine the free energy change upon aggregation of pairs of PTB7 oligomers. We validate this approach by comparing free energies to experimental solubilities and find qualitative agreement for a series of common solvents. Model results are also validated against experimental persistence lengths and simulations of 10 repeat unit oligomers. We then study the solubility of three side-chain variants of PTB7: branched (2-ethylhexyl), linear (octyl), and cleaved (methyl), finding that side-chains disrupt the stacking of conjugated polymer backbones, and in the case of branched side-chains, enhance solubility. However, the enhanced solubility is not directly related to the disrupted backbone structure, but rather the destabilization of the solvent associated with the more disordered, bulky structure, similar to mechanisms found previously.⁴¹ These results provide both an experimentally-validated framework for screening conjugated polymer solubility and a means of understanding the structural origin of solubility in conjugated materials.

Three common solvents/additives are studied: chlorobenzene (CB), chloronaphthalene (CN), and diiodooctane (DIO). The details of our simulation procedure are described in the Methods and Supporting Information. To summarize: Pairs of PTB7 aggregated oligomers are solvated. Dimers of PTB7 are used for branched and linear side-chains, and tetramers for cleaved side-chains; these degrees of polymerization ensure that the aggregate shows an aligned and stacked structure, as would be seen in a larger polymer. Steered molecular dynamics (MD) is performed to generate initial configurations for free energy sampling, which is performed using replica exchange umbrella sampling, measuring the free energy with respect to the center-of-mass (COM) separation of the two conjugated PTB7 backbones.

Calculated free energies of aggregation (ΔA) are shown in Figure 1, where r is the COM separation, n is the degree of polymerization, and L_c is the PTB7 oligomer contour length. Free-energies are normalized by the degree of polymerization (n). PTB7 in CB and CN shows a shallow free energy basin with a minimum of ≈ -8.4 kJ/mol- n , whereas in DIO it exhibits a deeper basin of ≈ -25.1 kJ/mol- n . The deeper free energy basin in DIO indicates that DIO is a worse solvent than both CB and CN. Note that experimentally DIO is never used alone as a solvent, but in our simulations we do so to magnify its effect on PTB7's solubility and avoid complications in the analysis that might arise from a ternary system (e.g. PTB7/CB/DIO) system at small box sizes. Experimentally determined solubilities for PTB7 in CB, CN, and DIO are (>75 , >75 and <0.1) mg/mL, respectively. It was not feasible to determine exact solubilities, and solutions with high concentrations of PTB7 were opaque and gel-like. Despite this, experiments clearly differentiate between good and poor solvents, and simulations are in agreement. The two free-energy minima of Figure 1 present at $r/L_c \approx 0.5$ and $r/L_c \approx 0.05$ correspond to the dimers having one or both, respectively, of their monomers stacked with the other dimer. This suggests that PTB7 (dis)aggregates via a sliding process, rather than a rotationally isotropic approach. Visual examination of trajectories as shown in Supporting Information supports this hypothesis.

To validate that the previous dimer aggregation simulations capture simulated polymer solubilities more broadly, we also perform MD simulations of single PTB7 10-mers in CB, CN, and DIO. Single PTB7 10-mer chains are initialized in a self-aggregated (folded) state and are run for 100 ns at 300 K to observe the stability of the self-aggregated state. Three replicates are run for each solvent. All 10-mer aggregation results are presented in the Supporting Information. 10-mers disaggregate in good solvents and remain self-aggregated in poor solvents. The 10-mers in CB disaggregate at 4 ns, 10 ns, and 53 ns. Two of three 10-mers in CN disaggregated at 13 ns and 40 ns, while the third remains self-aggregated. All 10-mers in DIO remain self-aggregated. These results are consistent with solubility trends from dimer simulations. From configurations which disaggregate, persistence lengths of PTB7 are calculated to be 4.3 nm and 4.1 nm in CB and CN, respectively, which are in good agreement with previous computational results.³³ Persistence lengths were estimated using the computed bond-bond correlation function and a simple worm-like chain model⁴² defined by

$$\langle t_i \cdot t_{i+s} \rangle = e^{-\frac{s \cdot l}{L_p}} \quad (1)$$

where t_i is the bond vector for PTB7 monomer i , l is the length of a PTB7 monomer, and L_p is the persistence length. To further validate the computational model, small angle neutron scattering measurements were performed on low molar mass PTB7 (≈ 35 kg/mol) in d^5 -CB. From these measurements, the persistence length was determined via a flexible cylinder model to be (5 ± 1) nm at 298 K, which is in agreement with our calculated value, particularly since the persistence length is expected to be larger for higher molar masses (see Supporting Information for details on the measurements and fit). These results suggest that dimers capture the relevant polymer behavior to predict solubilities.

Solubility parameters derived from MD simulations are also determined, as explained in the Supporting Information; however, they fail to capture experimental solubility trends. Having established the accuracy of our free energy calculations, we examine the mechanisms by which PTB7 side-chains influence solubility and aggregation. Simulations of PTB7 are performed in explicit CB solvent with three different types of side-chains: branched, linear, and cleaved. The branched and linear variants are chosen to conserve carbon atoms (2-ethylhexyl/octyl). Representative snapshots of the polymer architectures are shown in Figure 2.

The free energies of aggregation for the PTB7 side-chain variants are shown in Figure 3 a). The free energy minima suggest that PTB7 with linear and cleaved side-chains also aggregate via a sliding mechanism. Branched side-chain PTB7 is more soluble than linear side-chain PTB7, as demonstrated by the 8.4 kJ/mol-n difference in the depth of the free energy basin. This solubility trend is commonly observed in experiments,²⁸ accounting for the proliferation of polymer architectures with branched side-chains. Curiously, cleaved side-chain PTB7 shows a free energy basin very similar to that of the linear side-chain variant. This goes against the intuition that the addition of side-chains reliably increases solubility.

To quantify how side-chain architecture influences solubility, the free energies of aggregation are decomposed into enthalpic and entropic contributions in Figure 3 b) and c), respectively. The linear side-chain variant is the most enthalpically stable, and also exhibits the lowest entropy, suggesting an ordered aggregate, which is corroborated by Figure 2 b). The branched side-chain variant differs, showing the highest enthalpy and the second lowest entropy. The cleaved side-chain variant, on the other hand, shows the highest entropy. This is likely due to the side-chain degrees of freedom being constrained upon aggregation, which does not occur in the cleaved side-chain case. The backbone stacking energy for the three side-chain variants suggests that this entropic difference is not due to backbone stacking disorder ($U = -88$ kJ/mol-n vs $(-58$ and $-71)$ kJ/mol-n for branched and linear, respectively).

Entropic contributions can be attributed to backbone and side-chain disorder, however enthalpic contributions require more study. Figure 4 a) partitions U into polymer-polymer interactions shown in solid lines and solvent interactions shown in dashed lines. The negative of the solvent interaction energy is shown. The variant without side-chains shows the smallest U for both types of interactions, as it has the fewest atoms. Interestingly, U of polymer-polymer interactions is strongest for branched side-chain PTB7, despite showing the highest system U . Two features must be explored: first, why does PTB7 with branched side-chains exhibit the strongest enthalpic interactions, and second, how do these stable branched side-chain aggregates lead to a less stable system overall?

The favorable polymer-polymer interactions are not explained by enhanced backbone stacking interactions. Backbone-backbone stacking interactions are calculated as the pairwise interactions between atoms in the thienothiophene and benzodithiophene units. Figure 4 b) shows backbone-backbone energies for the three PTB7 variants, demonstrating that cleaved, linear, and branched side-chains destabilize aggregates from least to greatest, respectively. These backbone energies do not correlate with polymer-polymer energy (Figure 4 a)), suggesting that while side-chains disrupt π -stacking, this disruption is not directly responsible for the change in solubility.

Figure 4 c) demonstrates that the enhanced stabilization of dimers with branched side-chains originates from increased side-chain-backbone interactions. With the backbone stacking disrupted, the branched architecture of the side-chain can associate freely with the backbone, resulting in strong polymer-polymer interactions within the dimer aggregate.

We now examine the role of solvent interaction energies in Figure 4 d). Solid lines depict the U of polymer-solvent interaction energy, and dashed lines the U of solvent-solvent interaction energy. The data show that aggregates with branched side-chains interact least favorably with the solvent, despite having the same number of atoms as the linear side-chains. This energetic contribution is largely responsible for destabilizing the system of aggregated PTB7 with branched side-chains. This result suggests that the more disordered aggregation motifs caused by the branched side-chain structures create a less favorable interaction surface for the solvent, which plays a crucial role in determining the solubility of the aggregate. In the Supporting Information it is verified that the absolute, in addition to relative, energies of oligomer-solvent interaction support this idea.

Taken together, these results unveil the intricate behavior of solubility in conjugated polymers. While dogma has held that branched side-chains increase solubility by disrupting backbone stacking, we propose a more subtle picture. While side-chains do disrupt backbone stacking, this does not directly lead to increased solubility. In fact, branched side-chain PTB7 is more stable than linear side-chain PTB7 in the absence of solvent. Rather, the side-chains' effect on solvent interactions dominate the enthalpic contribution to the free energy of aggregation. Entropic contributions can be understood through the lens of side-chain-induced disorder, however these interactions are relatively small compared to the enthalpic contributions. To design materials with higher solubility, we suggest that new designs should include side-chains that maximize polymer disorder to the extent that it disrupts solvent structure. Finally, it is important to emphasize that, even in the solution-phase, side-chain induced aggregation may be under kinetic control. While the calculations performed here shed light on the thermodynamics of this process, future work exploring the kinetics of conjugated polymer aggregation will be critical to further controlling film morphologies. Moving forward, it will be of interest to explore the approaches introduced here to investigate the role of structure or chemical modifications, such as side chains, in aggregation and ultimately the performance of materials.^{43,44}

Methods

Simulations utilize the opls-aa force-field for explicit solvent,⁴⁵ and an opls-style atomistic force-field for PTB7 recently parameterized in the literature.³² This parameterization utilizes opls-aa Lennard Jones parameters that reproduce high-accuracy quantum-chemistry simulations of π -stacking energies to within ~ 1 kcal/mol, and has been validated on a set of experimental thermophysical properties of PTB7.³³ Simulations employ the graphics processing unit (GPU) code DASH.⁴⁶ A Lennard Jones interaction cutoff of 1 nm was used for all simulations. Coulombic interactions in the solubility parameter simulations used the damped shifted force with a cutoff of 1.2 nm. Coulombic interactions in the free-energy simulations used a short-range cutoff of 1.2 nm and the particle-particle-particle-mesh formalism for long-range interactions. The Nose-Hoover thermostat was used, with a time constant of 200 fs. Details of the free energy sampling are given in Supplementary Information.

Experimental Solubilities

Saturated solutions were prepared by mixing an excess of PTB7 with a small volume of each test solvent, (200 to 300) μL , and stirring for 24 h at room temperature. The saturate was filtered from the solution using a 0.45 μm PTFE filter and diluted in ortho-dichlorobenzene (oDCB) to achieve an optical density suitable for ultraviolet-visible (UV-Vis) absorption measurement. Measurements were performed at room temperature using a PerkinElmer Lambda 950 UV/Vis spectrometer.⁴⁷ Absorbance was compared to a set of standard curves with known concentrations of PTB7 in oDCB.

Measurement of Persistence Length

Small angle neutron scattering (SANS) measurements were performed at the National Institute of Standards and Technology (NIST) Center for Neutron Research (NCNR) on the

NG7 SANS instrument, and data were reduced and fit to a flexible cylinder model using software described elsewhere.^{48,49} Detailed information is provided in the Supporting Information.

Supplementary Material

Refer to Web version on PubMed Central for supplementary material.

Acknowledgement

This work is supported by NIST through the Center for Hierarchical Materials Design (CHi-MaD). All the simulations presented in this work were carried out with the DASH code, whose development is supported by the Department of Energy, Basic Energy Sciences, Materials Science and Engineering Division, through the Midwest Integrated Center for Computational Materials (MICCOM). N.E.J. thanks Argonne National Laboratory for funding from the Maria Goeppert Mayer Named Fellowship.

References

- (1). Dou L; You J; Hong Z; Xu Z; Li G; Street RA; Yang Y 25th Anniversary Article: A Decade of Organic/Polymeric Photovoltaic Research. *Adv. Mater* 2013, 25, 6642–6671. [PubMed: 24105687]
- (2). Heeger AJ 25th Anniversary Article: Bulk Heterojunction Solar Cells: Understanding the Mechanism of Operation. *Adv. Mater* 2014, 26, 10–27. [PubMed: 24311015]
- (3). Rivnay J; Mannsfeld SC; Miller CE; Salleo A; Toney MF Quantitative Determination of Organic Semiconductor Microstructure from the Molecular to Device Scale. *Chem. Rev* 2012, 112, 5488–5519. [PubMed: 22877516]
- (4). Jackson NE; Savoie BM; Marks TJ; Chen LX; Ratner MA The Next Breakthrough for Organic Photovoltaics? *J. Phys. Chem. Lett* 2015, 6, 77–84. [PubMed: 26263095]
- (5). Zhao J; Swinnen A; Assche GV; Manca J; Vanderzande D; Mele BV Phase Diagram of P3HT / PCBM Blends and Its Implication for the Stability of Morphology. *J. Phys. Chem. B* 2009, 113, 1587–1591. [PubMed: 19159197]
- (6). Liu J; Guo T.-f.; Yang Y Effects of Thermal Annealing on the Performance of Polymer Light Emitting Diodes. *J. Appl. Phys* 2002, 91, 1595–1600.
- (7). Kroon R; Gehlhaar R; Steckler TT; Henriksson P; Christian M; Bergqvist J; Hadipour A; Heremans P; Andersson MR Solar Energy Materials & Solar Cells New Quinoxaline and Pyridopyrazine-Based Polymers for Solution-Processable Photo-voltaics. *Sol. Energy Mater. Sol. Cells* 2012, 105, 280–286.
- (8). Chu T.-y.; Lu J; Beaupré S; Zhang Y; Pouliot J.-r.; Zhou J; Najari A; Leclerc M; Tao Y Effects of the Molecular Weight and the Side-Chain Length on the Photovoltaic Performance of Dithienosilole / Thienopyrrolodione Copolymers. *Adv. Funct. Mater* 2012, 22, 2345–2351.
- (9). Bartelt JA; Douglas JD; Mateker WR; Labban AE; Tasone CJ; Toney MF; Frechet JM; Beaujuge PM; McGehee MD Controlling Solution-Phase Polymer Aggregation with Molecular Weight and Solvent Additives to Optimize Polymer-Fullerene Bulk Heterojunction Solar Cells. *Adv. Energy Mater* 2014, 4, 1–11. [PubMed: 26190956]
- (10). Steyrleuthner R; Schubert M; Howard I; Klaumu B; Schilling K; Chen Z; Saal-frank P Aggregation in a High-Mobility n-type, Type Low-Bandgap Copolymer with Implications on Semicrystalline Morphology. *J. Am. Chem. Soc* 2012, 134, 18303–18317. [PubMed: 22957688]
- (11). Zheng Y-Q; Yao Z-F; Lei T; Dou J-H; Yang C-Y; Zou L; Meng X; Ma W; Wang J-Y; Pei J Understanding the Solution-State Supramolecular Structure of Donor-Acceptor Polymers and their Influence on Solid-State Morphology and Charge-Transport Properties. *Adv. Mater* 2017, 29, 1701072.
- (12). Nguyen T-Q; Yee R; Schwartz B Solution Processing of Conjugated Polymers: The Effects of Polymer Solubility on the Morphology and Electronic Properties of Semiconducting Polymer Films. *J. Photochem. Photobiol* 2001, 144, 21–30.

- (13). Nguyen T-Q; Doan V; Schwartz B Conjugated Polymer Aggregates in Solution: Control of Interchain Interactions. *J. Chem. Phys* 1999, 110, 4068–4078.
- (14). Zhao L-H; Ping R-Q; Zhuo J-M; Wong L-Y; Tang J-C; Su Y-S; Chua L-L Role of Borderline Solvents to Induce Pronounced Extended-Chain Lamellar Order in π -Stackable Polymers. *Macromolecules* 2011, 44, 9692–9702.
- (15). Huang Y; Cheng H; Han CC Temperature Induced Structure Evolution of Regioregular Poly(3-hexylthiophene) in Dilute Solution and its Influence on Thin Film Morphology. *Macromolecules* 2010, 43, 10031–10037.
- (16). Diao Y; Shaw L; Bao Z; Mannsfeld SC Morphology Control Strategies for Solution-Processed Organic Semiconductor Thin Films. *Energy Environ. Sci* 2014, 7, 2145–2159.
- (17). Cheng P; Yan C; Li Y; Ma W; Zhan X Diluting Concentrated Solution: A General, Simple and Effective Approach to Enhance Efficiency of Polymer Solar Cells. *Energy Environ. Sci* 2015, 8, 2357–2364.
- (18). Eder T; Stangl T; Gmelch M; Remmerssen K; Laux D; Hoger S; Lupton JM; Vogelsang J Switching Between H- and J-Type Electronic Coupling in Single Conjugated Polymer Aggregates. *Nat. Commun* 2018, 8, 1641.
- (19). Wang S; Fabiano S; Himmelberger S; Puzinas S; Crispin X; Salleo A; Berggren M Experimental Evidence That Short-Range Intermolecular Aggregation is Sufficient for Efficient Charge Transport in Conjugated Polymers. *Proc. Natl. Acad. Sci. U.S.A* 2015, 112, 10599–10604. [PubMed: 26261305]
- (20). Liu Y; Zhao J; Li Z; Mu C; Ma W; Hu H; Jiang K; Lin H; Ade H; Yan H Multiple Cases of High-Efficiency Polymer Solar Cells. *Nat. Commun* 2014, 5, 1–8.
- (21). Park YD; Park JK; Seo JH; Yuen JD; Lee WH; Cho K; Bazan GC Solubility-Controlled Structural Ordering of Narrow Bandgap Conjugated Polymers. *Adv. Energy Mater* 2010, 1, 63–67.
- (22). Chen MS; Lee OP; Niskala JR; Yiu AT; Tassone CJ; Schmidt K; Beau-juge PM; Onishi SS; Toney MF; Zettl A; et al., Enhanced Solid-State Order and Field-Effect Hole Mobility through Control of Nanoscale Polymer Aggregation. *J. Am. Chem. Soc* 2013, 135, 19229–19236. [PubMed: 24295228]
- (23). Luzio A; Criante L; Caironi M Control of Charge Transport in a Semiconducting Copolymer by Solvent-Induced Long-Range Order. *Sci. Rep* 2013, 3, 1–6.
- (24). Wang D; Yuan Y; Mardiyati Y; Bubeck C; Koynov K From Single Chains to Aggregates, How Conjugated Polymers Behave in Dilute Solutions. *Macromolecules* 2013, 46, 6217–6224.
- (25). Fauvell TJ; Zheng T; Jackson NE; Ratner MA; Yu L; Chen LX Photo-physical and Morphological Implications of Single-Strand Conjugated Polymer Folding in Solution. *Chem. Mater* 2016, 28, 2814–2822.
- (26). Hu Z; Liu J; Simon-Bower L; Zhai L; Gesquiere AJ Influence of Backbone Rigidity on Single Chain Conformation of Thiophene-Based Conjugated Polymers. *J. Phys. Chem. B* 2012, 117, 4461–4467.
- (27). Traub MC; Dubay KH; Ingle SE; Zhu X; Plunkett KN; Reichman DR; Bout DAV Chromophore-Controlled Self-Assembly of Highly Ordered Polymer Nanostructures. *J. Phys. Chem. Lett* 2013, 4, 2520–2524.
- (28). Mei J; Bao Z Side Chain Engineering in Solution-Processable Conjugated Polymers. *Chem. Mater* 2014, 26, 604–615.
- (29). McCulloch B; Ho V; Hoarfrost M; Stanely C; Do C; Heller WT; Segalman RA Polymer Chain Shape of Poly(3-alkylthiophenes) in Solution Using Small-Angle Neutron Scattering. *Macromolecules* 2013, 46, 1899–1907.
- (30). Aime J; Bargain F; Schott M; Eckhardt H; Miller G; Elsenbaumer R Structural Study of Doped and Undoped Polythiophene in Solution by Small-Angle Neutron Scattering. *Phys. Rev. Lett* 1989, 62. [PubMed: 10040433]
- (31). Kuei B; Gomez ED Chain Conformations and Phase Behavior of Conjugated Polymers. *Soft Matter* 2017, 13. [PubMed: 28124764]

- (32). Jackson NE; Kohlstedt KL; Savoie BM; de la Cruz MO; Schatz GC; Chen LX; Ratner MA Conformational Order in Aggregates of Conjugated Polymers. *J. Am. Chem. Soc* 2015, 137, 6254–6262. [PubMed: 25920989]
- (33). Root SE; Jackson NE; Savagatrup S; Arya G; Lipomi DJ Modelling the Morphology and Thermomechanical Behaviour of Low-Bandgap Conjugated Polymers and Bulk Heterojunction Films. *Energy Environ. Sci* 2017, 10, 558–569.
- (34). Lee CK; Hua CC; Chen SA Hybrid Solvents Incubated pi-pi Stacking in Quenched Conjugated Polymer Resolved by Multiscale Computation. *Macromolecules* 2011, 44, 320–324.
- (35). Hu Z; Adachi T; Lee Y-G; Haws RT; Hanson B; Ono RJ; Biewlawski C; Ganesan V; Rossky PJ; et al., Effect of the Side-Chain-Distribution Density on the Single-Conjugated-Polymer-Chain Conformation. *Chem. Phys. Chem* 2015, 14, 4143–4148.
- (36). Lee FL; Farimani AB; Gu KL; Yan H; Toney MF; Bao Z; Pande VS Solution-Phase Conformation and Dynamics of Conjugated Isoindigo-Based Donor-Acceptor Polymer Single Chains. *J. Phys. Chem. Lett* 2017, 8, 5479–5486. [PubMed: 29065685]
- (37). Yi HL; Wu CH; Wang CI; Hua CC Solvent-Regulated Mesoscale Aggregation Properties of Dilute PBTTC-C14 Solutions. *Macromolecules* 2017, 50, 5498–5509.
- (38). Hu D; Yu J; Wong K; Bagchi B; Rossky PJ; Barbara PF Collapse of Stiff Conjugated Polymers with Chemical Defects Into Ordered, Cylindrical Conformations. *Nature* 2000, 405, 4143–4148.
- (39). Lee CK; Hua CC; Chen SA An Ellipsoid-Chain Model for Conjugated Polymer Solutions. *J. Chem. Phys* 2012, 136, 084901. [PubMed: 22380060]
- (40). Shie SC; Lee CK; Hua CC; Chen SA A Predictive Coarse-Grained Model for Semiflexible Polymers in Specific Solvents. *Macromol. Theory Simul* 2012, 19, 179–189.
- (41). Peerless JS; Bowers GH; Kwansa AL; Yingling YG Fullerenes in Aromatic Solvents: Correlation Between Solvation-Shell Structure, Solvate Formation, and Solubility. *J. Phys. Chem. B* 2015, 119, 15344–15352. [PubMed: 26560403]
- (42). Doi M; Edwards SF *The Theory of Polymer Dynamics*; Oxford University Press, 1988; Vol. 73.
- (43). Zou Y; Wu Y; Yang H; Dong Y; Cui C; Li Y The effect of alkylthio side chains in oligothiophene-based donor materials for organic solar cells. *Mol. Syst. Des. Eng* 2018, 131–141.
- (44). Huang W; Li M; Lin F; Wu Y; Ke Z; Zhang X; Ma R; Yang T; Ma W; Liang Y Rational design of conjugated side chains for high-performance all-polymer solar cells. *Mol. Syst. Des. Eng* 2018, 103–112.
- (45). Jorgensen WL; Maxwell DS; Tirado-Rives J Development and Testing of the OLPS All-Atom Force Field on Conformational Energetics and Properties of Organic Liquids. *J. Am. Chem. Soc* 1996, 118, 11225–11236.
- (46). DASH. https://github.com/MICCoM/DASH_public.
- (47). Certain commercial equipment, instruments, or materials are identified in this paper in order to specify the experimental procedure adequately. Such identification is not intended to imply recommendation or endorsement by the National Institute of Standards and Technology, nor is it intended to imply that the materials or equipment identified are necessarily the best available for the purpose.
- (48). Kline S Reduction and Analysis of SANS and USANS Data Using IGOR Pro. *J. Appl. Crystallogr* 2006, 39, 895–900.
- (49). This work benefited from the use of the Sas View application, originally developed under NSF award DMR-0520547. Sas View contains code developed with funding from the European Union's Horizon 2020 research and innovation programme under the SINE2020 project, grant agreement No 654000. <http://www.sasview.org/>

Figure 1:

Free-energy vs COM separation of two PTB7 oligomers with 2-ethylhexyl side-chains in CB, CN, and DIO. Free-energy is normalized by the degree of polymerization (n) and the COM separation (r) by oligomer contour length (L_c). Poor solvents yield more stable aggregated states, corresponding to low values of ΔA at $r/L_c \approx 0.95$. 95 % confidence intervals are shown.

Figure 2:

Representative configurations of PTB7 aggregates with (a) branched (2-ethylhexyl), (b) linear (octyl), and (c) cleaved (methyl) side-chains. The aggregate with branched side-chains is poorly stacked while that with linear or cleaved side-chains is well-stacked. These behaviors are quantified through average backbone stacking energies of $U = (-58, -71, \text{ and } -88) \text{ kJ/mol-n}$ for a), b), and c), respectively.

Figure 3:

a) Free energy b) potential energy and c) entropy vs scaled COM separation r/L_c of two PTB7 oligomers with three variants of side-chains in explicit CB solvent. All energies are normalized by the degree of polymerization (n). 95 % confidence intervals are shown.

Figure 4:

Potential energy (U) contributions of the three PTB7 variants. For all panels, blue, green and red data sets refer to branched, linear, and cleaved side-chain structures. a) U of polymer-polymer interactions (solid lines) and the *negative* sum of solvent-polymer and solvent-solvent interactions (dashed lines). The difference between these two is the total U of the system. b) U of interactions between PTB7 backbones. Results indicate that side-chains disrupt backbone stacking. c) U of side-chain-backbone (solid lines) and side-chain-side-chain (dashed lines) interactions. d) U of polymer-solvent (solid lines) and solvent-solvent (dashed lines) interactions. 95 % confidence intervals are shown.